

1 INK-JET PRINTING CLOTH, INK-JET PRINTING PROCESS
AND PRODUCTION PROCESS OF PRINT

BACKGROUND OF THE INVENTION

5 Field of the Invention

The present invention relates to an ink-jet printing cloth, an ink-jet printing process and a production process of a print.

10 Related Background Art

Besides screen printing and roller printing, ink-jet printing has heretofore been known as a process of printing on cloth formed of cotton, silk, polyester or the like. This ink-jet printing is conducted by means of an ink-jet printing apparatus obtained by improving an image-forming apparatus of an ink-jet system for forming images on recording media such as plastics and recording paper so as to be fitted for textile printing and the kind of a cloth to be used.

20 The ink-jet system is one of non-impact printing systems, which ejects an ink or the like to directly apply the ink to cloth or the like and is little in noise. A textile printing apparatus equipped with a printing head of the ink-jet system permits high-density printing operation at high speed. Therefore, the textile printing processes using a plate such as a screen or a design roller are unfit for multi-kind small-quantity production,

25



1 whereas the ink-jet textile printing process is a system
making no use of any plate, and permits the multi-kind
small-quantity production in a short period of time
because data for printing can be formed with ease by a
5 host system or the like.

The textile printing apparatus of the ink-jet system
is generally equipped with a carriage mounting a printing
means (printing head) thereon, a feeding means for feeding
a cloth and control means for controlling these means.

10 The printing head by which ink droplets are ejected
through a plurality of ejection orifices is serially
scanned in a direction (a main scanning direction)
perpendicular to the feeding direction (a secondary
scanning direction) of the cloth. On the other hand, the
15 cloth is intermittently fed by a predetermined length at
the time printing is stopped. According to this printing
process, inks are ejected on the cloth according to
printing signals to conduct printing. Therefore, The ink-
jet printing process attracts attention as a printing
20 method which is low in running cost and silent. When a
printing head in which a plurality of ink-ejecting nozzles
has been aligned in the secondary scanning direction is
used, printing of a width corresponding to the number of
the nozzles can be performed every time the printing head
25 is scanned once on the cloth.


In the case of color textile printing, a color image
is formed by overlapping ink droplets of plural colors



1 ejected from respective printing heads each other. In
general, the color printing requires three or four
printing heads and ink tanks corresponding to 3 primary
colors of yellow (Y), magenta (M) and cyan (C) or 4 colors
5 including black (B) in addition to these primary colors.

Since such devices are used, the techniques required
of the ink-jet printing are greatly different from those
of the screen and roller printing. This is caused by such
differences in system as the optimum value of viscosity
10 among properties of inks used in the ink-jet printing is
greatly different from that of textile printing inks used
in screen printing or the like and is low, the ink-jet
printing requires to take steps as to reliability such as
clogging of a head, so-called additive color process, in
15 which a few inks of different colors are shot on the same
position so as to overlap each other, is conducted, and
dots of inks are very small.

Various investigations have thus been attempted as
to methods of such ink-jet printing. For example,
20 Japanese Patent Publication No. 63-31594 discloses a
method in which textile printing is conducted on a cloth
containing a water-soluble polymer, a water-soluble salt
and water-insoluble inorganic fine particles, and Japanese
Patent Publication No. 63-31593 discloses a textile
25 printing method in which inks each having a viscosity of
200 cP or lower and a surface tension of 30 to 70 dyn/cm
are used, and a cloth having a water repellency of 50



1 points or more as measured in accordance with JIS L 1079
is employed.

Since the prior art printing methods described above
are based on thinking that the penetration of inks into
5 the interior of fiber is prevented to prevent the
diffusion of dyes, thereby improving coloring, the
improvement in coloring is recognized to some extent.
However, they involve problems such as (1) it takes a long
time to dry the inks, (2) no strike-through occurs because
10 the inks do not spread, and (3) an area factor becomes
small because the inks do not spread, and so coloring
ability is limited.

On the other hand, for example, Japanese Patent
Application Laid-Open No. 4-59282 discloses an ink-jet
15 printing cloth obtained by incorporating 0.1 to 3 % by
weight of a surfactant into a cloth formed of a
hydrophilic fiber material. According to the cloth
subjected to such a treatment, inks are absorbed in the
interior of fiber by diffusion, and so tendency to strike-
20 through is enhanced. However, such a cloth is unfavorable
to improvement in coloring ability because dyes penetrate
into the interior of the fiber.

As described above, the prior art techniques have
been able to satisfy individual performance
25 characteristics required of the ink-jet printing process
for obtaining excellent prints to some extent, but has
been unable to satisfy all the performance characteristics



1 at the same time.

SUMMARY OF THE INVENTION

5 It is therefore an object of the present invention to provide an ink-jet printing cloth and an ink-jet printing process, which can provide bright prints excellent in drying property, free of bleeding and high in color depth, image quality and grade, and a production process of prints excellent in properties.

10 The above object can be achieved by the present invention described below.

According to the present invention, there is thus provided an ink-jet printing cloth on which textile printing is conducted using an ink-jet system, wherein the
15 cloth contains a water repellent and a hydrophilic agent so as to have a predetermined water repellency.

According to the present invention, there is also provided a process for producing an ink-jet printing cloth on which textile printing is conducted using an ink-jet
20 system, which comprises the steps of:

applying a water repellent to a cloth;
drying the cloth; and
further applying a hydrophilic agent to the dry cloth.

25 According to the present invention, there is further provided an ink-jet printing process comprising ejecting inks by an ink-jet system to print a cloth, wherein a

1 cloth containing a water repellent and a hydrophilic agent
and having a predetermined water repellency is used as
said cloth.

According to the present invention, there is still
5 further provided a process for producing a print by
applying inks to a cloth using an ink-jet system to print
the cloth, which comprises the steps of:

applying inks to a cloth containing a water
repellent and a hydrophilic agent and having a
10 predetermined water repellency;

fixing dyes in the inks to the cloth; and
washing the thus-treated cloth.

BRIEF DESCRIPTION OF THE DRAWINGS


15 Fig. 1A is a typical sectional side elevation
schematically illustrating the constitution of an ink-jet
printing apparatus to which the present invention is
applied.

Fig. 1B is an enlarged view of a portion of a
20 conveyor belt in Fig. 1A.

Fig. 2 is a perspective view typically illustrating
a printer section and a feed section in the apparatus
shown in Fig. 1A.

Fig. 3 is a typical perspective view of an ink-
25 feeding system in the apparatus shown in Fig. 1A.

Fig. 4 is a perspective view schematically
illustrating the constitution of a printing head to be



1 mounted on the apparatus shown in Fig. 1A.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

5 According to the ink-jet printing cloth and printing process based on the present invention, prints excellent in drying property, coloring ability and resistance to bleeding can be provided.

10 According to the ink-jet printing cloth according to the present invention, inks do not very penetrate into the interior of fiber owing to the water repellent contained therein, and so dyes do not diffuse, resulting in improvement in coloring. The hydrophilic agent simultaneously contained in the cloth moderately prevents the inks from being repelled by the water repellent. More
15 specifically, the inks used have affinity for the hydrophilic agent, and are hence absorbed in the cloth to some extent and also laterally spread.

Therefore, since the cloth according to the present invention also becomes excellent in drying property and
20 great in area factor, it is also excellent in coloring ability. The term "area factor" means a proportion of dots occupied in a unit area. When the permeability (water repellency) of the cloth is preset to a value less than 50 points by uniformly containing the water repellent
25 and the hydrophilic agent in a certain proportion in the cloth, scattering of hydrophilicity of fiber itself due to density, directional property, irregularities, impurities



1 and the like can be lessened, and so uneven spread
(bleeding) of inks can be prevented.

The preferred embodiments of the present invention
will then be described to explain the present invention in
5 more detail.

No particular limitation is imposed on the fiber
material for the ink-jet printing cloth according to the
present invention. Examples thereof include various fiber
materials such as cotton, silk, wool, nylon, polyester,
10 rayon and acrylic fibers. The cloth used may be a blended
fabric or union cloth thereof.

The water repellency in the present invention has
been measured by using, as a measuring means, the water
repellency test (spray method) described in JIS L 1092.

15 No particular limitation is imposed on the water
repellent useful in the practice of the present invention
so far as it has the ability to repel water which is a
main component of inks. However, examples thereof include
paraffins, fluorine-containing compounds, pyridinium
20 salts, N-methylolalkylamides, alkylethyleneureas,
oxazoline derivatives, silicone compounds, triazine
compounds, zirconium compounds and mixtures thereof. Of
these, paraffinic and fluorine-containing type water
repellents are particularly preferred from the viewpoints
25 of easy adjustment of water repellency, prevention of
bleeding and concentration.

The amount of the water repellent to be applied is



1 0.05 to 40 % by weight based on the cloth. If the amount
is less than 0.05 % by weight, the effect of preventing
excessive penetration of ink becomes insufficient. On the
other hand, if the water repellent is contained in an
5 amount exceeding 40 % by weight, a great change in
performance can no longer be brought about.

Any water-soluble polymer having a water-repellent
function may also be used as the water repellent.
Examples of such water-soluble polymers include starch,
10 cellulosic substances such as carboxymethylcellulose,
methylcellulose and hydroxyethylcellulose, sodium
alginate, gum arabic, guar gum, gelatin, tannin and
derivatives thereof, polyvinyl alcohol and derivatives
thereof, polyethylene oxide and derivatives thereof,
15 water-soluble acrylic polymers, and water-soluble maleic
anhydride polymers.

The amount of the water-soluble polymer is 0.1 to 20
% by weight based on the cloth. Any amount of the water-
soluble polymer exceeding 20 % by weight results in a
20 cloth markedly deteriorated in desizing ability. It is
also not preferred from the viewpoint of economy to
contain the water-soluble polymer in such a great amount.
On the other hand, if the amount is less than 0.1 % by
weight, the effect of such an agent is not sufficiently
25 exhibited.

The hydrophilic agent useful in the practice of the
present invention is a substance capable of improving the



1 ink-absorbing ability of a cloth when added in a
predetermined amount or more to the cloth as compared with
the cloth before its addition. Increase in the absorbing
ability can be determined by whether the water repellency
5 is reduced or not, and the degree of the reduction. As
specific examples of a method of applying the hydrophilic
agent, there are considered various methods such as a
method of containing a surfactant and a method of
containing a water-soluble substance having a hydrophilic
10 group. Any of these methods may be used.

As the surfactant used for enhancing the absorbing
ability, are preferred anionic, nonionic and amphoteric
surfactants. As examples of the anionic surfactant, may
be mentioned surfactants of the sulfonic acid, carboxylic
15 acid, sulfuric acid ester and phosphoric acid ester types.
As the nonionic surfactant, there may be used ether types
such as polyoxyethylene alkyl ethers, polyoxyethylene
alkyl allyl ethers and acetylene glycol, the ester types
such as polyoxyethylene alkyl esters and sorbitan fatty
20 acid esters, aminoether types such as polyoxyethylene
alkylamines, ether ester types such as polyoxyethylene
sorbitan fatty acid esters, and the like. As the
amphoteric surfactant, there may be used betaine types and
the like.

25 The surfactant is preferably applied in an amount of
0.01 to 50 % by weight based on the cloth. If the amount
exceeds 50 % by weight, a change in absorbing ability can



1 no longer be brought about, and such a great amount is
hence not preferred from the viewpoint of economy. On the
other hand, if the amount is less than 0.01 % by weight,
the effect of such an agent is not sufficiently exhibited.

5 As the water-soluble substance having a hydrophilic
group used for improving the absorbing ability, are
preferred those like water-soluble solvents generally
incorporated into ink-jet inks. Examples of usable
solvents include lower alkylene glycols such as ethylene
10 glycol, diethylene glycol, triethylene glycol and
propylene glycol; lower alkyl ethers of alkylene glycols,
such as ethylene glycol methyl (ethyl, propyl or butyl)
ether, diethylene glycol methyl (ethyl, propyl or butyl)
ether, triethylene glycol methyl (ethyl, propyl or butyl)
15 ether, propylene glycol methyl (ethyl, propyl or butyl)
ether, dipropylene glycol methyl (ethyl, propyl or butyl)
ether and tripropylene glycol methyl (ethyl, propyl or
butyl) ether; polyalkylene glycols such as polyethylene
glycol and polypropylene glycol and products obtained by
20 modifying one or two hydroxyl groups thereof, typified by
mono- or dialkyl ethers thereof; glycerol; and
thiodiglycol. Most of them are liquid, but those having a
high molecular weight may be solid. However, their effect
is not different from that of the liquid.

25 The water-soluble substance having a hydrophilic
group is preferably applied in an amount of 0.01 to 50 %
by weight based on the cloth. If the amount exceeds 50 %



1 by weight, a change in easiness of wetting can no longer
be brought about, and such a great amount is hence not
preferred from the viewpoint of economy. On the other
hand, if the amount is less than 0.01 % by weight, the
5 effect of such an agent is not sufficiently exhibited.

The preferable ranges of the water repellent and
hydrophilic agent to be added to the cloth are as
described above. However, a ratio between the amounts of
these agents to be added is important. With respect to
10 this ratio, the amounts of the water repellent and
hydrophilic agent are preferably determined in such a
manner that the water repellency of the resulting cloth is
less than 50 points.

The cloth according to the present invention
15 contains the above-described substances for the purpose of
adjusting its water repellency, but may also contain
compounds other than these substances. Examples of the
compounds usable include water-soluble inorganic salts,
urea, catalysts, alkalis, acids, antireductants,
20 antioxidants, level dyeing agents, deep dyeing agents,
carriers, reducing agents, oxidizing agents and metal
ions.

As compounds effective in prevention of bleeding and
improvement of coloring ability, may be mentioned water-
25 soluble inorganic salts. Examples of water-soluble
inorganic salts preferably used include alkali metal salts
such as NaCl, Na₂SO₄, KCl and CH₃COONa, and alkaline earth



1 metal salts such as CaCl_2 and MgCl_2 .

Urea is also very effective in prevention of bleeding and improvement of coloring ability. In particular, its combined use with the water-soluble
5 inorganic salt has a synergistic effect and is hence preferred.

As a method of containing the above-described substances in the cloth, any method such as padding, spraying, dipping, printing or ink-jet may be used.

10 A cloth may be impregnated with a treating liquid containing the water repellent and hydrophilic agent. However, when a cloth is impregnated with a treating liquid containing the water repellent so as to make the cloth hard to be penetrated by inks, and then dried,
15 followed by application of the hydrophilic agent for improving wetting property, the treating liquid for improving the wetting property does not penetrate the interior of fiber because the fiber is impregnated with the water repellent, and so the treating liquid adheres
20 only to the peripheral surface of the fiber. Therefore, the wetting property of the peripheral surface of the fiber is improved. As a method of determining the wetting property where the interior of fiber is different from the peripheral surface of the fiber in the wetting property as
25 described above, such a difference can be confirmed by conducting ink-jet printing on a cloth, observing a fiber section of the resulting print to distinguish a difference



1 in the concentration of a fixed dye between the peripheral
surface and the interior in the fiber section. More
specifically, if the concentration of the fixed dye on the
peripheral surface side of the fiber in the fiber
5 structure is higher than that on the interior side of the
fiber, it can be said that the wetting property of the
peripheral surface of the fiber is higher than that of the
interior of the fiber. On the other hand, if there is
little difference in the concentration of the fixed dye
10 between the peripheral surface and the interior of the
fiber, it can be said that there is no difference in the
wetting property as well.

After conducting the treatment as described above,
the thus-treated cloth is finally dried and optionally cut
15 into sizes feedable in an ink-jet apparatus, thereby
providing these cut pieces as ink-jet printing cloths.

No particular limitation is imposed on textile
printing inks used for the ink-jet printing cloths
according to the present invention. However, when the
20 cloth is formed of a material such as cotton or silk, ink-
jet textile printing inks composed of a reactive dye and
an aqueous medium are preferably used. When the cloth is
formed of a material such as nylon, wool, silk or rayon,
ink-jet textile printing inks composed of an acid or
25 direct dye and an aqueous medium are preferably used.
Besides, when the cloth is formed of a polyester material,
ink-jet textile printing inks composed of a disperse dye

1 and an aqueous medium are preferably used.

As specific preferable examples of these dyes, may be mentioned the following dyes. The reactive dyes include C.I. Reactive Yellow 2, 15, 37, 42, 76, 95, 168
5 and 175; C.I. Reactive Red 21, 22, 24, 33, 45, 111, 112, 114, 180, 218, 226, 228 and 235; C.I. Reactive Blue 15, 19, 21, 38, 49, 72, 77, 176, 203, 220, 230 and 235; C.I. Reactive Orange 5, 12, 13, 35 and 95; C.I. Reactive Brown 7, 11, 33, 37 and 46; C.I. Reactive Green 8 and 19; C.I.
10 Reactive Violet 2, 6 and 22; C.I. Reactive Black 5, 8, 31 and 39; and the like.

The acid and direct dyes include C.I. Acid Yellow 1, 7, 11, 17, 23, 25, 36, 38, 49, 72, 110 and 127; C.I. Acid Red 1, 27, 35, 37, 57, 114, 138, 254, 257 and 274; C.I.
15 Acid Blue 7, 9, 62, 83, 90, 112 and 185; C.I. Acid Black 26, 107, 109 and 155; C.I. Acid Orange 56, 67 and 149; C.I. Direct Yellow 12, 44, 50, 86, 106 and 142; C.I. Direct Red 79 and 80; C.I. Direct Blue 86, 106, 189 and 199; C.I. Direct Black 17, 19, 22, 51, 154, 168 and 173;
20 C.I. Direct Orange 26 and 39; and the like.

The disperse dyes include C.I. Disperse Yellow 3, 5, 7, 33, 42, 60, 64, 79, 104, 160, 163 and 237; C.I. Disperse Red 1, 60, 135, 145, 146 and 191; C.I. Disperse Blue 56, 60, 73, 143, 158, 198, 354, 365 and 366; C.I.
25 Disperse Black 1 and 10; C.I. Disperse Orange 30 and 73; Teraprint Red 3GN Liquid and Teraprint Black 2R; and the like.

1 The amount (in terms of solids) of these dyes to be
used is preferably within a range of from 1 to 30 % by
weight based on the total weight of the ink.

 As a water-soluble solvent used together with the
5 dyes, there may be used any water-soluble solvent
generally used in ink-jet inks. Preferable examples
thereof include lower alkylene glycols such as ethylene
glycol, diethylene glycol, triethylene glycol and
propylene glycol; lower alkyl ethers of alkylene glycols,
10 such as ethylene glycol methyl (ethyl, propyl or butyl)
ether, diethylene glycol methyl (ethyl, propyl or butyl)
ether, triethylene glycol methyl (ethyl, propyl or butyl)
ether, propylene glycol methyl (ethyl, propyl or butyl)
ether, dipropylene glycol methyl (ethyl, propyl or butyl)
15 ether and tripropylene glycol methyl (ethyl, propyl or
butyl) ether; polyalkylene glycols such as polyethylene
glycol and polypropylene glycol and products obtained by
modifying one or two hydroxyl groups thereof, typified by
mono- or dialkyl ethers thereof; glycerol; thiodiglycol;
20 sulfolane; N-methyl-2-pyrrolidone; 2-pyrrolidone; and 1,3-
dimethyl-2-imidazolidinone. The preferable content of
these water-soluble solvents is generally within a range
of from 0 to 50 % by weight based on the total weight of
the ink.

25 In the case of a water-based ink, the content of
water as a principal component is preferably within a
range of from 30 to 95 % by weight based on the total

1 weight of the ink.

Besides the above components, anti-clogging agents such as urea and derivatives thereof, dispersants, surfactants, viscosity modifiers such as polyvinyl
5 alcohol, cellulosic compounds and sodium alginate, pH adjusters, optical whitening agents, mildewproofing agents, and the like may be added as other ingredients for inks as needed.

As an ink-jet recording method and apparatus used,
10 there may be used any method and apparatus conventionally known. Examples thereof include a method and an apparatus in which thermal energy corresponding to recording signals is applied to an ink within a recording head, and ink droplets are generated by this thermal energy.

15 The inks applied onto the ink-jet printing cloth of this invention in accordance with the process of the present invention in the above-described manner only adhere to the cloth in this state. Accordingly, it is preferable to subsequently subject the cloth to a process
20 for fixing the dyes in the inks to fiber and a process for removing unfixed dyes. Such a fixing process may be conducted in accordance with any conventionally-known method. Examples thereof include a steaming process, an HT steaming process and a thermofix process. The removal
25 of the unreacted dyes may be performed by any washing process conventionally known.

After conducting the ink-jet printing and the post-



1 treatment of the cloth in the above-described manner, the
cloth is dried to provide a print according to the present
invention.

An exemplary constitution of an ink-jet printing
5 apparatus used in the present invention will hereinafter
be roughly described. It goes without saying that the
apparatus to which the present invention can be applied is
not limited to the constitution as described below. It is
therefore possible to make any change in constitution and
10 add any constitutional element, which are easily conceived
by those skilled in the art.

Fig. 1A is a typical sectional side elevation
schematically illustrating the constitution of a printing
apparatus. Reference numeral 1 designates a cloth as a
15 printing medium. The cloth 1 is unwound according to the
rotation of a rewind roller 11, fed in a substantially
horizontal direction by a conveyance section 100, which is
provided at a position opposite to a printer section 1000,
through intermediate rollers 13 and 15, and then wound up
20 on a take-up roller 21 through a feed roller 17 and an
intermediate roller 19.

The conveyance section 100 roughly includes
conveyance rollers 110 and 120 respectively provided on
the upstream and downstream sides of the printer section
25 1000 viewing from the feeding direction of the cloth 1, a
conveyor belt 130 in the form of an endless belt, which is
extended between and around these rollers, and a pair of



1 platen rollers 140 provided so as to extend the conveyor
belt 130 under an appropriate tension in a predetermined
range to enhance its evenness, thereby evenly regulate the
surface of the cloth 1 to be printed upon printing by the
5 printer section 1000. In this apparatus illustrated, the
conveyor belt 130 is made of a metal as disclosed in
Japanese Patent Application Laid-Open No. 5-212851. As
illustrated in Fig. 1B with partial enlargement, an
adhesive layer (sheet) 133 is provided on its surface.
10 The cloth 1 is adhered to the conveyor belt 130 through
the adhesive layer 133 by an attaching roller 150, thereby
ensuring the evenness of the cloth 1 upon the printing.

To the cloth 1 fed in a state that the evenness has
been ensured as described above, is applied a printing
15 agent in the region between the platen rollers 140 by the
printer section 1000. The thus-printed cloth 1 is
separated from the conveyor belt 130, or the adhesive
layer 133 at the position of the conveyance roller 120 and
wound up on the take-up roller 21. In the course of the
20 winding, the cloth is subjected to a drying treatment by a
drying heater 600. In particular, this drying heater 600
is effective when a liquid agent is used as the printing
agent. The form of the drying heater 600 may be suitably
selected from a heater by which hot air is blown on the
25 cloth 1, a heater by which infrared rays are applied to
the cloth 2, and the like.

Fig. 2 is a perspective view typically illustrating



1 the printer section 1000 and the feed system of the cloth 1. The constitution of the printer section 1000 will be described with reference to this drawing and Fig. 1A.

5 In Figs. 1A and 2, the printer section 1000 includes a carriage 1010 which scans in a direction different from the conveying direction (a secondary scanning direction) f of the cloth 1, for example, the width direction S of the cloth 1 perpendicular to the conveying direction f.

10 Reference numeral 1020 designates a support rail extending in the S direction (a main scanning direction) and supporting a slide rail 1022 which supports and guides a slider 1012 fixed to the carriage 1010. Reference numeral 1030 indicates a motor as a drive source for conducting

15 main scanning of the carriage 1010. The driving power thereof is transmitted to the carriage 1010 through a belt 1032 to which the carriage 1010 has been fixed, or another suitable drive mechanism.

On the carriage 1010, are mounted sets of printing

20 heads 1100 each having many printing agent-applying elements arranged in a predetermined direction (in this case, the conveying direction f), said sets each being composed of a plurality of the printing heads 1100 arranged in a direction (in this case, the main scanning

25 direction S) different from said predetermined direction. In this embodiment, two sets of the printing heads 1100 are held in the conveying direction. In each set, the



1 printing heads 1100 are provided by the number
corresponding to the number of printing agents of
different colors, thereby permitting color printing.
Colors of the printing agents and the number of the
5 printing heads in each set may be suitably selected
according to an image intended to be formed on the cloth
1, and the like. For example, yellow (Y), magenta (M) and
cyan (C), or the three primary colors for printing, or
black (Bk) in addition to these colors may make one set.
10 Alternatively, special colors (metallic colors such as
gold and silver, and bright red, blue, etc.), which are
impossible or difficult to be expressed by the three
primary colors, may be used in place of or in addition to
the above color set. Further, a plurality of printing
15 agents may be used according to the color depth even if
they have the same colors as each other.

In this embodiment, as illustrated in Fig. 1A, two
sets of the printing heads 1100, which each are composed
of plural printing heads arranged in the main scanning
20 direction S, are provided one by one in the conveying
direction f. The colors, arranging number, arranging
order and the like of the printing agents used in the
printing heads in the respective sets may be the same or
different from each other according to the image intended
25 to be printed, and the like. Further, printing may be
made again by the printing heads of the second set on a
region printed by main scanning of the printing heads of

1 the first set (either complementary thinning-out printing
or overlap printing may be conducted by the respective
sets of the printing heads). Furthermore, a printing
region may be allotted to each set to perform high-speed
5 printing. Besides, the number of sets of the printing
heads is not limited to two and may also be defined as one
or more than two.

In these drawings, ink-jet heads, for example,
bubble jet heads proposed by Canon Inc., each having a
10 heating element which generates thermal energy causing
film boiling of ink as energy used for ejecting the ink,
are used as the printing heads 1100. Each of the printing
heads is used in a state that ink ejection orifices as the
printing agent-applying elements have been disposed
15 downward toward the cloth 1 substantially horizontally
conveyed by the conveyance section 100, thereby ironing
out the difference in water head between the individual
ejection orifices and hence making ejection conditions
uniform to permit both formation of good images and even
20 purging operation for all the ejection orifices.

A flexible cable 1110 is connected to each of the
printing heads 1100 in such a manner that it follows the
movement of the carriage 1010, so that various signals
such as drive signals and state signals for the head are
25 transferred between the head and control means not
illustrated. Inks are fed from an ink-feeding system
1130, in which respective inks of different colors are



1 contained, to the printing heads 1100 through flexible tubes 1120.

Fig. 3 is a perspective view typically illustrating the ink-feeding system in this embodiment. The ink-feeding system 1130 is composed of two lines. More specifically, in the first line, first ink-feeding tubes 1120 respectively connected to the first set of ink-storage tanks 1131 are connected to a head joint 1150 through the flexible tube 1110. In the second line, similarly, second ink-feeding tubes 1121 respectively connected to the second set of ink-storage tanks 1132 are connected to the head joint 1150 through the flexible tube 1110.

Each ink-feeding tube 1120 or 1121 forms a circulation path composed of an outward ink-feeding tube 1120a or 1121a and an inward ink-feeding tube 1120b or 1121b.

The ink-storage tanks 1131 and 1132 each have a pressure pump not illustrated. The ink in the tank 1131 or 1132 is pressurized by this pressure pump so as to pass through the outward ink-feeding tube 1120a or 1121a as illustrated in Fig. 3, circulate through the printing head 1100 and then pass through the inward ink-feeding tube 1120b or 1121b, thereby returning to the ink-storage tank 1131 or 1132.

By this pressure pump, it is possible to recharge the inks into the ink-feeding tubes 1120 and 1121 and also



1 to conduct purging operation of the head by circulating
the ink through the head and discharging a fraction of
this ink out of nozzles in the head. The ink-storage
tanks 1131 and 1132 may be provided respectively by a
5 number corresponding to the number of the printing agents
of different colors, thereby permitting color printing.

The number of the ink-storage tanks in each set may
be suitably selected according to an image intended to be
formed on the cloth 1, and the like. For example, three
10 tanks for yellow (Y), magenta (M) and cyan (C) colors, or
the three primary colors for printing, or four tanks with
a tank for a black (Bk) color added to these tanks may be
provided. Alternatively, tanks for special colors
(metallic colors such as gold and silver, and bright red,
15 blue, etc.), which are impossible or difficult to be
expressed by the three primary colors, may be used in
place of or in addition to the above tanks. Further, a
plurality of tanks may be used according to the color
depth even if printing agents used have the same colors as
20 each other.

The head joint 1150 is composed of a head joint 1151
for the first set indicated by a full line, a head joint
1152 for the second set indicated by a broken line and a
joint cover 1160.

25 The constitution of the head used in the above-
described apparatus will hereinafter be described
schematically with reference to Fig. 4.



1 Fig. 4 is a sectional perspective view schematically illustrating the constitution of an ink-jet head to be mounted on the ink-jet printing apparatus used in the present invention.

5 In this drawing, the printing head is constructed by overlapping a top plate 71 and a base plate 72. The top plate 71 has a plurality of grooves 73, which are to define nozzles passing an ink therethrough, a groove 74, which is to define a common liquid chamber communicating
10 with these grooves, and a feed opening 75 for feeding the ink to the common liquid chamber. On the other hand, the base plate 72 includes electrothermal converters 76 corresponding to the individual nozzles and electrodes 77 for supplying electric power to the electrothermal
15 converters 76, respectively, said electrothermal converters and electrodes being formed integrally by a film-forming technique. Ejection openings (orifices) 78 through which the ink is ejected are defined by overlapping the top plate 71 and the base plate 72 as
20 described above.

Here, the process of forming ink droplets by the bubble jet system, which is carried out by the above-described printing head, will be described simply.

When a heating resistor (heater) reaches a
25 predetermined temperature, such a filmy bubble as covers a heater surface is first formed. The internal pressure of this bubble is very high, and so an ink within a nozzle is

1 forced out. The ink is moved toward the outside of the
nozzle and the interior of the common liquid chamber by
inertia force by this forcing out. When the movement of
the ink is facilitated, the moving speed of the ink within
5 the nozzle becomes slow because the internal pressure of
the bubble turns negative pressure, and flow path
resistance also arises in addition. Since the ink portion
ejected out of the ejection opening (orifice) is faster in
moving speed than the ink within the nozzle, it is
10 constricted by the balance among inertia force, flow path
resistance, shrinkage of the bubble and surface tension of
the ink, whereby the ink portion is separated into a
droplet. At the same time as the shrinkage of the bubble,
the ink is fed to the nozzle from the common liquid
15 chamber by capillary force to wait a next pulse.

As described above, the printing head (hereinafter
may referred to as an ink-jet head), in which the
electrothermal converter is used an energy-generating
means (hereinafter may referred to as an energy-generating
20 element), can generate a bubble in the ink within the flow
path in one-to-one correspondence in accordance with a
driving electrical pulse signal and also immediately and
appropriately cause the growth/shrinkage of the bubble,
and so the ejection of ink droplets can be achieved with
25 excellent responsiveness in particular. The printing head
is advantageous in that it can also be made compact with
ease, merits of IC techniques and macro processing



1 techniques in the recent semiconductor field, which are
remarkable for advance in technique and enhancement in
reliability, can be fully applied thereto, high-density
mounting can be achieved with ease, and production costs
5 are also low.

The present invention will hereinafter be described
more specifically by the following examples and
comparative examples. Incidentally, all designations of
"part" or "parts" and "%" as will be used in the following
10 examples mean part or parts by weight and % by weight
unless expressly noted.

Examples 1 to 12:

(A) Production of ink-jet printing cloth:

Using a 100 % cotton satin fabric (mercerized
15 product), a 100 % nylon taffeta fabric and a 100 %
polyester tropical fabric, pretreatments using their
corresponding pretreatment agents shown in Table 1 were
conducted by the padding process. The thus-pretreated
fabrics were then squeezed to a pickup of 70 % by a mangle
20 and dried at a drying temperature of 120°C for 2 minutes.

(B) Preparation of ink-jet printing ink:

Reactive dye inks, acid dye inks and disperse dye
inks were prepared in the following manner. The total
amounts of the inks are all 100 parts.

25 (1) Reactive dye inks:

Reactive dye	10 parts
Thiodiglycol	40 parts

1	Water	50 parts.
---	-------	-----------

Dyes used were C.I. Reactive Yellow 95, C.I. Reactive Red 226, C.I. Reactive Blue 15 and C.I. Reactive Black 39.

5 (2) Acid dye inks:

Acid dye	10 parts
Diethylene glycol	40 parts
Water	50 parts.

Dyes used were C.I. Acid Yellow 110, C.I. Acid Red

10 266, C.I. Acid Blue 90 and C.I. Acid Black 26.

(3) Disperse dye inks:

Disperse dye	10 parts
Thiodiglycol	40 parts
Water	50 parts.

15 Dyes used were C.I. Disperse Yellow 42, Teraprint Red 3GN Liquid (trade name, product of Ciba-Geigy AG), C.I. Disperse Blue 56 and Teraprint Black 2R (trade name, product of Ciba-Geigy AG).

(C) Ink-jet printing:

20 Using a Bubble Jet Printer BJC-820J (trade name,
manufactured by Canon Inc.) as an ink-jet printing apparatus,
sets of the above-prepared printing inks were separately
charged in this printer. The fabrics were separately mounted
on base paper webs to permit the conveying of the fabrics,
25 thereby printing the fabrics. Any printing apparatus may be
used without limiting to the above printer.

(D) Post-treatment:

1 The printed fabrics were subjected to a steaming
treatment at 100°C for 8 minutes for the reactive dye
inks, at 100°C for 30 minutes for the acid dye inks, and
at 180°C for 10 minutes for the disperse dye inks. The
5 thus-treated cloths were washed and then dried.

(E) Evaluation of prints:

The thus-obtained print samples and the fabrics used
were evaluated in the following manner. The results are
shown in Table 1.

10 (1) Bleeding:

The linearity of fine-line portions in each print
sample was visually observed to rank resistance to
bleeding in accordance with the following standard:

A: Good;

15 B: Somewhat poor;

C: Poor.

(2) Color depth (K/S) of print:

A minimum spectral reflectance of a 20 x 20 mm
square printed portion in each print sample was measured
20 by a Minolta Spectrocolorimeter CM-2022 (trade name). A
K/S value was found from this reflectance. The color
depth of each print sample was ranked in terms of this K/S
value in accordance with the following standard:

A: Greater than 13;

25 B: 10 to 13;

C: Smaller than 10.

(3) Drying property:

1 Printing was conducted by the BJC-820J printer, and
the printed area was rubbed with a cloth upon elapsed time
of 30 seconds after the printing. The drying property was
evaluated by whether ink smearing occurred or not and
5 ranked in accordance with the following standard:

A: No ink smearing occurred;

C: Ink smearing occurred.

(4) Water repellency:

Each fabric sample was sprayed with 250 ml of water
10 by a Spray Tester (trade name, manufactured by Daiei
Kagaku Seiki Seisakusho) in accordance with the water
repellency test (spray method) described in JIS L 1092.
The water repellency was ranked in terms of 0 to 100
points according to the wet state of the sample after the
15 test.

Comparative Examples 1 to 11:

Ink-jet printing and evaluation were conducted in
the same manner as in Examples 1 to 12 except that the
cloths and the textile printing inks were changed to those
20 shown in Table 2. The results are shown in Table 2.

Table 1

	Cloth	Pretreatment	Ink	Water repellency	Resistance to bleeding	Color depth	Drying property
		Agent [conc. in aq. solution (%)]					
Ex. 1	Cotton	Water repellent 1 [3], Surfactant 1 [1], Na ₂ CO ₃ [2]	Reactive	0	A	A	A
Ex. 2	Cotton	Water repellent 2 [1], Surfactant 2 [1], Na ₂ CO ₃ [2]	Reactive	0	A	A	A
Ex. 3	Cotton	Water repellent 1 [3], Surfactant 1 [1], Na ₂ SO ₄ [4], Na ₂ CO ₃ [2]	Reactive	0	A	A	A
Ex. 4	Cotton	Water repellent 1 [3], Surfactant 1 [1], urea [4], Na ₂ CO ₃ [2]	Reactive	0	A	A	A
Ex. 5	Cotton	Water repellent 1 [3], Surfactant 1 [1], Na ₂ SO ₄ [4], urea [4], Na ₂ CO ₃ [2]	Reactive	0	A	A	A
Ex. 6	Nylon	Water repellent 1 [3], Surfactant 1 [1]	Acid	0	A	A	A
Ex. 7	Nylon	Water repellent 2 [3], Surfactant 1 [1]	Acid	0	A	A	A
Ex. 8	Nylon	Water repellent 1 [3], Surfactant 1 [1], Na ₂ SO ₄ [4]	Acid	0	A	A	A
Ex. 9	Nylon	Water repellent 2 [3], Surfactant 1 [1], Na ₂ SO ₄ [4]	Acid	0	A	A	A
Ex. 10	Polyester	Water repellent 2 [3], Hydrophilic substance 1 [5]	Disperse	0	A	A	A
Ex. 11	Polyester	Water repellent 2 [3], Surfactant 1 [1]	Disperse	0	A	A	A
Ex. 12	Polyester	Water repellent 2 [3], Surfactant 2 [1]	Disperse	0	A	A	A

Water repellent 1: Paragium SS (trade name, paraffinic softening water repellent, product of Chara Paragium Chemical Co., Ltd.).

Water repellent 2: Zebran F-1 (trade name, fluorine-containing type water repellent, product of Ipposha Oil Industries Co., Ltd.).

Surfactant 1: Noigen HC (trade name, nonionic surfactant, product of Dai-ichi Kogyo Seiyaku Co., Ltd.).

Surfactant 2: Neocall SW (trade name, anionic surfactant, product of Dai-ichi Kogyo Seiyaku Co., Ltd.).

Hydrophilic substance 1: Triethylene glycol butyl ether.

Table 2

	Cloth	Pretreatment	Ink	Water repellency	Resistance to bleeding	Color depth	Drying property
		Agent [conc. in aq. solution (%)]					
Comp. Ex. 1	Cotton	Na ₂ CO ₃ [2]	Reactive	0	C	C	A
Comp. Ex. 2	Cotton	Water repellent 1 [1], Na ₂ CO ₃ [2]	Reactive	70	A	C	C
Comp. Ex. 3	Cotton	Water repellent 2 [1], Na ₂ CO ₃ [2]	Reactive	90	A	C	C
Comp. Ex. 4	Cotton	Hydrophilic substance 1 [5], Na ₂ CO ₃ [2]	Reactive	0	C	B	A
Comp. Ex. 5	Cotton	Surfactant 1 [1], Na ₂ CO ₃ [2]	Reactive	0	C	C	A
Comp. Ex. 6	Cotton	Surfactant 2 [1], Na ₂ CO ₃ [2]	Reactive	0	C	C	A
Comp. Ex. 7	Nylon	Surfactant 1 [1]	Acid	0	C	C	A
Comp. Ex. 8	Nylon	Hydrophilic substance 1 [5]	Acid	0	C	C	A
Comp. Ex. 9	Nylon	Water repellent 1 [1]	Acid	50	A	C	C
Comp. Ex. 10	Polyester	Surfactant 1 [1]	Disperse	0	C	C	A
Comp. Ex. 11	Polyester	Hydrophilic substance 1 [5]	Disperse	0	C	B	A

Water repellent 1: Paragium SS (trade name, paraffinic softening water repellent, product of Ohara Paragium Chemical Co., Ltd.).

Water repellent 2: Zebran F-1 (trade name, fluorine-containing type water repellent, product of Ipposha Oil Industries Co., Ltd.).

Surfactant 1: Noigen HC (trade name, nonionic surfactant, product of Dai-ichi Kogyo Seiyaku Co., Ltd.).

Surfactant 2: Neocall SW (trade name, anionic surfactant, product of Dai-ichi Kogyo Seiyaku Co., Ltd.).

Hydrophilic substance 1: Triethylene glycol butyl ether.




1 As apparent from Tables 1 and 2, all the prints
according to Examples 1 to 12 were free of bleeding, high
in color depth and also excellent in drying property. In
particular, the cloth added with urea and inorganic salts
5 thereto described in Example 5 was excellent in resistance
to bleeding and coloring ability, whereas the cloths
according to Comparative Examples 1 to 11 gave unfavorable
results such as low color depth, poor drying property
and/or the like.

10 Examples 13 to 27 and Comparative Examples 12 to 19:

Prints were produced in the same manner as in
Examples 1 to 12 except that the following fabrics were
used as ink-jet printing cloths.

15 Using a 100 % cotton broadcloth (mercerized
product), a 100 % nylon taffeta fabric and a 100 %
polyester crepe de Chine, pretreatments 1 using their
corresponding agents shown in Tables 3 and 4 were
conducted by the padding process. The thus-pretreated
fabrics were then squeezed to a pickup of 70 % by a mangle
20 and dried at a drying temperature of 120°C for 2 minutes.
The thus-treated fabrics were further subjected to
pretreatments 2 using their corresponding agents shown in
Tables 3 and 4 were conducted similarly by the padding
process. The thus-pretreated fabrics were then squeezed
25 to a pickup of 70 % by a mangle and dried at a drying
temperature of 120°C for 2 minutes. Besides the
formulations according to the examples as the pretreatment



1 formulations, treatment formulations according to the comparative examples, which are outside the scope of the present, are shown in Table 5.

Evaluation of prints:

5 The thus-obtained print samples and the fabrics used were evaluated in the following manner. The results are shown in Tables 3 to 5.

(1) Bleeding:

The linearity of fine-line portions in each print
10 sample was visually observed to rank resistance to bleeding in accordance with the following standard:

A: Good;

B: Somewhat poor;

C: Poor.

15 (2) Optical density (OD):

The optical density of a solid printed area was measured by a Macbeth densitometer RD918, thereby ranking it in accordance with the following standard:

A: OD value not lower than 1.3;

20 B: OD value ranging from 0.8 to 1.2;

C: OD value lower than 0.8.

(3) Tendency to strike-through:

The optical densities of the front and back surfaces of a solid printed area were measured by a Macbeth
25 densitometer RD918. The tendency to strike-through was ranked in terms of a ratio (OD of the back surface to OD of the front surface) between the OD values in accordance

1 with the following standard:

(Cotton)

A: Not lower than 0.7;

B: 0.60 to 0.69;

5 C: Lower than 0.60.

(Nylon and polyester)

A: Not lower than 0.9;

B: 0.80 to 0.89;

C: Lower than 0.80.

10 (4) Drying property:

An ink in an amount of 0.03 g was dropped on a cloth to be tested to rank the drying property in terms of time required to absorb the ink in accordance with the following standard:

15 A: Not longer than 10 seconds;

B: 11 to 30 seconds;

C: Longer than 30 seconds.

(5) Permeability or wetting property (contact angle):

20 An ink in an amount of 0.03 g was dropped on a cloth to be tested to measure its contact angle with the cloth (the cloth is easier to wet as the contact angle is narrower, i.e., the wetting property is greater).

(Contact angle)

25 S: Narrower than 90° (unmeasurable due to strike-through);

I: 90 to 110°;

G: Wider than 110°.

1 (6) Dye distribution:

 An ink-jet print to be tested was cut so as to permit the observation of its fiber section. The section was observed through a microscope to determine a
5 difference in the concentration of a fixed dye between the peripheral surface and the interior of the fiber. The print was ranked as A where the color was deep in a wide range of the peripheral surface of the fiber because its OD value was also high.

- 10 A: The color was deep in a wide range of the peripheral surface of the fiber, but the color was thin in the interior of the fiber;
- B: The color was deep only in a part of the peripheral surface of the fiber;
- 15 C: The color was even and thin as a whole in both peripheral surface and interior of the fiber.

20

25

Table 3

	Cloth	Pretreatment 1		Pretreatment 2		Ink	Bleeding	OD	Strike-through	Drying prop.	Dye Distr.	Water repell.
		Agent/conc. in aq. soln. (%)	Cont. angle	Agent/conc. in aq. soln. (%)	Cont. Angle							
Ex. 13	Cotton	Water repell. 1/1, Na ₂ CO ₃ /2	G	Surfactant 1/1, Na ₂ CO ₃ /2	S	Reactive	A	A	A	A	A	0
Ex. 14	Cotton	Water repell. 2/1, Na ₂ CO ₃ /2	G	Surfactant 2/1, Na ₂ CO ₃ /2	S	Reactive	A	A	A	A	A	0
Ex. 15	Cotton	Water repell. 3/1, Na ₂ CO ₃ /2	G	Surfactant 3/1, Na ₂ CO ₃ /2	S	Reactive	A	A	A	A	A	0
Ex. 16	Cotton	Water repell. 2/1, Na ₂ CO ₃ /2	G	Surfactant 1/1, Na ₂ CO ₃ /2	S	Reactive	A	A	A	A	A	0
Ex. 17	Cotton	Water-soluble polymer 1/3, Na ₂ CO ₃ /2	G	Surfactant 1/1, Na ₂ CO ₃ /2	S	Acid	A	A	A	A	A	0
Ex. 18	Nylon	Water repell. 1/1	G	Surfactant 1/1	S	Acid	A	A	A	A	A	0
Ex. 19	Nylon	Water repell. 2/1	G	Surfactant 2/1	S	Acid	A	A	A	A	A	0
Ex. 20	Nylon	Water repell. 3/1	G	Surfactant 3/1	S	Acid	A	A	A	A	A	0

Table 4

	Cloth	Pretreatment 1		Pretreatment 2		Ink	Bleeding	OD	Strike-through	Drying prop.	Dye Distr.	Water repell.
		Agent/conc. in aq. soln. (%)	Cont. angle	Agent/conc. in aq. soln. (%)	Cont. Angle							
Ex. 21	Nylon	Water repell. 2/1	G	Surfactant 1/1	S	Acid	A	A	A	A	A	0
Ex. 22	Nylon	Water-soluble polymer 1/3	G	Surfactant 1/1	S	Acid	A	A	A	A	A	0
Ex. 23	Polyester	Cationic substance 1/1	G	Surfactant 1/1	S	Disperse	A	A	A	A	A	0
Ex. 24	Polyester	Water repell. 1/1	G	Surfactant 2/1	S	Disperse	A	A	A	A	A	0
Ex. 25	Polyester	Water repell. 2/1	G	Surfactant 3/1	S	Disperse	A	A	A	A	A	0
Ex. 26	Polyester	Water repell. 3/1	G	Surfactant 1/1	S	Disperse	A	A	A	A	A	0
Ex. 27	Polyester	Water-soluble polymer 1/3	G	Surfactant 1/1	S	Disperse	A	A	A	A	A	0



Table 5

	Cloth	Pretreatment 1		Pretreatment 2		Ink	Bleeding	OD	Strike-through	Drying prop.	Dye Distr.	Water repell.
		Agent/conc. in aq. soln. (%)	Cont. angle	Agent/conc. in aq. soln. (%)	Cont. Angle							
Comp. Ex. 12	Cotton	$\text{Na}_2\text{CO}_3/2$	S	Not conducted	-	Reactive	C	C	B	A	C	0
Comp. Ex. 13	Cotton	Water repell. 1/1, $\text{Na}_2\text{CO}_3/2$	G	Not conducted	-	Reactive	A	B	C	C	B	70
Comp. Ex. 14	Cotton	Water repell. 1/1, $\text{Na}_2\text{CO}_3/2$	G	Water repell. 1/1, $\text{Na}_2\text{CO}_3/2$	G	Reactive	A	B	C	C	B	70
Comp. Ex. 15	Cotton	Surfactant 1/1, $\text{Na}_2\text{CO}_3/2$	S	Not conducted	-	Reactive	C	C	B	A	C	70
Comp. Ex. 16	Nylon	Water repell. 1/1	G	Not conducted	-	Acid	A	B	C	C	B	80
Comp. Ex. 17	Nylon	Surfactant 1/1	S	Not conducted	-	Acid	C	C	B	A	C	0
Comp. Ex. 18	Polyester	Water repell. 1/1	G	Not conducted	-	Disperse	A	B	C	C	B	80
Comp. Ex. 19	Polyester	Surfactant 1/1	S	Not conducted	-	Disperse	C	C	B	A	C	0

1 (Note):

Water repellent 1: Sumifluoil EM51 (trade name, fluorine-
containing type water repellent,
product of Sumitomo Chemical Co.,
5 Ltd.).

Water repellent 2: TSW831/CW80 (trade name, silicone type
water repellent, product of Toshiba
Silicone Co., Ltd.).

Water repellent 3: Paraguard 519Z (trade name, reactive
10 fluoro-resin type water repellent,
product of Ohara Paragium Chemical Co.,
Ltd.).

Surfactant 1: Noigen HC (trade name, nonionic surfactant,
product of Dai-ichi Kogyo Seiyaku Co.,
15 Ltd.).

Surfactant 2: Neocall SW (trade name, anionic surfactant,
product of Dai-ichi Kogyo Seiyaku Co.,
Ltd.).

Surfactant 3: Migregirl GWL (trade name, nonionic
20 surfactant, product of Senka K.K.).

Water-soluble polymer 1:
Carboxymethylcellulose.

Cationic substance 1:

Sanfix PRO (trade name, polyamine type,
25 product of Sanyo Chemical Industries, Ltd.)

As apparent from Tables 3 to 5, all the prints
according to Examples 13 to 27 were free of bleeding, high

1 in color depth on the front surfaces and excellent in
tendency to strike-through and drying property, whereas
the cloths according to Comparative Examples 12 to 19
could not satisfy all the performance properties at the
5 same time.

In the prior art, it has been said that coloring
ability and resistance to bleeding, and tendency to
strike-through are antipodal properties, and hence
difficult to satisfy at the same time. However, according
10 to the present invention, it has been possible to satisfy
all properties of coloring ability, resistance to
bleeding, tendency to strike-through and ink-drying
property at the same time by causing the permeability or
wetting property to inks of the fiber structure to differ
15 between the interior and peripheral surface thereof as
described above. In the present invention, the terms
"permeability" and "wetting property" are used as
substantial synonyms. However, they are sometimes used
each in its proper way in order to make easy to
20 understand. The term "peripheral surface" means fiber
surface, i.e., an outer periphery in section of a fiber.
For example, if a fiber structure is made hard to be
wetted (hard to be permeated) by an ink on the interior
side thereof and easy to be wetted (easy to be permeated)
25 by the ink on the periphery side thereof like the present
invention, the ink impacted on the cloth by ink-jet
printing becomes easy to spread in the peripheral



1 direction of the fiber, but hard to be absorbed in the
interior (thickness) direction. In such a case, the ink
becomes a state that it diffuses into the peripheral
surface of the fiber and does not almost exist in the
5 interior thereof. Such a state is equal, as to the
prevention of the diffusion into the interior, to the
method in the prior art technique that "the penetration of
inks into the interior of fiber is prevented to prevent
the diffusion of dyes". However, they differ as to
10 whether the dye diffuses into the peripheral surface of
the fiber or not. In the prior art technique, the cloth
is hard to be permeated or wetted in both interior and
peripheral sides of the fiber. Therefore, the inks do not
also spread in the peripheral direction of the fiber. Due
15 to this difference in "the spreading in the peripheral
direction of the fiber", the prior art technique has
provided a cloth failing to satisfy the coloring ability
and having poor tendency to strike-through. To the
contrary, when the present invention is applied, the area
20 factor becomes great, the coloring ability is enhanced,
and the tendency to strike-through is improved because the
ink goes along the peripheral surface of the fiber to the
back surface.

On the other hand, when compared with the method of
25 the prior art technique that "a surfactant is contained in
fiber to absorb inks in the interior of the fiber by
diffusion", this prior art technique can improve the



1 tendency to strike-through, but does not achieve effective
absorption of light by dyes because the dyes penetrate
into the interior of the fiber, and hence can provide only
a cloth poor in coloring ability. To the contrary,
5 according to the present invention, no ink is absorbed in
the interior of the fiber, and so coloring ability is
improved.

As described above, the ink-jet printing cloths and
printing processes according to the present invention
10 permit the provision of bright prints excellent in drying
property, free of bleeding and high in color depth and
image quality.

Besides, the cloths obtained by containing the water
repellent and the hydrophilic agent by at least two cloth-
15 treating steps can provides bright prints free of
bleeding, high in color depth, good in tendency to strike-
through and high in image quality and grade, and are
excellent in ink-drying property upon printing, and hence
permits textile printing free from ink smearing.

20 While the present invention has been described with
respect to what is presently considered to be the
preferred embodiments, it is to be understood that the
invention is not limited to the disclosed embodiments. To
the contrary, the invention is intended to cover various
25 modifications and equivalent arrangements included within
the spirit and scope of the appended claims. The scope of
the following claims is to be accorded to the broadest

1 interpretation so as to encompass all such modifications
and equivalent structures and functions.

5

10

15

20

25



1 WHAT IS CLAIMED IS:

1. An ink-jet printing cloth on which textile printing is conducted using an ink-jet system, wherein the cloth contains a water repellent and a hydrophilic agent
5 so as to have a predetermined water repellency.

2. The ink-jet printing cloth according to Claim 1, wherein the water repellency is less than 50 marks in terms of the water repellency prescribed by the water
10 repellency test with a spray method described in JIS L 1092.

3. The ink-jet printing cloth according to Claim 1 or 2, wherein the water repellent is any of paraffinic and
15 fluorine-containing type water repellents.

4. The ink-jet printing cloth according to Claim 1, wherein the water repellent is applied in an amount of 0.05 to 40 % by weight based on the cloth.
20

5. The ink-jet printing cloth according to Claim 1, wherein the hydrophilic agent is applied in an amount of 0.01 to 50 % by weight based on the cloth.

25 6. The ink-jet printing cloth according to Claim 1, further comprising at least one of a water-soluble inorganic salt and urea.



1 7. The ink-jet printing cloth according to Claim 1,
wherein the wetting property to inks of the peripheral
surface of fiber constituting the cloth is higher than
that of the interior of the fiber.

5

 8. A process for producing an ink-jet printing
cloth on which textile printing is conducted using an ink-
jet system, which comprises the steps of:
 applying a water repellent to a cloth;
10 drying the cloth; and
 further applying a hydrophilic agent to the dry
cloth.

 9. The production process according to Claim 8,
15 wherein a predetermined water repellency is given to the
cloth through the steps according to Claim 8.

 10. The production process according to Claim 9,
wherein the water repellency is less than 50 marks in
20 terms of the water repellency prescribed by the water
repellency test with a spray method described in JIS L
1092.

 11. The production process according to Claim 8,
25 wherein the water repellent is any of paraffinic and
fluorine-containing type water repellents.



1 12. The production process according to Claim 8,
wherein the water repellent is applied in an amount of
0.05 to 40 % by weight based on the cloth.

5 13. The production process according to Claim 8,
wherein the hydrophilic agent is applied in an amount of
0.01 to 50 % by weight based on the cloth.

10 14. The production process according to Claim 8,
wherein at least one of a water-soluble inorganic salt and
urea is applied to the cloth.

15 15. The production process according to Claim 8,
wherein the wetting property to inks of the peripheral
surface of fiber constituting the cloth is made higher
than that of the interior of the fiber through the steps
according to Claim 8.

20 16. An ink-jet printing process comprising ejecting
inks by an ink-jet system to print a cloth, wherein a
cloth containing a water repellent and a hydrophilic agent
and having a predetermined water repellency is used as
said cloth.

25 17. The ink-jet printing process according to Claim
16, wherein a cloth having a water repellency less than 50
marks in terms of the water repellency prescribed by the



1 water repellency test with a spray method described in JIS
L 1092 is used.

18. The ink-jet printing process according to Claim
5 16, wherein the water repellent is any of paraffinic and
fluorine-containing type water repellents.

19. The ink-jet printing process according to Claim
16, wherein the water repellent is applied in an amount of
10 0.05 to 40 % by weight based on the cloth.

20. The ink-jet printing process according to Claim
16, wherein the hydrophilic agent is applied in an amount
of 0.01 to 50 % by weight based on the cloth.

15

21. The ink-jet printing process according to Claim
16, wherein the cloth contains at least one of a water-
soluble inorganic salt and urea.

20 22. The ink-jet printing process according to Claim
16, wherein an electrothermal converter which generates
thermal energy causing film boiling of ink is used as an
energy-generating means for ejecting the ink.

25 23. The ink-jet printing process according to Claim
16, which comprises the steps of:
applying inks to the cloth;



1 fixing the applied inks to the cloth; and
washing the cloth after the fixing treatment.

24. The ink-jet printing process according to Claim
5 16, wherein the wetting property to inks of the peripheral
surface of fiber constituting the cloth is higher than
that of the interior of the fiber.

25. A process for producing a print by applying inks
10 to a cloth using an ink-jet system to print the cloth,
which comprises the steps of:

applying inks to a cloth containing a water repellent
and a hydrophilic agent and having a predetermined water
repellency;

15 fixing dyes in the inks to the cloth; and
washing the thus-treated cloth.

26. The precess for producing a print according to
Claim 25, wherein a concentration of a fixed dye at the
20 peripheral surface of fiber constituting the print is
higher than that at the interior of the fiber through the
steps according to Claim 25.

27. The process according to Claim 25, wherein a
25 cloth having a water repellency less than 50 marks in
terms of the water repellency prescribed by the water
repellency test with a spray method described in JIS L



1 1092 is used.

28. The process according to Claim 25, wherein the
water repellent is any of paraffinic and fluorine-
5 containing type water repellents.

29. The process according to Claim 25, wherein the
water repellent is applied in an amount of 0.05 to 40 % by
weight based on the cloth.

10

30. The process according to Claim 25, wherein the
hydrophilic agent is applied in an amount of 0.01 to 50 %
by weight based on the cloth.

15

31. The process according to Claim 25, wherein the
cloth contains at least one of a water-soluble inorganic
salt and urea.

20

25