

DESCRIPTION

BONDING WIRE FOR SEMICONDUCTOR DEVICE

5 TECHNICAL FIELD

[0001] The present invention relates to a bonding wire for a semiconductor device used to connect electrodes on a semiconductor device and wiring of a circuit wiring board such as external leads.

10

BACKGROUND ART

[0002] As a bonding wire for a semiconductor device which connects electrodes on a semiconductor device and external leads (hereinafter referred to as a "bonding wire"), a thin wire with a wire diameter of about 15 to 50 μm is mainly used today. For a bonding method with bonding wire, there is generally used a thermal compressive bonding technique with the aid of ultrasound, in which a general bonding device, a capillary tool used for bonding by passing a bonding wire therethrough, and the like are used. A bonding process of a bonding wire is carried out by heating and melting a tip of wire by arc heat input to form a ball through surface tension; crimp-bonding the ball part onto an electrode of the semiconductor device heated within 20 a range of 150 to 300°C (hereinafter referred to as "ball bonding"); forming a loop; and finally crimp-bonding a wire part onto an electrode of the external lead (hereinafter referred to as "wedge bonding"). For the electrode on the semiconductor device as an object to be bonded with the 25 bonding wire, there is used an electrode structure in which a film of alloy mainly containing Al is formed on a Si substrate. For the electrode of the external lead, an electrode structure with Ag plating or Pd plating is used. 30

[0003] Although Au has been mainly used for a material of the bonding wire, a replacement of Au with Cu is being conducted mainly in LSI use. On the background of recent proliferation of electric vehicles and hybrid vehicles, needs for replacing Au with Cu are increasing also in on-vehicle device use.

[0004] In comparison to general electronic devices, on-vehicle devices are required to operate under a rigorous high-temperature and high-humidity environment. It is therefore required for on-vehicle devices to have an excellent bonding longevity of a ball bonded part (hereinafter referred to as a "bonding reliability"), and to enable a stable formation of ball with excellent sphericity (hereinafter referred to as a "ball formability") for achieving a stable bonding strength.

[0005] It is also required for on-vehicle devices to cope with a densification of mounting associated with high functionalization and miniaturization. With an increase in mounting density, a diameter of bonding wire becomes thinner and then an area that contributes to bonding at the time of wedge bonding decreases, which results in difficulty to achieve a bonding strength. Therefore, it is necessary to achieve a high bonding strength at a wedge bonded part, that is, to improve wedge bondability. There is also required a technique of deforming a ball to a true circular shape at the time of ball bonding, because a distance narrows between electrodes on a semiconductor device and it is thus concerned that a ball becomes in contact with an adjacent electrode to cause short circuit. Furthermore, when subjected to resin sealing, it is necessary to obtain a linearity of loop and to reduce variation in loop height in order to prevent adjacent wires from coming in contact with each other due to deformation

of bonding wires caused by resin flow.

[0006] As for a Cu bonding wire, there has been proposed a wire using high-purity Cu (purity: 99.99 wt.% or more) (for example, Patent Literature 1). Cu has the drawback of being more susceptible to oxidation than Au and has problems in that bonding reliability, ball formability and wedge bondability are inferior. As a method for preventing surface oxidation of a Cu bonding wire, there has been proposed a structure in which a surface of Cu core material is coated with a metal such as Au, Ag, Pt, Pd, Ni, Co, Cr and Ti (Patent Literature 2). There has been also proposed a structure in which a surface of Cu core material is coated with Pd and a surface thereof is coated with Au, Ag, Cu or an alloy thereof (Patent Literature 3).

15

RELATED ART REFERENCE

Patent Literature

[0007] Patent Literature 1: JP-A-S61-48543

Patent Literature 2: JP-A-2005-167020

20

Patent Literature 3: JP-A-2012-36490

SUMMARY OF INVENTION

PROBLEM TO BE SOLVED BY THE INVENTION

[0008] The present inventors studied in light of properties required for on-vehicle devices and, as a result, found that practical problems still remain in the conventional Cu bonding wire having Pd coating layer as noted below.

[0009] In comparison to general electronic devices, on-vehicle devices require bonding reliability in a rigorous high-temperature and high-humidity environment. Some methods are developed for evaluating the bonding reliability, and a representative evaluation method

30

includes a high-temperature and high-humidity test. In a case of general electronic devices, the high-temperature and high-humidity test is usually conducted under a condition of a temperature of 130°C and a relative humidity of 85%. In contrast, on-vehicle devices require a practical performance at higher temperature and thus require a bonding reliability of 1500 hours or more in a condition of a temperature of 150°C and a relative humidity of 85%.

10 [0010] It has been found that, in a case when a conventional Cu bonding wire having a Pd coating layer is used to perform a bonding operation with a pure Al electrode, followed by performing a sealing operation with an epoxy resin and conducting a high-temperature and high-humidity test in a condition of a temperature of 150°C and a relative humidity of 85%, a bonding strength decreases within 1500 hours or less due to the occurrence of cracks in bonding interface, and the bonding reliability required for on-vehicle devices is not achieved. According to detailed observation on the bonding interface, a plurality of intermetallic compounds based on Al and Cu are formed. The decrease in bonding strength is estimated to be caused by a preferential corrosion of Cu_9Al_4 among these compounds.

20 [0011] As a result of evaluating a ball formability, it has been found that, a conventional Cu bonding wire having a Pd coating layer cannot meet the ball formability required for on-vehicle devices. In particular, there was frequently observed a ball having voids on surface thereof and a ball having poor sphericity. As for a cause of voids occurrence, it is considered because H_2 and N_2 that were absorbed when Pd was melt with an arc discharge are released during a solidification of Pd. As for a cause of

decrease in sphericity, it is considered an effect of thermal conductivity. A ball is solidified by releasing heat toward a wire. Pd has a low thermal conductivity compared to Cu and Cu is solidified earlier than Pd, which results in that a surface Pd cannot be deformed so as to follow a solidification and shrinkage of Cu and a surface irregularity occurs. Such phenomenon becomes more marked with increasing a thickness of Pd coating layer. Even in a case where Au, Ag or Cu was coated on a Pd coating layer, a ball formability could not be improved.

[0012] In view of the above result of study, it has been revealed that, when using a conventional Cu bonding wire having a Pd coating layer, it is not able to meet a criterion for a bonding reliability and a ball formability required for on-vehicle devices. It has been also revealed that, even when using improved methods focused on a thickness and structure of Pd coating layer which has been conventionally studied, there cannot be achieved a bonding reliability and a ball formability required for on-vehicle devices at the same time.

[0013] It is therefore an object of the present invention to provide a bonding wire that improves bonding reliability of a ball bonded part and a ball formability and is suitable for on-vehicle devices.

25

MEANS FOR SOLVING PROBLEM

[0014] A bonding wire of the present invention is a bonding wire for a semiconductor device including a Cu alloy core material and a Pd coating layer formed on a surface of the Cu alloy core material, and is characterized in that the Cu alloy core material contains Ni, a concentration of Ni is 0.1 to 1.2 wt.% relative to the entire wire, and a thickness of the Pd coating layer is

30

0.015 to 0.150 μm .

EFFECT OF THE INVENTION

[0015] The present invention includes a Pd coating layer
5 and a Cu alloy core material containing Ni. In the present
invention, Pd or Ni is concentrated at a bonding interface
with electrode in a ball bonded part and a diffusion of Cu
and Al at the bonding interface during a high-temperature
and high-humidity test is reduced, which can reduce a
10 growth rate of corrodible compound. It is thus able to
improve the bonding reliability. Also, in the present
invention, a concentration of Ni is 0.1 wt.% or more
relative to the entire wire, and thus, an occurrence of
surface irregularity of ball can be reduced, which leads to
15 improvement in a ball formability.

EMBODIMENT FOR CARRYING OUT THE INVENTION

[0016] There will be described an embodiment of the
present invention in detail bellow.

20 [0017] 1. Embodiment

(General constitution)

A bonding wire of an embodiment of the present
invention includes a Cu alloy core material and a Pd
coating layer formed on a surface of the Cu alloy core
25 material. The Cu alloy core material contains Ni, a
concentration of Ni is 0.1 to 1.2 wt.% relative to the
entire wire, and a thickness of the Pd coating layer is
0.015 to 0.150 μm . With this configuration, the bonding
wire can improve a bonding reliability and ball formability
30 required for on-vehicle devices.

[0018] There will be described the definition of the Cu
alloy core material and the Pd coating layer of the bonding
wire. A boundary between the Cu alloy core material and

the Pd coating layer was determined based on a concentration of Pd. The boundary was set to be a position at which a concentration of Pd was 50 at.%, and a region in which a concentration of Pd was 50 at.% or more was
5 determined to be the Pd coating layer, and a region in which a concentration of Pd was less than 50 at.% was determined to be the Cu alloy core material. This is because if a concentration of Pd is 50 at.% or more in the Pd coating layer, there can be expected an effect of
10 improving characteristics from the structure of the Pd coating layer. The Pd coating layer may contain a region of a Pd single layer and a region having concentration gradients of Pd and Cu in a wire depth direction. The reason why the region having the concentration gradients is
15 formed in the Pd coating layer is that atoms of Pd and Cu may diffuse through heat treatment or the like in a manufacturing process. In addition, the Pd coating layer may contain inevitable impurities. Furthermore, Ni contained in the Cu alloy core material may be diffused to
20 the Pd coating layer through heat treatment or the like and may be present in the Pd coating layer.

[0019] When a ball is formed using such bonding wire by arc discharge, an alloy layer having a higher concentration of Pd or Ni than an inside of the ball is formed in a
25 surface of the ball during the process when the bonding wire melts and solidifies. Such ball is used to bond with an Al electrode and a high-temperature and high-humidity test is performed, which allows Pd or Ni to be concentrated at a bonding interface. A concentrated layer formed by the
30 concentrated Pd or Ni can reduce a diffusion of Cu and Al at a bonding interface during a high-temperature and high-humidity test and can reduce a growth rate of corrodible compound. Thus, the bonding wire can increase the bonding

reliability. On the other hand, when a concentration of Ni is less than 0.1 wt.% or a thickness of Pd coating layer is less than 0.015 μm , the concentrated layer is not sufficiently formed and thus the bonding reliability cannot be increased.

[0020] The alloy layer with a high concentration of Pd or Ni formed on a surface of the ball is excellent in oxidation resistance and can thereby reduce failures such as deviation of a ball forming position relative to a center of the bonding wire at the time of ball formation.

[0021] In addition, an occurrence of surface irregularity of ball can be reduced by the configuration that a Cu alloy of core material contains Ni and a concentration of Ni is 0.1 wt.% or more relative to the entire wire. This is considered because a thermal conductivity of a Cu alloy core material is decreased by adding Ni into a Cu alloy of core material and becomes closer to a thermal conductivity of a Pd coating layer, which can reduce a difference between ball surface and ball inside for a required time from molten state to completing solidification.

[0022] On the other hand, when a concentration of Ni becomes more than 1.2 wt.% relative to the entire wire, it is not suitable for practical use because a ball hardens and Si chip damage at the time of ball bonding becomes a problem. When a thickness of Pd coating layer becomes 0.150 μm or more, there cannot be obtained good ball formability because voids occur in a ball surface when forming a ball.

[0023] In some cases, Cu is present at an outermost surface of the Pd coating layer.

[0024] The bonding wire may further include an Au skin

layer of a thickness of 0.0005 to 0.050 μm formed on a surface of the Pd coating layer. With this configuration, the bonding wire can further increase the bonding reliability and can improve the wedge bondability.

5 [0025] There will be described the definition of the Au skin layer of the bonding wire. A boundary between the Au skin layer and the Pd coating layer was determined based on a concentration of Au. The boundary was set to be a position at which a concentration of Au was 10 at.%, and a
10 region in which a concentration of Au was 10 at.% or more was determined to be the Au skin layer, and a region in which a concentration of Au was less than 10 at.% was determined to be the Pd coating layer. Even in the region in which a concentration of Pd was 50 at.% or more, a
15 region in which Au was present at 10 at.% or more was determined to be the Au skin layer. These determinations are because if a concentration of Au falls within the range mentioned above, there can be expected an effect of improving characteristics from the structure of the Au skin
20 layer. The Au skin layer is an Au-Pd alloy and a region including a region having concentration gradients of Au and Pd in the wire depth direction. The reason why the region having the concentration gradients is formed in the Au skin layer is that atoms of Au and Pd diffuse through heat
25 treatment or the like in the manufacturing process. Furthermore, the Au skin layer may contain inevitable impurities.

[0026] In a high-temperature and high-humidity test, Au forms a concentrated layer of ternary system alloy of Au, Ni and Pd in combination with Ni and Pd at a bonding
30 interface in a ball bonded part, which can remarkably reduce a growth rate of corrodible compound. Thus, the bonding wire can further increase a bonding reliability.

The Au skin layer also reacts with Ni contained in the Pd coating layer or the Cu alloy core material to increase adhesive strength among the Au skin layer, the Pd coating layer and the Cu alloy core material and to prevent the Pd coating layer and the Au skin layer from peeling at the time of wedge bonding. Accordingly, the bonding wire can improve the wedge bondability. If a thickness of the Au skin layer is less than 0.0005 μm , the above effect is not obtained. If the thickness becomes more than 0.050 μm , it is not suitable for practical use because a propagation of ultrasonic wave at the time of wedge bonding degrades and a good bonding strength cannot be obtained. The Au skin layer can be formed by the same method as the Pd coating layer. In some cases, Cu is present at an outermost surface of the Au skin layer.

[0027] In the bonding wire, when the Cu alloy core material further contains at least one element selected from B, In, Ca, P and Ti and a concentration of the elements is 3 to 100 wt. ppm relative to the entire wire, there can be improved a crushed shape of a ball bonded part required for high-density mounting, that is, there can be improved a circularity of shape of a ball bonded part. This is because an addition of the elements can allow a size of crystal grain in the ball to be fine and can reduce a deformation of the ball. If a concentration of the elements relative to the entire wire is less than 3 wt. ppm, the above effect is not obtained. If the concentration exceeds 100 wt. ppm, it is not suitable for practical use because the ball hardens and chip damage at the time of ball bonding becomes a problem.

[0028] In the bonding wire, when the Cu alloy core material further contains Pt or Pd and a concentration of Pt or Pd contained in the Cu alloy core material is 0.05 to

1.20 wt.%, there can be increased a loop formability, that is, there can be increased a linearity of loop required for high density mounting and can be decreased a variation in loop height. This is because the Cu alloy core material contains Pd or Pt to increase a yield strength of bonding wire, which can reduce a deformation of bonding wire. In order to increase a linearity of loop and to reduce a variation in loop height, it is more effective that the Cu alloy core material has higher strength. There cannot be obtained sufficient effect even when improving a coating structure such as increasing a thickness of the Pd coating layer. If a concentration of Pt or Pd contained in the Cu alloy core material is less than 0.05 wt.%, the above effect is not obtained. If the concentration exceeds 1.20 wt.%, the bonding wire hardens and a deformation of a bonded part of wire becomes insufficient, and a decrease in wedge bondability becomes a problem.

[0029] For a concentration analysis of wire surface in order to determine the Pd coating layer and the Au skin layer, a method of performing analysis while trimming the bonding wire from its surface in the depth direction by sputtering or the like, or a method of exposing a cross-section of the wire and performing a line analysis, a point analysis, or the like thereon is effective. As a method for exposing a cross-section of wire, a mechanical polishing, an ion etching, etc., can be applied. For an analyzer used for concentration analysis, an Auger electron spectroscopic apparatus installed in a scanning electron microscope or a transmission electron microscope, an energy dispersive X-ray analyzer, and an electron probe micro analyzer, etc., can be applied. Among these concentration analysis methods, an analysis method using a scanning electron microscope in which both of a sputtering apparatus

and an Auger electron spectroscopic apparatus are installed is preferable because it can obtain a concentration profile in a depth direction with regard to a plurality of elements in a relatively short time. For a concentration analysis
5 of elements contained in the entire bonding wire, there can be used an ICP emission spectrometer.

[0030] (Manufacturing Method)

Next, there will be described a method for manufacturing the bonding wire according to the embodiment
10 of the present invention. The bonding wire is obtained by manufacturing a Cu alloy used for a core material, working it into a thin wire, forming a Pd coating layer and an Au skin layer, and performing heat treatment. After forming the Pd coating layer and the Au skin layer, another wire
15 drawing and heat treatment may be performed. There will be described in detail a method for manufacturing the Cu alloy core material, a method for forming the Pd coating layer and the Au skin layer, and a method of heat treatment.

[0031] The Cu core alloy used for a core material is
20 obtained by melting Cu as a raw material and additive elements together and solidifying them. An arc heating furnace, a high-frequency heating furnace, a resistance heating furnace, or the like can be used for the melting. In order to prevent gases such as O_2 , N_2 and H_2 being mixed
25 therein from air, the melting is preferably performed in a vacuum atmosphere or an inert atmosphere such as Ar and N_2 .

[0032] A method for forming the Pd coating layer and the Au skin layer on a surface of the Cu alloy core material includes a plating method, a vapor deposition method, and a
30 melting method. For a plating method, both of an electroplating method and an electroless plating method can be used. The electroplating, called a strike plating or a flash plating, is high in plating speed and is favorable in

adhesiveness with a substrate. A solution used for electroless plating is classified into a substitutional type and a reduction type. Although performing the substitutional type plating alone is sufficient for a smaller thickness, it is effective for a larger thickness to perform the reduction type plating after the substitutional type plating in a step-by-step manner.

[0033] For a vapor deposition method, there can be used a physical adsorption such as a sputtering method, an ion plating method and a vacuum vapor deposition, and a chemical adsorption such as plasma CVD. They are all dry processes, and are free from the necessity of cleaning after forming the Pd coating layer and the Au skin layer and from any concern about surface contamination and the like during cleaning.

[0034] For a formation of the Pd coating layer and the Au skin layer, both a method of forming them after performing wire drawing to a final diameter of wire and a method of forming them on a Cu alloy core material of large diameter and then performing wire drawing several times until obtaining a target diameter of wire are effective. In the former in which the Pd coating layer and the Au skin layer are formed at the final diameter of wire, a manufacture, a quality control, and the like are simple. In the latter in which the wire drawing is performed in combination with the formed Pd coating layer and Au skin layer, there is the advantage that adhesiveness with the Cu alloy core material improves. Specific examples of the respective formation methods include a method of forming the Pd coating layer and the Au skin layer on a Cu alloy core material with a final diameter by successively sweeping the wire through an electroplating solution and a method of forming the Pd coating layer and the Au skin

layer by immersing a Cu alloy core material of large diameter into an electro or electroless plating solution and then drawing the wire to achieve a final diameter of wire.

5 [0035] After forming the Pd coating layer and the Au skin layer, heat treatment may be carried out. By carrying out the heat treatment, diffusion of atoms occurs among the Au skin layer, the Pd coating layer and the Cu alloy core material, which improves adhesive strength therebetween and
10 is effective in that the Au skin layer and the Pd coating layer are prevented from peeling during working, and thus, improving productivity. In order to prevent O₂ being mixed therein from air, it is preferable to perform the melting in a vacuum atmosphere or an inert atmosphere such as Ar or
15 N₂.

[0036] The present invention is not limited to the above embodiment, and appropriate alterations can be made within the scope of the spirit of the present invention.

20 [0037] 2. Example

The bonding wire according to an embodiment of the present invention will be described in detail below with reference to examples.

[0038] (Sample)

25 First, there will be described a method for manufacturing a sample. For Cu and Ni as a raw material of a core material, the ones with a purity of 99.99 wt.% or more and containing inevitable impurities as the remainder was used. For B, In, Ca, P, Ti, Pt and Pd, the ones with a
30 purity of 99 wt.% or more and containing inevitable impurities as the remainder were used.

[0039] The Cu alloy for the core material was manufactured by charging the raw materials into a carbon

crucible worked into a cylindrical shape with a diameter of 3 to 6 mm, heating and melting the raw materials at 1,090 to 1,300°C in vacuum or in an inert atmosphere such as an N₂ or Ar gas using a high-frequency furnace, and performing furnace cooling. The obtained alloy with a diameter of 3 mm was drawn to manufacture a wire with a diameter of 0.9 to 1.2 mm. Thereafter, a wire with a diameter of 300 to 600 μm was manufactured by successively performing wire drawing and the like using a die. A commercially available lubricant was used for the wire drawing, and a wire drawing speed was 20 to 150 m/min. In order to remove an oxide film on a surface of wire, a pickling treatment with hydrochloric acid was performed, and a Pd coating layer was formed by 1 to 15 μm so as to cover the entire surface of the Cu alloy as the core material. Furthermore, for some wires, an Au skin layer was formed by 0.05 to 1.5 μm on the Pd coating layer. For the formation of the Pd coating layer and the Au skin layer, electroplating was used. A commercially available semiconductor plating solution was used for a plating solution. Heat treatment at 200 to 500°C and wire drawing were then repeatedly carried out to perform working to a diameter of 20 μm. After working, heat treatment was performed in vacuum or while being flowed with an Ar gas so that breaking elongation will finally be about 9 to 15%. A method of heat treatment was performed while successively sweeping the wire and was carried out while being flowed with an Ar gas. A wire feeding speed was 20 to 200 m/min, a heat treatment temperature was 200 to 600°C, and a heat treatment time was 0.2 to 1.0 second.

[0040] The configurations of the samples manufactured according to the above procedure are listed in Tables 1-1,

1-2, 1-3 and 2. The thicknesses of the Pd coating layer and the Au skin layer described in Tables are calculated values based on concentration profiles of Pd, Au and Cu in a depth direction which is obtained by conducting an Auger electron spectroscopy analysis while trimming a wire surface with an Ar ion sputtering.

[0041] [Table 1-1]

Remarks		Concentration of Ni relative to entire wire (wt.%)	Thickness of Pd coating layer (μm)	Thickness of Au skin layer (μm)	Concentration of each element relative to entire wire				Concentration of each element in Cu alloy core material		Wire diameter (μm)
					B conc. (wt.ppm)	Ir conc. (wt.ppm)	Ca conc. (wt.ppm)	P conc. (wt.ppm)	Pt conc. (wt.%)	Pd conc. (wt.%)	
Example	1	0.1	0.016	-	-	-	-	-	-	-	20
Example	2	0.2	0.090	-	-	-	-	-	-	-	20
Example	3	0.3	0.150	-	-	-	-	-	-	-	20
Example	4	0.8	0.017	-	-	-	-	-	-	-	20
Example	5	0.8	0.110	-	-	-	-	-	-	-	20
Example	6	0.8	0.150	-	-	-	-	-	-	-	20
Example	7	1.2	0.150	-	-	-	-	-	-	-	20
Example	8	1.2	0.110	-	-	-	-	-	-	-	20
Example	9	1.2	0.150	-	-	-	-	-	-	-	20
Example	10	0.2	0.016	0.002	-	-	-	-	-	-	20
Example	11	0.1	0.016	0.050	-	-	-	-	-	-	20
Example	12	0.1	0.150	0.003	-	-	-	-	-	-	20
Example	13	0.2	0.150	0.040	-	-	-	-	-	-	20
Example	14	0.7	0.016	0.002	-	-	-	-	-	-	20
Example	15	0.7	0.016	0.050	-	-	-	-	-	-	20
Example	16	0.7	0.150	0.004	-	-	-	-	-	-	20
Example	17	0.7	0.150	0.040	-	-	-	-	-	-	20
Example	18	1.2	0.016	0.002	-	-	-	-	-	-	20
Example	19	1.2	0.016	0.040	-	-	-	-	-	-	20
Example	20	1.2	0.150	0.002	-	-	-	-	-	-	20
Example	21	1.2	0.150	0.050	-	-	-	-	-	-	20
Example	22	0.2	0.016	-	4	-	-	-	-	-	20
Example	23	0.3	0.016	-	20	-	-	-	-	-	20
Example	24	1.2	0.150	-	45	-	-	-	-	-	20
Example	25	0.3	0.016	-	98	-	-	-	-	-	20
Example	26	1.2	0.150	-	3	-	-	-	-	-	20
Example	27	1.2	0.150	-	97	-	-	-	-	-	20
Example	28	0.3	0.016	0.004	3	-	-	-	-	-	20
Example	29	0.2	0.017	0.004	20	-	-	-	-	-	20
Example	30	0.3	0.016	0.004	45	-	-	-	-	-	20
Example	31	0.2	0.016	0.003	99	-	-	-	-	-	20
Example	32	1.2	0.016	0.050	4	-	-	-	-	-	20
Example	33	1.2	0.016	0.050	95	-	-	-	-	-	20
Example	34	0.2	0.150	0.004	5	-	-	-	-	-	20
Example	35	0.3	0.150	0.003	98	-	-	-	-	-	20
Example	36	1.2	0.150	0.050	4	-	-	-	-	-	20
Example	37	1.2	0.150	0.050	99	-	-	-	-	-	20
Example	38	1.2	0.150	0.050	20	30	-	-	-	-	20
Example	39	1.2	0.150	0.050	30	50	-	-	-	-	20
Example	40	1.2	0.150	-	-	6	-	-	-	-	20
Example	41	0.2	0.016	-	-	100	-	-	-	-	20
Example	42	0.2	0.016	0.006	-	3	-	-	-	-	20
Example	43	0.1	0.016	0.007	-	97	-	-	-	-	20
Example	44	0.1	0.016	-	-	3	-	-	-	-	20
Example	45	0.2	0.016	-	-	-	98	-	-	-	20

[0042] [Table 1-2]

Remarks		Concentration of Ni relative to entire wire (wt.%)	Thickness of Pd coating layer (μm)	Thickness of Au skin layer (μm)	Concentration of each element relative to entire wire				Concentration of each element in Cu alloy core material		Wire diameter (μm)
					B conc. (wt.ppm)	In conc. (wt.ppm)	Ca conc. (wt.ppm)	P conc. (wt.ppm)	Pt conc. (wt.%)	Pd conc. (wt.%)	
Example	46	0.1	0.016	0.006	-	-	3	-	-	-	20
Example	47	0.1	0.016	0.008	-	-	99	-	-	-	20
Example	48	0.2	0.016	-	-	-	-	5	-	-	20
Example	49	0.2	0.016	-	-	-	-	98	-	-	20
Example	50	0.1	0.016	0.007	-	-	-	6	-	-	20
Example	51	0.1	0.016	0.006	-	-	-	97	-	-	20
Example	52	0.2	0.016	-	-	-	-	-	0.05	-	20
Example	53	0.2	0.016	-	-	-	-	-	1.20	-	20
Example	54	1.2	0.150	-	-	-	-	-	0.05	-	20
Example	55	1.2	0.150	-	-	-	-	-	1.20	-	20
Example	56	0.2	0.016	0.003	-	-	-	-	0.05	-	20
Example	57	0.2	0.016	0.003	-	-	-	-	1.20	-	20
Example	58	1.2	0.016	0.05	-	-	-	-	0.05	-	20
Example	59	1.2	0.016	0.05	-	-	-	-	1.20	-	20
Example	60	0.2	0.150	0.003	-	-	-	-	0.05	-	20
Example	61	0.3	0.150	0.003	-	-	-	-	1.20	-	20
Example	62	1.2	0.150	0.05	-	-	-	-	0.05	-	20
Example	63	1.2	0.150	0.05	-	-	-	-	1.20	-	20
Example	64	1.2	0.150	0.05	20	-	-	-	0.30	-	20
Example	65	1.2	0.150	0.05	30	60	-	-	0.40	-	20
Example	66	0.3	0.016	-	-	-	-	-	-	0.05	20
Example	67	0.2	0.016	-	-	-	-	-	-	1.20	20
Example	68	0.2	0.016	0.006	-	-	-	-	-	0.05	20
Example	69	0.3	0.016	0.006	-	-	-	-	-	1.20	20
Example	70	0.2	0.016	0.006	30	-	-	-	-	0.30	20
Example	71	0.3	0.016	0.006	40	50	-	-	-	0.35	20
Example	72	0.7	0.100	0.0004	-	-	-	-	-	-	20
Example	73	0.7	0.100	-	2	-	-	-	-	-	20
Example	74	0.7	0.100	-	115	-	-	-	-	-	20
Example	75	0.7	0.100	0.08	2	-	-	-	-	-	20
Example	76	0.7	0.100	0.08	115	-	-	-	-	-	20
Example	77	0.7	0.100	-	-	2	-	-	-	-	20
Example	78	0.7	0.100	-	-	108	-	-	-	-	20
Example	79	0.7	0.100	-	-	-	2	-	-	-	20
Example	80	0.7	0.100	-	-	-	104	-	-	-	20
Example	81	0.7	0.100	-	-	-	-	2	-	-	20
Example	82	0.7	0.100	-	-	-	-	106	-	-	20
Example	83	0.7	0.100	-	-	-	-	-	0.03	-	20
Example	84	0.7	0.100	-	-	-	-	-	1.30	-	20
Example	85	0.7	0.100	0.006	-	-	-	-	0.03	-	20
Example	86	0.7	0.100	0.100	-	-	-	-	1.30	-	20
Example	87	0.7	0.100	-	-	-	-	-	-	0.03	20
Example	88	0.7	0.100	-	-	-	-	-	-	1.30	20
Example	89	0.7	0.100	0.006	-	-	-	-	-	0.03	20
Example	90	0.7	0.100	0.100	-	-	-	-	-	1.30	20

[0043] [Table 1-3]

Remarks		Concentration of Ni relative to entire wire (wt.%)	Thickness of Pd coating layer (μm)	Thickness of Au skin layer (μm)	Concentration of each element relative to entire wire					Concentration of each element in Cu alloy core material		Wire diameter (μm)
					B conc. (wt.ppm)	In conc. (wt.ppm)	Ca conc. (wt.ppm)	P conc. (wt.ppm)	Ti conc. (wt.ppm)	Pt conc. (wt.%)	Pd conc. (wt.%)	
Example	91	0.7	0.1	-	-	-	-	-	2	-	-	20
Example	92	0.7	0.1	-	-	-	-	-	103	-	-	20
Example	93	0.7	0.1	0.080	-	-	-	-	2	-	-	20
Example	94	0.7	0.1	0.080	-	-	-	-	103	-	-	20

[0044] [Table 2]

Remarks		Concentration of Ni relative to entire wire (wt.%)	Thickness of Pd coating layer (μm)	Thickness of Au sputter layer (μm)	Concentration of each element relative to entire wire				Concentration of each element in Cu alloy core material		Wire diameter (μm)
					B conc. (wt.ppm)	In conc. (wt.ppm)	Ca conc. (wt.ppm)	P conc. (wt.ppm)	Pt conc. (wt.%)	Pd conc. (wt.%)	
Comparative Example	1	0.05	0.010	*	*	*	*	*	*	*	20
Comparative Example	2	0.05	0.110	*	*	*	*	*	*	*	20
Comparative Example	3	0.05	0.010	*	*	*	*	*	*	*	20
Comparative Example	4	1.30	0.120	*	*	*	*	*	*	*	20
Comparative Example	5	0.80	0.160	*	*	*	*	*	*	*	20

[0045] (Method of Evaluation)

5 The bonding reliability was determined by manufacturing a sample for bonding reliability evaluation, followed by evaluating the bonding longevity of the ball bonded part when exposed to a high-temperature and high humidity environment.

10 [0046] The sample for bonding reliability evaluation was manufactured by performing ball bonding onto an electrode, which has been formed by forming an alloy of Al-0.5%Cu as a film with a thickness of 1.0 μm on a Si substrate on a general metallic frame, using a commercially available wire
15 bonder and sealing it with a commercially available epoxy resin. A ball was formed while flowing an $\text{N}_2 + 5\%\text{H}_2$ gas at a flow rate of 0.4 to 0.6 L/min, and its size was a diameter of a range from 34 to 36 μm .

[0047] The manufactured sample for bonding reliability
20 evaluation was exposed to a high-temperature and high-humidity environment of a temperature of 150°C and a relative humidity of 85% using an unsaturated type pressure cooker tester. A shear test on the ball bonded part was performed every 100 hours, and a time until a value of
25 shear strength became half of the initial shear strength was determined to be the bonding longevity of the ball bonded part. The shear test after the high-temperature and high-humidity test was carried out after removing a resin by acid treatment and exposing the ball bonded part.

[0048] A tester manufactured by DAGE was used for a shear tester. An average value of measurement values on 10 ball bonded parts randomly selected was used for the value of the shear strength. In the above evaluation, the bonding longevity being less than 1500 hours was determined to be practically problematic to be marked with a symbol of "triangle," being 1500 to 2000 hours was determined to be practically no problem to be marked with a symbol of "circle," being 2000 hours or more was determined to be especially excellent to be marked to with a symbol of "double circle" in the column "High-temperature and high-humidity test" in Tables 3-1, 3-2 and 4.

[0049] For the evaluation of ball formability, a ball before performing bonding was collected and observed, and there were evaluated the presence or absence of voids on a surface of the ball and the presence or absence of deformation of the ball, which is primarily a perfect sphere. The occurrence of any of the above was determined to be faulty. The formation of the ball was performed while an $N_2+5\%H_2$ gas was blown at a flow rate of 0.4 to 0.6 L/min in order to reduce oxidation in a melting process. The size of the ball was 26, 32 and 38 μm . For one condition, 30 balls were observed. An SEM was used for the observation. In the evaluation of the ball formability, a case where three or more failures occurred was determined to be problematic to be marked with a symbol of "triangle," a case of one or two failures was determined to be no problem to be marked with a symbol of "circle," and a case where no failure occurred was determined to be excellent to be marked with a symbol of "double circle" in the column "Ball formability" in Tables 3-1, 3-2 and 4.

[0050] The evaluation of wedge bondability on the wire bonded part was determined by performing 1,000 pieces of

bonding on leads of a lead frame and evaluating by the occurrence frequency of peeling of the bonded part. An Fe-42 at.% Ni alloy lead frame plated with 1 to 3 μm Ag was used for the lead frame. In this evaluation, assuming more rigorous bonding conditions than normal, a stage temperature was set to be 150°C, which was lower than a generally set temperature range. In the above evaluation, a case where six or more failures occurred was determined to be problematic to be marked with a symbol of "triangle," a case of one to five failures was determined to be no problem to be marked with a symbol of "circle," and a case where no failure occurred was determined to be excellent to be marked with a symbol of "double circle" in the column "Wedge bondability" in Tables 3-1, 3-2 and 4.

[0051] The evaluation of a crushed shape of the ball bonded part was determined by observing the ball bonded part from immediately above after bonding and evaluating by its sphericity. For an object to be bonded with the bonding wire, an electrode in which an Al-0.5 % Cu alloy was formed as a film with a thickness of 1.0 μm on a Si substrate was used. The observation was performed using an optical microscope, and 200 sites were observed for one condition. Being elliptic with large deviation from a perfect circle and being anisotropic in deformation were determined to be faulty in the crushed shape of the ball bonded part. In the above evaluation, a case where six or more failures occurred was determined to be problematic to be marked with a symbol of "triangle," being one to five was determined to be no problem to be marked with a symbol of "circle," and a case where a favorable perfect circle was obtained for all was determined to be especially excellent to be marked with a symbol of "double circle" in

the column "Crushed shape" in Tables 3-1, 3-2 and 4.

[0052] The evaluation of a loop formability was determined based on linearity and variation in height. The forming condition of loop was a loop length of 2 mm and a maximum height of 80 μm . The maximum height of loop was a distance from an electrode surface of ball bonded part to a topmost height of wire. For the evaluation of linearity, 50 bonding wires were observed for one condition using a scanning electron microscope. A case where a maximum gap between an axis that connects a ball bonded part and a wire bonded part with straight line and a bonding wire was less than 45 μm was determined to be good, and a case of 45 μm or more was determined to be faulty. For the evaluation of variation in height, 50 bonding wires were observed for one condition using a scanning electron microscope and an average height was calculated. A case where a deviation from average value was less than 15 μm was determined to be good, and a case of 15 μm or more was determined to be faulty. In the above evaluation, a case where six or more failures of any of linearity and variation in height occurred was determined to be problematic to be marked with a symbol of "triangle," a case of one to five failures was determined to be no problem to be marked with a symbol of "circle," and a case where no failure occurred was determined to be excellent to be marked with a symbol of "double circle" in the column "Loop formability" in Tables 3-1, 3-2 and 4.

[0053] [Table 3-1]

Remarks		High-temperature and high-humidity test (Temp.: 150°C; Relative humidity: 85%)	Ball formability			Wedge bondability	Crushed shape	Loop formability
			Ball diameter φ26 μm	Ball diameter φ32 μm	Ball diameter φ38 μm			
Example	1	○	◎	◎	◎	○	○	○
Example	2	○	◎	◎	◎	○	○	○
Example	3	○	◎	◎	◎	○	○	○
Example	4	○	◎	◎	◎	○	○	○
Example	5	○	◎	◎	◎	○	○	○
Example	6	○	◎	◎	◎	○	○	○
Example	7	○	◎	◎	◎	○	○	○
Example	8	○	◎	◎	◎	○	○	○
Example	9	○	◎	◎	◎	○	○	○
Example	10	◎	◎	◎	◎	◎	○	○
Example	11	◎	◎	◎	◎	◎	○	○
Example	12	◎	◎	◎	◎	◎	○	○
Example	13	◎	◎	◎	◎	◎	○	○
Example	14	◎	◎	◎	◎	◎	○	○
Example	15	◎	◎	◎	◎	◎	○	○
Example	16	◎	◎	◎	◎	◎	○	○
Example	17	◎	◎	◎	◎	◎	○	○
Example	18	◎	◎	◎	◎	◎	○	○
Example	19	◎	◎	◎	◎	◎	○	○
Example	20	◎	◎	◎	◎	◎	○	○
Example	21	◎	◎	◎	◎	◎	○	○
Example	22	○	◎	◎	◎	○	◎	○
Example	23	○	◎	◎	◎	○	◎	○
Example	24	○	◎	◎	◎	○	◎	○
Example	25	○	◎	◎	◎	○	◎	○
Example	26	○	◎	◎	◎	○	◎	○
Example	27	○	◎	◎	◎	○	◎	○
Example	28	◎	◎	◎	◎	◎	◎	○
Example	29	◎	◎	◎	◎	◎	◎	○
Example	30	◎	◎	◎	◎	◎	◎	○
Example	31	◎	◎	◎	◎	◎	◎	○
Example	32	◎	◎	◎	◎	◎	◎	○
Example	33	◎	◎	◎	◎	◎	◎	○
Example	34	◎	◎	◎	◎	◎	◎	○
Example	35	◎	◎	◎	◎	◎	◎	○
Example	36	◎	◎	◎	◎	◎	◎	○
Example	37	◎	◎	◎	◎	◎	◎	○
Example	38	◎	◎	◎	◎	◎	◎	○
Example	39	◎	◎	◎	◎	◎	◎	○
Example	40	○	◎	◎	◎	○	◎	○
Example	41	○	◎	◎	◎	○	◎	○
Example	42	◎	◎	◎	◎	◎	◎	○
Example	43	◎	◎	◎	◎	◎	◎	○
Example	44	○	◎	◎	◎	○	◎	○
Example	45	○	◎	◎	◎	○	◎	○

[0054] [Table 3-2]

Remarks		High-temperature and high-humidity test (Temp.: 150°C; Relative humidity: 85%)	Ball formability			Wedge bondability	Crushed shape	Loop formability
			Ball diameter $\phi 26 \mu\text{m}$	Ball diameter $\phi 32 \mu\text{m}$	Ball diameter $\phi 38 \mu\text{m}$			
Example	46	◎	◎	◎	◎	◎	◎	○
Example	47	◎	◎	◎	◎	◎	◎	○
Example	48	○	◎	◎	◎	○	◎	○
Example	49	○	◎	◎	◎	○	◎	○
Example	50	◎	◎	◎	◎	◎	◎	○
Example	51	◎	◎	◎	◎	◎	◎	○
Example	52	○	◎	◎	◎	○	○	◎
Example	53	○	◎	◎	◎	○	○	◎
Example	54	○	◎	◎	◎	○	○	◎
Example	55	○	◎	◎	◎	○	○	◎
Example	56	◎	◎	◎	◎	◎	○	◎
Example	57	◎	◎	◎	◎	◎	○	◎
Example	58	◎	◎	◎	◎	◎	○	◎
Example	59	◎	◎	◎	◎	◎	○	◎
Example	60	◎	◎	◎	◎	◎	○	◎
Example	61	◎	◎	◎	◎	◎	○	◎
Example	62	◎	◎	◎	◎	◎	○	◎
Example	63	◎	◎	◎	◎	◎	○	◎
Example	64	◎	◎	◎	◎	◎	◎	◎
Example	65	◎	◎	◎	◎	◎	◎	◎
Example	66	○	◎	◎	◎	○	○	◎
Example	67	○	◎	◎	◎	○	○	◎
Example	68	◎	◎	◎	◎	◎	○	◎
Example	69	◎	◎	◎	◎	◎	○	◎
Example	70	◎	◎	◎	◎	◎	◎	◎
Example	71	◎	◎	◎	◎	◎	◎	◎
Example	72	○	◎	◎	◎	○	○	○
Example	73	○	◎	◎	◎	○	○	○
Example	74	○	◎	◎	◎	△	◎	○
Example	75	◎	◎	◎	◎	△	○	○
Example	76	◎	◎	◎	◎	△	◎	○
Example	77	○	◎	◎	◎	○	○	○
Example	78	○	◎	◎	◎	△	◎	○
Example	79	○	◎	◎	◎	○	○	○
Example	80	○	◎	◎	◎	△	◎	○
Example	81	○	◎	◎	◎	○	○	○
Example	82	○	◎	◎	◎	△	◎	○
Example	83	○	◎	◎	◎	○	○	○
Example	84	○	◎	◎	◎	△	○	◎
Example	85	◎	◎	◎	◎	◎	○	○
Example	86	◎	◎	◎	◎	△	○	◎
Example	87	○	◎	◎	◎	○	○	○
Example	88	○	◎	◎	◎	△	○	◎
Example	89	◎	◎	◎	◎	◎	○	○
Example	90	◎	◎	◎	◎	△	○	◎
Example	91	○	◎	◎	◎	○	○	○
Example	92	○	◎	◎	◎	△	◎	○
Example	93	◎	◎	◎	◎	△	○	○
Example	94	◎	◎	◎	◎	△	◎	○

[0055] [Table 4]

Remarks		High-temperature and high-humidity test (Temp.: 150°C; Relative humidity: 85%)	Ball formability			Wedge bondability	Crushed shape	Loop formability
			Ball diameter φ26 μm	Ball diameter φ32 μm	Ball diameter φ38 μm			
Comparative Example	1	△	△	△	△	○	○	△
Comparative Example	2	△	⊗	⊗	⊗	○	○	△
Comparative Example	3	△	△	△	○	○	○	○
Comparative Example	4	○	△	△	△	○	○	○
Comparative Example	5	○	△	△	△	○	○	○

[0056] (Evaluation Results)

5 The bonding wires according to Examples 1 through 94 each include a Cu alloy core material and a Pd coating layer formed on the surface of the Cu alloy core material, and the bonding wire contains Ni, the concentration of Ni is 0.1 to 1.2 wt.% relative to the entire wire, and the

10 thickness of the Pd coating layer is 0.015 to 0.150 μm. It has been revealed that with this configuration the bonding wires according to Examples 1 through 94 can achieve a good bonding reliability and excellent ball formability. In contrast, for Comparative Examples 1 through 4, the

15 concentration of Ni was out of the above range; and for Comparative Example 5, the thickness of the Pd coating layer was out of the above range. Therefore, there were not achieved sufficient effects in a bonding reliability and ball formability for Comparative Examples.

20 [0057] In Examples 10 through 21, 28 through 39, 42, 43, 46, 47, 50, 51, 56 through 65, 68 through 72, 75, 76, 85, 86, 89, 90, 93 and 94, it has been revealed that excellent bonding reliability can be obtained because they further include an Au skin layer on the Pd coating layer. In

25 Examples 10 through 21, 28 through 39, 42, 43, 46, 47, 50, 51, 56 through 65, 68 through 71, 85 and 89, it has been revealed that further excellent wedge bondability can be obtained because a thickness of the Au skin layer is 0.0005

to 0.050 μm .

[0058] In Examples 22 through 51, 64, 65, 70, 71, 74, 76, 78, 80, 82, 92 and 94, it has been revealed that crushed shape of ball bonded part with excellent circularity can be
5 achieved because the Cu alloy core material further contains at least one element selected from B, In, Ca, P and Ti, and a concentration of the elements is 3 wt. ppm or more relative to the entire wire.

[0059] In Examples 52 through 71, it has been revealed
10 that good loop formability can be obtained because the Cu alloy core material further contains Pt or Pd and a concentration of Pt or Pd contained in the Cu alloy core material is 0.05 to 1.20 wt.%. In Examples 83, 85, 87 and 89, excellent loop formability was not obtained because the
15 concentration of Pt or Pd was less than the lower limit of the above range. In Examples 84, 86, 88 and 90, excellent loop formability was obtained but wedge bondability decreased because the concentration of Pt or Pd exceeded the upper limit of the above range.

CLAIMS

1. A bonding wire for a semiconductor device comprising:
a Cu alloy core material; and
5 a Pd coating layer formed on a surface of the Cu alloy
core material, wherein
the Cu alloy core material contains Ni,
a concentration of Ni is 0.1 to 1.2 wt.% relative to
the entire wire, and
10 a thickness of the Pd coating layer is 0.015 to 0.150
μm.
2. The bonding wire for a semiconductor device according
to claim 1, further comprising an Au skin layer on the Pd
15 coating layer.
3. The bonding wire for a semiconductor device according
to claim 2, wherein a thickness of the Au skin layer is
0.0005 to 0.050 μm.
20
4. The bonding wire for a semiconductor device according
to any one of claims 1 to 3, wherein
the Cu alloy core material further contains at least
one element selected from B, In, Ca, P and Ti, and
25 a concentration of the elements is 3 to 100 wt. ppm
relative to the entire wire.
5. The bonding wire for a semiconductor device according
to any one of claims 1 to 4, wherein
30 the Cu alloy core material further contains Pt or Pd,
and
a concentration of Pt or Pd contained in the Cu alloy
core material is 0.05 to 1.20 wt.%.

6. The bonding wire for a semiconductor device according to any one of claims 1 to 5, wherein Cu is present at an outermost surface of the bonding wire.

5

10

15

20

25

30