

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
10 November 2005 (10.11.2005)

PCT

(10) International Publication Number
WO 2005/105362 A1

(51) International Patent Classification⁷: **B23K 31/02**,
33/00, F16L 13/02

(21) International Application Number:
PCT/SE2005/000572

(22) International Filing Date: 20 April 2005 (20.04.2005)

(25) Filing Language: Swedish

(26) Publication Language: English

(30) Priority Data:
0401139-1 30 April 2004 (30.04.2004) SE

(71) Applicant (for all designated States except US): **SAND-
VIK INTELLECTUAL PROPERTY AB** [SE/SE]; S-811
81 Sandviken (SE).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **ÖHNGREN, Claes**
[SE/SE]; Prästgårdsgatan 13 B, S-752 30 Uppsala (SE).

(74) Agent: **MELIN, Linda**; Sandvik AB, Intellectual Prop-
erty, S-811 81 Sandviken (SE).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA,
MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM,
PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY,
TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU,
ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO,
SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN,
GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: METHOD FOR JOINING DISPERSION-STRENGTHENED ALLOY

(57) **Abstract:** The present invention relates to a method for joining two or more components and/or construction parts, at least one of which consists of a dispersion-strengthened alloy having the following composition (in % by weight): C up to 0,08 Si up to 0,7 Cr 10-25 Al 1-10 Mo 1,5-5 Mn up to 0,4 balance Fe as well as normally occurring impurities by the fact that the cross section in the joint is enlarged by forging before joining and where the product manufactured according to the method can be used in high-temperature applications at temperatures above 900 °C.



WO 2005/105362 A1