

TITLE OF INVENTION

GOLF BALL IMMERSION INDICATOR



166166

BACKGROUND OF THE INVENTION

G00002

As indicated in the September, 1996 issue of "Golf Digest", hitting golf balls into the water occurs with a great degree of frequency. As a result, an entire industry has developed in the recovery of golf balls which are then resold despite the fact that the ball has spent a fair amount of time in the water. While the golf ball cover seems to be fairly impervious, the question has become as to the effect of the immersion of the ball over a number of days at the bottom of a pond laying in the mud.

As will be appreciated, golf balls come in two varieties, a three-piece ball and a two-piece ball. According to the above article, when such balls were tested using a robotic hitting machine and a standard length metal driver with a 9.53 degree loft and an extra stiff shaft, with a club head speed 93.7 miles per hour and a launch angle of 90 degrees and with a spin rate of 2,800 rpm, the result for a three-piece ball was a difference in carry of 6 yards after an eight day immersion, a 12 yard loss after three months a 15 yard loss after six months.

For a two-piece ball, the amount of carry was 6 yards shorter and after having been immersed for eight days, and an additional 3.3 yards after three months, for a total of 9.1 yards. While for two-piece balls being in the water typically makes the ball harder in terms of compression, it also slows down the coefficient of restitution or the ability of the ball to regain its roundness after impact. The above factors make the ball fly shorter. Three-piece balls have been found to get softer in terms of compression, but they also fly shorter according to the above-mentioned article.

Whatever the results of the immersion of a golf ball in a pond, the characteristics of the ball in flight are altered by

the immersion. The problem therefore becomes one of being able to determine when a golf ball has been immersed so that it may be rejected in favor of a new golf ball.

Note that golf ball construction is shown in the following U.S. patents: 5,609,953; 5,586,950; 5,538,794; 5,496,035; 5,480,155; 5,415,937; 5,314,187; 5,096,201; 5,006,297; 5,002,281; 4,690,981; 4,984,803; 4,979,746; 4,955,966; 4,931,376; 4,919,434; 4,911,451; 4,884,814; 4,863,167; 4,848,770; 4,792,141; 4,715,607; 4,714,253; 4,688,801; 4,683,257; 4,625,964; 4,483,537; 4,436,276; 4,431,193; 4,266,772; 4,065,537; 3,784,209; 3,572,722; 3,264,272.

SUMMARY OF INVENTION

In order to alleviate the problem of having to deal with balls which may have been immersed and recovered, in the subject invention a golf ball is provided which changes color or has some other indicia which changes after immersion to indicate that the ball has been immersed.

In the present invention, in one embodiment, encapsulated dyes are utilized as a means of creating a golf ball which irreversibly changes its color when it is exposed to water for long periods of time. The invention is thus used as an indicator of balls previously exposed to water for one to several days in the bottom of a lake, pond, pool or other body of water. Such an indicator is used to alert golfers to potential changes in ball properties due to long water exposure times.

In one embodiment, the composition of the golf ball is that of traditional two or three piece golf balls. A two piece golf ball is one with a solid rubber core and an outer shell made from a hard resin such as an ionomer resin. Three piece balls are those consisting of a solid or liquid core material, a wound

or molded rubber outer core, and an in ionomer or polybutadiene or poly trans isoprene rubber shell referred to as balata ball. In both cases, in one embodiment, the encapsulated dye is included in an overcoating of polymer resin containing the dye encapsulant, followed by a final gloss coating. Alternatively, the dye may be blended, either directly or in an encapsulated form, with the golf ball balata or ionomer shell and a single gloss coating may be added. In both cases, diffusion of water through the gloss coating, followed by diffusion through the encapsulant overcoating or the shell, initiates slow diffusion of a water soluble dye from the microencapsulated particles. The water soluble dye gradually colors the ionomer or polybutadiene shell, leaving a permanently stained ball. The time frame for diffusion may be tailored by adjusting the thickness of the polymer film coatings and the type and size of the polymer microencapsulant, dye and the gloss coatings used.

BRIEF DESCRIPTION OF THE DRAWINGS

These and other features of the subject invention will be better understood when taken in conjunction with the Detailed Description the Drawings of which;

Figure 1 is a diagrammatic illustration of a golfer hitting a golf ball into a water hazard;

Figure 2 is a diagrammatic illustration of the ball of Figure 1 after immersion in water, showing a visual indicator that the ball has been immersed in water for an extended period of time;

Figure 3 is a diagrammatic illustration of a two piece ball which provides a visual indicator of elongated water immersion in which the ball includes a solid rubber core and a hard molded shell of an ionomer or ionomer blend such as Surlyn or a similar appropriate polymer resin, with the ball being provided with a

conformal overcoat polymer dispersion containing encapsulated dye particles that goes over the shell or mantle of the ball, and with this overcoat then being covered with a final gloss coat containing no dye particles to maintain a high gloss finish and provide an additional diffusion barrier on the ball to prevent dye release in humid or moist environments;

Figure 4 is a diagrammatic illustration of a three piece ball which provides a visual indication of elongated water immersion in which the ball includes a solid, liquid or gel, a wound rubber band or molded rubber outer core and a shell of a glossy rubbery material such as balata rubber, polybutadiene blends or low shore hardness ionomer and an additional overcoat layer of polymer/encapsulated dye underneath the gloss final coat;

Figure 5 is a schematic diagram depicting diffusion of water into the ball when it is immersed in a body of water for long time periods;

Figure 6 is a diagrammatic representation of an encapsulated dye particle; and,

Figure 7 is a diagrammatic illustration of another type two piece golf ball.

DETAILED DESCRIPTION

Referring now to Figure 1, in a typical situation, a ball 10 has been hit by a golfer 12 into a water hazard 13, where it resides until it is plucked out either by the golfer or by a company which retrieves golf balls from water hazards. It will be appreciated that, as mentioned before, such balls when immersed for a long period of time lose their flight characteristics, and regardless of their being washed and resold, will not regain these characteristics due to the immersion.

In order to provide an indicator of golf balls that have been immersed in water for some time, and referring now to Figure 2, it can be seen that golf ball 10 is provided with a mottled appearance 15, which serves as an indicator that the ball has been immersed in water.

It is this or some other indicator which is water activated that provides a convenient method for the purchaser of a golf ball to ascertain that the ball is in fact a used ball and one which has been immersed in water for some time or has been subjected to some other predetermined condition.

As will be described, in one embodiment this distinctive discoloration or indication is provided through the utilization of water soluble inks or dyes which are activated through the infusion of water into encapsulated dye particles in one embodiment. The result of the infusion of water is that the dye particles emit their dyes to mark the golf ball in some distinctive manner. Whether it is with dyes or inks which are water soluble or are released upon water activation, it is immaterial as to what type of indication is given so long as the golfer purchasing the golf ball can ascertain that it is in fact one that has been immersed in water or is otherwise unsuitable for play.

It is noted that controlled release technology is a well-proven means of slowly delivering a small amount of a compound over a given time period or at a specific time based on a desired stimulus. In the subject invention controlled release technology is used as an approach to the slow color change of a golf ball in water. The subject invention, in one embodiment, involves the use of inks or dyes which are micro-encapsulated with a thin polymer coating to form small particles or beads. These micro-capsules, which may vary in size from tens of microns to millimeters, can be incorporated into a hard, glassy polymer coating material such as polymethyl methacrylate or

polyvinyl acrylate ester, which can act as a gloss coat for the ball, or the encapsulant can be incorporated into the rubber or ionomer cover of the ball itself.

A microencapsulant is a polymer coating used to enclose a liquid or solid material within a small particle. Microencapsulants are generally in the range of tens to hundreds of microns in diameter. Encapsulation approaches have been used for a number of applications in which a compound must be slowly but systematically released to an environment under the desired conditions. Examples include microcapsules in drug delivery, vitalizing nutrients or proteins in time release cosmetic products and fertilizers or pesticides for agricultural products.

The polymer coating may consist of a broad range of potential polymeric materials and polymer blends. The basis for most controlled release technology is the slow diffusion of the encapsulated product through the polymer coating or matrix and into the surrounding environs. The driving force for diffusion is mass transfer from the highly concentrated interior to the dilute exterior regions. The diffusion process is often accelerated or activated by the presence of a solvent that swells or partially solvates the polymer film, thus plasticizing the polymer film and increasing the effective diffusivity of the polymer matrix. The result is a faster rate of transport of the encapsulated material out of the microcapsule.

A second route to controlled release systems is the slow dissolution of an uncrosslinked or linear polymer coating in a good solvent, resulting in the release of the encapsulated compound as the coating walls become thinner and ultimately dissolve completely. In this case, the dissolution rate of the polymer, rather than the diffusion rate alone, is the rate determining step in the release of the encapsulant.

A third approach to the controlled release of a material is macro-encapsulation. In this case, the material is slowly released from a continuous polymer matrix, which may be molded into any number of shapes or objects. The primary difference between this approach and that of microencapsulation is that in the latter, the material is enclosed in well defined microspheres on the order of magnitude of several microns, whereas in macroencapsulation, the material of interest is directly enclosed in an object of the order of magnitude of centimeters and greater. Both of these approaches involve the slow diffusion of the material out of the matrix or the encapsulant shell.

Referring now to Figure 3, in one embodiment of the subject invention a conventional two piece ball 10 with a solid rubber core 12 is illustrated having a hard molded shell 14 of an ionomer blend such as Surlyn, or a similar polymer resin. As can be seen, a conformal overcoat polymer dispersion 16 contains encapsulated dye particles 18, with the dispersion going over the shell or mantle of the ball.

This overcoat is then covered with a final gloss coat 20 containing no dye particles to maintain a high gloss finish and provides an additional diffusion barrier on the ball to prevent dye release in humid or moist environments.

Likewise, for a three piece ball as illustrated in Figure 4, the three piece ball 30 is provided with a solid, liquid or gel inner core 32, a wound rubber band or molded rubber outer core 34 and a shell 36 of glossy rubber material such as balata rubber, polybutadyne blends or low shore hardness ionomer.

Note that an additional overcoat layer 36 of polymer/encapsulated dye is formed underneath the final gloss coat 38.

Referring to Figure 5 and as will be described, a schematic diagram depicts the diffusion of water 50 into ball 10 when it is immersed in a body of water for a long period of time. Water

molecules slowly diffuse as illustrated at 51 into the ball through gloss overcoat 52. In some cases, dye capsules 54 in layer 56 will exist close to the gloss overcoat and away from the shell here illustrated at 58. Water will permeate these capsules first and will then take longer to diffuse to capsules in the bulk of the layer 56. The water will slowly seep into or solvate the microencapsulant allowing controlled diffusion of a water soluble dye out of the polymer microcapsule and gloss overcoat 52, staining the overcoat. Over time, water will diffuse across the layer into the ionomer shell 58 where the ionomer resin will permanently absorb the dye resulting in a deep color change.

A number of different polymers and blends of polymers may be used for microencapsulation coating, including polymethyl methacrylate, polymethacrylic acid, polyacrylic acid, polyacrylates, polyacrylamide, polyacryldextran, polyalkyl cyanoacrylate, cellulose acetate, cellulose acetate butyrate, cellulose nitrate, methyl cellulose and other cellulose derivatives, nylon 6,10, nylon 6,6, nylon 6, polyterephthalamide and other polyamides, polycaprolactones, polydimethylsiloxanes and other siloxanes, aliphatic and aromatic polyesters, polyethylene oxide, polyethylene-vinyl acetate, polyglycolic acid, polylactic acid and copolymers, poly(methyl vinyl ether/maleic anhydride), polystyrene, polyvinyl acetate phthalate, polyvinyl alcohol, polyvinylpyrrolidone, shellac, starch and waxes such as paraffin, beeswax, carnauba wax. Polymers used should have a near zero diffusivity of the ink through the polymer matrix in the absence of water. Upon the introduction of water in the surrounding matrix and the subsequent diffusion of water through the polymer film, the diffusivity of the polymer coating for the dye molecules increases, allowing transport of the dye across the polymer film. The ideal polymer systems for this application are those which have a limited

permeability to water and thus provide a longer range of diffusion times before releasing the water soluble dye. Such polymers could be crosslinked or uncrosslinked blends of a hydrophobic and a hydrophilic polymer, segmented or block copolymer films with a hydrophilic block or polymers which are not soluble in water, but have a small but finite affinity for water. Such polymers include nylons such as nylon 6,10 or nylon 6, polyacrylonitrile, polyethylene terephthalate (PET), polyvinyl chloride. More water permeable polymers which may be blended with hydrophobic polymers to adjust the dye and water permeability coefficients of the film include cellulose derivatives, polyacrylates, polyethylene oxides, polydimethyl siloxane and polyvinylalcohol.

Dyes that may be used should be water-soluble and may vary from a broad range of industrial dye materials. Ideally, the dye should be compatible with the polymer used for the shell or mantle underneath the dye-encapsulant coating. Ionic and a number of water soluble dyes would be particularly compatible with ionomer materials commonly used in such mantles due to the presence of carboxylate and carboxylic acid groups in the polymer. Some dye systems change color in the presence of more polar solvents. This effect may be useful if the dye has very little color until exposed to water. Some potential dyes for this application might include merocyanine dyes and pyridinium-N-phenoxide dyes. Examples may include Naphthalene Orange G, Crystal Violet, CI Disperse Red and a number of other common industrial dyes. Dyes of larger molecular weight may be desirable as higher molecular weight dyes diffuse more slowly through a polymer matrix.

Prior to water exposure, the water-soluble dye is enclosed by a rigid solid polymer film, which is immersed in a nonaqueous medium, with a very low driving force and a high resistance to diffusion through the coating. As shown in Figure 5, on

exposure to water for long time periods, water will slowly diffuse into polymer layer 56 and thence, through microcapsule 60 to dye particle 62 as shown in Figure 6. The diffusion of the dye out of layer 56 can be modeled using basic mass transfer laws. Note, the rate at which dye diffuses out of the capsule is shown in Figure 6 to be related to R_{out} and R_{in} for a dye capsule 60 which encapsulates a dye particle 62. Fick's first law is commonly used to model the diffusion process. At steady state, the mass transfer of dye from the microcapsule can be modeled using the equation below:

$$\frac{dM}{dt} = 4\pi D K \Delta C \frac{R_o R_i}{(R_o - R_i)}$$

where dM/dt is the rate of transfer of dye with time, D is the diffusivity of the dye in the polymer layer, K is the solubility of the dye in the layer, C is the concentration difference of the dye in the microcapsule versus the exterior capsule, R_o is the outer diameter and R_i is the inner diameter of the capsule. For a microcapsule that is 50 microns in diameter, with an inner diameter of 45 microns, and thus a wall thickness of 5 microns, the time for diffusion of half of the dye through a polymer film such as nylon could range from ten to one hundred hours, depending on the relative solubility of the dye in the matrix. The diffusion times can be tailored using various polymers or polymer blends, as well as different materials. Processing the techniques, including the use of a thin secondary top coating layer of pure polymer containing no particles, can control the distribution of ink microparticles to prevent the immediate release of ink from microparticles that may be located at the surface of the ball.

The formation of microcapsules may be done using a number of technologies. These technologies include polymer coacervation/phase separation using the agitation of colloidal suspensions of

insoluble polymer and subsequent isolation of microparticles in a nonaqueous medium. Polyamide and some polyester and polyurethane coatings may be formed using interfacial polymerization, using stabilizers to form stabilized microemulsions. Bead suspension polymerization techniques, again using nonaqueous nonsolvent medium, may be used for a number of polymers achieved through free radical polymerization of vinyl polymers such as polyacrylates or acetates, or copolymers. It may be necessary to "hide" the color of the dye in the microencapsulant if the polymer coating is very transparent. In this case, the incorporation of white pigment in the polymer coating wall can be introduced during the encapsulation process.

After the dye microcapsules are prepared at the desired size and film thickness, the particles may be stored under a desiccator, and dried under a vacuum with desiccant at least 24 hours prior to formulation with a polymer film to form an overcoat. The polymer medium for the overcoat can be a traditional gloss coating material such as a polyurethane or polyacrylate. Diffusion limitations of water to the particles will vary with the choice of polymer medium for both the overcoat and gloss coat. Preferred materials may include polyurethanes, polymethyl methacrylate, polyethyl methacrylate, polybutadiene and various polyvinyls. The particles must be blended in the polymer overcoat film under dry conditions with a humidity of 50% or lower, at loadings of 1 to 30%. The conditions of dispersion may be at temperatures below the flow temperature of microsphere polymer coating, or in an overcoat polymer-solvent mixture with a solvent that cannot dissolve the microsphere polymer coating. Alternatives include the use of crosslinked microspheres, which cannot dissolve or flow under heat, or the use of a crosslinkable liquid monomer or prepolymer. The overcoating can be dip coated or spraycoated

onto the ball and cured. A second gloss coating containing no particles may then be applied to the ball. The coating thicknesses of the overcoat and gloss should approximate the thickness of traditional gloss coatings used on conventional golf balls.

Example 1

In one configuration, the golf ball can be a two piece golf ball consisting of a wound rubber core and a thick Surlyn ionomer cover containing TiO₂ powder and blue as a brightener. Then a translucent coating containing dye particles can be applied. This coating will consist of a soluble nylon, polyester, PET or other barrier coating blended with 5% of dye encapsulant material. If the encapsulated form of the dye is colored, some TiO₂ may be added to this layer to ensure whiteness is preserved. Finally, a final gloss coating will be added to the outer layer. The layers important to color change in the ball are the two outermost layers, which should be approximately 100 microns, or 0.1 mm, in thickness.

In the first embodiment, the dye used is a common water soluble dye, Nile Blue. This dye is a crystalline material at room temperature and is available as a granular powder containing crystals that are 20 to 40 microns in size. These solid crystals are hard and non-porous and small enough that when dispersed in a matrix at low concentrations, there will be no detected color change. The individual dye particles would be encapsulated with a gelatin coating using gelatin coacervation in an organic solvent to prevent water solubilization of the dye molecules; procedures for coacervation are well-known, and have been used in drug encapsulation and in the cosmetics and agricultural industries for many years. The encapsulated dye would then be isolated and added in a 1% by mass concentration

to a polymeric gloss coating such as a polyurethane or polyester gloss coat. The two piece Surllyn coated ball would be dip-coated with the gloss coat resin which would then be dried during a solvent removal process using heat and/or air flow; the overcoat layer should be approximately 100-200 microns thick. A second layer of gloss coating such as polyurethane could then be added using a spray-coating method. This second layer would be added to provide one additional barrier to moisture and to ensure an even gloss coating. The thickness of the gloss coating should be approximately 100 microns thick.

The resulting ball would thus contain a water-soluble dye encapsulated in thin film barrier. Permeation of water through a 100 micron thick polymer film such as a polyurethane with a DK or diffusivity times solubility of 60 m²/sec-Pa would result in a diffusion half time for water of approximately 10 to 12 hours. The water would then be able to access the dye particles in the second layer containing dye encapsulant. The time for permeation of water through the gel encapsulant, assuming an inner radius of 40 microns and an outer radius of 50 microns, for a typical gelatin encapsulant, would be on the order of 5 to 6 hours, resulting in a color change after exposure to water of 16 to 18 hours, or essentially overnight. The time for permeation may be increased by using encapsulants or gloss barrier coatings with lower permeabilities. A nylon based overcoating would result in diffusion half-times approximately 100 times longer and the color change would then take place over the period of 100 to 160 hours or several days.

Example 2

A second embodiment involves the use of a dye particle encapsulated in a water-soluble polymer such as polyethylene oxide or poly acrylic acid, by formation of a mixture of hard dye particles in a fluid prepolymer. The prepolymer could be, for example, a water soluble polyacrylamide resin with a temperature activated initiator and bisacrylamide crosslinker agent. The mixture would be added dropwise to an incompatible organic solvent such as toluene with an emulsifying agent such as polyvinyl alcohol with stirring at high speeds. The emulsified drops are polymerized when the emulsion is heated, and the resulting beads contain dye particles. This process can be adjusted to produce dye beads in varying sizes. 100 micron sized beads would be produced for this application. The resulting beads should not be colored because the bead formation process is done in the absence of water under controlled conditions. The resulting beads are then isolated, and added in 1% by weight to a polyurethane gloss coating followed by a second barrier gloss coating. In this case, dye diffusion would be dependent solely on the thickness of the outer barrier coating. Once water reaches the dye particles, the polyacrylamide beads would swell, and dye diffusion through the polyacrylamide beads would be very rapid, resulting in the release of a very strong dye in the golf ball overcoating. As described in the first embodiment, diffusion through a barrier gloss coat could range from 10 to 100 hours depending on the polymer chosen for the coating. Polymers of choice include polyurethanes and nylons such as Nylon 6,6, Nylon 6 and Nylon 6,10.

Example 3

In a third embodiment, a colorless compound called a color former is used. Color formers are converted to strong dyes when exposed to a developer. The developer is a slightly acidic clay or resin which absorbs or dissolves the color former and results in a colored dye. This technology is extremely well developed and has been used for thermal printing, electrochromic printing, pressure sensitive (carbonless copy paper) industries. Colors achieved with these dyes include very deep black and blue shades that would be easily recognized against a white golf ball.

In this invention, the developer would be mixed in the gloss resin along with encapsulated particles containing the color former. Water diffusion would activate the developer, and water and developer would diffuse into the microparticle containing the color former. The resulting dye would then be released from the microparticle. In this example, a common color former known as Crystal Violet Lactone, which goes from colorless to blue in the presence of the developer, is encapsulated in a nylon microcapsule using interfacial polymerization.

In the polymerization process, the color former, which is organic and non-water soluble, is contained in an organic phase with a diacid chloride which is then contacted with a diamine in aqueous solution containing a weak base. The resulting emulsified droplets become microparticles for the carbonless copy paper industry and is well documented. A gloss resin can then be formulated to contain a commercially available color developer. A common developer is bisphenol A, which is cheap and fairly easy to process. A second choice which is a more effective developer and thus requires smaller quantities, but is more expensive, is zinc salicylate. Both compounds can be added to the encapsulant containing inner coating in small quantities - 1 to 5 wgt. %.

The water diffusion process will involve the solubilization of the water soluble developer. The water then acts as a carrier of the developer and delivers it via diffusion to the colorformer in the microparticles. The dye is then converted to a colored water soluble dye, which can diffuse out of the microparticle to produce a colored ball. For this example, the diffusion rates are dependent on the thickness of a second, barrier coating of polyurethane or nylon, which regulates the speed with which water reaches the first color former microparticles which again can be adjusted from 10 to 100 hours. The intensity or effectiveness of the system may be improved by putting the developer in this outer coating, while the encapsulated color former remains in the inner coating.

All of the above examples involve the formation of a two layer gloss coating on the golf ball. The resulting release of dye from the inner layer will result in the coloration of the gloss coat and the underlying golf ball cover. The described invention may be used for detection of water absorption in two or three piece golf balls.

The processing steps required to manufacture golf balls are varied depending on the manufacturer and the final properties of the ball desired. This invention involves modification of the final finishing process steps in the manufacture of the golf ball. The application of the primer, label and the gloss coat are replaced by:

1. Application of primer on the golf ball cover
2. Application of company logo or label
3. dip-coating of gloss coat with encapsulant particles onto ball
4. drying/solvent removal and/or cure of encapsulant containing gloss coat
5. spray coating of second gloss coat
6. drying or cure of second gloss coat

Spinning or air flow may be used to dry the first coat and ensure a uniform coating. The thickness of the second coat should be fairly well controlled to ensure the appropriate amount of time before color change is activated.

A golf ball has thus been described which contains dye particles which are activated by the presence of water, resulting in a color change marker which effectively destroys the appearance of the ball, alerting the consumer to balls which have been exposed to water for inordinate amounts of time, and the potential for poor ball performance.

Example 4

The above describes the incorporation of dyes into an intermediate coating between the gloss coat and the golf ball cover. A different approach would involve the incorporation of dye into the golf ball cover itself. In this embodiment, illustrated in Figure 7, dye 60 may be incorporated into the ionomer ball cover of a two piece golf ball 62 as a solid particle or as an encapsulated dye. Here the ball has a core 64 and a shell 66 which acts as a cover. Dyes which exist as solid, crystalline dye particles that are 10 to 40 microns in diameter. If such dyes can be compounded with the ionomer at temperatures below the dye melt point, the dye particles should remain suspended in the polymer matrix without adversely coloring the ball. Upon absorption of water into the ionomer cover, the dye would immediately begin to dissolve, producing a splotchy, colored appearance in the ball cover. In this case, the golf ball gloss coating 68 is the primary barrier to water, and as water permeates the gloss coating and begins to diffuse into the ball shell or cover 66, color change will occur. The use of an encapsulated dye could be used to obtain better

control of the discoloration process. The dye encapsulant used would have to be chosen to withstand the compounding conditions of the ionomer ball.

Having now described a few embodiments of the invention, and some modifications and variations thereto, it should be apparent to those skilled in the art that the foregoing is merely illustrative and not limiting, having been presented by the way of example only. Numerous modifications and other embodiments are within the scope of one of ordinary skill in the art and are contemplated as falling within the scope of the invention as limited only by the appended claims and equivalents thereto.

WHAT IS CLAIMED IS:

1. A water immersion indicating golf ball which changes appearance upon water immersion to indicate that otherwise invisible characteristics of said golf have been altered due to said immersion, comprising:

materials providing said golf ball with predetermined characteristics of play including weight, size, spherical symmetry, overall distance, initial velocity, and other flight characteristics conforming to golf ball characteristic standards; and,

a water activated material introduced in solid, liquid, or gaseous form within or onto said golf ball and subject to infusion of water into said ball due to the water permeability of said ball's materials thereof which changes appearance to indicate that the performance characteristics of said ball have been altered due to said immersion, whereby otherwise playable gold balls retrieved from water hazards can be identified as having altered performance characteristics due to the immersion thereof.

2. A golf ball, comprising:

one or more layers of construction, and a material provided in liquid, solid, or gaseous form between, on or in any of said layers which causes a change in appearance to said ball upon the presence of water without changing the shape of said ball.

3. The golf ball of claim 1, wherein said cover includes balata.

4. The golf ball of claim 1, wherein said cover includes rubber.

5. The golf ball of claim 1, wherein said cover includes a synthetic material.

6. The golf ball of claim 1, wherein said core includes a crosslinkable elastomer.
7. The golf ball of claim 6, wherein said elastomer is polybutadiene rubber.
8. The golf ball of claim 1, wherein said core includes a synthetic material.
9. The golf ball of claim 1, wherein said water-activated material includes a dye.
10. The golf ball of claim 1, wherein said water-activated material is microencapsulated.
11. The golf ball of claim 1, wherein said water-activated material includes an ink.
12. The golf ball of claim 1, wherein said water-activated material includes a multi-part system that, upon water infusion, results in a chemical reaction to produce color.
13. A golf ball, comprising:
- a core,
 - a water insoluble, water permeable cover over said core; and,
 - a water soluble material between said core and said cover which changes color upon the presence of water.

14. The golf ball of claim 13, wherein said cover includes an ionomer resin.
15. The golf ball of claim 13, wherein said cover includes balata.
16. The golf ball of claim 13, wherein said cover includes rubber.
17. The golf ball of claim 13, wherein said cover includes a synthetic material.
18. The golf ball of claim 13, wherein said core includes a crosslinkable elastomer.
19. The golf ball of claim 18, wherein said elastomer is polybutadiene rubber.
20. The golf ball of claim 13, wherein said core includes a synthetic material.
21. The golf ball of claim 13, wherein said water-activated material includes a dye.
22. The golf ball of claim 13, wherein said water-activated material is microencapsulated.
23. The golf ball of claim 13, wherein said water-activated material includes an ink.

20/1
21

24. The golf ball of claim 13, wherein said water-activated material includes a multi-part system that, upon water infusion, results in a chemical reaction to produce color.

25. A golf ball, comprising:

a core,

a water insoluble, water permeable cover; and,

a water soluble material at said cover which changes color upon the presence of water.

26. The golf ball of claim 25, wherein said cover includes an ionomer resin.

27. The golf ball of claim 25, wherein said cover includes balata.

28. The golf ball of claim 25, wherein said cover includes rubber.

29. The golf ball of claim 25, wherein said cover includes a synthetic material.

30. The golf ball of claim 25, wherein said core includes a crosslinkable elastomer.

31. The golf ball of claim 30, wherein said elastomer is polybutadiene rubber,

32. The golf ball of claim 25, wherein said core includes a synthetic material.

10/7
22

12 MAR 2012

33. The golf ball of claim 25, wherein said water-activated material includes a dye.

34. The golf ball of claim 25, wherein said water-activated material is microencapsulated.

35. The golf ball of claim 25, wherein said water-activated material includes an ink.

36. The golf ball of claim 25, wherein said water-activated material includes a multi-part system that, upon water infusion, results in a chemical reaction to produce color.

37. A golf ball, comprising:
a core,
a water insoluble, water permeable cover, and,
a water soluble material at said core which changes color upon the presence of water.

38. The golf ball of claim 37, wherein said cover includes an ionomer resin.

39. The golf ball of claim 37, wherein said cover includes balata.

40. The golf ball of claim 37, wherein said cover includes rubber.

29/3
SHEET

41. The golf ball of claim 37, wherein said cover includes a synthetic material.
42. The golf ball of claim 37, wherein said core includes a crosslinkable elastomer.
43. The golf ball of claim 42, wherein said elastomer is polybutadiene rubber.
44. The golf ball of claim 37, wherein said core includes a synthetic material.
45. The golf ball of claim 37, wherein said water-activated material includes a dye.
46. The golf ball of claim 37, wherein said water-activated material is microencapsulated.
47. The golf ball of claim 37, wherein said water-activated material includes an ink.
48. The golf ball of claim 37, wherein said water-activated material includes a multi-part system that, upon water infusion, results in a chemical reaction to produce color.

49. A golf ball comprising:

a core,

a water insoluble, water permeable cover, and,

a water-activated material on said cover which changes color upon presence of

water.

50. The golf ball of claim 49, wherein said cover includes an ionomer resin.

51. The golf ball of claim 49, wherein said cover includes balata.

52. The golf ball of claim 49, wherein said cover includes rubber.

53. The golf ball of claim 49, wherein said cover includes a synthetic material.

54. The golf ball of claim 49, wherein said core includes a crosslinkable elastomer.

55. The golf ball of claim 54, wherein said elastomer is polybutadiene rubber.

56. The golf ball of claim 49, wherein said core includes a synthetic material.

57. The golf ball of claim 49, wherein said water-activated material includes a dye.

58. The golf ball of claim 49, wherein said water-activated material is microencapsulated.

59. The golf ball of claim 49, wherein said water-activated material includes an ink.

60. The golf ball of claim 49, wherein said water-activated material includes a multi-part system that, upon water infusion, results in a chemical reaction to produce color.

61. A water immersion indicating golf ball which changes appearance upon water immersion to indicate that otherwise invisible characteristics of said golf ball have been altered due to said immersion, comprising:

a core;

a water insoluble cover over said core for providing said golf ball with predetermined characteristics of play including weight, size, spherical symmetry, overall distance and initial velocity conforming to golf ball characteristic standards, said cover having a predetermined water permeability; and,

a water activated material within said golf ball and subject to infusion of water into said cover due to the water permeability thereof which changes appearance to indicate that the performance characteristics of said ball have been altered due to said immersion, whereby otherwise playable golf balls retrieved from water hazards can be identified as having altered characteristics due to the immersion thereof.

29/p
x