

5

Sintering Powder

The invention relates to a sintering powder, a sintering paste and film comprising the sintering powder, and a
10 sintered joint formed using the same.

Sintered joints provide an alternative to soldered joints. A typical method of forming a sintered joint involves placing a metal powder, often in the form of a powder compact,
15 between two work pieces to be joined and then sintering the metal powder. The resulting atomic diffusion of the metal atoms forms a bond between the two work pieces.

Metal nanopowders have been used to form sintered joints in
20 the electronics industry, and are considered to be useful alternatives to lead-free soldering. The differing behaviour between nanomaterials and the corresponding bulk material is thought to be due to nanomaterials having a higher surface-to-volume ratio.

25

Sintering powders containing silver nanoparticles are known. Sintered joints formed by atomic diffusion of silver nanoparticles can be processed at a temperature significantly lower than the melting temperature of the bulk
30 and can also be used for high temperature applications. The potential advantages, such as high temperature stability, high electrical and thermal conductivity, and good

mechanical properties, make such sintering powders promising candidates for die attachment applications. However, the sintering temperatures of such sintering powders are still too high for effective use in most electronics applications.

5

Sintering temperatures may be reduced by applying an external pressure during sintering. Pressure-assisted low-temperature sintering of silver paste has been shown to be a viable alternative to solder reflow as a die-attachment method. The application of high pressure has been shown to significantly lower the sintering temperature, and the desired properties for die attachment can be achieved at a relatively faster rate resulting in the formation of a sintered joint within a few minutes. However, a large external pressure makes automation of the process difficult. Furthermore, application of a large external pressure may result in damage to the work pieces.

10

15

20

25

30

It is known to dispense solder paste for a variety of applications, but mostly as an alternative when wave solder or screen printing is not possible. Solder paste can be dispensed on a variety of surface mount applications on printed circuit boards, integrated circuit packages, and electrical component connectors. Typical problems of solder paste include: dripping, skipped dots, and inconsistent dispensing. Soft and hard solders are typically used in the electronic industries for die attached and dispensing. The soft solders are susceptible to fatigue failure under thermal cycling conditions. On the other hand, hard solders and glass matrix composites are used to enable devices to run at higher junction temperatures, but their higher elastic moduli and processing temperatures can generate high

mechanical stresses in devices, and these materials also have relatively low thermal and electrical conductivities.

5 The present invention seeks to tackle at least some of the problems associated with the prior art or at least to provide a commercially acceptable alternative solution thereto.

10 The present invention provides a sintering powder comprising:

a particulate having a mean longest diameter of less than 10 microns, wherein at least some of the particles forming the particulate comprise a metal at least partially coated with a capping agent.

15 Each aspect or embodiment as defined herein may be combined with any other aspect(s) or embodiment(s) unless clearly indicated to the contrary. In particular, any features indicated as being preferred or advantageous may be combined
20 with any other feature indicated as being preferred or advantageous.

The term "sintering powder" as used herein may encompass a powder capable of forming a sintered joint. Sintered joints
25 are formed by atomic diffusion of metal particles placed between two work pieces to be joined. The term "sintering powder" may encompass a particulate. The sintering powder may comprise regular shaped particles (such as, for example, spheres) or irregular shaped particles (such as, for
30 example, whiskers, plates, rods or flakes).

The term "capping agent" as used herein may encompass a species that, when present on the surface of metal particles, reduces agglomeration of the metal particles, enables particle size control during powder production and
5 reduces particles' surface oxidation or other contamination.

The inventors have surprisingly found that the sintering powder as described herein may be sintered at low temperatures with the application of only very low pressure,
10 typically substantially no pressure. As a result, formation of a sintered joint between work pieces using the sintering powder may occur with reduced damage to the work pieces. In addition, since the application of high pressures is not required, the formation of a sintered joint is simplified,
15 and may be more easily automated.

Advantageously, the use of a capping agent may help to reduce agglomeration of the particles making up the particulate. Such agglomeration is unfavourable, since it
20 may increase the sintering temperature of the sintering powder. Accordingly, the use of a capping agent enables the formation of a sintered joint between work pieces at lower temperatures and, therefore, may help to reduce damage to a work piece caused by exposure to high sintering
25 temperatures. In addition, the use of a capping agent may help to avoid degradation of the metal such as, for example, damage caused by exposure of the metal to air.

The particulate has a mean longest diameter of less than 10
30 microns. Typically most of the particles forming the particulate have a longest diameter less than 10 microns, more typically substantially all of the particles forming

the particulate have a longest diameter of less than 10 microns. When the particles forming the particulate are spherical, the longest diameter will be the diameter of the sphere. When the particles forming the particulate are
5 irregularly shaped, the longest diameter will be the longest dimension of the particle.

Since the particulate has a mean longest diameter of less than 10 microns, the particles forming the particulate
10 exhibit a high surface-to-volume ratio. Such a high surface-to-volume ratio is particularly desirable since it may serve to decrease the sintering temperature of the sintering powder. The mean longest diameters referred to herein may be calculated using X-ray diffraction using Scherrer's formula.

15

In the sintering powder described herein at least some of the particles forming the particulate comprise a metal at least partially coated with a capping agent. Typically, the majority of particles forming the particulate comprise a
20 metal at least partially coated with a capping agent, more typically substantially all of the particles forming the particulate comprise a metal at least partially coated with a capping agent. Typically the metal is substantially coated with a capping agent, more typically completely coated with
25 a capping agent. Increasing the coverage of the capping agent on the metal particles may help to further reduce the agglomeration of the metal particles and, therefore, further reduce the sintering temperature.

30 At least some of the particles forming the particulate comprise a metal. The particles may all comprise the same metal. Alternatively, some of the particles may comprise

different metals. In addition, individual particles may comprise two or more different metals. The term "metal" as used herein may encompass alloys. Accordingly, the particles may comprise one or more alloys of one or more metals.

5

During the sintering process, heating melts or chemically decomposes the capping agent and breaks molecular bonds between the metal atoms and the capping agent. Metal particles then begin to sinter.

10

The capping agent may be inorganic and/or organic. Examples of organic capping agents include polymers and ligands. Preferably the capping agent comprises an amine and/or a carboxylate functional group. Such capping agents may form a weak bond with the metal particles. Accordingly the temperature required to break the bonding may be reduced, which may help to reduce the sintering temperature. Capping agents that comprise an amine functional group are particularly preferred in this regard.

20

Preferably the capping agent comprises straight chain alkylamine (C6 to C18) or a branched chain aliphatic alkylamine. One preferred example is octylamine. Octylamine forms a particularly weak bond with metal particles. In addition, octylamine is particularly effective at reducing agglomeration of metal particles.

25

30

Preferably the particulate has a mean longest diameter of from 1 to 100 nm, more preferably from 5 to 75 nm, even more preferably from 5 to 65 nm. Such mean longest diameters may be particularly effective at providing a high surface-to-volume ratio. Particulates having a mean longest diameter

smaller than 1 nm may be difficult to handle and may also be more susceptible to degradation.

The particulate may have a mean longest diameter of from 100
5 nm to 10 microns, preferably from 600 nm to 1 micron. Larger
particle sizes may require less capping agent, typically
substantially no capping agent. Accordingly, due to the
reduction in residual organics in the resulting joint, the
resistivity is much lower. In one aspect of the present
10 invention, the particulate has a mean longest diameter of
from 100 nm to 10 microns, preferably from 600 nm to 1
micron, and does not contain capping agent.

When the particulate has a mean longest diameter in the
15 ranges specified above, typically most of the particles
forming the particulate have a longest diameter within the
range, more typically substantially all of the particles
forming the particulate have a longest diameter within the
range.

20 The particulate typically exhibits heterogeneous particles
sizes. For example, the difference between the mean longest
diameter of the largest 10 % of the particles and mean
longest diameter of the smallest 10 % of the particles may
25 be greater than 20 nm, typically greater than 30 nm, even
more typically greater than 60 nm, still even more typically
from 60 to 150 nm. The heterogeneous particle sizes may help
to reduce the sintering temperature of the sintering powder,
presumably due to the large point of contact between the
30 particles. In addition, such heterogeneous sizes may help to
increase the packing fraction.

The metal preferably comprises silver or an alloy thereof. Silver has excellent electrical and thermal conductivity, and is therefore capable of forming a sintered joint with high electrical and/or thermal conductivity. Accordingly,

5 the use of silver metal makes the sintering powder particularly suitable for use in electronics applications, such as die attachment and microelectronic packaging. Alternatively, the metal may comprise other metals such as, for example, copper and gold.

10

The sintering powder preferably comprises up to 5 wt% capping agent, more preferably from 0.1 to 3 wt% capping agent, even more preferably about 1 wt% capping agent. If the sintering powder comprises more than 5 wt% capping agent, then higher temperatures may be required to melt the capping agent prior to sintering. If the sintering powder comprises less than 0.1 wt% capping agent, then the capping agent may not adequately cover the surface of the metal. This may result in an increase in agglomeration of the particles and, therefore, an increase in the sintering temperature.

20

The particulate preferably comprises a first type of particles having a longest diameter of from 1 to 100 nm and a second type of particles having a longest diameter of from greater than 100 nm to 50 microns. The presence of the second type of particles, having larger diameters, increases the contact points of the particles forming the particulate. This may result in better sintering and also an improved morphology of the powder. Accordingly, the thermocycling properties of a joint formed using such a powder are improved. In addition, the larger second type of particles

25

30

typically do not require a capping agent. Accordingly, the total amount of capping agent in the sintering powder may be reduced, thereby minimising the existence of residual organics in any formed joint. As a result, the

5 thermoconductivity and high temperature properties, such as thermocycling, are improved.

The first type of particles preferably have a diameter of from 5 to 75 nm and/or the second type of particles have a

10 diameter of from greater than 100 nm to 20 microns, more preferably from 600 nm to 1 micron.

The particulate preferably comprises from 81 to 99 wt% of the first type of particles and from 1 to 19 wt% of the

15 second type of particles, more preferably from 85 to 95 wt% of the first type of particles and 5 to 15 wt% of the second type of particles. Such ranges are particularly suitable for providing the combination of improved thermoconductivity and thermocycling properties, and low sintering temperature. In

20 a preferred embodiment, the particulate comprises about 90 wt% of the first type of particles and about 10 wt% of the second type of particles.

In a particularly preferred embodiment, the sintering powder

25 comprises:

a particulate having a mean longest diameter of from 1 to 100 nm,

wherein at least some of the particles forming the particulate comprise silver at least partially coated with a

30 straight chain or branched chain aliphatic amine, preferably octylamine.

In a further aspect, the present invention provides a sintered joint formed using the sintering powder as described herein. Such a sintered joint may exhibit particularly high strength and/or particularly high electrical and thermal conductivity. Furthermore, the sintered joint may exhibit very little change in shear strength following thermal shock, typically substantially no change in shear strength.

- 10 In a further aspect the present invention provides a sintering paste comprising:
- the sintering powder as described herein;
 - a binder;
 - a solvent; and
 - 15 optionally a rheology modifier and/or an activator and/or a surfactant.

The paste may be printable and/or dispensable and/or jettable and/or pin transferable. The paste may have viscosity and flow characteristics particularly favourable for dispensing, meaning that the paste may be used as a one-to-one replacement for solders.

The binder and/or solvent are typically selected so that they are able to be removed from the paste (for example by evaporation and/or burn out) at a temperature below the targeted sintering temperature of the sintering powder. This may help to promote near complete sintering of the metal particles. When organic material remains in the joint during sintering, inadequate sintering of the metal particles may occur. This may result in a weak sintered joint.

The binder may serve to bind the paste together so that it is easier to handle and position accurately in the location of a desired sintered joint. Examples of suitable binders include, but are not restricted to,

- 5 hydroxypropylmethylcellulose, triacetin and polyvinyl acetate. Preferably the binder comprises an epoxy-based resin. Epoxy-based resin may be particularly effective at binding the paste together so that the paste is easier to handle and may be easier to position accurately in the
- 10 location of a desired sintered joint. Furthermore, the use of epoxy resin may result in the formation of a stronger joint prior to sintering, meaning that there is no requirement to hold together the work pieces to be joined prior to sintering. The use of epoxy resin is particularly
- 15 advantageous when the capping agent comprises an amine functional group. In this case, the amine acts as a hardener forming a cross-linked structure. This may result in a particularly strong joint prior to sintering.
- 20 The solvent preferably comprises a monoterpene alcohol and/or a glycol and/or glycol ether, preferably terpineol and/or triethylene glycol. Monoterpene alcohol and/or a glycol may be particularly effective at dispersing the metal particles within the paste, resulting in a homogeneous
- 25 distribution of metal particles in the matrix of organic components with reduced cluster aggregation and/or agglomeration. The use of monoterpene alcohol and/or a glycol may serve to increase the flow-ability and printer-ability of the sintering paste.

A rheology modifier may be added to control the viscosity of the paste. Examples of suitable rheology modifiers include, but are not restricted to, Thixcin R and Crayvallac Super.

- 5 An activator may be added to remove any metal oxide that may be present from the surface being printed and/or to remove any oxides that may be present in the sintering powder. Aryl or alkyl carboxylic acids may be used as activators, such as, for example, one or more of adipic acid, succinic acid
10 and glutaric acid.

- A surfactant may be added to the sintering paste to help disperse the sintering powder in the sintering paste. Examples of suitable surfactants include, but are not
15 restricted to, Disperbyk 163 and TritonX 100.

The sintering paste preferably comprises:

- from 1 to 15 wt% binder; and/or
- from 1 to 15 wt% solvent; and/or
- 20 up to 1 wt% rheology modifier; and/or
- up to 1 wt% activator; and/or
- up to 6 wt% surfactant.

- Binder and/or solvent contents within these ranges may help
25 to provide the sintering paste with particularly desirable flow-ability and printer-ability. Preferably the sintering paste comprises from 5 to 8 wt%, binder. In one embodiment the sintering paste comprises about 6.5 wt% binder. Preferably the sintering paste comprises from 5 to 8 wt%,
30 solvent. In one embodiment the sintering paste comprises about 6.5 wt% solvent. The sintering paste may comprise at

least 0.1 wt% rheology modifier and/or at least 0.1 wt% activator and/or at least 0.1 wt% surfactant.

In a further aspect the present invention provides a

5 sintering paste comprising:

the sintering powder as disclosed herein;

an organosilver compound;

a solvent; and

10 optionally an activator and/or rheology modifier and/or surfactant.

During sintering, the organosilver compound may break down to metallic silver, which may increase the thermal conductivity of the sintered joint. In addition, the

15 presence of the organosilver compound increases the wetting of the paste to the joint interface. The organosilver compound may comprise one or more of silver oxalate, silver lactate, silver citrate, silver peroxide, silver neodecanoate, silver succinate and silver stearate. In some
20 embodiments, the organosilver compound may be omitted.

The sintering paste preferably further comprises one or more fatty acids, such as, for example, stearic acid, neodecanoic acid and lauric acid. The presence of fatty acids helps to
25 bind the paste together. In other words, the presence of a fatty acid avoids the need for a separate binder, such as the epoxy based resin binder discussed above. Accordingly, the total amount of organics in the paste is less, resulting in a stronger final joint.

30

The sintering paste preferably further comprises a peroxide. Examples of suitable peroxides include, but are not

restricted to, hydrogen peroxide, tertiary-butyl hydroperoxide and tertiary-butyl peroxy-2-ethylhexanoate. Peroxide introduces oxygen into the paste, which may aid sintering of the paste beneath the die area in a die attach
5 method. The oxygen may also enable sintering of the metal particles under an inert atmosphere, such as, for example, a nitrogen atmosphere. The sintering paste preferably comprises up to 3 wt.% hydrogen peroxide, preferably from 0.5 to 2 wt.% hydrogen peroxide, more preferably from 0.7 to
10 1.8 wt.% hydrogen peroxide. Liquid peroxides are preferred to control rheology and silver settling.

The sintering paste may comprise a film forming agent such as, for example, a polyamide.
15 Preferably the sintering paste is substantially resin free, more preferably completely resin free. The presence of resin may reduce the thermal and electrical conductance of the silver. The solvent may comprise propylene carbonate.

20 The sintering paste preferably comprises:
from 1 to 15 wt% solvent; and/or
up to 50 wt% organosilver compound, preferably from 1 to 25 wt%, more preferably from 2 to 10 wt%, even more
25 preferably from 3 to 9 wt%; and/or
up to 1 wt% rheology modifier; and/or
up to 1 wt% activator; and/or
up to 6 wt% surfactant.

30 The sintering paste may comprise at least 0.1 wt% rheology modifier and/or at least 0.1 wt% activator and/or at least 0.1 wt% surfactant.

In a further aspect the present invention provides a sintering film comprising the sintering powder as described herein and a binder. The film may be applied at the wafer level, die level, package/substrate level, and/or module level. Such a film may be obtained, for example, by printing the sintering paste as described herein onto a polyester sheet, heating the paste to at least partially remove the solvent and form a film, and then removing the film from the polyester sheet. The film as described herein is especially advantageous since it can be transferred on the die by simply pressing the die on to the film at slightly elevated temperature. Transferred film is an alternate application method, beneficially offered in certain situations.

15

In a further aspect the present invention provides the use of the sintering powder as described herein or the sintering paste or film as described herein in a method selected from: die attachment (e.g. chip-to-board, chip-to-substrate, chip-to-heat sink, chip-to-fixture), wafer-to-wafer bonding (e.g. chip-to-heat sink), reflective layer printing, hermetic and near hermetic sealing (for example for packages and perimeter seals), the production of interconnect lines (for example circuitry, pads), via filling in semiconductor devices and substrates, and flip-chip and wafer bumping.

20
25

In a further aspect the present invention provides a method of manufacturing a sintered joint comprising the steps:

providing the sintering powder as described herein or the sintering paste or film as described herein in the vicinity of two or more work pieces to be joined; and

30

heating the sintering powder or sintering paste or film to at least partially sinter the metal.

Advantageously, the heating step may be carried out at atmospheric pressure. The sintering powder or sintering paste or film may be placed in the vicinity of the workpiece under low pressure (typically 1-5 MPa for 0.1 to 60 seconds at a temperature of about 175 to 250 °C).

- 10 The heating step is preferably carried out at a temperature of at least 140 °C, more preferably from 150 to 350 °C, even more preferably from 160 to 300 °C. Temperatures lower than 140 °C may not result in adequate sintering of the particles in the sintering powder and/or may not result in adequate removal of the organics by evaporation and/or burn out. 15 Temperatures higher than 350 °C may result in damage to the work pieces.

- In a further aspect the present invention provides a method of manufacturing the sintering powder as described herein comprising the steps:

- providing a metal salt solution;
contacting the metal salt solution with a capping agent; and
25 precipitating metal particles at least partially coated with the capping agent.

- The precipitated metal particles may be recovered from the solvent, for example by filtering. An example of the metal salt solution is a metal nitrate solution. 30

The precipitating step may be carried out using a reducing agent. Reducing agents are particularly effective at causing precipitation of the metal particles. Particularly suitable reducing agents include, for example, hydrazine (e.g.

5 hydrazine hydrate) and sodium borohydride.

Excess of the capping agent may be washed off using a polar solvent such as, for example, methanol or acetone.

10 The invention will now be described in relation to the following non-limiting Figures, in which:

Figure 1 shows TEM micrographs of a sintering powder of the present invention.

15 Figure 2 shows histograms of the particles sizes of a sintering powder of the present invention.

Figure 3 shows a powder X-ray diffraction pattern of a sintering powder of the present invention.

20

Figure 4 shows a thermogram of a sintering powder of the present invention.

25 Figure 5 shows the results of differential scanning calorimetry (DSC) analysis of a sintering powder of the present invention.

30 Figure 6 shows the topology of a printed sintering paste of the present invention. The paste has a height of from 80 to 90 μm . There are no flat deposits, no dog-ears and no undulations.

Figure 7 shows cross-sections of a joint formed between a Si die and a substrate using a sintering paste of the present invention. The images indicate good adhesion of the sintered paste to the metallization of the die as well as the substrate.

Figure 8 shows a wet and a free standing dry film of the present invention together with the morphology of the film.

Figure 9 shows Keyance microscope images of the topology of dispensed paste according to the present invention: dots (left hand side), pattern (right hand side).

Figure 10 shows Koh Young images of dispensed paste according to the present invention: typical image of dispensed dots (left hand side), volume measurement (right hand side).

The invention will now be described in relation to the following non-limiting examples.

Example 1 - preparation of sintering powder

The sintering powder was prepared in a single phase reaction. A 3 M ethylene glycol solution of silver nitrate was prepared by adding silver nitrate to ethylene glycol and stirring at 0 to 5 °C until the solution became clear. The solution was then made to 0.3 M by adding a mixture of 50 % toluene and 50 % ethanol. The silver nitrate solution (0.3 M, 3.5 liter) was then added to a toluene solution of octylamine (3.5 kg, 27.07 moles), which was prepared by adding octylamine to toluene at room temperature. 262.5g

(0.998 M, 5.24 moles) of 80 % hydrazine hydrate dissolved in N,N dimethyl formamide was then immediately added. The reaction mixture was stirred for 45 minutes at a speed of 350 rpm before being allowed to settle for few a minutes.

- 5 The colorless supernatant solution was then pumped out and the silver nanoparticles, which had settled at the bottom of the tank, were transferred to a Buchner funnel and washed with methanol to remove excess octylamine. Finally, the powder was washed with acetone and dried under vacuum at
10 room temperature. The yield of the reaction was around 98 %.

TEM micrographs of the powder were obtained and are shown in Figure 1. The micrographs indicate silver nanoparticles heterogeneous in size ranging from 5 to 60 nm. Furthermore,
15 the micrographs appear to indicate the distribution of very small particles around the larger grains. The distribution of the particles sizes is shown in Figure 2 and appears to be bimodal.

- 20 Figure 3 shows the powder X-ray diffraction pattern of the powder and indicates a face-centred cubic structure. Using the Scherrer formula, the mean particle size was calculated to be around 25 nm. This particle size was confirmed by the use of a particle size analyser (Microtrac Nanotrac Ultra
25 NPA 253) which indicated a D50 of around 20 nm.

The powder was subjected to thermogravimetric analysis (TGA) and the corresponding thermogram is shown in Figure 4. The results indicate that the powder comprises approximately 1
30 wt% capping agent, i.e. octylamine.

The sintering temperature of the powder was analysed using differential scanning calorimetry (DSC) and the results are shown in Figure 5. The plot indicates a sintering temperature of 195.2 °C with a specific heat of 36.7 J/g.

5

Example 2 - preparation of sintering paste

3 g of epoxy resin was added to 40 g of the powder of Example 1. It was then mixed in an orbital mixer at 1000 rpm. To the mixture, 3 g of solvent mixture (1.5 g of terpeneol and 1.5 g of triethylene glycol) was added and mixed in an orbital mixer at 1000 rpm. After mixing it was milled in a three roll mill for a few minutes to provide a homogeneous paste. The composition of the paste is shown in Table 1.

10
15

Component	Weight %
Silver	86.96
Resin	6.52
Solvent mixture	6.52

20

Table 1: Composition of the paste

The tackiness, viscosity and thermal conductivity of the paste were measured and the results are shown in Table 2. The tackiness was measured in a Rhesca tackiness tester tac (II) using Japanese Industrial Standard (JIS). The paste was printed on a microscopic glass side using a 10 mil stencil of three circular openings. The immersion speed of the probe was 120mm/min and a test speed of 600mm/min was used with a press time of 0.2 seconds. The viscosity of the paste was measured using a Brookfield DVIII ultra programmable

25

30

rheometer (Spindle CP51). The thermal conductivity was measured using a Netzsch LFA 447 Nanoflash. Thermal conductivity K was calculated using the following formula:

$$K = \alpha \rho c_p$$

where α is the thermal diffusivity (m^2/s), ρ is the density of the material (kg/m^3) and c_p is the specific heat capacity ($\text{J}/\text{kg}\cdot\text{K}$). The tackiness, viscosity and thermal conductivity values for Examples 3, 4, 12 and 26 were measured in a similar manner.

Tackiness (JIS)	105 -125 gf
Viscosity (2rpm)	170 (± 15) (Pa-s)
Thermal conductivity	80 W/m K

Table 2: Properties of the paste

Example 3

4g of epoxy resin was added to 40g of the powder of Example 1. It was then mixed in an orbital mixer at 1000rpm. 4g of terpeneol was then added and mixing in the orbital mixer at 1000rpm was continued. After mixing the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

Component	Weight %
Silver	83.34

Resin	8.33
Terpineol	8.33

5

Table 3: Composition of the paste

Tackiness (JIS)	120 -140 gf
Viscosity (5rpm)	40 (± 10) (Pa-s)

10

Table 4: Properties of the paste

Example 4

8g of epoxy resin and 6.67g of terpineol were mixed
 15 thoroughly so as to obtain a homogeneous solution, which was
 then added to 40g of powder of Example 1. It was then mixed
 in an orbital mixer at 1000rpm. To the mixture, 4g of
 terpineol was added and mixed in an orbital mixer at
 1000rpm. After mixing, the mixture was milled in a three
 20 roll mill for few minutes to obtain a homogenous paste.

25

Component	Weight %
Silver	73.17
Resin	14.63
Terpineol	12.20

Table 5: Composition of the paste

Tackiness (JIS)	170 -220 gf
Viscosity (5rpm)	30 (± 10)

	(Pa-s)
--	--------

Table 6: Properties of the paste

Example 5

5

2.5g of epoxy resin, 3.4g of solvent mixture (1.7g of
 terpineol and 1.7g of triethylene glycol) and 0.1g of
 cryvallac super were mixed thoroughly to obtain a
 homogeneous solution, which was then added to 40g of powder
 of Example 1. It was then mixed in an orbital mixer at
 1000rpm. After mixing, the mixture was milled in a three
 roll mill for a few minutes to obtain a homogenous paste.

10

15

Component	Weight %
Silver	86.96
Resin	5.43
Solvent mixture	7.4
Rheology modifier	0.21

20

Table 7: Composition of the paste

25 Example 6

2.7g of epoxy resin, 3g of solvent mixture (1.5g of
 terpineol and 1.5g of triethylene glycol) and 0.3g of
 succinic acid were mixed thoroughly to obtain a homogeneous
 solution, which was then added to 40g of powder of Example
 1. It was then mixed in an orbital mixer at 1000rpm. After

30

mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

5

Component	Weight %
Silver	86.96
Resin	5.86
Solvent mixture	6.52
Activator	0.66

10

Table 8: Composition of the paste

Example 7

15

2.6g of epoxy resin, 3g of solvent mixture (1.5g of terpineol and 1.5g of triethylene glycol), 0.3g of succinic acid and 0.1g of cryvallac super were mixed thoroughly and added to 40g of powder of Example 1. Mixing was then carried out in an orbital mixer at 1000rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

20

25

Component	Weight %
Silver	86.96
Resin	5.65
Solvent mixture	6.52
Rheology modifier	0.21
Activator	0.66

30

Table 9: Composition of the paste

Example 8

5

40g of the powder of Example 1, 2.88g of epoxy resin and 0.25g of Disperbyk163 were mixed in orbital mixer at 1000rpm. 2.88g of solvent mixture (propylene glycol, methyl digol and terpineol) was then added. After mixing, the

10 mixture was milled in a three roll mill for few minutes to obtain a homogenous paste.

Composition	Weight %
Silver	86.94
Resin	6.26
Disperbyk163	0.54
Propylene glycol	1.565
Methyl digol	1.565
Terpineol	3.13

Table 10: Composition of paste

15

Example 9

40g of the powder of Example 1, 2.88g of epoxy resin and 0.25g of TritonX 100 were mixed in orbital mixer at 1000rpm.

20 2.88g of solvent mixture (propylene glycol, methyl digol and terpineol) was then added. After mixing, the mixture was milled in a three roll mill for few minutes to obtain a homogenous paste.

Composition	Weight %
-------------	----------

Silver	86.94
Resin	6.26
TritonX100	0.54
Propylene glycol	1.565
Methyl digol	1.565
Terpineol	3.13

Table 11: Composition of paste

Example 10

5

40g of the powder of Example 1, 2.88g of epoxy resin and 0.25g of Disperbyk163 were mixed in orbital mixer at 1000rpm. 2.88g of solvent mixture was then added. After mixing, the mixture was milled in a three roll mill for few minutes to obtain a homogenous paste.

10

Composition	Weight %
Silver	86.94
Resin	6.26
Disperbyk 163	0.54
Glycolic ester	3.13
Terpineol	3.13

Table 12: Composition of paste

15 Example 11

40g of the powder of Example 1, 2.93g of epoxy resin, 0.25g of Disperbyk163 and 0.125g of hydroxypropylmethylcellulose were mixed in orbital mixer at 1000rpm. 3.7g of solvent mixture (terpineol and triacetin) was then added. After

20

mixing, the mixture was milled in a three roll mill for few minutes to obtain a homogenous paste.

Composition	Weight %
Silver	85.1
Resin	6.22
Disperbyk 163	0.53
Hydroxypropylmethylcellulose	0.27
Triacetin(Plastiziser)	3.94
Terpineol	3.94

5

Table 13: Composition of paste

Example 12

40g of the powder of Example 1, 2.35g of epoxy resin, 0.46g of Disperbyk163 and 0.46g of polyvinyl acetate were mixed in orbital mixer at 1000rpm. 3.72g of solvent mixture (propylene glycol, methyl digol and terpineol) was then added. After mixing, the mixture was milled in a three roll mill for few minutes to obtain a homogenous paste.

15

Composition	Weight %
Silver	85.1
Resin	5.0
Disperbyk 163	1.0
Polyvinyl acetate	1.0
Propylene glycol	1.97
Methyl digol	1.97

Terpineol	3.96
-----------	------

Table 14: Composition of paste

The properties of the paste are set out in Table 14.

5

Specific Heat	0.413 J/g/K
Thermal diffusivity	48.1 mm ² /s
Thermal conductivity	88.7 W/m/K
Volume resistivity	2.8x10 ⁻⁵ Ω cm

10

Table 15: Properties of paste (volume resistivity measured using four probe method)

15

The tackiness and viscosity of the paste were measured at regular intervals to observe the stability of the paste, and the results are set out in Table 15. The results indicate that the paste is stable for 25 days at room temperature and pressure.

20

Days	Viscosity (PAS) at 2rpm	Tackiness (g/f)
1	164	140
10	168	149
25	170	151

25

Table 16: Viscosity/tackiness over time

30

Example 13

6 g of epoxy resin was added to 30 g of the powder of Example 1. 5 g of terpeneol was then added. The mixture was then mixed in an orbital mixer at 1000rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to
 5 obtain a homogenous paste.

Composition	Weight %
Silver powder	73.17
Resin	14.63
Terpineol	12.20

Table 17: Composition of paste

10 Example 14

4.9g of epoxy resin was added to 30 g of the powder of Example 1. 2g of terpeneol and 2g of triethylene glycol was then added and mixed in an orbital mixer at 1000 rpm. After
 15 mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

Composition	Weight %
Silver powder	77.12
Resin	12.60
Terpineol	5.14
Triethylene glycol	5.14

Table 18: Composition of paste

Example 15

6 g of epoxy resin was added to 30 g of the powder of Example 1. 3 g of terpineol and 3 g of triethylene glycol was then added and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

Composition	Weight %
Silver powder	71.44%
Resin	14.28%
Terpineol	7.14%
Triethylene glycol	7.14%

Table 19: Composition of paste

Example 16 - printing paste

The paste of Example 8 was printed on direct bond copper (DBC) having Au/Ni finish with a 3mil stencil having an aperture size of 7mm*7mm. The printed surface was observed to be absolutely flat having no undulation. The thickness of the printed layer was around 75µm.

The printed layer was sintered in a box oven by heating the film at 160°C for 90 minutes. SEM indicated the necking of the silver nanoparticle with a good packing fraction.

Example 17 - preparation of film

The paste of Example 2 was printed on a silicon coated polyester sheet. It was then heated at 130 °C for 30 minutes in a hot plate/box oven. The resulting film was de-attached from the sheet and could be used as a free standing film.

- 5 Figure 8 shows the film as printed in wet condition and also as a free standing dry film after being de-attached from the polyester sheet. No cracks were found in the film after it was de-attached from the polyester sheet. The thickness of the dried film was 72 µm.

10

The silver film was then placed on silicon rubber. The die of 3mm*3mm was stamped onto the film by putting a pressure of 2MPa for a second at 130° C with help of die bonder.

15 Example 18 - dispensing paste

The paste of Example 15 was dispensed using a Nordson Auger Valve. The following were the set parameters for dispensing:

20

Needle size: 22Gauge

Pressure: 1Bar

Dispense Type: Point and pattern

Dispense Time: 0.15sec

25

The topology of the dispensed pattern was examined using a Keyance microscope (see Figure 9). It was seen that the all the dispensed dots and patterns were of the same diameter (~520 microns) and length (2.3 mm), respectively. The volume of the dispensed patterns were then examined using a Koh

30

Young apparatus (see Figure 10), which revealed consistent dispense deposit and height (~ 63.6 microns to 67.2 microns).

Example 19

5.55 g of terpineol was mixed with 1.48 g of Silver Oxalate.

- 5 To this mixture 30 g of the powder of Example 1 was added and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

Composition	Weight %
Silver powder	81%
Silver oxalate	4%
Terpineol	15%

10

Table 20: Composition of paste

Example 20

- 15 1.39 g of terpineol, 2.08 g of propylene glycol, 2.08 g of methyl digol was mixed with 1.48 g of Silver Oxalate. To this mixture 30 g of the powder of Example 1 was added and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to
- 20 obtain a homogenous paste.

Composition	Weight %
Silver powder	81%
Silver oxalate	4%

Propylene glycol	5.61%
Methyl digol	5.61%
Terpineol	3.78%

Table 21: Composition of paste

Example 21

5

0.925 g of terpineol, 1.39 g of propylene glycol, 1.39 g of methyl digol was mixed with 3.33 g of Silver Oxalate. To this mixture 30 g of the powder of Example 1 was added and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

10

Composition	Weight %
Silver powder	81%
Silver oxalate	9%
Propylene glycol	3.75%
Methyl digol	3.75%
Terpineol	2.5%

Table 22: Composition of paste

15

Example 22

0.9 g of terpineol, 1.35g of propylene glycol, 1.35 g of methyl digol was mixed with 7.2 g of Silver Oxalate. To this mixture 25.2 g of the powder of Example 1 was added and mixed in an orbital mixer at 1000 rpm. After mixing, the

20

mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

Composition	Weight %
Silver powder	70%
Silver oxalate	20%
Propylene glycol	3.75%
Methyl digol	3.75%
Terpineol	2.5%

5 Table 23: Composition of paste

Example 23

0.074 g of Lauric acid was mixed with 2.59 g of Silver
 10 Oxalate. To this 1.85 g of terpeneol, 2.22 g of propylene carbonate, 0.296 g of Hydrogen peroxide was added and mixed. To this mixture 30 g of the powder of Example 1 was added and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to
 15 obtain a homogenous paste.

Composition	Weight %
Silver powder	81%
Silver oxalate	7%
Lauric Acid	0.2%
Propylene carbonate	6.00%
Terpineol	5.00%
Hydrogen peroxide	0.8%

Table 24: Composition of paste

Example 24

5 0.074 g of Lauric acid was mixed with 3.33 g of Silver Oxalate. To this 1.85 g of terpeneol, 1.48 g of propylene carbonate, 0.296 g of hydrogen peroxide was added and mixed. To this mixture 30 g of the powder of Example 1 was added and mixed in an orbital mixer at 1000 rpm. After mixing, the
 10 mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

Composition	Weight %
Silver powder	81%
Silver oxalate	9%
Lauric Acid	0.2%
Propylene carbonate	4.00%
Terpineol	5.00%
Hydrogen peroxide	0.8%

Table 25: Composition of paste

15

Example 25

0.074 g of Lauric acid was mixed with 2.96 g of Silver Oxalate. To this 2.03 g of terpeneol, 1.67 g of propylene
 20 carbonate, 0.296 g of hydrogen peroxide was added and mixed. To this mixture 30 g of the powder of Example 1 was added and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

Composition	Weight %
Silver powder	81%
Silver oxalate	8%
Lauric Acid	0.2%
Propylene carbonate	4.5%
Terpineol	5.48%
Hydrogen peroxide	0.8%

Table 26: Composition of paste

5 Example 26

0.074 g of Lauric acid was mixed with 2.96 g of Silver Oxalate. To this 2.58 g of terpineol, 1.11 g of propylene carbonate, 0.296 g of hydrogen peroxide was added and mixed.

- 10 To this mixture 30 g of the powder of Example 1 was added and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

Composition	Weight %
Silver powder	81%
Silver oxalate	8%
Lauric Acid	0.2%
Propylene carbonate	3.0%
Terpineol	6.98%
Hydrogen peroxide	0.8%

Table 27: Composition of paste

The properties of the paste are set out in the table below.

Specific Heat	0.27 J/g·K
Thermal diffusivity	99.5 mm ² /s
Thermal conductivity	223.6 W/m·K
Density	8.65 g/cm ³
Viscosity at 2rpm (Pas)	50 (± 10%)
Tack (gf)	95 (± 10%)

Table 28: Properties of paste

The paste of this example exhibits good printing features. The cross section of a die attached material using the paste exhibited an excellent packing fraction, and the joint strength was around 20 MPa.

Example 27

0.212 g of Lauric acid was mixed with 3.59 g of Silver Oxalate. To this 5.89 g of terpineol, 4.85 g of propylene carbonate, 0.859 g of hydrogen peroxide was added and mixed. To this mixture 30 g of the powder of Example 1 was added and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

Composition	Weight %
-------------	----------

Silver powder	69.99%
Silver oxalate	6.99%
Lauric Acid	0.413%
Propylene carbonate	9.45%
Terpineol	11.48%
Hydrogen peroxide	1.674%

Table 29: Composition of paste

Example 28

5

0.174 g of Lauric acid was mixed with 4.61 g of Silver Oxalate. To this 4.86 g of terpineol, 4 g of propylene carbonate, 0.708 g of hydrogen peroxide was added and mixed. To this mixture 30 g of the powder of Example 1 was added and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

10

Composition	Weight %
Silver powder	72.01%
Silver oxalate	9.00%
Lauric Acid	0.34%
Propylene carbonate	7.8%
Terpineol	9.47%
Hydrogen peroxide	1.38%

15

Table 30: Composition of paste

Example 29

0.074g of Lauric acid was mixed with 2.96g of Silver Lactate. To this 2.58g of terpeneol, 1.11g of propylene carbonate, 0.296 of Hydrogen peroxide was added and mixed. To this mixture 30 g of the powder of Example 1 was added and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

Composition	Weight %
Silver powder	81%
Silver Lactate	8%
Lauric Acid	0.2%
Propylene carbonate	3.0%
Terpeneol	6.98%
Hydrogen peroxide	0.8%

Table 31: Composition of paste

Example 30

0.074g of Lauric acid was mixed with 7.4g of Silver Lactate. To this 2.59g of terpeneol, 1.11g of propylene carbonate, 0.296 of Hydrogen peroxide was added and mixed. To this mixture 25.55 g of the powder of Example 1 was added and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

Composition	Weight %
Silver powder	69%

Silver Lactate	20%
Lauric Acid	0.2%
Propylene carbonate	3.0%
Terpineol	7.0%
Hydrogen peroxide	0.8%

Table 32: Composition of paste

Example 31

5

85-90 % of the powder of Example 1 and 0 to 1% of fatty acid was mixed in a jar A. In another jar B, 0 to 3% of propylene carbonate, 3 to 8% of terpineol, 3 to 8% triethylene glycol and 0 to 2 % organic peroxide were mixed. The mixture from jar A was added to jar B and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

Example 32

15

80-85 % of the powder of Example 1, 0 to 5 % of silver compound and 0 to 1% of fatty acid was mixed in a jar A. In another jar B, 0 to 3% of propylene carbonate, 3 to 8% of terpineol, 7 to 10 % triethylene glycol and 0 to 2 % organic peroxide were mixed. The mixture from jar A was added to jar B and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

25 Example 33

85 - 90 % of the power of Example 1, 0 to 5 % of silver compound and 0 to 1% of fatty acid was mixed in a jar A. In another jar B, 0 to 3% of propylene carbonate, 3 to 8% of terpeneol, 3 to 8% triethylene glycol and 0 to 2 % organic peroxide were mixed. The mixture from jar A was added to jar B and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

10 Example 34

75 - 80% of the powder of Example 1, 0 to 5 % of silver compound and 0 to 1% of fatty acid was mixed in a jar A. In another jar B, 0 to 3% of propylene carbonate, 3 to 8% of terpeneol, 6 to 12% triethylene glycol and 0 to 5% organic peroxide were mixed in jar B. The mixture from jar A was added to jar B and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

20

Example 34

80 - 85 % of the powder of Example 1, 5 to 10 % of Silver compound and 0 to 1% of fatty acid was mixed in a jar A. In another jar B, 0 to 5% of propylene carbonate, 0 to 5 % of terpeneol, 3 to 7% triethylene glycol and 0 to 2 % organic peroxide were mixed. The mixture from jar A was added to jar B and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste

30

Example 35

0.3M AgNO₃ solution was made in aqueous medium. To the aqueous solution of AgNO₃, reducing agent was added drop wise. The solution was stirred for 1 hour at room temperature. Silver starts precipitating out on the addition of the reducing agent and the supernatant becomes fully colorless. The solution mixture was then filtered using a Buchner funnel. The micron silver powder obtained was then washed with water so as to remove excess silver salt and reducing agent. Final washing was then done with acetone so as to ensure the complete removal of water. The powder obtained was then characterized with SEM, indicating a particle size of around 600nm to 1 micron.

Example 36

80 - 85 % of mixture the powders of Example 1 and Example 35 (about 90 wt% Example 1, about 10 wt% Example 35), 5 to 10 % of silver lactate and 0 to 1% of lauric acid were mixed in a jar A. In another jar B, 0 to 5% of propylene carbonate, 0 to 5 % of terpeneol, 3 to 7% triethylene glycol and 0 to 2 % organic peroxide were mixed. The mixture from jar A was added to jar B and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste

Example 37

85 - 90 % of the powder of Example 35, 0 to 5 % of silver lactate and 0 to 1% of lauric acid were mixed in a jar A. In another jar 0 to 3% of propylene carbonate, 3 to 8% of

terpineol, 3 to 8% triethylene glycol and 0 to 2 % organic peroxide were mixed in jar B. The mixture from Jar A was added to B and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste.

Example 38

80 - 85 % of the powder of Example 35, 5 to 10 % of silver lactate and 0 to 1% of lauric acid was mixed in a jar A. In another jar 0 to 5% of propylene carbonate, 0 to 5 % of terpeneol, 3 to 7% triethylene glycol and 0 to 2 % organic peroxide were mixed in jar B. The mixture from Jar A was added to B and mixed in an orbital mixer at 1000 rpm. After mixing, the mixture was milled in a three roll mill for a few minutes to obtain a homogenous paste

Example 39 - printing paste

Print definition:

The paste of Example 31 was printed on direct bond copper (DBC) having Au/ Ni finish with a 3 mil stencil having an aperture size of 3mm*3mm. It was observed that the printed surface was absolutely flat having no undulation. The thickness of the printed layer was around 75um.

Die placement:

Gold metalized silicon dies were placed on the printed pattern using a die bonder. The uniform print deposit was confirmed by Koh Young 8030 as shown in graph below. The

vehicle was then kept in a box oven for sintering at different temperature profile.

Temperature profile:

5

Silicon die metallized with gold coating was placed with the help of a die bonder using controlled Z height and was sintered at 180°C, 200°C, 225°C and 250°C in a box oven. It is seen that the joint strength decreased when heated after 225°C.

10

In this Example, 200°C was considered the optimized sintering temperature, since high temperature die shear at 260°C shows a drop of around 50 %.

15

Cross section of the sintered layer:

The cross section of the above die attached material shows a good diffusion of silver nanoparticle at both the interfaces (die side as well as on the substrate side). SEM reveals a very good packing fraction with very good necking phenomena.

20

Dispense topology:

25

The paste of the above example was also dispensed using Nordson EFD dispenser. The nanosilver paste was dispensed at 0.8 bar pressure and a speed of 40 mm/sec on lead frames.

Die placement:

30

Gold metalized silicon dies were placed on the dispensed pattern using a die bonder. Uniform dispensing was observed

throughout. The vehicle was kept in a box oven. The average die shear obtained was around 20 -25 MPa with 100% pad coverage. About 20% deterioration was seen when the shearing was done at 260°C

5

Cross section of the sintered layer:

The cross section of the above die attached material shows a good diffusion of silver nanoparticle at both the interfaces
10 (die side as well as on the substrate side). SEM reveals the bond line thickness of around 20 micron.

As will be appreciated, the method, powder, paste and film disclosed herein are associated with a number of benefits
15 over prior art techniques. In particular, there is no slump phenomena, no bridges, no bubbles in print deposit, no bleed-out and no aperture blocking when printing with the paste. Moreover, it is possible to provide a paste height of from 80 - 90 micrometers with flat deposits, no Dog - ears
20 and no undulations. Thus, the benefits of the paste which includes a binder (e.g. resin) include:

Pressure-less Sintering

Process ability in standard SMT Line

25 Flat and uniform surface topology

Die Shear Strength average > 20MPa

No interfacial failure mode

Room Temp Stability = min 1 month

Thermal Cycling: Acceptable joint strength up to 1500
30 cycles (-40C to +125C, 10 min dwell).

Needle and Jet Dispensable

Film Form Factor

In addition to the benefits mentioned above, the paste containing organosilver compound has some further benefits which are listed below:

5

High die shear strength (25 to 45MPa)
High thermal conductivity (> 200W/ mK)
Pin transferable
Good high thermal properties

10

The sintering powder, paste and film will now be further described, by way of example, with reference to the following non-limiting applications A-H:

15

A. Attachment of semiconductor die (either flip chip or wire bonded), onto a variety of substrates such as DBC (Direct Bond Copper), DPC (Direct Plate Copper), MCPCB (Metal Core PCBs), FR4, Copper lead-frames, Flexible PCBs and substrates, Copper and Aluminum Heat-Sinks, Fixtures,

20

etc.). Applications include LED die (light emitting diodes for example of the lateral, vertical thin film or flip chip varieties) made from various compound semiconductor materials, power die made from silicon, concentrated photovoltaic compound semiconductor cells (e.g. multi-

25

junction cells) silicon carbide and gallium nitride used in power modules, and discretes, MEMS (micro-electromechanical sensor) devices of all types, semiconductor and stacked die, Thermoelectric material element attach to substrates, as well as Piezo-electric element stack attach, and oscillator

30

crystals and optical and other sensor device attach. The attachment of such semiconductor or other die elements may be accomplished by printing on to the substrates, followed

by die placement via a die bonder or a pick and place machine, and sintering in either a reflow oven belt oven or box oven. Attachment of such semiconductor and die elements can also be accomplished via dispensing the paste, followed
5 by die placement and sintering as outlined above, or doing film transfer and lamination on the die backside of the film made from the said material, followed by die placement and tacking onto the substrate, followed by sintering. Flip chip die can be assembled by printing bumps on the substrate,
10 placing the die, followed by sintering. Low temperature sintering, and sintering with a regular short lead free reflow profile enables assembly of high CTE mismatch stacks as well as temperature sensitive material stacks. A major benefit of the sintering powder as disclosed herein in such
15 applications is improved throughput with short cycle times while using existing standard installed equipment (such as printers, die bonders and reflow/belt ovens).

B. Attachment of semiconductor packages of various types
20 (for example bottom termination components such as, for example, LGAs, QFNs, QFPs), onto a variety of substrates such as, for example, DBC (Direct Bond Copper), DPC (Direct Plate Copper), MCPCB (Metal Core PCBs), FR4, Flexible PCBs and substrates, Copper and Aluminum Heat-Sinks, Fixtures,
25 etc.). Applications include LED packages of various types (for example, ceramic submount LEDs, SMD LEDs with leadframe construction, etc,) power modules, and discretes, MEMS (micro-electromechanical sensor) packages of all types, semiconductor and stacked die packages, Thermoelectric
30 material element attach to substrates, as well as Piezo-electric element stack attach, and oscillator crystals and optical and other sensor device attach. The attachment of

such semiconductor or other packages can be accomplished by printing on to the substrates, followed by package placement via standard a pick and place machine with Z Height adjustment and / or pressure capability, and sintering in
5 either a reflow oven belt oven or box oven. Low temperature sintering and sintering with a regular short lead free reflow profile enables assembly of high CTE mismatch stacks as well as temperature sensitive material stacks. A major benefit of the sintering powder as disclosed herein in such
10 applications is improved throughput with short cycle times while using existing standard installed equipment (such as printers, die bonders and reflow/belt ovens).

C. Production of interconnect lines ('circuitry, pads,
15 etc.) separately and along with flip chip interconnects. For example, applications for interconnect lines include LED boards and luminaires, where the interconnect lines can be applied by a variety of printing (e.g. stencil printing) or dispensing or jetting techniques. In the case of LED
20 applications, such interconnects can serve as both electrical and thermal conductors to carry the electrons to and from the device, and the heat away from the device. Further, such interconnect lines can be directly applied in the same step with interconnects for attaching flip chip or
25 wire bonded devices. Another example of such interconnects is solar cells (either silicon based or thin film based), where the interconnects in a grid pattern could be used to collect electrons generated, and also connect one cell to another. Another example of such applications is an OLED
30 device where a grid of such interconnect lines can be used to enhance the electrical conductivity of transparent conductive films.

D. Wafer-to-wafer bonding layers, based on both printable pastes and films. There is a significant need for wafer-to-wafer bonding at low temperatures (under 250 °C) where the bonding layer exhibits very high temperature properties post bonding. In the case of LED wafer bonding, this can be accomplished for example, in the context of either thin film flip chip or vertical thin film or truncated inverted pyramid LEDs, where CTE mismatch and therefore strain and defect generation can be minimized, while allowing for high temperature post processing with a variety of advanced materials for enhancing light output and electrical efficiency of the device. Further, the high temperature and high thermal and electrical conductivities of the bonding layer allow for superior thermal transfer, high temperature operation of the device and superior current spreading, among other advantages. Such wafer bonding can be accomplished by lamination of films of the said material on the backside of the wafers, followed by temperature and pressure processing in a standard wafer bonder or a press. Another means of doing the processing includes printing a conformal layer of paste on the wafer backside, followed by drying and bonding in a standard wafer bonder or press, under temperature and pressure conditions. Applications for such wafer bonding include power semiconductor wafers, Through Silicon Via (TSV) applications, stacked die applications, MEMS, Thermoelectric Material wafers, Piezo-electric materials, concentrated photovoltaics and other applications. Low temperature sintering enables assembly of high CTE mismatch stacks as well as temperature sensitive material stacks. A major benefit of the sintering powder as

disclosed herein in such applications is improved throughput with short cycle times while using existing standard installed equipment (such as printers/laminators, wafer bonders and reflow/belt ovens).

5

E. Wafer back-side lamination, based on both printable pastes and films. In certain applications there is a need to laminate the back-side of the semiconductor wafers with the solder powder as disclosed herein in paste or film form, prior to drying and dicing. Such an approach can provide a convenient way to apply the die attach material to the wafer prior to mounting on dicing tape and dicing, so that it can be transported to the die bonder with the pre-laminated Supernova N die attach material. Applications for such an approach can include lateral and vertical LED devices, semiconductor die used in power electronics (power modules, and discretes), MEMS (micro-electromechanical sensor) packages of all types, semiconductor and stacked die packages and other applications, Thermoelectric Materials, Piezo-electric element stack attach, and other applications such as oscillator crystals and optical and other sensor device attach.

F. Reflective layer printing for LED and optical applications. The said material can be used to print reflective layers on to substrates such as DBC (Direct Bond Copper), DPC (Direct Plate Copper), MCPCB (Metal Core PCBs), FR4, Flexible PCBs and substrates, Copper and Aluminum Heat-Sinks, Fixtures, etc.), in order to provide light output enhancement and therefore luminous efficacy enhancement of LED and other optical systems. Such reflective layers can be formed via stencil or screen printing, jetting or

dispensing or film lamination of the said material. A major benefit of the sintering powder as disclosed herein in such applications is improved throughput with short cycle times while using existing standard installed equipment (such as
5 printers/laminators, wafer bonders and reflow/belt ovens).

G. Hermetic and near hermetic sealing for packages, perimeter seals, etc. for LED, MEMS, optical sensors and
10 oscillator crystals, OLED and PV applications and general semiconductor packaging. There is a significant need for hermetic sealing of LED, OLED, MEMS and thin film PV packages, to protect the devices from moisture ingress. The said material can exhibit hermetic or near hermetic sealing
15 behavior with proper application and sintering. The said material can be applied in various stages of the manufacturing processes for the above devices: Either at the wafer level with wafer bonding, or in the packaging process via film lamination and bonding, or paste
20 jetting/dispensing followed by lid or glass or laminate cover attach and sintering. Low temperature sintering and sintering with a regular short lead free reflow profile enables assembly of high CTE mismatch stacks as well as temperature sensitive material stacks.

25

H. ACF Replacements. Arrays of bumps of the said material can be delivered to the substrate via stencil printing, bump transfer, or high speed jet dispensing. Such arrays can be
30 used to serve as electrical contacts to assemble devices without explicit high degrees of alignment. Low temperature sintering and sintering with a regular short lead free

reflow profile enables such applications. A major benefit of the sintering powder as disclosed herein in such applications is improved throughput with short cycle times while using existing standard installed equipment (such as
5 printers/laminators, wafer bonders and reflow/belt ovens).

The foregoing detailed description has been provided by way of explanation and illustration, and is not intended to limit the scope of the appended claims. Many variations in
10 the presently preferred embodiments illustrated herein will be apparent to one of ordinary skill in the art and remain within the scope of the appended claims and their equivalents.

Claims:

1. A sintering powder comprising:
a particulate having a mean longest diameter of less
5 than 10 microns, wherein at least some of the particles
forming the particulate comprise a metal at least partially
coated with a capping agent.
2. The sintering powder of claim 1 wherein the capping
10 agent comprises an amine and/or a carboxylate functional
group.
3. The sintering powder of claim 1 or claim 2 wherein the
capping agent comprises a straight chain or branched chain
15 aliphatic amine, preferably octylamine.
4. The sintering powder of any preceding claim wherein the
metal comprises silver or an alloy thereof.
- 20 5. The sintering powder of any preceding claim comprising
up to 5 wt% capping agent, preferably from 0.1 to 3 wt%
capping agent, more preferably about 1 wt% capping agent.
6. The sintering powder of any preceding claim, wherein
25 the particulate comprises a first type of particles having a
longest diameter of from 1 to 100 nm and a second type of
particles having a longest diameter of from greater than 100
nm to 50 microns.
- 30 7. The sintering powder of claim 6, wherein the first type
of particles have a diameter of from 5 to 75 nm and/or the
second type of particles have a diameter of from greater

than 100 nm to 20 microns, preferably from 600 nm to 1 micron.

8. The sintering powder of claim 6 or claim 7, wherein the
5 particulate comprises from 81 to 99 wt% of the first type of particles and from 1 to 19 wt% of the second type of particles, preferably from 85 to 95 wt% of the first type of particles and 5 to 15 wt% of the second type of particles.

10 9. The sintering powder of any of claims 1 - 5, wherein the particulate has a mean longest diameter of from 1 to 100 nm, preferably from 5 to 75 nm.

10. The sintering powder of any of claims 1 - 5, wherein
15 the particulate has a mean longest diameter of from 100 nm to 10 microns, preferably from 600 nm to 1 micron.

11. A sintered joint formed using the sintering powder of any preceding claim.

20

12. A sintering paste comprising:

the sintering powder of any of claims 1 - 10;

a binder;

a solvent; and

25 optionally an activator and/or rheology modifier and/or surfactant.

13. The sintering paste of claim 10 wherein the binder comprises an epoxy-based resin.

30

14. The sintering paste of claim 12 or claim 13 wherein the solvent comprises a monoterpene alcohol and/or a glycol

and/or glycol ether, preferably a terpineol and/or triethylene glycol.

15. The sintering paste of any of claims 12 - 14

5 comprising:

from 1 to 15 wt% binder; and/or
from 1 to 15 wt% solvent; and/or
up to 1 wt% rheology modifier; and/or
up to 1 wt% activator; and/or
10 up to 6 wt% surfactant.

16. A sintering paste comprising:

the sintering powder of any of claims 1 - 10;
an organosilver compound;

15 a solvent; and

optionally an activator and/or rheology modifier and/or
surfactant.

17. The sintering paste of claim 16 wherein the

20 organosilver compound comprises one or more of silver
oxalate, silver lactate, silver succinate, silver
neodecanoate, silver citrate and silver stearate.

18. The sintering paste of claim 16 or claim 17 further

25 comprising a fatty acid, preferably lauric acid, stearic
acid and/or citric acid.

19. The sintering paste of any of claims 16-18 further
comprising a peroxide, preferably hydrogen peroxide.

30

20. The sintering paste of any of claims 16-19 wherein the
paste is substantially resin free.

21. The sintering paste of any of claims 16 - 20, wherein the paste is pin transferable and/or exhibits a thermal conductivity of greater than 200 W/mK and/or is capable of providing a die shear strength of from 25 to 45 MPa.

22. A sintering film comprising the sintering powder of any of claims 1 - 10 and a binder.

23. Use of the sintering powder of any of claims 1 - 10 or the sintering paste of any of claims 12 - 21 or the sintering film of claim 22 in a method selected from: die attachment, wafer-to-wafer bonding, reflective layer printing, hermetic and near hermetic sealing, sintering films comprising a sintering powder and a binder formed in a film on a backing layer, dispensing and the production of interconnect lines.

24. A method of manufacturing a sintered joint comprising the steps:

providing the sintering powder of any of claims 1 - 10 or the sintering paste of any of claims 12 - 21 or the sintering film of claim 22 in the vicinity of two or more work pieces to be joined; and

heating the sintering powder or sintering paste or sintering film to at least partially sinter the metal.

25. The method of claim 24 wherein the heating is carried out at a temperature of at least 140 °C, preferably from 150 °C to 300 °C.

26. A method of manufacturing the sintering powder of any preceding claim comprising the steps:

providing a metal salt solution;

contacting the metal salt solution with a capping

5 agent; and

precipitating metal particles at least partially coated with the capping agent.

27. The method of claim 26 wherein the precipitating step
10 is carried out using a reducing agent.

28. The method of claim 27 wherein the reducing agent comprises hydrazine and/or sodium borohydride.