

ABSTRACT

Disclosed is a pressure sensitive adhesive sheet in which a photocurable pressure sensitive adhesive composition is formed in a sheet shape. The pressure sensitive adhesive composition includes an acryl-based base polymer having a crosslinked structure, a photopolymerizable polyfunctional compound having two or more photopolymerizable functional groups per molecule, and a photopolymerization initiator. The pressure sensitive adhesive sheet preferably has a storage elastic modulus of 100 to 250 kPa at 25°C and 1 Hz. The pressure sensitive adhesive sheet preferably has a gel fraction of 25 to 70%. After the pressure sensitive adhesive composition is photocured, the photocured pressure sensitive adhesive sheet preferably has a storage elastic modulus of 180 to 400 kPa at 25°C and 1 Hz.

Representative Drawing: FIG. 1