

(19) World Intellectual Property
Organization
International Bureau



(10) International Publication Number

WO 2022/256535 A9

(43) International Publication Date
08 December 2022 (08.12.2022)

WIPO | PCT

(51) International Patent Classification:

H01M 10/0568 (2010.01) H01M 4/38 (2006.01)
H01M 10/0569 (2010.01) H01M 4/48 (2010.01)
H01M 10/0567 (2010.01) H01M 4/525 (2010.01)
H01M 10/052 (2010.01) H01M 4/505 (2010.01)
H01M 4/36 (2006.01) H01M 4/62 (2006.01)

(71) Applicant: **IONBLOX, INC.** [US/US]; 3390 Gateway Blvd., Fremont, California 94538 (US).

(72) Inventors: **DONG, Yingnan**; 38627 Cherry Lane, Apartment 61, Fremont, California 94536 (US). **LOPEZ, Herman A.**; 325 Beemer Avenue, Sunnyvale, California 94086 (US). **HAYS, Kevin**; 40464 Ditmus Court, Fremont, California 94538 (US). **HUANG, Yu-Hsin**; 305 Elan Village Lane, Unit 317, San Jose, California 95134 (US).

(21) International Application Number:

PCT/US2022/031969

(22) International Filing Date:

02 June 2022 (02.06.2022)

(74) Agent: **DARDI, Peter S.**; Christensen, Fonder, Dardi & Herbert PLLC, 11322 86th Avenue North, Maple Grove, Minnesota 55369 (US).

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

63/196,536

03 June 2021 (03.06.2021)

US

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ,

(54) Title: LITHIUM ION CELLS WITH HIGH PERFORMANCE ELECTROLYTE AND SILICON OXIDE ACTIVE MATERIALS ACHIEVING LONG CYCLE LIFE, FAST CHARGE AND HIGH THERMAL STABILITY




FIG. 20B

(57) Abstract: Improved electrolytes for lithium-based cells can include a dual salt combination of lithium hexafluorophosphate and lithium bis(fluorosulfonyl)imide or lithium bis(trifluoro-methanesulfonyl)imide, and a solvent that includes dimethyl carbonate, ethylmethyl carbonate and 5 to 25 volume percent of fluoroethylene carbonate. The improved electrolytes can include additives triethyl phosphate, ethoxy(pentafluoro)cyclotriphosphazene, 1,3-propane sultone, or mixtures thereof, and have small limited amounts of additional cosolvents and/or lithium-free organic additives. The improved electrolytes can be used to prepare lithium-based cells with silicon-based active materials as negative electrodes and nickel rich lithium metal oxides as positive electrodes. The lithium-based cells can achieve high energy, high power, fast charge and long cycle life along with good thermal stability.

[Continued on next page]

CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO,
DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN,
HR, HU, ID, IL, IN, IQ, IR, IS, IT, JM, JO, JP, KE, KG, KH,
KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA,
MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI,
NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU,
RW, SA, SC, SD, SE, SG, SK, SL, ST, SV, SY, TH, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, WS, ZA, ZM,
ZW.

- (84) Designated States** (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(48) Date of publication of this corrected version:

17 August 2023 (17.08.2023)

(15) Information about Correction:

see Notice of 17 August 2023 (17.08.2023)