

ABSTRACT

5 A resin sheet is for molding, has an impact strength of 1.0 J or greater in a DuPont impact test, and has a value of 80 N/m² or smaller obtained through integration from an origin point to a strain when fracture has occurred in a stress strain curve obtained in a tensile test. A carrier tape 100 is a molded body 16 of the resin sheet, wherein an accommodation portions 20 capable of accommodating an article is provided.