

A PACKING LAMINATE IN THE FORM OF A WEB
AND A METHOD FOR MANUFACTURING THE SAME

The present invention relates to a method for manufacturing a packing laminate in the form of a web by processing and dividing up a raw material web which comprises a layer of a stiffening material.

The invention also relates to a packing laminate in the form of a web comprising a carrier layer of stiffening material and at least one layer of thermoplastic material laminated to the same.

Packing containers of the non-returnable type for the packaging of e.g. milk and other liquid dairy products are manufactured from laminated packing material which comprises a carrier layer of relatively stiff material, e.g. paper, which, at least on the side which is intended to be in contact with the contents, is covered with a liquid-tight, preferably thermoplastic material, e.g. polyethylene. Beside serving as a material conferring imperviousness, the thermoplastic layer is also used for making possible the heat-sealing of the laminate. For this reason it is often advantageous if the opposite side, that is to say the outer side, of the carrier layer is also covered with a thermoplastic material. When the packing laminate is converted into packing containers, these are formed in such a manner, by folding and sealing of the laminate, that packing containers of

the desired shape are obtained. It is of the greatest importance that the seals, which unavoidably must be present on the finished packing container, should be completely impervious to liquid. This is particularly
05 difficult to achieve if seals of the inside-to-outside type are used, since the lower packing laminate edge, that is to say the edge facing towards the inside of the packing container, will then come into contact with the contents not only with the thermoplastic-
10 covered surface, but also with the cut edge itself where the carrier layer is exposed. In the case of a carrier layer of the fibrous type, this will gradually absorb contents, which detrimentally affects the tightness and the durability of the package. In order
15 to prevent this, either a separate liquid-tight strip has been placed over the exposed cut edge on the inside of the seal up to now, or else the internal edge zone of the material is doubled so that the inner thermoplastic layer extends around the edge and
20 prevents contact between the contents and the carrier layer. The latter method is generally preferred, since in this case no separate strip need be used. However, the packing laminate has to be prepared for this method by a certain thinning of the edge which is
25 to be folded, since otherwise the multiple material thickness causes the sealing zone to become thick and unwieldy.

The thinning of the edge on the packing laminate web which is to be folded has been achieved up to now as a last stage in the manufacture of the laminate web. After the carrier layer has been provided with 05 the different layers of thermoplastic, and possibly other, material which are intended to constitute the finished laminate, and has been cut to an appropriate width, the thinning of the edge in question is performed by causing the web to pass a grinding wheel 10 or a cylindrical cutter which along a longitudinal edge zone grinds or cuts away a portion of the carrier layer together with the outside thermoplastic layer. Since the cutting away is taking place only in the edge region of the material web, it is difficult to 15 carry out the operation with sufficient precision, since the edge region tends to give way or move in lateral direction under the effect of the cutting tool. The operation, moreover, takes a long time, since the speed of the material web has to be kept 20 relatively low owing to the instability of the edge. In order to prevent any dust, which is formed in connection with the cutting away, from following the material web and eventually settling in the packages, some form of cleaning of the material web also has to 25 be performed before it is converted to finished packing containers.

It is an object of the present invention to provide a method for manufacturing a packing laminate in the form of a web of the type described, which method is not subject to the aforementioned disadvantages.

5 It is a further object of the present invention to provide a method for manufacturing a packing laminate in the form of a web with reduced edge thickness, which method can be carried out with good precision even at high web speed.

10 It is a further object of the present invention to provide a high capacity method for manufacturing a packing laminate in the form of a web with cut edges which does not require cleaning prior to conversion to packing containers.

15 These and other objects have been achieved in accordance with the invention in that a method of the type described in the beginning has been given the characteristic that the thickness of the raw material web is reduced within longitudinal zones, located
20 regularly spaced over the width of a face of the raw material web, by cutting away a portion of the stiffening layer, whereupon a coating layer is applied to the said face of the raw material web and the raw material web is divided into individual, narrower packing material webs by means of
25 cuts in the said zones.

- 5 -

By carrying out the thinning of the material already when it is in the form of a wide raw material web and only thereafter dividing the raw material web into individual packing laminate webs, an appreciably
05 higher capacity is achieved than by using any of the previously known methods, since firstly the raw material web can be processed simultaneously by a number of cutting tools arranged side by side over the width and, since secondly it can be advanced at an
10 appreciably higher speed, as the processing is taking place largely at a distance from the unstable edge zones.

Preferred embodiments of the method in accordance with the invention have been given moreover the
15 characteristics evident from subsidiary claims 2-6.

It is an object of the present invention, moreover, to provide a packing laminate in the form of a web of the aforementioned type, which packing laminate is not subject to the disadvantages
20 exemplified above.

It is a further object of the present invention, therefore, to provide a packing laminate in the form of a web of the aforementioned type, which laminate has edge zones of such a shape that they can be used
25 to produce seals of good liquid-tightness.

It is a further object of the present invention, moreover, to provide a packing laminate in the form of a web whose edge zones are shaped so that jointly they make it possible to produce seals of optimum

05 properties insofar as tightness, suppleness and appearance are concerned.

These and other objects have been achieved in accordance with the invention in that a packing laminate in the form of a web of the type described in
10 the beginning has been given the characteristic that the laminate web along its longitudinal edges is provided with edge zones wherein the thickness of the carrier layer is reduced, the said edge zones as well as the remaining parts of the carrier layer being
15 covered by the thermoplastic layer.

Preferred embodiment of the packing laminate in accordance with the invention have been given, moreover the characteristics evident from subsidiary Claims 8-11.

20 A preferred embodiment of the method as well as of the packing laminate in accordance with the invention will now be described in detail with special reference to the attached schematic drawing which on an enlarged scale illustrates the particulars
25 necessary for the understanding of the invention.

Figure 1 shows in perspective presentation a portion of a raw material web during the manufacture of the packing laminate in accordance with the method according to the invention.

05 Figure 2 is a cross-section through a raw material web in accordance with Figure 1 during a later phase of the manufacture;

 Figure 3 is a cross-section through a packing material web with folded over edge according to the
10 invention;

 Figure 4 is a cross-section through an overlap seal produced with a packing laminate according to the invention;

 In Figure 1 is shown in perspective view a
15 portion of a raw material web which has been provided with longitudinal zones of reduced thickness in accordance with the invention. In this stage of the manufacture the raw material web consists exclusively of a carrier layer 1 of stiffening material, generally
20 paper. In accordance with the method according to the invention, the thickness of the carrier layer 1 has been reduced within longitudinal zones 2 located regularly spaced over the width of the raw material web. This is done appropriately with the help of a
25 number of rotating cylindrical cutters which during the manufacture of the material are arranged so as to

be in contact with the raw material web passing by in such a manner that by means of the active part of their periphery they cut away a strip of the desired thickness from one side of the raw material web. The
05 method suitable for achieving this as well as the appropriate arrangements are described in some detail in Swedish patent application 8000890-7, to which reference is made, so that a more detailed description can be dispensed with.

10 In Figure 2 the raw material web in accordance with Figure 1 is shown in section during a later phase of the course of manufacture. After the zones 2 have been produced, through a reduction in thickness of the carrier layer 1 of the raw material web, the carrier
15 layer is provided with a thin layer 3 of homogeneous thermoplastic material, preferably polyethylene. The thermoplastics is extruded onto the raw material web after the zones 2 have been produced, and is laminated to the carrier layer 1 by allowing the latter, after
20 it has passed an extruder die, to pass between two rollers in contact with one another which press the still partly soft thermoplastics 3 into the surface of the carrier layer 1 so that a complete lamination is achieved. To ensure a true contact between the therm-
25 oplastic layer 3 and the carrier layer 1, also in the zones 2, it is appropriate for one of the two rollers to consist of rubber or some other flexible material.

After the lamination has been completed, and the carrier layer possibly has also been provided with a further thermoplastic layer on its opposite, plane side, the raw material web is divided into individual, narrower packing laminate webs 4 with the help of longitudinal cuts 5 in the thickness-reduced zones 2. As is evident from Figure 2, the cuts 5 are placed asymmetrically in the zones and more particularly in such a manner that each cut 5 divides a thickness-reduced zone 2 into a wider and a narrower edge zone 2' and 2" respectively. In fact the cuts 5 are located so that the two edge zones 2', 2" are given a definite mutual width ratio. As can be seen in particular from Figure 2, each of the thickness-reduced zones 2 comprises a centrally situated, substantially plane area of minimum thickness. This area takes up approximately half the total width of the zone 2. On either side of this plane area of minimum thickness there are two gradual transition areas, each of which taking up approximately $\frac{1}{4}$ of the total width of the reduced zone 2. Now each of the thickness-reduced zones 2 is divided with the help of cuts 5 in such a manner that the wider edge zone 2', beside a gradual transition area, also comprises the greater part of, or the whole of, the area of minimum thickness, whilst the narrower

edge zone 2" only comprises one of the areas where the material thickness gradually diminishes. As a result the two thickness-reduced edge zones 2' and 2" will be given a mutual width ratio which substantially comes to 3:1, and at all events is between 5:1 and 3:2.

The wider, thickness-reduced edge zone 2' thus comprises the greater part of, or the whole of, the area within which the laminate thickness is smallest. Within this area the thickness of the carrier layer 1 has been reduced to between half and 1/3rd of the original thickness and the laminate can be doubled in this area, therefore, without the thickness so produced exceeding the original thickness of the laminate, which is a great advantage.

The doubling of a wider edge zone 2' of an individual packing laminate web 4 is illustrated in Figure 3. It can be seen from the figure how the longitudinal edge is folded over 180° along a folding line whose location substantially coincides with the centre of the area in the wider edge zone 2' wherein the material thickness is smallest. The original outer cut edge 6 of the material web 4 is thus at the same level (but at the opposite side of the laminate) as the transition between the central area of the edge zone 2' of minimum thickness and the transition zone to full material thickness. The edge zone of the

packing laminate has been folded over 180° in such a manner that the thermoplastic layer, which afterwards will be facing towards the interior of the packing container, extends around the material edge. The
05 folded part of the edge zone can be sealed to the outer side of the packing laminate with the help of the thermoplastic layer (not shown) which usually covers the outside of the laminate or by means of glue.

10 In Figure 4 is shown how the packing material web according to Figure 3 has been formed to a tube (only partly shown), its two edges having been joined together in an overlap seal.

The folded over edge zone 2' of the packing
15 material web is situated here inside the edge zone 2" (that is to say inside the tube or eventually the packing container), so that the whole of the surface of the packing laminate which comes into contact with the contents present inside the packing container will
20 be covered by the thermoplastic material layer 3 of the laminate. The two parts of the thermoplastic layer 3 are sealed in liquid-tight manner to one another within that area of the seal where the folded over part of the wide edge zone 2' rests against the
25 overlapping edge zone 2". The strength and tightness of the seal is improved further in that the inner

thermoplastic layer of the narrower edge zone 2" rests against, and is joined to, the opposite laminate edge via the outer thermoplastic layer, not shown in the drawing. Since the doubling of one of the edge zones
05 of the material is performed within the thickness-reduced area, the complete seal will have a thickness which only insignificantly exceeds the original thickness of the laminate.

The method of manufacturing the laminate in
10 accordance with the invention by means of thickness reduction in longitudinal zones whilst the material is still in the form of a raw material web makes it possible, as mentioned before, to manufacture the material at an appreciably higher rate whilst
15 maintaining accuracy, and thus with a higher capacity than previously. The application of the outer thermoplastics after the reduction in thickness moreover eliminates the problem of remaining paper fibres and dust being entrained into the finished packing
20 container, since any residual dust is covered by the thermoplastic layer and is thus rendered harmless.

The asymmetric design of the thickness-reduced edge zones provides optimum facilities for doubling one of the edge zones and forming a liquid-tight
25 overlap seal without the latter acquiring an excessive thickness which might prevent the continued forming of the packing container.



22

CLAIMS

1. A method for manufacturing a packing laminate in the form of a web by processing and dividing up a raw material web which comprises a layer of stiffening material, characterised in that the thickness of the raw material web is reduced within
5 longitudinal zones located regularly spaced over the width of a face of the raw material web by cutting away a portion of the stiffening layer, whereupon a coating layer is applied to the said face of the raw material web, and the raw material web is divided into individual, narrower packing material webs by
10 means of cuts in the said zones.
2. A method in accordance with Claim 1, characterised in that the said cuts are placed asymmetrically in the zones.
3. A method in accordance with Claim 1 or 2, characterised in that the cuts divide each of the said zones into two
15 edge zones whose mutual width ratio is between 5:1 and 3:2.
4. A method in accordance with any one of the preceding claims, characterised in that the cuts are placed at mutually equal distances from one another.
5. A method in accordance with any one of the preceding
20 claims, characterised in that the covering layer applied to the stiffening layer of the raw material web, after the said reduction in thickness, comprises liquid-tight material.



- 14 -

6. A method in accordance with Claim 5, characterised in that the liquid-tight material layer consists of thermoplastic material which is extruded onto the raw material web and laminated to the same.
- 5 7. A packing laminate in the form of a web whenever produced by a method as claimed in any of Claims 1 - 6, comprising a carrier layer of stiffening material and at least one layer of thermoplastic material laminated to the same, characterised in that the laminate web along
- 10 its longitudinal edges is provided with edge zones wherein the thickness of the carrier layer is reduced, the said edge zones as well as the remaining parts of the carrier layer being covered by the thermoplastic layer.
8. A packing laminate in accordance with Claim 7,
- 15 characterised in that the said edge zones are of different width.
9. A packing laminate in accordance with Claim 8, characterised in that the thickness of the laminate within the wider edge zone gradually diminishes from
- 20 the full material thickness to the minimum thickness which is largely maintained within an area along the longitudinal edge of the web.
10. A packing laminate in accordance with Claim 9, characterised in that the said area of minimum
- 25 thickness is of a width which is substantially equal



24

- 15 -

to, or greater than, half the width of the edge zone.

11. A packing laminate in accordance with Claim 10,
characterised in that the one longitudinal edge of the
web is folded over 180° along a folding line whose
05 location substantially coincides with the centre of
the area in the edge zone wherein the material
thickness is smallest.

12. A method as claimed in Claim 1 and substantially
as hereinbefore described with reference to the
10 drawings.

13. A packing laminate as claimed in Claim 7 and
substantially as hereinbefore described with reference
to and as shown in the drawings.

14. A packing laminate whenever prepared by a method
15 as claimed in any one of Claims 1 to 6 and 12.
