

DESCRIPTION

PROCESS FOR PRODUCING HYDROGENATED PETROLEUM RESIN

TECHNICAL FIELD

[0001]

5 The present invention relates to a method for producing a hydrogenated petroleum resin.

BACKGROUND ART

[0002]

Hot-melt adhesives are widely used for manufacturing disposal diapers, binding
10 books and packaging various products. Examples of the material of the hot-melt adhesives include Styrene-Butadiene-Styrene block copolymer (referred to as SBS hereinafter), Styrene-Isoprene-Styrene block copolymer (referred to as SIS hereinafter), Ethylene Vinyl Acetate block copolymer (referred to as EVA hereinafter) and Amorphous PolyAlpha-Olefin (referred to as APAO hereinafter). A tackifier in a form of a hydrogenated
15 petroleum resin is blended in the base polymer.

The hydrogenated petroleum resin is produced by a hydrogenation process for hydrogenating a polymer obtained by adding styrene monomer to cyclopentadiene as disclosed in Patent Literature 1, for instance. The hydrogenated petroleum resin is sometimes provided in a form of hemispherical pellets in view of handleability.

20 In producing the hydrogenated petroleum resin, a batch processing in which the pelletized hydrogenated petroleum resin is analyzed and polymerization conditions and hydrogenating conditions are adjusted based on the results of the analysis is performed to produce a hydrogenated petroleum resin of predetermined physical properties.

However, in order to produce hydrogenated petroleum resin pellets of desired
25 physical properties, such a batch processing requires repetition of the adjustment of the production conditions based on the results of the analysis of the produced pellet, and, consequently, requires much production time and complicated work. Accordingly, simplification of production management has been desired.

In view of the above, as disclosed in Patent Literatures 2 to 4 for instance, some

of known processes employ a near-infrared spectrometer in producing a synthetic resin to measure an absorption spectrum in the resin that is under production for predicting the physical properties of the final products to control the production process.

CITATION LIST

5 PATENT LITERATURE(S)

NON-PATENT LITERATURE(S)

[0003]

Patent Literature 1 WO2004/056882 A

Patent Literature 2 JP-A-2002-145966

10 Patent Literature 3 Japanese Patent No. 4385433

Patent Literature 4 Japanese Patent No. 2865755

SUMMARY OF THE INVENTION

PROBLEM(S) TO BE SOLVED BY THE INVENTION

[0004]

15 As described above, in order to produce hydrogenated petroleum resin pellets of desired physical properties, the production process may be controlled based on a near-infrared spectrometry as disclosed in Patent Literatures 2 to 4.

However, in order to obtain the hydrogenated petroleum resin of desired physical properties, after the hydrogenation reaction in a hydrogenation solvent, the hydrogenation
20 solvent and low-molecular-weight components have to be removed as needed from the hydrogenated petroleum resin pellets. Thus, it is difficult to appropriately control the production process.

An object of the invention is to provide a production method of a hydrogenated petroleum resin capable of easily producing the hydrogenated petroleum resin.

25 MEANS FOR SOLVING THE PROBLEM(S)

[0005]

A method for producing a hydrogenated petroleum resin according to an aspect of the invention includes: measuring a near-infrared absorption spectrum of a molten resin from which a hydrogenation solvent is separated; and controlling a process for producing

hydrogenated petroleum resin pellets based on a result of the measurement.

[0006]

In the above aspect of the invention, in controlling the method for producing the hydrogenated petroleum resin pellets, it is preferable that the result of the measurement indicates a physical property value of at least one of an aromatic content ratio and a
5 bromine number of the molten resin, and at least one of a temperature, a pressure, a reaction time and a hydrogen content of a hydrogenation reaction is controlled such that a difference between the physical property value of the molten resin and a physical property value of a target hydrogenated petroleum resin pellet becomes small.

10 [0007]

In the above aspect of the invention, in controlling the method for producing the hydrogenated petroleum resin pellets, it is preferable that the result of the measurement indicates a softening point of the molten resin, and at least one of a temperature and a pressure in a step for separating the hydrogenation solvent or a low-molecular-weight
15 component is controlled such that a difference between the softening point of the molten resin and a softening point of a target hydrogenated petroleum resin pellet becomes small.

BRIEF DESCRIPTION OF DRAWING(S)

[0008]

Fig. 1 is a block diagram schematically showing an arrangement of a production
20 plant of hydrogenated petroleum resin pellets used in a production method of a hydrogenated petroleum resin according to an exemplary embodiment of the invention.

Fig. 2 is a graph showing analytical curve data relating to an aromatic content ratio stored in an analytical curve database in a near-infrared analyzing portion of the production plant of the hydrogenated petroleum resin pellets.

25 Fig. 3 is a graph showing analytical curve data relating to a bromine number stored in the analytical curve database in the near-infrared analyzing portion.

Fig. 4 is a graph showing analytical curve data relating to a softening point stored in the analytical curve database in the near-infrared analyzing portion.

DESCRIPTION OF EMBODIMENT(S)

[0009]

As a transfer device of pelletized products of the invention, an exemplary embodiment related to a transfer device of hydrogenated petroleum resin pellets will be described below with reference to the attached drawings.

5 The pelletized product in a form of hydrogenated petroleum resin pellets will be exemplified in the invention. However, the invention is also applicable to various granular substances and especially to granular substances easily damaged due to collision.

Initially, an arrangement of a production plant provided with the transfer device of the hydrogenated petroleum resin pellets for producing the hydrogenated petroleum
10 resin pellets will be described below.

[0010]

Arrangement of Production Plant of Hydrogenated Petroleum Resin Pellets

As shown in Fig. 1, a production plant 1 for hydrogenated petroleum resin pellets is a plant for producing hydrogenated petroleum resin pellets from a hydrogenated
15 petroleum resin material.

The production plant 1 includes: a polymerizing portion 2; a hydrogenating portion 3; a hydrogenation solvent recovering portion 4; a pelletizing portion 5; a transferring portion 6; a storage portion 7; and a control portion (not shown).

[0011]

20 Polymerization Reaction

The polymerizing portion 2 performs a polymerization reaction in which a cyclopentadiene compound and a vinyl aromatic compound are thermally polymerized to produce a copolymer.

The polymerizing portion 2 is provided with, for instance, a polymerization
25 reaction tank in which the hydrogenated petroleum resin materials in a form of the cyclopentadiene compound and the vinyl aromatic compound are thermally polymerized using a solvent.

Examples of the cyclopentadiene compound include cyclopentadiene, methylcyclopentadiene, ethylcyclopentadiene, dimmer thereof and co-dimers thereof.

Examples of the vinyl aromatic compound include styrene, α -methylstyrene and vinyl toluene.

Examples of the solvent include an aromatic solvent, naphthene solvent and aliphatic hydrocarbon solvent. Specifically, benzene, toluene, xylene, cyclohexane, methylcyclohexane, dimethylcyclohexane and ethylcyclohexane are suitably usable. The solvent is recovered as necessary from the polymerization reaction tank to be recycled.

The recovered solvent typically contains a low-molecular-weight component with a molecular weight approximately in a range from 250 to 300.

In order to avoid degradation of the physical properties, the concentration of the low-molecular-weight component is at least set at 4 mass% or less when the solvent is recycled for the thermal polymerization. According to the content of the low-molecular-weight component in the recovered solvent, the low-molecular-weight component is further separately removed or the solvent is diluted with a new solvent so that the concentration of the low-molecular-weight component falls at 4 mass% or below before being used as the polymerization solvent at the start of the polymerization reaction.

[0012]

The polymerization reaction tank is a reactor for performing the polymerization in a pressurized and heated environment. The polymerization reaction tank includes a stirrer and a heater (both not shown). A first material tank, a second material tank and a solvent tank of the solvent recovering portion are connected to the polymerization reaction tank, whereby the cyclopentadiene compound, the vinyl aromatic compound and the solvent are put into the polymerization reaction tank as needed. The obtained copolymer flows out through the bottom of the polymerization reaction tank to be subjected to the subsequent hydrogenation reaction.

Herein, though the mixture ratio of the cyclopentadiene compound and the vinyl aromatic compound is not particularly limited, a typical ratio (the cyclopentadiene compound : the vinyl aromatic compound) is in a range from 70:30 to 20:80.

Further, the used amount of the polymerization solvent is in a range from 50 to 500 parts by mass relative to 100 parts by mass of a mixture of the monomers.

[0013]

At the start of the thermal polymerization, it is desirable that the temperature of the solvent is heated to 100 degrees C or more, preferably 150 degrees C or more in the polymerization reaction tank. The mixture of the cyclopentadiene compound and the vinyl aromatic compound is added in a divided manner into the heated solvent in the polymerization reaction tank for copolymerization.

The time for adding the mixture in a divided manner is typically in a range from 0.5 to 5 hours. It is desirable that the mixture is added in equal parts. The copolymerization reaction desirably continues after the addition of the mixture of the cyclopentadiene compound and the vinyl aromatic compound is completed. Though the reaction conditions at this time are not specifically limited, the typical reaction temperature is in a range from 150 to 350 degrees C, the typical reaction pressure is in a range from 0 to 2 MPa and the typical reaction time is in a range from 1 to 10 hours.

After the thermal polymerization in the polymerization reaction tank according to the above conditions, a copolymer having a softening point in a range from 60 to 130 degrees C, a content of the vinyl aromatic compound in a range from 30 to 90 mass%, a bromine number in a range from 30 to 90 g/100g and a number average molecular weight in a range from 400 to 1000 is obtained.

[0014]

Hydrogenation Reaction

In the hydrogenating portion 3, a hydrogenation reaction for adding hydrogen to the copolymer generated by the thermal polymerization in the polymerizing portion 2 to obtain a hydrogenated product is performed.

The hydrogenating portion 3 includes a plurality of hydrogenation reactors for performing the hydrogenation reaction for adding hydrogen to the copolymer generated by the thermal polymerization in the polymerizing portion 2 under the presence of the hydrogenation solvent, and the like.

Examples of the hydrogenation solvent are cyclohexane, methylcyclohexane, dimethylcyclohexane, ethylcyclohexane and tetrahydrofuran.

A hydrogenation catalyst is fed in each of the hydrogenation reactors. The hydrogenation reactors may be used in multiple stages. A nickel catalyst, palladium catalyst, cobalt catalyst, platinum catalyst, rhodium catalyst and the like are used for the hydrogenation catalyst. Under the presence of the hydrogenation catalyst, hydrogen and the copolymer are subjected to a hydrogenation reaction at a temperature in a range from 120 to 300 degrees C and a reaction pressure in a range from 1 to 6 MPa and for a reaction time in a range from 1 to 7 hours.

A hydrogenated product having a softening point in a range from 70 to 140 degrees C, a content of the vinyl aromatic compound in a range from 0 to 35 mass%, a bromine number in a range from 0 to 30 g/100g and a number average molecular weight in a range from 400 to 1000 is obtained according to the above hydrogenation conditions.

In the hydrogenating portion 3, gas phase component including unreacted hydrogen is separated to be recovered after the hydrogenation by the hydrogenation reactors and is subjected to a process outside the system.

[0015]

Hydrogenation Solvent Removal

The hydrogenation solvent recovering portion 4 separates and removes the hydrogenation solvent from the hydrogenated product. The hydrogenation solvent recovering portion 4 includes a solvent evaporation tank 41 (first evaporator), a thin-film evaporator 42 (second evaporator) and the like.

The solvent evaporation tank 41 is connected to the hydrogenating portion 3. The solvent evaporation tank 41 separates and recovers the hydrogenation solvent by evaporation from the hydrogenated product obtained in the hydrogenating portion 3. The evaporated hydrogenation solvent is separately recovered and is recycled as the hydrogenation solvent used during the hydrogenation reaction in the hydrogenating portion 3.

The thin-film evaporator 42 is connected to the solvent evaporation tank 41. The thin-film evaporator 42 separates and recovers the hydrogenation solvent remained in the hydrogenated product by evaporation. The evaporated hydrogenation solvent and the low-

molecular-weight component are separately recovered and are recycled as a hydrogenation solvent used during the hydrogenation reaction in the hydrogenating portion 3 according to the values of the physical properties of the hydrogenated petroleum resin pellets to be produced (target hydrogenated petroleum resin).

5 [0016]

An adding portion for adding an antioxidant is provided between the solvent evaporation tank 41 and the thin-film evaporator 42 of the hydrogenation solvent recovering portion 4.

10 The adding portion of the antioxidant adds an antioxidant to the hydrogenated product from which most of the hydrogenation solvent is removed in the solvent evaporation tank 41.

The hydrogenation solvent separated and recovered in the evaporation process in the downstream thin-film evaporator 42 from the hydrogenation solvent remained together with the solvent in which the antioxidant is dissolved can be recycled for the
15 hydrogenation reaction so that the hydrogenation reaction is not influenced thereby.

The solvent in which the antioxidant is dissolved is separated and recovered from the hydrogenated product together with the hydrogenation solvent by the downstream thin-film evaporator 42.

[0017]

20 A near-infrared analyzing portion 45 for measuring physical properties of the molten resin (the hydrogenated product before being pelletized: i.e. hydrogenated petroleum resin from which the hydrogenation solvent and the low-molecular-weight component are removed) is provided between the hydrogenation solvent recovering portion 4 and the downstream pelletizing portion 5.

25 The near-infrared analyzing portion 45 measures using near-infrared light the physical properties of the molten hydrogenated petroleum resin to be supplied to the pelletizing portion 5 by a supply pump 44. Specifically, the near-infrared analyzing portion 45 includes a light-transmissive pipe in which the molten resin flows, a spectrum detecting portion that irradiates the near-infrared light to the molten resin flowing in the

light-transmissive pipe to detect the near-infrared absorption spectrum, and a calculating portion that calculates the physical properties of the molten resin based on a near-infrared absorption spectrum detected by the spectrum detecting portion with reference to an analytical curve database.

5 [0018]

Herein, the analytical curve database stores analytical curve data based on the measurement of the near-infrared absorption spectrum of the produced various hydrogenated petroleum resin pellets and actual measurement results of the physical properties of the hydrogenated petroleum resin pellets.

10 The analytical curve data includes, for instance, analytical curve data of an aromatic content ratio of the molten resin as shown in a graph in Fig. 2, analytical curve data of a bromine number of the molten resin as shown in a graph in Fig. 3 and analytical curve data of a softening point of the produced hydrogenated petroleum resin pellets as shown in a graph in Fig. 4.

15 These analytical curves are obtained based on the measurement results represented by the dots in Figs. 2 to 4 showing measurement results of the aromatic content ratio, bromine number and softening point of the previously produced various hydrogenated petroleum resin pellets. These analytical curves are calculated according to typically used various calculation methods.

20 [0019]

The calculating portion calculates the physical properties (i.e. the aromatic content ratio, bromine number and softening point of the hydrogenated compound) of the measured molten resin from the measurement results of the near-infrared absorption spectrum of the hydrogenated product detected by the spectrum detecting portion with
25 reference to the analytical curve data in the analytical curve database.

Then, the calculating portion sends the detected physical properties of the hydrogenated petroleum resin pellets to the control portion to control the operation conditions of the production plant 1 so that the hydrogenated petroleum resin pellets under production exhibit desired physical properties.

[0020]

Pelletizing

The pelletizing portion 5 pelletize the molten resin (i.e. the hydrogenated product from which the hydrogenation solvent is removed and to which the antioxidant is added) into hemispherical hydrogenated petroleum resin pellets. The pelletizing portion 5 includes a pelletizer, a pellet-air-cooling unit (both not shown) and the like.

In the pelletizer, the molten resin is, for instance, dropped onto a cooling conveyor to produce hemispherical hydrogenated petroleum resin pellets. The produced hydrogenated petroleum resin pellets are scraped off from the surface of the cooling conveyor to be supplied to the transferring portion 6 for transferring the pellets to the storage portion 7.

[0021]

Transfer

The transferring portion 6 transfers the hydrogenated petroleum resin pellets produced in the pelletizing portion 5 to the storage portion 7.

The transferring portion 6 includes a chute connected to the pelletizing portion 5, a transfer conveyor, a bucket conveyor and the like. The transferring portion 6 transfers the hydrogenated petroleum resin pellets.

It should be understood that the transferring portion 6 is not necessarily constructed as described above but various transfer devices and structures can be used for the transferring portion 6. However, since the hydrogenated petroleum resin pellets are relatively brittle, it is preferable that the transferring portion 6 is constructed so that the hydrogenated petroleum resin pellets are not damaged due to impacts during the transfer.

[0022]

Storage

The storage portion 7 stores the hydrogenated petroleum resin pellets transferred by the transferring portion 6 in a manner so that the pellets are capable of being taken out.

The storage portion 7 includes storage hopper(s) (not shown) and a switching portion (not shown) for loading the hydrogenated petroleum resin pellets transferred by

the bucket conveyor of the transferring portion 6 to a predetermined one of the storage hopper(s).

[0023]

Control

5 The control portion controls the entire process of the production plant 1. The control portion includes a memory unit for storing various programs and database and an arithmetic unit for running the program to perform various calculations in order to control the entire process of the production plant 1. Specifically, the control unit controls: a temperature, a pressure and a reaction time in the polymerization reaction in the
10 polymerizing portion 2 and the hydrogenation reaction in the hydrogenating portion 3; the recovery of the hydrogenation solvent in the hydrogenation solvent recovering portion 4; the addition of the antioxidant in the adding portion of the antioxidant; the pelletization of the hydrogenated petroleum resin pellets in the pelletizing portion 5; the transferring operation and intake/discharge of air by the transferring portion 6; operation conditions of
15 various valves, blowers and pumps; and the like.

 Further, the control portion compares the property values of the hydrogenated compound under production sent from the calculating portion of the near-infrared analyzing portion 45 with physical property values of the target hydrogenated petroleum resin pellets. Then, the control portion controls the operating condition of the production
20 plant 1 so that the property of the hydrogenated compound become equal to the target physical properties of the hydrogenated petroleum resin pellets. Specifically, the control portion changes at least one of hydrogenation reaction conditions including the temperature, pressure, reaction time and hydrogen content in accordance with a difference between the measured aromatic content ratio and a target aromatic content ratio and a
25 difference between the measured bromine number and a target bromine number. Further, the control portion changes at least one of operation conditions including the temperature and pressure in the thin-film evaporator 42 in the hydrogenation solvent removing step for separating the hydrogenation solvent or the low-molecular-weight component in accordance with a difference between the measured softening point and a target softening

point.

[0024]

Advantage(s) of Embodiment(s)

As described above, in the above exemplary embodiment, the near-infrared
5 absorption spectrum of the hydrogenated compound (hydrogenated petroleum resin) in a
form of the molten resin from which the hydrogenation solvent is separated in the
hydrogenation solvent removing step is measured to calculate the physical property values
of the hydrogenated compound based on the analytical curve data, and a series of
processes for producing the hydrogenated petroleum resin pellets is controlled based on
10 the obtained physical property values.

Accordingly, the physical properties of the hydrogenated petroleum resin under
production can be automatically detected without requiring an analysis outside the
production plant and the operation can be controlled based on the automatically detected
physical properties. Thus, the hydrogenated petroleum resin of desired physical properties
15 can be easily produced.

[0025]

Further, in the above exemplary embodiment, at least one of the temperature,
pressure, reaction time and hydrogen content of the hydrogenation reaction that affect the
aromatic content ratio and the bromine number is controlled so that the difference between
20 the physical property value of at least one of the aromatic content ratio and the bromine
number shown by the measurement results of the measured near-infrared absorption
spectrum and the physical property values of the target hydrogenated petroleum resin
pellets becomes small.

Thus, a hydrogenated petroleum resin of desired physical properties can be easily
25 produced.

[0026]

Further, in the above exemplary embodiment, at least one of the temperature and
pressure in the step for separating the hydrogenation solvent or the low-molecular-weight
component that affect the softening point is controlled so that the difference between the

softening point indicated by the measurement results of the measured near-infrared absorption spectrum and the softening point of the target hydrogenated petroleum resin pellets becomes small.

Thus, a hydrogenated petroleum resin of desired physical properties can be easily
5 produced.

[0027]

Modification(s)

Incidentally, it should be understood that the scope of the present invention is not limited to the above-described exemplary embodiment(s) but includes modifications and
10 improvements as long as the modifications and improvements are compatible with the invention.

Specifically, it is not necessary for the control portion to control the operation conditions of the production plant by a computer program and the like. For instance, the control portion may notify a worker to control the operation conditions of the production
15 plant based on the measurement results and the worker may change the operation conditions based on the notified results.

[0028]

In the above exemplary embodiment, though the aromatic content ratio, bromine number and softening point are respectively measured to control the operation conditions
20 in the hydrogenation reaction step and the hydrogenation solvent removing step, only one or two of the physical property values of the aromatic content ratio, bromine number and softening point may be measured. In controlling the operation conditions of the hydrogenation reaction step based on the aromatic content ratio or bromine number, all of the temperature, pressure, reaction time and hydrogen content in the hydrogenation are not
25 necessarily controlled but at least one of the operation conditions including the temperature, pressure, reaction time and hydrogen content is necessary to be measured. Similarly, in controlling the operation conditions of the hydrogenation solvent removal step based on the softening point, both of the temperature and pressure in the thin-film evaporator 42 are not necessarily controlled but at least one of the operation conditions of

the temperature and pressure is necessary to be measured.

Further, though the hydrogenation reaction step is exemplarily performed in two stages (i.e. the solvent evaporation tank 41 and the thin-film evaporator 42), the hydrogenation solvent and the low-molecular-weight component may be separated in a single stage or in three or more stages. In such an arrangement, at least one of the pressure and temperature in the step for separating the low-molecular-weight component that especially affects the softening point only needs to be controlled.

[0029]

Other specific structure and process in implementing the invention may be altered otherwise as long as the structure and the process are compatible with the invention.

INDUSTRIAL APPLICABILITY

[0030]

The invention is applicable for producing hydrogenated petroleum resin pellets by separating a hydrogenation solvent to obtain a molten resin.

EXPLANATION OF CODES

[0031]

3...hydrogenating portion

4...hydrogenation solvent recovering portion

42...thin-film evaporator

CLAIMS

1. A method for producing a hydrogenated petroleum resin, comprising:
measuring a near-infrared absorption spectrum of a molten resin from which a hydrogenation solvent is separated; and
controlling at least one of a temperature, a pressure, a reaction time and a hydrogen content of a hydrogenation reaction is controlled such that a difference between the physical property value of the molten resin and a physical property value of a target hydrogenated petroleum resin pellet becomes small, based on a physical property value of at least one of an aromatic content ratio and a bromine number of the molten resin indicated by a result of the measurement.
2. The method for producing the hydrogenated petroleum resin according to claim 1, further comprising:
based on a softening point of the molten resin indicated by the result of the measurement, controlling at least one of a temperature and a pressure in a step for separating the hydrogenation solvent or a low-molecular-weight component such that a difference between the softening point and a softening point of a target hydrogenated petroleum resin pellet becomes small.
3. A method for producing a hydrogenated petroleum resin, comprising:
measuring a near-infrared absorption spectrum of a molten resin from which a hydrogenation solvent is separated; and
based on a softening point of the molten resin indicated by the result of the measurement controlling at least one of a temperature and a pressure in a step for separating the hydrogenation solvent or a low-molecular-weight component such that a difference between the softening point of the molten resin and a softening point of a target hydrogenated petroleum resin pellet becomes small.
4. The method for producing a hydrogenated petroleum resin according to any one of claims 1 to 3, wherein
in order to manufacture the hydrogenated petroleum resin pellet,
a hydrogenated petroleum resin material is thermally polymerized using a solvent,
hydrogen is added to a copolymer obtained in the thermal polymerization under a presence of a hydrogenation catalyst and hydrogenation solvent to perform a hydrogenation reaction,
the hydrogenation solvent is separated and removed from the hydrogenation product obtained in the hydrogenation reaction to obtain a molten resin whose near-infrared absorption spectrum is measured, and
the molten resin is pelletized.
5. The method for producing a hydrogenated petroleum resin according to claim 4, wherein
in the thermal polymerization, the hydrogenated petroleum resin materials in a form of a cyclopentadiene compound and a vinyl aromatic compound are thermally polymerized.

6. The method for producing a hydrogenated petroleum resin according to claim 5, wherein

the cyclopentadiene compound is selected from the group consisting of cyclopentadiene, methylcyclopentadiene, ethylcyclopentadiene, dimer thereof and co-dimers thereof.

7. The method for producing a hydrogenated petroleum resin according to claim 5 or 6, wherein the vinyl aromatic compound is selected from the group consisting of styrene, α -methylstyrene and vinyl toluene.

8. The method for producing a hydrogenated petroleum resin according to any one of claims 5 to 7, wherein

a mixture ratio of the cyclopentadiene compound and the vinyl aromatic compound (the cyclopentadiene compound : the vinyl aromatic compound) is in a range from 70:30 to 20:80 in a mass ratio.

9. The method for producing a hydrogenated petroleum resin according to any one of claims 4 to 8, wherein

the solvent comprises an aromatic solvent, naphthene solvent and aliphatic hydrocarbon solvent.

10. The method for producing a hydrogenated petroleum resin according to any one of claims 4 to 9, wherein

the solvent used in the thermal polymerization is recovered to be reused as the solvent for the thermal polymerization.

11. The method for producing a hydrogenated petroleum resin according to any one of claims 4 to 10, wherein

the hydrogenation solvent separated and removed from the hydrogenated product is recovered to be reused as the hydrogenation solvent used in the hydrogenation reaction.

12. The method for producing a hydrogenated petroleum resin according to any one of claims 4 to 11, wherein

the hydrogenation solvent and the low-molecular-weight component are further separated and removed from the hydrogenated product from which the hydrogenation solvent is separated and removed.

13. A production plant of hydrogenated petroleum resin pellets, comprising:

a polymerizing portion for polymerizing a hydrogenated petroleum resin material to obtain a copolymer;

a hydrogenating portion for adding hydrogen to the copolymer obtained in the polymerizing portion to hydrogenate the copolymer to obtain a hydrogenated product;

a hydrogenation solvent recovering portion for separating and removing a hydrogenation solvent from the hydrogenated product obtained in the hydrogenating portion to obtain a molten resin;

a pelletizing portion for pelletizing the molten resin obtained in the hydrogenation solvent recovering portion to obtain a hydrogenated petroleum resin pellets; and

a controller for controlling a process of an entirety of the production plant, wherein

the hydrogenation solvent recovering portion comprises a near-infrared analyzing portion for measuring a near-infrared absorption spectrum of the obtained molten resin and calculating a physical property value of at least one of an aromatic content ratio and a bromine number of the molten resin based on an analytical curve database, and

the controller controls at least one of a temperature, a pressure, a reaction time and a hydrogen content of a hydrogenation reaction based on the physical property value calculated by the near-infrared analyzing portion such that a difference between the physical property value of the molten resin and a physical property value of a target hydrogenated petroleum resin pellet becomes small.

14. A production plant of hydrogenated petroleum resin pellets, comprising:

a polymerizing portion for polymerizing a hydrogenated petroleum resin material to obtain a copolymer;

a hydrogenating portion for adding hydrogen to the copolymer obtained in the polymerizing portion to hydrogenate the copolymer to obtain a hydrogenated product;

a hydrogenation solvent recovering portion for separating and removing a hydrogenation solvent from the hydrogenated product obtained in the hydrogenating portion to obtain a molten resin;

a pelletizing portion for pelletizing the molten resin obtained in the hydrogenation solvent recovering portion to obtain a hydrogenated petroleum resin pellets; and

a controller for controlling a process of an entirety of the production plant, wherein

the hydrogenation solvent recovering portion comprises a near-infrared analyzing portion for measuring a near-infrared absorption spectrum of the obtained molten resin and calculating a softening point of the molten resin based on an analytical curve database, and

the controller controls at least one of a temperature and a pressure at which the hydrogenation solvent or the low-molecular-weight component is separated in the hydrogenation solvent recovering portion based on the softening point calculated by the near-infrared analyzing portion such that a difference between the softening point of the molten resin and the softening point of a target hydrogenated petroleum resin pellet becomes small.