



(51) International Patent Classification:

B01J 37/03 (2006.01) **C11C 3/10** (2006.01)
B01J 23/02 (2006.01) **B01J 37/04** (2006.01)
B01J 23/04 (2006.01) **B01J 37/08** (2006.01)
B01J 23/34 (2006.01) **B01J 33/00** (2006.01)

(21) International Application Number:

PCT/GB2014/052515

(22) International Filing Date:

15 August 2014 (15.08.2014)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

1315276.4 28 August 2013 (28.08.2013) GB

(71) Applicant: **JOHNSON MATTHEY PUBLIC LIMITED COMPANY** [GB/GB]; 5th Floor, 25 Farringdon Street, London EC4A 4AB (GB).

(72) Inventors: **ELLIS, Peter Richard**; 21 Lea Road, Sonning Common, Reading Berkshire RG4 9LH (GB). **EVANS, Gary**; 117 Luscinia View, Napier Road, Reading Berkshire RG1 8AF (GB). **ZWIJNENBURG, Aalbert**; Bieslookveld 18, NL-7006 TH Doetinchem (NL).

(74) Agent: **GIBSON, Sara Hillary Margaret**; Johnson Matthey Catalysts, PO Box 1, Belasis Avenue, Billingham Cleveland TS23 1LB (GB).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: INTERESTERIFICATION CATALYST AND PROCESS

(57) Abstract: A process for the production of an ester product from a mixture of at least two different ester compounds comprises the steps of mixing together at least two different starting ester compounds to form a first ester mixture; and contacting said first ester mixture with a catalyst comprising from 30 -60% of calcium oxide and at least one second metal oxide at a temperature of at least 180 °C, for a duration of at least one hour, with mixing, to form a second ester mixture having a melting point which is lower than the melting point of said first ester mixture.



WO 2015/028779 A1