

1

1 A PROCESS FOR MAKING LOW OPTICAL DENSITY POLYMERS AND
2 COPOLYMERS FOR PHOTORESISTS AND OPTICAL APPLICATIONS

3
4
5
6

7 BACKGROUND OF THE INVENTION

8 1. Field of the Invention

9 The present invention pertains to a process for making and to
10 compounds comprising homopolymers, copolymers, and terpolymers (hereinafter
11 referred to as "polymers") of 4-hydroxystyrene and/or substituted 4-
12 hydroxystyrene. The polymers have low optical density (absorbance) over a
13 wavelength range from about 240 to 260 nm, as well as low optical density over
14 the visible and near UV spectrum (310 to 800 nm). Such polymers can be
15 produced using a single compound which serves as a reaction medium for the
16 polymerization, as a chain transfer agent and as a transesterification reactant,
17 providing an unusually economical process. The polymers of the present
18 invention are particularly useful (directly or in modified form) as photoresist
19 materials for deep UV, X-ray, and E-Beam imaging systems.

20 2. Description of the Background Art

21 There are numerous applications within the semiconductor industry
22 which require photoresists materials having low absorbance in the deep U.V. (240

1 to 260 nm) wavelength region. The novolak photoresist polymers which have
2 been used for optical lithography are limited to wavelengths longer than 300 nm
3 because of the high absorbance of the novolak material at shorter wavelengths. It
4 has recently been learned that polymers and copolymers of 4-hydroxystyrene and
5 substituted 4-hydroxystyrenes are particularly useful over a wavelength range
6 from about 240 to 260 nm. The molar absorptivity (ϵ) of such polymers and
7 copolymers over this wavelength range is as low as about $50 \text{ l cm}^{-1} \text{ mole}^{-1}$.

8 There is a need for an economic method or process for producing
9 polymers and copolymers of 4-hydroxystyrene and substituted 4-hydroxystyrene.

10 U.S. Patent No. 4,822,862, issued April 18, 1989, to R. W. Rupp et al.,
11 describes the homopolymerization and copolymerization of 4-acetoxystyrene
12 monomer (4-ASM) in an aqueous emulsion and, without isolation, the hydrolysis
13 of the polymers and copolymers of 4-ASM to homopolymers and copolymers of
14 4-hydroxystyrene using a base.

15 U.S. Patent No. 4,912,173, issued March 27, 1990, to D. L. Keene et
16 al., discloses a process for hydrolyzing homopolymers of 4-ASM to
17 homopolymers of 4-hydroxystyrene. The hydrolysis is carried out in an aqueous
18 suspension in the presence of a nitrogen-comprising base.

19 European Patent No. 343,986, issued November 29, 1989, to R. Vicari
20 et al., describes the preparation of polymers of 4-ASM or polymers of 4-
21 hydroxystyrene by suspension polymerization. The suspension polymerization
22 comprises forming an aqueous suspension of 4-ASM in the presence of

1 polyacrylic acid and at least 2 free radical catalysts, one of which has a half life
2 of 1 hour below 100°C and the other which has a half life of 1 hour above 100°C.

3 The suspension is heated to 70-95°C to achieve about 50 wt%
4 polymerization, and then polymerization is completed by heating above 95°C. To
5 form the polymer of 4-hydroxystyrene (4-HSM), the reaction temperature is then
6 reduced to between 30-95°C and the suspension is reacted with ammonium
7 hydroxide in an amount of at least 2 moles of ammonia for each equivalent of 4-
8 ASM.

9 The poly(4-hydroxystyrene) produced by the above-described method,
10 typically has an absorbance at 248 nm which ranges from about 300 to 350
11 liters/cm⁻¹ mole⁻¹ (molar absorptivity, ϵ).

12 U.S. Patent No. 4,898,916, issued February 6, 1990, to B. Gupta et al.
13 describes a process for the conversion of poly(4-acetoxystyrene) (4-PAS) to
14 poly(4-hydroxystyrene) (4-PHS). The process comprises: a) forming an alcoholic
15 slurry of (4-PAS); b) adding an acid to the slurry; and c) maintaining slurry
16 temperature at 20-65°C until the polymer dissolves in the alcohol, indicating
17 complete acetoxy to phenolic group conversion.

18 Processes wherein the 4-ASM is polymerized into a homopolymer or a
19 copolymer with another copolymerisable monomer, and especially wherein the
20 comonomer is styrene, are claimed. The 4-PHS or copolymers of 4-HSM is
21 expected to have a molar absorptivity, ϵ , ranging from about 300 to 1,000
22 depending on the 4-PAS used as the precursor for the reaction described.

1 U.S. Patent No. 4,689,379, issued August 25, 1987, to J. D. Elmore et
2 al., discloses the hydrolysis of polymers of 4-ASM by methanolysis with
3 quaternary ammonium hydroxides to 4-PHS.

4 European Patent Application No. 87307912.3, published March 16,
5 1988, discloses a process for preparing polymers comprising 4-PHS by initially
6 reacting 4-ASM and methanol, with subsequent reaction of 4-ASM, methanol,
7 4-HSM, polymers of 4-ASM, and polymers of 4-HSM, in the presence of an
8 ammonium base using a free radical initiator. The initiator is selected from a
9 group of initiators including benzoyl peroxide, lauroyl peroxide, acetyl peroxide,
10 cumene hydroperoxide, paramethane hydroperoxide, etc.

11 G. Pawlowski et al. disclosed the polymerization of 3-methyl-4-
12 acetoxystyrene using 2,2'-azobis(2-methylpropanenitrile) in tetrahydrofuran
13 (THF) to produce poly(3-methyl-4-acetoxystyrene) at the March 1990 SPIE
14 meeting held at San Jose, California.

15 The poly(3-methyl-4-acetoxystyrene) polymerized by G. Pawlowski et
16 al. in THF was isolated (precipitated) and dried prior to subsequent use. This
17 dried poly(3-methyl-4-acetoxystyrene) can then be slurried in methanol and
18 processed as described above by B. Gupta et al. to provide homopolymers and
19 copolymers of poly(3-methyl-4-hydroxystyrene).

20 However, preparation of 4-HSM polymers using a combination of the
21 above techniques would be very expensive. The THF solvent used by Powlowski
22 et al. in polymerizing the 4-PAS is toxic. In addition, the precipitation and
23 drying of the 4-PAS adds additional cost in the form of unit operations and waste

disposal. In addition, the method of Gupta et al. disclosed in U.S. Patent No. 4,898,916 is difficult to accomplish on a large scale due to problems encountered in a making of a slurry of the 4-PAS in alcohol. The 4-PAS tends to "clump" or remain in agglomerated form in the alcohol, due to insolubility.

SUMMARY OF THE INVENTION

In accordance with the present invention, it has been discovered that despite the partial insolubility of poly(4-acetoxystyrene) (4-PAS) in alcohols, it is possible to polymerize homopolymers, copolymers, and terpolymers (hereinafter referred to as "polymers") comprising poly(4-acetoxystyrene) and/or substituted poly(4-acetoxystyrene) (S-4-PAS) in an alcohol reaction medium, and to subsequently transesterify the polymer comprising 4-PAS and/or S-4-PAS, preferably in the same alcohol reaction medium, to produce a polymer comprising poly(4-hydroxystyrene (4-PHS) and/or substituted poly(4-hydroxystyrene) (S-4-PHS). The initial polymerization of 4-acetoxystyrene monomer (4-ASM) and/or substituted 4-acetoxystyrene monomer (S-4-ASM) to produce a polymer comprising 4-PAS and/or S-4-PAS is carried out in a manner which permits formation of a transesterification reaction mixture comprising no more than 10% by weight of residual monomer(s) (based on the polymer produced). This 10% by weight residual monomer can be achieved by obtaining 90% conversion of the combination of all monomers initially present during the polymerization reaction, or by removing such monomers from the reaction mixture after the polymerization is completed but prior to the transesterification reaction. The



1 initial concentration of monomer in the monomer/reaction medium mixture is
2 preferably greater than 40% by weight. The transesterification of 4-PAS and/or
3 S-4-PAS is carried out so that at least 85% of the 4-PAS and/or S-4-PAS is
4 converted to 4-PHS and/or S-4-PHS.

5 As described above, it would be possible to produce polymers
6 comprising the 4-PAS and/or S-4-PAS by polymerizing the starting monomers to
7 less than 90% conversion, so long as residual monomer is removed from the
8 polymerization reaction mixture prior to the transesterification reaction. It has
9 been discovered that, in the production of homopolymers and copolymers of 4-
10 PAS and/or S-4-PAS, as the polymerization of monomers progresses and the
11 polymer formed therefrom increases in molecular weight, the polymer becomes
12 insoluble in an alcohol polymerization medium. It is then possible to discontinue
13 agitation of the reaction mixture, permitting the swollen polymer to separate, to
14 decant the alcohol reaction medium containing the residual monomer, to replace
15 the decanted alcohol with fresh, clean alcohol, and to proceed with the
16 transesterification. This removal of the 4-PAS and/or S-4-PAS alcohol
17 polymerization medium (and replacement with fresh clean alcohol) accomplishes
18 the removal of excess initiator, initiator fragments, unreacted monomer and
19 oligomers, all of which can be sources for harmful, optical-density-increasing
20 contamination of the 4-PHS and/or S-4-PHS product.

21 The above description is in terms of the use of an alcohol solvent as the
22 polymerization reaction medium, since this is the most preferred embodiment of
23 the present invention. However, other solvents can be used in the method of the

1 present invention, so long as there is sufficient alcohol present during the
2 transesterification step for transesterification to take place.

3 Preferred "other solvents" are polar solvents which do not contain
4 acetate groups. In a less preferred embodiment of the present invention, these
5 polar solvents can be used as the sole solvent during polymerization of the
6 polymer comprising 4-acetoxystyrene and/or substituted 4-acetoxystyrene;
7 however, an alcohol must then be added prior to the transesterification to a
8 polymer comprising 4-hydroxystyrene and/or substituted 4-hydroxystyrene. In a
9 more preferred embodiment of the present invention, the polar solvent would be
10 used as a co-solvent with an alcohol throughout the process of the present
11 invention. Examples of suitable polar solvents include tetrahydrofuran,
12 methylethyl ketone, acetone, and 1,4-dioxane.

13 Nonpolar solvents can be used as co-solvents in combination with an
14 alcohol, provided the concentration of the nonpolar solvent is sufficiently low.
15 Typically, the nonpolar solvent is present at a concentration of less than 25% by
16 weight. Examples of suitable nonpolar solvents include heptane, hexane, and
17 cyclohexane.

18 Other comonomers can be copolymerized in combination with the 4-
19 ASM and/or S-4-ASM so long as the other comonomers do not absorb at
20 radiation wavelengths ranging from about 240 to about 260 nm.

21 "Substituted", as referred to above is intended to mean that the ring
22 structure of the molecule has substituent groups thereon, wherein the substituent

1 groups are methyl or ethyl. Preferred substituent groups are methyl and the
2 preferred substituted positions are the 3, 5, or 3 and 5 positions.

3 It is possible to obtain polymers comprising 4-PHS and/or S-4-PHS
4 having a molar absorptivity, ϵ , ranging from about 40 to about 250 (at a
5 wavelength of 248 nm) using the method described above. To obtain a polymer
6 comprising 4-PHS and/or a S-4-PHS having this molar absorptivity at 248 nm, it
7 is necessary to:

- 8 1) a. Use a polymerization initiator which does not comprise an absorbant
9 structure; absorbant structures such as aromatic rings increase molar
10 absorptivity, ϵ_{248} , typically by a factor of 2 when the weight average
11 molecular weight of the polymer comprising 4-PHS or S-4-PHS ranges
12 from about 5,000 to about 25,000 (as determined by gel permeation
13 chromatography (GPC vs. polystyrene standards), or
14 b. Use a polymerization initiator which does comprise an absorbant structure
15 but limit the initiator concentration to less than about 3 mole % of the
16 monomer used to produce the polymer.
- 17 2) Obtain a polymerization conversion of the monomer(s) of at least 90% by
18 weight; or remove residual monomer(s) from the reaction medium so that
19 residual monomer in the subsequent transesterification reaction mixture
20 comprises no more than 10% by weight of the polymer comprising 4-PAS
21 and/or S-4-PAS polymer;
- 22 3) Obtain a transesterification conversion of at least 85% by weight;

4) Use acid catalysts in the alcoholysis transesterification of the polymer comprising 4-PAS or S-4-PAS to the polymer comprising 4-PHS or S-4-PHS, respectively; use of basic catalysts can cause the formation of quinones and other chemical structures which absorb over the 240-260 nm wavelength range, and can also absorb over the near UV and visible wavelengths from about 310-800 nm. 4-PHS prepared using basic catalysts is typically opaque and brown in color.

It is also advisable to avoid monomer storage inhibitors which substantially absorb over the deep UV wavelengths.

The composition of the polymers made by the process described above has empirically been determined to meet specific requirements which result in the desired low optical density (absorbivity of 250 or less) over the 240 to 260 nm wavelength. In particular, the polymer comprising 4-PHS (and/or S-4-PHS) contains less than about 2.5% by weight of residual 4-hydroxystyrene monomer (or derivative residues thereof). When the polymer contains as much as 2.5% by weight of such residual 4-hydroxystyrene monomer, then the amount of poly 4-acetoxystyrene which remains in the polymer (due to less than 100% transesterification) must be less than about 2.5% by weight of the polymer. When the polymer contains less than 2.5% by weight of the residual 4-hydroxystyrene monomer (or derivative residues thereof), the amount of poly 4-acetoxystyrene which remains in the polymer can be larger. For example, when residual 4-hydroxystyrene monomer is less than about 0.7% by weight of the

1 polymer, the poly(4-acetoxystyrene) content must be less than about 13% by
2 weight of the polymer.

3 For purposes of clear expression of the concept of the present invention,
4 the language is simplified in portions of the following text by describing the
5 invention in terms of the preparation of polymers comprising poly(4-
6 hydroxystyrene). However, it is intended that polymers comprising substituted
7 poly(4-hydroxystyrene) be included as well. When it is necessary to make a
8 distinction, or when the language does not become too cumbersome, substituted
9 4-acetoxystyrene monomers are discussed specifically.

10 The "single pot", simplified process of the present invention, can be
11 used for the preparation of polymers comprising of poly(4-hydroxystyrene) and
12 comprises the following steps:

13 a) reacting a mixture comprising 4-acetoxystyrene (monomer) and an initiator,
14 which itself, its decomposition products, and capped structures which it
15 produces, do not substantially absorb over the wavelengths ranging between
16 about 240-260 nm; or, using no more than about 3 mole % of an absorbing
17 initiator per mole of monomer, in an organic solvent reaction medium, to
18 produce a polymer comprising 4-acetoxystyrene; wherein, either as a result of
19 monomer conversion or due to removal of residual monomer after
20 polymerization, residual monomer in the subsequent transesterification
21 reaction medium comprises no more than 10% by weight of the polymer
22 comprising 4-acetoxystyrene which is produced; and

1 b) subsequently transesterifying the polymer comprising 4-acetoxystyrene to a
2 polymer comprising 4-hydroxystyrene in a transesterification reaction medium
3 comprising at least one equivalent of alcohol per equivalent of non-
4 transesterified poly(4-acetoxystyrene), using an acid catalyst, wherein at least
5 85% conversion of the poly(4-acetoxystyrene) to poly(4-hydroxystyrene) is
6 achieved.

7 In the most preferred embodiment of the above-described invention, at
8 least the majority of the organic solvent reaction medium of step a) is a C_1 - C_5
9 (straight or branched) alcohol. In addition, the step b) transesterification reaction
10 medium is essentially the same reaction medium as that used in step a) or is a
11 functional equivalent thereof.

12 When monomer(s) other than 4-ASM and/or S-4-ASM are used in
13 combination with these monomers in the above-described process, the other
14 monomer must have at least one vinyl group present and must not substantially
15 absorb radiation over wavelengths ranging from about 240 to about 260 nm.

16 The simplified process of the present invention can be used for the
17 preparation of copolymers of 4-hydroxystyrene with substituted 4-hydroxystyrene,
18 wherein the preferred substituted 4-hydroxystyrene monomer is selected from the
19 group consisting of 4-hydroxystyrene substituted in the 3, 5, or 3 and 5 positions
20 with methyl or ethyl substituents. The process steps for producing a copolymer
21 of 4-PHS with S-4-PHS comprise:

22 a) reacting a mixture comprising 4-acetoxystyrene monomer, substituted 4-
23 acetoxystyrene monomer and an initiator, wherein said initiator and its

1 decomposition products alone, and capped structures which it produces, do
2 not substantially absorb radiation over wavelengths ranging from about 240 to
3 about 260 nm; or, using no more than about 3 mole % of an absorbing
4 initiator per mole of monomer, in an organic solvent reaction medium to
5 produce a copolymer of poly(4-acetoxystyrene) with substituted poly(4-
6 acetoxystyrene), in a manner such that residual monomers present in the
7 reaction medium during subsequent transesterification reaction step(s)
8 comprises no more than 10% by weight of the copolymer formed during the
9 reaction; and

- 10 b) subsequently transesterifying the copolymer of poly(4-acetoxystyrene) and
11 substituted poly(4-hydroxystyrene) to copolymers of poly(4-hydroxystyrene)
12 and substituted poly(4-hydroxystyrene), in a transesterification reaction
13 medium comprising at least one equivalent of alcohol per equivalent of non-
14 transesterified copolymer, using an acid catalyst to achieve transesterification
15 of at least 85% of the poly(4-acetoxystyrene) and poly(4-hydroxystyrene).

16 In the most preferred embodiment of the above-described invention, at
17 least the majority of the organic solvent reaction medium of step a) is a C_1 - C_5
18 (straight or branched) alcohol. In addition, the step b) transesterification reaction
19 medium is essentially the same reaction medium as that used in step a) or is a
20 functional equivalent thereof.

21 The following description applies to the embodiments of the invention
22 for which the process steps are disclosed above.



The initiator used in step a) must not comprise a structure which decomposes to an initiating free radical which alone or as a polymer capping group substantially absorbs in the 240-260 nm wavelength range, when the quantity of such initiator is more than about 3 mole % of the monomer. Such absorbing free radical initiators, which should be avoided at concentrations above that described above, include those having aromatic components, for example benzoyl peroxide, t-butylperoxybenzoate, and di-t-butyl di-peroxyphthalate. Examples of useful initiators which do not substantially absorb over the 240-260 nm wavelength range include, but are not limited to, 2,2'-azobis(2,4-dimethylpentanenitrile), 2,2'-azobis(2-methylpropanenitrile), 2,2'-azobis(2-methylbutanenitrile), 1,1'-azobis(cyclohexanecarbonitrile), t-butyl peroxy-pivalate, t-amyl peroxy-pivalate, t-butyl peroxy-2-ethylhexanoate, diisononanoyl peroxide, decanoyl peroxide, succinic acid peroxide, di(n-propyl) peroxydicarbonate, di(sec-butyl) peroxydicarbonate, di(2-ethyl-hexyl) peroxydicarbonate, t-butylperoxy-neodecanoate, 2,5-dimethyl-2,5-di(2 ethylhexanoylperoxy)hexane, t-amylperoxy-neodecanoate, t-butylperoxy-neodecanoate, and combinations thereof. The most preferred initiators include 2,2'-azobis(2-methylpropanenitrile), 2,2'-azobis(2,4-dimethylpentanenitrile), and t-butylperoxy-pivalate.

The useful initiator for step a) of the present invention should have a half life ranging from about 0.5 to about 10 hours at the temperature at which the reaction is carried out. Typically the reaction temperature is the reflux temperature of the alcohol reaction medium. However, it is not necessary that the reaction temperature be the alcohol reaction medium reflux temperature. Reaction

1 vessel pressure can be used to adjust the reaction temperature. A preferred
2 initiator half life ranges from about 0.75 to about 5 hours at the reaction
3 temperature, with a most preferred initiator having a half life ranging from about
4 1 to about 2 hours.

5 An alcohol used in step a) as the reaction medium can be any of the
6 known alcohols which dissolve the monomer(s), preferably C₁ to C₃ alcohols in
7 view of reaction rate considerations of step b), with C₁ to C₃ and n-alcohols being
8 more preferred. The most preferred alcohols are methanol and ethanol, which
9 function well in the step b) transesterification reaction. Methanol reacts faster
10 than ethanol in the transesterification reaction. Mixtures of alcohols with other
11 alcohols or with other organic solvents can be used as the step a) and step b)
12 reaction medium. Methanol or ethanol can be added to or used as the reaction
13 medium in step b) to achieve transesterification.

14 It is an added benefit when the solvent used in step a) can function as a
15 chain transfer agent, whereby the molecular weight of the polymer can be
16 controlled. The alcohols described above and in particular solvents such as THF
17 appear to function well as chain transfer agents.

18 To achieve at least 90% conversion of the monomer(s) in the
19 polymerization reaction of step a) periodic or continuous addition of initiator
20 during the reaction is required. Failure to convert the 4-ASM to 4-PAS (or S-4-
21 ASM to S-4-PAS) permits the formation of 4-hydroxystyrene (4-HSM) during
22 step b). The 4-HSM or S-4-HSM can form quinones which highly absorb in the
23 240-260 nm wavelength range. When a monomer(s) conversion of at least 90%

1 is not achieved, excess monomer must be removed prior to the transesterification
2 step. Such excess monomer can be removed using a decantation step or other
3 means so that residual monomer present is no more than 10% by weight of the
4 polymer produced.

5 The transesterification step b) is most preferably carried out in the
6 alcohol reaction medium of step a). However, at least one transesterifying
7 alcohol must be present in step b) or substituted for the reaction medium of step
8 a) after decantation. The preferred transesterifying alcohols include methanol and
9 ethanol when this reaction is carried out at the reflux temperature of the reaction
10 medium organic solvent at atmospheric pressure (or at the reflux temperature
11 above atmospheric pressure). Other alcohols up to about C₄ alcohols can be used
12 to provide an acceptable transesterification reaction rate, at temperatures above
13 their atmospheric pressure reflux temperature.

14 It is important that the transesterification of 4-PAS to 4-PHS (also S-4-
15 PAS to S-4-PHS, etc.) in step b) be at least 85% by weight, preferably 95% by
16 weight, and most preferably 98% by weight, since residual PAS absorbs in the
17 240-260 nm wavelength range.

18 Typically steps a) and b) of the present invention will be followed by a
19 step c) in which the polymer comprising 4-PHS and/or S-4-PHS which is
20 produced in step b) is precipitated from the organic solvent reaction medium
21 using water. Other non-solvents for the polymer such as hexane can be used in
22 place of water for the precipitation. It is important that the precipitation be
23 accomplished by adding the polymer/reaction medium mixture to water (or other

1 non-solvent) which is in motion. Typically, at room temperature, the weight
2 amount of water should be in excess of the weight amount of polymer/reaction
3 medium mixture by at least a factor of eight. Addition of water to the
4 polymer/reaction medium mixture causes formation of an agglomeration of
5 polymer containing residual alcohol and alcohol acetate rather than the formation
6 of discrete particles.

7 The amount of polymer which comprises 4-PHS and/or S-4-PHS in the
8 final, transesterification reaction mixture typically ranges between about 10 wt%
9 to about 30 wt%. The preferred weight % polymer range is between about 15%
10 and about 25%, since the particle size of the precipitated homopolymer or
11 copolymer is typically larger than about 25 microns when a concentration of
12 polymer of less than about 30% by weight is present in the final reaction mixture.


13 Residual acid-catalyst from step b) can be removed by: 1) adding a
14 base to the reaction medium at the completion of the transesterification step b); 2)
15 processing the polymer/reaction medium after completion of step b) through an
16 ion exchange resin, wherein the ion exchange resin contains a chemically bound
17 base; 3) adding a base to the water used in the precipitation step c); 4) water
18 washing the precipitated polymer from step c) using a neutral pH water, or; 5)
19 water washing the precipitated polymer from step c) using a base-containing
20 water, preferably having a pH ranging from about 7.5 to about 10.

21 The method or process of the present invention is particularly
22 economical when an alcohol functions as the reaction medium in steps a) and b),
23 since the alcohol can function as the chain transfer agent during polymerization of

the 4-ASM and as the transesterification reactant used to form 4-PHS. The initial alcohol acetate formed during the transesterification reaction also aids in the dissolution of the 4-PAS, which helps to speed up the transesterification reaction.


DETAILED DESCRIPTION OF THE INVENTION

The process of the present invention is shown in the reaction sequence structures depicted below for the production of homopolymers of PHS produced in an alcohol reaction medium:




Homopolymers of S-4-PHS, wherein the substituent groups are methyl or ethyl, or copolymers of 4-PHS and S-4-PHS can be produced in the same manner.

When other monomers are used in combination with 4-ASM or S-4-ASM to produce copolymers or terpolymers of 4-PHS or S-4-PHS, such monomers are added to step a). Such monomers include compounds having at least one vinyl group present, which compounds do not substantially absorb in the 240-260 nm wavelength range. Examples of monomers which do not substantially absorb include, but are not limited to:



Methylacrylate
(MA)

and



Methylmethacrylate
(MMA)

When copolymers of 4-PHS with S-4-PHS are prepared by the method of the present invention, the preferred substituent groups on the S-4-PHS molecule are methyl and ethyl. The preferred substituent positions on the 4-hydroxystyrene molecule are the 3, 5, or 3 and 5 positions.

The most preferred method of the present invention, wherein homopolymers of 4-PHS and S-4-PHS were produced, is described in EXAMPLES 1 to 57 which follow. EXAMPLES 58-60 pertain to the method of the invention wherein the reaction medium comprises a mixture of organic solvents. The method of the present invention wherein a copolymer of 4-PHS and methyl methacrylate was produced is described in EXAMPLE 61. EXAMPLE 62 is a comparative example in view of published related art.

EXAMPLES 1 to 62 were carried out as batch reactions in reactor vessels ranging from about 500 ml to 2,000 ml in volume. Each reaction vessel was a 4-neck flask outfitted with a chilled water reflux condenser, nitrogen purge line (used to exclude oxygen from the reaction vessel), overhead stirrer/mixer, and a temperature indicator (thermocouple).

A premix of an alcohol, an alternative organic solvent, or an alcohol/co-organic solvent reaction medium, the 4-ASM, or S-4-ASM, or 4-ASM and methyl methacrylate and the initiator was prepared in a beaker and the premix

1 was placed in the reaction vessel. The initial concentration of 4-ASM (or other
2 monomer(s)) in the reaction medium-monomer mixture typically ranged from
3 about 10% by weight to about 50% by weight. Preferably the relative amount of
4 4-ASM (or other monomer(s)) to reaction medium was greater than 30% by
5 weight and most preferably greater than 40% by weight. Conversion of 4-ASM
6 to 4-PAS appears to be reduced when the relative amount of 4-ASM to reaction
7 medium is reduced.

8 The mixer was started (typically mixing speed was about 100 to 400
9 rpm). The premix was then nitrogen purged at room temperature for a time
10 period of about 5 to 10 minutes.

11 After the 5 to 10 minute time period, the temperature of the premix was
12 increased to the reflux temperature of the reaction medium using an electrically
13 heated jacket on the exterior of the flask reaction vessel.

14 The 4-ASM (or other monomer(s)) was permitted to polymerize for a
15 time period equal to about one half life of the initiator at the reflux temperature
16 (at atmospheric pressure). The "half life" as used herein is the time required for
17 one half by weight of the initiator to thermally decompose to produce free
18 radicals (typically two free radicals per initiator molecule).

19 At the time about one half by weight of the initiator had decomposed,
20 additional initiator (dissolved in a solvent such as the same alcohol as that
21 typically used as at least a portion of the reaction medium), was added to the
22 reaction vessel. The amount of additional initiator added ranged from about 10%
23 to about 90% of the amount of initiator in the premix.

1 The above procedure for adding initiator to progressing polymerization
2 was repeated as necessary to achieve at least 90% conversion of 4-ASM to 4-
3 PAS. Typically 4 to 8 additions of initiator were made during the
4 polymerization. One skilled in the art can use a continuous addition of initiator
5 during polymerization to accomplish the at least 90% conversion described above.

6 Applicants carried out a batch polymerization wherein there was no
7 initiator in the premix, but initiator was added continuously to the premix during
8 the polymerization. The initiator was dissolved in the alcohol used for the
9 reaction medium. The amount of initiator added was based on the amount of
10 initiator required for previous polymerizations but was reduced by about 30% in
11 view of anticipated continuous free radical availability. See Example 25 of
12 TABLE 1.

13 The time period for the polymerization of 4-ASM to 4-PAS was that
14 sufficient to achieve at least 90% by weight conversion of the 4-ASM to 4-PAS.
15 Conversion was typically determined by capillary gas/liquid chromatography of
16 the reaction mixture. Typically reaction times ranged from about 4 hours to
17 about 9 hours.

18 The weight average molecular weight of 4-PAS produced by the above-
19 described method ranged from about 6,500 to about 27,000.


20 The transesterification reaction was typically carried out in the
21 polymerization reaction medium. However, whereas the polymerization of 4-
22 ASM to 4-PAS can be carried out in a non-alcohol-comprising reaction medium,
23 the transesterification reaction requires the presence of an alcohol. The amount of

1 alcohol which must be present at any time during the transesterification reaction
2 is at least about one equivalent based on the amount of unreacted (non-
3 transesterified) 4-acetoxystyrene. Typically, at least about ten equivalents of
4 alcohol based on unreacted 4-acetoxystyrene are used, since the transesterification
5 rate is improved by an increase in the number of equivalents of alcohol.

6 An example wherein the polymerization reaction medium (alcohol) was
7 decanted and replaced with clean alcohol prior to the transesterification is marked
8 with a # in the tables containing the Examples. The replacement alcohol in this
9 example was the same alcohol as that used during the polymerization.

10 Reflux temperature of the reaction medium was typically maintained
11 during the transesterification reaction (at atmospheric pressure).

12 Transesterification was carried out using an acid catalyst, to cause the alcohol
13 present in the reaction medium to react with the 4-PAS, converting the 4-PAS to
14 4-PHS. The acid catalyst concentration typically ranged from about 100 to about
15 400 ppm based on the total weight of the reaction mixture. However, acid
16 catalyst concentrations ranging from about 5 ppm to about 10,000 ppm can be
17 used, with catalyst concentration preferably ranging from about 50 ppm to about
18 2,000 ppm, and most preferably from about 100 ppm to about 500 ppm. The
19 acid was typically dissolved in the same alcohol as that used for at least a portion
20 of the reaction medium, to produce an alcohol solution containing an acid catalyst
21 concentration ranging from about 0.5% by weight to 2.0% by weight acid based
22 on the total acid catalyst solution. The acid catalyst solution was added to the



1 reaction vessel in a single addition. However, acid catalyst can be added during
2 the reaction, if desired.

3 Acids which were used as acid catalyst included hydrochloric acid,
4 phosphoric acid, nitric acid, sulfuric acid, methane sulfonic acid, and toluene
5 sulfonic acid. The particular acid used is not critical to the invention. Preferred
6 acids were those which did not substantially react with the 4-PAS or the 4-PHS
7 formed from the 4-PAS. In the present embodiments, non-reacting acids included
8 hydrochloric acid and phosphoric acid. Hydrochloric acid was used in
9 EXAMPLES 1-60 shown in TABLES 1 and 2, and in EXAMPLE 61.

10 To drive the reaction toward complete conversion of 4-PAS to 4-PHS, it
11 was necessary to maintain an excess of the alcohol present in the reaction
12 medium, or to remove alcohol acetate from the reaction medium as it is formed.
13 Typically, an excess of alcohol was used, wherein the molar equivalents of
14 alcohol to initial 4-ASM ranged from about 5 to about 15. In addition, alcohol
15 acetate was periodically or continuously removed after the concentration of
16 alcohol acetate was such that the solubility of the 4-PAS resulted in a translucent
17 polymer/reaction medium mixture. The alcohol acetate was removed as an
18 azeotrope with alcohol and other reaction medium co-solvents (if present), and
19 typically the combined amount by weight of the alcohol (or alcohol/co-organic
20 solvent)/alcohol acetate removed was replaced with an equivalent amount by
21 weight of the alcohol.

22 The transesterification reaction was carried out at the reflux temperature
23 of the reaction mixture at atmospheric pressure (about 66°C for a methanol

1 reaction medium or about 78°C for an ethanol reaction medium). The time period
2 for reaction was that sufficient to provide at least 85% conversion of 4-PAS to 4-
3 PHS. Conversion was measured by Fourier-Transform Infrared Spectroscopy
4 (FTIR), quantitating the acetate carbonyl peak at about 1760 cm⁻¹, on precipitated,
5 washed and dried polymer. Reaction time periods ranged from about 2 hours to
6 about 16 hours depending on the alcohol used for transesterification
7 (predominantly methanol). The required reaction time period can be decreased by
8 increasing the reaction temperature, by increasing the acid catalyst concentration
9 and or by more rapid removal of alcohol acetate as it is formed.

TABLE 1

POLYMERIZATION OF 4-ASM AND 3-METHYL-4-ASM TO LOW OPTICAL DENSITY (ABSORBANCE) 4-PHS AND 3-METHYL-4-PHS

Example No.	Type of Initiator	Initial Initiator wt% with Respect to 4-ASM or 3-M-4-ASM	Post Additions of Initiator (wt% with Respect to 4-ASM or 3-M-4-ASM)	Type of Alcohol Reaction Medium	Wt% Conv. of 4-ASM to 4-PAS or Conv. of 3-M-4-ASM to 3-M-4-PHS	Molar Absorbivity	4-PHS or 3-M-4-PHS Wt. Avg. Molecular Wt. (GPC)	Wt% of Residual 4-PAS or S-4-PAS in Polymer (FTIR)	Wt% of Residual 4-HSM or S-4-HSM or Derivative Residues in Polymer (by GC)
1	AIBN	10		EtOH		248	7,200	NA	NA
2	AIBN	5		EtOH		334	5,400	NA	NA
3	AIBN	1		EtOH		231	13,800	NA	NA
4	AIBN	1.75		EtOH			12,400	NA	NA
5	AIBN	2		EtOH		656	11,500	NA	NA
6	AIBN	5		EtOH		335	7,500	NA	NA
7	AIBN	4		EtOH		419	7,500	NA	NA
8	IBPE	5		EtOH		374	14,300	NA	0.74
9	IBPE	5.33	1	EtOH		161	14,300	1.79	0.15
10	IBPE	6	1.2	EtOH		168	13,600	NA	0.11
11	AIBN	2	0.6	EtOH		346	10,900	NA	NA
12	AIBN	2	0.5, 0.2	EtOH		341	12,000	12.7	0.72
13	IBPE	5	1.3, 0.5	EtOH	95.6 ***	151	16,000	< 0.5	0.10
14	AIBN	2	0.7	MeOH	99.3	203	13,500	> 4.0	0.35
15	AIBN	2	0.1	EtOH	94.8	457	13,700	> 4.0	1.83
16	AIBN	2	0.1	MeOH	89.5	364	14,500	> 4.0	0.92
17	ADPN	2	1.1	MeOH	83.5	195	12,800	14.1	0.14
18	AIBN	2	1.1, 0.5	EtOH	91.5 **	163	13,400	4.6	0.06
19	AIBN	4	0.4, 0.4	EtOH	97.8	161	6,100	< 0.5	0.05
20	ADPN	2.5	6 additions @ 0.5	MeOH	95.6	175	11,800	< 0.5	0.32
21	AIBN	2.5	5 additions @ 0.5	EtOH	96.2	156	12,900	< 0.5	0.15
22	ADPN	2.5	6 additions @ 0.5	MeOH	97.8	155	16,500	< 0.5	0.06
23	AIBN	2.5	6 additions @ 0.5	EtOH	97.3	153	12,400	< 0.5	0.04
24	ADPN	2.5	8 additions @ 0.5	MeOH	98.4	144	10,300	< 0.5	0.30
25	ADPN	4 (Total)	Cont. over 3 hours	MeOH	94.8	188	12,400	> 4.0	0.42
26	ADPN	2.5	7 additions @ 0.5	MeOH	96.1	161	11,100	2.6	0.42
27	ADPN	2.5	8 additions @ 0.5	MeOH	98.5	204	10,400	15.0	0.60
28 *	AIBN	4	3 additions @ 1.0	EtOH	96.7	163	10,600	< 2.0	0.14

AIBN = 2,2'-azobis(2-methylpropanenitrile)

ADPN = 2,2'-azobis(2,4-dimethylpentanenitrile)

IBPE = i-butylperoxy-2-ethylhexanoate

NA = Not Available

* 3-methyl-4-ASM converted to 3-methyl-4-PHS.

** This weight % conversion appears to be incorrect based on final GC

*** This number was determined using 4-PAS isolated from the reaction mixture by measurements on the dried polymer.

precipitation. Other weight % conversions in TABLE 1 were determined using the entire reaction mixture. Isolated 4-PAS provides an inaccurately high apparent weight % conversion, since the 4-ASM is completely soluble in the alcohol reaction medium.

TABLE 2

POLYMERIZATION OF 4-ASM AND 3-METHYL-4-ASM TO LOW OPTICAL DENSITY (ABSORBANCE) 4-PHS AND 3-METHYL-4-PHS

Example No. (4-ASM only)	Type of Initiator	Initial Initiator Wt% with Respect to 4-ASM	Post Additions of Initiator (Wt% with Respect to 4-ASM)	Type of Alcohol Reaction Medium	Wt% Conv. of 4-ASM to 4-PHS	Molar Absorbivity	4-PHS Wt. Avg. Molecular Wt (GPC)	Wt% of Residual 4-PAS in Polymer (FTIR)	Wt% of Residual 4-HSM or Derivative Residues Thereof in Polymer by GC
29	ADPN	2.5	1.25, 1.0, 0.75, 0.5	MeOH	96.4	248	11,200	1.06	NA
30	ADPN	2.5	0.75, 1.0, 1.25, 2.5	MeOH	94.2	160	19,200	< 0.5	NA
31	ADPN	4.0	0.5, 0.75, 1.0, 1.25	MeOH	98.0	171	10,900	2.44	NA
32	ADPN	2.5	4 additions @ 0.5	MeOH	95.0	147	8,900	< 0.5	0.23
33	ADPN	2.5	0.5, 0.75, 1.0, 1.25	MeOH	95.9	179	NA	< 0.5	0.08
34	ADPN	5.0	Con. over 6 hours	MeOH	94.3	150	NA	< 0.5	0.32
35	ADPN	2.5	0.5, 0.75, 1.0, 1.25	MeOH	95.8	166	12,300	13.0	NA
36	ADPN	2.5	0.5, 0.75, 1.0, 1.25	MeOH	96.9	172	11,300	7.2	0.56
37	ADPN	4.5	4 additions @ 0.5	MeOH	95.5	156	8,600	< 0.5	NA
38	ADPN	4.5	4 additions @ 0.5	MeOH	92.6	211	8,400	< 0.5	0.24
39	ADPN	2.5	0.5, 0.75, 1.0, 1.25	MeOH	89.4	191	12,300	< 0.5	0.62
40	ADPN	2.5	0.5, 0.75, 1.0, 1.25	MeOH	92.5	188	13,800	< 0.5	0.25
41	ADPN	2.5	0.5, 0.75, 1.0, 1.25	MeOH	98.9	325	11,500	17.0	0.61
42	ADPN	2.5	0.5, 0.75, 1.0	MeOH	91.8	171	11,200	2.7	0.58
43	ADPN	4.5	4 additions @ 0.5	MeOH	97.1	182	7,700	4.8	0.17
44	ADPN	2.5	0.5, 0.75, 1.0, 1.25	MeOH	94.4	206	11,100	< 0.5	0.26
45	ADPN	4.5	4 additions @ 0.5	MeOH	88.4	189	7,800	< 0.5	0.68
46	ADPN	2.5	0.5, 0.75, 1.0, 1.25	MeOH	99.4	305	10,100	> 4.0	2.04
47	ADPN	2.5	0.5, 0.75, 1.0, 1.25	MeOH	98.2	159	10,200	1.6	1.8
48	ADPN	2.5	0.5, 0.75, 1.0, 1.25	MeOH	NA	173	11,500	< 0.5	NA
49	ADPN	2.5	0.5, 0.75, 1.0, 1.25	MeOH	99.9	171	10,800	< 0.5	0.37
50	ADPN	2.5	0.5, 0.75, 1.0, 1.25	MeOH	92.5	163	10,100	< 0.5	NA
51	ADPN	2.5	0.5, 0.75, 1.0, 1.25	MeOH	95.3	160	10,400	3.3	NA
52	ADPN	2.5	0.5, 0.75, 1.0, 1.25	MeOH	94.0	149	10,500	< 0.5	NA
53	t-BPP	2.5	6 additions @ 0.5	MeOH	94.7	184	20,830	< 0.5	0.16
54	t-BPP	4.0	3 additions @ 0.5	MeOH	94.5	155	14,700	< 0.5	NA
55	LP	4.0	4 additions @ 0.5	MeOH	NA	244	31,200	< 0.5	NA
56	LP	4.0	4 additions @ 0.5	MeOH	NA	142	36,100	< 0.5	NA
57 #	ADPN	2.5	0.5, 0.75, 1.0, 1.25	MeOH	99.5 #	133	11,200	< 0.5	NA
58	ADPN	2.5	2 @ 1.0, 1 @ 0.5	@75% THF @25% MeOH	92.5	239	9,000	< 1.4	0.3
59	ADPN	2.5	2 @ 1.0	@20% THF @80% MeOH	93.5	145	10,100	< 2.0	0.41
60	ADPN	2.5	3 additions @ 0.5	@45% Acetone @55% MeOH	94.1	158	11,600	< 1.4	0.27

Alcohol reaction medium decanted after conversion of 4-ASM to 4-PAS and replaced with clean alcohol prior to transesterification.

@ % by weight of the Reaction Medium

t-BPP = t-butylperoxyisovalate
LP = lauroyl peroxide
NA = Not Available
THF = tetrahydrofuran

To further illustrate the method of the present invention in a manner which assists one skilled in the art in reproducing the EXAMPLES contained in TABLES 1 and 2, EXAMPLES 24 and 28 are described below in more specific detail.

Example 24

To a 500 ml glass round-bottom flask reactor fitted with a chilled water reflux condenser, a thermowell with thermocouple, a nitrogen purge fitting, an overhead stirrer, and an external heating mantle, a reaction mixture of 80 grams of 4-acetoxystyrene (4-ASM), 120 grams of methanol and 2.0 grams of 2,2'-azobis(2,4-dimethylpentanenitrile) initiator was added. The reaction mixture was stirred for 5 minutes under nitrogen purge to remove oxygen gas present in the reactor. The reaction mixture was then raised to about 66°C, the reflux temperature of methanol. After one hour of polymerization, 0.4 grams of 2,2'-azobis(2,4-dimethylpentanenitrile) dissolved in about 10 grams of methanol was added. At each hour, for the next 7 hours, 0.4 grams of 2,2'-azobis(2,4-dimethylpentanenitrile) in 10 grams of methanol was added. After each addition, a sample of the polymer mixture was withdrawn from the reactor. Analysis of the final polymer mixture sample by capillary gas chromatography showed 94.8% by weight conversion of the 4-acetoxystyrene to poly(4-acetoxystyrene). The transesterification reaction was begun without cooling the reaction mixture; 0.2 grams of 37% hydrochloric acid in water was combined with about 10 grams of methanol and the combination was added to the reaction mixture. The reaction mixture was permitted to react until the color of the mixture turned from white to

1 clear, at which time 150 grams methyl acetate/methanol was removed as a
2 distillate and 150 grams of fresh methanol was added. The transesterification was
3 allowed to proceed for about 4.5 hours, at which time the clear reaction mixture
4 was cooled, precipitated in deionized water, the precipitant was isolated by
5 filtration, the acid was washed from the precipitant (essentially poly(4-
6 hydroxystyrene) with deionized water, and the poly(4-hydroxystyrene) was dried
7 in a vacuum oven at about 70°C until less than 2 wt% water remained in the
8 poly(4-hydroxystyrene). An FTIR analysis of the poly(4-hydroxystyrene) showed
9 less than 0.5 wt% 4-acetoxystyrene groups remained in the poly(4-
10 hydroxystyrene) as determined by quantitating the absorbance of the carbonyl
11 peak at about 1760 cm^{-1} , the acetoxy carbonyl absorbance. A UV-VIS scan
12 showed a molar absorptivity of 144 $\text{l cm}^{-1} \text{mole}^{-1}$ at 248 nm. The product was
13 visually very white.

14 Example 28

15 To a 2000 ml glass round-bottom flask reactor fitted with a chilled
16 water reflux condenser, a thermowell with thermocouple, a nitrogen purge fitting,
17 an overhead stirrer, and an external heating mantel, a reaction mixture of 200
18 grams of 3-methyl-4-acetoxystyrene (3-M-4-ASM), 800 grams of absolute
19 ethanol, and 8.0 grams of 2,2'-azobis(2-methylpropanenitrile) initiator was added.
20 The reaction mixture was stirred for five minutes under nitrogen purge to remove
21 oxygen gas present in the reactor. The reaction mixture was then raised to about
22 78°C, the reflux temperature of ethanol. After two hours of polymerization, 2.0
23 grams of 2,2'-azobis(2-methylpropanenitrile) dissolved in about 20 grams of

1 ethanol was added to the reaction mixture. Every two hours, for the next four
2 hours, 2.0 grams of 2,2'-azobis(2-methylpropanenitrile) in about 20 grams of
3 ethanol was added. Analysis of the final polymer mixture sample, two hours
4 after the last initiator addition, by capillary gas chromatography showed 97.6% by
5 weight conversion of the 3-methyl-4-acetoxystyrene, to poly(3-methyl-4-
6 acetoxystyrene).

7 The transesterification reaction was begun without cooling the reaction
8 mixture; 1.0 gram of 37% hydrochloric acid in water was combined with about
9 20 grams of ethanol and the combination was added to the reaction mixture. The
10 reaction mixture was permitted to react until the color of the mixture turned from
11 white to clear, at which time about 250 grams of ethyl acetate/ethanol was
12 removed as a distillate and about 250 grams of fresh ethanol was added. The
13 transesterification was allowed to proceed for 7 hours at which time the clear
14 reaction mixture was cooled, precipitated in deionized water, the precipitant was
15 isolated by filtration, the acid was washed from the precipitant (essentially poly(3-
16 methyl-4-hydroxystyrene) with deionized water, and the poly(3-methyl-4-
17 hydroxystyrene) was dried in a vacuum oven at about 70°C until less than 2 wt%
18 water remained in the poly(3-methyl-4-hydroxystyrene). An FTIR analysis of the
19 poly(3-methyl-4-hydroxystyrene) showed less than 2.0 wt% (3-methyl-4-
20 acetoxystyrene) groups remaining in the poly(3-methyl-4-hydroxystyrene) as
21 determined by quantitating the absorbance at about 1760 cm^{-1} , the acetoxy
22 carbonyl absorbance. A UV-VIS scan showed a molar absorptivity of 163 l cm^{-1}
23 mole^{-1} at 248 nm. The product was visually white.

1 The method of the present invention wherein copolymers comprising
2 PHS were produced is described in EXAMPLE 61 which follows.

3 EXAMPLE 61 was carried out using the same reaction conditions and
4 using the same reactants as those described for production of homopolymers of 4-
5 PHS except that the comonomer was added to the premix comprising ASM. A
6 specifically detailed description of EXAMPLE 61 follows.

7 Example 61

8 A copolymer of 4-acetoxystyrene and methyl methacrylate was prepared
9 and transesterified to a poly(4-hydroxystyrene-methyl methacrylate) copolymer
10 using the following method.

11 To a 500 ml glass round-bottom flask reactor fitted with a chilled water
12 reflux condenser, a thermowell with thermocouple, a nitrogen purge fitting, an
13 overhead stirrer, and an external heating mantel, a reaction mixture of 62.5 grams
14 of 4-acetoxystyrene (4-ASM), 62.5 grams of methylmethacrylate, 125 grams of
15 methanol, and 1.5 grams of 2,2'-azobis(2,4-dimethylpentanenitrile) initiator was
16 added. The reaction mixture was stirred for five minutes under nitrogen purge to
17 remove oxygen gas present in the reactor. The reaction mixture was then raised
18 to about 64°C, the reflux temperature of the mixture. After one hour of
19 polymerization, 0.3 grams of 2,2'-azobis(2,4-dimethylpentanenitrile) dissolved in
20 about 10 grams of methanol was added to the reaction mixture. Two hours after
21 the start of the polymerization, 0.5 grams of 2,2'-azobis(2,4-
22 dimethylpentanenitrile) in about 10 grams of methanol was added to the reaction
23 mixture. Three hours after the start of the polymerization, 0.65 grams of 2,2'-

1 azobis(2,4-dimethylpentanenitrile) was added to the reaction mixture. Four hours
2 after the start of the polymerization, 0.8 grams of 2,2'-azobis(2,4-
3 dimethylpentanenitrile) was added to the reaction mixture. Analysis of the final
4 polymer mixture sample, two hours after the last initiator addition, by capillary
5 gas chromatography showed 98.3% by weight conversion of the 4-acetoxystyrene
6 and methylmethacrylate to poly(4-acetoxystyrene-co-methylmethacrylate). The
7 transesterification reaction was begun without cooling the reaction mixture; 0.3
8 grams of 37% hydrochloric acid in water was combined with about 10 grams of
9 methanol and the combination was added to the reaction mixture. The reaction
10 mixture was permitted to react until the color of the mixture turned from white to
11 clear, at which time about 150 grams of methyl acetate/methanol was removed as
12 a distillate and about 150 grams of fresh methanol was added. The
13 transesterification was allowed to proceed for 4 hours at which time the clear
14 reaction mixture was cooled, precipitated in deionized water, the precipitant was
15 isolated by filtration, the acid was washed from the precipitant (essentially poly(4-
16 hydroxystyrene-co-methylmethacrylate) with deionized water, and the poly(4-
17 hydroxystyrene-co-methylmethacrylate) (4-PHS/MMA). The 4-PHS/MMA was
18 dried in a vacuum oven at about 70°C until less than 2 wt% water remained in
19 the 4-PHS/MMA. An FTIR analysis of the 4-PHS/MMA showed less than 2.0
20 wt% (4-acetoxystyrene) groups remaining in the 4-PHS/MMA. The weight
21 average molecular weight of the 4-PHS/MMA was about 22,000 by GPC. A UV-
22 VIS scan showed a molar absorptivity of $48 \text{ l cm}^{-1} \text{ mole}^{-1}$ at 248 nm. The
23 product was visually white.

1 Example 62 - Comparative Example

2 The purpose of this Example is to demonstrate that the simultaneous
3 polymerization and hydrolysis method of producing poly(4-hydroxystyrene)
4 described by Elmore, European Patent Application No. 87307912.3, even if
5 carried out using an acid catalyzed methanolysis as disclosed by Gupta, U.S.
6 Patent No. 4,898,916, provides a reaction product which does not have the low
7 optical density (absorbance over a 240-260 nm wavelength) characteristics of the
8 product produced by the method of the present invention.

9 A 500 ml glass round-bottom flask reactor fitted with a chilled water
10 reflux condenser, a thermowell with thermocouple, a nitrogen purge fitting, an
11 overhead stirrer, and an external heating mantle, was charged with 100 gm of
12 methanol (MeOH) and 2.7 gm of 37% HCl (0.5% by weight HCl based on the
13 MeOH and the 4-ASM to be added subsequently). Separately 100 gm of 4-
14 acetoxystyrene (4-ASM), 2,2'-azobis(2-methylpropanenitrile) were mixed and
15 kept cold in an ice bath. The methanol/HCl mixture was stirred for about 5
16 minutes under a nitrogen purge to remove gases other than nitrogen from the
17 reactor. The temperature of the methanol/HCl mixture was then raised to about
18 66°C, the reflux temperature of methanol at atmospheric pressure. The 4-
19 ASM/initiator mixture was periodically added to the flask reactor over a 3 hour
20 period. 110 gm of methylacetate/methanol was removed during the reaction.
21 Upon the initial addition of 4-ASM/initiator solution, the temperature of the
22 reactants in the flask reactor dropped to 61.4°C, indicating the production of

1 methyl acetate. As methyl acetate was removed, and fresh methanol added, the
2 temperature climbed to 64.5°C toward the end of the reaction.

3 Analysis of the final polymer mixture sample by capillary gas
4 chromatography showed a 99% by weight conversion of the 4-acetoxystyrene.

5 After completion of the simultaneous polymerization-hydrolysis
6 reaction, the reaction mixture was cooled, and precipitated in deionized water, the
7 precipitate was isolated by filtration, residual acid was washed from the
8 precipitant using deionized water, and the reaction product was dried in a vacuum
9 oven at about 70°C until less than 2 weight % water remained in the reaction
10 product.

11 An FTIR analysis of the precipitant portion of the reaction product
12 showed the precipitant to comprise PHS, wherein less than about 1.7 wt% 4-
13 acetoxystyrene groups remained in the PHS. The weight average molecular
14 weight (Mw) of this PHS portion of the reaction product was about 2,000. This
15 reaction method does not permit the isolation of PHS. This reaction method also
16 did not permit control of the Mw of the reaction product. The Mw of the PHS
17 could not be controlled, in part because hydroxystyrene monomer (HSM) was
18 formed and polymerized not only via free radical means, but possibly by cationic
19 means.

20 The molar absorbtivity, ϵ , of the PHS portion of the reaction product at
21 UV_{248} measured 868 (far greater than the 250 or less desired for the product
22 produced by the method of the present invention). This high ϵ is apparently due

1 to the formation of quinones or other highly absorbing species due to the
2 simultaneous polymerization and hydrolysis reaction technique.


3 Pertaining to the method of the present invention, the homopolymers
4 and copolymers comprising 4-PHS (and S-4-PHS) were isolated from the final,
5 transesterification reaction medium by precipitation. The preferred precipitation
6 medium is water although organic solvents, such as heptane, hexane, and
7 cyclohexane, in which the PHS homopolymers and copolymers thereof are
8 sufficiently insoluble can be used.

9 When water was used as the precipitation medium, the polymer/reaction
10 medium mixture was added to water which water was in motion. Typically, at
11 room temperature, the weight amount of water was in excess of the weight
12 amount of polymer/reaction medium mixture by at least a factor of eight. The
13 preferred alcohol reaction medium is methanol for a water precipitation, since the
14 PHS polymer or copolymer thereof precipitates at a particle size larger than about
15 50 microns. Use of higher molecular weight alcohol reaction mediums appears to
16 cause the precipitated particle size of the PHS homopolymer (or copolymer
17 thereof) to be smaller than about 50 microns. Larger particle size is easier to
18 filter.

19 Although the present invention is described in terms of polymers of 4-
20 hydroxystyrene and/or substituted 4-hydroxystyrene, further functionalization of
21 these polymers which provides enhanced performance in particular optical
22 applications is considered to fall within the scope of the present invention. For
23 example, when these polymers are to be used as polymeric components in

1 photoresists, it is known to be desirable to replace the hydroxy group at the 4
2 position of the compound structure with a t-butoxycarbonyl group. The presence
3 of this t-butoxycarbonyl group on the polymer improves the sensitivity of
4 polymer to imaging radiation striking the photoresist. It is also known to replace
5 the hydroxy group with a t-butoxy group, also for use in photoresist applications.
6 The present invention provides polymeric compounds (and a method for their
7 preparation) which meet the optical (radiation absorption) requirements necessary
8 to function as a deep UV, X-ray, or E-Beam photoresist material. Further
9 functionalization of this basic polymeric material, which does not detrimentally
10 affect the overall performance of the polymer in the intended application, is
11 intended to fall within the scope of the present invention.

12 It will of course be understood that the present invention
13 has been described above purely by way of example and that modifications
14 of detail can be made within the scope of the invention.
15
16
17


CLAIMS

What is claimed is:

1. A process for preparation of polymers comprising poly(4-hydroxystyrene) or substituted poly(4-hydroxystyrene) or both, said process comprising the steps of:
 - a) reacting a mixture comprising 4-acetoxystyrene monomer or substituted 4-acetoxystyrene monomer or both and an initiator, wherein said initiator and its decomposition products alone or as polymer capping groups do not substantially absorb radiation over wavelengths ranging from about 240 to about 260 nm, or wherein said initiator is present at a concentration of less than about 3 mole % of said monomer, in a reaction medium comprising at least one organic solvent, to produce a polymer comprising poly(4-acetoxystyrene) or substituted poly(4-acetoxystyrene) or both, whereby, either as a result of monomer conversion, or due to removal of residual monomer, 10 wt% or less residual monomer, based on the weight of polymer produced, is present in the reaction mixture used during a subsequent transesterification reaction step; and
 - b) subsequently transesterifying said poly(4-acetoxystyrene) to poly(4-hydroxystyrene) or transesterifying said substituted poly(4-acetoxystyrene) to substituted poly(4-hydroxystyrene) or transesterifying both, in a transesterification reaction medium comprising at least one equivalent of alcohol per equivalent of non-transesterified poly(4-acetoxystyrene) or

This Sheet Has Been Replaced





substituted poly(4-acetoxystyrene), using an acid catalyst to achieve said transesterification, wherein at least 85% by weight conversion of said poly(4-acetoxystyrene) to said poly(4-hydroxystyrene) or conversion of said substituted
5 poly(4-acetoxystyrene) to said substituted poly(4-hydroxystyrene) or at least 85% by weight transesterification of both is obtained.

2. The process of claim 1, wherein the amount of said poly(4-hydroxystyrene) or said substituted poly(4-hydroxystyrene) or both in said reaction mixture is in the
10 range from about 10% to about 30% by weight.

3. A process for preparation of polymers comprising poly(4-hydroxystyrene) or substituted poly(4-hydroxystyrene) or both, said process comprising the steps of:

- 15 a) reacting a mixture comprising 4-acetoxystyrene monomer or substituted 4-acetoxystyrene monomer or both and a comonomer having at least one vinyl group present, wherein said comonomer does not substantially absorb radiation over wavelengths ranging from about 240 to about 260 nm; and an
20 initiator, wherein said initiator and its decomposition products alone or as capping groups do not substantially absorb radiation over wavelengths ranging from about 240 to about 260 nm, or wherein said initiator is present at a concentration of less than about 3 mole % of said monomer;
25 in a reaction medium comprising at least one organic solvent, to produce a copolymer of poly(4-acetoxystyrene) or said substituted poly(4-acetoxystyrene) with said comonomer, whereby, either as a result of monomer conversion or due to removal of residual monomer, 10 wt% or less residual
30 monomer, based on the weight of polymer produced, is present in the reaction mixture during a subsequent, transesterification reaction step; and
b) subsequently transesterifying said poly(4-acetoxystyrene) to poly(4-hydroxystyrene) or
35 transesterifying said substituted poly(4-acetoxystyrene) to substituted poly(4-hydroxystyrene) or transesterifying both to a conversion of at least 85% by weight, in a transesterification reaction medium comprising at least one





equivalent of alcohol per equivalent of non-transesterified copolymer, using an acid catalyst to achieve said transesterification.

4. The process of claim 3, wherein the said comonomer having at least one vinyl group present is methyl acrylate, methyl methacrylate or a mixture thereof.

5. A process for preparation of copolymers of poly(4-hydroxystyrene) with substituted poly(4-hydroxystyrene), said process comprising the steps of:

- a) reacting a mixture comprising 4-acetoxystyrene monomer, substituted 4-acetoxystyrene monomer and an initiator, wherein said initiator and its decomposition products alone or as polymer capping groups do not substantially absorb radiation over wavelengths ranging from about 240 to about 260 nm, or wherein said initiator is present at a concentration of less than about 3 mole % of said monomer, in a reaction medium comprising at least one organic solvent, preferably at least one alcohol, to produce a copolymer of poly(4-acetoxystyrene) with substituted poly(4-acetoxystyrene), wherein at least 90% by weight conversion of said 4-acetoxystyrene monomer and said substituted 4-acetoxystyrene monomer combined is obtained; and
- b) subsequently transesterifying said poly(4-acetoxystyrene) and said substituted poly(4-acetoxystyrene) to poly(4-hydroxystyrene) and substituted poly(4-hydroxystyrene), in a transesterification reaction medium comprising an alcohol, preferably in substantially said reaction medium of step a), using an acid catalyst to achieve said transesterification, wherein at least 85% by weight conversion of the combination of said poly(4-acetoxystyrene) to said poly(4-hydroxystyrene) and said substituted poly(4-acetoxystyrene) to said substituted poly(4-hydroxystyrene) is obtained.

6. The process of any of claims 1 to 5, wherein said reaction medium of step a) is an alcohol reaction medium selected from alcohols having 1 to 5 carbon atoms and combinations thereof.

7. The process of any of claims 1 to 5, wherein a C_1 -





C₅ alcohol constitutes at least the majority of said reaction medium of step a).

8. The process of any of claims 1 to 7, wherein said alcohol reaction medium is selected from alcohols having 1 to 5 carbon atoms and combinations thereof.

9. The process of claim 8, wherein said alcohol reaction medium is selected from alcohols having 1 to 2 carbon atoms and combinations thereof.

10. The process of any of claims 1 to 9, wherein said transesterification reaction medium of step b) is essentially the same reaction medium as that used in step a) or is a functional equivalent thereof.

11. The process of any of claims 6 to 10, wherein said alcohol reaction medium is selected from alcohols having from 3 to 5 carbon atoms and wherein an additional alcohol is added during step b) and wherein said additional alcohol is selected from alcohols having 1 to 2 carbon atoms and combinations thereof.

12. The process of any of claims 1 to 11, wherein said initiator is added periodically or continuously during step a), whereby at least 90% by weight conversion of said 4-acetoxystyrene monomer or said substituted 4-acetoxystyrene monomer or the combination of said 4-acetoxystyrene monomer and/or said substituted 4-acetoxystyrene monomer and said comonomer or said 4-acetoxystyrene monomer and said substituted 4-acetoxystyrene monomer combined, as the case may be, is achieved.

13. The process of any of claims 1 to 11, wherein said step a) conversion of monomer to polymer is less than 90% by weight, but wherein said reaction medium of step a) is substantially decanted from said polymer and replaced with fresh, clean alcohol reaction medium prior to said step b) transesterification.

14. The process of claim 13, wherein C₁-C₅ alcohol constitutes at least the majority of said reaction medium of step a) and wherein said replacement alcohol reaction medium is essentially the alcohol reaction medium as that used in step a) or a functional equivalent thereof.



15. The process of claim 13, wherein said replacement alcohol reaction medium is a substantially different kind of alcohol reaction medium from that used in step a).

16. The process of claim 13, wherein said replacement
5 alcohol reaction medium comprises at least one alcohol selected from alcohols having from 1 to 5 carbon atoms.

17. The process of any of claims 1 to 16, wherein said reacting mixture comprises substituted 4-acetoxystyrene monomer, and wherein the substitution is on the ring
10 structure of said 4-acetoxystyrene at the 3, or 5, or 3 and 5 positions.

18. The process of claim 17, wherein said substituent group is methyl or ethyl.

19. The process of any of claims 1 to 18, wherein said
15 initiator is selected from 2,2'-azobis(2,4-dimethylpentanenitrile), 2,2'-azobis(2-methylpropanenitrile), 2,2'-azobis(2-methylbutanenitrile), 1,1'-azobis(cyclohexanecarbonitrile), t-butyl peroxy-2-ethylhexanoate, t-butyl peroxy-pivalate, t-amyl
20 peroxy-pivalate, diisononanoyl peroxide, decanoyl peroxide, succinic acid peroxide, di(n-propyl) peroxydicarbonate, di(sec-butyl) peroxydicarbonate, di(2-ethyl-hexyl) peroxydicarbonate, t-butylperoxy-neodecanoate 2,5-dimethyl-2,5-di(2-ethylhexanoylperoxy) hexane, t-amylperoxy-
25 neodecanoate, t-butylperoxy-neodeconate, and combinations of any two or more of these.

20. The process of any of claims 1 to 18, wherein said initiator is selected from the group consisting of benzoyl peroxide, t-butyl-peroxybenzoate, and di-t-butyl
30 diperoxyphthalate, and wherein the mole % of said initiator is less than about 3 mole % of said monomer.

21. The process of any of claims 1 to 20, wherein said initiator exhibits a half life in the range from about 0.5 hours to about 10 hours at the temperature at which said
35 reaction is carried out.

22. The process of any of claims 1 to 21, wherein said acid catalyst will not substantially react with, as the case may be, said poly(4-acetoxystyrene), said substituted



poly(4-acetoxystyrene), the polymer of said comonomer, said poly(4-hydroxystyrene), said substituted poly(4-hydroxystyrene), any transesterified form of said comonomer and the copolymer comprising any of these.

5 23. The process of claim 22, wherein said acid catalyst is selected from hydrochloric acid, phosphoric acid, nitric acid, sulfuric acid, methane sulfonic acid, and toluene sulfonic acid.

24. The process of any of claims 1 to 23, including an
10 additional step:

c) isolation of the polymer or copolymer comprising poly(4-hydroxystyrene), substituted poly(4-hydroxystyrene) or both from the transesterification reaction medium.

25. The process of claim 24, wherein said step c)
15 isolation is accomplished by precipitation of said polymer or copolymer comprising poly(4-hydroxystyrene), substituted poly(4-hydroxystyrene) or both from said reaction medium.

26. The process of claim 25, wherein said precipitation
is accomplished by adding the reaction mixture of step b) to
20 water which is in motion.

27. The process of claim 25 or 26, wherein the precipitate of said polymer or copolymer comprising poly(4-hydroxystyrene), substituted poly(4-hydroxystyrene) or both is treated to remove residual acid.

25 28. The process of any of claims 1 to 27, wherein said 4-acetoxystyrene monomer or said substituted 4-acetoxystyrene monomer or both and, if present, said comonomer of step a) contain no inhibitor which substantially absorbs radiation over wavelengths in the
30 range of from about 240 to about 260 nm.

29. A polymer comprising 4-hydroxystyrene having a molar absorbtivity of 250 or less, at a wavelength of about 250 nm, wherein said polymer contains less than about 2.5% by weight of residual 4-hydroxystyrene monomer or derivative
35 residues thereof.

30. The polymer of claim 29, wherein said polymer comprises less than about 2.5% by weight of poly (4-acetoxystyrene).



31. A polymer comprising 4-hydroxystyrene having a molar absorbtivity of 250 or less, at a wavelength of about 250 nm, wherein said polymer contains less than about 0.7% by weight of 4-hydroxystyrene monomer or derivative residues
5 thereof, and comprises less than about 13% by weight poly(4-acetoxystyrene).


32. The polymer of claim 29, 30 or 31, wherein said polymer has been further functionalized by replacing at least a portion of the hydroxy functional groups with t-
10 butylcarbonyloxy or t-butoxy functional groups.

A process for making low optical density polymers and
copolymers for photoresists and optical applications.

Abstract

5

Polymers comprising poly(4-hydroxystyrene) and/or substituted poly(4-hydroxystyrene) are produced by polymerizing 4-acetoxystyrene and/or substituted 4-acetoxystyrene monomers, with or without other comonomers,
10 and subsequently performing transesterification. Preferably, the polymers are produced using at least one alcohol as a reaction medium, a chain transfer agent and a transesterification reactant. It is appropriate: to use an initiator which does not comprise a substantially
15 absorbant structure over the 240 to 260 nm range or to use an initiator concentration of less than about 3 mole % of the monomer(s); to obtain a polymerization conversion of the initial polymerization monomers of at least about 90% by weight, or to remove residual monomer(s) from the reaction
20 medium prior to transesterification; to obtain a transesterification conversion of the polymerized monomers of at least 85% by weight; and to avoid the use of transesterification catalysts which can cause the formation of chemical structures which can absorb over the 240 to 260
25 nm radiation wavelength range. The target polymers have low optical density (absorbance) over a wavelength range from 240 to 260 nm, as well as low optical density over the near UV and visible spectrum (310 to 800 nm); and are useful as photoresist components for use in combination with deep UV,
30 X-ray, and E-Beam imaging systems.



5

REPLACEMENT SHEET

☒ Description: pages 5, 10, 12, 13, 21

☒ Claim(s): 35

☐ Drawing(s): pages 1, 2, 3, 4, 6, 7, 8, 9, 11, 14, 15, 16, 17, 18, 19, 20, 22, 23, 24, 25, 26, 27, 28, 29, 30, 31, 32, 33, 34, 36, 37, 38, 39, 40, 41, 42, 43, 44, 45, 46, 47, 48, 49, 50, 51, 52, 53, 54, 55, 56, 57, 58, 59, 60, 61, 62, 63, 64, 65, 66, 67, 68, 69, 70, 71, 72, 73, 74, 75, 76, 77, 78, 79, 80, 81, 82, 83, 84, 85, 86, 87, 88, 89, 90, 91, 92, 93, 94, 95, 96, 97, 98, 99, 100

☐ Abstract: pages 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, 22, 23, 24, 25, 26, 27, 28, 29, 30, 31, 32, 33, 34, 35, 36, 37, 38, 39, 40, 41, 42, 43, 44, 45, 46, 47, 48, 49, 50, 51, 52, 53, 54, 55, 56, 57, 58, 59, 60, 61, 62, 63, 64, 65, 66, 67, 68, 69, 70, 71, 72, 73, 74, 75, 76, 77, 78, 79, 80, 81, 82, 83, 84, 85, 86, 87, 88, 89, 90, 91, 92, 93, 94, 95, 96, 97, 98, 99, 100

DATE OF RECEIPT 19/8/99

disposal. In addition, the method Gupta et al. disclosed in

U.S. Patent No. 4,898,916 is difficult to accomplish on a large scale due to problems encountered in a making of a slurry of the 4-PAS in alcohol. The 4-PAS tends to "clump"

or remain in agglomerated form in the alcohol, due to insolubility.

SUMMARY OF THE INVENTION

In one aspect, the present invention provides a process for preparation of polymers having a molar absorbtivity of 250 or less in the wavelength range of from 240 to 260 nm and comprising poly(4-hydroxystyrene) or substituted poly(4-hydroxystyrene) or both, said process comprising the steps of:

a) reacting a mixture comprising 4-acetoxystyrene monomer or substituted 4-acetoxystyrene monomer or both and an initiator, wherein said initiator and its decomposition products alone or as polymer capping groups do not substantially absorb radiation over wavelengths ranging from about 240 to about 260 nm, and/or wherein said initiator is present at a concentration of less than about 3 mole % of said monomer, in a reaction medium comprising at least one organic solvent, to produce a polymer comprising poly(4-acetoxystyrene) or substituted poly(4-acetoxystyrene) or both, whereby, either as a result of monomer conversion, or due to removal of residual monomer, 10 wt% or less residual monomer, based on the weight of polymer produced, is present in the reaction mixture used during a subsequent transesterification reaction step; and

b) subsequently transesterifying said poly(4-acetoxystyrene) to poly(4-hydroxystyrene) or transesterifying said substituted poly(4-acetoxystyrene) to substituted poly(4-hydroxystyrene) or transesterifying both, in a transesterification reaction medium comprising at least one equivalent of alcohol per equivalent of non-transesterified poly(4-acetoxystyrene) or substituted

AMENDED SHEET

19 AUG 1999

5a

poly(4-acetoxystyrene), using an acid catalyst to achieve said transesterification, the acid catalyst being present in an amount of from 5 to 2,000 ppm, wherein at least 85% by weight conversion of said poly(4-acetoxystyrene) to said poly(4-hydroxystyrene) or conversion of said substituted poly(4-acetoxystyrene) to said substituted poly(4-hydroxystyrene) or at least 85% by weight transesterification of both is obtained.

In another aspect, the present invention provides a process for preparation of polymers having a molar absorbtivity of 250 or less in the wavelength range of from 240 to 260 nm and comprising poly(4-hydroxystyrene) or substituted poly(4-hydroxystyrene) or both, said process comprising the steps of:

a) reacting a mixture comprising 4-acetoxystyrene monomer or substituted 4-acetoxystyrene monomer or both and a comonomer having at least one vinyl group present, wherein said comonomer does not substantially absorb radiation over wavelengths ranging from about 240 to about 260 nm; and an initiator, wherein said initiator and its decomposition products alone or as capping groups do not substantially absorb radiation over wavelengths ranging from about 240 to about 260 nm, and/or wherein said initiator is present at a concentration of less than about 3 mole % of said monomer; in a reaction medium comprising at least one organic solvent, to produce a copolymer of 4-acetoxystyrene or substituted 4-acetoxystyrene or both with said comonomer, whereby, either as a result of monomer conversion or due to removal of residual monomer, 10 wt% or less residual monomer, based on the weight of polymer produced, is present in the reaction mixture during a subsequent, transesterification reaction step; and

b) subsequently transesterifying said copolymer of 4-acetoxystyrene or substituted 4-acetoxystyrene or both with said comonomer to a copolymer of 4-hydroxystyrene or substituted 4-hydroxystyrene or both with said comonomer to

AMENDED SHEET


5b

5 a conversion of at least 85% by weight of said 4-acetoxystyrene and said substituted 4-acetoxystyrene, in a transesterification reaction medium comprising at least one equivalent of alcohol per equivalent of non-transesterified copolymer, using an acid catalyst to achieve said transesterification, the acid catalyst being present in an amount of from 5 to 2,000 ppm.

10 In a further aspect, the present invention provides a process for preparation of copolymers, having a molar absorbtivity of 250 or less in the wavelength range of from 240 to 260 nm, of poly(4-hydroxystyrene) with substituted poly(4-hydroxystyrene), said process comprising the steps of:

15 a) reacting a mixture comprising 4-acetoxystyrene monomer, substituted 4-acetoxystyrene monomer and an initiator, wherein said initiator and its decomposition products alone or as polymer capping groups do not substantially absorb radiation over wavelengths ranging from
20 about 240 to about 260 nm, and/or wherein said initiator is present at a concentration of less than about 3 mole % of said monomer, in a reaction medium comprising at least one organic solvent, preferably at least one alcohol, to produce a copolymer of 4-acetoxystyrene with substituted 4-
25 acetoxystyrene, wherein at least 90% by weight conversion of said 4-acetoxystyrene monomer and said substituted 4-acetoxystyrene monomer combined is obtained; and

b) subsequently transesterifying said copolymer of 4-acetoxystyrene with substituted 4-acetoxystyrene to a
30 copolymer of 4-hydroxystyrene with substituted 4-hydroxystyrene, in a transesterification reaction medium comprising an alcohol, preferably in substantially said reaction medium of step a), using an acid catalyst to achieve said transesterification, the acid catalyst being
35 present in an amount of from 5 to 2,000 ppm, wherein at least 85% by weight conversion of the combination of said



5c

4-acetoxystyrene to said 4-hydroxystyrene and of said substituted 4-acetoxystyrene to said substituted 4-hydroxystyrene is obtained.

5

DETAILED DESCRIPTION OF EXEMPLARY EMBODIMENTS

In accordance with the present invention, it has been discovered that despite the partial insolubility of poly(4-acetoxystyrene)(4-PAS) in alcohols, it is possible to
10 polymerize homopolymers, copolymers, and terpolymers (hereinafter referred to as "polymers") comprising poly(4-acetoxystyrene) and/or substituted poly(4-acetoxystyrene) (S-4-PAS) in an alcohol reaction medium, and to subsequently transesterify the polymer comprising 4-PAS and/or S-4-PAS,
15 preferably in the same alcohol reaction medium, to produce a polymer comprising poly(4-hydroxystyrene)(4-PHS) and/or substituted poly(4-hydroxystyrene)(S-4-PHS). The initial polymerization of 4-acetoxystyrene monomer (4-ASM) and/or substituted 4-acetoxystyrene monomer (S-4-ASM) to produce a
20 polymer comprising 4-PAS and/or S-4-PAS is carried out in a manner which permits formation of a transesterification reaction mixture comprising no more than 10% by weight of residual monomer(s) (based on the polymer produced). This 10% by weight residual monomer can be achieved by obtaining
25 90% conversion of the combination of all monomers initially present during the polymerization reaction, or by removing such monomers from the reaction mixture after the polymerization is completed but prior to the transesterification reaction. The

30

AMENDED SHEET

1 polymer, the poly(4-acetoxystyrene) content must be less than about 13% by
2 weight of the polymer.

3 For purposes of clear expression of the concept of the present invention,
4 the language is simplified in portions of the following text by describing the
5 invention in terms of the preparation of polymers comprising poly(4-
6 hydroxystyrene). However, it is intended that polymers comprising substituted
7 poly(4-hydroxystyrene) be included as well. When it is necessary to make a
8 distinction, or when the language does not become too cumbersome, substituted
9 4-acetoxystyrene monomers are discussed specifically.



10 The "single pot", simplified process of the present invention, can be
11 used for the preparation of polymers comprising of poly(4-hydroxystyrene) and
12 comprises the following steps:

13 a) reacting a mixture comprising 4-acetoxystyrene (monomer) and an initiator,
14 which itself, its decomposition products, and capped structures which it
15 produces, do not substantially absorb over the wavelengths ranging between
16 about 240-260 nm; ^{and/} or, using no more than about 3 mole % of an absorbing
17 initiator per mole of monomer, in an organic solvent reaction medium, to
18 produce a polymer comprising 4-acetoxystyrene; wherein, either as a result of
19 monomer conversion or due to removal of residual monomer after
20 polymerization, residual monomer in the subsequent transesterification
21 reaction medium comprises no more than 10% by weight of the polymer
22 comprising 4-acetoxystyrene which is produced; and

1 decomposition products alone, and capped structures which it produces, do
2 not substantially absorb radiation over wavelengths ranging from about 240 to
3 about 260 nm;^{and/}or, using no more than about 3 mole % of an absorbing
4 initiator per mole of monomer, in an organic solvent reaction medium to
5 produce a copolymer of ~~poly(4-acetoxystyrene)~~ with substituted ~~poly(4-~~
6 ~~acetoxystyrene)~~, in a manner such that residual monomers present in the
7 reaction medium during subsequent transesterification reaction step(s)
8 comprises no more than 10% by weight of the copolymer formed during the
9 reaction; and
10 b) subsequently transesterifying the copolymer of ~~poly(4-acetoxystyrene)~~ and
11 substituted ~~poly(4-hydroxystyrene)~~ to copolymers of ~~poly(4-hydroxystyrene)~~
12 and substituted ~~poly(4-hydroxystyrene)~~, in a transesterification reaction
13 medium comprising at least one equivalent of alcohol per equivalent of non-
14 transesterified copolymer, using an acid catalyst to achieve transesterification
15 of at least 85% of the ~~poly(4-acetoxystyrene)~~ and ^{substituted}~~poly(4-hydroxystyrene)~~.

16 In the most preferred embodiment of the above-described invention, at
17 least the majority of the organic solvent reaction medium of step a) is a C₁-C₅
18 (straight or branched) alcohol. In addition, the step b) transesterification reaction
19 medium is essentially the same reaction medium as that used in step a) or is a
20 functional equivalent thereof.


21 The following description applies to the embodiments of the invention
22 for which the process steps are disclosed above.



the 4-ASM and as the transesterification reactant used to form 4-PHS. The initial alcohol acetate formed during the transesterification reaction also aids in the dissolution of the 4-PAS, which helps to speed up the transesterification reaction.


DETAILED DESCRIPTION OF THE INVENTION

The process of the present invention is ~~shown~~^{illustrated} in the ~~reaction~~^{reaction} sequence structures depicted below for the production of homopolymers of PHS produced in an alcohol reaction medium:



Homopolymers of S-4-PHS, wherein the substituent groups are methyl or ethyl, or copolymers of 4-PHS and S-4-PHS can be produced in the same manner.

When other monomers are used in combination with 4-ASM or S-4-ASM to produce copolymers or terpolymers of 4-PHS or S-4-PHS, such monomers are added to step a). Such monomers include compounds having at least one vinyl group present, which compounds do not substantially absorb in the 240-260 nm wavelength range. Examples of monomers which do not substantially absorb include, but are not limited to:




1 alcohol which must be present at any time during the transesterification reaction
2 is at least about one equivalent based on the amount of unreacted (non-
3 transesterified) 4-acetoxystyrene. Typically, at least about ten equivalents of
4 alcohol based on unreacted 4-acetoxystyrene are used, since the transesterification
5 rate is improved by an increase in the number of equivalents of alcohol.

6 An example wherein the polymerization reaction medium (alcohol) was
7 decanted and replaced with clean alcohol prior to the transesterification is marked
8 with a # in the tables containing the Examples. The replacement alcohol in this
9 example was the same alcohol as that used during the polymerization.


10 Reflux temperature of the reaction medium was typically maintained
11 during the transesterification reaction (at atmospheric pressure).

12 Transesterification was carried out using an acid catalyst, to cause the alcohol
13 present in the reaction medium to react with the 4-PAS, converting the 4-PAS to
14 4-PHS. The acid catalyst concentration typically ranged from about 100 to about
15 400 ppm based on the total weight of the reaction mixture. However, acid
16 catalyst concentrations ranging from about 5 ppm to about ~~10,000~~ ^{2,000} ppm can be
17 used, with catalyst concentration preferably ranging from about 50 ppm to about
18 2,000 ppm, and most preferably from about 100 ppm to about 500 ppm. The
19 acid was typically dissolved in the same alcohol as that used for at least a portion
20 of the reaction medium, to produce an alcohol solution containing an acid catalyst
21 concentration ranging from about 0.5% by weight to 2.0% by weight acid based
22 on the total acid catalyst solution. The acid catalyst solution was added to the

AMENDED SHEET

CLAIMS

1. A process for preparation of polymers having a molar absorbtivity of 250 or less in the wavelength range of from
5 240 to 260 nm and comprising poly(4-hydroxystyrene) or substituted poly(4-hydroxystyrene) or both, said process comprising the steps of:
- a) reacting a mixture comprising 4-acetoxystyrene monomer or substituted 4-acetoxystyrene monomer or both and an
10 initiator, wherein said initiator and its decomposition products alone or as polymer capping groups do not substantially absorb radiation over wavelengths ranging from about 240 to about 260 nm, ^{and/} ~~or~~ wherein said initiator is present at a concentration of less than about 3 mole % of
15 said monomer, in a reaction medium comprising at least one organic solvent, to produce a polymer comprising poly(4-acetoxystyrene) or substituted poly(4-acetoxystyrene) or both, whereby, either as a result of monomer conversion, or due to removal of residual monomer, 10 wt% or less residual
20 monomer, based on the weight of polymer produced, is present in the reaction mixture used during a subsequent transesterification reaction step; and
- b) subsequently transesterifying said poly(4-acetoxystyrene) to poly(4-hydroxystyrene) or
25 transesterifying said substituted poly(4-acetoxystyrene) to substituted poly(4-hydroxystyrene) or transesterifying both, in a transesterification reaction medium comprising at least one equivalent of alcohol per equivalent of non-transesterified poly(4-acetoxystyrene) or substituted
30 poly(4-acetoxystyrene), using an acid catalyst to achieve said transesterification, the acid catalyst being present in an amount of from 5 to 2,000 ppm, wherein at least 85% by weight conversion of said poly(4-acetoxystyrene) to said poly(4-hydroxystyrene) or conversion of said substituted
35 poly(4-acetoxystyrene) to said substituted poly(4-hydroxystyrene) or at least 85% by weight transesterification of both is obtained.



2. The process of claim 1, wherein the amount of said poly(4-hydroxystyrene) or said substituted poly(4-hydroxystyrene) or both in said reaction mixture is in the range from about 10% to about 30% by weight.
- 5 3. A process for preparation of polymers having a molar absorbtivity of 250 or less in the wavelength range of from 240 to 260 nm and comprising poly(4-hydroxystyrene) or substituted poly(4-hydroxystyrene) or both, said process comprising the steps of:
- 10 a) reacting a mixture comprising 4-acetoxystyrene monomer or substituted 4-acetoxystyrene monomer or both and a comonomer having at least one vinyl group present, wherein said comonomer does not substantially absorb radiation over wavelengths ranging from about 240 to about 260 nm; and an
- 15 initiator, wherein said initiator and its decomposition products alone or as capping groups do not substantially absorb radiation over wavelengths ranging from about 240 to about 260 nm, and/or wherein said initiator is present at a concentration of less than about 3 mole % of said monomer;
- 20 in a reaction medium comprising at least one organic solvent, to produce a copolymer of 4-acetoxystyrene or substituted 4-acetoxystyrene or both with said comonomer, whereby, either as a result of monomer conversion or due to removal of residual monomer, 10 wt% or less residual
- 25 monomer, based on the weight of polymer produced, is present in the reaction mixture during a subsequent, transesterification reaction step; and
- 30 b) subsequently transesterifying said copolymer of 4-acetoxystyrene or substituted 4-acetoxystyrene or both with said comonomer to a copolymer of 4-hydroxystyrene or substituted 4-hydroxystyrene or both with said comonomer to a conversion of at least 85% by weight of said 4-acetoxystyrene and said substituted 4-acetoxystyrene, in a transesterification reaction medium comprising at least one
- 35 equivalent of alcohol per equivalent of non-transesterified copolymer, using an acid catalyst to achieve said

AMENDED SHEET



transesterification, the acid catalyst being present in an amount of from 5 to 2,000 ppm.

4. The process of claim 3, wherein the said comonomer having at least one vinyl group present is methyl acrylate, methyl methacrylate or a mixture thereof.

5. A process for preparation of copolymers, having a molar absorbtivity of 250 or less in the wavelength range of from 240 to 260 nm, of poly(4-hydroxystyrene) with substituted poly(4-hydroxystyrene), said process comprising the steps of:

a) reacting a mixture comprising 4-acetoxystyrene monomer, substituted 4-acetoxystyrene monomer and an initiator, wherein said initiator and its decomposition products alone or as polymer capping groups do not substantially absorb radiation over wavelengths ranging from about 240 to about 260 nm, and/or wherein said initiator is present at a concentration of less than about 3 mole % of said monomer, in a reaction medium comprising at least one organic solvent, preferably at least one alcohol, to produce a copolymer of 4-acetoxystyrene with substituted 4-acetoxystyrene, wherein at least 90% by weight conversion of said 4-acetoxystyrene monomer and said substituted 4-acetoxystyrene monomer combined is obtained; and

b) subsequently transesterifying said copolymer of 4-acetoxystyrene with substituted 4-acetoxystyrene to a copolymer of 4-hydroxystyrene with substituted 4-hydroxystyrene, in a transesterification reaction medium comprising an alcohol, preferably in substantially said reaction medium of step a), using an acid catalyst to achieve said transesterification, the acid catalyst being present in an amount of from 5 to 2,000 ppm, wherein at least 85% by weight conversion of the combination of said 4-acetoxystyrene to said 4-hydroxystyrene and of said substituted 4-acetoxystyrene to said substituted 4-hydroxystyrene is obtained.

37a



6. The process of any of claims 1 to 5, wherein said reaction medium of step a) is an alcohol reaction medium selected from alcohols having 1 to 5 carbon atoms and combinations thereof.
- 5 7. The process of any of claims 1 to 5, wherein a C₁-

