

- 1 -

DESCRIPTION

COMPOSITE AND PROCESS FOR PRODUCING THE SAME

5 TECHNICAL FIELD

The present invention relates to a composite (or a composite member) of a thermoplastic resin bonded to a rubber integrally which is useful for a mechanical part or a machine element, an automobile part and so on, and
10 relates to a process for producing the same.

BACKGROUND ART

An adhering method for adhering a resin molded article to a rubber molded article by an adhesive is known
15 as a process of integrally joining a resin molded element to a rubber molded element. However, the process using the adhesives not only complicates the process to cause a troublesome process-control with resulting in costly but also does not necessarily give a sufficient adhesive
20 strength.

Meanwhile, a composite of a resin directly bonded to a rubber has been proposed. For example, Japanese Patent Application Laid-Open No. 25682/1975 (JP-50-25682A) discloses a process for producing a rubber-plastic
25 composite, which comprises rubbing a thermoplastic plastic component (e.g., a polyformaldehyde and an olefinic polymer) and a vulcanized rubber component (e.g.,

- 2 -

polybutadiene, nitrile) compatible with the thermoplastic plastic component with contacting each other to melt or fuse the surface of the plastic, and solidifying the melted surface of the resin with contacting the thermoplastic resin component and the vulcanized rubber component.
5 However, in the process, since a configuration of the bonding site or position in the composite is restricted, it is difficult to produce a composite of a thermoplastic resin molded article and a rubber molded article, each
10 having a complicated configuration on a bonding site, and to increase the productivity of the composite.

Regarding to a polyphenylene ether-rubber composite, Japanese Patent Application Laid-Open No. 204260/1986 (JP-61-204260A) discloses a process for producing a
15 composite, which comprises heating a polyphenylene ether-series resin which may have a styrenic polymer and/or an additive together with a synthetic rubber comprising SBR, BR, IR, IIR or the like in the presence of the vulcanizing system. The literature also discloses that a
20 double bond-containing rubber vulcanizable by sulfur is suitable as the rubber component, and that a sulfur-containing compound is used as a vulcanization-activating agent. Further, a comparative example (Table 2) of the literature discloses an example using a rubber composition
25 comprising E-SBR or BR as the rubber component and a peroxide-containing vulcanizing agent or a sulfur-containing vulcanizing agent.

- 3 -

With respect to an ABS resin-rubber composite, Japanese Patent Application Laid-Open No. 301973/1993 (JP-5-301973A) discloses a process for producing a composite, which comprises laminating an ABS resin molded member and an unvulcanized-rubber sheet composed of a rubber component having a critical surface tension of 37 to 39 mN/m, and subsequently heating the laminated sheet for adhering integrally. Japanese Patent Application Laid-Open No. 124803/1997 (JP-9-124803A) discloses a process for producing a composite member, which comprises heating an acrylonitrile-containing thermoplastic resin (e.g., AS resin, ABS resin) with an acrylonitrile-containing rubber with intimately contacting each other. However, these processes markedly restrict species of resins and rubbers for combination because the adhesion depends on a compatibility between the thermoplastic resin and the rubber, and therefore the practical applications are much limited.

Referring to a polyamide-rubber composite, Japanese Patent Application Laid-Open No. 150439/1990 (JP-2-150439A), Japanese Patent Application Laid-Open No. 133631/1991 (JP-3-133631A) and Japanese Patent Application Laid-Open No. 138114/1991 (JP-3-138114A) disclose a process for producing a polyamide-rubber composite, which comprises vulcanizing or crosslinking a rubber component with contacting a polyamide-series resin in the presence of the vulcanizing agent, wherein the rubber

- 4 -

component comprises a carboxyl group- or an acid anhydride group-containing rubber, a peroxide, a vulcanization-activating agent (e.g., ethylene glycol dimethacrylate, triallyl isocyanurate), and an alkoxysilane compound. In these documents, a polyamide-series resin containing the larger number of a terminal amino group than that of a terminal carboxyl group is used as an aliphatic polyamide-series resin. Since these processes utilize a reaction between an amino group and a carboxyl group or an acid anhydride group, a combination of species of resins and rubbers is markedly restricted, and therefore it is difficult to obtain a resin/rubber composite in a wide combination of the resin and the rubber.

Japanese Patent Application Laid-Open No. 11013/1995 (JP-7-11013A) discloses a process for producing a composite member of a vulcanized rubber firmly bonded to a polyamide, which comprises vulcanizing or crosslinking a rubber compound composed of a peroxide-containing vulcanizing agent and a silane compound with contacting a polyamide molded article. The literature discloses that the rubber compound may contain, if necessary, a vulcanization-activating agent, and also discloses that, in a comparative example (Table 2), even if an EPDM rubber comprising a peroxide (perkadox 14/40) and butanediol dimethacrylate (BDMA) was vulcanized in contact with a polyamide-series resin, a bonding between the resin and the rubber was not effected. Therefore, the

composite member is hardly produced without an expensive silane compound.

Japanese Patent Application Laid-Open No. 156188/1996 (JP-8-156188A) discloses a process for
5 producing a composite member, which comprises vulcanizing or crosslinking a carboxyl group- or an acid anhydride group-containing rubber member with contacting closely an epoxy group-containing resin member. However, since this process also uses a reaction between the epoxy group and
10 the carboxyl group, a combined species of the resin and the rubber is markedly limited, and it is difficult to obtain composites widely.

Regarding a process for producing a polyester-rubber composite comprising a thermoplastic polyester as a hard
15 component and a vulcanized rubber as a soft component, Japanese Patent Application Laid-Open No. 304880/1995 (JP-7-304880A) discloses a use of a rubber component comprising a rubber, a peroxide vulcanizing agent, a di- or poly-functional maleimide, and, if necessary, a
20 vulcanization-activating agent, and Japanese Patent Application Laid-Open No. 166043/1995 (JP-7-166043A) proposes to use a rubber component comprising a rubber, a peroxide vulcanizing agent, a silane compound, and, if necessary, a vulcanization-activating agent. Further,
25 concerning a composite film or sheet comprising a resin film and a rubber film, Japanese Patent Application Laid-Open No. 58605/1998 (JP-10-58605A) discloses a

20 JUN 2005

process for producing a composite film by laminating a rubber film (e.g., silicone rubber, ethylene-propylene-series rubber) comprising a polyfunctional methacrylate as an adhesion-improving agent on a substrate
5 film (e.g., a polyester film), and vulcanizing or crosslinking the laminate. However, such processes cause difficulty for bonding the polyester film to the rubber film with a high adhesive strength.

Thus, conventional techniques require trial and
10 error investigation for obtaining a high adhesive strength in a combination of a thermoplastic resin and a rubber, and it is difficult to obtain generally or universally a combination of a thermoplastic resin with a rubber to firmly bond each other.

15 It is, therefore, an object of the present invention to provide a composite of a resin bonded directly to a rubber firmly without an adhesive in a wide extent of combinations of a resin and a rubber, and a process for producing the same.

20 Another object of the invention is to provide a composite excellent in an adhesive strength between a resin and a rubber, and a process for producing the same.

DISCLOSURE OF INVENTION

25 The inventors of the present invention did intensive research, and finally found that a hydrogen atom and a sulfur atom are highly active to a radical-generating agent,

- 7 -

each atom having a specific orbital interaction energy coefficient according to a molecular orbital method, and it is possible that a resin bonds directly to a rubber generally or universally by means of a combination of a thermoplastic resin having plural highly active hydrogen or sulfur atoms per molecule and an unvulcanized rubber comprising a radical-generating agent accompanied with vulcanizing or crosslinking the unvulcanized rubber in a wide extent of combinations of the resin and the rubber.

That is, the composite of the present invention is a composite comprising a vulcanized rubber member obtained by a vulcanization of an unvulcanized rubber and a resin member comprising a thermoplastic resin and bonded directly to the rubber member, which comprises a combination of a rubber member vulcanized with a radical-generating agent and a resin member comprising a thermoplastic resin having at least 2 atoms, on average, selected from a hydrogen atom and a sulfur atom per molecule, and each atom has an orbital interaction energy coefficient S of not less than 0.006, wherein the orbital interaction energy coefficient S is represented by the following formula (1):

$$S = (C_{\text{HOMO},n})^2 / |E_c - E_{\text{HOMO},n}| + (C_{\text{LUMO},n})^2 / |E_c - E_{\text{LUMO},n}| \quad (1)$$

wherein each of E_c , $C_{\text{HOMO},n}$, $E_{\text{HOMO},n}$, $C_{\text{LUMO},n}$, and $E_{\text{LUMO},n}$ represents a value calculated by a semiempirical molecular orbital method MOPACPM3, E_c representing an orbital energy (eV) of a radical of the radical-generating

agent, $C_{\text{HOMO},n}$ representing a molecular-orbital coefficient of a highest occupied molecular orbital (HOMO) of an n-th hydrogen or sulfur atom constituting a constitutive unit of the thermoplastic resin, $E_{\text{HOMO},n}$ representing an orbital energy (eV) of the HOMO, $C_{\text{LUMO},n}$ representing a molecular-orbital coefficient of a lowest unoccupied molecular orbital (LUMO) of the n-th hydrogen or sulfur atom constituting the constitutive unit of the thermoplastic resin, and $E_{\text{LUMO},n}$ representing an orbital energy (eV) of the LUMO.

Said combination excludes or is substantially free from the following combinations (1) to (3); (1) a combination of an aliphatic polyamide-series resin having an amino group and an unvulcanized rubber having a carboxyl group or an acid anhydride group, (2) a combination of an aliphatic polyamide-series resin and an unvulcanized rubber comprising a silane compound, and (3) a combination of an epoxy group-containing resin and an unvulcanized rubber having a carboxyl group or an acid anhydride group. Further, said combination includes the following cases (4) and (5); (4) when the thermoplastic resin comprises a polyamide-series resin, the unvulcanized rubber comprises a polyfunctional vulcanization-activating agent, and (5) when the thermoplastic resin comprises a polyphenylene ether-series resin, the unvulcanized rubber comprises a vulcanization-activating agent.

The thermoplastic resin includes various resins, for

example, a polyamide-series resin, a polyester-series resin, a polyether-series resin, a polyolefinic resin, a polyurethane-series resin, and a thermoplastic elastomer. The rubber includes various rubbers such as a diene-series rubber, an olefinic rubber, an acrylic rubber, a fluorine-containing rubber, and a urethane-series rubber. The radical-generating agent includes, for example, an organic peroxide, an azo compound, and a sulfur-containing organic compound. At least one component selected from the
5 unvulcanized rubber and the thermoplastic resin may
10 comprise a vulcanization-activating agent (e.g., an organic compound having at least two polymerizable-unsaturated bonds per molecule), and the thermoplastic resin may comprise a vulcanizing auxiliary (e.g., a
15 compound having at least 2 hydrogen atoms on average per molecule in which hydrogen atoms each has an orbital interaction energy coefficient S of not less than 0.006).

In the process of the present invention, the composite of a resin member comprising a thermoplastic resin bonded to a rubber member comprising a vulcanized rubber is produced with use of a combination of the above mentioned thermoplastic resin and an unvulcanized rubber comprising a radical-generating agent. The process may comprises molding a resin molding element or material and
20 a rubber molding element or material with contacting said elements or materials each other, and vulcanizing or
25 crosslinking the rubber molding element to produce a

- 10 -

composite of a resin member bonded to a rubber member, wherein said resin molding element or material is either of a resin composition and a resin member, each comprising the thermoplastic resin, and said rubber molding element
5 or material is either of a rubber composition and a rubber premolded article, each comprising at least an unvulcanized rubber and a radical-generating agent being active on a surface to be contacted with said molding resin member or element. The vulcanization-activating agent may
10 be incorporated into at least one component selected from the unvulcanized rubber and the thermoplastic resin, and the thermoplastic resin may comprise the vulcanizing auxiliary.

Moreover, the production process of the present
15 invention also includes a process which comprises heat-molding the resin molding element or material and the rubber molding element or material with interposing a vulcanization-activating agent (and a coating agent comprising the vulcanizing auxiliary) on an interface
20 between the resin molding element or material and the rubber molding element or material to produce a composite comprising the resin member and the rubber member bonded to the resin member.

Further, the process of the present invention
25 includes a process for producing a composite comprising a resin member comprising the thermoplastic resin and a vulcanized rubber member bonded to the resin member, which

- 11 -

comprises heat-molding the resin member and the vulcanized rubber member with interposing a vulcanization-activating agent (and a coating agent comprising the vulcanizing auxiliary) on an interface between the resin member and the vulcanized rubber member. In this process, a combination of the resin and the rubber is not restricted in a combination of the resin member obtained from a resin composition comprising the thermoplastic resin and the vulcanized rubber member obtained from an unvulcanized rubber composition comprising an unvulcanized rubber and a radical-generating agent, and various combinations of the resin and the rubber may be used. The composite of the resin member bonded to the vulcanized rubber member may be produced by treating (coat-treating) a surface of the resin member with a solvent capable of dissolving or swelling the resin member, and contacting the treated surface with the unvulcanized rubber composition. In this process, even if a solvent is removed from the solvent-treated resin member, the firmly bonding of the vulcanized rubber member to the resin member can be realized by contacting the treated surface of the resin member with the unvulcanized rubber composition.

DETAILED DESCRIPTION OF THE INVENTION

[Resin member]

As the thermoplastic resin constituting a resin member, a resin having a plurality of hydrogen atom (an

- 12 -

active hydrogen atom) or sulfur atom (an active sulfur atom) can be selected, and each atom is highly active to a radical-generating agent (hereinafter, the hydrogen atom and the sulfur atom may be referred to as an active atom).

5 That is, the thermoplastic resin can be selected depending on species of the radical-generating agent, and contains for example, an active atom having an orbital interaction energy coefficient S represented by the following formula (1) of not less than the given value (e.g., 0.006, and

10 preferably 0.008). The preferred value of the orbital interaction energy coefficient S of the active atom is about 0.006 to 0.06, and preferably about 0.007 to 0.05 (particularly about 0.01 to 0.045). The number of the active atom in the resin depends on a bonding position or

15 site of a functional group having the active atom (e.g., an end or terminal, a branched chain, or a main chain), and may be, for example, not less than 2 (about 2 to 10000), preferably not less than 2.5 (about 2.5 to 5000), and more preferably not less than 3 (about 3 to 1000) as an average

20 per the thermoplastic resin molecule. The number of the active atom per the thermoplastic resin molecule is usually about 2 to 100 (preferably about 2.5 to 50, more preferably about 3 to 25, and particularly about 3 to 20). The selection of thermoplastic resin satisfied with such

25 conditions progresses a crosslinking reaction on an interface between a rubber component and a thermoplastic resin component in a vulcanization or curing of the rubber

- 13 -

component to firmly or strongly bond each other...

$$S = (C_{\text{HOMO},n})^2 / |E_c - E_{\text{HOMO},n}| + (C_{\text{LUMO},n})^2 / |E_c - E_{\text{LUMO},n}| \quad (1)$$

wherein each of E_c , $C_{\text{HOMO},n}$, $E_{\text{HOMO},n}$, $C_{\text{LUMO},n}$, and $E_{\text{LUMO},n}$ represents a value calculated by the semiempirical molecular orbital method MOPACPM3, E_c representing an orbital energy (eV) of a radical of the radical-generating agent, $C_{\text{HOMO},n}$ representing a molecular-orbital coefficient of a highest occupied molecular orbital (HOMO) of an n-th hydrogen or sulfur atom constituting a constitutive unit of the thermoplastic resin; $E_{\text{HOMO},n}$ representing an orbital energy (eV) of the HOMO; $C_{\text{LUMO},n}$ representing a molecular-orbital coefficient of a lowest unoccupied molecular orbital (LUMO) of the n-th hydrogen or sulfur atom constituting the constitutive unit of the thermoplastic resin, and $E_{\text{LUMO},n}$ representing an orbital energy (eV) of the LUMO.

MOPACPM3 represented by the formula (1) is one of molecular orbital (MO) methods. The molecular orbital method is one of approximations for discussing a molecular electron condition or state, and is classified into three main methods; an empirical method such as Huckel's rule, a semiempirical method enhancing an approximation of the Huckel's rule, and a nonempirical method determining strictly a molecular orbital function by only calculation. In recent years, with developing a computer system, the semiempirical method and the nonempirical method are main methods. The molecular orbital method is a most

- 14 -

convincible method correlating a molecular structure and chemical reactivity thereof. For example, when searching the term "molecular orbital method" as a keyword in JST Online Information System (JOIS), about 53000 of a
5 registered number can be found (term : 1980 to 2000 May). The MOPACPM3 is the core of NDDO (Neglect of Diatomic Differential Overlap) method which is one of the semiempirical methods.

The MOPACPM3 is used for mainly studying a reaction
10 of an organic compound, and is explained in many literatures and publications [e.g., "Molecular orbital method MOPAC guidebook" (Tsuneo Hirano, Kazutoshi Tanabe; Kaibundo, 1991), "Quantum Chemistry, 3rd revised edition" (Teijiro Yonezawa et al., Kagaku Dojin, 1983), "Calculation
15 Chemistry giudebook" (translated by Eiji Osawa et al., written by Tim Clark, Maruzen, 1985)].

A constitutive unit (or basic unit) in the formula (1) means a modeling molecular structure comprising a polymer terminal and about 1 to 3 repeating unit(s). That
20 is, it is difficult to calculate a molecular orbital for a polymer compound itself by MOPACPM3, since the polymer compound has too much numbers of atoms per molecule. Therefore, a calculation may be carried out for a modeling molecular structure (a constitutive unit or basic unit)
25 comprising a polymer terminal and about 2 to 3 repeating units. For example, a molecular structure (repeating unit) of polybutylene terephthalate (PBT) is generally

- 15 -

represented by a chemical formula $-(\text{CH}_2-\text{CH}_2-\text{CH}_2-\text{CH}_2-\text{O}-\text{C}(=\text{O})-\text{C}_6\text{H}_4-\text{C}(=\text{O})-\text{O})_n-$, and the calculation of a molecular orbital in the formula (1) may be conducted for "HO-CH₂-CH₂-CH₂-CH₂-O-C(=O)-C₆H₄-C(=O)-OH" as a constitutive
5 unit.

The orbital interaction energy coefficient S represented by the formula (1) may be referred to as a reactive index, and is defined and explained in various publications. When a chemical reactivity is discussed,
10 the orbital interaction energy coefficient S is used as a parameter for the chemical reactivity in general. For example, "Introduction of Frontier orbital theory" (p.72, Shinichi Yamabe, Satoshi Inagaki, Kodansha Scientific, 1989) describes that an orbital interaction energy
15 coefficient S indicates a concept "Regarding to an interaction between two orbits, (a) a smaller energy difference between two orbits and (b) a larger overlap between two orbits make the interaction stronger". The formula (1) is based upon an idea of superdelocalizability
20 (Sr) published at 1954 by Dr. Fukui given a Nobel prize (see "To use a molecular orbital method", p.71, Minoru Imoto, Kagaku Dojin, 1986), a formula similar to the formula (1) is reported from the concept of Sr on various publications and literatures.

25 Hereupon, it is important that the molecular orbital method is widely known in discussion of a molecular structure and chemical reactivity thereof. Therefore, an

- 16 -

orbital interaction energy coefficient S (1/eV) defined by the following formula (1) does not represent a mere conceptual value, and represents a value meaning a parameter or properties of a material (e.g., a molecular weight, a functional group) for definition of the material.

The radical orbital energy E_C (eV) of a radical-generating agent is preferably calculated based on a radical molecular structure with the use of MOPACPM3, and a predetermined value based on species of the radical-generating agent may be used for convenience. For example, the E_C value of the radical-generating agent may be -8 eV for an organic peroxide, -5 eV for an azo compound, and -6 eV for a sulfur-containing organic compound excluding a sulfur.

As the hydrogen atom having a predetermined value (e.g., 0.006) or more of an orbital interaction energy coefficient S (an active hydrogen atom) in the case where the radical-generating agent comprises an organic peroxide, there may be mentioned, for example, a hydrogen atom constituting, an amino group ($-NH_2$) (e.g., a terminal amino group), an imino group ($-NH-$) (e.g., a main-chain or terminal imino group, $-NH-$ of an amide group), a mercapto group ($-SH$), a methyl group ($-CH_3$), a methylene group ($-CH_2-$) (a methylene group adjacent to an electron-withdrawing or-attracting group, i.e., an active methylene group), and a methylidyne group ($-CH=$) (a main-chain or terminal methylidyne group), etc.

- 17 -

As the sulfur atom having a given value (e.g., 0.006) or more of an orbital interaction energy coefficient S (an active sulfur atom) in the case where the radical-generating agent comprises an organic peroxide, there may
5 be mentioned, for example, a sulfur atom constituting a thio group (-S-), a mercapto group (-SH), an alkylthio group (e.g., a C₁₋₄alkylthio group such as a methylthio group, an ethylthio group), a sulfinyl group (-SO-), etc.

The methyl group includes, for example, a methyl
10 group bonding to an alkylene chain, a cycloalkylene chain, or an aromatic ring; a methyl group bonding to an oxygen atom (e.g., a methyl group in a methoxy group). The methylene group may include, for example, a methylene group adjacent to an oxygen atom constituting a
15 (poly)oxyalkylene unit such as a (poly)oxymethylene unit and a (poly)oxyethylene unit, and a methylene group adjacent to a nitrogen atom constituting an amino group or an imino group. The methylidyne group includes, for example, an α -positioned methylidyne group adjacent to an
20 amino group or an imino group, and a methylidyne group α -positioned to an amino group in an aminocycloalkyl group.

It is sufficient that a thermoplastic resin has plural (e.g., not less than 2) active atoms on average per molecule. That is, the thermoplastic resin is not usually
25 constituted by a single molecule, and comprises a mixture of numerous molecules being partially different in a structure and a chain length. Therefore, all molecules of

- 18 -

the thermoplastic resin are not required essentially to have a plurality of active atoms, and the number of an active atom on average per molecule is to be not less than 2 in calculating a plurality of predictable predominant
5 constitutive or basic units. For example, the number of an active hydrogen atom constituting a polymer having a repeating unit $-(\text{NH}-(\text{CH}_2)_6-\text{NH}-\text{C}(=\text{O})-(\text{CH}_2)_4-\text{C}(=\text{O}))_n-$ (polyamide 66) may be calculated based on a modeling constitutive unit $\text{NH}_2-(\text{CH}_2)_6-\text{NH}-\text{C}(=\text{O})-(\text{CH}_2)_4-\text{C}(=\text{O})-\text{OH}$,
10 and when a radical-generating agent comprises an organic peroxide, an active hydrogen atom comprises 2 hydrogen atoms of a terminal NH_2 group (that is, S is not less than 0.006). In this case, an average number N of an active hydrogen atom per polyamide 66 molecule can be calculated
15 with the use of the following formula (2) from a ratio of a terminal NH_2 group and a terminal COOH group in a polymer (polyamide 66) as an aggregate;

$$N = 2 \times A \quad (2)$$

wherein A represents an average number of a terminal
20 NH_2 group per molecule.

For example, in a ratio of a terminal NH_2 group/terminal COOH group=1/1 (molar ratio) in the resin, the number A of the terminal NH_2 group per molecule is 1, and the number N of the active hydrogen atom per molecule
25 is equal to 2. Moreover, in 1/2 (molar ratio) of terminal NH_2 group /terminal COOH group, the number A of the terminal NH_2 group per molecule shows 2/3, and the number N of the

active hydrogen atom per molecule is $4/3$.

In the case where the thermoplastic resin is a resin mixture comprising plural resins different in the number of an active atom, the number of an active atom in the resin mixture may be represented by an average number of an active atom in each resin. That is, the number of an apparent active atom in the resin mixture can be estimated by calculating respectively an average number of an active atom for each resin based on a constitutive unit, and averaging the calculated number of the active atom according to a proportion (molar ratio) of the plural resins. For example, when the resin mixture comprises (A) the above mentioned polyamide 66 ($N=2$) and (B) the above mentioned polyamide 66 ($N=4/3$), and the ratio of (A)/(B) (molar ratio) is $1/1$, an average active atom number N can be counted as $5/3$. Moreover, when the resin mixture comprises (A) the above mentioned polyamide 66 ($N=2$) and (C) a polyamide 66 having carboxyl group as all terminal groups ($N=0$) and the ratio of (A)/(C) (molar ratio) is $3/1$, an average active atom number N per molecule of the resin mixture can be counted as $3/2$.

The thermoplastic resin is not particularly restricted as far as there are a plurality of active atoms per molecule, and includes various resins, for example, a polyamide-series resin, a polyester-series resin, a polyether-series resin (e.g., a polyacetal-series resin, a polyphenylene ether-series resin, a polysulfide-series

- 20 -

resin), a polyolefinic resin, a polyurethane resin, a thermoplastic elastomer. Moreover, even when a resin does not have the plural active atoms mentioned above, the resin can be modified to a thermoplastic resin capable of firmly bonding to a rubber member by introducing an active atom into the resin. These thermoplastic resins can be used singly or in combination. In the case that two or more thermoplastic resins are used in combination, a resin composition may be a mixed- or compounded-resin composition such as a polymer alloy.

Incidentally, the molecular weight of the thermoplastic resin is not particularly restricted. Even if a polymer having the plural active atoms per molecule, a concentration of the active atom in the polymer relatively decreases with increasing a molecular weight of the polymer to cause a lower crosslinking rate or density between a resin and a rubber. As a result, contribution of the active atom relative to a bonding of the members deteriorates sometimes. Therefore, a resin having a low molecular weight is advantageous for bonding the members. In the present invention, a number-average molecular weight of a resin is usually about 3000 to 400000, preferably about 5000 to 100000, and more preferably about 5000 to 50000, for example, about 8000 to 20000.

(1) A polyamide-series resin

As the polyamide-series resin, there may be mentioned an aliphatic polyamide-series resin, an alicyclic

- 21 -

polyamide-series resin, and an aromatic polyamide-series resin, and the aliphatic polyamide-series resin is practically used. The aliphatic polyamide-series resin includes a condensed compound of an aliphatic diamine component (e.g., a C₄₋₁₀alkylene diamine such as tetramethylenediamine, hexamethylenediamine) and an aliphatic dicarboxylic acid (e.g., an alkylene dicarboxylic acid having about 4 to 20 carbon atoms such as adipic acid, sebacic acid and dodecanedioic acid), for example, polyamide 46, polyamide 66, polyamide 610, polyamide 612 and so on; a homopolymer or a copolymer of a lactam (e.g., a lactam having about 4 to 20 carbon atoms such as ϵ -caprolactam, ω -laurolactam) or an aminocarboxylic acid (e.g., an aminocarboxylic acid having about 4 to 20 carbon atoms such as ω -aminoundecanoic acid), for example, polyamide 6, polyamide 11, polyamide 12 and so on; a copolyamide copolymerizing these polyamide components (e.g., polyamide 6/11, polyamide 6/12, polyamide 66/11, polyamide 66/12) and the like.

As the alicyclic polyamide-series resin, there may be exemplified a polyamide in which an alicyclic diamine and/or an alicyclic dicarboxylic acid is used as at least part of the aliphatic diamine component and/or the aliphatic dicarboxylic acid. The alicyclic polyamide includes, for example, a condensed compound of the aliphatic dicarboxylic acid and an alicyclic diamine component [e.g., a C₅₋₈cycloalkyl diamine such as

- 22 -

cyclohexyl diamine; a bis (aminocyclohexyl)alkane such as bis(aminocyclohexyl) methane and 2,2-bis(aminocyclohexyl)propane].

As the aromatic polyamide-series resin, there may
5 be mentioned, a polyamide in which at least one component among the aliphatic diamine components and the aliphatic dicarboxylic acid components comprises an aromatic component, for example, a polyamide in which the diamine component comprises an aromatic component [e.g., a
10 condensed compound of an aromatic diamine (e.g., meta-xylylenediamine) and an aliphatic dicarboxylic acid, such as MXD-6]; a polyamide in which the dicarboxylic acid component comprises an aromatic component [e.g., a condensate compound of an aliphatic diamine (e.g.,
15 trimethylhexamethylenediamine) and an aromatic dicarboxylic acid (e.g., terephthalic acid, isophthalic acid)]; a polyamide in which both the diamine component and the dicarboxylic acid component comprise an aromatic component [e.g., a fully aromatic amide such as a
20 poly(m-phenyleneisophthalamide (e.g., Aramid^(R))], and others.

The polyamide-series resin further includes a polyamide comprising a dimeric acid as the dicarboxylic acid component, a polyamide having a branched structure
25 by introducing a small amount of a polyfunctional polyamine and/or a polycarboxylic acid component, and a modified polyamide (e.g., N-alkoxymethylpolyamide).

In the polyamide-series resin, an active hydrogen atom includes, for example, a hydrogen atom of a terminal amino group, a hydrogen atom bonding to an α -positioned carbon atom relative to a terminal amino group, a hydrogen atom bonding to a carbon atom adjacent to a group -NH- of an amide bond (e.g., a hydrogen atom of a methylene group, a hydrogen atom of a methylidyne group), in particular the hydrogen atom of the terminal amino group.

In the polyamide-series resin, the proportion of a terminal NH_2 group relative to a terminal COOH group is not particularly restricted, and may be, for example, selected from the range of about 10/90 to 100/0, preferably about 20/80 to 100/0, and more preferably about 25/75 to 100/0 as a molar ratio of terminal amino group/terminal carboxyl group, when the active hydrogen atom comprises a hydrogen atom of the terminal amino group and a hydrogen atom of the α -positioned carbon atom. Moreover, in the case where the active hydrogen atom comprises only hydrogen atoms of the terminal amino group, the ratio (molar ratio) of terminal amino group/terminal carboxyl group, may be about 50/50 to 100/0, preferably about 60/40 to 100/0, and more preferably about 70/30 to 100/0.

(2) A polyester-series resin

The polyester-series resin may be an aliphatic polyester-series resin, and is usually an aromatic polyester-series resin, for example, a polyalkylene arylate-series resin or a saturated aromatic

- 24 -

polyester-series resin. The aromatic polyester-series resin includes, for example, a polyC₂₋₄alkylene terephthalate such as polyethylene terephthalate (PET) and polybutylene terephthalate (PBT); a polyC₂₋₄alkylene naphthalate corresponding to the polyalkylene terephthalate (e.g., polyethylene naphthalate); 1,4-cyclohexyldimethylene terephthalate (PCT). The polyester-series resin may be a copolyester comprising an alkylene arylate unit as a predominant or main component (e.g., not less than 50 % by weight), and a copolymerizable component may be exemplified a C₂₋₆alkylene glycol such as ethylene glycol, propylene glycol, butanediol, and hexanediol; a polyoxyC₂₋₄alkylene glycol; an asymmetrical aromatic dicarboxylic acid or an acid anhydride thereof such as phthalic acid, isophthalic acid; and an aliphatic dicarboxylic acid such as adipic acid. Moreover, a branched structure may be introduced into a linear polyester by using or modifying with small amounts of polyol and/or polycarboxylic acid component.

In the case that the aromatic polyester-series resin has a lower concentration of the active atom relative to the predetermined concentration, a polyester-series resin modified with a modifying compound having the active atom (e.g., an aromatic polyester-series resin comprising at least one member selected from an amino group and an oxyalkylene group) may be used. As the compound having the active atom, particularly, an active hydrogen atom, there

may be mentioned, for example, a polyamine [e.g., an aliphatic diamine such as a linear- or branched-alkylenediamine having about 2 to 10 carbon atoms, e.g., ethylenediamine, trimethylenediamine, propylenediamine, 5 tetramethylene diamine, pentamethylenediamine, hexamethylenediamine, trimethylhexamethylenediamine, 1,7-diaminoheptane, and 1,8-diaminooctane; an alicyclic diamine such as isophorone diamine, bis(4-amino-3-methylcyclohexyl) methane, and bis(aminomethyl) 10 cyclohexane; and an aromatic diamine such as phenylenediamine, xylylenediamine, and diaminodiphenylmethane]; and a polyol [e.g., a (poly)oxyC₂₋₄alkylene glycol such as a (poly)oxyethylene glycol, a (poly)oxytrimethylene glycol, a 15 (poly)oxypropylene glycol, and a (poly)oxytetramethylene glycol]. The modification can be conducted by, for example, heating a mixture of a polyester resin and the modifying compound to cause an amidation, an esterification or an transesterification reaction. The degree of the 20 modification of the polyester-series resin may depend on a concentration of the active hydrogen atom in the compound, and may be, for example, about 0.1 to 2 mol, preferably about 0.2 to 1.5 mol, and more preferably about 0.3 to 1 mol of the modified compound relative to 1 mol of a 25 functional group (e.g., a hydroxyl group or a carboxyl group) of the polyester-series resin. In the transesterification reaction, the amount of the

(poly)oxyC₂₋₄alkylene glycol may be about 1 to 50 parts by weight, and preferably about 5 to 30 parts by weight relative to 100 parts by weight of the polyester-series resin.

5 In the polyester-series resin, the active hydrogen atom usually comprises a hydrogen atom of methylene group adjacent to an oxygen atom of a (poly)oxyalkylene unit. In the modified polyester-series resin, an active hydrogen atom usually comprises a hydrogen atom of a terminal amino
10 group, a hydrogen atom bonding to an α -positioned carbon atom relative to a terminal amino group, a hydrogen atom bonding to a carbon atom adjacent to a group -NH- of an amide bond (e.g., a hydrogen atom of a methylene group, a hydrogen atom of a methylidyne group), and particularly
15 the hydrogen atom of the terminal amino group.

(3) A poly(thio)ether-series resin

The poly(thio)ether-series resin includes a polyoxyalkylene-series resin, a polyphenylene ether-series resin, and a polysulfide-series resin
20 (polythioether-series resin). As examples of the polyoxyalkylene-series resin, there may be mentioned a polyoxyC₁₋₄alkylene glycol such as a polyoxymethylene glycol, a polyoxyethylene glycol, a polyoxypropylene glycol, a polyoxyethylene-polyoxypropylene block-
25 copolymer, and a polyoxytetramethylene glycol, and the like. Preferred examples of the polyether-series resin include a polyacetal-series resin, a polyphenylene

- 27 -

ether-series resin, and a polysulfide-series resin.

(3a) A polyacetal-series resin

The polyacetal-series resin may be a homopolymer (homopolymer of formaldehyde), or a copolymer (e.g., a
5 copolymer of trioxane with ethylene oxide and/or 1,3-dioxolane). Moreover, an end or terminal of the polyacetal-series resin may be blocked or capped to stablized. In the polyacetal-series resin, an active hydrogen atom comprises, for example, a hydrogen atom of
10 an oxymethylene unit, a hydrogen atom of an alkoxy group (particularly methoxy group) of a blocked terminal, and particularly the hydrogen atom of the oxymethylene unit.

(3b) A polyphenylene ether-series resin

The polyphenylene ether-series resin includes
15 various resins comprising 2,6-dimethylphenylene oxide as a main component, for example, a copolymer of 2,6-dimethylphenylene oxide and a phenol, a modified resin in which blending or being grafted with a styrenic resin, and so on. In the polyphenylene ether-series resin, for
20 example, the active hydrogen atom comprises a hydrogen atom of a methyl group bonding to a benzene ring.

(3c) A polysulfide-series resin (polythioether-series resin)

The polysulfide-series resin is not particularly
25 restricted to a specific resin so far as the resin has a thio group (-S-) in the polymer chain. Such a resin includes, for example, a polyphenylene sulfide resin, a

- 28 -

polydisulfide resin, a polybiphenylene sulfide resin, a polyketone sulfide resin, a polythioether sulfone resin, and the like. Moreover, the polysulfide-series resin may have a substituent such as an amino group, including a
5 poly(aminophenylene sulfide). The preferred polysulfide-series resin includes a polyphenylene sulfide resin. In the polysulfide-series resin, the active sulfur atom comprises a sulfur atom of a thio group in the main chain. For example, regarding the polyphenylene sulfide
10 resin, an average number N of the active sulfur atom per molecule can be calculated based on a model of constitutive unit "Cl-C₆H₄-S-C₆H₄-S-C₆H₄-Cl", and the unit has N=2.

(4) A polyolefinic resin

The polyolefinic resin includes, for example, a
15 homopolymer or copolymer of an olefin such as a polyethylene, a polypropylene, an ethylene-propylene copolymer, a poly(methylpentene-1); a copolymer of an olefin and a copolymerizable monomer (e.g., an ethylene-vinyl acetate copolymer, an ethylene-(meth)acrylic acid copolymer, an
20 ethylene-(meth)acrylate copolymer). These polyolefinic resins can be used singly or in combination.

Preferred examples of the polyolefinic resin includes a polypropylene-series resin having a propylene content of not less than 50 % by weight (in
25 particular, 75 to 100 % by weight), for example, polypropylene, propylene-ethylene copolymer, propylene-butene copolymer, propylene-ethylene-butene

copolymer, and so on. Moreover, the polyolefinic resin preferably has a crystallinity.

In the polyolefinic resin, an active hydrogen atom comprises, for example, a hydrogen atom in a methylene group constituting a main chain of a polyolefin, a hydrogen atom
5 in a methyl group branched from the main chain.

(5) A polyurethane-series resin

The polyurethane-series resin can be obtained by reacting a diisocyanate, a polyol and, if necessary, a
10 chain-extension agent. As the diisocyanate, there are exemplified an aliphatic diisocyanate such as hexamethylene diisocyanate and 2,2,4-trimethylhexamethylene diisocyanate; an alicyclic diisocyanate such as 1,4-cyclohexane diisocyanate and
15 isophorone diisocyanate; an aromatic diisocyanate such as a phenylene diisocyanate, a tolylene diisocyanate, and a diphenylmethane-4,4'-diisocyanate; an araliphatic diisocyanate such as a xylylene diisocyanate, and so on. The diisocyanate may be a compound having an alkyl group
20 (e.g., methyl group) substituted on a main chain or a ring.

As a diol, there may be mentioned a polyester diol (e.g., a polyesterdiol derived from a C₄₋₁₂ aliphatic dicarboxylic acid component such as adipic acid; a C₂₋₁₂ aliphatic diol component such as ethylene glycol,
25 propylene glycol, butanediol, and neopentyl glycol; a C₄₋₁₂ lactone component such as ϵ -caprolactone), a polyether diol (e.g., a polyethylene glycol, a polypropylene glycol,

- 30 -

a polyoxyethylene-polyoxypropylene block-copolymer, a polyoxytetramethylene glycol, a bisphenol A-alkylene oxide adduct), a polyester ether diol (a polyester diol in which the polyether diol is used as part of the diol component).

As the chain-extension agent, a C₂₋₁₀alkylene diol such as ethylene glycol and propylene glycol as well as a diamine can be used. The diamine includes, for example, an aliphatic diamine such as a linear- or branched-alkylenediamine having about 2 to 10 carbon atoms (e.g., ethylenediamine, trimethylenediamine, tetramethylenediamine, pentamethylenediamine, hexamethylenediamine, trimethylhexamethylenediamine, 1,7-diaminoheptane, 1,8-diaminooctane) and a linear- or branched-polyalkylenepolyamine (e.g., diethylenetriamine, triethylenetetramine, tetraethylenepentamine, dipropylenetriamine); an alicyclic diamine such as isophoronediamine, bis(4-amino-3-methylcyclohexyl)methane, and bis(aminomethyl)cyclohexane; and an aromatic diamine such as phenylenediamine, xylylenediamine, and diaminodiphenylmethane.

In the polyurethane-series resin, an active hydrogen atom comprises, for example, a hydrogen atom of an alkyl group bonding to a main chain or a ring of the diisocyanate (particularly a hydrogen atom at a benzyl position), a hydrogen atom in an alkylene group of a polyol or a polyoxyalkylene glycol, a hydrogen atom in an amino group

of the chain-extension agent, etc.

(6) A thermoplastic elastomer

The thermoplastic elastomer includes, for example, a polyamide-series elastomer (a copolymer comprising a polyamide as a hard segment and an aliphatic polyether as a soft segment), a polyester-series elastomer (a copolymer comprising a polyalkylene arylate as a hard segment and an aliphatic polyether or aliphatic polyester as a soft segment), a polyurethane-series elastomer (a copolymer comprising a polyurethane containing a short-chain glycol as a hard segment and an aliphatic polyether or an aliphatic polyester as a soft segment, for example, a polyester-urethane elastomer, a polyether-urethane elastomer, or the like), a polystyrenic elastomer (a copolymer comprising a polystyrenic block as a hard segment and a diene-polymer block or a hydrogenated thereof as a soft segment), a polyolefinic elastomer (e.g., a copolymer comprising a polystyrene or a polypropylene as a hard segment and an ethylene-propylene rubber or an ethylene-propylene-diene rubber as a soft segment; an olefinic elastomer comprising a hard segment and a soft segment which are different in crystallinity), a polyvinyl chloride-series elastomer, a fluorine-containing thermoplastic elastomer, and so on. As the aliphatic polyether, the (poly)oxyC₂₋₄alkylene glycol and the other (particularly, the polyoxyethylene glycol) mentioned in the items of the polyester-series resin and the polyurethane-series resin can be used. As

- 32 -

the aliphatic polyester, the polyesterdiol and the other mentioned in the item the polyurethane-series resin can be used. These thermoplastic elastomers can be used singly or in combination.

5 When the thermoplastic elastomer is a block copolymer, a block structure is not particularly restricted, and may be a triblock structure, a multiblock structure, a star-shaped structure or another structure.

 Preferred examples of the thermoplastic elastomer
10 include polyamide-series elastomer, polyester-series elastomer, polyurethane-series elastomer, polystyrenic elastomer, and polyolefinic elastomer.

 In the thermoplastic elastomer, an active hydrogen atom may comprise, for example, a hydrogen atom in an
15 oxyalkylene unit of a soft segment.

(7) Another thermoplastic resin (modified resin)

 The present invention applies to bonding or joining of a thermoplastic resin having a predetermined concentration of the active atom to a rubber. Therefore,
20 when the thermoplastic resin has a lower concentration of the active atom relative to the given concentration, the thermoplastic resin may be used as a modified resin introducing the active atom (amino group, oxyalkylene group, mercapto group, and so on). Such a thermoplastic
25 resin (a resin having less concentration of an active atom than the determined concentration) includes, for example, a vinyl polymerization-series resin [e.g., a (meth)acrylic

- 33 -

resin (e.g., a poly(methyl methacrylate), a methyl methacrylate-styrene copolymer (MS resin)); a styrenic resin (e.g., a polystyrene; a styrenic copolymer such as a AS resin and a styrene-methyl methacrylate copolymer; 5 a styrenic grafted copolymer such as HIPS and ABS resin), a homopolymer or copolymer comprising a halogen-containing monomer (e.g., a polyvinyl chloride, a vinylidene chloride copolymer), a vinyl-series resin (e.g., a polyvinyl acetate, a polyvinyl alcohol)], a condensation-series 10 resin [e.g., a polycarbonate resin (e.g., a bisphenol A-based polycarbonate resin), polyimide-series resin, polysulfone-series resin, polyether sulfone-series resin, polyether ether ketone-series resin, polyarylate-series resin], and another resins.

15 In the vinyl polymerization-series resin, a modified resin may be obtained by copolymerization of a vinyl monomer and a monomer containing a carboxyl group or an acid anhydride group such as (meth)acrylic acid and maleic anhydride to introduce a carboxyl group or an acid anhydride 20 group into the vinyl polymerization-series resin, and, if necessary, reacting the resulting resin with thionyl chloride to produce an acid chloride group, and reacting the resultant with ammonia, a mono-substituted amine (e.g., a monoalkylamine, a monoarylamine) or the diamine 25 mentioned above to introduce an amino group into the resin. Further, a copolymerization of (poly)oxyalkylene glycol mono(meth)acrylate or a (poly)oxyalkylene glycol

- 34 -

monoalkylether (meth)acrylate with the vinyl monomer, or a graft-polymerization of the mono(meth)acrylate to the vinyl polymerization-series resin may introduce the active hydrogen atom for a modification of the vinyl

5 polymerization-series resin.

Further, for the condensation-series resin as well as the vinyl polymerization-series resin, a modification may be carried out by graft-polymerizing a carboxyl group- or an acid anhydride group-containing monomer with a resin
10 to introduce the carboxyl group or the acid anhydride group, if necessary, by reacting the resulting resin with thionyl chloride to produce an acid chloride group, and by reacting the acid chloride group with ammonia, a mono-substituted amine, or the diamine mentioned above to introduce an amino
15 group as same manner as in the above vinyl polymerization-series resin.

(Other component)

The resin member may essentially comprise a thermoplastic resin having a given concentration of the active atom, and may be a resin composition comprising the
20 above-mentioned thermoplastic resin and other thermoplastic resin. As the other thermoplastic resin, there may be mentioned an unmodified thermoplastic resin corresponding to the modified resin (8) such as a styrenic
25 resin, a (meth)acrylic resin, a homopolymer or copolymer of a halogen-containing monomer (e.g., fluorine-containing resin), a vinyl-series resin, a

- 35 -

polycarbonate-series resin, a polyimide-series resin, a polysulfone-series resin, a polyether sulfone-series resin, a polyetheretherketone-series resin, a polyarylate-series resin, a liquid-crystal polyester resin, and the like.

The amount of the thermoplastic resin having the active atom is about 30 to 100 % by weight, preferably about 50 to 100 % by weight, and more preferably about 80 to 100 % by weight based on the total amount of the resin components.

The resin composition for the resin member may comprise various additives, for example, a filler or reinforcer, a stabilizer (an ultraviolet ray absorber, an antioxidant, a heat stabilizer), a colorant, a plasticizer, a lubricant, a flame retardant, an antistatic agent, and other conventional additives.

[Rubber member]

(Rubber)

The rubber member may be obtained by molding (or vulcanizing) a rubber composition comprising a radical-generating agent and a rubber. The rubber is not particularly restricted insofar as the rubber can react with the thermoplastic resin mentioned in the item Resin member, and various rubbers can be used. Particularly, in the present invention, since the thermoplastic resin is capable of being activated by the radical-generating agent, the rubber can be selected within the wide range.

The rubber may include, for example, a diene-series

- 36 -

rubber, an olefinic rubber, an acrylic rubber, a
fluorine-containing rubber, a urethane-series rubber, an
epichlorohydrin rubber (e.g., a homopolymer CO of
epichlorohydrin, a copolymer ECO of epichlorohydrin and
5 ethylene oxide, a copolymer further copolymerized with an
allyl glycidyl ether), a chlorosulfonated polyethylene,
a propylene oxide rubber (GPO), an ethylene-vinyl acetate
copolymer (EAM), a polynorbornene rubber, a modified
rubber of these mentioned above (e.g., acid-introduced
10 rubber), and other rubbers. These rubbers can be used
singly or in combination. Among these rubbers, in view of
a practical use, a widely used rubber includes usually the
diene-series rubber, the olefinic rubber, the acrylic
rubber, the fluorine-containing rubber, the urethane-
15 series rubber, and so on.

As the diene-series rubber, there may be mentioned
a natural rubber (NR); a polymer of a diene-series monomer
such as an isoprene rubber (IR), an isobutylene-isoprene
rubber (butyl rubber) (IIR), a butadiene rubber (BR), and
20 a chloroprene rubber (CR); an acrylonitrile-diene
copolymerized rubber such as an acrylonitrile-butadiene
rubber (nitrile rubber) (NBR), a nitrile-chloroprene
rubber (NCR), and a nitrile-isoprene rubber (NIR); a
styrene-diene copolymerized rubber such as a styrene-
25 butadiene rubber (SBR, for example, a random copolymer of
styrene and butadiene, a SB-block copolymer comprising a
styrene block and a butadiene block, and the like), a

styrene-chloroprene rubber (SCR), and a styrene-isoprene rubber (SIR); and other diene-containing rubber. The diene-series rubber also includes a hydrogenated rubber, for example, a hydrogenated nitrile rubber (HNBR) or the
5 like.

The olefinic rubber includes, for example, an ethylene-propylene rubber (EPM), an ethylene-propylene diene rubber (EPDM), a polyoctenylene rubber, and other rubbers.

10 The acrylic rubber includes a rubber comprising an alkyl acrylate as a main component such as a copolymer ACM of an alkyl acrylate and a chlorine-containing crosslinkable monomer, a copolymer ANM of an alkyl acrylate and acrylonitrile, a copolymer of an alkyl acrylate and
15 a carboxyl group- and/or epoxy group-containing monomer, and an ethylene-acrylic rubber.

As the fluorine-containing rubber, there are exemplified a rubber using a fluorine-containing monomer, for example, a copolymer FKM of vinylidene fluoride and
20 perfluoropropene, if necessary, tetrafluoroethylene; a copolymer of tetrafluoroethylene and propylene; a copolymer FFKM of tetrafluoroethylene and perfluoromethylvinylether.

The urethane rubber (U) includes, for example, a
25 polyester-based urethane elastomer, a polyether-based urethane elastomer, and other elastomers.

As the modified rubber, there may be mentioned, for

- 38 -

example, an acid-introduced rubber such as a carboxyl group- or acid anhydride group-containing rubber [e.g., a carboxylic styrene-butadiene rubber (X-SBR), a carboxylic nitrile rubber (X-NBR), a carboxylic ethylene-propylene rubber (X-EP(D)M)], and other functional group-containing rubbers.

(Radical-generating agent)

In the present invention, the radical-generating agent not only vulcanizes (or crosslinks) the above rubber but also acts to the above thermoplastic resin (for example, activates the above thermoplastic resin radically by a hydrogen-drawing reaction in which the active hydrogen atom is drawn from the thermoplastic resin), to directly bond the thermoplastic resin and a vulcanized rubber by a crosslinking reaction. As the radical-generating agent, various radical-generators can be used depending on species of the thermoplastic resin or the rubber, and the radical-generating agent may be selected from, for example, an organic peroxide, an azo compound, a sulfur-containing organic compound other than a sulfur. Incidentally, since the sulfur causes an ionic reaction and has a considerably lower radical-generating efficiency, and further traps a generated radical, the sulfur is excluded from the radical-generating agent. The radical-generating agent can be used singly or in combination.

The organic peroxide includes, for example, a diacyl peroxide (e.g., lauroyl peroxide, benzoyl peroxide, 4-

chlorobenzoyl peroxide, 2,4-dichlorobenzoyl peroxide), a dialkyl peroxide [e.g., di-t-butyl peroxide; 2,5-di(t-butylperoxy)-2,5-dimethylhexane; 1,1-bis(t-butylperoxy)-3,3,5-trimethylcyclohexane; 2,5-di(t-butylperoxy)-2,5-dimethylhexane-3, 1,3-bis(t-butylperoxyisopropyl) benzene; dicumyl peroxide], an alkyl peroxide (e.g., t-butyl hydroperoxide, cumene hydroperoxide, 2,5-dimethylhexane-2,5-dihydroperoxide, diisopropylbenzene hydroperoxide), an alkylidene peroxide [e.g., ethylmethylketone peroxide, cyclohexanone peroxide, 1,1-bis(t-butylperoxy)-3,3,5-trimethylcyclohexane], a peracid ester (e.g., t-butyl peracetate, t-butyl perpivalate), etc.

The azo compound includes azoisobutyronitrile and other compound. The sulfur-containing organic compound includes, for example, a thiuram [e.g., tetramethylthiuram monosulfide (TMTM), tetramethylthiuram disulfide (TMTD), tetraethylthiuram disulfide (TETD), tetrabutylthiuram disulfide (TBTD), dipentamethylenethiuram tetrasulfide (DPTT)], a dithiocarbamate (e.g., a salt of a diC₁-alkyldithiocarbamic acid such as dimethyldithiocarbamic acid and diethyldithiocarbamic acid with sodium, potassium, iron, copper, zinc, selenium, or tellurium), a thiazole [e.g., 2-mercaptobenzothiazole, 2-(4'-morpholinodithio)benzothiazole], and the like.

As the radical-generating agent, a photopolymerization initiator also may be employed as far

- 40 -

as a photoirradiation can be applied to an adhesion between the resin member and the rubber member. The photopolymerization initiator or photoinitiator may include, for example, a benzophenone or a derivative thereof (e.g., 3,3'-dimethyl-4-methoxybenzophenone, 4,4-dimethoxybenzophenone), an alkylphenylketone or a derivative thereof [e.g., acetophenone, diethoxyacetophenone, 2-hydroxy-2-methyl-1-phenylpropan-1-on, benzyldimethylketal, 1-hydroxycyclohexylphenylketone, 2-benzyl-2-dimethylamino-1-(morpholinophenyl)-butanone], an anthraquinone or a derivative thereof (e.g., 2-methyl anthraquinone), a thioxanthone or a derivative thereof (e.g., 2-chlorothioxanthone, an alkylthioxanthone), a benzoin ether or a derivative thereof (e.g., benzoin, a benzoin alkyl ether), a phosphine oxide or a derivative thereof, and others. The radical-generator also includes a persulfate (e.g., ammonium persulfate, potassium persulfate).

Among these radical-generating agents, the preferred agent is the organic peroxide.

The ratio of the radical-generating agent can be selected within a range of, for example, about 0.5 to 15 parts by weight, and is usually about 1 to 10 parts by weight, and preferably about 1 to 8 parts by weight (e.g., about 2 to 7 parts by weight) relative to 100 parts by weight of an unvulcanized rubber.

- 41 -

(Vulcanization-activating agent or activator)

In the present invention, a vulcanization-activating agent (hereinafter may be sometimes referred to as a hardening agent) may be used together with the radical-generating agent in order to enhance an adhesion efficiency by the radical-generating agent. The vulcanization-activating agent accelerates not only a vulcanization of rubbers but also a crosslinking between the rubber molecule and the resin molecule to bond firmly the rubber member and the resin member. For example, when a thermoplastic resin comprises a polyphenylene ether resin, use of a radical-generating agent and a vulcanization-activating agent in combination progresses a crosslinking reaction between the resin member and the rubber member to ensure the bonding of the members firmly or strongly. The amount of the vulcanization-activating agent may be an amount required for the acceleration of rubber vulcanization and the crosslinking formation between rubbers and resins, and an excess amount of the activating agent may deteriorate a rubber's property. Therefore, an appropriate amount of vulcanization-activating agent can be selected suitably.

As the vulcanization-activating agent, there may be mentioned, for example, an organic compound having a carbon-carbon double bond (a polymerizable unsaturated bond) [e.g., a vinyl-series monomer (e.g., divinylbenzene), an allyl-series monomer (e.g., a diallyl phthalate, a

- 42 -

triallyl phosphate, a triallyl (iso)cyanurate,
a (meth)acrylic monomer], a maleimide-series compound, and
other unsaturated compounds. These vulcanization-
activating agents (activators) can be used singly or in
5 combination. As the vulcanization-activating agent, a
vulcanization-activating agent having the polymerizable
unsaturated bond of not less than 2 is practically used.

Examples of the (meth)acrylic monomer include a
bifunctional (meth)acrylate [e.g., a C₂₋₁₀alkylene glycol
10 di(meth)acrylate such as ethylene glycol di(meth)acrylate,
propylene glycol di(meth)acrylate, 1,4-butanediol
di(meth)acrylate, hexanediol di(meth)acrylate, and
neopentyl glycol di(meth)acrylate; a polyC₂₋₄alkylene
glycol di(meth)acrylate such as diethylene glycol
15 di(meth)acrylate, triethylene glycol di(meth)acrylate,
polyethylene glycol di(meth)acrylate, dipropylene glycol
di(meth)acrylate, tripropylene glycol di(meth)acrylate,
polypropylene glycol di(meth)acrylate, and
polytetramethylene glycol di(meth)acrylate; glycerol
20 di(meth)acrylate; trimethylolpropane di(meth)acrylate;
pentaerythritol di(meth)acrylate; and di(meth)acrylate of
bisphenol A-C₂₋₄ alkylene oxide-adduct], a tri- or
poly-functional (meth)acrylate [e.g., glycerol
tri(meth)acrylate, trimethylolethane tri(meth)acrylate,
25 trimethylolpropane tri(meth)acrylate, pentaerythritol
tri(meth)acrylate, pentaerythritol tetra(meth)acrylate,
dipentaerythritol tetra(meth)acrylate, dipentaerythritol

- 43 -

hexa(meth)acrylate].

A maleimide-series compound having a plurality of maleimide groups can be obtained by a reaction of a polyamine with a maleic anhydride. Examples of the maleimide-series compound include an aromatic bismaleimide [e.g., N,N'-1,3-phenylenedimaleimide, N,N'-1,4-phenylenedimaleimide, N,N'-(3-methyl-1,4-phenylene)dimaleimide, 4,4'-bis(N,N'-maleimide)diphenylmethane, 4,4'-bis(N,N'-maleimide)diphenyl sulfone, 4,4'-bis(N,N'-maleimide)diphenyl ether], an aliphatic bismaleimide (e.g., N,N'-1,2-ethylenebismaleimide, N,N'-1,3-propylenebismaleimide, N,N'-1,4-tetramethylenebismaleimide), etc.

The preferred vulcanization-activating agent includes a compound having a plurality (e.g., about 2 to 6, particularly about 3 to 6) of a carbon-carbon double bond (polymerizable unsaturated bond) per molecule, for example, a triallyl (iso)cyanurate, a di- or poly-functional (meth)acrylate (in particular, tri- or poly-functional (meth)acrylate), and an aromatic maleimide compound.

In the present invention, the addition of the vulcanization-activating agent is not essential. For example, depending on the number of an active atom of a thermoplastic resin and species of a rubber material to be used, the presence of the vulcanization-activating

- 44 -

agent is not required to bond both members. In practical cases, however, in order to ensure firmly bonding of the rubber member and the resin member, the vulcanization-activating agent is advantageously added. The

5 vulcanization-activating agent may be added to at least one component selected from the unvulcanized rubber (or unvulcanized rubber composition) and the thermoplastic resin (or a resin composition), and may be added to both components. The vulcanization-activating agent is

10 usually added to the unvulcanized rubber. The amount of the vulcanization-activating agent is varied depending on species of the vulcanization-activating agent and species of the component to be added (the unvulcanized rubber and/or the thermoplastic resin), and is usually an effective

15 amount for accelerating an adhesion or bonding between the thermoplastic resin and the rubber, for example, about 0.1 to 10 parts by weight, preferably about 0.1 to 5 parts by weight, and more preferably about 0.1 to 3 parts by weight, relative to 100 parts by weight of at least one component

20 selected from the rubber and the resin. For example, in the case where the vulcanization-activating agent comprises a methacrylate of a polyhydric alcohol, the amount of the vulcanization-activating agent is about 0.1 to 10 parts by weight, preferably about 0.1 to 5 parts by

25 weight, more preferably about 0.1 to 3 parts by weight, and practically about 0.1 to 1.9 parts by weight (e.g., 0.5 part by weight, 1.0 part by weight), relative to 100

- 45 -

parts by weight of at least one component selected from the rubber and the resin. Moreover, in the case that the vulcanization-activating agent is added both of the resin and the rubber, a small amount of the vulcanization-
5 activating agent may be added to the resin, and the vulcanizing activator may be used in a proportion of about 0.1 to 7 parts by weight, preferably about 0.1 to 5 parts by weight, and more preferably about 0.1 to 3 parts by weight, relative to 100 parts by weight of the resin.

10 An excess amount of the vulcanization-activating agent may significantly affect properties of the rubber member or the resin member, depending on species of the vulcanization-activating agent. For example, the addition of the excess amount of the vulcanization-
15 activating agent to the rubber component causes troublesomeness, for example, a far higher hardness of a vulcanized rubber than a designed value, and significant deterioration in a long-term property of the rubber member such as a weather resistance. Moreover, the addition of
20 the excess amount of the vulcanization-activating agent to the resin component causes a gel-formation accompanying with a resin member molding to make an appropriate molding difficulty, and a decrease of a mechanical strength. Further, the added vulcanization-activating agent may be
25 migrated from the resin member.

Therefore, in any case of addition of the vulcanization-activating agent to the rubber component or

- 46 -

the resin member, the exceeding amount of more than 10 parts by weight of the vulcanization-activating agent relative to 100 parts by weight of an added object (rubber or resin) is objectionable, and it should be carefully handled the amount of not less than 5 parts by weight, and thus, prior to practical usage, a consequence for the amount of the vulcanization-activating agent to the added object may have been examined. To obtain a sufficient bonding strength between the rubber member and the resin member without any considerations affecting the object to be added, the amount of the vulcanization-activating agent is, for the object comprising a rubber, not more than 2 parts by weight, for example, about 0.1 to 1.9 parts by weight (e.g., about 0.5 to 1.9 parts by weight) relative to 100 parts by weight of the rubber, and for the object comprising a resin, not more than 5 parts by weight, for example, about 0.1 to 5 parts by weight (e.g., about 3 to 5 parts by weight) relative to 100 parts by weight of the resin.

When the vulcanization-activating agent is added to the rubber, the proportion of the radical-generating agent and the vulcanization-activating agent (weight ratio) may be such that, for example, the former/the latter is equal to about 0.3/1 to 20/1 (e.g., about 0.5/1 to 20/1), preferably about 0.4/1 to 15/1 (e.g., about 1/1 to 15/1), and more preferably about 0.5/1 to 10/1 (e.g., about 2/1 to 10/1).

Incidentally, as described later, the

- 47 -

vulcanization-activating agent is not essentially added to the rubber composition and/or the resin composition, and may be applied or coated on a bonding surface or site of the rubber member and/or the resin member.

5 (Vulcanization auxiliary)

In the present invention, to enhance the adhesion efficiency, a vulcanization auxiliary may be used. According to species of the rubber and the resin, an addition of the vulcanizing auxiliary make a bonding
10 between a rubber member and the resin member firmly. The vulcanization auxiliary may be added to at least one component selected from an unvulcanized rubber (or an unvulcanized rubber composition) and a thermoplastic resin (or a resin composition), and may be added to both
15 components. Usually, the vulcanization auxiliary may be added to the thermoplastic resin.

The vulcanization auxiliary can be selected depending on species of the resin and the rubber, and includes, for example, an oligomer of the thermoplastic
20 resin described in the headings (1) to (8) (e.g., an oligomer having a number-average molecular weight of about 100 to 1000 such as an oligomer of the polyamide-series resin and an oligomer of the polyester-series resin), a polyamine [e.g., the polyamine described in the heading
25 (2) polyester-series resin], a polyol [e.g., the polyol described in the heading (2) polyester-series resin], a polycarboxylic acid or an acid anhydride thereof, a

- 48 -

plural-aldehyde groups containing compound, an epoxy compound, a nitrogen-containing resin (e.g., an amino resin), a methanol group- or alkoxymethyl group-containing compound, a polyisocyanate, and the like. These
5 vulcanization auxiliaries may be used singly or in combination.

The preferred vulcanization auxiliary includes a compound having not less than 2 of an active hydrogen atom on the average per molecule, each hydrogen atoms having
10 a predetermined value of an orbital interaction energy coefficient S represented by the formula (1), for example, the oligomer of the thermoplastic resin described in the heads (1) to (8) (e.g., the oligomer of the above mentioned polyamide-series resin and the oligomer of the
15 polyester-series resin), the above mentioned polyamine, and the other.

The amount of the vulcanization auxiliary is, for example, about 0.1 to 30 parts of weight, preferably about 0.5 to 20 parts of weight, and about 1 to 15 parts of weight,
20 relative to 100 parts of weight of the rubber and/or the resin.

(Other additive)

To the rubber composition mentioned above may be added, if necessary, various additives, for example, a
25 filler, a plasticizer or softening agent, a co-vulcanizing agent (e.g., a metal oxide such as zinc oxide), an age resistor (e.g., a heat resistant, an antiozonant, an

- 49 -

antioxidant, an ultraviolet ray absorber), a tackifier, a processing auxiliary, a lubricant (e.g., stearic acid, a metal stearate, a wax), a colorant, a forming agent, a dispersant, a flame retardant, an antistatic agent, and
5 so forth.

The filler (or reinforcer) includes, for example, a powdery or particulate filler or reinforcer (e.g., mica, a clay, a talc, a silicic acid, a silica, a calcium carbonate, a magnesium carbonate, a carbon black, a ferrite), a fibrous
10 filler or reinforcer (e.g., an organic fiber such as rayon, nylon, vinylon, and aramid; an inorganic fiber such as a carbon fiber and a glass fiber), and other fillers.

The plasticizer is not particularly restricted so far as a plasticity can be imparted to the rubber
15 composition, and includes conventional softening agents (e.g., a plant oil such as linolic acid, oleic acid, castor oil, and perm oil; a mineral oil such as a paraffin oil, a process oil, and an extender oil) and plasticizers (e.g., a phthalic acid ester, an aliphatic dicarboxylic acid ester,
20 a sulfur-containing plasticizer, a polyester-series polymer plasticizer).

The content of the filler may be, for example, about 0 to 300 parts by weight, preferably about 0 to 200 parts by weight, and more preferably about 0 to 100 parts by weight,
25 relative to 100 parts by weight of the rubber. The proportion of the plasticizer or softening agent may be, for example, about 0 to 200 parts by weight, preferably

about 0 to 150 parts by weight, and more preferably about 0 to 120 parts by weight, relative to 100 parts by weight of the rubber. The each of the co-vulcanizing agent, the age resistor, the processing agent or lubricant, or the colorant may be used in a proportion of an effective amount, and the amount of the co-vulcanizing agent may, for example, be about 0 to 20 parts by weight, preferably about 0.5 to 15 parts by weight, and more preferably about 1 to 10 parts by weight relative to 100 parts by weight of the rubber.

According to the present invention, since a thermoplastic resin containing an active atom in a predetermined concentration and a rubber are combined, it is possible to bond or unite the resin member comprising the thermoplastic resin and the rubber member comprising the vulcanized rubber in a wide range combination, and further, if necessary, the coexistence of the vulcanization-activating agent ensures the intimate adhesion firmly. Therefore, the combination of the thermoplastic resin and the rubber is not particularly restricted to a specific combination, and the following combinations (a) to (i) may, for example, be mentioned;

(a) a combination of a polyamide-series resin with a unvulcanized rubber comprising a radical-generating agent and being substantially free from modification or introduction of a carboxyl group or an acid anhydride group;

(b) a combination of a polyamide-series resin with a unvulcanized rubber which comprises a radical-generating

agent and a polyfunctional vulcanization-activating agent having two or more functional group (e.g., polyfunctional vulcanization-activating agent having three or more functional group) and substantially free from an alkoxy
5 silane compound,

that is, in the present invention, an unmodified rubber (e.g., a rubber unmodified or unintroduced by a carboxyl group/an acid anhydride group) as an unvulcanized rubber can be used without utilizing the reaction between
10 an amino group of the polyamide-series resin and a carboxyl group or an acid anhydride group of the rubber, and therefore an applicability of the combination of polyamide-series resin (e.g., an aliphatic polyamide-series resin) with the rubber can be widely expanded;

15 (c) a combination of an aromatic polyester-series resin having an amino group and an oxyalkylene group with an unvulcanized rubber comprising a radical-generating agent;

(d) a combination of a polyacetal-series resin with
20 an unvulcanized rubber comprising a radical-generating agent;

(e) a combination of a polyphenylene ether-series resin with an unvulcanized rubber comprising a radical-generating agent and a vulcanization-activating
25 agent;

(f) a combination of a polysulfide-series resin with an unvulcanized rubber comprising a radical-generating

agent;

(g) a combination of a polypropylene-series resin with an unvulcanized rubber comprising a radical-generating agent;

5 (h) a combination of a polyurethane-series resin with an unvulcanized rubber comprising a radical-generating agent;

(i) a combination of a thermoplastic elastomer with an unvulcanized rubber comprising a radical-generating agent.
10

In such combinations, the preferred radical-generating agent includes an organic peroxide, and the preferred vulcanization-activating agent comprises a di- or poly-functional vulcanization-activating agent
15 (particularly tri- or poly-functional (meth)acrylate).

[Process for producing a composite]

In the present invention, a composite of a resin member comprising the thermoplastic resin bonded to a rubber member comprising a vulcanized rubber can be
20 produced by use of a combination of the thermoplastic resin and an unvulcanized rubber comprising a radical-generating agent. The composite (or resin/rubber composite) can be produced by molding a resin molding element or material and a rubber molding element or material with contacting
25 each other and a vulcanizing or crosslinking the rubber molding member or element.

The resin molding element or material may be a resin

- 53 -

composition comprising a thermoplastic resin, or a resin preformed or premolded member beforehand (or a resin shaped article). Moreover, the rubber molding element or material is not particularly restricted to a specific member as far as the rubber molding member or element has an active radical-generating agent on a surface contacted with the resin molding member or element and comprises at least an unvulcanized rubber. The rubber molding element or material may be an unvulcanized rubber composition, or a rubber preformed or premolded article (rubber molded precursor) having a partially vulcanized or crosslinked rubber.

That is, the composite may be produced by molding a resin composition comprising a thermoplastic resin (preferably a resin composition containing at least the vulcanization-activating agent) and an unvulcanized rubber composition comprising an unvulcanized rubber and a radical-generating agent (preferably a unvulcanized rubber composition further comprising at least the vulcanization-activating agent) with contacting each other, and vulcanizing or crosslinking the unvulcanized rubber composition to bond or join the resin member and the rubber member.

Moreover, as far as the radical-generating agent is activated, at least one member selected from the resin member (or a shaped resin article) and the rubber member (or a shaped rubber article) may have been molded or formed

- 54 -

beforehand. The examples of the molding technique are further illustrated as follows:

(1) a composite may be produced by contacting a resin member comprising a thermoplastic resin with an
5 unvulcanized rubber composition, and then molding the unvulcanized rubber composition with vulcanizing or crosslinking the unvulcanized rubber composition.

(2) a composite may be produced by contacting a premolded rubber article (a precursor or intermediate)
10 comprising a preliminarily vulcanized or crosslinked rubber composition with the resin composition mentioned above, and molding the resin composition in a desired shape.

(3) a composite may be produced by contacting a resin member comprising a thermoplastic resin with a premolded
15 rubber article (a precursor) obtained by vulcanizing or crosslinking the rubber composition to be molded. Incidentally, the preformed rubber article has an activated radical-generating agent at least on a surface contacted with the resin molding member or element, and
20 may have a residual radical-generating agent.

More concretely, the process of the present invention includes a process which comprises contacting or meeting (or converging) a resin composition with an unvulcanized rubber composition with molding the resin composition and
25 the unvulcanized rubber composition respectively in a metal mold to bond or adhere directly the resin member and the vulcanized rubber member (one-step method); a process

- 55 -

which comprises contacting a premolded or preformed resin member with an unvulcanized rubber composition, and molding the unvulcanized rubber composition by vulcanizing or crosslinking the unvulcanized rubber composition to join or bond the resin member and the vulcanized rubber member (two-step method); a process comprising a step for contacting a premolded resin member with a preformed rubber article produced by molding an unvulcanized rubber composition to the intermediate stage (partially vulcanized or crosslinked), and a step for vulcanizing or crosslinking the premolded rubber article to bond or adhere the resin member and the vulcanized rubber member (three-step method); and other molding methods.

The preferred process includes the one-step method and the two-step method (particularly the two-step method). In the one-step method, a composite molded article can be obtained by melting and kneading the resin composition and the unvulcanized rubber composition, respectively, injecting or extruding the molten and kneaded compositions into a metal mold having a desired cavity or configuration with use of, for example, a conventional multi-molding apparatus (e.g., a multi-injection molding apparatus, a multilayer extruder), and vulcanizing or crosslinking the unvulcanized rubber on or after the molding. The resin composition and the unvulcanized rubber composition may be mixed or mingled at or in the contact interface area between these compositions.

In the two-step method, a conventional molding apparatus (e.g., an injection molding apparatus, an extrusion molding apparatus, a thermal-press molding apparatus) can be used for forming the shaped resin member, and a conventional molding apparatus (e.g., an injection molding apparatus, a press molding apparatus, a transfer molding apparatus, an extrusion molding apparatus) can be used for forming the rubber member. In the molding process, a vulcanized rubber member and a resin member may be bonded or adhered by placing or setting a resin member into a mold (or a cavity) in conformity with a configuration of a composite, injecting or extruding an unvulcanized rubber composition to the resin member, and vulcanizing or crosslinking the unvulcanized rubber composition.

Moreover, when the shape of the composite is a plate- or sheet-like member having a two-dimensional configuration, the composite may be produced by laminating a plate- or sheet-like unvulcanized rubber composition to a shaped resin member, and vulcanizing or crosslinking the unvulcanized rubber composition without the mold (or cavity). Incidentally, when contacting (e.g., closely contacting or adhering) a resin member (or a resin composition) with an unvulcanized rubber composition, a pressure molding may be conducted by applying a pressure suitably with use of a thermalpress molding or an injection molding, for example, under a reduced pressure in order to remove a volatile component or a gas component from the

- 57 -

composition(s).

The vulcanization (or curing) or crosslinking temperature (or a bonding temperature between the rubber member and the resin member) can be selected, for example, from about 70 to 250 °C, preferably about 100 to 230 °C, and more preferably about 150 to 220 °C. The pressure loaded to the rubber and the resin can be selected, for example, from within the range of about 0 to 350 MPa, preferably about 1 to 150 MPa, and more preferably about 2 to 100 MPa.

In the production process of the composite, at least one component selected from an unvulcanized rubber and a thermoplastic resin may comprise a vulcanization-activating agent (e.g., a polymerizable compound having the above mentioned plural polymerizable groups) and a vulcanization auxiliary (e.g., the above mentioned polyamine). Usually, the vulcanization auxiliary is added practically to the thermoplastic resin.

Moreover, as described above, the vulcanization-activating agent is usually incorporated into the unvulcanized rubber composition (or the rubber member) and/or the resin composition, and the process of the present invention also includes a production process of a composite of the resin member bonded to the rubber member by molding the resin molding member or element and the rubber molding member or element under heating with interposing at least the vulcanization-activating agent (if necessary, further

- 58 -

incorporation of the vulcanization auxiliary) on a contacting surface (or a bonding surface) between the resin molding member or element and the rubber molding member or element.

5 Further, the process of the present invention also includes a process for producing a composite by pressing or contacting a shaped resin member comprising a thermoplastic resin with a vulcanized rubber member under heating with interposing at least the vulcanization-
10 activating agent (if necessary, further incorporation of the vulcanization auxiliary) on a contacting surface (or a bonding surface) between the resin member and the vulcanized rubber member to bond or adhere the resin member and the rubber member. In the process, the vulcanized
15 rubber member is not essentially vulcanized or crosslinked by the radical-generating agent (e.g., an organic peroxide), and may be vulcanized with use of a sulfur containing vulcanizing agent. In the preferred process, a shaped resin member or element of the thermoplastic resin
20 is used in a combination with a shaped rubber member or element of the unvulcanized rubber composition. That is, a resin member comprising the thermoplastic resin is preferably combined with a vulcanized rubber member obtained from an unvulcanized rubber composition
25 comprising at least a radical-generating agent and an unvulcanized rubber.

Furthermore, on an interface between the resin member

- 59 -

and the vulcanized rubber member, a coating agent comprising at least the vulcanization-activating agent (if necessary, further the vulcanization auxiliary) may be interposed by a coating technique, and the coating agent
5 may be a radically active agent comprising the radical-generating agent and the vulcanization-activating agent (if necessary, further the vulcanization auxiliary). The amount of the coating agent on the interface between the resin member and the vulcanized rubber member may, for
10 example, be about 0.1 to 10 g/m², preferably about 0.5 to 5 g/m², and particularly about 1 to 5 g/m².

The composite of the resin member bonded to the vulcanized rubber member can be obtained by heating (in particular, heat-pressing) the resin member and the
15 vulcanized rubber member with interposing the above mentioned coating agent between these members. The heating temperature and pressure can be selected within the range similar to the vulcanization or crosslinking temperature and pressure mentioned above.

20 Moreover, it is effective for bonding the resin member to the unvulcanized rubber member that a surface of the resin member is treated with a solvent capable of dissolving or swelling the resin member by a treatment such as coating or dipping, and the treated surface is contacted
25 with the unvulcanized rubber composition. The solvent can be selected, depending on species of the resin member and includes, for example, a hydrocarbon (e.g., an aliphatic

hydrocarbon such as hexane and octane, an alicyclic hydrocarbon such as cyclohexane, an aromatic hydrocarbon such as toluene and xylene), an alcohol (e.g., an alcohol such as isopropanol, butanol, and cyclohexanol; a
5 haloalkylalcohol such as tetrafluoroethanol and hexafluoroisopropanol), a phenol (e.g., phenol, cresol), an organic acid (e.g., formic acid, acetic acid, trifluoroacetic acid, trichloroacetic acid), an ester (e.g., ethyl acetate, butyl acetate), a ketone (e.g.,
10 acetone, methyl ethyl ketone, methyl isobutyl ketone), an ether (e.g., dioxane, diethyl ether, tetrahydrofuran), a sulfoxide (e.g., dimethyl sulfoxide), an amide (e.g., dimethylformamide, dimethylacetoamide), and a mixture thereof.

15 For example, for a resin comprising a polyamide resin, a solvent such as a phenol (e.g., phenol, cresol), an organic acid (e.g., formic acid), a ketone (e.g., hexafluoroacetone), an alcohol (e.g., hexafluoro isopropyl alcohol) may be coated singly or in combination
20 with a conventional solvent on the contacting surface with the rubber member. Moreover, for a resin comprising a polyphenylene ether resin, as the solvent or a swelling agent, there may be, for example, exemplified with a hydrocarbon (e.g., toluene), a ketone (e.g., acetone,
25 methyl ethyl ketone, hexafluoroacetone), an ether (e.g., tetrahydrofuran), an amide (e.g., dimethylformamide), an alcohol (e.g., hexafluoroisopropylalcohol), and so on.

- 61 -

After treating the resin member with the solvent, even if the solvent is removed from the resin member by washing, drying, or other methods, the firmly bonding of the vulcanized rubber member to the resin member can be realized by contacting the treated surface of the resin member with the unvulcanized rubber composition.

Thus, the obtained composite has a markedly high adhesive strength between the rubber member and the resin member by vulcanization. Therefore, both properties of the thermoplastic resin and the rubber can be effectively expressed, and the obtained composite can be advantageously employed as various applications, for example, an automobile part (e.g., a vibration- or shock-absorbing bush, a spring plate, a door locking part, a radiator mount), a rubber vibration isolator, a valve, an electrical plug, and other parts or elements.

INDUSTRIAL APPLICABILITY

According to the present invention, a thermoplastic resin containing a predetermined concentration of a hydrogen or sulfur atom, each atom having a specific orbital interaction energy coefficient, is combined with an unvulcanized rubber comprising a radical-generating agent. Thus, the resin can be directly bonded to the rubber firmly without an adhesive in a wide combination to obtain a composite having a high adhesive strength.

- 62 -


EXAMPLES

The following examples are intended to describe this invention in further detail and should by no means be interpreted as defining the scope of the invention. In Examples and Comparative examples, the following resin composition and rubber composition were used.

[Resin compositions (A) to (J)]

Resin compositions A1 to A6

The following resin compositions (A1 to A6) were prepared by use of a polyamide 612 (a polycondensate of hexamethylenediamine and dodecanedicarboxylic acid) as a thermoplastic resin. A MOPACPM3 calculation was carried out for the following basic constitutive unit.



Resin composition (A1):

A polyamide 612 [terminal NH_2 /terminal COOH = 9/1 (molar ratio)]

(Preparation)

A predetermined amount of hexamethylenediamine was added to 80 % by weight aqueous solution of a salt of hexamethylenediamine with dodecanedicarboxylic acid, and the mixture was heated at 220°C under an applied pressure (17.5 kg/cm^2) in an autoclave substituted with nitrogen gas to flow out water with nitrogen gas from the inside to the outside of the reaction system for 4 hours.

Subsequently, the temperature of the system was gradually raised to 275°C over 1 hour to discharge a residual water

- 63 -

in the system, and the applied pressure of the autoclave was reduced to be an atmospheric pressure. After cooling the system, a polyamide 612 was obtained. The obtained polymer had a number average molecular weight (M_n) of about
5 20,000 and a ratio of terminal amino group/terminal carboxyl group = 9/1. The polymer was used alone for Resin composition (A1).

Resin composition (A2):

50 % by weight of a polyamide 612 [terminal NH_2 /
10 terminal COOH = 9/1 (molar ratio)]

50 % by weight of a carbon staple (shorten-fiber)
(Preparation)

Equal or equivalent amounts of Resin composition (A1) and a carbon fiber were kneaded by a biaxial extruder, and
15 the kneaded one was used for Resin composition (A2).

Resin composition (A3):

12 % by weight of a polyamide 612 [terminal NH_2 /
terminal COOH = 9/1 (molar ratio)]

88 % by weight of a soft ferrite
20 (Preparation)

100 parts by weight of Resin composition (A1) and 733 parts by weight of a soft ferrite were kneaded by a kneader, and the resultant was used for Resin composition (A3).

25 Resin composition (A4):

A polyamide 612 [terminal NH_2 /terminal COOH = 1/1
(molar ratio)]

- 64 -

(Preparation)

An aqueous solution containing a salt of hexamethylenediamine with dodecanedicarboxylic acid in an amount of 80 % by weight was heated at 220°C under an applied pressure (17.5 kg/cm²) in an autoclave substituted with nitrogen gas to flow out water with nitrogen gas from the reaction system for 4 hours. Subsequently, the temperature of the system was gradually increased to 275 °C over 1 hour to remove water remaining in the system, and the applied pressure of the autoclave was reduced to be an atmospheric pressure. After cooling the system, a polyamide 612 was obtained. The polymer had a molecular weight (Mn) of about 20000 to 25000, and a ratio of terminal amino group/terminal carboxyl group = 1/1. The polymer was used alone for Resin composition (A4).

Resin composition (A5):

A polyamide 612 [terminal NH₂/terminal COOH = 3/7 (molar ratio)]

(Preparation)

A resin composition (A1) and the following resin composition (A6) were kneaded in a proportion of the former/the latter = 1/3 (weight ratio) by a biaxial extruder. The obtained composition was used for Resin composition (A5).

Resin composition (A6):

A polyamide 612 [terminal NH₂/terminal COOH = 1/9 (molar ratio)]


- 65 -

(Preparation)

To an aqueous solution containing a salt of hexamethylenediamine with dodecanedicarboxylic acid in an amount of 80 % by weight was added a predetermined amount of dodecanedicarboxylic acid, and the mixture was heated at 220 °C under an applied pressure (17.5 kg/cm²) in an autoclave substituted with nitrogen gas to remove water with nitrogen gas from the reaction system for 4 hours. Subsequently, the temperature of the system was gradually elevated to 275 °C with taking 1 hour to discharge a residual water in the system, and the applied pressure of the autoclave was reduced to be an atmospheric pressure. After cooling, a polyamide 612 was obtained. The obtained polymer had a molecular weight (Mn) of about 20000 and a ratio of terminal amino group/terminal carboxyl group = 1/9. The polymer was used for Resin composition (A6).

Resin compositions B1 to B2

The following resin compositions (B1 to B2) were prepared by use of a polyamide 66 (a polycondensate of hexamethylenediamine and adipic acid) as a thermoplastic resin. A calculation with MOPACPM3 was carried out for the following constitutive unit.



Resin composition (B1):

A polyamide 66 [terminal NH₂/terminal COOH = 1/1 (molar ratio)]

(Preparation)

- 66 -

A resin composition was prepared by the same manner as in Resin composition (A4) except for using a monomer combination of hexamethylenediamine and adipic acid to obtain a polyamide 66 having a molecular weight (Mn) of about 20000 to 25000 and a ratio of terminal amino group/terminal carboxyl group = 1/1. The polyamide 66 was used for Resin composition (B1).

Resin composition (B2):


A polyamide 66 [terminal NH_2 /terminal COOH = 1/3 (molar ratio)]

(Preparation)

A preparation procedure was conducted in the same manner as in Resin composition (A6) except for using a monomer combination of hexamethylenediamine and adipic acid to obtain a polyamide 66 having a molecular weight (Mn) of about 20000 of and a ratio of terminal amino group/terminal carboxyl group = 1/9. The polyamide 66 and Resin composition (B1) were kneaded in a weight ratio of 62.5/37.5 by a biaxial extruder, and the resulting resin composition was employed for Resin composition (B2).

Resin compositions C1 to C3

The following resin compositions (C1 to C3) were prepared with use of a polyamide 6 (a ring-opening polymerized product of ϵ -caprolactam) as a thermoplastic resin. A calculation with MOPACPM3 was carried out with use of the following unit as a constitutive unit.



- 67 -

Resin composition (C1):

A polyamide 6 [terminal NH_2 /terminal COOH = 1/1
(molar ratio)]

(Preparation)

5 An aqueous solution containing ϵ -caprolactam in an
amount of 80 % by weight was heated at 250 to 260 °C in the
presence of a small amount of phosphoric acid in an
autoclave substituted with nitrogen gas to remove water
with nitrogen gas from the reaction system for 4 hours.
10 Subsequently, the temperature of the inside system was
gradually elevated to 275 °C for taking 1 hour to remove
a residual water to outside system. After cooling, a
polyamide 6 was obtained. The obtained polymer had a
molecular weight (M_n) of about 20000 to 25000 and a ratio
15 of terminal amino group/terminal carboxyl group = 1/1. The
polymer was used for Resin composition (C1).

Resin composition (C2):

A polyamide 6 (terminal NH_2 /terminal COOH =1/3 (molar
ratio))

20 (Preparation)

A predetermined amount of adipic acid was
added to an aqueous solution containing ϵ -caprolactam in
an amount of 80 % by weight, and the mixture was heated
at 250 to 260 °C in the presence of a small amount of
25 phosphoric acid in an autoclave substituted with nitrogen
gas to flow out water with nitrogen gas from the reaction
system for 4 hours. The temperature of the system was

- 68 -

gradually raised to 275 °C with taking 1 hour to remove a residual water from the system, and the applied pressure of the autoclave was reduced to be an atmospheric pressure. After cooling, a polyamide 6 was obtained. The polyamide
5 6 had a molecular weight (Mn) of about 20000 and a ratio of terminal amino group/terminal carboxyl group = 1/9. The polymer was used for Resin composition (C4). Resin composition (C4) and Resin composition (C1) were kneaded in a weight ratio of the former/the latter = 37.5/62.5,
10 and the resulting resin composition was employed for Resin composition (C2).

Resin composition (C3):

A polyamide 6 [terminal NH₂/terminal COOH = 1/4
(molar ratio)]

15 (Preparation)

Resin composition (C1) and Resin composition (C4) were kneaded in a weight ratio of 25/75 as the former/the latter ratio to obtain Resin composition (C3).

Resin compositions D1 to D3

20 The following resin compositions (D1 to D3) were prepared by using a polyamide 46 (a polycondensation product of diaminobutane and adipic acid) as a thermoplastic resin. A calculation with MOPACPM3 was carried out for the following constitutive unit.

25 NH₂-(CH₂)₄-NH-C(=O)-(CH₂)₄-C(=O)-OH

Resin composition (D1):

A polyamide 46 [terminal NH₂/terminal COOH = 1/1

- 69 -

(molar ratio)]

Resin composition (D2):


A polyamide 46 [terminal NH_2 /terminal COOH = 1/3
(molar ratio)]

5 Resin composition (D3):

A polyamide 46 (terminal NH_2 /terminal COOH = 1/4
(molar ratio))

Resin compositions E1 to E3

The following resin compositions (E1 to E3) were
10 prepared by using a polycondensate of terephthalic acid
and trimethylhexamethylenediamine (an aromatic polyamide
A5) as a thermoplastic resin. A MOPACPM3 calculation was
carried out for the following constitutive unit.



15

Resin composition (E1):

Anaromatic polyamide A5 [terminal NH_2 / terminal COOH
= 1/1 (molar ratio)]

(Preparation)

20

A resin composition was prepared in the same manner
as in Resin composition (A4) except for using a monomer
combination of trimethylhexamethylene diamine and
terephthalic acid to give a polymer having a molecular
weight (M_n) of about 20000 to 25000 and a weight ratio of
25 terminal amino group/terminal carboxyl group = 1/1. The

- 70 -

polymer was used as Resin composition (E1).

Resin composition (E2):

An aromatic polyamide A5 [terminal NH_2 / terminal COOH
= 1/3 (molar ratio)]

5 (Preparation)

A resin composition was prepared in the same manner
as in Resin composition (A6) except for using a monomer
combination of trimethylhexamethylene diamine and
terephthalic acid to obtain a polymer having a molecular
10 weight (M_n) of about 20000 and a weight ratio of terminal
amino group/terminal carboxyl group = 1/9. The polymer was
used for Resin composition (E4). Resin composition (E4)
and Resin composition (E1) were kneaded in a weight ratio
of 62.5/37.5 by a biaxial extruder, and the obtained resin
15 composition was used as Resin composition (E2).

Resin composition (E3):

An aromatic polyamide A5 [terminal NH_2 / terminal COOH
= 1/4 (molar ratio)]

(Preparation)


20 Resin composition (E1) and Resin composition (E4)
were kneaded in a weight ratio of 25/75 as the former/the
latter to obtain Resin composition (E3).

Resin compositions F1 to F3

The following resin compositions (F1 to F3) were
25 prepared by using a polycondensation product of
dodecanedicarboxylic acid and bis(4-aminocyclohexyl)
methane (an alicyclic polyamide A6) as a thermoplastic

- 71 -

resin. The following constitutive unit was used for a MOPACPM3 calculation.



5 Resin composition (F1):

 An alicyclic polyamide A6 [terminal NH_2 /terminal $\text{COOH}=1/1$ (molar ratio)]

 (Preparation)

 The same manner as in Resin composition (A4) was
 10 repeated except for using a monomer combination of
 bis(4-aminocyclohexyl) methane and dodecanedicarboxylic
 acid to obtain a polymer having a molecular weight (M_n)
 of about 20000 to 25000 and a ratio of terminal amino
 group/terminal carboxyl group = 1/1. The polymer was
 15 employed as Resin composition (F1).

 Resin composition (F2):

 An alicyclic polyamide A6 [terminal NH_2 /terminal $\text{COOH}=1/2$ (molar ratio)]

 (Preparation)

20 A resin composition was produced by the same manner
 as in Resin composition (A6) except for using a monomer
 combination of bis(4-aminocyclohexyl) methane and
 dodecanedicarboxylic acid to give a polymer having a
 molecular weight (M_n) of about 20000 of and a weight ratio
 25 of terminal amino group/terminal carboxyl group = 1/9.

- 72 -

The polymer was Resin composition (F4). Resin composition (F4) and Resin composition (F1) were kneaded in a weight ratio of 133.4/66.6 as the former/the latter ratio by a biaxial extruder, and the obtained resin composition was
 5 used as Resin composition (F2).

Resin composition (F3):

An alicyclic polyamide A6 [terminal NH_2 /terminal COOH = 1/3 (molar ratio)]


(Preparation)

10 Resin composition (F4) and Resin composition (F1) were kneaded by a biaxial extruder in a proportion of 62.5/37.5 (weight ratio) as a former/latter ratio, and the obtained resin composition was used as Resin composition (F3).

Resin compositions G1 to G2


15 The following resin compositions (G1 to G2) were prepared by using PBT (a polycondensation product of terephthalic acid and 1,4-butanediol) or an amine-modified PBT (a reaction product of the PBT and hexamethylenediamine) as a thermoplastic resin. A
 20 calculation with MOPACPM3 was carried out based upon the following constitutive unit.

for the PBT:



for the amine-modified PBT:

- 73 -



Resin composition (G1):

A PBT [terminal OH/terminal COOH = 1/1 (molar ratio)]

(Preparation)

5 To a reactor equipped with a nitrogen-introducing unit and a distilling unit were charged 14.587 kg of dimethyl terephthalate, 6.767 kg of 1,4-butanediol, 30 g of calcium acetate, and 60 g of antimony oxide, and the mixture was heated at 180°C with supplying nitrogen gas.

10 At the point of confirming an effluent of methanol, the mixture was gradually heated to 270°C under a reduced pressure with stirring to reach degree of vacuum of not more than 100 Pa. With confirming an effluent of ethylene glycol, the mixture was heated at 270°C for 3 hours. The

15 resultant was allowed to stand for cooling. The obtained polymer was used for Resin composition (G1).

Resin composition (G2):

An amine-modified PBT [terminal NH₂/terminal OH=1/1 (molar ratio)]

20 (Preparation)


Resin composition (G2) was obtained by kneading Resin composition (G1) and an equimolar methylenediamine relative to a carboxylic group content of Resin composition (G1) at 230°C for 30 minutes with use of a kneader.

25 Resin compositions H

- 74 -


As Resin composition H, poly(2,5-dimethylphenylene ether) (manufactured by Degussa Co. Ltd., Vestoran 1990) was used. A MOPACPM3 calculation was carried out based upon the following constitutive unit.

5




Resin compositions I

A polypropylene was used as Resin composition I. A MOPACPM3 calculation was conducted for the following
10 constitutive unit.




Resin compositions J

A polyacetal (manufactured by Polyplastics Co. Ltd., Juracone M90) was used as Resin composition J. A
15 calculation with MOPACPM3 was carried out for the following basic unit.



Resin compositions K

A polyphenylene sulfide [manufactured by
20 Polyplastics Co. Ltd., Fortlon 0220A9 (non-charged)] was used for a resin composition K. The following constitutive unit was bases for calculation of MOPACPM3.



Resin compositions (L to N) were prepared by mixing

- 75 -

or compounding a resin and a vulcanization-activating agent in a suitable ratio.

Resin compositions L1 to L2

Resin composition (L1):

5 (i) 100 parts by weight of a polyamide 612 [terminal NH_2 /terminal $\text{COOH} = 1/1$ (molar ratio)] and

 (ii) 3 parts by weight of a vulcanization-activating agent (trimethylolpropane trimethacrylate)

Resin composition (L2):

10 (i) 100 parts by weight of a polyamide 612 (terminal NH_2 /terminal $\text{COOH} = 1/9$ (molar ratio)] and

 (ii) 3 parts by weight of a vulcanization-activating agent (trimethylolpropane trimethacrylate)

Resin compositions M1 to M2

15 Resin composition (M1):

 (i) 100 parts by weight of a polyamide 6 [terminal NH_2 /terminal $\text{COOH} = 1/1$ (molar ratio)] and

 (ii) 3 parts by weight of a vulcanization-activating agent (N,N'-1,3-phenylenedimaleimide)

20 Resin composition (M2):

 (i) 100 parts by weight of a polyamide 6 [terminal NH_2 /terminal $\text{COOH} = 1/4$ (molar ratio)] and

 (ii) 3 parts by weight of a vulcanization-activating agent (N,N'-1,3-phenylenedimaleimide)

25 Resin compositions N1 to N2

 The following resin compositions (N1 to N2) were prepared by use of a polycondensation product of

- 76 -

dodecanedicarboxylic acid and bis(4-aminocyclohexyl) methane (the above mentioned alicyclic polyamide A6) as a thermoplastic resin.

Resin composition (N1):

- 5 (i) 100 parts by weight of an alicyclic polyamide A6 [terminal NH_2 /terminal COOH = 1/1 (molar ratio)] and
- (ii) 3 parts by weight of a vulcanization-activating agent (triallyl isocyanurate)

Resin composition (N2):

- 10 (i) 100 parts by weight of an alicyclic polyamide A6 [terminal NH_2 /terminal COOH = 1/2 (molar ratio)] and
- (ii) 5 parts by weight of a vulcanization-activating agent (triallyl isocyanurate)

Resin compositions O1 to O2

15 Resin composition (O1):

- (i) 100 parts by weight of a PBT [terminal OH /terminal COOH = 1/1 (molar ratio)] and
- (ii) 3 parts by weight of a vulcanization-activating agent (trimethylolpropane trimethacrylate)

20 Resin composition (O2):

- (i) 100 parts by weight of an amine-denatured or modified PBT [terminal NH_2 /terminal COOH = 1/1 (molar ratio)] and
- (ii) 3 parts by weight of a vulcanization-activating agent (trimethylolpropane trimethacrylate)
- 25

[Unvulcanized rubber composition (R)]

The following components was mixed or compounded in

- 77 -

order to prepare unvalcanized rubber compositions (R1 to R10).

Rubber composition R1

(i) 100 parts by weight of a rubber [90 parts by weight
5 of an ethylene-propylene-diene rubber (manufactured by DSM
Co. Ltd., Keltan 509X100, diene content: 8.2 % by weight)
and 10 parts by weight of a polyoctenylene rubber
(manufactured by Degussa Co. Ltd., Vestenamer 8012)]

(ii) 1 part by weight of a filler [carbon black (FEF)]

10 (iii) 5 parts by weight of a radical-generating agent
[organic peroxide (dicumyl peroxide)]

(iv) 0 part by weight of a vulcanization-activating
agent

(v) 100 parts by weight of a plasticizer
15 (manufactured by Idemitsu Kosan Co. Ltd., Diana process
oil NM-68)

(vi) 5 parts by weight of zinc oxide and

(vii) 1 part by weight of stearic acid

Rubber composition R2

20 (i) 100 parts by weight of a rubber [90 parts by weight
of an ethylene-propylene-diene rubber (manufactured by DSM
Co. Ltd., Keltan 509X100, diene content: 8.2 % by weight)
and 10 parts by weight of a polyoctenylene rubber
(manufactured by Degussa Co. Ltd., Vestenamer 8012)]

25 (ii) 1 part by weight of a filler [carbon black (FEF)]

(iii) 5 parts by weight of a radical-generating agent
[organic peroxide (dicumyl peroxide)]

- 78 -

(iv) 1 part by weight of a vulcanization-activating agent (trimethylolpropane trimethacrylate)

(v) 100 parts by weight of a plasticizer
(manufactured by Idemitsu Kosan Co. Ltd., Diana process
5 oil NM-68)

(vi) 5 parts by weight of zinc oxide and

(vii) 1 part by weight of stearic acid

Rubber composition R3

(i) 100 parts by weight of a rubber [90 parts by weight
10 of an ethylene-propylene-diene rubber (manufactured by DSM
Co. Ltd., Keltan 509X100, diene content: 8.2 % by weight)
and 10 parts by weight of a polyoctenylene rubber
(manufactured by Degussa Co. Ltd., Vestenamer 8012)]

(ii) 1 part by weight of a filler [carbon black (FEF)]

15 (iii) 5 parts by weight of a radical-generating agent
[organic peroxide (dicumyl peroxide)]

(iv) 2 parts by weight of a vulcanization-activating agent (butanediol dimethacrylate)

(v) 100 parts by weight of a plasticizer
20 (manufactured by Idemitsu Kosan Co. Ltd., Diana process
oil NM-68)

(vi) 5 parts by weight of zinc oxide and

(vii) 1 part by weight of stearic acid

Rubber composition R4

25 (i) 100 parts by weight of a rubber [90 parts by weight
of an ethylene-propylene-diene rubber (manufactured by DSM
Co. Ltd., Keltan 509X100, diene content: 8.2 % by weight)

and 10 parts by weight of a polyoctenylene rubber
(manufactured by Degussa Co. Ltd., Vestenamer 8012)]

(ii) 1 part by weight of a filler [carbon black (FEF)]

(iii) 3 parts by weight of a radical-generating agent
5 (tetramethylthiuram disulfide)

(iv) 1 part by weight of a vulcanization-activating
agent (trimethylolpropane trimethacrylate)

(v) 100 parts by weight of a plasticizer
(manufactured by Idemitsu Kosan Co. Ltd., Diana process
10 oil NM-68)

(vi) 5 parts by weight of zinc oxide and

(vii) 1 part by weight of stearic acid

Rubber composition R5

(i) 100 parts by weight of a rubber [60 parts by weight
15 of natural rubber, 35 parts by weight of ethylene-
propylene-diene rubber (manufactured by DSM Co. Ltd.,
Keltan 509X100, diene content: 8.2 % by weight), and 5 parts
by weight of polyoctenylene rubber (manufactured by
Degussa Co. Ltd., Vestenamer 8012)]

20 (ii) 1 part by weight of a filler [carbon black (FEF)]

(iii) 5 parts by weight of a radical-generating agent
[organic peroxide (dicumyl peroxide)]

(iv) 0 part by weight of a vulcanization-activating
agent

25 (v) 100 parts by weight of a plasticizer
(manufactured by Idemitsu Kosan Co. Ltd., Diana process
oil NM-68)

- 80 -

(vi) 5 parts by weight of zinc oxide and

(vii) 1 part by weight of stearic acid

Rubber composition R6

(i) 100 parts by weight of a rubber [60 parts by weight
5 of natural rubber, 35 parts by weight of ethylene-
propylene-diene rubber (manufactured by DSM Co. Ltd.,
Keltan 509X100, diene content : 8.2 % by weight), and 5
parts by weight of polyoctenylene rubber (manufactured by
Degussa Co. Ltd., Vestenamer 8012)]

10 (ii) 1 part by weight of a filler [carbon black (FEF)]

(iii) 5 parts by weight of a radical-generating agent
[organic peroxide (dicumyl peroxide)]

(iv) 1 part by weight of a vulcanization-activating
agent (trimethylolpropane trimethacrylate)

15 (v) a plasticizer (manufactured by Idemitsu Kosan
Co. Ltd., Diana process oil NM-68) of 100 parts by weight

(vi) zinc oxide of 5 parts by weight

(vii) stearic acid of 1 part by weight

Rubber composition R7

20 (i) 100 parts by weight of a hydrogenated nitrile
rubber (HNBR) ("Zetpol 3110" manufactured by Nihon Zeon
Co.Ltd.)

(ii) 50 parts by weight of a filler [carbon black
(N550)]

25 (iii) 3 parts by weight of a radical-generating agent
[1,3-bis(t-butylperoxyisopropyl)benzene]

(iv) 0 part by weight of a vulcanization-activating

agent

(v) 10 parts by weight of a plasticizer
(dibutylmethylene bithioglycolate)

(vi) 0 part by weight of zinc oxide and

5 (vii) 0 part by weight of stearic acid

Rubber composition R8

(i) 100 parts by weight of a hydrogenated nitrile
rubber (HNBR) ("Zetpol 3110" manufactured by Nihon Zeon
Co.Ltd.)

10 (ii) 50 parts by weight of a filler [carbon black
(N550)]

(iii) 3 parts by weight of a radical-generating agent
[1,3-bis(t-butylperoxyisopropyl)benzene]

(iv) 4 parts by weight of a vulcanization-activating
15 agent (N,N'-1,3-phenylenedimaleimide)

(v) 10 parts by weight of a plasticizer
(dibutylmethylene bithioglycolate)

(vi) 0 part by weight of zinc oxide and

(vii) 0 part by weight of stearic acid

20 Rubber composition R9

(i) 100 parts by weight of a fluorine-containing
rubber (FPM) ("Dai El G920" manufactured by Dikin Kogyo
Co.Ltd.)

(ii) 0 part by weight of a filler

25 (iii) 3 parts by weight of a radical-generating agent
(dicumyl peroxide)

(iv) 0 part by weight of a vulcanization-activating

agent

(v) 0 part by weight of a plasticizer (manufactured by Idemitsu Kosan Co. Ltd., Diana process oil NM-68)

(vi) 0 part by weight of zinc oxide and

5 (vii) 0 part by weight of stearic acid

Rubber composition R10

(i) 100 parts by weight of a fluorine-containing rubber (FPM) ("Dai El G920" manufactured by Dikin Kogyo Co.Ltd.)

10 (ii) 0 part by weight of a filler

(iii) 3 parts by weight of a radical-generating agent (dicumyl peroxide)

(iv) 4 parts by weight of a vulcanization-activating agent (triallyl isocyanurate)

15 (v) 0 part by weight of a plasticizer (manufactured by Idemitsu Kosan Co. Ltd., Diana process oil NM-68)

(vi) 0 part by weight of a zinc oxide and

(vii) 0 part by weight of a stearic acid

Examples 1 to 147 and Comparative examples 1 to 77

20 The resin composition was injected and molded, and the obtained resin member (plate, size: 100mm X 100mm X 4mm) was arranged in a mold. Subsequently, the unvulcanized rubber composition was injected to the surface of the resin member, and vulcanization or
25 crosslinking was conducted at a temperature of 180°C under a pressure of 20 MPa for 20 minutes to produce a composite.

The obtained composite was subjected to a peeling

- 83 -

or adhesion test in order to measure a adhesive strength between the resin member and a rubber member, and was evaluated according to the following criteria.

A : Remarkably film adhesion was achieved, and when
5 the resin member was peeled from the rubber member forcibly,
the specimen was broken with a cohesive failure.

B : Firm adhesion was achieved, and when the resin
member was peeled from the rubber member forcibly, the resin
member was peeled from the rubber member along the
10 interface.

C : The rubber member was easily separated from the
resin member along the interface.

The results are set forth in Tables 1 to 10. In the
Tables, the term "the number of active atom per molecule"
15 represents the number of an active atom having S of not
less than 0.006 per molecule, which is calculated by
MOPACPM3, of the thermoplastic resin. Incidentally, on
the above calculation, Ec value was used -8 eV for a
radical-generating agent comprising an organic peroxide,
20 or -6 eV for a radical-generating agent comprising
tetramethylthiuram disulfide.

- 84 -

Table 1

Rubber composition R1			
	thermoplastic resin composition	number of active atom per molecule	adhesive strength
Example 1	A1	7.2	A
Example 2	A2	7.2	A
Example 3	A3	7.2	A
Example 4	A4	4	A
Example 5	A5	2.4	B
Comparative example 1	A6	0.8	C
Example 6	B1	2	B
Comparative example 2	B2	1	C
Example 7	C1	7.2	A
Example 8	C2	2	B
Comparative example 3	C3	1.6	C
Example 9	D1	4	B
Example 10	D2	2	B
Comparative example 4	D3	1.6	C
Example 11	E1	5 or more	B
Example 12	E2	4 or more	B
Example 13	E3	3.8 or more	B
Example 14	F1	3	A
Example 15	F2	2	B
Comparative example 5	F3	1.2	C
Comparative example 6	G1	0	C
Example 16	G2	4	A
Example 17	H	6 or more	B
Example 18	I	9 or more	B
Example 19	J	6 or more	B
Example 20	K	2 or more	B
Example 21	L1	4	A
Comparative example 7	L2	0.8	C
Example 22	M1	7.2	A
Comparative example 8	M2	1.6	C
Example 23	N1	3	B
Comparative example 9	O1	0	C
Example 24	O2	4	A

Table 2

Rubber composition R2			
	thermoplastic resin composition	number of active atom per molecule	adhesive strength
Example 25	A1	7.2	A
Example 26	A2	7.2	A
Example 27	A3	7.2	A
Example 28	A4	4	A
Example 29	A5	2.4	A
Comparative example 10	A6	0.8	C
Example 30	B1	2	A
Comparative example 11	B2	1	C
Example 31	C1	7.2	A
Example 32	C2	2	A
Comparative example 12	C3	1.6	C
Example 33	D1	4	B
Example 34	D2	2	B
Comparative example 13	D3	1.6	C
Example 35	E1	5 or more	A
Example 36	E2	4 or more	B
Example 37	E3	3.8 or more	B
Example 38	F1	3	A
Example 39	F2	2	A
Comparative example 14	F3	1.2	C
Comparative example 15	G1	0	C
Example 40	G2	4	A
Example 41	H	6 or more	A
Example 42	I	9 or more	B
Example 43	J	6 or more	B
Example 44	K	2 or more	B
Example 45	L1	4	A
Comparative example 16	L2	0.8	C
Example 46	N1	3	A
Comparative example 17	N2	1.2	C

- 86 -

Table 3

Rubber composition R3			
	thermoplastic resin composition	number of active atom per molecule	adhesive strength
Example 47	A1	7.2	A
Example 48	A2	7.2	A
Example 49	A3	7.2	A
Example 50	A4	4	A
Example 51	A5	2.4	A
Comparative example 18	A6	0.8	C
Example 52	B1	2	B
Comparative example 19	B2	1	C
Example 53	C1	7.2	A
Example 54	C2	2	B
Comparative example 20	C3	1.6	C
Example 55	D1	4	B
Example 56	D2	2	B
Comparative example 21	D3	1.6	C
Example 57	E1	5 or more	A
Example 58	E2	4 or more	B
Example 59	E3	3.8 or more	B
Example 60	F1	3	A
Example 61	F2	2	B
Comparative example 22	F3	1.2	C
Comparative example 23	G1	0	C
Example 62	G2	4	A
Example 63	H	6 or more	B
Example 64	I	9 or more	B
Example 65	J	6 or more	B
Example 66	K	2 or more	B

- 87 -

Table 4

Rubber composition R4			
	thermoplastic resin composition	number of active atom per molecule	adhesive strength
Comparative example 24	A1	0	C
Comparative example 25	A2	0	C
Comparative example 26	A3	0	C
Comparative example 27	A4	0	C
Comparative example 28	A5	0	C
Comparative example 29	A6	0	C
Comparative example 30	B1	0	C
Comparative example 31	B2	0	C
Example 67	C1	2	B
Comparative example 32	C2	1	C
Comparative example 33	C3	0.8	C
Example 68	D1	4	B
Example 69	D2	2	B
Comparative example 34	D3	1.6	C
Comparative example 35	E1	0	C
Comparative example 36	E2	0	C
Comparative example 37	E3	0	C
Comparative example 38	F1	1	C
Comparative example 39	F2	0.7	C
Comparative example 40	F3	0.4	C
Comparative example 41	G1	0	C
Example 70	G2	2	B
Comparative example 42	H	0	C
Example 71	I	3 or more	B
Example 72	J	4 or more	B
Example 73	K	2 or more	B

- 88 -

Table 5

Rubber composition R5			
	thermoplastic resin composition	number of active atom per molecule	adhesive strength
Example 74	A5	2.4	B
Comparative example 43	A6	0.8	C
Example 75	F2	2	B
Comparative example 44	F3	1.2	C
Example 76	L1	4	A
Comparative example 45	L2	0.8	C
Example 77	M1	7.2	B
Comparative example 46	M2	1.6	C
Example 78	N1	3	B
Comparative example 47	N2	1.2	C
Comparative example 48	O1	0	C
Example 79	O2	4	A

Table 6

Rubber composition R6			
	thermoplastic resin composition	number of active atom per molecule	adhesive strength
Example 80	A1	7.2	A
Example 81	A2	7.2	A
Example 82	A3	7.2	A
Example 83	A4	4	A
Example 84	A5	2.4	A
Comparative example 49	A6	0.8	C
Example 85	B1	2	B
Comparative example 50	B2	1	C
Example 86	C1	7.2	A
Example 87	C2	2	B
Comparative example 51	C3	1.6	C
Example 88	D1	4	B
Example 89	D2	2	B
Comparative example 52	D3	1.6	C
Example 90	E1	5 or more	B
Example 91	E2	4 or more	B
Example 92	E3	3.8 or more	B
Example 93	F1	3	A
Example 94	F2	2	B
Comparative example 53	F3	1.2	C
Comparative example 54	G1	0	C
Example 95	G2	4	B
Example 96	H	6 or more	B
Example 97	I	9 or more	B
Example 98	J	6 or more	B
Example 99	K	2 or more	B
Example 100	L1	4	A
Example 101	N1	3	A
Comparative example 55	N2	1.2	C

- 90 -

Table 7

Rubber composition R7			
	thermoplastic resin composition	number of active atom per molecule	adhesive strength
Example 102	A5	2.4	B
Comparative example 56	A6	0.8	C
Example 103	F2	2	B
Comparative example 57	F3	1.2	C
Example 104	L1	4	A
Comparative example 58	L2	0.8	C
Example 105	N1	3	A
Comparative example 59	N2	1.2	C

Table 8

Rubber composition R8			
	thermoplastic resin composition	number of active atom per molecule	adhesive strength
Example 106	A1	7.2	A
Example 107	A4	4	A
Example 108	A5	2.4	A
Comparative example 60	A6	0.8	C
Example 109	B1	2	B
Comparative example 61	B2	1	C
Example 110	C1	7.2	A
Example 111	C2	2	B
Comparative example 62	C3	1.6	C
Example 112	E1	5 or more	A
Example 113	E2	4 or more	B
Example 114	E3	3.8 or more	B
Example 115	F1	3	B
Example 116	F2	2	B
Comparative example 63	F3	1.2	C
Comparative example 64	G1	0	C
Example 117	G2	4	A
Example 118	H	6 or more	A
Example 119	I	9 or more	B
Example 120	J	6 or more	B
Example 121	K	2 or more	B
Example 122	L1	4	A
Comparative example 65	L2	0.8	C
Example 123	N1	3	A
Comparative example 66	N2	1.2	C

- 91 -

Table 9

Rubber composition R9			
	thermoplastic resin composition	number of active atom per molecule	adhesive strength
Example 124	A5	2.4	B
Comparative example 67	A6	0.8	C
Example 125	F2	2	B
Comparative example 68	F3	1.2	C
Example 126	L1	4	A
Comparative example 69	L2	0.8	C
Example 127	M1	7.2	A
Comparative example 70	M2	1.6	C
Example 128	N1	3	A
Comparative example 71	N2	1.2	C
Comparative example 72	O1	0	C
Example 129	O2	4	A

Table 10

Rubber composition R10			
	thermoplastic resin composition	number of active atom per molecule	adhesive strength
Example 130	A1	7.2	A
Example 131	A4	4	B
Example 132	A5	2.4	B
Comparative example 73	A6	0.8	C
Example 133	B1	2	B
Comparative example 74	B2	1	C
Example 134	C1	7.2	B
Example 135	C2	2	B
Comparative example 75	C3	1.6	C
Example 136	E1	5 or more	B
Example 137	E2	5 or more	B
Example 138	E3	3.8 or more	B
Example 139	F1	3	A
Example 140	F2	2	B
Comparative example 76	F3	1.2	C
Comparative example 77	G1	0	C
Example 141	G2	4	B
Example 142	H	6 or more	A
Example 143	I	9 or more	B
Example 144	J	6 or more	B
Example 145	K	2 or more	B
Example 146	L1	4	A
Example 147	N1	3	A

- 92 -

As shown in Tables 1 to 10, since resins having the number of an active atom of not less than 2 were used in examples, a firmly bonding between the resin and the rubber can be effected regardless of species of rubbers.

5 Example 148

An adhesive effect of a solvent treatment was examined in the combination of Rubber composition R1/Resin composition A5 (PA612) having an adhesive strength level "B". That is, a paper ("Kimwipe wiper S-200" manufactured
10 by Cresia, Co. Ltd.) was folded 3 times in a cross or lateral direction and once in a longitudinal direction, and a tip of the folded paper was dipped in a solvent (hexafluoroisopropanol). A bonding surface of a test piece of a resin A5 (PA612) (plate, size: 100mm X 100mm
15 X 4mm) was slightly wiped with the dipped paper. It was confirmed visually that the surface of the test piece was completely wetted with solvent, and as a result it was evaluated that the surface was wiped down or cleaned. After cleaning the surface, the test piece was allowed to
20 stand for 5 minutes, and washed with water, and subsequently dried at 100°C for 5 hours in the vacuum dryer to be subjected to an adhesion test. In the same manner as in Example 1, a composite was produced with use of the test piece and an unvulcanized rubber composition. The obtained
25 composite was subjected to an adhesion test in order to evaluate an adhesive strength between the resin member and the rubber member, and the adhesive strength of the

- 93 -

composite was improved to a level "A".

Example 149

A composite was produced in the same manner as in Example 148 except for using a methacresol instead of
5 hexafluoroisopropanol. The obtained composite was subjected to an adhesion test in order to measure an adhesive strength between the resin member and the rubber member, and the adhesive strength of the composite was improved to a level "A".

10 Example 150

In a composite of Rubber composition R1/Resin composition H (m-PPE) having the adhesive strength level "B", the procedure was repeated in the same manner as in Example 148 except for wiping a bonding surface of the test
15 piece of the Resin composition H (m-PPE) (plate, size: 100mm X 100mm X 4mm) with a methacresol-impregnated paper to give a composite. The obtained composite was subjected to an adhesion test in order to measure an adhesive strength between the resin member and the rubber member, and the
20 adhesive strength of the composite was enhanced to be a level "A".

- 94 -

CLAIMS

1. A composite comprising a vulcanized rubber member formed by a vulcanization of a non-silicone-series unvulcanized rubber, and a resin member comprising a thermoplastic resin and directly bonded to the rubber member, which is produced by molding a resin molding element and a rubber molding element comprising at least an unvulcanized rubber and a radical-generating agent being active on a surface with contacting said elements each other, and vulcanizing or crosslinking the rubber molding member,

wherein the composite comprises a combination of a rubber member vulcanized with a radical-generating agent and a resin member comprising a thermoplastic resin having at least 2 atoms, on average, selected from a hydrogen atom and a sulfur atom per molecule, and each atom has an orbital interaction energy coefficient S of not less than 0.006,

and the orbital interaction energy coefficient S is represented by the following formula (1):

$$S = (C_{\text{HOMO},n})^2 / |E_c - E_{\text{HOMO},n}| + (C_{\text{LUMO},n})^2 / |E_c - E_{\text{LUMO},n}| \quad (1)$$

wherein each of E_c , $C_{\text{HOMO},n}$, $E_{\text{HOMO},n}$, $C_{\text{LUMO},n}$, and $E_{\text{LUMO},n}$ represents a value calculated by a semiempirical molecular orbital method MOPACPM3, E_c representing an orbital energy (eV) of a radical of the radical-generating agent, $C_{\text{HOMO},n}$ representing a molecular-orbital coefficient of a highest occupied molecular orbital (HOMO) of an n -th

hydrogen or sulfur atom constituting a constitutive unit of the thermoplastic resin, $E_{HOMO,n}$ representing an orbital energy (eV) of the HOMO, $C_{LUMO,n}$ representing a molecular-orbital coefficient of a lowest unoccupied molecular orbital (LUMO) of the n-th hydrogen or sulfur atom constituting the constitutive unit of the thermoplastic resin, and $E_{LUMO,n}$ representing an orbital energy (eV) of the LUMO; provided that said combination excludes the following combinations (1) to (3);

(1) a combination of an aliphatic polyamide-series resin having an amino group and an unvulcanized rubber having a carboxyl group or an acid anhydride group,

(2) a combination of an aliphatic polyamide-series resin and an unvulcanized rubber comprising a silane compound, and

(3) a combination of an epoxy group-containing resin and an unvulcanized rubber having a carboxyl group or an acid anhydride group; and

provided that said combination includes the following cases (4) and (5):

(4) when the thermoplastic resin comprises a polyamide-series resin, an unvulcanized rubber comprises a polyfunctional vulcanization-activating agent, and

(5) when the thermoplastic resin comprises a polyphenylene ether-series resin, an unvulcanized rubber comprises a vulcanization-activating agent.

2. A composite according to Claim 1, wherein the thermoplastic resin comprises at least one member selected from the group consisting

of a polyamide-series resin, a polyester-series resin, a polyether-series resin, a polyolefinic resin, a polyurethane-series resin, and a thermoplastic elastomer.

3. A composite according to Claim 1, wherein the thermoplastic resin comprises at least one member selected from the group consisting of an aliphatic polyamide-series resin, an aromatic polyester-series resin, a polyacetal-series resin, a polyphenylene ether-series resin, a polysulfide-series resin, a polyolefinic resin, a polyurethane-series resin, a polyamide-series elastomer, a polyester-series elastomer, a polyurethane-series elastomer, a polystyrenic elastomer, and a polyolefinic elastomer.

4. A composite according to Claim 1, wherein the rubber comprises at least one member selected from the group consisting of a diene-series rubber, an olefinic rubber, an acrylic rubber, a fluorine-containing rubber, and a urethane-series rubber.

5. A composite according to Claim 1, wherein the radical-generating agent comprises at least one member selected from the group consisting of an organic peroxide, an azo compound, and a sulfur-containing organic compound.

6. A composite according to Claim 1, wherein the radical-generating agent comprises an organic peroxide.

7. A composite according to Claim 1, wherein the amount of the radical-generating agent is 1 to 10 parts by weight relative to 100 parts by weight of the unvulcanized rubber.

8. A composite according to Claim 1, wherein at least one component selected from the unvulcanized rubber and the thermoplastic

resin comprises a vulcanization-activating agent.

9. A composite according to Claim 8, wherein the vulcanization-activating agent comprises an organic compound having at least two polymerizable-unsaturated bonds per molecule.

10. A composite according to Claim 8, wherein the amount of the vulcanization-activating agent is 0.1 to 10 parts by weight relative to 100 parts by weight of at least one component selected from the unvulcanized rubber and the thermoplastic resin.

11. A composite according to Claim 8, wherein the amount of the vulcanization-activating agent is not more than 2 parts by weight relative to 100 parts by weight of the unvulcanized rubber.

12. A composite according to Claim 1, wherein the thermoplastic resin comprises a vulcanizing auxiliary comprising a compound having at least 2 hydrogen atoms on average per molecule, and said hydrogen atoms each has an orbital interaction energy coefficient S recited in Claim 1 of not less than 0.006.

13. A composite according to Claim 12, wherein the amount of the vulcanizing auxiliary is 0.1 to 30 parts by weight relative to 100 parts by weight of the thermoplastic resin.

14. A composite according to Claim 1, wherein said combination is any of the following combinations:

(a) a combination of a polyamide-series resin and an unvulcanized rubber unmodified with a carboxyl group or an acid anhydride group;

(b) a combination of a polyamide-series resin and an unvulcanized rubber comprising an organic peroxide, a polyfunctional

- 98 -

vulcanization-activating agent and excluding an alkoxy silane compound;

(c) a combination of an aromatic polyester-series resin having at least one group selected from the group consisting of an amino group and an oxyalkylene group, and an unvulcanized rubber comprising an organic peroxide;

(d) a combination of a polyacetal-series resin and an unvulcanized rubber comprising an organic peroxide;

(e) a combination of a polyphenylene ether-series resin and an unvulcanized rubber comprising an organic peroxide and a vulcanization-activating agent;

(f) a combination of a polysulfide-series resin and an unvulcanized rubber comprising an organic peroxide;

(g) a combination of a polypropylene-series resin and an unvulcanized rubber comprising an organic peroxide;

(h) a combination of a polyurethane-series resin and an unvulcanized rubber comprising an organic peroxide; and

(i) a combination of a thermoplastic elastomer and an unvulcanized rubber comprising an organic peroxide.

15. A process for producing a composite of a resin member bonded to a rubber member comprising a vulcanized rubber with use of a combination of a thermoplastic resin recited in Claim 1 with an unvulcanized rubber comprising a radical-generating agent, which comprises molding a resin molding element and a rubber molding element with contacting said elements each other, and vulcanizing or crosslinking the rubber molding element,

- 99 -

wherein said resin molding element is either of a resin composition and a resin member, each comprising the thermoplastic resin, and

said rubber molding element is either of a rubber composition and a rubber premolded article, each comprising at least an unvulcanized rubber and a radical-generating agent being active on a surface to be contacted with said resin molding element.

16. A process according to Claim 15, wherein the vulcanization-activating agent is incorporated into at least one component selected from the unvulcanized rubber and the thermoplastic resin.

17. A process according to Claim 15, wherein the thermoplastic resin comprises a vulcanizing auxiliary having at least 2 hydrogen atoms on average per molecule, said hydrogen atom has an orbital interaction energy coefficient S recited in Claim 1 of not less than 0.006.

18. A process according to Claim 15, which comprises heat-molding the resin molding element and the rubber molding element with interposing a vulcanization-activating agent on an interface between the resin molding element and the rubber molding element to produce a composite comprising the resin member and the rubber member bonded to the resin member.

19. A process according to Claim 15, which comprises heat-molding the resin molding element and the rubber molding element with interposing a coating agent on an interface between the resin molding element and the rubber molding element, wherein the

coating agent comprises a vulcanization-activating agent and a vulcanization auxiliary having at least 2 hydrogen atoms on average per molecule, said hydrogen atoms each has the orbital interaction energy coefficient S recited in Claim 1 of not less than 0.006.

20. A process for producing a composite comprising a resin member comprising a thermoplastic resin recited in Claim 1 and a vulcanized rubber member bonded to the resin member, which comprises heat-molding the resin member and the vulcanized rubber member with interposing a vulcanization-activating agent on an interface between the resin member and the vulcanized rubber member.

21. A process for producing a composite comprising a resin member comprising a thermoplastic resin recited in Claim 1 and a vulcanized rubber member bonded to the resin member, which comprises heat-molding the resin member and the vulcanized rubber member with interposing a coating agent on an interface between the resin member and the vulcanized rubber member,

wherein the coating agent comprises a vulcanization-activating agent and a vulcanization auxiliary having at least 2 hydrogen atoms on average per molecule, said hydrogen atoms each has an orbital interaction energy coefficient S recited in Claim 1 of not less than 0.006.

22. A process for producing a composite comprising a resin member comprising a thermoplastic resin recited in Claim 1 and a rubber member comprising a vulcanized rubber by use of a combination of the thermoplastic resin and an unvulcanized rubber composition comprising

- 101 -

a radical-generating agent, which comprises treating a surface of the resin member with a solvent capable of dissolving or swelling the resin member, and contacting the treated surface with the unvulcanized rubber composition.