

DESCRIPTION

Title of Invention: RESIN PLATING METHOD

Technical Field

5 [0001]

The present invention relates to a resin plating method.

Background Art

[0002]

10 In recent years, molded resin articles have been used as automobile components to reduce automobile weight, etc. To achieve this object, resins such as ABS resins, PC/ABS resins, PPE resins, and polyamide resins have been used. Molded resin articles are often plated with copper, nickel, or the like to provide a high-quality impression and beautiful appearance.

15 Further, a method of plating a resin substrate with copper or the like is also used as a method for forming a conductor circuit by imparting conductivity to a resin substrate.

[0003]

20 A common method for plating a resin material, such as a resin substrate or a molded resin article, comprises the steps of degreasing and etching, optionally followed by neutralization and predipping; and then applying an electroless plating catalyst using a colloidal solution containing a tin compound and a palladium compound, optionally followed by activation (treatment with an accelerator), to perform electroless plating and
25 electroplating sequentially.

[0004]

30 In this case, a chromic acid mixture comprising a mixed solution of chromium trioxide and sulfuric acid has been widely used as an etching treatment solution. However, chromic acid mixtures, which contain toxic hexavalent chromium, adversely affect work environments. Furthermore, safe disposal of the liquid waste requires reduction of the hexavalent chromium to a trivalent chromium ion, followed by neutralization and
35 precipitation, thus requiring complicated treatment for the

disposal of the liquid waste. Therefore, in consideration of workplace safety during the treatment and adverse effects of the liquid waste on the environment, avoiding the use of chromic acid-containing etching solutions is preferable.

5 [0005]

Etching baths containing manganese as an active ingredient are known as etching solutions that can be used in place of chromic acid mixtures. For example, Patent Literature (PTL) 1 listed below discloses an acidic etching bath containing permanganate. Patent Literature 1 teaches that various inorganic and organic acids can be used for adjusting the pH of the etching bath, and that sulfuric acid was used to adjust the pH to 1 or less in the Examples. Patent Literature (PTL) 2 listed below also discloses an etching treatment solution containing permanganate and inorganic acid. Non-patent Literature (NPL) 1 listed below discloses an acidic etching treatment agent using manganese(IV) oxide.

Citation List

Patent Literature

20 [0006]

PTL 1: JP2009-228083A

PTL 2: JP2008-31513A

Non-patent Literature (NPL)

[0007]

25 Non-patent Literature (NPL) 1: Journal of the Chinese Chemical Society, 2009, 56, 1225-1230

Summary of Invention

Technical Problem

[0008]

30 The above-described acidic etching baths containing manganese, which do not contain toxic hexavalent chromium, are advantageous etching solutions in terms of work environment or environmental impact. However, acidic etching baths containing manganese are disadvantageous in that etching power is
35 significantly reduced during continuous use. This is one factor

that inhibits the practical application of an acidic etching bath containing manganese. Accordingly, in resin plating methods using an etching bath containing manganese as an active ingredient, a method capable of maintaining stable etching performance even
5 during continuous use has been desired.

Solution to Problem

[0009]

The present inventors conducted extensive research to
10 achieve the above object. As a result, the inventors found that when a plating treatment is performed by a process comprising an etching step in which a resin material, such as a molded resin article, is used as an object to be treated and is subjected to etching, followed by a catalyst application step and an
15 electroless plating step, palladium used as catalyst metal in the etching bath is gradually accumulated during a long-term continuous plating treatment by repeating the above steps. The inventors further discovered an unexpected phenomenon; specifically, when an etching treatment is performed using an
20 acidic etching bath containing manganese as an active ingredient, etching performance is significantly reduced with an increase of palladium concentration in the bath. As a result, the inventors found that when the palladium concentration in the etching bath is controlled at a specific concentration or lower, good etching
25 performance can be maintained over a long period of time. The present invention has been accomplished based on this finding.

[0010]

More specifically, the present invention provides the following resin plating methods and methods for controlling the
30 resin plating etching bath.

Item 1. A resin plating method comprising an etching step in which an article comprising a resin material is used as an object to be treated and is subjected to etching using an acidic etching bath containing manganese; a catalyst application step using
35 palladium as a catalyst metal; and an electroless plating step,

the method further comprising a step of maintaining the palladium concentration in the acidic etching bath at 100 mg/L or less.

Item 2. The resin plating method according to Item 1, wherein the step of maintaining the palladium concentration in the acidic

5 etching bath at 100 mg/L or less is performed by one or more methods selected from the group consisting of: a method for removing palladium adsorbed on a jig; a method for reducing the palladium concentration in an etching bath by cathodic electrolysis; and a method for reducing the palladium
10 concentration by iodide addition to an etching bath.

Item 3. The resin plating method according to Item 2, wherein the method for removing palladium adsorbed on a jig is a method of immersing a jig in a palladium-removing treatment solution comprising an aqueous solution containing at least one compound
15 selected from the group consisting of nitric acid, persulfates, hydrogen peroxide, and compounds having a stability constant with palladium of 2.0 or more.

Item 4. The resin plating method according to Item 2, wherein the method for reducing the palladium concentration in an etching
20 bath by cathodic electrolysis is a method of depositing palladium in an etching bath on a cathode as metallic palladium by electrolytic treatment.

Item 5. The resin plating method according to Item 2, wherein the method for reducing the palladium concentration by iodide
25 addition to an etching bath is a method comprising adding to an etching bath at least one iodide selected from the group consisting of sodium iodide, potassium iodide, iodic acid, iodates, periodic acid, and periodates, and separating the formed precipitate.

30 Item 6. A method for controlling a resin plating etching bath, comprising maintaining the palladium concentration in a manganese-containing acidic etching bath at 100 mg/L or less.

[0011]

Hereinafter, the resin plating method of the present
35 invention is specifically explained.

[0012]

Resin plating method

The resin plating method of the present invention comprises: an etching step in which an article comprising a resin material is used as an object to be treated and is subjected to an etching treatment using an acidic etching bath containing manganese; a catalyst application step using palladium as a catalyst metal; and an electroless plating step. This method is described below in detail. Washing with water is usually performed between each treatment step.

[0013]

(1) Object to be treated

The object to be treated by the resin plating method of the present invention is an article comprising a resin material as a component. For example, molded articles comprising a resin material; and articles, such as printed circuit boards, including a portion comprising a resin material, can be used as objects to be treated.

[0014]

The kind of resin material used as an object to be treated is not particularly limited. In particular, a good electroless plating film can be formed on various resin materials that have been etched using a chromic acid-sulfuric acid mixture. For example, the following resin materials can be used as objects to be treated to form a good electroless plating film: styrene-based resins such as acrylonitrile-butadiene-styrene copolymer resins (ABS resins); resins (AAS resins) having an acrylic rubber component in place of a butadiene rubber component of ABS resin; and resins (AES resins) having an ethylene-propylene rubber component or the like in place of a butadiene rubber component of ABS resin. Examples of resin materials preferably used further include alloy resins of the styrene-based resins mentioned above and polycarbonate (PC) resins (for example, alloy resins containing a PC resin in a proportion of about 30 to about 70 wt.%). It is also possible to use polyphenylene ether resins,

polyphenylene oxide resins, and like resins that have excellent heat resistance and physical properties.

[0015]

5 There is no specific limitation on the shape, size, etc., of the object to be treated. A good plating film with excellent appearance, physical properties, etc., can be formed even on large objects having a large surface area. Examples of such large resin products include automobile parts and accessories, such as radiator grills, hubcaps, medium or small
10 emblems, and door handles; exterior equipment used in the electrical or electronic field; faucet fittings used in places where water is supplied; game machine-related products, such as pachinko components; and the like.

[0016]

15 (2) Etching step

 The etching bath using the resin plating method of the present invention comprises an acidic aqueous solution containing manganese as an active ingredient.

[0017]

20 Manganese contained in the etching bath may be trivalent, tetravalent, or heptavalent. For example, manganese may be present in the etching bath in the form of manganese ions such as trivalent manganese ions or tetravalent manganese ions, or as heptavalent manganese in the form of permanganic acid ions.

25 [0018]

 The manganese concentration in the etching bath is not particularly limited. For example, the etching bath having a manganese concentration of about 0.01 to 100 g/L can be used for the treatment.

30 [0019]

 The etching bath comprises an acidic aqueous solution containing an acid component. Examples of acid components contained in the etching bath include inorganic acids, such as sulfuric acid, phosphoric acid, nitric acid, and hydrochloric
35 acid; organic sulfonic acids, such as methanesulfonic acid and

ethanesulfonic acid; and the like.

[0020]

The acid component concentration in the etching bath is not particularly limited, and may be, for example, about 100 to
5 1800 g/L.

[0021]

The etching bath may further contain various additives. Examples of such additives include surfactants. The kind of surfactant is not particularly limited as long as the surface
10 tension of the etching solution can be reduced. In particular, examples of surfactants relatively stable in an oxidizing atmosphere include anionic surfactants, such as alkylbenzenesulfonic acid, perfluorooctanoate, and perfluoroheptanoate.

15 [0022]

The etching conditions are not particularly limited, and can be suitably selected according to the type of etching bath used, kind of resin material to be treated, the desired degree of etching, etc. For example, etching may be performed by
20 immersing an object to be treated in an etching bath at an etching solution temperature of about 30 to 70°C for about 3 to 30 minutes.

[0023]

When the surface of the resin molded article, which is
25 an object to be treated, is extremely dirty, the surface may, if necessary, be degreased according to a usual method prior to etching.

[0024]

(3) Catalyst application step

30 After the resin material is etched by the above method, an electroless plating catalyst is applied.

[0025]

In the catalyst application step of the resin plating method of the present invention, a catalyst application solution
35 containing palladium is used as a catalyst metal. Examples of

representative methods for applying a palladium catalyst include the so-called sensitizing-activating method, catalyzing method, and the like.

[0026]

5 Among these methods, the sensitizing-activating method comprises sensitizing a substrate using an aqueous solution containing stannous chloride and hydrochloric acid, and then activating its surface by using an aqueous solution containing a palladium salt, such as palladium chloride.

10 [0027]

 The catalyzing method can be roughly classified into acid-catalyzing methods and alkali-catalyzing methods. The acid-catalyzing method comprises catalyzing a substrate with an acidic colloidal solution containing palladium chloride and stannous
15 chloride, and then activating its surface by using an aqueous sulfuric acid solution, an aqueous hydrochloric acid solution, or the like. The alkali-catalyzing method comprises catalyzing a substrate to be plated with an alkaline solution containing palladium chloride and an amine compound, and then reducing its
20 surface using dimethylamine borane or hypophosphite.

[0028]

 Specific treatment methods, treatment conditions, etc. of these methods may be according to known methods.

[0029]

25 If necessary, in order to remove manganese that has adhered to the surface of the object to be treated as a result of etching, post-etching treatment may be performed using an inorganic acid, such as sulfuric acid or hydrochloric acid, or a reducing agent, such as erythorbic acid or hydrogen peroxide,
30 prior to the catalyst application step.

[0030]

(4) Plating step

 After a catalyst is applied by the above method, electroless plating treatment is performed. The electroless
35 plating solution may be any known autocatalytic electroless

plating solution. Examples of such electroless plating solutions include electroless nickel plating solutions, electroless copper plating solutions, electroless cobalt plating solutions, electroless copper-nickel alloy plating solutions, electroless nickel-cobalt alloy plating solutions, electroless gold plating solutions, and the like.

[0031]

The electroless plating conditions may also be according to known methods. If necessary, two or more layers of electroless plating film may be formed.

[0032]

After the electroless plating, electroplating may be performed. In this case, after the electroless plating, an activation treatment may be optionally performed using an aqueous solution of an acid, alkali, or the like, after which electroplating may be performed. The kind of electroplating solution is not particularly limited. The electroplating solution can be suitably selected from known electroplating solutions according to the purpose.

[0033]

The resin plating method according to the present invention comprises the above-mentioned etching step, catalyst application step, and plating step. If necessary, the method may further comprise other various treatment steps. Examples of such treatment steps include a swelling treatment before etching (pre-etching), rack protection treatment for preventing the deposition on a jig, and like treatment steps.

[0034]

Step of maintaining the palladium concentration at 100 mg/L or less

According to the resin plating method of the present invention comprising an etching step using an acidic etching bath containing manganese, a catalyst application step using palladium as a catalyst metal, and an electroless plating step, when a plating treatment is continuously performed by repeating these

steps, it is necessary to maintain the palladium concentration in the manganese-containing acidic etching bath at 100 mg/L or less. [0035]

5 The present inventors' research found that that when a plating treatment is repeatedly performed on a resin material by the above method, palladium contained in the catalyst application solution used in the catalyst application step, which is a step performed after the etching treatment, is gradually accumulated in the etching bath. The present inventors discovered a
10 conventionally unknown phenomenon that when the palladium concentration contained in the etching bath exceeds 100 mg/L, the etching performance is significantly reduced. [0036]

Accordingly, when an article comprising a resin
15 material is subjected to a plating treatment by the plating method of the present invention comprising an etching treatment step using an acidic etching bath containing manganese, a catalyst application step using palladium as a catalyst metal, and an electroless plating step, it is necessary to control and
20 maintain the palladium concentration in the etching bath at 100 mg/L or less. It is particularly preferable that the palladium concentration in the etching bath be maintained at about 50 mg/L or less, and more preferably at about 20 mg/L or less. [0037]

25 The method for maintaining the palladium concentration at 100 mg/L or less is not particularly limited. For example, the entire etching bath or a portion thereof may be replenished to maintain the palladium concentration at 100 mg/L or less. However, in view of cost efficiency, for example, a method for removing
30 palladium adsorbed on a jig, a method for reducing the palladium concentration in an etching bath by cathodic electrolysis, or a method for reducing the palladium concentration by iodide addition to an etching bath is preferably used. These methods may be performed singly, or in a combination of two or more. Using
35 these methods in combination can more efficiently reduce the

palladium concentration. These treatments do not have to be performed every time in the resin plating method comprising the above steps, but may be appropriately performed according to the degree of accumulation of palladium in the etching bath.

5 [0038]

These methods are described below more specifically.

[0039]

(i) Method for removing palladium adsorbed on jig

The present inventors' research revealed that the main
10 factor that causes palladium accumulation in an etching bath is the desorption, in the etching bath, of palladium that has been adsorbed on the jig used in a plating treatment. Accordingly, the resin plating method of the present invention comprises a step of removing palladium adsorbed on a jig to suppress accumulation of
15 palladium in an etching bath, thus maintaining the palladium concentration in an etching bath at 100 mg/L or less.

[0040]

The method for removing palladium adsorbed on a jig is not particularly limited. For example, the method for removing
20 palladium adsorbed on a jig may be a method of immersing a jig in a palladium-removing treatment solution comprising an aqueous solution containing at least one compound selected from the group consisting of nitric acid, persulfates, hydrogen peroxide, and compounds having a stability constant with palladium of 2.0 or
25 more (hereinafter sometimes referred to as "the palladium-removing compound").

[0041]

Among the palladium-removing compounds, specific examples of persulfates include sodium persulfate, ammonium
30 persulfate, potassium persulfate, and the like. Examples of compounds having a stability constant with palladium of 2.0 or more include ethylenediamine, thiourea, acetylacetone, and like various compounds; and dimethylglyoxime, cyclohexanone oxime, benzophenone oxime, diphenylmethanone oxime, and like oxime
35 compounds.

[0042]

The concentration of the palladium-removing compound in the palladium-removing treatment solution is not particularly limited. However, an excessively low concentration of the
5 palladium-removing compound may result in an insufficient palladium removal effect. Although the concentration of the palladium-removing compound may vary depending on its solubility, an excessively high concentration of the palladium-removing compound is disadvantageous in terms of cost. Accordingly, the
10 concentration of the palladium-removing compound in the palladium-removing treatment solution is preferably about 0.01 to 1000 g/L, more preferably about 0.1 to 500 g/L, and even more preferably about 1 to 100 g/L.

[0043]

15 The liquid temperature of the palladium-removing treatment solution is not particularly limited. An excessively low liquid temperature may result in an insufficient palladium removal effect. An excessively high liquid temperature tends to deteriorate the jig. Accordingly, the liquid temperature of the
20 palladium-removing treatment solution is preferably about 10 to 70°C, and more preferably about 20 to 50°C.

[0044]

Although the time of immersing a jig in the palladium-removing treatment solution is not particularly limited, an
25 excessively short immersion time may result in an insufficient palladium removal effect. An excessively long immersion time is disadvantageous in terms of productivity on an industrial scale. Accordingly, the immersion time in the palladium-removing treatment solution is preferably about 1 second to about 5 hours,
30 more preferably about 10 seconds to about 2 hours, and even more preferably about 1 minute to about 1 hour.

[0045]

The treatment for removing palladium can be performed at any stage after the electroless plating treatment or before
35 the etching treatment. In particular, if the treatment for

removing palladium is performed after the object to be treated has been removed from the jig after electroplating, the treatment may also function as a step of dissolving and stripping a plating film deposited on the contact point of a jig (so-called "jig cleaning"); however, this may depend on the composition of the palladium-removing treatment solution. For example, if a jig from which after an electroplating treatment, the object to be treated has been removed is immersed in nitric acid, the plating film deposited on the contact point of the jig may be dissolved and stripped while removing palladium adsorbed on the jig, thus achieving an efficient treatment.

[0046]

(ii) Method for reducing the palladium concentration by cathodic electrolysis

The palladium accumulated in the etching bath can be removed, for example, by electrolytic treatment to deposit palladium in an etching bath on a cathode as metallic palladium.

[0047]

The electrolytic treatment conditions are not particularly limited, and can be suitably determined according to the composition of the etching bath and the amount of palladium accumulated. To efficiently remove palladium, for example, the cathode current density may be, for example, about 50 A/dm² or less, preferably about 40 A/dm² or less, and more preferably about 30 A/dm² or less. The lower limit of the cathode current density is not particularly limited. In view of treatment efficiency, it is usually preferable that the cathode current density be about 0.1 A/dm² or more, and more preferably about 0.5 A/dm² or more.

[0048]

The liquid temperature of the etching bath during the electrolytic treatment is not particularly limited. An excessively low liquid temperature may result in insufficient palladium removal efficiency. An excessively high liquid temperature increases the burden on equipment such as electrodes. Accordingly, for example, the liquid temperature of the etching

bath during the electrolytic treatment is preferably about 30 to 80°C, and more preferably about 50 to 70°C.

[0049]

Any electrode material exhibiting durability and
5 sufficient electrical conductivity in an acidic solution may be used as the anode in the electrolytic treatment. Examples of usable electrode materials include Pt/Ti, carbon, SUS, Pt, Pb, PbO₂, Ta, Zr, Fe-Si, diamond, and the like.

[0050]

10 As with the anode, any electrode material exhibiting durability and sufficient electrical conductivity in an acidic solution may be used as the cathode. Examples of usable electrode materials include Pt/Ti, carbon, SUS, Pt, Pb, PbO₂, Ta, Zr, Fe-Si, diamond, and the like.

15 [0051]

The electrolysis may be performed until the palladium concentration in the etching bath becomes less than or equal to the target concentration.

[0052]

20 (iii) Method for reducing the palladium concentration by iodide addition

Adding an iodide to a palladium-accumulated etching bath can form a precipitate of insoluble palladium iodide. Separating this precipitate by a method such as filtration can
25 remove palladium from the etching bath.

[0053]

Examples of iodides added to remove palladium include sodium iodide, potassium iodide, iodic acid, iodates (e.g., sodium iodate, potassium iodate, and ammonium iodate), periodic
30 acid, periodates (e.g., sodium periodate, potassium periodate, and ammonium iodate), and the like. Such iodides can be used singly, or in a combination of two or more.

[0054]

Although the amount of iodide added is not particularly
35 limited, an excessively low amount of iodide may result in an

insufficient palladium removal effect, whereas a large excess of iodide does not provide cost-effective effects. Accordingly, the concentration of the iodide added to the etching bath is preferably 2 to 100 times, more preferably about 5 to 50 times, the concentration of the palladium concentration in the bath in terms of molar ratio.

[0055]

The liquid temperature during the treatment for removing palladium is not particularly limited. However, an excessively low temperature may result in an insufficient palladium removal effect, whereas an excessively high liquid temperature tends to deteriorate the jig. Accordingly, the liquid temperature is preferably, for example, about 30 to 80°C, and more preferably about 50 to 70°C.

[0056]

To efficiently form the precipitate of palladium iodide, the etching bath is preferably stirred after adding an iodide to the etching bath. Although the stirring time is not particularly limited, an excessively short stirring time may result in an incomplete palladium iodide production reaction and fail to obtain a sufficient effect. On the other hand, an excessively long stirring time is disadvantageous in terms of productivity on an industrial scale. Accordingly, the stirring time after iodide addition is preferably about 1 minute to about 2 hours, and more preferably about 10 minutes to about 1 hour.

Advantageous Effects of Invention

[0057]

According to the resin plating method of the present invention, even if an acidic etching bath containing manganese as an active ingredient is used continuously, excellent etching performance can be maintained for a long period of time while inhibiting the reduction of etching power.

[0058]

Therefore, according to the resin plating method of the

present invention, a good plating film can be continuously formed for a long period of time on articles comprising various resin materials, which are used as objects to be plated.

5 Description of Embodiments

[0059]

The present invention is described below in more detail with reference to Examples.

[0060]

10 Examples 1 to 7 and Comparative Examples 1 to 7

Flat plates (10 cm x 5 cm x 0.3 cm, surface area: about 1 dm²) of ABS resin (produced by UMG ABS, Ltd., trade name: UMG ABS3001M) were used as test pieces and attached to a jig coated with vinyl chloride. The test pieces were plated by the steps shown in Table 1 below. The volumes of treatment solutions used in the treatments were all set to 1 L, and the test pieces were washed with water between each treatment.

[0061]

Table 1

Treatment step	Type of treatment solution	Treatment conditions
Degreasing treatment	Alkaline degreasing solution (produced by Okuno Chemical Industries Co., Ltd., ACE CLEAN A-220 bath)	40°C, immersion time: 5 min.
Etching treatment	Etching bath shown in Table 2 below	68°C, immersion time: 20 min.
Acid pickling	300 ml/L sulfuric acid	25°C, immersion time: 1 min.
Catalyst application	Palladium-tin colloidal catalyst solution (produced by Okuno Chemical Industries Co., Ltd., catalyst C bath)	40°C, immersion time: 5 min.
Activation	Aqueous solution containing 100 ml/L of 35% hydrochloric acid	35°C, immersion time: 5 min.
Electroless nickel Plating	Electroless nickel plating solution (produced by Okuno Chemical Industries Co., Ltd., Chemical Nickel SEP-LF bath)	40°C, immersion time: 5 min.
Copper sulfate plating	Copper sulfate plating solution (produced by Okuno Chemical Industries Co., Ltd., Top Lucina 2000 bath)	Cathode current density: 3A, 25°C, plating time: 30 min.
Semi-bright nickel plating	Semi-bright nickel plating solution (produced by Okuno Chemical Industries Co., Ltd.,	Cathode current density: 3A 55°C, plating time: 20 min.

	ACNA NEO bath)	
Bright nickel plating	Bright nickel plating solution (produced by Okuno Chemical Industries Co., Ltd., (KAI) ACNA B bath)	Cathode current density: 3A, 55°C, plating time: 15 min.
Trivalent chrome Plating	Trivalent chromium plating solution (produced by Okuno Chemical Industries Co., Ltd., Top Fine chromium WR bath)	Cathode current density: 10A, 35°C, plating time: 4 min.

[0062]

Table 2 to 5 below show the compositions of the etching baths used in the plating steps above.

5 [0063]

In the resin plating method comprising the treatment steps described above, the treatment for removing Pd from a jig, the treatment for removing Pd by cathodic electrolysis and/or the treatment for removing Pd by iodide addition were performed under the conditions shown in Tables 2 to 5 below.

[0064]

Among these treatments, the treatment for removing Pd from a jig was performed every time after each test piece plated with trivalent chrome was removed from the jig. The treatment for removing Pd by cathodic electrolysis and the treatment for removing Pd by iodine addition were performed in the etching bath used every 100 times of the resin plating treatment comprising the above treatment steps.

[0065]

20 Using the test pieces obtained in the Examples, the palladium concentration in the etching bath after treating 1000 test pieces (treatment area: 1000 dm²/L) and the peel strength of the obtained plating film were measured. The palladium concentration in the bath was measured by the ICP method. The peel strength was determined in the following manner. The test pieces plated by the above steps were dried at 80°C for 120 minutes, and allowed to stand to cool to room temperature. Thereafter, parallel cuts with a width of 10 mm were made in the plating film, and the plating film was pulled in a direction

vertical to the resin surface using a tensile tester (Autograph AGS-J 1kN; produced by Shimadzu Corporation) to determine the peel strength. Tables 2 to 5 below show the results.

[0066]

5 Resin plating was performed in the same manner as in the Examples except that none of the treatment for removing Pd from a jig, the treatment for removing Pd by cathodic electrolysis, and the treatment for removing Pd by iodide addition was performed. These results are shown as Comparative
10 Examples in Tables 2 to 5.

Table 2

		Comp. Ex. 1	Example 1	Comp. Ex. 2	Example 2
Composition of the etching bath		10 g/L manganese(III) phosphate + 1200 g/L sulfuric acid		4 g/L manganese(IV) oxide + 900 g/L phosphoric acid	
Treatment for removing Pd from the jig	Composition	-	300 g/L nitric acid	-	-
	Temperature (°C)		25		
	Time (min.)		30		
Treatment for removing Pd in the etching bath by cathodic electrolysis	Anode	-	-	-	Pt/Ti
	Cathode				Zr
	Cathode current density (A/dm ²)				20
	Temperature (°C)				70
	Time (min.)				60
Treatment for removing Pd in the etching bath by iodide addition	Iodide salt	-	-	-	-
	Amount added (mg/L)				
	Temperature (°C)				
	Time (min.)				
Pd concentration (mg/L) in the bath after treating 1000 test pieces		120	30	114	55
Peel strength	Immediately after preparing the bath	0.61	0.61	0.57	0.57
	1000 dm ² /L	0.11	0.58	0.09	0.51

[0068]

Table 3

		Comp. Ex. 3	Example 3	Comp. Ex. 4	Example 4
Composition of the etching bath		3 g/L potassium permanganate(VII) + 700 g/L sulfuric acid + 700 g/L phosphoric acid		2 g/L manganese(III) fluoride + 5 g/L sodium permanganate(VII) + 700 g/L sulfuric acid + 600 g/L phosphoric acid	
Treatment for removing Pd from the jig	Composition	-	-	-	300 g/L nitric acid + 20 g/L ethylene diamine
	Temperature (°C)				25
	Time (min.)				60
Treatment for removing Pd in the etching bath by cathodic electrolysis	Anode	-	-	-	Pb
	Cathode				Zr
	Cathode current density (A/dm ²)				30
	Temperature (°C)				70
	Time (min.)				30
Treatment for removing Pd in the etching bath by iodide addition	Iodide salt	-	KI	-	-
	Amount added (mg/L)		200		
	Temperature (°C)		70		
	Time (min.)		30		
Pd concentration (mg/L) in the bath after treating 1000 test pieces		150	20	190	15
Peel strength	Immediately after preparing the bath	0.96	0.96	0.89	0.89
	1000 dm ² /L	0.19	0.94	0.21	0.85

[0069]

Table 4

		Comp. Ex. 5	Example 5	Comp. Ex. 6	Example 6
Composition of the etching bath		5 g/L manganese(IV) oxide + 10 g/L sodium permanganate(VII) + 1000 g/L methanesulfonic acid		5 g/L manganese(IV) oxide + 10 g/L sodium permanganate(VII) + 700 g/L sulfuric acid + 700 g/L methanesulfonic acid	
Treatment for removing Pd from the jig	Composition	-	-	-	200 g/L hydrogen peroxide + 10 g/L thiourea
	Temperature (°C)				40
	Time (min.)				90
Treatment for removing Pd in the etching bath by cathodic electrolysis	Anode	-	Pb	-	-
	Cathode		Pt/Ti		
	Cathode current density (A/dm ²)		15		
	Temperature (°C)		70		
	Time (min.)		90		
Treatment for removing Pd in the etching bath by iodide addition	Iodide salt	-	NaI	-	Sodium iodate
	Amount added (mg/L)		200		100
	Temperature (°C)		70		70
	Time (min.)		20		10
Pd concentration (mg/L) in the bath after treating 1000 test pieces		185	5	210	8
Peel strength	Immediately after preparing the bath	0.91	0.91	0.99	0.99
	1000 dm ² /L	0.18	0.88	0.12	0.94

[0070]

Table 5

		Comp. Ex. 7	Example 7
Composition of the etching bath		10 g/L manganese(III) acetate + 4 g/L manganese(IV) oxide + 15 g/L potassium permanganate(VII) + 700 g/L sulfuric acid + 700 g/L methanesulfonic acid	
Treatment for removing Pd from the jig	Composition	-	300 g/L nitric acid + 20 g/L dimethylglyoxime
	Temperature (°C)		30
	Time (min.)		60
Treatment for removing Pd in the etching bath by cathodic electrolysis	Anode	-	Carbon
	Cathode		Pt/Ti
	Cathode current density (A/dm ²)		10
	Temperature (°C)		70
	Time (min.)		60
Treatment for removing Pd in the etching bath by iodide addition	Iodide salt	-	Potassium periodate
	Amount added (mg/L)		150
	Temperature (°C)		70
	Time (min.)		15
Pd concentration (mg/L) in the bath after treating 1000 test pieces		205	0.2
Peel strength	Immediately after preparing the bath	1.02	1.02
	1000 dm ² /L	0.13	1.02

[0071]

The above results clearly confirm that when the palladium concentration in the etching bath was maintained at 100 mg/L or less (Examples 1 to 7) by any one of the treatment for removing Pd from a jig, the treatment for removing Pd in an etching bath by cathodic electrolysis, and the treatment for removing Pd from an etching bath by iodide addition, substantially no reduction in peel strength occurred, and good etching power could be maintained even after treating 1000 test pieces (treatment area: 1000 dm²/L). In particular, when two or more of the above treatments were performed in combination (Examples 5 to 7), the palladium concentration in the etching bath could be maintained at a lower level, and good etching performance was exhibited.

15 [0072]

In contrast, when no treatment for reducing the Pd concentration was performed (Comparative Examples 1 to 7), the palladium concentration in the bath was increased to 114 to 210 mg/L after treating 1000 test pieces; etching power was reduced, compared with that immediately after preparing the bath; and significant reduction in peel strength of the obtained plating film was observed.

[0073]

25 These results clearly show that controlling the metal palladium concentration in an acidic etching bath containing manganese as an active ingredient at 100 mg/L or less can maintain good etching power over a long period of time.

[Claim 1]

A resin plating method comprising:

an etching step in which an article comprising a resin material is used as an object to be treated and is
5 subjected to etching using an acidic etching bath containing manganese;

a catalyst application step using palladium as a catalyst metal; and

an electroless plating step,

10 the method further comprising a step of maintaining the palladium concentration in the acidic etching bath at 100 mg/L or less,

wherein the step of maintaining the palladium concentration in the acidic etching bath at 100 mg/L or less is performed by

15 a method for removing palladium adsorbed on a jig;

wherein the method for removing palladium adsorbed on a jig is a method of immersing a jig in a palladium-removing treatment solution comprising an aqueous solution containing at least one compound selected from the group consisting of nitric acid,
20 persulfates, hydrogen peroxide, and compounds having a stability constant with palladium of 2.0 or more.

[Claim 2]

A resin plating method comprising:

an etching step in which an article comprising a resin material is used as an object to be treated and is
25 subjected to etching using an acidic etching bath containing manganese;

a catalyst application step using palladium as a catalyst metal; and

30 an electroless plating step,

the method further comprising a step of maintaining the palladium concentration in the acidic etching bath at 100 mg/L or less,

wherein the step of maintaining the palladium concentration in
35 the acidic etching bath at 100 mg/L or less is performed by a

method for reducing the palladium concentration in the etching bath by cathodic electrolysis.

[Claim 3]

A resin plating method comprising:

5 an etching step in which an article comprising a resin material is used as an object to be treated and is subjected to etching using an acidic etching bath containing manganese;

10 a catalyst application step using palladium as a catalyst metal; and

 an electroless plating step,
the method further comprising a step of maintaining the palladium concentration in the acidic etching bath at 100 mg/L or less,

15 wherein the step of maintaining the palladium concentration in the acidic etching bath at 100 mg/L or less is performed by a method for reducing the palladium concentration by iodide addition to the etching bath.

[Claim 4]

20 The resin plating method according to claim 2, wherein the method for reducing the palladium concentration in an etching bath by cathodic electrolysis is a method of depositing palladium in an etching bath on a cathode as metallic palladium by electrolytic treatment.

[Claim 5]

25 The resin plating method according to claim 3, wherein the method for reducing the palladium concentration by iodide addition to an etching bath is a method comprising adding to an etching bath at least one iodide selected from the group
30 consisting of sodium iodide, potassium iodide, iodic acid, iodates, periodic acid, and periodates, and separating the formed precipitate.

[Claim 6]

35 A method for controlling a resin plating etching bath, comprising maintaining the palladium concentration in a

manganese-containing acidic etching bath at 100 mg/L or less, wherein the step of maintaining the palladium concentration in the acidic etching bath at 100 mg/L or less is performed by a method for removing palladium adsorbed on a jig;

5 wherein the method for removing palladium adsorbed on a jig is a method of immersing a jig in a palladium-removing treatment solution comprising an aqueous solution containing at least one compound selected from the group consisting of nitric acid, persulfates, hydrogen peroxide, and compounds having a stability
10 constant with palladium of 2.0 or more.

[Claim 7]

A method for controlling a resin plating etching bath, comprising maintaining the palladium concentration in a manganese-containing acidic etching bath at 100 mg/L or less,
15 wherein the step of maintaining the palladium concentration in the acidic etching bath at 100 mg/L or less is performed by a method for reducing the palladium concentration in the etching bath by cathodic electrolysis.

[Claim 8]

20 A method for controlling a resin plating etching bath, comprising maintaining the palladium concentration in a manganese-containing acidic etching bath at 100 mg/L or less, wherein the step of maintaining the palladium concentration in the acidic etching bath at 100 mg/L or less is performed by a
25 method for reducing the palladium concentration by iodide addition to the etching bath.

[Claim 9]

The method for controlling a resin plating etching bath according to claim 7, wherein the method for reducing the
30 palladium concentration in an etching bath by cathodic electrolysis is a method of depositing palladium in an etching bath on a cathode as metallic palladium by electrolytic treatment.

[Claim 10]

35 The method for controlling a resin plating etching

bath according to claim 8, wherein the method for reducing the palladium concentration by iodide addition to an etching bath is a method comprising adding to an etching bath at least one iodide selected from the group consisting of sodium iodide, 5 potassium iodide, iodic acid, iodates, periodic acid, and periodates, and separating the formed precipitate.