

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
10 May 2007 (10.05.2007)

PCT

(10) International Publication Number
WO 2007/053475 A1

(51) International Patent Classification:

C08J 5/18 (2006.01) *C08L 33/08* (2006.01)
C08K 3/20 (2006.01) *C08J 3/28* (2006.01)

(21) International Application Number:

PCT/US2006/042104

(22) International Filing Date: 27 October 2006 (27.10.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

2005-315107 28 October 2005 (28.10.2005) JP

(71) Applicant (for all designated States except US): **3M INNOVATIVE PROPERTIES COMPANY** [US/US];
3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **YODA, Masaki** [JP/JP]; 33-1, Tamagawadai 2-chome, Setagaya-ku, Tokyo 158-8583 (JP). **YAMAZAKI, Yoshinao** [JP/JP]; 33-1, Tamagawadai 2-chome, Setagaya-ku, Tokyo 158-8583 (JP).

(74) Agents: **HARTS, Dean, M.** et al.; 3M Center, Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHOD FOR PRODUCING THERMALLY CONDUCTIVE SHEET AND THERMALLY CONDUCTIVE SHEET PRODUCED BY THE METHOD

(57) Abstract: To provide a single-layer thermally conductive sheet having tackiness differing between the front surface and the back surface without requiring an additional step of removing surface tackiness, for example, applying a base material, beads or an anti-blocking powder. A method for producing a thermally conductive sheet, comprising: (a) shaping a thermally conductive precursor composition into a sheet, the thermally conductive precursor composition comprising a (meth)acrylic monomer or a polymerizable oligomer thereof, a photopolymerization initiator, and a thermally conductive filler present in an amount of 20 vol% or more based on the total volume of the thermally conductive composition obtained, and (b) irradiating the front surface and the back surface of the sheet with ultraviolet radiation at different ultraviolet irradiation intensities such that the irradiation intensity on the surface irradiated at a higher intensity is 30 times or less the irradiation intensity on the surface irradiated at a lower intensity, thereby curing the sheet and obtaining a thermally conductive sheet consisting of a single-layer thermally conductive composition and having tackiness differing between the front surface and the back surface.



WO 2007/053475 A1