



**Halide-containing silicon, method for producing the  
same, and use of the same**

The present invention relates to silicon obtained by  
5 thermal decomposition of halogenated polysilane in  
particular silicon obtained by thermal decomposition of  
chlorinated polysilane.

WO 2006/125425 A1 discloses a method for producing  
10 silicon from halosilanes, wherein, in a first step, the  
halosilane is converted into a halogenated polysilane  
with generation of a plasma discharge, said halogenated  
polysilane subsequently being decomposed in a second  
step with heating to form silicon. For the  
15 decomposition of the halogenated polysilane, the latter  
is preferably heated to a temperature of 400°C  
to 1500°C. Temperatures of 800°C, 700°C, 900°C and once  
again 800°C are used in the exemplary embodiments. As  
far as the pressure used is concerned, reduced pressure  
20 is preferably employed, vacuum being employed in the  
exemplary embodiments.

It goes without saying that the production of silicon  
that is as pure as possible is striven for with the  
25 method described above. In particular, the silicon  
obtained has a low halide content.

The present invention is based on the object of  
providing a silicon variant obtained by thermal  
30 decomposition of halogenated polysilane, which in  
particular can be used for silicon purification  
purposes. Furthermore, the intention is to provide a  
method for producing such a silicon variant.

35 The object mentioned above is achieved according to the  
invention by means of halide-containing silicon  
obtained by thermal decomposition of halogenated



polysilane and having a halide content of 1 at% - 50 at%.

It has been observed according to the invention that the high temperatures and low pressures used in the known method for producing silicon as described in the introduction are responsible for the high purity of the end product obtained, in particular with regard to the halide content of the end product. The invention now does not strive to produce silicon having a halide content that is as low as possible, rather the silicon is intended to have, in a targeted manner, a relatively high halide content of 1 at% - 50 at%. This silicon having a relatively high halide content is afforded by relative low temperatures and relatively high pressures during the thermal decomposition (pyrolysis).

The silicon obtained by thermal decomposition of halogenated polysilane is preferably obtained directly in granular form. It preferably has a bulk density of 0.2 - 1.5 g/cm<sup>3</sup>, furthermore preferably a grain size of 50 - 20000 µm.

It has been observed that the halide content is dependent on the grain size. The halide content increases as the grain size grows.

The halide content can be determined quantitatively by titration using silver nitrate (according to Moor). IR spectroscopic measurements (ATR technique, diamond single reflection) on chloride-containing silicon show a signal at 1029 cm<sup>-1</sup>. The intensity is dependent on the halide content and increases as the halide content increases.

Whereas, therefore, in the prior art presented in the introduction, the method conditions (pyrolysis conditions) are selected such that silicon being as

pure as possible is obtained, the silicon according to the invention has, in a targeted manner, a relatively high halide content.

5 As far as the halide content of the silicon is concerned, the latter comprises, for example, halosilanes ( $\text{Si}_n\text{X}_{2n+2}$  ( $\text{X} = \text{halogen}$ )) in the voids of halogen-containing silicon grains. Said halosilanes can be present in a physical mixture with the silicon  
10 grains. However, the silicon can also comprise halogen chemically fixedly bonded to Si atoms, wherein the silicon according to the invention normally includes both variants.

15 The color of the silicon according to the invention is dependent on the halide content (chloride content). By way of example, silicon having a chloride content of 30 at% is reddish brown, while silicon having a chloride content of 5 at% is blackish grey.

20 The present invention furthermore relates to a method for producing the granular silicon according to the invention, wherein the halogenated polysilane is thermally decomposed with continuous addition in a  
25 reactor. Preferably, in this case, the halogenated polysilane is introduced into the reactor dropwise. The relatively high halide content desired according to the invention is obtained by means of this continuous procedure.

30 Thereby, the thermal decomposition preferably takes place in a temperature range of  $350^\circ\text{C}$  -  $1200^\circ\text{C}$ , wherein the temperature for the decomposition of the halogenated polysilane is preferably less than  $400^\circ\text{C}$ .

35 Furthermore, the thermal decomposition is preferably carried out at a pressure of  $10^{-3}$  mbar to 300 mbar above

atmospheric pressure, wherein pressures > 100 mbar are preferred.

According to an alternative of the method according to  
5 the invention, an inert gas atmosphere, in particular argon atmosphere, is maintained in the reactor used for the thermal decomposition.

The setting of the desired halide content is possible  
10 by variation of a series of parameters, for example setting a desired time profile, temperature profile and pressure profile. As already mentioned, in the method according to the invention, the halide-containing silicon is preferably obtained directly in granular  
15 form. This does not, of course, rule out the possibility of correspondingly modifying the obtained end product by means of further mechanical measures such as mechanical comminution, screening, etc. in order to obtain desired material properties in specific  
20 ranges.

A further alternative of the method for setting the halide content of the granular silicon obtained concerns an aftertreatment of the silicon obtained. By  
25 way of example, the halide content can be reduced by baking. Thus, by way of example, the chloride content of a specific silicon type (grain size 50  $\mu\text{m}$  to 20 000  $\mu\text{m}$ , chloride content 15%) was reduced to 4% by baking to 1150°C over four hours. By way of example, baking,  
30 baking under vacuum, comminution or screening shall be mentioned as suitable aftertreatment.

The present invention furthermore relates to the use of the halide-containing silicon for purifying  
35 metallurgical silicon.

US 4 312 849 discloses a method for removing phosphorus impurities in a method for purifying silicon, where a

silicon melt is produced and the melt is treated with a chlorine source in order to remove phosphorus. The preferred chlorine source used is a gaseous chlorine source, in particular  $\text{Cl}_2$ ,  $\text{COCl}_2$  and  $\text{CCl}_4$  are indicated as alternative chlorine sources. Aluminum is additionally added to the melt. The gas containing the chlorine source is bubbled through the melt.

DE 29 29 089 A1 discloses a method for refining and growing silicon crystals, wherein a gas is caused to react with a silicon melt, wherein the gas is selected from the group comprising wet hydrogen, chlorine gas, oxygen and hydrogen chloride.

EP 0 007 063 A1 describes a method for producing polycrystalline silicon, wherein a mixture of carbon and silicon is heated to form a melt and a gas containing chlorine and oxygen is conducted through the melt.

As shown by the explanations above, it is already known to remove impurities from silicon melts with the aid of gaseous chlorine sources. Thereby, gas mixtures containing chlorine gas or chlorine are introduced into the Si melt. However, the implementation of such technology is very complex since the chlorine has to be introduced directly into the melt, which is generally effected by means of small tubes or specific nozzles. Therefore, a homogeneous distribution of the chlorine over the entire melt is only possible to a limited extent. Moreover, the apparatuses for introducing the chlorine into the melt can adversely affect the melt itself, that is to say that impurities originating from the apparatuses for introducing gas can occur, for example.

It has now been found that the halide-containing silicon according to the invention is excellently

suitable for purifying metallurgical silicon, to be precise in a particularly simple and effective manner. Thereby, according to a first alternative, the following steps are carried out:

5

mixing halide-containing silicon with the metallurgical silicon to be purified;

melting the mixture and thereby sublimating out the impurities and removing the same from the melt in the form of metal halides.

Consequently, rather than the use of a gaseous chlorine source for purifying the metallurgical silicon, as is the case in the prior art, solid halide-containing silicon is mixed with the metallurgical silicon to be purified, and the resulting mixture is melted. As a result, the impurities, in particular heavy metals are sublimated out in the form of chlorides, for example  $\text{FeCl}_3$ , and thus removed from the melt.

According to a second alternative of the use according to the invention, the following steps are carried out:

25 melting the metallurgical silicon to be purified;

introducing halide-containing silicon into the melt and thereby sublimating out the impurities and removing the same from the melt in the form of metal halides.

30

In this second method variant, therefore, prior mixing of the halide-containing silicon with the metallurgical silicon to be purified does not take place, rather the halide-containing silicon is introduced directly into a melt composed of the metallurgical silicon to be purified. By this means, too, impurities of the silicon to be purified are sublimated out and removed from the melt in the form of metal halides.

In this case, the halide-containing silicon used is preferably chloride-containing silicon.

5 The halide-containing silicon used can preferably be halide-containing silicon which contains halosilane fractions mixed with Si fractions. Such halosilanes ( $\text{Si}_n\text{X}_{2n+2}$ , where X denotes halogen and n denotes 1 - 10, preferably 1 - 3) are preferably present (physically)  
10 in the vacancies of chlorine-containing silicon grains, but can also be fixedly bonded to silicon atoms (Si-X) by chemical bonds.

The corresponding halide content can be determined  
15 quantitatively by titration using silver nitrate (according to Moor). IR-spectroscopic measurements (ATR technique, diamond single reflection) on chloride-containing silicon show a signal at  $1029\text{ cm}^{-1}$ . The intensity is dependent on the halide content and  
20 increases as the halide content increases.

In order to achieve good mixing of the halide-containing silicon with the metallurgical silicon to be purified, preferably granular, in particular fine-  
25 grained halogen-containing silicon is used. In this case, the grain size is expediently  $50\text{ }\mu\text{m}$  to  $20000\text{ }\mu\text{m}$ . The halide-containing silicon preferably has a bulk density of  $0.2\text{ g/cm}^3$  to  $1.5\text{ g/cm}^3$ .

30 The halide content is dependent on the grain size. The halide content increases as the grain size grows.

A further alternative of the method according to the invention is distinguished by the fact that the halide  
35 content of the halide-containing silicon used for purification is set by means of aftertreatment. Said aftertreatment preferably takes place under vacuum. By way of example, the chloride content of chloride-

containing silicon of a specific type (grain size 50  $\mu\text{m}$  to 20000  $\mu\text{m}$  (without screening) chloride content 15%) was reduced to a chloride content of 4% by baking to 1150°C over 4 hours. Suitable aftertreatment methods  
5 include, for example, baking, baking under vacuum, comminution or screening.

It has been found that good results with regard to the purification of metallurgical silicon can be achieved  
10 according to the invention without complicated devices for introducing gas into the melt. In this case, in particular, heavy metals were able to be removed in the form of chlorides from the melt in a completely satisfactory manner.

15 In a further embodiment of the use according to the invention, the melt is replenished with halide-containing silicon. In this case, "melt" is taken to mean the melt consisting of the mixture of halide-  
20 containing silicon and silicon to be purified, or the melt consisting solely of silicon to be purified. In both cases, by means of the "replenishing" performed, the corresponding purification process can be set, for example readjusted or begun anew.

25 Yet another embodiment of the use of the invention is distinguished by the fact that the melt is homogenized. This can be effected, for example, by means of agitation of the melt, in particular by crucible  
30 rotation, use of a stirrer, etc. However, the melt can also be homogenized simply by being allowed to stand for a sufficient time, such that suitable homogenization arises by convection in this case.

35 The purification according to the invention can be used, in particular, in Si crystallization methods, for example in ingot casting methods, Czochralski methods, EFG methods, string ribbon methods, RSG methods.

Thereby, it is used for purifying the Si melt from which the crystals are produced. In the ingot casting method, multicrystalline Si ingots are produced by crystals with a width of up to a plurality of  
5 centimeters being allowed to grow through the entire ingot by means of controlled solidification. In the EFG method (edge-defined film growth) an octagonal "tube" is pulled from the silicon melt. The resulting multicrystalline tube is sawn at the edges and  
10 processed to form wafers. In the string ribbon method, between two wires a ribbon is pulled from the silicon melt. In the RGS method (ribbon growth on substrate) a ribbon of silicon arises by a carrier material being moved under a crucible with liquid silicon. The  
15 Czochralski method is a method for producing silicon single crystals wherein a crystal is pulled from the silicon melt. Under pulling and rotational movements, a cylindrical silicon single crystal deposits on a crystalline seed.

20

#### Exemplary embodiment

Halogenated polysilane produced plasma-chemically in  
25 the form of PCS was continuously introduced dropwise into a reactor, the reaction zone of which was kept at a pressure of 300 mbar. The temperature of the reaction zone was kept at 450°C. A solid granular end product obtained was continuously extracted from the reactor,  
30 said end product being silicon having a chloride content of 33 at%. The chloride-containing silicon obtained had a bulk density of 1.15 g/cm<sup>3</sup> and a red color.

### Patent Claims

1. Halide-containing silicon obtained by thermal decomposition of halogenated polysilane and having a  
5 halide content of 1 at% - 50 at%.

2. The halide-containing silicon according to claim 1, characterized in that it is present in granular form.

10

3. The halide-containing silicon according to claim 1 or 2, characterized in that it has a bulk density of 0.2 - 1.5 g/cm<sup>3</sup>.

15

4. The halide-containing silicon according to any of the preceding claims, characterized in that it has a grain size of 50 - 20000 μm.

20

5. The halide-containing silicon according to any of the preceding claims, characterized in that it comprises halosilanes ( $\text{Si}_n\text{X}_{2n+2}$  (X = halogen)) in the voids of halogen-containing silicon grains.

25

6. The halide-containing silicon according to any of the preceding claims, characterized in that it comprises halogen chemically fixedly bonded to Si atoms.

30

7. The halide-containing silicon according to any of the preceding claims, characterized in that it contains chloride.

35

8. A method for producing the halide-containing silicon according to any of the preceding claims, characterized in that the halogenated polysilane is thermally decomposed with continuous addition in a reactor.

9. The method according to claim 8, characterized in that the halogenated polysilane is introduced into the reactor dropwise.

5 10. The method as claimed in either of claims 8 and 9, characterized in that the thermal decomposition takes place in a temperature range of 350°C - 1200°C.

10 11. The method according to claim 10, characterized in that the temperature for the decomposition of the halogenated polysilane is less than 400°C.

12. The method according to any of claims 8 to 11, characterized in that the thermal decomposition takes  
15 place at a pressure of  $10^{-3}$  mbar to 300 mbar above atmospheric pressure.

13. The method according to any of claims 8 to 12, characterized in that an inert gas atmosphere, in  
20 particular argon atmosphere, is maintained in the reactor used for the thermal decomposition.

14. The method according to any of claims 8 to 13, characterized in that the halide content of the halide-  
25 containing silicon obtained is set by aftertreatment of said halide-containing silicon.

15. The use of the halide-containing silicon according to any of the preceding claims, for purifying  
30 metallurgical silicon, comprising the following steps:

mixing halide-containing silicon with the metallurgical silicon to be purified;

35 melting the mixture and thereby sublimating out the impurities and removing the same from the melt in the form of metal halides.

16. The use of the halide-containing silicon according to any of claims 1 to 14 for purifying metallurgical silicon, comprising the following steps:

5 melting the metallurgical silicon to be purified;

introducing halide-containing silicon into the melt and thereby sublimating out the impurities and removing the same from the melt in the form of metal halides.

10

17. The use according to claim 15 or 16, characterized in that the halide-containing silicon used is halide-containing silicon which contains halosilane fractions mixed with Si fractions.

15

18. The use according to any of claims 15 to 17, characterized in that the halide-containing silicon used is halide-containing silicon which contains halogen chemically bonded to Si atoms.

20

19. The use according to any of claims 15 to 18, characterized in that granular, in particular fine-grained halide-containing silicon is used.

25

20. The use according to any of claims 15 to 19, characterized in that the melt is replenished with halide-containing silicon.

21. The use according to any of claims 15 to 20,  
30 characterized in that the melt is homogenized.

22. The method according to any of claims 15 to 21, characterized in that it is used in Si crystallization methods, in particular ingot casting methods,  
35 Czochralski methods, EFG methods, string ribbon methods, RSG methods.