

Process for preparing granular sodium silicates

Abstract of the disclosure:

To prepare a compacted, granular sodium silicate having an $\text{SiO}_2/\text{Na}_2\text{O}$ molar ratio of 1.7 : 1 to 4.1 : 1, sodium silicate having a median particle diameter of $< 500 \mu\text{m}$ is first mixed with a material increasing its hardness before being converted into pressed granules having particle sizes of 0.1 to 5 mm by compacting, comminution and screening.

18 SEP 1995