

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08G 64/40, 64/30, C08K 3/32, 5/42, C08L 69/00	A1	(11) International Publication Number: WO 00/69947 (43) International Publication Date: 23 November 2000 (23.11.00)
(21) International Application Number: PCT/US00/11292 (22) International Filing Date: 26 April 2000 (26.04.00) (30) Priority Data: 09/313,063 17 May 1999 (17.05.99) US (71) Applicant: GENERAL ELECTRIC COMPANY [US/US]; 1 River Road, Schenectady, NY 12345 (US). (72) Inventor: MBSTANZA, Raphael; Rue de St. Valery en Caux, F-76460 Saint Riquier es Plain (FR). (74) Agents: SNYDER, Bernard et al.; General Electric Company, 3135 Easton Turnpike W3C, Fairfield, CT 06431 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KH, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: METHOD FOR QUENCHING OF POLYCARBONATE AND COMPOSITIONS PREPARED THEREBY		
(57) Abstract Polycarbonate produced by melt condensation of a diaryl carbonate and a dihydric phenol in the presence of a basic catalyst to produce an intermediate polycarbonate composition is finished by quenching with both an alkyl tosylate quencher and phosphorous acid. The efficiency of quenching can be measured by UV retention. Surprisingly, although phosphorous acid alone has no impact on the UV retention, the combination of alkyl tosylate quenchers and phosphorous acid provides a significant improvement over the use of the alkyl tosylate quencher alone. Thus, the method of the invention permits a reduction in the amount of alkyl tosylate quencher used, and can achieve superior results which cannot be achieved even by increasing the alkyl tosylate levels.		