

70

1 47 281

PATENT SPECIFICATION

(11) 1 474 281

- (21) Application No. 9969/74 (22) Filed 6 March 1974
(31) Convention Application No. 3514/73
(32) Filed 9 March 1973
(31) Convention Application No. 9249/73
(32) Filed 25 June 1973
(31) Convention Application No. 235/74
(32) Filed 9 Jan. 1974 in
(33) Switzerland (CH)
(44) Complete Specification published 18 May 1977
(51) INT CL³ C07D 231/20, 403/06, 409/06; C08K 5/34




- (52) Index at acceptance
C2C 1400 1510 1512 1628 213 215 220 221 225 226 22Y
250 252 254 25Y 28X 292 29Y 30Y 351 355 35X
35Y 364 365 36Y 388 401 40Y 509 50Y 623 624
625 633 662 665 672 675 699 793 797 UK
C3F 331 336 390 391 400 413 441 631 655
C3P 102 2D1A2 2K7 2K8 7D1A 7D1C 7D2A1 7K2 7K8
8D3A 8K2 8K7 E2 PC12B PC12X PC16C PC17
PC18 PC20B PC20C PC20D1 PC7
C3R 21C 22C 32C 36C 38C 3C C11 C12 C13M C13S
C28A C28X C9N C9Q C9S
(72) Inventors LAJOS AVAR, KURT HOFER and MARTIN
PREISWERK

(54) THE USE OF PYRAZOLE COMPOUNDS FOR THE STABILIZATION OF ORGANIC MATERIALS

(71) We, SANDOZ LTD., of 35 Lichtstrasse, 4002 Basle, Switzerland, a Swiss Body Corporate, do hereby declare the invention, for which we pray that a patent may be granted to us, and the method by which it is to be performed, to be particularly described in and by the following statement:—

The present invention relates to pyrazole compounds useful as stabilizers against heat, oxidation or ultraviolet light.

Accordingly, the present invention provides a method of stabilizing organic material susceptible to degradation under the effect of heat, oxidation or ultraviolet light which comprises treating said material with a compound of formula I,



wherein R₁ is alkyl (C₁—C₂₂); cycloalkyl (C₃—C₁₂); cycloalkyl (C₅—C₁₁) alkyl (C₁—C₇); alkyl (C₁—C₂₁) thioalkyl (C₁—C₂₁) with C₂—C₂₂ in the aggregate thereof; cycloalkyl (C₃—C₁₁) alkyl (C₁—C₆) thioalkyl (C₁—C₆) with C₇—C₁₈ in the aggregate thereof; aralkyl (C₇—C₁₂); aralkyl (C₇—C₁₂); substituted on the aryl nucleus by 1 or 2 hydroxyl groups, 1 or 2 alkyl (C₁—C₁₂) groups, cycloalkyl (C₃—C₁₂) and/or cycloalkyl (C₅—C₁₁) alkyl (C₁—C₁₁); phenyl; phenyl substituted by 1 to 3 halogen atoms, cyano, 1 or 2 hydroxyl groups, 1 or 2 alkyl (C₂—C₁₂) groups, 1 or 2 alkoxy (C₁—C₁₂) groups, phenyl, —SO₃H and/or a radical R₄—O— or R₄—SO₂—, wherein R₄ is phenyl or phenyl substituted by 1 or 2 alkyl (C₁—C₆) groups; R₂ has one of the significances of R₁ or is a furane, thiophene, benzothiophene, indole, pyridine or quinoxaline radical, each of which is either unsubstituted or substituted by halogen, alkyl (C₁—C₄) and/or alkoxy (C₁—C₄) with 1 or 2 substituents in the aggregate thereof;

11

2


1,474,281

2

R_3 has one of the significances of R_1 or is cyano or $-\text{COOR}_5$,
wherein R_5 is alkyl (C_1-C_{12}), cycloalkyl (C_3-C_{12}), cycloalkyl (C_3-C_{11})
alkyl (C_1-C_7), phenyl or phenyl substituted by hydroxy and/or 1 to 2
alkyl (C_1-C_8) groups,

5 and Me is hydrogen or an equivalent of a bivalent metal ion.

A preferred group of compounds in the method of the invention are the compounds of formula Ia,



wherein R_1' and R_3' are each independently, alkyl (C_1-C_8), phenyl or phenyl substituted by halogen and/or 1 or 2 alkyl (C_1-C_4) groups,

10


Me' is hydrogen or an equivalent of nickel, zinc, manganese, copper, chromium, calcium, barium or cobalt, and

10

R_2 is as defined above.

A further preferred group of compounds in the method of the invention are the compounds of formula Ib,

15



wherein R_2' is alkyl (C_6-C_{18}); cycloalkyl (C_6-C_8); aralkyl (C_7-C_{10}); aralkyl (C_7-C_{10}) substituted on the aryl nucleus by hydroxyl and/or 1 or 2 alkyl (C_1-C_6) groups; phenyl; phenyl substituted by 1 to 3 halogen atoms, 1 or 2 hydroxyl groups, 1 or 2 alkyl or alkoxy (C_1-C_8) groups and/or phenyl; a furane, thiophene or benzothiophene radical, unsubstituted or substituted by halogen and/or alkyl (C_1-C_4), with 1 or 2 substituents in the aggregate thereof, and

20


20

R_1' , R_3' and Me' are as defined above.

A further preferred group of compounds in the method of the invention are the compounds of formula Ic,

25

25



wherein R_2'' is alkyl (C_8-C_{18}); cycloalkyl (C_6-C_8); aralkyl (C_7-C_{10}); aralkyl substituted on the aryl nucleus by a hydroxyl and/or 1 or 2 alkyl (C_1-C_6) groups; phenyl; phenyl substituted by 1 or 2 halogen, hydroxyl, 1 or 2 alkyl or alkoxy (C_1-C_8) groups and/or phenyl with 1 to 3 substituents in the aggregate thereof; or a furane, thiophene or benzothiophene radical unsubstituted or substituted by 1 or 2 halogen atoms or alkyl (C_1-C_4);

30

30

Me'' is nickel, zinc, manganese, copper, chromium or cobalt, and


35

35

R_1' and R_3' are as defined above.

A further preferred group of compounds in the method of the invention are the compounds of formula Id,

12




wherein R_1'' is phenyl or phenyl substituted by alkyl- (C_1-C_4) ,

R_3'' is alkyl (C_1-C_4) or phenyl,

R_2''' is alkyl (C_8-C_{11}) ; cyclohexyl; phenylethyl; phenylethyl substituted on the phenyl nucleus by a hydroxyl group, and/or 1 or 2 alkyl (C_1-C_4) groups; phenyl; phenyl substituted by hydroxyl, 1 or 2 alkyl (C_1-C_4) groups, alkoxy (C_1-C_4) and/or phenyl with 1 to 3 substituents in the aggregate thereof; or a furane, thiophene or benzothiophene radical unsubstituted or substituted by chlorine, methyl or ethyl with 1 or 2 substituents in the aggregate thereof,

and Me'' is as defined above.

The invention also provides new compounds of formula Ie ,




wherein R_2^{iv} is alkyl (C_8-C_{18}) ; a cycloalkyl (C_6-C_{12}) ; aralkyl (C_7-C_{10}) ; aralkyl (C_7-C_{10}) substituted on the aryl nucleus by hydroxyl and/or 1 or 2 alkyl (C_1-C_6) groups; phenyl; phenyl substituted by 1 or 2 halogen atoms, a hydroxyl, 1 or 2 alkyl or alkoxy (C_1-C_6) groups and/or phenyl with 1 to 3 substituents in the aggregate thereof and when exclusively substituted by halogen and Me is hydrogen or an equivalent of a calcium ion, then the phenyl has 2 halogen substituents; a furane, thiophene, benzothiophene, indole, pyridine or quinoxaline radical, unsubstituted or substituted by 1 or 2 halogen atoms, 1 or 2 alkyl or alkoxy (C_1-C_4) groups with 1 or 2 substituents in the aggregate thereof, and

R_1 , R_3 and Me are as defined above,

with the proviso that R_2^{iv} is other than unsubstituted phenyl when R_1 is phenyl or methyl and R_3 is methyl.

Examples of interesting groups of compounds within the scope of formula I are the compounds of formula If ,




wherein R_1^v is alkyl (C_1-C_6) , phenyl or phenyl substituted by alkyl (C_1-C_4) ,

R_2^v is alkyl (C_1-C_{20}) ; cyclohexyl; phenyl or phenylethyl, unsubstituted or substituted on the phenyl nucleus by 1 or 2 alkyl (C_1-C_4) groups, an alkoxy (C_1-C_4) group, a hydroxyl group and/or a phenyl group and bearing 1 to 3 substituents in the aggregate; a thiophene radical unsubstituted or substituted by an alkyl (C_1-C_4) group or chlorine atom; or a quinoxaline radical unsubstituted or disubstituted on the hetero ring thereof by chlorine,

R_3^v is alkyl (C_1-C_4) or phenyl, and


Me is as defined above,

e.g. compounds of formula Ig,



wherein R_1^v , R_3^v and Me are as defined above, and
 R_2^{vi} is alkyl (C_1-C_{20}),

5 compounds of formula Ih,




wherein R_1^v , R_3^v and Me are as defined above, and
 R_2^{vii} is phenyl or phenylethyl, unsubstituted or substituted on the phenyl nucleus
 by 1 or 2 alkyl (C_1-C_4) groups, an alkoxy (C_1-C_4) group, a hydroxyl
 group and/or a phenyl group,

10

10

the compounds of formula Ii,




wherein R_1^v , R_3^v and Me are as defined above, and
 R_2^{viii} is a thiophene radical, unsubstituted or substituted by an alkyl (C_1-C_4)
 group or a chlorine atom;

15

15

and the compounds of formula Ij,



wherein R_1^v , R_3^v and Me are as defined above, and


R_2^{ix} is quinoxaline unsubstituted or disubstituted on the hetero ring thereof by
 chlorine.

20

20

Amongst the preferred compounds of formula Ie are the compounds of formula
 Ie',

14



wherein R_{1vi} is phenyl or phenyl substituted by alkyl (C_1-C_4),


R_{2x} is alkyl (C_5-C_{17}), phenyl, phenylethyl or phenyl or phenylethyl substituted on the phenyl nucleus by 1 or 2 alkyl (C_1-C_4) groups and/or by hydroxyl,

R_{3vi} is alkyl (C_1-C_4), and

$Meiv$ is H or one equivalent of Ni or Mn,

with the proviso that R_{2x} is other than unsubstituted phenyl when R_{1iv} is phenyl and R_{3iv} is methyl.

A particular embodiment of the method of the present invention is the method of stabilizing organic material susceptible to degradation under the effect of heat, oxidation or ultraviolet light which comprises treating said material with a compound of formula Ik,



wherein each of R_{1a} and R_{2a} , independently, is alkyl (C_1-C_{22}); cycloalkyl (C_5-C_{12}); cycloalkyl (C_5-C_{11}) alkyl (C_1-C_7); alkyl (C_1-C_{21}) thioalkyl (C_1-C_{21}) with C_2-C_{22} in the aggregate thereof; cycloalkyl (C_5-C_{11}) alkyl (C_1-C_6) thioalkyl (C_1-C_6) with C_7-C_{18} in the aggregate thereof; aralkyl (C_7-C_{12}); aralkyl (C_7-C_{12}) substituted on the aryl nucleus by hydroxyl, 1 or 2 alkyl (C_1-C_{12}) groups, cycloalkyl (C_5-C_{12}) and/or cycloalkyl (C_5-C_{11}) alkyl (C_1-C_7), the latter group with C_6-C_{12} in the aggregate thereof; phenyl; phenyl substituted by halogen, cyano, hydroxyl, 1 or 2 alkyl (C_1-C_{12}) groups, 1 or 2 alkoxy (C_1-C_{12}) groups, phenyl, $-SO_3H$ and/or a radical R_4-O- or R_4-SO_2- ,


wherein R_4 is phenyl or phenyl substituted by 1 or 2 alkyl (C_1-C_8) groups;

R_{3a} has one of the significances of R_{1a} and R_{2a} or is cyano or $-COOR_5$,

wherein R_5 is alkyl (C_1-C_{12}), cycloalkyl (C_5-C_{12}), cycloalkyl (C_5-C_{11}) alkyl (C_1-C_7), phenyl or phenyl substituted by hydroxy and/or 1 to 2 alkyl (C_1-C_8) groups,

and Me is hydrogen or an equivalent of a bivalent metal ion.

A particular embodiment of the compounds of the present invention consists of the compounds of formula II,




wherein R_{1a} , R_{3a} and Me are as defined above,

and R_{2b} is aralkyl (C_7-C_{10}); aralkyl (C_7-C_{10}) substituted on the aryl nucleus by hydroxyl and/or 1 or 2 alkyl (C_1-C_6) groups; phenyl, or phenyl substituted by halogen, hydroxyl, 1 or 2 alkyl or alkoxy (C_1-C_6) groups and/or phenyl with 1 to 3 substituents is the aggregate thereof;

with the provisos (i) that when Me is hydrogen or an equivalent of a calcium ion, then R_{2b} is other than halogen-substituted phenyl, and (ii) that when R_{1a} is phenyl or methyl and R_{3a} is methyl, then R_{2b} is other than unsubstituted phenyl.

A further particular embodiment of the method of the present invention is the method of stabilizing organic material susceptible to degradation under the effect of heat, oxidation or ultraviolet light which comprises treating said material with a compound of formula Im



wherein R_{1c} is alkyl (C_1-C_{22}); cycloalkyl (C_3-C_{12}); cycloalkyl (C_5-C_{11}) alkyl (C_1-C_7) with C_6-C_{12} in the aggregate thereof; alkyl (C_1-C_{21}) thioalkyl (C_1-C_{21}) with C_2-C_{22} in the aggregate thereof; cycloalkyl (C_5-C_{10}) alkyl (C_1-C_6) thioalkyl (C_1-C_6) with C_7-C_{12} in the aggregate thereof; aralkyl (C_7-C_{12}); aralkyl (C_7-C_{12}) substituted on the aryl nucleus by 1 or 2 hydroxyl groups, 1 or 2 alkyl (C_1-C_{12}) groups, cycloalkyl (C_5-C_{12}) and/or cycloalkyl (C_5-C_{11}) alkyl (C_1-C_7) with C_6-C_{12} in the aggregate thereof; phenyl; phenyl substituted by halogen, cyano, hydroxyl, 1 or 2 alkyl (C_1-C_{12}) groups, 1 or 2 alkoxy (C_1-C_{12}) groups, phenyl, $-SO_3H$ and/or a radical R_4-O- or R_4-SO_2- , wherein R_4 is phenyl or phenyl substituted by 1 or 2 alkyl (C_1-C_8) groups;

R_{2c} is a furane, thiophene, benzothiophene, indole, pyridine or quinoxaline radical, each of which is either unsubstituted or substituted by halogen, alkyl (C_1-C_4) and/or alkoxy (C_1-C_4) with 1 or 2 substituents in the aggregate thereof;

R_{3c} has one of the significances of R_{1c} or is cyano or $-COOR_{6c}$, wherein R_{6c} is alkyl (C_1-C_{12}), cycloalkyl (C_5-C_{12}), cycloalkyl (C_5-C_{11}) alkyl (C_1-C_7) with C_6-C_{12} in the aggregate thereof, phenyl or phenyl substituted by hydroxyl and/or 1 or 2 alkyl (C_1-C_8) groups,

and Me is hydrogen or an equivalent of a bivalent metal ion.

A further particular embodiment of the compounds of the present invention consists of the compounds of formula Im, as defined above.

By the term "halogen" as used herein is meant chlorine and bromine.

Alkyl radicals, unless otherwise stated, are natural or synthesizable primary, secondary, or tertiary, straight or branched chain radicals. Examples of primary radicals are methyl, ethyl, *n*-propyl, *n*-butyl, *n*-pentyl, *n*-hexyl, *n*-heptyl, *n*-octyl, *n*-nonyl, *n*-undecyl, *n*-dodecyl, *n*-hexadecyl, *n*-heptadecyl, *n*-octadecyl and *n*-docosanyl.

Examples of secondary alkyl radicals are isopropyl, 2-butyl, 3-methyl-2-butyl, 2-pentyl, 2-hexyl, 3-hexyl, 2-methyl-3-pentyl, 3-octyl, 4-octyl, 2-decyl, 5-decyl, 2,2-dimethyl-3-octyl, 2-heptadecyl, 2-hexadecyl and 2-nonadecyl.

Examples of tertiary alkyl radicals are tertiary butyl, 3-methyl-3-hexyl, 1-methyl-cyclohexyl and tertiary octyl.

Examples of branched alkyl radicals are 2-methyl-1-propyl, 2,2-dimethyl-1-propyl, 2-methyl-1-butyl, and 2,2-dimethyl-1-decyl.

Examples of cycloalkyl radicals are cyclopentyl, cyclohexyl, cycloheptyl, 2-, 3- or 4-methyl-cyclohexyl, cyclooctyl and cyclododecyl.


The term "cycloalkyl" as used herein includes a cycloalkyl ring bearing alkyl substituents.

Examples of cycloalkylalkyl are cyclohexyl-methyl, cyclohexyl-ethyl and cycloheptyl-methyl.



Examples of aralkyl radicals are benzyl and 2-phenylethyl.

Examples of radicals, where the aliphatic chain is interrupted by sulphur are 2-methylthioethyl, 2-dodecylthioethyl and methyl-thiomethyl.



Examples of substituted phenyl radicals are:




16



Examples of unsubstituted and substituted furane, thiophene, benzothiophene, indole, pyridine and quinoxaline radicals are:



The present invention also provides a process for producing a compound of formula Ie, which comprises condensing a compound of formula III,



10 wherein R_1 and R_3 are as defined above, with a compound of formula II, 10



II

15 wherein R_2^{IV} is as defined above, preferably in an equimolar ratio and, when Me signifies an equivalent of a metal ion, converting the resulting product into the corresponding Me-salt. 15

The reaction is preferably effected in an inert organic solvent and the starting materials may be dissolved or suspended therein. The solution is preferably heated to between 20° and 110°C with the cleavage of hydrochloric acid which may be allowed to escape from the reaction vessel at an elevated temperature. Generally, it is, however, more convenient to effect the reaction in the presence of an acid binding agent, e.g. CaO, an alkali metal carbonate or bicarbonate, pyridine, a trialkyl amine or a dialkyl aniline. The reaction is preferably carried out in the absence of moisture. Appropriate solvents are, for example, benzene, xylene, cymol, diphenyl ether, tetrahydrofuran and dioxane. When Me signifies a bivalent metal ion, the compound of formula I, wherein Me signifies hydrogen, may be converted first into the alkali metal salt, e.g. by dissolving the compound of formula I in alcohol and adding an alkali hydroxide such as NaOH or KOH. A Me- salt, e.g. the chloride, is subsequently added to the reaction mixture and the desired product is then obtained. 20 25

Alternatively and preferably, a metal salt may be produced directly from the compound of formula I, wherein Me signifies hydrogen, by heating the compound of formula I wherein Me is hydrogen with an Me- acetate, e.g. the acetate of nickel, zinc, manganese, cobalt, copper, calcium or barium. This reaction is preferably effected in an alcohol such as methanol, ethanol and propanol, at a temperature between room temperature and the reflux temperature of the solvent. On cooling the product generally precipitates. 30 35

If the product does not precipitate sufficiently, the precipitation may be accelerated by the addition of water.

The compounds of formula I are useful for stabilizing organic material susceptible to degradation under the effect of heat, oxidation or u.v. light by a method comprising treating the organic material with a compound of formula I. By the term "treating" 40

is meant either surface coating or incorporation into the body of the organic material, in manner known *per se*.

The above method also forms part of the present invention.

5 The method of the invention comprises treating the organic material, either by way of coating the compound of formula I as a film on the surface of the organic material, or by way of mixing the compound of formula I with the organic material, preferably the latter so as to uniformly distribute the compound of formula I throughout the body of the organic material. Thus, according to a first embodiment the method may be effected by intimately mixing the stabilizer with a particulate form of, 10 for example, a plastics material such as polypropylene, e.g. polypropylene granules, in a kneader or other suitable device, to obtain uniform distribution of the stabilizer throughout the plastics material. The plastics material may thereafter be formed into final shape, e.g. by extrusion or injection moulding. By such method, homogeneous distribution of the stabilizer throughout the plastics material is achieved which is 15 important for good protection.

According to a second embodiment, organic material in final form, for example, a textile filament, is passed through a dispersion of the stabilizer, e.g. in aqueous medium, to provide a protective coating of the stabilizer as a surface film on the organic material. Textile filaments or fabrics of polyethylene terephthalate or cellulose acetate are suited to this mode of application. 20

According to a third embodiment of the method of the present invention, particularly suited to stabilization of polymers or copolymers, e.g. polypropylene, the stabilizer is mixed with the monomer or prepolymer before polymerisation or, as the case may be, copolymerisation, is effected, to yield the polymer or copolymer having the stabilizer uniformly distributed therethrough. The polymer or copolymer may thereafter be extruded, moulded or otherwise formed into final shape. 25

Examples of organic materials susceptible to degradation and embraced by the method of the present invention are cellulose derivatives, such as cellulose acetate, cellulose acetobutyrate, ethyl cellulose, cellulose nitrate and cellulose propionate, plastics materials, such as polyalkylenes, notably polyethylene and polypropylene, polyvinyl derivatives, e.g. polyvinyl chloride, polyvinyl chloride acetate and polyvinyl alcohol, polyamides, polyesters, polyacrylonitrile, polystyrene, silicon rubber, melamine-formaldehyde resins, urea-formaldehyde resins, allyl casting resins, polymethylmethacrylate, polypropylene oxide, polyphenylene oxide, polyurethanes and copolymers, e.g. acrylonitrile-butadiene-styrene copolymers, and natural products, such as natural rubber, cellulose, wool and silk. 30 35

The compounds according to the invention are preferably used for the stabilization of plastics materials such as polypropylene, polyethylene, polyester, polyamide, polyurethanes, polyacrylonitrile, copolymers such as acrylonitrile-butadiene-styrene (ABS) terpolymer, acrylic ester-styrene-acrylonitrile terpolymer, styrene-acrylonitrile copolymer or styrene-butadiene copolymer. 40

Stabilized organic materials according to the invention may exist in solid form, e.g. panels, rods, coatings, sheets, films, tapes, fibres, granules or powders, or in liquor form, e.g. solutions, emulsions or dispersions. 45

The amount of stabilizer employed in the method of the present invention will of course vary with the mode of application, the compound employed and the nature of the organic material to be treated. In general, however, satisfactory results are obtained when the amount of stabilizer employed is between 0.01 and 5%, preferably between 0.05 and 1% of the weight of organic material to be treated. 50


The compounds of formula I may be employed in formulation form for the stabilization of organic materials, in association with an inert carrier or diluent. Such formulations may be in the form of polishes, creams and lotions, e.g. for surface application to the organic material so as to form a barrier or filter coating. Such formulations also form part of the present invention. 55

In the following Examples the parts and percentages are by weight and the temperatures in degrees centigrade. The indicated structures are verified by microanalysis and spectroscopic analysis. 60

EXAMPLE 1.

A mixture of 17.4 parts of 1-phenyl-3-methyl-pyrazolone (5), 11.2 parts of CaO and 19.6 parts of 4-tert.butyl-benzoyl chloride is boiled at reflux in 100 parts of dioxane over the course of 30 minutes. The obtained thick slurry is poured into 200 parts of water, at room temperature and with stirring. The resulting brown solution 60

is acidified with diluted hydrochloric acid, the preprecipitate is filtered by suction, washed to neutral, dried and crystallized from methanol. The compound of formula




is obtained. M.P.: 107—109°C.

In order to produce the nickel salt, 10 parts of the resulting compound are dissolved in 20 parts of methanol and the stoichiometric amount of nickel acetate is added. The mixture is then heated to 70°C over the course of 30 minutes and allowed to cool. The green precipitate is filtered by suction, washed with methanol/water 1:1 and dried at 110°C. M.P.: 205°C. A practically quantitative yield is obtained.

The salts of zinc, manganese, cobalt, copper, calcium or barium are obtained by analogy.

EXAMPLE 2.

A mixture of 8.26 parts of 1,3-diphenyl-pyrazolone (5), 3.92 parts of CaO and 9.38 parts of 3,5-di-tert.butyl-4-hydroxybenzoyl chloride is boiled at reflux in 100 parts of dioxane over the course of 2 hours. The mixture is subsequently cooled to room temperature and poured into a solution consisting of 50 parts of 2N hydrochloric acid and 100 parts of ice water. The precipitate is filtered by suction, washed until neutral and crystallized from methanol. The compound of formula




is obtained. M.P.: 187—188°C.

The nickel salt may be produced in analogy with Example 1.

EXAMPLE 3.

3.75 Parts of 1,3 - diphenyl - 4[3',5' - di - tert.butyl - 4' - hydroxy]benzoyl-5 - hydroxy - pyrazole are entered into 60 parts of ethanol and the mixture is heated to 45°. 4 Parts of 2N sodium chloride solution are added at the same temperature. After 10 minutes a solution of 0.94 parts of $\text{NiCl}_2 \cdot 6\text{H}_2\text{O}$ in 20 parts of ethanol is added to the mixture. The solution immediately turns green and KCl is precipitated. After 30 minutes of reaction the KCl is filtered off and the green solution evaporated. The solid residue is washed with water, filtered by suction and dried at 120°. The compound of the formula




is obtained. M.P.: 250°C.

EXAMPLE 4.

34.8 Parts of 1 - phenyl - 3 - methyl - pyrazolone (5) and 13.2 parts of CaO are entered at room temperature into 40.0 parts of dioxane. The mixture is then heated to 80°C in an oil bath. 43.7 Parts of lauric acid chloride are added dropwise at 75°C with stirring. The acid chloride is added over the course of 45 minutes. The temperature is raised to 95°C and a thick, brown well stirrable paste is obtained. After


the addition of the acid chloride the mixture is allowed to react at 80°C for 1 hour and is then cooled to 50°C. 100 parts of methanol and 23.0 parts of hydrochloric acid are successively added. After the addition of the hydrochloric acid the mixture is stirred for 30 minutes and 24.8 parts of nickel acetate are added. The mixture is stirred at reflux for 30 minutes (internal temperature: 70°C). The precipitated nickel complex is filtered by suction at 50°C, washed until free from halogen with 1.5 parts of water and then washed twice with 30 parts of methanol each time and dried at 110°C. M.P.: 144—148°C. The nickel salt of the compound of formula



is obtained. The corresponding zinc, cobalt, manganese, copper, calcium or barium complex is produced in analogy with Example 1 or 3.

EXAMPLE 5.


A mixture of 53.3 g of 1-phenyl-3-methyl-pyrazolone (5), 18.5 g of CaO and 44.0 g of thiophene-2-carboxylic acid chloride is stirred in 120 cc of dioxane at 95°C over the course of 2 hours. After cooling to 50°C, 100 cc of methanol and 30 cc of concentrated hydrochloric acid are successively added. The mixture is then stirred for a further 30 minutes. The mixture is then poured into 500 cc of ice water, whereupon a voluminous precipitate is obtained. The precipitate is filtered by suction, washed with water and crystallized from methanol. M.P.: 133—136°C. The compound of formula



is obtained.

EXAMPLE 6.


A mixture consisting of 20.2 g of 1-phenyl-3-n-propyl-pyrazolone (5) and 6.2 g of CaO is heated to 75°C in 80 cc of dioxane; 14.7 g of thiophene-2-carboxylic acid chloride are added with stirring at the same temperature over the course of 15 minutes, whereupon the reaction temperature rises to 95°C. The mixture is allowed to react at 95°C for 1 hour and the dioxane is subsequently distilled off. To the resulting thick, brown slurry are added 100 cc of methanol and 10 cc of concentrated hydrochloric acid and the mixture is kept under reflux for 30 minutes. The obtained clear, brown solution is poured on 200 cc of ice water. The reaction product precipitates. The precipitate is filtered by suction, washed with water and crystallized from ethanol. M.P.: 124—128°C. The compound of formula



is obtained.

EXAMPLE 7.


5.0 g of Nickel acetate 6H₂O are added at 45°C to 12.5 g of the compound of Example 6 in 100 cc of methanol. The mixture is stirred for 1 hour without further heating. The green precipitate is filtered by suction, washed with water and dried at 90°C. M.P.: 145—155°C. The compound of formula



is obtained.

EXAMPLE 8.


To 18.8 g of 1 - p - tolyl - 3 - methyl - pyrazolone (5) and 6.18 g of CaO in 100 cc of dioxane there are added with stirring at 90°C over the course of 30 minutes 14.7 g of thiophene-2-carboxylic acid chloride. The dioxane is subsequently distilled off in a water-jet vacuum. 30 cc of methanol and 10 cc of concentrated hydrochloric acid are added at 60°C to the resulting thick paste which is boiled under reflux over the course of 30 minutes. 11.8 g of nickel acetate 6H₂O are then added, the mixture is stirred for a further 30 minutes and subsequently cooled to room temperature. The green precipitate is filtered by suction, washed with water and dried. M.P.: 180—184°C. The compound of formula



is obtained.

EXAMPLE 9.


A solution of 1.6 g of NaOH in 10 cc of water is added at 45°C to 11.4 g of the compound of Example 5 in 100 cc of methanol and the mixture is stirred for 30 minutes. 4.6 g of NiCl₂ · 6H₂O, dissolved in 20 cc of water, are then added to the yellow solution. After the addition of the nickel chloride a green precipitate is obtained which is filtered by suction at room temperature, washed with water and dried. M.P.: 175—180°C. The compound of formula



is obtained.

EXAMPLE 10.

5.0 g of Cobalt (II) acetate are added with stirring at 45°C to 11.4 g of the compound of Example 5 in 150 cc of methanol. After the addition of the salt a precipitate is obtained. The yellow precipitate is filtered by suction at room temperature, washed with water and dried. M.P.: 165—170°C. The compound of formula









is obtained.

The compounds indicated in Tables 1, 2, 3 and 4 are produced in analogous manner to that described in Examples 1 to 10.

21

TABLE 1

			
Ex. No.	R ₁	R ₃	R ₂
11		CH ₃	
12		CH ₃	
13		CH ₃	
14		CH ₃	
15		CH ₃	
16		CH ₃	-C ₈ H ₁₇ (n)
17		CH ₃	-C ₁₇ H ₃₅ (n)
18		CH ₃	

22

TABLE 1 (Continued)

















Ex. No.	R ₁	R ₃	R ₂
19			
20			
21			$-C_8H_{17}(n)$
22			
23			$n-C_{11}H_{23}$
24	CH_3	CH_3	
25		CH_3	
26		CH_3	
27		C_3H_7-n	

TABLE 2

			
Ex. No.	R ₃	R ₂	Me
28	CH ₃		Ca
29	CH ₃		Ni
30	CH ₃		Mn
31	CH ₃		Cu
32	CH ₃		Ca
33	CH ₃		Ni
34	CH ₃		Cu
35	CH ₃		Ni

24

TABLE 2 (Continued)

Ex. No.	R ₃	R ₂	Me
36	CH ₃		Cu
37	CH ₃		Mn
38	CH ₃	-C ₈ H ₁₇ (n)	Ni
39	CH ₃		Ni
40	CH ₃		Cu
41	CH ₃		Zn
42	CH ₃		Ni
43	CH ₃		Mn

25

TABLE 2 (Continued)





Ex. No.	R ₃	R ₂	Me
44	CH ₃		Mn
45	CH ₃		Zn
46	CH ₃		Ni
47	CH ₃		Ni
48	nC ₃ H ₇ -	nC ₁₁ H ₂₃	Ni
49	nC ₃ H ₇ -	nC ₁₁ H ₂₃	Mn
50	nC ₃ H	nC ₁₁ H ₂₃	Zn
51	nC ₃ H ₇ -		Ni
52	nC ₃ H ₇ -		Mn
53		C ₈ H ₁₇ (n)	Ni
54		C ₁₁ H ₂₃ (n)	Ni



TABLE 2 (Continued)

Ex. No.	R ₃	R ₂	Me
55		nC ₁₁ H ₂₃	Mn
56			Zn
57	do.	do.	Mn
58	do.	do.	Cu
59	do.		Ni
60	do.		Mn
61	do.	do.	Zn
62	do.	H ₃ C-	Mn
63	do.		Ni
64	CH ₃		Ni

27

TABLE 2 (Continued)

Ex. No.	R ₃	R ₂	Me
65	CH ₃		Cr
66	do.	do.	Zn
67	do.	do.	Mn
68	n-C ₃ H ₇	do.	Ni
69	do.	do.	Zn
70	do.	do.	Co
71	CH ₃	C ₁₃ H ₂₇	Cu
72	do.	C ₁₃ H ₂₇	Ni
73	do.	C ₁₅ H ₃₁	Cu
74	do.	C ₁₅ H ₃₁	Ni
75	do.	C ₁₇ H ₃₅	Cu
76	do.	C ₁₇ H ₃₅	Ni

TABLE 3






			
Ex. No.	R ₁	R ₃	R ₂
77			
78	do.	do.	
79	do.	do.	
80	do.	.CH ₃ -	
81		CH ₃ -	do.
82		n-C ₃ H ₇	do.

TABLE 4


				
Ex. No.	R ₁	R ₃	Me	R ₂
83		CH ₃	Zn	
84	do.	do.	Mn	do.
85	do.	do.	Ca	do.
86	do.	do.	Cu	do.
87	do.	nC ₃ H ₇	Mn	do.
88	do.	do.	Zn	do.
89	do.	do.	Cr	do.
90	H ₃ C- 	CH ₃	Cr	do.
91	do.	do.	Mn	do.
92	do.	do.	Zn	do.
93			Ni	
94			Mn	do.
95	CH ₃	CH ₃	Ni	do.

TABLE 4 (Continued)







Ex. No.	R ₁	R ₃	Me	R ₂
96	CH ₃	CH ₃	Cr	
97		do.	Ni	
98	do.	do.	Cr	do.
99	do.	do.	Mn	do.
100	do.	do.	Ni	
101	do.	do.	Mn	do.
102	do.	nC ₃ H ₇ —	H	do.
103	do.	do.	Ni	do.
104	do.	do.	Mn	do.
105		CH ₃	Ni	
106	do.	do.	Zn	do.
107		CH ₃	Ni	do.
108	do.	do.	Zn	do.
109	do.	do.	Mn	do.

TABLE 4 (Continued)

Ex. No.	R ₁	R ₃	Me	R ₂
110		CH ₃	Ni	
111	do.	do.	Zn	do.
112	CH ₃	CH ₃	Ni	
113	do.	do.	Zn	do.
114	do.	do.	Co	do.


METHOD EXAMPLE.

6 samples of unstabilized polypropylene and 0.5% by weight of the compound of Examples numbers 9, 17, 25, 28, 43 and 52, respectively, are intimately kneaded on a roll mill at 180°. Each sample is extruded into a sheet of 0.3 mm thickness. The compounds are incorporated into unstabilized polyvinyl chloride using 0.5% of the compound and the resulting mixtures are extruded into sheets in an analogous manner.

Polyethylene, acrylonitrile-butadiene-styrene terpolymers, polyethylene terephthalate, cellulose acetobutyrate, polyamide 6, polystyrene, polycarbonate and polyurethane are similarly stabilized by incorporation of the compounds of formula I.



WHAT WE CLAIM IS:—

1. A method of stabilizing organic material susceptible to degradation under the effect of heat, oxidation or ultraviolet light which comprises treating said material with a compound of formula I,



wherein R₁ is alkyl (C₁—C₂₂); cycloalkyl (C₅—C₁₂); cycloalkyl (C₅—C₁₁) alkyl (C₁—C₇); alkyl (C₁—C₂₁) thioalkyl (C₁—C₂₁) with C₂—C₂₂ in the aggregate thereof; cycloalkyl (C₅—C₁₁) alkyl (C₁—C₆) thioalkyl-(C₁—C₆) with C₇—C₁₈ in the aggregate thereof; aralkyl (C₇—C₁₂); aralkyl (C₇—C₁₂) substituted on the aryl nucleus by 1 or 2 hydroxyl groups, 1 or 2 alkyl (C₁—C₁₂) groups, cycloalkyl (C₅—C₁₂) and/or cycloalkyl (C₅—C₁₁) alkyl (C₁—C₁₁); phenyl; phenyl substituted by 1 to 3 halogen atoms, cyano, 1 or 2 hydroxyl groups, 1 or 2 alkyl (C₂—C₁₂) groups, 1 or 2 alkoxy (C₁—C₁₂) groups, phenyl, —SO₃H and/or a radical R₄—O— or R₄—SO₂—, wherein R₄ is phenyl or phenyl substituted by 1 or 2 alkyl (C₁—C₆) groups; R₂ has one of the significances of R₁ or is a furane, thiophene, benzothiophene, indole, pyridine or quinoxaline radical, each of which is either unsubstituted

TABLE 4 (Continued)

Ex. No.	R ₁	R ₃	Me	R ₂
110		CH ₃	Ni	
111	do.	do.	Zn	do.
112	CH ₃	CH ₃	Ni	
113	do.	do.	Zn	do.
114	do.	do.	Co	do.


METHOD EXAMPLE.

6 samples of unstabilized polypropylene and 0.5% by weight of the compound of Examples numbers 9, 17, 25, 28, 43 and 52, respectively, are intimately kneaded on a roll mill at 180°. Each sample is extruded into a sheet of 0.3 mm thickness. The compounds are incorporated into unstabilized polyvinyl chloride using 0.5% of the compound and the resulting mixtures are extruded into sheets in an analogous manner.

Polyethylene, acrylonitrile-butadiene-styrene terpolymers, polyethylene terephthalate, cellulose acetobutyrate, polyamide 6, polystyrene, polycarbonate and polyurethane are similarly stabilized by incorporation of the compounds of formula I.

WHAT WE CLAIM IS:—

1. A method of stabilizing organic material susceptible to degradation under the effect of heat, oxidation or ultraviolet light which comprises treating said material with a compound of formula I,



I

wherein R₁ is alkyl (C₁—C₂₂); cycloalkyl (C₃—C₁₂); cycloalkyl (C₃—C₁₁) alkyl (C₁—C₇); alkyl (C₁—C₂₁) thioalkyl (C₁—C₂₁) with C₂—C₂₂ in the aggregate thereof; cycloalkyl (C₃—C₁₁) alkyl (C₁—C₆) thioalkyl-(C₁—C₆) with C₇—C₁₃ in the aggregate thereof; aralkyl (C₇—C₁₂); aralkyl (C₇—C₁₂) substituted on the aryl nucleus by 1 or 2 hydroxyl groups, 1 or 2 alkyl (C₁—C₁₂) groups, cycloalkyl (C₃—C₁₂) and/or cycloalkyl (C₃—C₁₁) alkyl (C₁—C₁₁); phenyl; phenyl substituted by 1 to 3 halogen atoms, cyano, 1 or 2 hydroxyl groups, 1 or 2 alkyl (C₂—C₁₂) groups, 1 or 2 alkoxy (C₁—C₁₂) groups, phenyl, —SO₃H and/or a radical R₄—O— or R₄—SO₂—, wherein R₄ is phenyl or phenyl substituted by 1 or 2 alkyl (C₁—C₆) groups; R₂ has one of the significances of R₁ or is a furane, thiophene, benzothiophene, indole, pyridine or quinoxaline radical, each of which is either unsubstituted



39

23

1,474,281

23


or substituted by halogen, alkyl (C_1-C_4) and/or alkoxy (C_1-C_4) with 1 or 2 substituents in the aggregate thereof;

R_3 has one of the significances of R_1 or is cyano or $-COOR_3$,

wherein R_3 is alkyl (C_1-C_{12}), cycloalkyl (C_3-C_{12}), cycloalkyl (C_6-C_{11}) alkyl (C_1-C_7), phenyl or phenyl substituted by hydroxy and/or 1 to 2 alkyl (C_1-C_8) groups,

and Me is hydrogen or an equivalent of a bivalent metal ion.

2. A method according to Claim 1, wherein said material is treated with a compound of formula Ia,




Ia

wherein R_1' and R_3' are each independently, alkyl (C_1-C_8), phenyl or phenyl substituted by halogen and/or 1 or 2 alkyl (C_1-C_4) groups,

Me' is hydrogen or an equivalent of nickel, zinc, manganese, copper, chromium, calcium, barium or cobalt, and

R_2 is as defined in Claim 1.

3. A method according to Claim 2, wherein said material is treated with a compound of formula Ib,




Ib

wherein R_2' is alkyl (C_6-C_{18}); cycloalkyl (C_6-C_8); aralkyl (C_7-C_{10}); aralkyl (C_7-C_{10}) substituted on the aryl nucleus by hydroxyl and/or 1 or 2 alkyl (C_1-C_6) groups; phenyl; phenyl substituted by 1 to 3 halogen atoms, 1 or 2 hydroxyl groups, 1 or 2 alkyl or alkoxy (C_1-C_6) groups and/or phenyl; a furane, thiophene or benzothiophene radical, unsubstituted or substituted by halogen and/or alkyl (C_1-C_4), with 1 or 2 substituents in the aggregate thereof, and

R_1' , R_3' and Me' are as defined in Claim 2.

4. A method according to Claim 3, wherein said material is treated with a compound of formula Ic,




Ic

wherein R_2'' is alkyl (C_6-C_{18}); cycloalkyl (C_6-C_8); aralkyl (C_7-C_{10}); aralkyl substituted on the aryl nucleus by a hydroxyl and/or 1 or 2 alkyl (C_1-C_6) groups; phenyl; phenyl substituted by 1 or 2 halogen, hydroxyl, 1 or 2 alkyl or alkoxy (C_1-C_6) groups and/or phenyl with 1 to 3 substituents in the aggregate thereof; or a furane, thiophene or benzothiophene radical unsubstituted or substituted by 1 or 2 halogen atoms or alkyl (C_1-C_4);

Me'' is nickel, zinc, manganese, copper, chromium or cobalt, and

R_1' and R_3' are as defined in Claim 2.

5. A method according to Claim 4, wherein said material is treated with a compound of formula Id,




wherein R_1'' is phenyl or phenyl substituted by alkyl- (C_1-C_4) ,

R_3'' is alkyl (C_1-C_4) or phenyl,

R_2'' is alkyl (C_8-C_{11}) ; cyclohexyl; phenylethyl; phenylethyl substituted on the phenyl nucleus by a hydroxyl group, and/or 1 or 2 alkyl (C_1-C_4) groups; phenyl; phenyl substituted by hydroxyl, 1 or 2 alkyl (C_1-C_4) groups, alkoxy (C_1-C_4) and/or phenyl with 1 to 3 substituents in the aggregate thereof; or a furane, thiophene or benzothiophene radical unsubstituted or substituted by chlorine, methyl or ethyl with 1 or 2 substituents in the aggregate thereof,

and Me'' is as defined in Claim 4.

6. A method according to Claim 1, wherein said material is treated with a compound of formula If,




wherein R_1^v is alkyl (C_1-C_6) , phenyl or phenyl substituted by alkyl (C_1-C_4) ,

R_2^v is alkyl (C_1-C_{20}) ; cyclohexyl; phenyl or phenylethyl, unsubstituted or substituted on the phenyl nucleus by 1 or 2 alkyl (C_1-C_4) groups, an alkoxy (C_1-C_4) group, a hydroxyl group and/or a phenyl group and bearing 1 to 3 substituents in the aggregate; a thiophene radical unsubstituted or substituted by an alkyl (C_1-C_4) group or chlorine atom; or a quinoxaline radical unsubstituted or disubstituted on the hetero ring thereof by chlorine,

R_3^v is alkyl (C_1-C_4) or phenyl, and

Me is as defined in Claim 1.


7. A method according to Claim 6, wherein said material is treated with a compound of formula Ig,



wherein R_1^v , R_3^v and Me are as defined in Claim 6, and

R_2^{vi} is alkyl (C_1-C_{20}) .

8. A method according to Claim 6, wherein said material is treated with a compound of formula Ih,



wherein R_1^v , R_3^v and Me are as defined in Claim 6, and



34

25

1,474,281


25

R_2^{vii} is phenyl or phenylethyl, unsubstituted or substituted on the phenyl nucleus by 1 or 2 alkyl (C_1-C_4) groups, an alkoxy (C_1-C_4) group, a hydroxyl group and/or a phenyl group.

5

9. A method according to Claim 6, wherein said material is treated with a compound of formula Ii,

5




wherein R_1^v , R_3^v and Me are as defined in Claim 6, and

R_2^{viii} is a thiophene radical, unsubstituted or substituted by an alkyl (C_1-C_4) group or a chlorine atom.

10

10. A method according to Claim 6, wherein said material is treated with a compound of formula Ij,

10



wherein R_1^v , R_3^v and Me are as defined in Claim 6, and

R_2^{ix} is a quinoline radical, unsubstituted or disubstituted on the hetero ring thereof by chlorine.

15

11. A method according to any one of the preceding claims, wherein the compound of formula I is incorporated into the body of the organic material.

15

12. A method according to any one of the preceding claims, wherein the organic material is selected from cellulose derivatives, plastics materials and natural products.

20

13. A method according to Claim 12, wherein the organic material is a plastics material.

20

14. A method according to Claim 13, wherein the plastics material is selected from polypropylene, polyethylene, polyester, polyamide, polyurethane, polyacrylonitrile, acrylonitrile-butadiene-styrene (ABS) terpolymer, acrylic ester-styrene-acrylonitrile terpolymer, styrene-acrylonitrile copolymer and styrene-butadiene copolymer.

25

25

15. A method according to any one of the preceding claims, wherein the amount of compound of formula I employed is between 0.05 and 1% of the weight of the organic material to be treated.

30

16. A method according to Claim 1, substantially as described herein with reference to the Method Example.

30


17. Organic material susceptible to degradation under the effect of heat, oxidation or u.v. light, whenever treated by the method of any one of the preceding claims.

35

18. Organic material according to Claim 17, substantially as described herein with reference to the Method Example.

35

19. A compound of formula Ia,




wherein R_1 is alkyl (C_1-C_{22}); cycloalkyl (C_3-C_{12}); cycloalkyl (C_5-C_{11}) alkyl (C_1-C_7); alkyl (C_1-C_{21}) thioalkyl (C_1-C_{21}) with C_2-C_{22} in the

40


40

- 5 aggregate thereof; cycloalkyl (C_6-C_{11}); alkyl (C_1-C_6); thioalkyl- (C_1-C_6) with C_7-C_{18} in the aggregate thereof; aralkyl (C_7-C_{12}); aralkyl (C_7-C_{12}) substituted on the aryl nucleus by 1 or 2 hydroxyl groups, 1 or 2 alkyl (C_1-C_{12}) groups, cycloalkyl (C_6-C_{12}) and/or cycloalkyl (C_5-C_{11}) alkyl (C_1-C_{11}); phenyl; phenyl substituted by 1 to 3 halogen atoms, cyano, 1 or 2 hydroxy groups; 1 or 2 alkyl (C_1-C_{12}) groups, 1 or 2 alkoxy (C_1-C_{12}) groups, phenyl, $-SO_3H$ and/or a radical R_4-O- or R_4-SO_2- ,
 10 R_2^{IV} is phenyl or phenyl substituted by 1 or 2 alkyl (C_1-C_8) groups; R_2^{IV} is alkyl (C_1-C_{18}); cycloalkyl (C_6-C_{12}); aralkyl (C_7-C_{10}); aralkyl (C_7-C_{10}) substituted on the aryl nucleus by hydroxyl and/or 1 or 2 alkyl (C_1-C_8) groups; phenyl; phenyl substituted by 1 or 2 halogen atoms, a hydroxyl, 1 or 2 alkyl or alkoxy- (C_1-C_8) groups and/or phenyl with 1 to 3 substituents in the aggregate thereof and when exclusively substituted by halogen and Me is hydrogen or an equivalent of a calcium ion, then the phenyl has 2 halogen substituents; a furane, thiophene, benzothiophene, indole, pyridine or quinoxaline radical, unsubstituted or substituted by 1 or 2 halogen atoms, 1 or 2 alkyl or alkoxy- (C_1-C_4) groups with 1 or 2 substituents in the aggregate thereof, and
 15 R_3 has one of the significances of R_1 or is cyano or $-COOR_5$,
 20 wherein R_5 is alkyl (C_1-C_{12}), cycloalkyl (C_6-C_{12}), cycloalkyl (C_5-C_{11}) alkyl (C_1-C_7), phenyl or phenyl substituted by hydroxy and/or 1 to 2 alkyl (C_1-C_8) groups,
 and Me is hydrogen or an equivalent or a bivalent metal ion,
 25 with the proviso that R_2^{IV} is other than unsubstituted phenyl when R_1 is phenyl or methyl and R_3 is methyl.

20. A compound according to Claim 19, of formula 1e',



- 30 wherein R_1^{VI} is phenyl or phenyl substituted by alkyl (C_1-C_4),
 R_2^X is alkyl (C_8-C_{17}), phenyl, phenylethyl or phenyl substituted on the phenyl nucleus by 1 or 2 alkyl (C_1-C_4) groups and/or by hydroxyl,
 R_3^{VI} is alkyl (C_1-C_4), and
 Me^{IV} is H or one equivalent of Ni or Mn,
 35 with the proviso that R_2^X is other than unsubstituted phenyl when R_1^{VI} is phenyl and R_3^{VI} is methyl.
 21. A compound of formula Ie, as defined in Claim 19, substantially as described herein with reference to any one of Examples 1 to 17, 19 to 27 and 32 to 114.
 22. A process for producing a compound of formula Ie, as defined in Claim 19, which comprises condensing a compound of formula III,



wherein R_1 and R_3 are as defined in Claim 19,
 with a compound of formula II,




II

- 45 wherein R_2^{IV} is as defined in Claim 19,
 and, when Me signifies an equivalent of a metal ion, converting the resulting product into the corresponding Me- salt.

23. A process according to Claim 22, substantially as described herein with reference to any one of Examples 1 to 17, 19 to 27 and 32 to 114.

24. A compound of formula Ie, as defined in Claim 19, whenever produced by a process according to Claim 22 or Claim 23.

25. A method of stabilizing organic material susceptible to degradation under the effect of heat, oxidation or ultraviolet light which comprises treating said material with a compound of formula Ik,



Ik


wherein each of R_{1a} and R_{2a} , independently, is alkyl (C_1-C_{22}); cycloalkyl (C_6-C_{12}); cycloalkyl (C_5-C_{11}); alkyl (C_1-C_7); alkyl (C_1-C_{21}); thioalkyl (C_1-C_{21}) with C_2-C_{22} in the aggregate thereof; cycloalkyl (C_6-C_{11}); alkyl (C_1-C_6); thioalkyl (C_1-C_6) with C_7-C_{18} in the aggregate thereof; aralkyl (C_7-C_{12}) substituted on the aryl nucleus by hydroxyl, 1 or 2 alkyl (C_1-C_{12}) groups, cycloalkyl (C_6-C_{12}) and/or cycloalkyl (C_5-C_{11}); alkyl (C_1-C_7), the latter group with C_8-C_{12} in the aggregate thereof; phenyl; phenyl substituted by halogen, cyano, hydroxyl, 1 or 2 alkyl (C_1-C_{12}) groups, 1 or 2 alkoxy (C_1-C_{12}) groups, phenyl, $-SO_3H$ and/or a radical R_4-O- or R_4-SO_2- ,

wherein R_4 is phenyl or phenyl substituted by 1 or 2 alkyl (C_1-C_8) groups; R_{3a} has one of the significances of R_{1a} and R_{2a} or is cyano or $-COOR_5$,

wherein R_5 is alkyl (C_1-C_{12}), cycloalkyl (C_6-C_{12}), cycloalkyl (C_5-C_{11}), alkyl (C_1-C_7), phenyl or phenyl substituted by hydroxy and/or 1 to 2 alkyl (C_1-C_8) groups,

and Me is hydrogen or an equivalent of a bivalent metal ion.

26. A compound of formula II,




Ie

wherein R_{1a} , R_{3a} and Me are as defined in Claim 25,

and R_{2b} is aralkyl (C_7-C_{10}); aralkyl (C_7-C_{10}) substituted on the aryl nucleus by hydroxyl and/or 1 or 2 alkyl (C_1-C_6) groups; phenyl, or phenyl substituted by halogen, hydroxyl, 1 or 2 alkyl or alkoxy (C_1-C_8) groups and/or phenyl with 1 to 3 substituents is the aggregate thereof;

with the provisos (i) that when Me is hydrogen or an equivalent of a calcium ion, then R_{2b} is other than halogen-substituted phenyl, and (ii) that when R_{1a} is phenyl or methyl and R_{3a} is methyl, then R_{2b} is other than unsubstituted phenyl.

27. A method of stabilizing organic material susceptible to degradation under the effect of heat, oxidation or ultraviolet light which comprises treating said material with a compound of formula Im



Im

37



wherein R_{1c} is alkyl (C_1-C_{22}); cycloalkyl (C_5-C_{12}); cycloalkyl (C_6-C_{11}) alkyl
(C_1-C_7) with C_6-C_{12} in the aggregate thereof; alkyl (C_1-C_{21}) thioalkyl
(C_1-C_{21}) with C_2-C_{22} in the aggregate thereof; cycloalkyl (C_5-C_{10})
5 alkyl (C_1-C_6) thioalkyl (C_1-C_6) with C_7-C_{12} in the aggregate thereof;
aralkyl (C_7-C_{12}); aralkyl (C_7-C_{12}) substituted on the aryl nucleus by
1 or 2 hydroxyl groups, 1 or 2 alkyl (C_1-C_{12}) groups, cycloalkyl (C_5-C_{12})
and/or cycloalkyl (C_5-C_{11}) alkyl (C_1-C_7) with C_6-C_{12} in the aggregate
thereof; phenyl; phenyl substituted by halogen, cyano, hydroxyl, 1 or 2
10 alkyl (C_1-C_{12}) groups, 1 or 2 alkoxy (C_1-C_{12}) groups, phenyl, $-SO_3H$
and/or a radical R_4-O- or R_4-SO_2- ,
wherein R_4 is phenyl or phenyl substituted by 1 or 2 alkyl (C_1-C_8)
groups;
 R_{2c} is a furane, thiophene, benzothiophene, indole, pyridine or quinoxaline radical,
each of which is either unsubstituted or substituted by halogen, alkyl
15 (C_1-C_4) and/or alkoxy (C_1-C_4) with 1 or 2 substituents in the aggregate
thereof;
 R_{3c} has one of the significances of R_{1c} or is cyano or $-COOR_{6c}$,
wherein R_{6c} is alkyl (C_1-C_{12}), cycloalkyl (C_5-C_{12}), cycloalkyl (C_5-C_{11})
alkyl (C_1-C_7) with C_6-C_{12} in the aggregate thereof, phenyl or phenyl
20 substituted by hydroxyl and/or 1 or 2 alkyl (C_1-C_8) groups,
and Me is hydrogen or an equivalent of a bivalent metal ion.
28. A compound of formula Im , as defined in Claim 27.

B. A. YORKE & CO.,
Chartered Patent Agents,
98, The Centre,
Feltham,
Middlesex TW13 4EP.
Agents for the Applicants.

Printed for Her Majesty's Stationery Office by the Courier Press, Leamington Spa, 1977.
Published by the Patent Office, 25 Southampton Buildings, London, WC2A 1AY, from
which copies may be obtained.