Abstract

Method of Manufacturing Dislocation-Free Single-Crystal Silicon by Czochralski Method

To provide a method of manufacturing dislocation-free single-crystal silicon by the Czochralski method.

The method according to the present invention is characterized in that silicon, which does not contain particles with an average particle diameter smaller than 250 μm, is used as raw material for melting.

Fig. 1