

Description

This invention relates to a coating apparatus, and more specifically to an apparatus for coating one side of one or more strips or tapes of any such materials as woven or nonwoven fabrics, plastics, paper, foam products, etc. The coating apparatus of this invention is of particular utility when used for applying a coating material of relatively high viscosity to the rear sides of elongate surface type fastener tapes having a multiplicity of hooks or loops on their front sides, in order to firmly anchor such hooks or loops to their carrier fabric.

The surface type fastener is known which comprises one fastener member having a multiplicity of hooks on a piece of carrier fabric, and another fastener member having a multiplicity of loops on another piece of carrier fabric. When pressed against each other, the two fastener members fasten together as a result of the interengagement of the hooks and loops. The hooks and loops are disengageable when the fastener members are forced apart. In the manufacture of such surface type fasteners, fastener tapes are prepared which are elongate strips of carrier fabric each having hooks or loops on its front side. The rear sides of these fastener tapes must be coated with a fluid material that, on curing, can provide a positive anchorage for the hooks or loops onto the carrier fabric against the possibility of detachment in use.

"Kiss roll coating" and "dip coating" represent two familiar methods of coating surface type fastener tapes or like strips. "Kiss roll coating" is such that the coating roller, partly immersed in a coating liquid in an open top vessel, carries a film of the liquid on its exposed upper portion. As the strip of substrate material travels in contact with the coating roller, part of the film transfers to the strip. In "dip coating", on the other hand, the strip to be coated is immersed in a vessel of coating material.

These conventional methods can both provide coatings of uniform thickness if the coating material is of relatively low viscosity. However, if the coating material is of higher viscosity, its layer on the desired strip tends to be of uneven thickness, particularly in cases where the strip to be coated is so pliant as to readily twist, bend or otherwise go out of planar shape while being coated.

The doctor blade has been a common expedient for applying high viscosity coating materials to surface type fastener tapes and other strips. For example, as taught by Japanese Laid Open Patent Application No. 59-228970, a strip or strips to be coated are fed in contact with a coating roller against which a doctor blade is held. The doctor blade is movable for adjustably varying the gap between itself and the coating roller, in order to form a metered film of the coating material on the roller. An objection to this prior art apparatus is that it has no provisions for guiding the strip as the same travels in contact with the coating roller. The strip is therefore easy to twist or bend while being coated, due in part to the minute variations in the diameter of the coating roller and to the oscillations of the revolving shaft on which it is mounted. The result has been

irregularities in the thickness of the coating in the longitudinal direction of the strip.

The instant applicant is aware of a prior art device having means for positively guiding the strip being coated, as suggested by Japanese Laid Open Patent Application No. 59-80355. This known device, however, is applicable only for coating the longitudinal edge portions of the strip and is not adaptable for coating its complete surface.

According to the present invention, there is provided a coating apparatus according to the appended claim 1 or 8, to which reference is directed.

A preferred embodiment of the present invention is such that it provides an improved coating apparatus whereby a coating material, no matter how high its viscosity may be, can be continuously applied to one complete surface of a surface type fastener tape or like strip to an unvarying thickness, without the likelihood of the tape or strip twisting, bending or otherwise deforming while being coated. The coating apparatus of this invention is also notable for its ready adaptability for simultaneously coating two or any greater number of strips.

Briefly stated in its simplest form, the invention provides a coating apparatus for continuously coating one surface of an elongate strip of substrate material such as a surface type fastener tape travelling longitudinally along a predetermined path in a predetermined direction. The coating apparatus comprises at least a pair of coating units disposed opposite each other on both sides of the predetermined path of the strip. Each coating unit has a recessed guideway defined in its side surface directed toward the other coating unit, for slidably receiving one longitudinal edge portion of the strip, so that the strip has its opposite longitudinal edge portions slidably engaged in the guideways in the pair of coating units. Each coating unit has also defined therein a passageway for supplying a coating material onto the surface of the strip travelling between the pair of coating units. A doctor blade is mounted to the pair of coating units and is disposed adjacent the downstream ends thereof so as to extend across the predetermined path of the strip and having a scraping edge disposed opposite the surface of the strip so as to create a uniform film of the coating material thereon as the strip travels past the doctor blade.

The strip to be coated may be a surface type fastener tape which is very pliant before being coated. However, travelling through the coating apparatus of the foregoing construction, the tape is guided by having its opposite longitudinal edge portions slidably engaged in the recessed guideways in the pair of coating units. A coating of constant thickness can therefore be formed on one side of the tape as the same travels under the doctor blade after having the coating material supplied thereon.

Preferably, the recessed guideway in each coating unit has upper and lower guide surfaces extending along the path of the strip for relative sliding contact with the opposite surfaces of one longitudinal edge portion of the strip. The upper guide surface tapers in width from the upstream end toward the downstream end of the guideway with respect to

the predetermined travelling direction of the strip, whereas the lower guide surface is of constant width throughout the length of the guideway. So constructed, the guideways can guide the strip still more positively and against the possibility of meandering or oscillating of the strip as the same travels toward the doctor blade for stable contact therewith throughout the transverse dimension of the strip.

Another preferred feature of this invention resides in a guide ledge formed on each coating unit just under the recessed guideway substantially in parallel relation thereto and protruding toward the other coating unit. In coating a surface type fastener tape by the apparatus of this invention, the tape is fed through the apparatus with its rear side, having no loops or hooks formed thereon, directed upwardly in order to be coated as above stated. Thus, as the opposite marginal edge portions of the fastener tape are guided through the recessed guideways in the pair of coating units, the loops or hooks on its front side are guided by the guide ledges so as not to be ruined during the coating. Also, by so guiding the protuberant elements of the fastener tape, the gaps between the coating units and the fastener tape can be reduced to a minimum to prevent the leakage of the coating material there-through.

According to an additional preferred feature of the invention, the recessed guideway in each coating unit declines from the upstream end toward the downstream end thereof with respect to the predetermined traveling direction of the strip. Traveling with its opposite longitudinal edge portions slidably engaged in the pair of guideways, the strip itself declines with the guideways. The doctor blade may be mounted upstandingly to the pair of coating units for relative sliding contact with the strip at the downstream ends of the pair of guideways, thereby making it possible to bend the strip into an obtuse angle to impart tension thereto. Consequently, supplied through the passageways in the coating units, the coating material will temporarily collect in the space bounded by the coating units, the doctor blade and the strip, and will form a film of constant thickness on the strip as the latter travels past the doctor blade.

Stated in another aspect thereof, the invention further provides an apparatus capable of simultaneously coating two or any desired greater number of surface type fastener tapes or other strips of substrate material traveling longitudinally in substantially coplanar, parallel spaced relation to one another. For simultaneously coating two strips, for example, there may be employed a pair of end coating units and one intermediate coating unit arranged alternately with the strips. The end coating units can be of exactly the same construction as the pair of coating units employed in the first described apparatus for coating one strip. The intermediate coating unit differs from each end coating unit in having a pair of recessed guideways defined in its opposite side surfaces. Each strip travels through the apparatus with its opposite longitudinal edge portions slidably engaged in one guideway in the intermediate coating unit and in the guideway in one end coating

unit. A doctor blade is mounted to the end and intermediate coating units so as to extend across the strips.

It will therefore be apparent that the coating material can be applied to each strip just as previously set forth in connection with the first described apparatus. As will also be understood, any desired greater number of strips can be coated at one time merely by increasing the number of intermediate coating units. Two intermediate coating units may be employed for simultaneously coating three strips, three intermediate coating units for simultaneously coating four strips, and so forth.

The above and other features and advantages of this invention and the manner of realizing them will become more apparent, and the invention itself will best be understood, from a study of the following description and appended claims, with reference had to the attached drawings showing a preferred embodiment of the invention.

FIG. 1 is a diagrammatic elevation of a typical arrangement including the apparatus of this invention for coating one or more surface type fastener tapes;

FIG. 2 is an enlarged top plan of the coating apparatus in the arrangement of FIG. 1, the coating apparatus being herein shown as adapted for simultaneously coating two surface type fastener tapes;

FIG. 3 is a perspective view of one of the pair of end coating units in the apparatus of FIG. 2, shown together with part of the doctor blade;

FIG. 4 is a vertical section through the coating apparatus of FIG. 2, taken along the line IV-IV therein and showing in particular one of the end coating units together with the doctor blade and one of the surface type fastener tapes being coated;

FIG. 5 is a vertical section through the coating apparatus of FIG. 2, taken along the line V-V therein and showing in particular one fastener tape traveling between one end coating unit and the intermediate coating unit;

FIG. 6 is a view similar to FIG. 5 but taken along the line VI-VI in FIG. 2;

FIG. 7 is also a view similar to FIG. 5 but taken along the line VII-VII in FIG. 2;

FIG. 8 is an enlargement of part of the showing of FIG. 4, the view being explanatory of the way in which the coating material is applied to each fastener tape by the apparatus of FIG. 2; and

FIG. 9 is a perspective view of the intermediate coating unit in the apparatus of FIG. 2;

The invention will now be described more specifically as adapted for simultaneously coating a plurality of surface type fastener tapes. As illustrated in FIG. 1, the fastener tapes F to be coated travel in the arrow marked direction along a predetermined path extending through the coating apparatus 10 of this invention. Hereinafter in this specification the directional terms "upstream" and "downstream" will be used in reference to this predetermined traveling direction of the fastener tapes F along the predetermined path.

The fastener tapes F are in coplanar, parallel

ed relation to each other as they travel along the predetermined path. Defining this path of the fastener tapes F are smaller diameter guide roller 12, a larger diameter guide roller 14, an idler roller 16 and a drive roller 18. The guide rollers 12 and 14 and idler roller 16 are disposed on the upstream side of the coating apparatus 10 so as to provide a zigzag path for the fastener tapes. Disposed on the downstream side of the coating apparatus 10, the drive roller 18 makes driving engagement with the fastener tapes F for pulling the same through the coating apparatus.

The idler roller 16 is provided with a brake mechanism 20 comprising a brake arm 22 which is pivoted at one end on a pin 24 affixed to an inverted L shaped frame 26. Depending from the frame 26, a threaded guide rod 28 extends with clearance into and through a hole formed in the free end of the brake arm 22. A helical compression spring 30 is sleeved upon the guide rod 28 and acts between a nut 32 thereon and the brake arm 22 for biasing the latter into frictional engagement with the idler roller 16. The force of the compression spring 30 is adjustably variable to correspondingly regulate the frictional force exerted by the brake arm 22 on the idler roller 16 and, in consequence, the tension imparted to the fastener tapes F as the latter travel between idler roller 16 and drive roller 18.

FIG. 2 is a detailed illustration of the coating apparatus 10, which is herein shown adapted for simultaneously coating two fastener tapes F. Broadly, the coating apparatus 10 comprises a pair of end coating units 34, an intermediate coating unit 34', and a doctor blade 36. The end coating units 34 are disposed on both sides of the fastener tapes F whereas the intermediate coating unit 34' is disposed between the fastener tapes.

The doctor blade 10 is mounted upstandingly to these end and intermediate coating units 34 and 34' so as to extend across the fastener tapes F. The coating units 34 and 34' have narrow openings 38 and 38', respectively, formed adjacent their downstream ends for receiving the doctor blade 36. Engaged in these openings 38 and 38', the doctor blade 36 is held fast by lock screws 40 and 40'. The lock screws 40 may be loosened for the adjustment, as required, for the relative positions of the end and intermediate coating units 34 and 34' to the widths of the fastener tapes F or other strips to be coated.

The pair of end coating units 34 are of substantially the same construction. Only one of these units 34 will therefore be described in detail with particular reference to FIG. 3, it being understood that the same description substantially applies to the other.

The representative end coating unit 34 of FIG. 3 is of approximately rectangular shape having a passageway 42 defined therethrough for the supply of a desired coating material. The passageway 42 has an inflow end 44 in the top surface 46 of the terminal coating unit 34. Extending downwardly from this inflow end and bent right angularly, the passageway 42 leads to an outflow end 48 at that side surface 50 of the end coating unit 34 which is directed toward the intermediate coating unit 34'. The passage-

way 42 is open to the doctor blade 36 mounted in the opening 38, FIG. 2, in the end coating unit 34.

Also formed in the side surface 50 of the end coating unit 34 and disposed under the outflow end 48 of the passageway 42 is a recessed guideway 52 extending along the path of one of the fastener tapes F being coated. As will be seen from FIG. 4, the guideway 52 is intended to slidably receive one longitudinal edge portion of one of the fastener tapes F being coated. Thus, in coaction with a similar guideway (to be set forth subsequently) in the intermediate coating unit 34', the guideway 52 serves to guide one fastener tape F through the coating apparatus 10.

As illustrated also in FIGS. 5, 6 and 7, which show both the representative end coating unit 34 and the intermediate coating unit 34', the recessed guideway 52 is defined by upper and lower guide surfaces 54 and 56 for relative sliding contact with the opposite surfaces of one longitudinal edge portion of the fastener tape F. The upper guide surface 54 tapers in width W (i.e. the dimension in the transverse direction of the fastener tape F) from the upstream end toward the downstream end of the guideway 52. The lower guide surface 56 can be of constant width y throughout the length of the guideway 52. It will be observed from FIGS. 5 through 7 that, gradually increasing in width W from the downstream end toward the upstream end of the guideway 52, the upper guide surface 54 protrudes toward the intermediate coating unit 34' in overhanging relation to the lower guide surface 56.

Seen at 58 in FIGS. 3 through 7 is a guide ledge formed on the side surface 50 of the coating unit 34 and disposed under the guideway 52 in parallel relation thereto. Each fastener tape F travels through the coating apparatus 10 with its rear side, which is to be coated, directed upwardly. On the downward facing front side of the fastener tape F there are formed a multiplicity of protuberant elements 60 herein shown as loops. The top surface 62 of the guide ledge 58, extending along the full length of the guideway 52, serves to guide the protuberant elements 60 of the fastener tape F.

It is to be understood that the illustrated coating apparatus 10 has the guide ledge 58 simply because it is herein shown adapted for coating the surface type fastener tapes F having the protuberant elements 60. The guide ledge 58 is of course unnecessary in apparatus for coating other strips having no such protuberant elements.

FIG. 4 best indicates that the guideway 52, as well as the guide ledge 58, declines from its upstream toward downstream ends. As the guideway 52 in each end coating unit 34 and the associated guideway in the intermediate coating unit 34' are thus angled, so is the fastener tape F traveling with its opposite edge portions engaged in these guideways. The upstream end portion 64 of the lower guide surface 56 may be inclined downwardly as it extends toward the upstream end of the guideway 52 in order to expedite the insertion of the fastener tape F.

As shown also in FIG. 4 and on an enlarged scale in FIG. 8, the doctor blade 36 on being fully inserted

in the opening 38 in the coating unit 34 has its scraping edge 66 held against the fastener tape F at the downstream end of the guideway 52, thereby bending the tape into an obtuse angle. The fastener tape F can thus be tensioned extending from idler roller 16 to drive roller 18 in the arrangement of FIG. 1. The scraping edge 66 of the doctor blade 36 may be rounded so as to enable the fastener tape F to travel therepast under tension. The clearance between the fastener tape F and the scraping edge of the doctor blade 36 may be determined in consideration of such factors as the viscosity of the coating material C to be applied and the thickness of the coating on the fastener tape.

As inspection of FIGS. 4 and 8 will further reveal that, since the guideway 52 is inclined as aforesaid, and since the doctor blade 36 is held against the fastener tape F at the downstream end of the guideway, the coating material C on being supplied through the passageway 42 collects on the space bounded by the terminal and intermediate coating units 34 and 34', the doctor blade 36 and the fastener tape F. Thus, as the fastener tape F travels under the doctor blade 36, a uniform film C' of the coating material is formed on its rear side.

As illustrated in detail in FIG. 9, the intermediate coating unit 34' has a passageway 42' for supplying the coating material onto the two fastener tape travelling on both side thereof. Therefore, extending downwardly from an inflow end 44' in the top surface 46' of the coating unit 34', the passageway 42' is bifurcated at its bottom end into a pair of branch passageways leading respectively to a pair of outflow ends 48' formed in the opposite side surfaces 50', one shown, of the coating unit.

The intermediate coating unit 34' also differs from each end coating unit 34 in having a pair of recessed, sloping guideways 52' defined in its opposite side surfaces 50' and disposed under the outflow ends 48' of the passageway 42'. Each guideway 52' has an upper guide surface 54' of tapering width and a lower guide surface 56' of constant width. A pair of guide ledges 58', each having a sloping guide surface 62', are formed on both side surfaces of the coating unit 34' and are disposed under the guideways 52'. The other constructional details of the intermediate coating unit 34' are as previously set forth in connection with the pair of end coating units 34.

It is to be understood that the coating apparatus 10 of FIG. 2 has but one intermediate coating unit 34' because this apparatus is herein shown adapted for simultaneously coating two fastener tapes F. Two intermediate coating units of like construction may be provided, in combination with the pair of end coating units 34, for simultaneously coating three fastener tapes or like strips. Likewise, for coating a multiplicity of strips at one time, a multiplicity of intermediate coating units may be employed in combination with the pair of end coating units 34. For a single tape F there would be no intermediate unit and the tape would have its longitudinal edges in the guideways 52 of the respective end coating units 34.

Driven by the drive roller 18 and retarded by the

idler roller 6, the surface type fastener tapes F will travel in the predetermined direction through the coating apparatus 10 of this invention. In the coating apparatus 10 each fastener tape F has its opposite marginal edge portions slidably engaged in the guideway 52 in one end coating unit 34 and one of the guideways 52' in the intermediate coating unit 34'. Each fastener tape F will thus be stably guided toward the doctor blade 36, particularly as each guideway 52 or 52' has the upper guide surface 54' or 54' of tapering width and the lower guide surface 56 or 56' of constant width.

The protuberant elements 60 on the underside of the fastener tapes F are further guided by the guide ledges 58 and 58' on the coating units 34 and 34'. With the protuberant elements 60 so guided, the fastener tapes F will make closer contact with the upper guide surfaces 54 and 54' of the guideways 52 and 52', thereby minimizing the leakage of the coating material C.

Still further, as the guideways 52 and 52' as well as the guide ledges 58 and 58' decline from their upstream toward their downstream ends, the fastener tapes F can be tensioned by the doctor blade 36 having its rounded scraping edge 66 held against the fastener tapes at the downstream ends of the guideways. The clearance between the fastener tapes F and the doctor blade 36 is adjustable by the degree of tension exerted on the fastener tapes as they extend from idler roller 16 to driver roller 18.

While the fastener tapes F are so travelling through the coating apparatus 10, the coating material C may be fed into the passageways 42 and 42' in the coating units 34 and 34' through their inflow ends 44 and 44'. Flowing out of the outflow ends 48 and 48' of the passageways 42 and 42', the coating material will collect on the fastener tapes F just upstream of the doctor blade 36. As the fastener tapes F travel under tension past the doctor blade 36, the coating material C will be applied to their entire upper surfaces in the form of the films C' of constant thickness by virtue of the "wedge effect" of the coating material in the neighborhood of the scraping edge 66 of the doctor blade.

After having been so coated, the fastener tapes F will be fed further by the drive roller 18 toward the subsequent drying station, not shown, where the coatings will be dried.

It is to be understood that the coating apparatus disclosed in the foregoing is meant purely to illustrate or explain and not to impose limitations upon the invention. A variety of modifications or alterations will readily occur to one skilled in the art to conform to system requirements or design preferences, without departing from the scope of the appended claims.

Claims

1. An apparatus for continuously coating one side of an elongate strip (F) of substrate material such as a surface type fastener tape travelling longitudinally along a predetermined path in a predetermined direction, the coating apparatus comprising:

a) at least a pair of coating units (34) disposed



In the opening 38 in the coating unit 34 has its scraping edge 66 held against the fastener tape F at the downstream end of the guideway 52, thereby bending the tape into an obtuse angle. The fastener tape F can thus be tensioned extending from idler roller 16 to drive roller 18 in the arrangement of FIG. 1. The scraping edge 66 of the doctor blade 36 may be rounded so as to enable the fastener tape F to travel therepast under tension. The clearance between the fastener tape F and the scraping edge of the doctor blade 36 may be determined in consideration of such factors as the viscosity of the coating material C to be applied and the thickness of the coating on the fastener tape.

As inspection of FIGS. 4 and 8 will further reveal that, since the guideway 52 is inclined as aforesaid, and since the doctor blade 36 is held against the fastener tape F at the downstream end of the guideway, the coating material C on being supplied through the passageway 42 collects on the space bounded by the terminal and intermediate coating units 34 and 34', the doctor blade 36 and the fastener tape F. Thus, as the fastener tape F travels under the doctor blade 36, a uniform film C' of the coating material is formed on its rear side.

As illustrated in detail in FIG. 9, the intermediate coating unit 34' has a passageway 42' for supplying the coating material onto the two fastener tape travelling on both side thereof. Therefore, extending downwardly from an inflow end 44' in the top surface 46' of the coating unit 34', the passageway 42' is bifurcated at its bottom end into a pair of branch passageways leading respectively to a pair of outflow ends 48' formed in the opposite side surfaces 50', one shown, of the coating unit.

The intermediate coating unit 34' also differs from each end coating unit 34 in having a pair of recessed, sloping guideways 52' defined in its opposite side surfaces 50' and disposed under the outflow ends 48' of the passageway 42'. Each guideway 52' has an upper guide surface 54' of tapering width and a lower guide surface 56' of constant width. A pair of guide ledges 58', each having a sloping guide surface 62', are formed on both side surfaces of the coating unit 34' and are disposed under the guideways 52'. The other constructional details of the intermediate coating unit 34' are as previously set forth in connection with the pair of end coating units 34.

It is to be understood that the coating apparatus 10 of FIG. 2 has but one intermediate coating unit 34' because this apparatus is herein shown adapted for simultaneously coating two fastener tapes F. Two intermediate coating units of like construction may be provided, in combination with the pair of end coating units 34, for simultaneously coating three fastener tapes or like strips. Likewise, for coating a multiplicity of strips at one time, a multiplicity of intermediate coating units may be employed in combination with the pair of end coating units 34. For a single tape F there would be no intermediate unit and the tape would have its longitudinal edges in the guideways 52 of the respective end coating units 34.

Driven by the drive roller 18 and retarded by the

idler roller 6, the surface type fastener tapes F will travel in the predetermined direction through the coating apparatus 10 of this invention. In the coating apparatus 10 each fastener tape F has its opposite marginal edge portions slidably engaged in the guideway 52 in one end coating unit 34 and one of the guideways 52' in the intermediate coating unit 34'. Each fastener tape F will thus be stably guided toward the doctor blade 36, particularly as each guideway 52 or 52' has the upper guide surface 54 or 54' of tapering width and the lower guide surface 56 or 56' of constant width.

The protuberant elements 60 on the underside of the fastener tapes F are further guided by the guide ledges 58 and 58' on the coating units 34 and 34'. With the protuberant elements 60 so guided, the fastener tapes F will make closer contact with the upper guide surfaces 54 and 54' of the guideways 52 and 52', thereby minimizing the leakage of the coating material C.

Still further, as the guideways 52 and 52' as well as the guide ledges 58 and 58' decline from their upstream toward their downstream ends, the fastener tapes F can be tensioned by the doctor blade 36 having its rounded scraping edge 66 held against the fastener tapes at the downstream ends of the guideways. The clearance between the fastener tapes F and the doctor blade 36 is adjustable by the degree of tension exerted on the fastener tapes as they extend from idler roller 16 to driver roller 18.

While the fastener tapes F are so travelling through the coating apparatus 10, the coating material C may be fed into the passageways 42 and 42' in the coating units 34 and 34' through their inflow ends 44 and 44'. Flowing out of the outflow ends 48 and 48' of the passageways 42 and 42', the coating material will collect on the fastener tapes F just upstream of the doctor blade 36. As the fastener tapes F travel under tension past the doctor blade 36, the coating material C will be applied to their entire upper surfaces in the form of the films C' of constant thickness by virtue of the "wedge effect" of the coating material in the neighborhood of the scraping edge 66 of the doctor blade.

After having been so coated, the fastener tapes F will be fed further by the drive roller 18 toward the subsequent drying station, not shown, where the coatings will be dried.

It is to be understood that the coating apparatus disclosed in the foregoing is meant purely to illustrate or explain and not to impose limitations upon the invention. A variety of modifications or alterations will readily occur to one skilled in the art to conform to system requirements or design preferences, without departing from the scope of the appended claims.

Claims

1. An apparatus for continuously coating one side of an elongate strip (F) of substrate material such as a surface type fastener tape travelling longitudinally along a predetermined path in a predetermined direction, the coating apparatus comprising:

a) at least a pair of coating units (34) disposed



opposite each other on both sides of the predetermined path of the strip;

b) there being a recessed guideway (52) defined in that side surface (50) of each coating unit (34) which is directed toward the other coating unit (34), for slidably receiving one longitudinal edge portion of the or one said strip (F), so that the strip (F) has its opposite longitudinal edge portions slidably engaged in the guideways (52) in the pair of coating units (34);

c) there also being a passageway (42) defined in each coating unit (34) for supplying a coating material (C) onto the surface of the strip (F) travelling through the pair of coating units (34); and

d) a doctor blade (36) mounted to the pair of coating units (34) and disposed adjacent the downstream ends thereof with respect to the predetermined travelling direction of the strip (F), so as to extend across the predetermined path of the strip (F) and having a scraping edge (66) disposed opposite the surface of the strip (F) so as to create a uniform film (C') of the coating material (C) thereon as the strip (F) travels past the doctor blade (36).

2. A coating apparatus as claimed in claim 1, wherein the recessed guideway (52) in each coating unit (34) has upper and lower guide surfaces (54, 56) extending along the predetermined path of the strip (F) for relative sliding contact with the opposite surfaces of one longitudinal edge portion of the strip (F), the upper guide surface (54) tapering in width from an upstream end toward a downstream end of the guideway (52) with respect to the predetermined travelling direction of the strip (F).

3. A coating apparatus as claimed in claim 2, wherein the lower guide surface (56) of the recessed guideway (52) in each coating unit (34) is of approximately constant width throughout the length of the guideway (52).

4. A coating apparatus as claimed in claim 1, 2 or 3, wherein the doctor blade (36) is mounted substantially upstandingly to the pair of coating units (34), and wherein the recessed guideway (52) in each coating unit (34) declines from an upstream end toward a downstream end thereof with respect to the predetermined travelling direction of the strip (F), whereby the coating material (C), supplied through the passageway (42) in each coating unit (34), collects in the space bounded by the coating units (34) and the doctor blade (36) and the strip (F).

5. A coating apparatus as claimed in claim 4, wherein the scraping edge (66) of the doctor blade (36) is rounded.

6. A coating apparatus as claimed in any preceding claim, adapted for coating a said strip (F) having a multiplicity of protuberant elements (60) formed on its underside, wherein each coating unit (34) has a guide ledge (58) disposed under the recessed guideway (52) and protruding therefrom toward the other coating unit (34) for relative sliding contact with the protuberant elements (60) of the strip (F).

7. A coating apparatus as claimed in any preceding claim, wherein the passageway (42) for the coating material (C) in each coating unit has an inflow end (44) disposed in a top surface (46) of the coat-

ing unit (34) and an outflow end (48) disposed in that side surface (50) of the coating unit (34) which is directed toward the other coating unit (34).

8. An apparatus for continuously and simultaneously coating one surface of each of a plurality of elongate strips (F) of substrate material such as surface type fastener tapes travelling longitudinally along a predetermined path in a predetermined direction and in substantially coplanar, parallel spaced relation to one another, the coating apparatus comprising:

(a) a pair of end coating units (34) and at least one intermediate coating unit (34') disposed alternately with the strips (F);

(b) each end coating unit (34) having a recessed guideway (52) defined in that side surface (50) thereof which is directed toward the intermediate coating unit (34'), for slidably receiving one longitudinal edge portion of one strip (F);

(c) the intermediate coating unit (34') having a pair of recessed guideways (52') defined in its opposite side surfaces (50'), each for slidably receiving one longitudinal edge portion of one strip (F), so that each strip (F) has its opposite longitudinal edge portions slidably engaged in respective guideways (52, 52') of one said intermediate coating unit (34') and of either one said end coating unit (34) or of another said intermediate coating unit (34'); and

(d) the end and intermediate coating units (34, 34') also having passageways (42, 42') defined therein for supplying a coating material (C) onto the surfaces of the strips (F) travelling through the end and intermediate coating units (34, 34'); and

e) a doctor blade (36) mounted to the end and intermediate coating units (34, 34') and disposed adjacent the downstream ends thereof with respect to the predetermined direction of the strips (F), so as to extend across the predetermined path of the strips (F) and having a scraping edge (66) disposed opposite the surfaces of the strips (F) so as to create a uniform film (C') of the coating material (C) thereon as the strips (F) travel past the doctor blade (36).

9. A coating apparatus as claimed in claim 8, wherein each recessed guideway (52, 52') in the end and intermediate coating units (34, 34') has upper and lower guide surfaces (54, 54', 56, 56') extending along the path of the strips (F) for relative sliding contact with the opposite surfaces of one respective said longitudinal edge portion of a respective said strip (F), each upper guide surface (54, 54') tapering in width from an upstream end toward downstream end of the guideway (52, 52') with respect to the predetermined travelling direction of the strips (F).

10. A coating apparatus as claimed in claim 9, wherein the lower guide surface (56, 56') of each recessed guideway (52, 52') in the end and intermediate coating units (34, 34') is of approximately constant width throughout the length of the guideway (52, 52').

11. A coating apparatus as claimed in claim 8, 9 or 10, wherein the doctor blade (36) is mounted sub-

stärklich upstandingly to the end and intermediate coating units (34, 34'), and wherein the recessed guideway (52, 52') in the end and intermediate coating units (34, 34') decline from the upstream toward the downstream ends thereof with respect to the predetermined travelling direction of the strips (F), whereby the coating material (C), supplied through the passageways (42, 42') in the end and intermediate coating units (34, 34') collects in the spaces bounded by the end and intermediate coating units (34, 34') and the doctor blade (36) and the strips (F).

12. A coating apparatus as claimed in claim 11, wherein the scraping edge (66) of the doctor blade (36) is rounded.

13. A coating apparatus as claimed in any one of claims 8 to 12, adapted for coating strips (F) each having a multiplicity of protuberant elements (60) formed on its underside, wherein each end coating unit (34) has a guide ledge (58) disposed under the recessed guideway (52) thereof and protruding therefrom toward the intermediate coating unit (34') for relative sliding contact with the protuberant elements (60) of one strip (F), and wherein the intermediate coating unit (34') has a pair of guide ledges (58') disposed under the respective recessed guideways (52') thereof and protruding therefrom toward the end coating units (34) for relative sliding contact with the protuberant elements (60) of the strips (F).

14. A coating apparatus as claimed in any one of claims 8 to 13, wherein the passageway (42) for the coating material (C) in each end coating unit (34) has an inflow end (44) disposed in a top surface (46) of the end coating unit (34) and an outflow end (48) disposed in that side surface (50) of the end coating unit (34) which is directed toward the intermediate coating unit (34'), and wherein the passageway (42') for the coating material (C) in the intermediate coating unit (34') has an inflow end (44') disposed in a top surface (46') of the intermediate coating unit (34') and a pair of outflow ends (48') disposed in the opposite side surfaces (50') of the intermediate coating unit (34') which are directed toward the respective end coating units (34).

Patentansprüche

1. Vorrichtung zum kontinuierlichen Beschichten einer Seite eines länglichen Streifens (F) eines Trägermaterials, wie z.B. ein Flächenhaftverschußband, der sich längs einer vorbestimmten Bahn in einer vorbestimmten Richtung längsweise bewegt, wobei die Beschichtungsvorrichtung umfaßt:

a) mindestens zwei Beschichtungseinheiten (34), die einander gegenüberliegend auf beiden Seiten der vorbestimmten Bahn des Streifens (F) angeordnet sind;

b) wobei eine ausgesparte Führungsbahn (52) in derjenigen Seitenfläche (50) einer jeden Beschichtungseinheit (34) ausgebildet ist, die der anderen Beschichtungseinheit (34) zugekehrt ist, um einen Längsrandbereich des Streifens (F) verschiebbar aufzunehmen, so daß die gegen-

überliegenden Längsrandbereiche des Streifens (F) in die Führungsbahnen (52) der beiden Beschichtungseinheiten (34) verschiebbar eingreifen;

5 c) wobei in jeder Beschichtungseinheit (34) ein Kanal (42) ausgebildet ist, um ein Beschichtungsmaterial (C) auf die Oberfläche des die beiden Beschichtungseinheiten (34) durchlaufenden Streifens (F) zuzuführen, und

10 d) ein Streichblech (36), das an den beiden Beschichtungseinheiten (34) angebracht und in bezug auf die vorbestimmte Bewegungsrichtung des Streifens (F) neben deren stromabwärtigem Ende angeordnet ist, so daß es sich quer zu der vorbestimmten Bahn des Streifens (F) erstreckt, und das eine Abstreifkante (66) hat, die gegenüber der Oberseite des Streifens (F) angeordnet ist, um auf dieser einen gleichförmigen Film (C) des Beschichtungsmaterials (C) zu bilden, wenn sich der Streifen (F) an dem Streichblech (36) vorbeibewegt.

2. Beschichtungsvorrichtung nach Anspruch 1, wobei die ausgesparte Führungsbahn (52) in jeder Beschichtungseinheit (34) obere und untere Führungsflächen (54, 56) hat, die sich längs der vorbestimmten Bahn des Streifens (F) erstrecken zum Gleiteingriff mit den gegenüberliegenden Seiten eines Längsrandbereiches des Streifens (F), wobei die Breite der oberen Führungsfläche (54) in bezug auf die vorbestimmte Bewegungsrichtung des Streifens (F) von einem stromaufwärtigen Ende zu einem stromabwärtigen Ende der Führungsbahn (52) nimmt.

3. Beschichtungsvorrichtung nach Anspruch 2, wobei die untere Führungsfläche (65) der ausgesparten Führungsbahn (52) einer jeden Beschichtungseinheit (34) über die gesamte Länge der Führungsbahn (52) eine näherungsweise konstante Breite hat.

4. Beschichtungsvorrichtung nach Anspruch 1, 2 oder 3, wobei das Streichblech (36) an den beiden Beschichtungseinheiten (34) im wesentlichen aufrecht angebracht ist und wobei die ausgesparte Führungsbahn (52) in jeder Beschichtungseinheit (34) in bezug auf die vorbestimmte Bewegungsbahn des Streifens (F) von einem stromaufwärtigen Ende zu einem stromabwärtigen Ende abfällt, wodurch sich das durch den Kanal (42) in jeder Beschichtungseinheit (34) zugeführte Beschichtungsmaterial (C) in dem von den Beschichtungseinheiten (34) und dem Streichblech (36) und dem Streifen (F) begrenzten Raum ansammelt.

5. Beschichtungsvorrichtung nach Anspruch 4, wobei die Abstreifkante (66) des Streichblechs (36) abgerundet ist.

6. Beschichtungsvorrichtung nach einem der vorhergehenden Ansprüche zum Beschichten eines Streifens (F), an dessen Unterseite eine Vielzahl vorspringender Elemente (60) ausgebildet ist, wobei jede Beschichtungseinheit (34) eine Führungsleiste (58) hat, die unter der ausgesparten Führungsbahn (52) angeordnet ist und von dieser zu der anderen Beschichtungseinheit (34) hin vorspringt zum Gleiteingriff mit den vorspringenden Elementen (60) des Streifens (F).



7. Beschichtungsvorrichtung nach einem der vorhergehenden Ansprüche, wobei der Kanal (42) für das Beschichtungsmaterial (C) in jeder Beschichtungseinheit ein Einströmende (44) hat, das in einer Oberseite (46) der Beschichtungseinheit (34) angeordnet ist, und ein Ausströmende (48) hat, das in derjenigen Seitenfläche (50) der Beschichtungseinheit (34) angeordnet ist, die der anderen Beschichtungseinheit (34) zugekehrt ist.

8. Vorrichtung zum kontinuierlichen und gleichzeitigen Beschichten einer Fläche eines jeden einer Vielzahl von länglichen Streifen (F) eines Trägermaterials, wie z.B. Flächenhaftverschlußbänder, die sich längs einer vorbestimmten Bahn in einer vorbestimmten Richtung längsweise und im wesentlichen in einer Ebene im parallelen Abstand voneinander bewegen, wobei die Beschichtungsvorrichtung umfaßt:

a) zwei endseitige Beschichtungseinheiten (34) und mindestens eine zwischenliegende Beschichtungseinheit (34'), die abwechselnd mit den Streifen (F) angeordnet sind;

b) wobei jede endseitige Beschichtungseinheit (34) eine ausgesparte Führungsbahn (52) hat, die in derjenigen Seitenfläche (50) derselben angeordnet ist, die der zwischenliegenden Beschichtungseinheit (34') zugekehrt ist, um einen Längsrandbereich eines Streifens (F) verschiebbar aufzunehmen;

c) wobei die zwischenliegende Beschichtungseinheit (34') zwei ausgesparte Führungsbahnen (52') hat, die in ihren gegenüberliegenden Seitenflächen (50') ausgebildet sind, um jeweils einen Längsrandbereich eines Streifens (F) verschiebbar aufzunehmen, so daß die gegenüberliegenden Längsrandbereiche eines jeden Streifens (F) in zugehörige Führungsbahnen (52, 52') einer der besagten zwischenliegenden Beschichtungseinheiten (34') und einer der besagten endseitigen Beschichtungseinheiten (34) oder einer anderen zwischenliegenden Beschichtungseinheit (34') verschiebbar eingreifen;

d) wobei die endseitigen und die zwischenliegenden Beschichtungseinheiten (34, 34') ferner Kanäle (42, 42') aufweisen um ein Beschichtungsmaterial (C) auf die Oberseiten der sich durch die endseitigen und die zwischenliegenden Beschichtungseinheiten (34, 34') hindurchbewegenden Streifen (F) zuzuführen; und

(e) ein Streichblech (36), das an den endseitigen und den zwischenliegenden Beschichtungseinheiten (34, 34') angebracht und in bezug auf die vorbestimmte Richtung der Streifen (F) neben dem stromabwärtigen Ende derselben angeordnet ist, um sich quer zu der vorbestimmten Bahn der Streifen (F) zu erstrecken, und das eine gegenüber der Oberseite der Streifen (F) angeordnete Abstreifkante (66) aufweist, um auf diesen einen gleichförmigen Film (C') zu schaffen, wenn sich die Streifen (F) an dem Streichblech (36) vorbeibewegen.

9. Beschichtungsvorrichtung nach Anspruch 8, wobei jede ausgesparte Führungsbahn (52, 52') in den endseitigen und in den zwischenliegenden Beschichtungseinheiten (34, 34') obere und untere Führungsflächen (54, 54', 56, 56') hat, die sich

längs der Bahn der Streifen (F) erstrecken zur Gleitberührung mit den gegenüberliegenden Seiten eines betreffenden Längsrandbereichs eines betreffenden Streifens (F), wobei sich jede obere Führungsfläche (54, 54') in bezug auf die vorbestimmte Bewegungsrichtung der Streifen (F) von einem stromaufwärtigen Ende zu einem stromabwärtigen Ende der Führungsbahn (52, 52') verjüngt.

10. Beschichtungsvorrichtung nach Anspruch 9, wobei die untere Führungsfläche (56, 56') jeder ausgesparten Führungsbahn (52, 52') in den endseitigen und zwischenliegenden Beschichtungseinheiten (34, 34') über die gesamte Länge der Führungsbahn (52, 52') eine näherungsweise konstante Breite hat.

11. Beschichtungsvorrichtung nach Anspruch 9, 9 oder 10, wobei das Streichblech (36) an den endseitigen und zwischenliegenden Beschichtungseinheiten (34, 34') im wesentlichen aufrecht angebracht ist, und wobei die ausgesparten Führungsbahnen (52, 52') in den endseitigen und zwischenliegenden Beschichtungseinheiten (34, 34') in bezug auf die vorbestimmte Bewegungsrichtung der Bänder (F) von ihrem stromaufwärtigen Ende zum stromabwärtigen Ende hin abfallen, wobei sich das durch die Kanäle (42, 42') in den endseitigen und zwischenliegenden Beschichtungseinheiten (34, 34') zugeführte Beschichtungsmaterial (C) in den von den endseitigen und zwischenliegenden Beschichtungseinheiten (34, 34') und dem Streichblech (36) und den Streifen (F) begrenzten Räumen sammelt.

12. Beschichtungsvorrichtung nach Anspruch 11, wobei die Abstreifkante (66) des Streichblechs (36) abgerundet ist.

13. Beschichtungsvorrichtung nach einem der Ansprüche 8 bis 12 zum Beschichten von Streifen (F), die an ihrer Unterseite jeweils eine Vielzahl von vorspringenden Elementen (60) haben, wobei jede endseitige Beschichtungseinheit (34) eine Führungsleiste (58) hat, die unter der ausgesparten Führungsbahn (52) derselben angeordnet ist und von dieser zu der zwischenliegenden Beschichtungseinheit (34') hin vorspringt zum Gleiteingriff mit den vorspringenden Elementen (60) eines Streifens (F), und wobei die zwischenliegende Beschichtungseinheit (34') zwei Führungsleisten (58') hat, die unter den entsprechenden ausgesparten Führungsbahnen (52') derselben angeordnet sind und zu den endseitigen Beschichtungseinheiten (34) hin vorspringen zum Gleiteingriff mit den vorspringenden Elementen (60) der Streifen (F).

14. Beschichtungsvorrichtung nach einem der Ansprüche 8 bis 13, wobei der Kanal (42) für das Beschichtungsmaterial (C) in jeder endseitigen Beschichtungseinheit (34) ein Einströmende (44) hat, das in einer Oberseite (46) der endseitigen Beschichtungseinheit (34) angeordnet ist, und ein Ausströmende (48) hat, das in derjenigen Seitenfläche (50) der endseitigen Beschichtungseinheit (34) angeordnet ist, die der zwischenliegenden Beschichtungseinheit (34') zugekehrt ist, und wobei der Kanal (42') für das Beschichtungsmaterial (c) in der zwischenliegenden Beschichtungseinheit (34') ein Einströmende (44') hat, das in einer Oberseite



(46') der zwischenliegenden Beschichtungseinheit (34') angeordnet ist, und zwei Ausströmenden (48') hat, die in den gegenüberliegenden Seitenflächen (50') der zwischenliegenden Beschichtungseinheit (34') angeordnet sind, die den zugeordneten endseitigen Beschichtungseinheiten (34) zugekehrt sind.

Revendications

1. Appareil pour revêtir d'une façon continue un des côtés d'une bande allongée (F) d'un matériau de support, tel qu'un ruban de fermeture du type à contact de surface ou auto-agrippant, se déplaçant longitudinalement le long d'un trajet prédéterminé dans un sens prédéterminé, l'appareil de revêtement comprenant:

a) au moins une paire de dispositifs de revêtement (34) disposés l'un en face de l'autre de part et d'autre du trajet prédéterminé de la bande (F);

b) un chemin de guidage (52) en creux formé dans la surface latérale (50) de chaque dispositif de revêtement (34) qui est orientée en direction de l'autre dispositif de revêtement (34) pour recevoir de façon coulissante une des parties marginales longitudinales de ladite bande (F) de telle sorte que la bande (F) ait ses parties marginales longitudinales opposées engagées de façon coulissante dans les chemins de guidages (52) de la paire de dispositifs de revêtement (34);

c) un passage (42) étant aussi formé dans chaque dispositif de revêtement (34) pour distribuer une matière (C) de revêtement sur la surface de la bande (F) se déplaçant à travers la paire de dispositifs de revêtement (34); et

d) une lame racleuse (36) montée sur la paire de dispositifs de revêtement (34) et disposée de façon adjacente aux extrémités d'aval de ces derniers par rapport au sens de déplacement prédéterminé de la bande (F), de manière à s'étendre en travers du trajet prédéterminé de la bande (F) et comportant un bord de raclage (66) disposé en face de la surface de la bande (F) afin de créer sur cette surface un film uniforme (C') de la matière de revêtement (C) au fur et à mesure que la bande (F) se déplace devant la lame racleuse (36).

2. Appareil de revêtement selon la revendication 1, dans lequel le chemin de guidage (52) en creux dans chaque dispositif de revêtement (34) comporte des surfaces de guidage supérieure et inférieure (54, 56) s'étendant le long du trajet prédéterminé de la bande (F) en vue d'un contact coulissant relatif avec les surfaces opposées d'une des parties marginales longitudinales de la bande (F), la surface de guidage supérieure (54) diminuant de largeur d'une extrémité d'amont à une extrémité d'aval du chemin de guidage (52) par rapport au sens de déplacement prédéterminé de la bande (F).

3. Appareil de revêtement selon la revendication 2, dans lequel la surface de guidage inférieure (56) du chemin de guidage (52) en creux dans chaque dispositif de revêtement (34) a une largeur à peu près constante sur la totalité de la longueur du chemin de guidage (52).

4. Appareil de revêtement selon la revendication 1, 2, ou 3, dans lequel la lame racleuse (36) est montée de façon sensiblement perpendiculaire à la paire de dispositifs de revêtement (34), et dans lequel le chemin de guidage (52) en creux dans chaque dispositif de revêtement (34) s'incline de son extrémité d'amont vers son extrémité d'aval par rapport au sens de déplacement prédéterminé de la bande (F), grâce à quoi la matière de revêtement (C), distribuée à travers le passage (42) de chaque dispositif de revêtement (34), se rassemble dans l'espace délimité par les dispositifs de revêtement (34) ainsi que par la lame racleuse (36) et la bande (F).

5. Appareil de revêtement selon la revendication 4, dans lequel le bord de raclage (66) de la lame racleuse (36) est arrondi.

6. Appareil de revêtement selon l'une quelconque des revendications précédentes, adapté pour revêtir une bande (F) comportant une multiplicité d'éléments protubérants (60) formés sur son côté de dessous, dans lequel chaque dispositif de revêtement (34) comporte une corniche de guidage (58) disposée sous le chemin de guidage (52) en creux et faisant saillie de ce dernier en direction de l'autre dispositif de revêtement (34) en vue d'un contact coulissant relatif avec les éléments protubérants (60) de la bande (F).

7. Appareil de revêtement selon l'une quelconque des revendications précédentes, dans lequel le passage (42) pour la matière de revêtement (C) dans chaque dispositif de revêtement comporte une extrémité d'entrée (44) située dans la surface supérieure (46) du dispositif de revêtement (34) et une extrémité de sortie (48) située dans la surface latérale (50) du dispositif de revêtement (34) qui est orientée en direction de l'autre dispositif de revêtement (34).

8. Appareil pour revêtir de façon continue et simultanée une des surfaces de chaque bande d'une pluralité de bandes allongées (F) d'un matériau de support, comme par exemple des rubans de fermeture du type à contact de surface ou auto-agrippant, se déplaçant longitudinalement le long d'un trajet prédéterminé dans un sens prédéterminé et en étant parallèles et espacées, sensiblement dans le même plan, les unes par rapport aux autres, l'appareil de revêtement comprenant:

a) une paire de dispositifs de revêtement terminaux (34) et au moins un dispositif de revêtement intermédiaire (34') disposés de façon alternée avec les bandes (F);

b) chaque dispositif de revêtement terminal (34) comportant un chemin de guidage (52) en creux formé dans la surface latérale (50) de ce dispositif qui est dirigée vers le dispositif de revêtement intermédiaire (34') pour recevoir de façon coulissante une des parties marginales longitudinales d'une des bandes (F);

c) le dispositif de revêtement intermédiaire (34') comportant une paire de chemins de guidage (52') en creux, formés dans les surfaces latérales opposées (50') de ce dispositif, chaque chemin de guidage recevant de façon coulissante une des parties marginales longitudinales d'une des bandes (F), de sorte que chaque bande (F) a ses





parties marginales longitudinales opposées engagées de façon coulissante dans les chemins de guidage respectifs (52, 52') d'un desdits dispositifs de revêtement intermédiaires (34') et de l'un ou l'autre des dispositifs de revêtement terminaux (34) ou d'un autre dispositif de revêtement intermédiaire (34');

d) les dispositif de revêtements terminaux et intermédiaires (34, 34') comportant aussi des passages (42, 42') qui y sont formés pour la distribution d'une matière de revêtement (C) sur les surfaces de bandes (F) se déplaçant à travers les dispositifs de revêtement terminaux et intermédiaires (34, 34'); et

e) une lame racleuse (36) montée sur les dispositifs de revêtement terminaux et intermédiaires (34, 34') et disposée de façon adjacente aux extrémités d'aval de ces dispositifs par rapport au sens de déplacement prédéterminé des bandes (F), de manière à s'étendre en travers du trajet prédéterminé des bandes (F) et comportant un bord de raclage (66) disposé en face des surfaces des bandes (F) afin de créer sur celles-ci un film uniforme (C) de la matière de revêtement (C) au fur et à mesure que les bandes (F) se déplacent devant la lame racleuse (36).

9. Appareil de revêtement selon la revendication 8, dans lequel chaque chemin de guidage (52, 52') en creux dans les dispositifs de revêtement terminaux et intermédiaires (34, 34') comporte des surfaces de guidage supérieure et inférieure (54, 54', 56, 56') étendant le long du trajet des bandes (F) en vue d'un contact coulissant relatif avec les surfaces opposées d'une partie marginale longitudinale correspondante d'une bande correspondante (F), chaque surface de guidage supérieure (54, 54') diminuant de largeur d'une extrémité d'amont vers une extrémité d'aval du chemin de guidage (52, 52') par rapport au sens de déplacement prédéterminé des bandes (F).

10. Appareil de revêtement selon la revendication 9, dans lequel la surface de guidage inférieure (56, 56') de chaque chemin de guidage (52, 52') en creux dans les dispositifs de revêtement terminaux et intermédiaires (34, 34') a une largeur à peu près constante sur la totalité de la longueur du chemin de guidage (52, 52').

11. Appareil de revêtement selon la revendication 8, 9 ou 10, dans lequel la lame racleuse (36) est montée de façon sensiblement perpendiculaire aux dispositifs de revêtement terminaux et intermédiaires (34, 34'), et dans lequel les chemins de guidage (52, 52') en creux dans les dispositifs de revêtement terminaux et intermédiaires (34, 34') s'inclinent de l'extrémité d'amont vers l'extrémité d'aval de ces derniers par rapport au sens de déplacement prédéterminé des bandes (F), grâce à quoi la matière de revêtement (C), distribuée à travers les passages (42, 42') dans les dispositifs de revêtement terminaux et intermédiaires (34, 34'), se rassemble dans les espaces délimités par les dispositifs de revêtement terminaux et intermédiaires (34, 34') ainsi que par la lame racleuse (36) et les bandes (F).

12. Appareil de revêtement selon la revendication

11, dans lequel le bord de raclage (66) de la lame racleuse (36) est arrondi.

13. Appareil de revêtement selon l'une quelconque des revendications 8 à 12, adapté pour revêtir des bandes (F) comportant chacune une multiplicité d'éléments protubérants (60) formés sur son côté de dessous, dans lequel chaque dispositif de revêtement terminal (34) comporte une corniche de guidage (58) disposée sous le chemin de guidage (52) en creux et en faisant saillie en direction du dispositif de revêtement intermédiaire (34') en vue d'un contact coulissant relatif avec les éléments protubérants (60) d'une des bandes (F), et dans lequel le dispositif de revêtement intermédiaire (34') comporte une paire de corniches de guidage (58') disposées sous les chemins de guidage respectifs (52') en creux de ce dispositif et en faisant saillie en direction des dispositifs de revêtement terminaux (34) en vue d'un contact coulissant relatif avec les éléments protubérants (60) des bandes (F).

14. Appareil de revêtement selon l'une quelconque des revendications 8 à 13, dans lequel le passage (42) pour la matière de revêtement (C) dans chaque dispositif de revêtement terminal (34) comporte une extrémité d'entrée (44) située dans la surface supérieure (46) du dispositif de revêtement terminal (34) et une extrémité de sortie (48) située dans la surface latérale (50) du dispositif de revêtement d'extrémité (34) qui est orientée en direction du dispositif de revêtement intermédiaire (34'), et dans lequel le passage (42') pour la matière de revêtement (C) dans le dispositif de revêtement intermédiaire (34') comporte une extrémité d'entrée (44') située dans la surface supérieure (46') du dispositif de revêtement intermédiaire (34') et une paire d'extrémités de sortie (48') situées dans les surfaces latérales opposées (50') du dispositif de revêtement intermédiaire (34') qui sont orientées en direction des dispositifs de revêtement d'extrémité respectifs (34).