

FAN AND COMPRESSOR BLADE DOVETAIL RESTORATION PROCESS

BACKGROUND OF THE INVENTION

(1) Field of the Invention

The present invention relates to a method for restoring compressor blade dovetails. More specifically, the present invention relates to a method of physically depositing parent metal onto a fretted or galled blade dovetail so as to restore the blade to operating condition.

(2) Description of Related Art

With reference to Figure 1, there is illustrated a compressor disk and compressor blades assembly known to the art. Compressor disk 11 comprises a plurality of compressor disk dovetail slots 15 into which are inserted a plurality of compressor blades 13. The same assembly is used as well with fan disks and fan blades. With reference to Figure 2, there is illustrated in greater detail the mating surfaces of the compressor blades 13, and the compressor disk 11. Fan and compressor blade 13 dovetail contact surfaces 19 are commonly subject to fretting, galling or wear in service due to contact with the mating surfaces 17 of fan and compressor disk dovetail slots 15. This damage frequently renders the blades 13 unsuitable for further service.

To inhibit such damage, lubricious anti-galling materials 21 are often applied to the dovetail contact surfaces 19. Such anti-galling materials 21 include, but are not limited to aluminum-bronze and copper-nickel or copper-nickel-indium materials. However, anti-galling materials 21 often suffer wear after extended use resulting in damage to the metallic structure of the blades 13. While it is common practice to reapply anti-galling materials 21 in such an event, there is little that can be done to replace or repair damage to the metallic structure of the blades 13. If sufficient damage has been done to the

metallic structure of the blades 13, the blade must be disposed of in order to avoid system failure when in use.

What is therefore needed is a method of restoring blades 13 exhibiting damage resulting from fretting and galling to their original condition.

SUMMARY OF THE INVENTION

Accordingly, it is an object of the present invention to provide a method of physically depositing parent metal onto a fretted or galled blade dovetail so as to restore the blade to operating condition

In accordance with the present invention, a method for restoring blade dovetails to their original shape comprises the steps of removing damaged material from a blade dovetail at a damage site, physically depositing a parent metal at the damage site in an amount sufficient to replace the removed damaged material, and machining the blade dovetail to the original shape.

BRIEF DESCRIPTION OF THE DRAWINGS

- FIG. 1 A diagram of a compressor disk, blades, and blade dovetails of the present invention.
- FIG. 2 A detailed illustration of the blade dovetail interface.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT(S)

It is a central feature of the present invention to employ a method whereby material having near parent material chemistry and near parent metal properties is applied to the dovetails 23 of damaged fan and/or compressor blades 13 so as to restore the blades 13 to operating condition. As used herein, "parent material composition" refers to a material added to the dovetails 23 that is substantially similar to the material out of which the dovetail 23 is constructed. "Near parent" material refers to a metal possessing similarity to the dovetail

construction material sufficient to meet the structural requirements of the blade.

The process of the present invention whereby there is dimensionally restored damaged contact surfaces 19 is as follows. First, damaged dovetail contact surfaces 19 are inspected, and damaged material (if present) is removed by machining or grinding. Machining proceeds to a depth sufficient to fully eradicate surface distress. Typically, the depth required to achieve such eradication is between approximately five and ten mils. Preferably, machining continues to approximately two mils beyond full eradication.

Second, material having an alloy content similar to the blade material is applied to the damaged dovetail contact surface 19 at the site of damage using either cathodic arc vapor deposition or electron beam physical vapor deposition (EBPVD). In a preferred embodiment, a variant of EBPVD is utilized wherein ion enhancement is employed to accelerate the vapor particles and increase the bond strength of the coating. In a preferred embodiment, when restoring fan blades, the alloy used is a Ti-6Al-4V alloy (i.e. Ti6-4) or other alloy of lower aluminum content. In the case of alloys containing Mo or other refractory elements, as are preferably used to restore compressor blades, a third process, electron beam flash vapor deposition, may be utilized. In such an instance, a Ti-8Al-1V-1Mo alloy is preferably employed. In a preferred embodiment, the alloy employed is identical to the material out of which the dovetail is fashioned. In another preferred embodiment, Ti6-4 can be deposited onto a substrate of a different titanium alloy.

Preferably, vapor deposition is performed at a process pressure of between 10^{-3} and 10^{-6} torr. More preferably, the process pressure is approximately 10^{-4} torr. Preferably, the rate of deposition is between 10 and 50 micrometers per minute. Most preferably, the rate of deposition is approximately 20 micrometers per minute.

After deposition has been performed, contact surfaces 19 are machined or ground to their original shape. Any coatings, required by the original equipment manufacturer are applied to the blade dovetail 23. Preferably, anti-galling materials such as those recited above are applied to the blade dovetails.

After the physical vapor deposition process has been performed, the dovetail 23 may be shot peened. Shot peening is a method whereby metal beads, usually steel beads, are shot at high velocity to impact with the surface of a target object. Such repeated impacting results in a compressed surface layer increasing the ability of the dovetail 23 to resist surface cracks which give rise to structural failure.

It is apparent that there has been provided in accordance with the present invention a method of physically depositing metal onto a distressed blade dovetail so as to restore the blade to operating condition which fully satisfies the objects, means, and advantages set forth previously herein. While the present invention has been described in the context of specific embodiments thereof, other alternatives, modifications, and variations will become apparent to those skilled in the art having read the foregoing description. For example, extension of the teachings of the present invention to encompass physically depositing metal onto any damaged machined part, particularly parts machined of titanium alloys, is encompassed in the present disclosure. Accordingly, it is intended to embrace those alternatives, modifications, and variations as fall within the broad scope of the appended claims.

WHAT IS CLAIMED IS:

1. A method for restoring blade dovetails to their original shape comprising the steps of:
 - removing damaged material from a blade dovetail at a damage site;
 - physically depositing a metal at said damage site in an amount sufficient to replace said removed damaged material; and
 - machining said blade dovetail to said original shape.
2. The method of claim 1 comprising the additional steps of applying an anti-galling material to a surface of said machined dovetail.
3. The method of claim 2 wherein said applying said anti-galling material comprises applying an anti-galling material selected from the group consisting of aluminum-bronze, copper-nickel, and copper-nickel-indium.
4. The method of claim 1 comprising the additional step of shot peening said blade dovetail.
5. The method of claim 1 wherein said removing damaged material from said blade dovetail comprises removing material from a blade dovetail selected from the group consisting of compressor blade dovetails and fan blade dovetails.
6. The method of claim 1 wherein said physically depositing said metal comprises performing physical deposition in a manner selected from the group consisting of vapor deposition, electron beam physical vapor deposition, and electron beam flash vapor deposition.

7. The method of claim 1 wherein physically depositing said metal comprises physically depositing a metal selected from the group consisting of Ti-6Al-4V and Ti-8Al-1V-1Mo.
8. The method of claim 1 wherein said removing said damaged material comprises the step of machining said dovetail to an approximate depth between five and fifteen mils.
9. The method of claim 1 wherein said physically depositing said metal comprises physically depositing Ti-6Al-4V where said damaged material comprises a titanium alloy different than Ti-6Al-4V.
10. The method of claim 6 wherein said performing said physical deposition is performed at a pressure between 10^{-3} and 10^{-6} torr.
11. The method of claim 10 wherein said performing said physical deposition is performed at a pressure of approximately 10^{-4} torr.
12. The method of claim 1 wherein said physically depositing said metal is performed at a rate between 10 and 50 micrometers per minute.
13. The method of claim 12 wherein said physically depositing said metal is performed at a rate of approximately 20 micrometers per minute.
14. The method of claim 1 wherein said physically depositing said metal comprises depositing a parent metal composition.
15. The method of claim 1 wherein said physically depositing said metal comprises depositing a near parent metal.

16. A method for restoring machined parts to their original shape comprising the steps of:

removing damaged material from said machined part at a damage site;

physically depositing a metal at said damage site in an amount sufficient to replace said removed damaged material; and

machining said machined part to said original shape.