

TILTED MEDIA FOR HARD DISK DRIVE

TECHNICAL FIELD

This invention relates to magnetic media used in data storage devices, and more
5 particularly to magnetic media having either a ring head or pole head for write operations.

BACKGROUND OF THE INVENTION

A conventional magnetic storage medium includes a substrate supporting an
underlayer disposed under a magnetic layer protected by an overcoating layer. These layers
10 are usually deposited using a sputtering process. The magnetic layer is typically formed from
a granular ferromagnetic material such as cobalt alloy, in which data bits are stored.
Transitions of magnetization in the tiny grains of the magnetic layer are used to store data and
generate signals, which may then be read or written by a read/write head.

Magnetic layers are typically classified as being either longitudinal or perpendicular.
15 In a longitudinal magnetic storage medium, the magnetic moments of the grains are aligned
parallel to the plane of the substrate surface of the storage medium. In perpendicular magnetic
media, the magnetic moments of the grains are aligned perpendicular to the same plane. A
longitudinal recording system uses a ring head for write operations while a perpendicular
recording system uses a single pole head for write operations.

20 As the demand for storage space grows, there is a constant need to increase the areal
density in magnetic storage media. To do so, the number of grains in a medium is increased
by decreasing the size of the magnetic grains. This reduction in grain size also leads to
sharper transitions and a higher signal to noise ratio (SNR), which improves data recording.
Unfortunately, a major problem with reducing grain size is that it leads to decreased thermal
25 stability.

Maintaining thermal stability of the magnetic grains is critical to data retention,
particularly over longer periods of time. If the grains are unstable, then it is likely that data
may be lost through magnetization decay. The energy required to store and maintain the

stability of written bits of data is known as magnetic-anisotropy energy, $K_u V$, where K_u is the anisotropy constant and V is the volume of the grain. Below a certain grain size, the magnetic layer will experience what is known as a super-paramagnetic effect due to the decrease of this magnetic-anisotropy-energy.

5 To ensure thermal stability of the grains and minimise the tendency for magnetization decay, a thermal stability factor is used as a reference to determine the stability of the grains with respect to the life span of the media. This thermal stability factor is defined by the magnetic-anisotropy energy over the thermal energy of the magnetic media: $\frac{K_u V}{k_B T}$, where T is the temperature and k_B is the Boltzmann's constant.

10 For example, a medium with thermal stability factor of 60, the industry standard, has a life span of about 3.6×10^9 years. If the thermal stability factor is reduced, the life span of the medium would be reduced, (e.g. at a thermal stability factor of 40, the life span would be approximately 7.5 years and at 25, the life span of the media is approximately 72 seconds). Therefore, it is important to have this factor at least at or above 40 to ensure that data stored in
15 a medium does not experience magnetization decay over a sufficiently long period of time.

 While it would be ideal to use materials that have a higher K_u to maintain the thermal stability factor while V is reduced, conventional longitudinal recording systems are limited by the ring heads that are used. Currently, the ring heads have a maximum head field of 2 Tesla. This head field sets a maximum limit on the K_u of the digital storage medium to about $2.1 \times$
20 10^6 erg/cm³. Accordingly, this limit sets a highly undesirable minimum threshold on grain size to maintain the thermal stability factor. In contrast, perpendicular recording systems using a single pole head are able to generate a higher field relative to that of the ring head. Unfortunately, perpendicular recording systems are subject to limitations and problems that have prevented the technology from being more widespread. In particular, excessive noise
25 interference is caused by a soft underlayer used in a perpendicular medium. Although perpendicular media have greater thermal stability than compared to longitudinal media, the coercivity in the perpendicular medium is considerably higher. The high coercivity requires higher switching field energy to perform write operations, which may cause further noise interference. Thus, perpendicular recording systems are not a commercially viable option.

In view of the foregoing, it is desirable to have magnetic recording disk media that will allow increase in areal density while preventing magnetization decay. To overcome the limitations of existing magnetic recording systems, there is a need to have a magnetic recording medium that allows continued reduction of grain size while preventing excessive interference from noise. In addition, it is also desirable to have a magnetic recording medium that maintains thermal stability as grain size is reduced.

SUMMARY OF THE INVENTION

The present invention provides a digital storage medium with a substrate where two magnetic layers are disposed and protected by an overcoat. The first magnetic layer is disposed on the substrate while the second magnetic layer is disposed on the first magnetic layer. The first of the two magnetic layers has a first magnetic moment with an easy axis that is tilted and the second magnetic layer has a second magnetic moment with an easy axis that is also tilted. The tilted axes are formed under the influence of exchange-coupling between the first and second magnetic layers. The tilted axes, which are biaxial, form acute angles with a perpendicular plane to the surface of the digital storage medium. The angles of the tilted easy axes in the two magnetic layers may have magnitudes that are the same or different. The tilted easy axes of the magnetic moments in the present invention provides the advantage of writing data on the digital storage medium with either a longitudinal ring head, a perpendicular single-pole head or any newly developed tilted field head.

On the substrate, which the first layer is disposed, is coated a nickel phosphorous seedlayer on top of which an underlayer is disposed. An intermediate layer is disposed on the underlayer before the first magnetic layer. A soft underlayer may also be disposed between the underlayer and the interlayer.

In one embodiment, an interlayer is disposed between the first and second magnetic layers. The interlayer can be cobalt, cobalt alloy or non-magnetic material like ruthenium (Ru), Rhodium (Rh), Chromium (Cr), Copper (Cu), Iridium (Ir), and their alloys. With non-magnetic material as the interlayer, the tilted easy axis of the first and second magnetic moments are anti-parallel while having cobalt or alloys of cobalt as the interlayer, the easy

axis of the first and second magnetic layers are parallel. The magnetic thickness of the digital storage medium is the combined thickness of the first and second magnetic layer as well as the thickness of the interlayer, if disposed between the two magnetic layers.

In one embodiment of the present invention, the first magnetic layer has a perpendicular magnetic anisotropy where the easy axis of the magnetic moment in the first magnetic layer is perpendicular to the plane of the digital storage medium; and the second magnetic layer has a longitudinal anisotropy where the easy axis of the magnetic moment in the second magnetic layer is parallel to the plane of the digital storage medium. Alternatively, the first magnetic layer has a longitudinal magnetic anisotropy and the second magnetic layer has a perpendicular magnetic anisotropy with respect to the plane of the digital storage medium. The magnetic layer with longitudinal anisotropy is formed with a ferromagnetic material selected from a group consisting of cobalt (Co), iron (Fe), nickel (Ni), and the alloys of these ferromagnetic materials while the magnetic layer with the perpendicular anisotropy is formed with ferromagnetic materials like cobalt, iron and their alloys. The magnetic layer with perpendicular anisotropy is a single layer of alloy like cobalt-chromium-platinum (CoCrPt), cobalt-chromium-platinum-boron (CoCrPtB), cobalt-chromium-platinum-tantalum (CoCrPtTa), cobalt-chromium-platinum-niobium (CoCrPtNb) and iron-platinum (FePt). The single layer can also be formed from alloys of cobalt which are doped with non-magnetic materials like silicon oxide and silicon nitride.

Alternatively, the perpendicular magnetic layer is formed from multiple layers of the same ferromagnetic materials with spacer layers between the multiple layers of ferromagnetic material. The ferromagnetic material forming the multiple layers can be cobalt, cobalt oxides and cobalt alloys while the spacer layer includes palladium and platinum. The cobalt alloys includes cobalt-silver (Co-Ag), cobalt-boron (Co-B), cobalt-chromium (Co-Cr), cobalt-copper (Co-Cu), cobalt-palladium (Co-Pd) and cobalt-tantalum (Co-Ta).

In another aspect, a method of manufacturing the digital storage medium of the present invention is provided. The method provides for deposition of a first magnetic layer on a substrate followed by a second magnetic layer, where the first magnetic layer has a first magnetic moment with a first easy axis; and the second magnetic layer has a second magnetic moment with a second easy axis such that the two easy axes are perpendicular to each other.

Exchange-coupling of the magnetic moments of the two magnetic layers result in the easy axes effectively tilting out of plane of the digital storage medium. The tilted easy axes of the present method form acute angles with a perpendicular plane to the plane of the digital storage medium. The magnitude of the acute angles depends on the exchange coupling strength, as well as the anisotropy energies of the respective magnetic layers. The anisotropy energies of the respective magnetic layers compete to attain a stable tilted configuration of the easy axes. The competition of the anisotropy energies is influenced by the exchange-coupling constant, anisotropy constant which can be changed by varying the type of ferromagnetic materials in the magnetic layers as well as the thickness of the respective magnetic layers. The thickness of the first and second magnetic layers are variable. While the exchange-coupling between the first and second magnetic layers increases the activation volume, V , through the combined thickness of the two magnetic layer and hence increases the thermal stability of the digital recording or storage medium according to the thermal stability factor, $\frac{K_u V}{k_B T}$, the exchange-coupling constant between the first and second magnetic layers is variable.

The method of the present invention provides for one magnetic layer having longitudinal anisotropy where the easy axis of the magnetic moment in the magnetic layer is parallel to the plane of the digital storage medium while another magnetic layer having perpendicular anisotropy where the easy axis of the magnetic moment is perpendicular to the plane of the digital storage medium. The magnetic layer with perpendicular anisotropy is disposed on the magnetic layer with longitudinal anisotropy or alternatively, the magnetic layer with the longitudinal anisotropy is disposed on the magnetic layer with perpendicular anisotropy. The magnetic layer with longitudinal anisotropy is formed with a ferromagnetic material selected from a group consisting of cobalt (Co), iron (Fe), nickel (Ni), and the alloys of these ferromagnetic materials while the magnetic layer with the perpendicular anisotropy is formed with ferromagnetic materials like cobalt, iron and their alloys. The magnetic layer with perpendicular anisotropy can take the form of a single layer of alloys of ferromagnetic materials like cobalt-chromium-platinum (CoCrPt), cobalt-chromium-platinum-boron (CoCrPtB), cobalt-chromium-platinum-tantalum (CoCrPtTa), cobalt-chromium-platinum-niobium (CoCrPtNb) and iron-platinum (FePt). The single layer can also be formed from alloys of cobalt which are doped with non-magnetic materials like silicon oxide and silicon

nitride. Alternatively, the magnetic layer with perpendicular anisotropy is formed from multiple layers of the same ferromagnetic materials with spacer layers between the multiple layers of ferromagnetic material. The ferromagnetic material can be cobalt, cobalt oxides and cobalt alloys and the spacer layer includes palladium and platinum. The cobalt alloys includes
 5 cobalt-silver (Co-Ag), cobalt-boron (Co-B), cobalt-chromium (Co-Cr), cobalt-copper (Co-Cu), cobalt-palladium (Co-Pd) and cobalt-tantalum (Co-Ta).

In the present method an underlayer is disposed between the substrate and the first magnetic layer, where a seedlayer is disposed on the substrate before the underlayer. On underlayer may be disposed an additional soft underlayer. An intermediate layer is then
 10 disposed between the underlayer and the first magnetic layer. On the first magnetic layer is disposed an interlayer. The interlayer is selected from a group of high saturation magnetization materials like pure cobalt, alloys and compounds of cobalt, nickel, iron, alloys of nickel and alloys of iron to enhance exchange-coupling at the interface of the first and second magnetic layers. Alternatively, the interlayer is selected from a group of nonmagnetic
 15 materials consisting of ruthenium (Ru), Rhodium (Rh), Chromium (Cr), Copper (Cu), Iridium (Ir), and their alloys such that the first magnetic layer is anti-ferromagnetically exchange-coupled to the second magnetic layer. The interlayer is of a variable thickness less than 1nm.

The present invention has a recording direction that is independent of the types of head used for write operations due to the natural formation of the bi-axial easy axis in the
 20 system. Thus, the present invention provides a method of manufacturing a recording medium that can be used with any read/write head independent of the field direction of the read/write head.

Furthermore, due to the tilted direction of the magnetic moment to writing field of either a ring head or single pole head, a much higher anisotropy constant, K_u , can be used to
 25 increase the thermal stability while maintaining the writeable switching field value. The magnetic medium also enables sharper magnetic transitions due to the reduction of the switching fields in the tilted transition. This result in a higher linear bit density for the medium.

BRIEF DESCRIPTION OF THE DRAWINGS

The details of the present invention will become apparent by reference to the following description and accompanying drawings wherein:

FIG. 1 is a perspective view of a disc of the present invention lying in a plane.

5 FIG. 2 is a cross-sectional view of the structure of an embodiment of the digital media of the present invention.

FIG. 3 is another cross-sectional view of the structure of another embodiment of the digital media of the present invention.

10 FIG. 4 is a schematic illustration of an orientation of the easy axes of the 2 magnetic layers of the embodiment of FIG. 2.

FIG. 5 is a schematic illustration of another orientation of the easy axes of the 2 magnetic layers of the embodiment of FIG. 3.

FIG. 6 is a schematic sectional view of the interaction of magnetic moments of the 2 magnetic layers of the present invention.

15 FIG. 7 is a graph illustrating the relationship of the tilted angle with the coupling constant.

FIG. 8 is a perspective view illustrating the relationship of the applied field, the easy axis and the plane of the magnetic medium.

20 FIG. 9 is a graph based on Stoner-Wolfarth model of the normalised switching field in relation to the angle of the tilted magnetic moment in a magnetic medium having a single magnetic layer.

FIG. 10 is a graph of differential switching in relation to the angle of the tilted magnetic moment in a magnetic medium having a single magnetic layer.

FIG. 11 is an illustration of the effective bi-axial easy axes due to exchange-coupling in each of the magnetic layers in the present invention.

25 FIG. 12 is a schematic sectional view of the interaction of magnetic moments of the 2 magnetic layers, where an interlayer is disposed between the 2 layers.

FIG. 13 is a schematic sectional view of the resultant magnetic moments at a recorded

magnetic transition of the present invention, where an interlayer disposed between the top and bottom magnetic layer results in anti-parallel magnetic moments in the respective layers.

FIG. 14 is a graph showing the time required for switching the magnetic moments in a magnetic medium having tilted magnetic moments when a field is applied on the medium.

5 FIG. 15 is a graph of coercivity field in relation to angle dependence for the structure FIG. 2 with Pd interlayer thicknesses of 0.6 nm, 1.2 nm and 2.5 nm.

FIG. 16 is a graph of magnetization squareness and angle dependence for structure of FIG. 2 with Pd interlayer layer thickness of 0.6 nm, 1.2 nm and 2.5 nm.

10 DETAILED DESCRIPTION OF INVENTION

FIG. 1 shows a digital storage medium **10** in the form of a disk lying in a plane **11**. The digital storage medium **10** typically comprises of a substrate **12**, on which a seedlayer **13** is disposed followed by an underlayer **14** as illustrated in FIG. 2 where the cross section of the digital medium is shown. Disposed on top of the underlayer is an intermediate layer **16** as in a
 15 typical disk storage medium. A first magnetic layer **18** is then deposited on the intermediate layer **16**. The seedlayer **13**, underlayer **14** and intermediate layer **16** are represented in subsequent figures in the layer denoted as **100**. This first magnetic layer **18** forms the bottom magnetic layer upon which a second magnetic layer **20** is deposited. The second magnetic layer includes a series of alternating layers of ferromagnetic materials and spacer layers. A
 20 protective overcoat **22** is then deposited on the second magnetic layer **20**.

The second magnetic layer **20** can be switched with the first magnetic layer **18** such that the bottom layer is the second magnetic layer **20** and the top layer is the first magnetic layer **18** as shown in FIG. 3. Between the first and second magnetic layers in both arrangement shown in FIG. 2 and FIG. 3, may be included an interlayer **20a**. This interlayer
 25 will be discussed in detail with reference to FIG. 12 and FIG. 13.

The relationship between the first magnetic layer **18** and the second magnetic layer **20** of the arrangement illustrated in the embodiment of FIG. 2 is further discussed with reference to FIG. 4. The first magnetic layer **18** includes a first magnetic moment having a first easy

axis **19**. Similarly, the second magnetic layer **20** includes a second magnetic moment having a second easy axis **21**. These easy axes are uniaxial in that the moments of the magnetic grains are orientated in one direction of the easy axes. In FIG. 4, the first easy axis **19** is parallel to the plane **11** of the surface of the digital storage medium **10** and the second easy axis **21** is perpendicular to the first easy axis **19**. From the embodiment of FIG. 3, the top magnetic layer **18** has a first easy axis **19** parallel to the surface of the digital storage medium **10** while the bottom magnetic layer **20** has a second easy axis **21** perpendicular to the first easy axis **19** as shown in FIG. 5.

In this invention, the easy axes for the magnetic layers are deliberately designed such that both are perpendicular in direction to each other. When the two magnetic layers are magnetically isolated or not exchange-coupled, the remnant moment at the respective layers align in the direction of the easy axis of the respective layers, thus in one layer the easy axis is perpendicular to the plane of the magnetic layers while the other easy axis lie in the same plane as the magnetic layers. When exchange-coupling is introduced at the interface between the two magnetic layers, a new energy is introduced and the magnetic moments tend to align together. The two exchange-coupled moments pull towards each other, but this pull is restricted by the anisotropy energy that exist in each respective magnetic layer. As illustrated in FIG. 4 and FIG. 5, the two easy axes which are perpendicular to each other have exchange-coupling linking the magnetic moments from the two magnetic layers together. However, at the same time, a competition between the anisotropy energies from the respective magnetic layers is created. When a balance of the competing anisotropy energies is achieved, a new easy axes with a different configuration is generated. The new easy axes tilt at an angle out of the plane **11** in which the magnetic layers **18** and **20** lie. This phenomenon of exchange-coupling at the interface of the magnetic layers will become apparent from FIG. 6 and FIG. 7.

FIG. 6 illustrates the interaction between the respective magnetic moments of the first **20** and second **18** magnetic layers. The interaction of the magnetic moments results in remnant magnetic moments, M_1 (**15**) and M_2 (**17**). The respective remnant magnetic moment is: $M_1 = M_{r1}t_1$ and $M_2 = M_{r2}t_2$, where M_{r1} and M_{r2} are the remnant magnetization from the respective magnetic layers due to exchange coupling at the interface of the two magnetic layers; t_1 and t_2 are the respective thickness of the magnetic layers. The exchange-coupling in

the present design is utilized for forming remnant magnetic moments **15** and **17** which tilt at an acute angle to the plane **11**. The tilting of the magnetic moments at an acute angle provides an advantage over existing prior art, which are either longitudinal or perpendicular in orientation to the plane of the medium. The magnitude of the acute angles, θ_1 and θ_2 , in which the remnant magnetic moments tilt is dependent on the exchange-coupling strength between the magnetic moments from the two magnetic layers. The graph of FIG. 7 illustrates the effect of the exchange-coupling constant on the angles θ_1 and θ_2 of the remnant magnetic moments M_1 and M_2 . In this example, both magnetic layers have the same anisotropy constant and thickness. As the exchange-coupling constant increases, the angle θ_2 of second easy axis **21** decreases while the angle θ_1 of first easy axis **19** increases. Therefore, an exchange-coupling constant has to be selected to have the remnant magnetic moments tilted at a desired angle. Depending on the exchange-coupling strength, the angles of the easy axes in the two magnetic layers will tilt at different angles (i.e. $\theta_1 \neq \theta_2$). The tilting angle is influenced by the competition of the anisotropy energies between the magnetic layers in an exchange-coupled system. The anisotropy energy for the respective magnetic layer can be varied to adjust the tilting angle. The strength of the anisotropy energy or the anisotropy density in each magnetic layer is determined by the thickness and anisotropy constant of the magnetic layer. The principle in this design is to control the competing energies between the two anisotropy energies in the perpendicular direction to each other when both are exchange coupled. As such, varying the anisotropy constants, K_{u1} and K_{u2} , of the respective magnetic layers will affect the competition of the anisotropy energies in the exchange-coupled system and the moment will tilt in the direction of the dominant anisotropy. Therefore, the tilting angle is also dependent on the anisotropy constant, K_{u1} , of the first magnetic layer **18** and K_{u2} , of the second magnetic layer **20**. This can be achieved by varying the magnetic properties of the two magnetic layers. Once the magnetic materials for the respective magnetic layers are selected, the anisotropy constants of each magnetic layer are constant. However, while the anisotropy constants K_{u1} , and K_{u2} , of the respective magnetic layers **18** and **20** are unchanged, the interaction through exchange-coupling of the two magnetic layers give rise to an effective anisotropy constant, $K_{u,eff}$ for the combined magnetic layers. Thus the exchange coupling between the two magnetic layers bring about a new magnetic property of the digital storage medium **10**. The overall magnetic property of the digital storage medium **10** is thus

determined through the exchange-coupling of the selected magnetic properties of the respective magnetic layers. The overall effective anisotropy constant, $K_{u,eff}$, would then take on a new value which differ from the anisotropy constant, K_{u1} and K_{u2} of the respective magnetic layers.

5 The degree in which the tilting angle tilts can also be controlled by adjusting the thickness of each magnetic layer since varying the thickness would vary the anisotropy energy of the respective layer. The overall magnetic properties may lean towards the magnetic layer having stronger magnetic properties in view of the competing energies from the two magnetic layers in the exchange-coupled system.

10 The overall remnant magnetic moment is: $M_r = M_1 + M_2$. It follows from the above that if the remnant magnetic moment of one magnetic layer dominates the other, the overall remnant magnetic moment will lean towards the dominant magnetic moment under the influence of the competing energies in the exchange coupling system. The exchange-coupling system provides the flexibility in enabling the design of a medium with particular magnetic
15 properties by selection of ferromagnetic materials to form the magnetic layers in the digital storage medium.

The exchange-coupling of the magnetic moments between the two magnetic layers provides an advantage through increasing the activation volume, V , of the digital storage magnetic medium 10. The activation volume is: $V = D \cdot t$, where D is the diameter of the grain
20 and t is the magnetic thickness of the digital storage medium. The magnetic thickness for the exchange coupled system is: $t = t_1 + t_2$, where t_1 is the thickness of the magnetic layer 18 and t_2 is the thickness of the magnetic layer 20 as shown in FIG. 2 and FIG. 3. From this relationship, $V = D \cdot t$, an increase in the thickness of the magnetic layers is directly proportional to the effective activation volume, V , of the exchange-coupled digital storage
25 medium 10. The present exchange coupled system enables the decrease in grain size in the respective magnetic layer while increasing the overall activation volume since the effective thickness of the medium is the combined thickness of the two magnetic layers. By increasing the thickness of the medium, vertical expansion of the medium is achieved and leads to improved thermal stability of the digital storage magnetic medium 10.

30 The increase in this coupled magnetic activation volume, V , is important for

determining thermal stability of the exchange-coupled system. The magnetic-anisotropy energy of the exchange-coupled system is: $K_{u,eff}V$, while the thermal energy is: $k_B T$. Therefore, the thermal stability factor of the exchange-coupled system is: $\frac{K_{u,eff}V}{k_B T}$. An increase in the magnetic-anisotropy-energy, $K_{u,eff}V$ of the exchange-coupled system provides greater thermal stability as compared to a prior art magnetic medium which is not exchange-coupled. The thermal stability of the tilted medium in the present invention can be increased through increasing the magnetic anisotropy energy, which can be achieved by increasing the overall effective anisotropy constant, $K_{u,eff}$ or the activation volume, V . The activation volume, V , when increased vertically would contribute to an increase the thermal stability of the tilted medium. However, if the activation volume, is increased through horizontal expansion, it can be easily seen from the relation in $V = D.t$ that a horizontal expansion of the medium indicates increase in D , which means a horizontal increase in domain size. This would translate into a decrease in areal density, which is not desired. Hence, the selection of the magnetic materials for the respective layers is important to ensure that the activation volume is increased only vertically through the thickness, t , of the medium.

In FIG. 8 is shown the relationship of the direction of the applied field **50**, the easy axis **52** and the plane **11** in which the magnetic medium lie. The easy axis forms an angle θ with the plane **11**, while the applied field form an angle α with the easy axis. The sum of these two angles is β (i.e. $\beta = \alpha + \theta$). From this illustration, the effects of having a medium with magnetic moments tilted at an angle θ is discussed with FIG. 9.

FIG. 9 shows the ratio of switching field and anisotropy field (H_s/H_k) in relation to the angle, α , between the tilted easy axis and the applied field direction. It is observed that the ratio of the switching field and anisotropy field decreases when the angle α of the tilted easy axis increases from 0° to 45° and this ratio of the fields increases when α increases further to 90° . If the anisotropy field H_k is kept at a constant, the switching field H_s reaches a minimum when the magnetic moment is tilted at an angle, $\alpha = 45^\circ$ to the applied field direction. This means that for the same magnitude of applied field, the anisotropy constant, K_u of the tilted magnetic medium can be increased while the writability of the medium is maintained. Therefore, the thermal stability of a tilted medium can be further improved by using materials

of high anisotropy constant K_u . It is shown that so long as the easy axis of the medium is angled between $\alpha = 0^\circ$ and $\alpha = 90^\circ$, the switching field, H_s , required for performing write operations by a transducer head will be less than that required for write operations in a longitudinal or perpendicular recording medium. This shows that the present invention provides an advantage in that the tilted medium can be paired with either a ring head or a single pole head or a tilted head for write operations. The anisotropy constant, K_u is related to the anisotropy field such that $K_u = \frac{H_k M_s}{2}$, where M_s is the saturation magnetization which is kept at a constant. From FIG. 9, the relationship: $H_s/H_k = X$ is illustrated, where $X = f(\alpha)$ and α is the angle between the easy axis and the applied field, therefore K_u can also be expressed in relation to the switching field, H_s : $K_u = \frac{H_s M_s}{2X}$. For optimum writing operations, the external writing field, $H_g = 1.5H_s$ and so $K_u = \frac{H_g M_s}{3X}$. In a longitudinal or perpendicular system where the magnetic moments are not tilted at an acute angle, (i.e. when $\alpha = 0^\circ$ or 90°), $X = f(\alpha) = 1$ leaving $K_u = \frac{H_g M_s}{3}$. When the magnetic moments are angled such that $\alpha = 45^\circ$, $X = f(\alpha) = 0.5$ which gives $K_u = 2 \frac{H_g M_s}{3}$. It is evident that given the same writing field, H_g and saturation magnetization, M_s , when the magnetic moments are tilted at an angle of 45° , the anisotropy constant K_u is doubled as compared to having magnetic moments at 0° or 90° . Therefore, a lower switching field also enables an increase in the anisotropy constant for the same writing field. To illustrate this, it is assumed that saturation magnetization, $M_s = 400 \text{ emu/cm}^3$ and the writing gap field, $H_g = 16 \text{ kOe}$, where the head field, $B_0 = 2 \text{ Tesla}$ and the optimum writing field is at 80% of B_0 . Using the relationship above, the value of $K_u = 2.1 \times 10^6 \text{ erg/cm}^3$ when $X = 1$ (i.e. when the angle $\alpha = 0^\circ$ or 90°); and the value of $K_u = 4.3 \times 10^6 \text{ erg/cm}^3$ when $X = 0.5$ (i.e. when the angle $\alpha = 45^\circ$). It is shown in this illustration that the anisotropy constant, K_u is increased when the magnetic moments tilt at an angle, θ between 0° and 90° in the same applied field.

It is further observed from FIG. 10 that the differential switching field over angle is minimal at the angle ranging from 10° to 80° . This indicates that the magnetic moment with a

tilted easy axis switching within this range is less sensitive to dispersion of the applied field. Hence the magnetic moments with an easy axis tilted at an angle in this range is able to reverse more uniformly and generate less noise as compared to the magnetic moments in a longitudinal (0°) or perpendicular (90°) system. In actual application of the tilted medium, it is preferable that the magnetic moments tilt at an angle ranging from 10° to 45° when using a ring head and tilt at an angle ranging from 45° - 80° when using a single pole head. This indicates that when the magnetic medium has an easy axis tilted at an angle that falls within these ranges, the medium is less sensitive to the dispersion in the applied field improving the performance of the medium.

One characteristic of the exchange-coupled system is that the remnant magnetic moments M_1 and M_2 have effective easy axes that are biaxial in character as illustrated in FIG. 11. The tilting remnant magnetic moments, M_1 and M_2 having direction of the remnant magnetic moments are allowed to fall in either direction of the biaxial easy axes. The biaxial character of the effective easy axes of the remnant magnetic moments, M_1 and M_2 , provides an advantage over existing prior art where the magnetic moments lie in effective easy axes that are uniaxial in character. When compared to storage medium in prior art having a tilted uniaxial easy axis which restricts the direction of the magnetic moment, the biaxial character provides flexibility to the writing of data on the magnetic medium without compromising quality. The grains of a magnetic medium with uniaxial tilted easy axis tilt either in the down-track or cross track direction providing a highly oriented tilted medium. Although such highly oriented media, particularly those with grains having easy axes tilted in the down-track directions, are acceptable for data storage application, they are not achievable with current sputter deposition methods. In addition to this limitation, concentration of magnetic moments at the edges of tracks will expand the track width limiting the track density and areal density of such a medium. In a magnetic medium of the present invention with biaxial easy axis, data bits can fall in an alternative direction avoiding concentration of dipole charge at the track edge. This reduces the interference with neighboring data bits, which reduces the overall transition and track edge noise providing an advantage over a magnetic medium with uniaxial easy axes.

Other Embodiments

In a separate embodiment, it is noted that the exchange-coupling constant can be varied by inserting a thin interlayer of high saturation magnetization material **27** between the first magnetic layer **18** and the second magnetic layer **20**. FIG. 12 shows the structure of one preferred embodiment of the present invention with a thin interlayer **27** selected from a group of cobalt compounds, including pure cobalt and cobalt alloy. The function of the interlayer **27** is to enhance the exchange-coupling at the interface between the first magnetic layer **18** and the second magnetic layer **20**. As such, the tilting angle of the respective layer can be tuned as desired with the specific recording system head. In the presence of the interlayer **27** a strong exchange-coupling can be achieved so that both magnetic moments from the first and second magnetic layers switch coherently and form a tilted angle in the same magnetization remnant state. The interlayer **27** may also be used in embodiments where the easy axes of the magnetic layers are switched as shown in FIG. 3. It is preferable to have the interlayer as thin as possible (below 1 nm) for maintaining the recording performance. If the thickness of the interlayer **27** is beyond 1nm, it is likely that the interlayer may contribute to horizontal expansion in the domain size of the magnetic medium. The thickness of the interlayer greater than 1nm may also contribute additional signal to the overall recording which will add on to the transition noise in high recording density medium.

In other embodiments of the present invention, the selection of the type of non-magnetic material for the interlayer **44** and its thickness is used to fabricate a digital storage medium that has resultant magnetic moments, M_1 **40** and M_2 **42**, anti-parallel to each other, as shown in FIG 13, such that the remnant magnetic moment is low but non-zero. An example of the type of material that can be used to achieve this is having ruthenium (Ru) as part of the interlayer. The ruthenium can be disposed between two layers of cobalt which are disposed between the first **18** and second **20** magnetic layers. The interaction of the exchange-coupling results in anti-parallel magnetic moments that are tilted at an angle to the plan **11** of the digital storage medium. Other types of non-magnetic materials that can be used for anti-ferromagnetic exchange-coupling includes Rhodium (Rh), Chromium (Cr), Copper (Cu), Iridium (Ir), and their alloys.

FIG. 14 compares the switching time required at tilted moments of various angles in

two different normalised applied fields, $H_z/H_k = 2$ and $H_z/H_k = 3$, where H_z is the applied external field which is also known as the Zeeman field. It is observed from the plots that at $\theta = 0^\circ$, the reversal or switching time is 220 ps (pico second) similarly, it can be observed from the trend of the plots when $\theta = 90^\circ$ the switching time is comparably high. When the angle, θ range between 0° and 90° , the switching time is considerably lower at below 120 ps for the applied field at $H_z/H_k = 3$ and below 160 ps for applied field at $H_z/H_k = 2$. This result shows that when magnetic moments are tilted at an acute angle, the time required to switch the magnetic moments is shorter. A shorter transition time also enable the speed of write operations to be faster as compared to a longitudinal or perpendicular recording media. Hence the faster transitions would serve extremely high recording density medium that require very fast writing operations.

Examples:

In an example of the present invention, the substrate **12** is formed from an aluminum magnesium (AlMg) or glass disk. The seedlayer **13** is disposed on the substrate **12**. The underlayer may be a chromium alloy deposited onto the seedlayer **13**. The intermediate layer **16** may comprise of cobalt, chromium and tantalum (CoCrTa). The first magnetic layer **18** disposed on the intermediate layer **16** includes cobalt (Co), chromium (Cr), platinum(Pt) and boron(B), to form an alloy, CoCrPtB. In the second magnetic layer **20** is a series of alternating cobalt/palladium (Co/Pd) layers, where the first contact layer **20a** with the first magnetic layer can be a palladium or cobalt. Three samples, with different thickness for a Pd interlayer **20a** interfaced with the CoCrPtB film were compared and the coercivity in relation to the field angel were measured at room temperature for each sample. These measurements are shown in FIG. 15. The field angle, β at 0° indicates that an external field was applied in the direction of the sample plane during measurement. At the field angle $\beta = 90^\circ$, the field is applied at a direction perpendicular to the plane during measurement. Varying the thickness of the first Pd layer **20a** modifies the exchange coupling strength between the two ferromagnetic layers, **18** and **20**.

The symmetry of the two peaks in FIG. 15 indicates a formation of the biaxial easy axes in all three examples where the thickness of the palladium is 0.6 nm, 1.2 nm and 2.5 nm.

The peaks are observed at angles occurring between (0°) and (90°) to the magnetic plane. In the sample where the thickness of palladium is 0.6 nm, two peaks occurs at angle, $\theta = \pm 60^\circ$, as the thickness of the palladium layers increases further, the peaks shift to $\theta = \pm 45^\circ$ at the thickness of 1.2 nm and $\theta = \pm 30^\circ$ at the thickness of 2.5 nm and the coercivity is observed to increase with the thickness of the palladium layer. Similar angle dependent trend was observed for the magnetization squareness measurement, given by the ratio of the remnant magnetic moment and the saturation magnetization: $\frac{M_r}{M_s}$, for the three samples as shown in FIG. 16. This observation re-enforce the conclusion that the exchange-coupling constant is enhanced by adjusting the thickness of the interlayer between the two magnetic layers 18 and 20.

Thermal stability is enhanced in the current invention because a higher anisotropy constant, K_u , can be achieved in the magnetic grains without affecting writing operations. The present invention allows the use of longitudinal ring head, perpendicular single pole head or a transducer head that is capable of applying writing field at an angle for recording purposes. This enables increase in areal density with an increase in the coupled magnetic activation volume while at the same time thermal stability is increased.

It is to be noted that the above description is only illustrative of the present invention. Modification of the examples without departing from the scope and spirit of the present disclosure is possible to provide different versions of the invention.

We claim:

1. A digital storage medium, comprising:

a substrate;

a first magnetic layer disposed over the substrate, wherein the first magnetic layer has a first magnetic moment having a tilted easy axis;

a second magnetic layer disposed over the first magnetic layer, wherein the second magnetic layer has a second magnetic moment having a tilted easy axis; and

an overcoat layer disposed over the second magnetic layer

wherein the first magnetic layer has a perpendicular magnetic anisotropy and the second magnetic layer has a longitudinal anisotropy.

2. A digital storage medium, comprising:

a substrate;

a first magnetic layer disposed over the substrate, wherein the first magnetic layer has a first magnetic moment having a tilted easy axis;

a second magnetic layer disposed over the first magnetic layer, wherein the second magnetic layer has a second magnetic moment having a tilted easy axis; and

an overcoat layer disposed over the second magnetic layer,

wherein the first magnetic layer has a longitudinal magnetic anisotropy and the second magnetic layer has a perpendicular anisotropy.

3. A digital storage medium, comprising:

a substrate;

a first magnetic layer disposed over the substrate, wherein the first magnetic layer has a first magnetic moment having a tilted easy axis;

a second magnetic layer disposed over the first magnetic layer, wherein the second magnetic layer has a second magnetic moment having a tilted easy axis;

an interlayer disposed between the first magnetic layer and the second
magnetic layer, and
an overcoat layer disposed over the second magnetic layer,

5 4. The digital storage medium of claims 1, 2 or 3, wherein the tilted easy axes form
acute angles with a perpendicular plane of the digital storage medium.

5. The digital storage medium of claim 4, wherein the acute angles are of different
magnitudes.

10 6. The digital storage medium of claim 4, wherein the acute angles are of the same
magnitude.

7. The digital storage medium of claim 4, wherein the tilted easy axes are bi-axial.

15 8. The digital storage medium of claim 1, 2 or 3, wherein an exchange coupling
occurs between the first and second magnetic layers.

20 9. The digital storage medium of claim 1 or 2, wherein the magnetic layer with the
longitudinal anisotropy includes a material selected from a group consisting of cobalt
(Co), iron (Fe), nickel (Ni), and alloys thereof.

25 10. The digital storage medium of claim 1 or 2, wherein the magnetic layer with the
perpendicular anisotropy includes a material selected from a group consisting of cobalt,
iron, and alloys thereof.

30 11. The digital storage medium of claim 10, wherein the magnetic layer is formed
from a single layer of alloys selected from a group consisting of cobalt-platinum (CoPt),
cobalt-palladium (CoPd), cobalt-chromium-platinum (CoCrPt), cobalt-chromium-
platinum-boron (CoCrPtB), cobalt-chromium-platinum-tantalum (CoCrPtTa), cobalt-
chromium-platinum-niobium (CoCrPtNb), and iron-platinum (FePt).

12. The digital storage medium of claim 10, wherein the magnetic layer is formed from multiple layers of ferromagnetic materials selected from a group consisting of cobalt with palladium as a spacer layer (Co/Pd), cobalt with platinum as a spacer layer (Co/Pt), a
5 cobalt alloy with palladium as a spacer layer, and a cobalt alloy with platinum as a spacer layer.

13. The digital storage medium of claim 11, wherein the alloys are doped with non-ferromagnetic materials selected from a group consisting of silicon oxide and silicon
10 nitride.

14. The digital storage medium of claim 3, wherein the interlayer includes a high saturation magnetization material selected from a group consisting of cobalt, nickel, iron, alloys of cobalt, alloys of nickel, and alloys of iron.

15. The digital storage medium of claim 3, wherein the interlayer includes a non-magnetic material selected from a group consisting of ruthenium (Ru), rhodium (Rh), chromium (Cr), copper (Cu), iridium (Ir), and alloys thereof.

16. The digital storage medium of claim 4, wherein data is transmitted through a transducer, and wherein the transducer is selected from a group consisting of a ring head, a single pole head, and a head which applies a magnetic field at an angle to the digital
20 storage medium.

17. The digital storage medium of claim 1, 2 or 3, wherein the magnetic moments with tilted easy axes of the first and second magnetic moments are anti-parallel.

18. The digital storage medium of claim 1, 2 or 3, wherein the magnetic moments with tilted easy axis of the first and second magnetic moments are parallel.

19. A method of manufacturing a digital storage medium, the method comprising:

depositing a first magnetic layer on a substrate surface, wherein the first
magnetic layer has a first magnetic moment with a first easy axis; and
depositing a second magnetic layer on the first magnetic layer, wherein the
second magnetic layer has a second magnetic moment with a second easy
axis; wherein the second easy axis is perpendicular to the first easy axis;
wherein exchange-coupling of the first magnetic moment and the second
magnetic moment forms tilted easy axes in the first and second magnetic
layers, and

wherein the first magnetic layer has a perpendicular anisotropy and the second magnetic
layer has a longitudinal anisotropy.

20. A method of manufacturing a digital storage medium, the method comprising:

depositing a first magnetic layer on a substrate surface, wherein the first
magnetic layer has a first magnetic moment with a first easy axis; and
depositing a second magnetic layer on the first magnetic layer, wherein the
second magnetic layer has a second magnetic moment with a second easy
axis; wherein the second easy axis is perpendicular to the first easy axis;
wherein exchange-coupling of the first magnetic moment and the second
magnetic moment forms tilted easy axes in the first and second magnetic
layers, and

wherein the first magnetic layer has a longitudinal anisotropy and the second
magnetic layer has a perpendicular anisotropy.

21. A method of manufacturing a digital storage medium, the method comprising:

depositing a first magnetic layer on a substrate surface, wherein the first
magnetic layer has a first magnetic moment with a first easy axis; and
depositing a second magnetic layer on the first magnetic layer, wherein the
second magnetic layer has a second magnetic moment with a second easy
axis; wherein the second easy axis is perpendicular to the first easy axis;
wherein exchange-coupling of the first magnetic moment and the second
magnetic moment forms tilted easy axes in the first and second magnetic
layers, and

wherein an interlayer is disposed between the first and second magnetic layers.

22. The method of claim 19 or 20, wherein the magnetic layer with the perpendicular anisotropy includes a ferromagnetic material selected from a group consisting of cobalt, iron, and alloys thereof.

5

23. The method of claim 22, wherein the magnetic layer is formed from a single layer of at least one alloy selected from a group consisting of cobalt-platinum (CoPt), cobalt-palladium (CoPd), cobalt-chromium-platinum (CoCrPt), cobalt-chromium-platinum-boron (CoCrPtB), cobalt-chromium-platinum-tantalum (CoCrPtTa), cobalt-chromium-platinum-ni-
obium (CoCrPtNb), and iron-platinum (FePt).

10

24. The method of claim 22, wherein the magnetic layer is formed from multiple layers of ferromagnetic materials selected from a group consisting of cobalt with palladium as a spacer layer (Co/Pd), cobalt with platinum as a spacer layer (Co/Pt), a
cobalt alloy with palladium as a spacer layer, and a cobalt alloy with platinum as a spacer layer.

15

25. The method of claim 23, wherein the alloys are doped with non-ferromagnetic materials selected from a group consisting of silicon oxide and silicon nitride.

20

26. The method of claim 19, 20 or 21, wherein the first magnetic layer and the second magnetic layer each have a thickness that is variable.

27. The method of claim 19, 20 or 21, wherein an angle is formed between the tilted easy axes and a perpendicular plane of the digital storage medium.

25

28. The method of claim 27, wherein the angle is adjustable by varying the type of ferromagnetic materials in the first and second magnetic layers.

29. The method of claim 27, wherein the angle is adjustable by varying an exchange-coupling constant between the first and second magnetic layer.

30

30. The method of claim 27, wherein the angle is adjustable by varying the thickness of the first and second magnetic layers.