

DESCRIPTION**TITLE: PROCESS FOR THE FORMATION OF A HANDLE SUBSTRATE FOR A
COMPOSITE STRUCTURE TARGETING RF APPLICATIONS****FIELD OF THE INVENTION**

The present invention relates to a handle substrate for a composite substrate compatible with high performance RF applications. It also relates to a method for the formation of such a handle substrate.

TECHNOLOGICAL CONTEXT OF THE INVENTION

High resistivity (HR) silicon substrates are the most commonly used handle substrates for making RF devices. An HR silicon substrate usually exhibits a resistivity of greater than 1000 ohm.cm and more generally of greater than 5000 ohm.cm.

Composite structures such as SOI (silicon on insulator) with HR silicon handle substrates, comprising or not comprising a charge-trapping layer between the handle substrate and the buried oxide, are well known in the field of radiofrequencies (RF). In particular, composite structures having a charge-trapping layer guarantee high performance qualities of the RF devices produced on the said structures, provided that the charge-trapping layer does not suffer damage when the structures are exposed to high temperatures, for example during its manufacture or during the manufacture of RF devices. For example, when a charge-trapping layer made of polysilicon recrystallizes, even partially, the RF performance qualities of the composite structure and the integrated devices which are formed thereon are affected, which is obviously not desirable.

Another problem arises from the supply of HR substrates, which is becoming increasingly restricted, in parallel with the increase in the manufacture of RF devices. As a result, the material is becoming increasingly expensive.

SUBJECT-MATTER OF THE INVENTION

The present invention proposes an alternative solution for providing a handle substrate suitable for composite structures on which high performance RF devices can be produced and for facilitating the supply and manufacturing processes.

BRIEF DESCRIPTION OF THE INVENTION

With a view to achieving this aim, the subject-matter of the present invention proposes a handle substrate for a composite structure comprising:

- a base substrate formed of an epitaxial layer of silicon on a monocrystalline silicon wafer of Cz type, *i.e.* obtained by Czochralski pulling, having a resistivity of between 10 and 500 ohm.cm, the said epitaxial layer of silicon exhibiting a resistivity of greater than 2000 ohm.cm and a thickness ranging from 2 to 100 microns,
- a passivation layer on and in contact with the epitaxial layer of silicon, the said passivation layer being amorphous or polycrystalline,
- a charge-trapping layer on and in contact with the passivation layer.

According to other advantageous and non-limiting characteristics of the invention, taken individually or according to any technically achievable combination:

- the passivation layer is a layer of silicon carbide formed by carbonization of the surface of the epitaxial layer of silicon;
- the passivation layer is a layer of silicon nitride formed by nitridation of the surface of the epitaxial layer of silicon.

The present invention also relates to a composite structure for radiofrequency applications comprising:

- a handle substrate as above,
- a dielectric layer on and in contact with the passivation layer,
- a thin film on the dielectric layer, suitable for radiofrequency devices.

The present invention relates finally to a process for the formation of a handle substrate for a composite structure, the process comprising:

- a) the provision of a monocrystalline silicon wafer obtained by Czochralski pulling having a resistivity of between 10 and 500 ohm.cm;
- b) the growth of an epitaxial layer of silicon on the monocrystalline silicon wafer obtained by Czochralski pulling to form a base substrate, the said epitaxial layer of silicon exhibiting a resistivity of greater than 2000 ohm.cm and a thickness ranging from 2 to 100 microns;
- c) the formation of a passivation layer on the epitaxial layer of silicon, the said passivation layer being amorphous or polycrystalline;
- d) the growth of a polycrystalline charge-trapping layer on the passivation layer.

According to other advantageous and non-limiting characteristics of the invention, taken individually or according to any technically achievable combination:

- stage c) comprises a carbonization of the surface of the epitaxial layer of silicon, so as to form a passivation layer made of polycrystalline silicon carbide;
- the carbonization of stage c) comprises the exposure of the base substrate to a single carbon precursor at a pressure below atmospheric pressure in order to form a passivation layer made of polycrystalline silicon carbide of at least 5 nm in thickness on the surface of the epitaxial layer of silicon;
- the said single carbon precursor exhibits a temperature of between 700°C and 1200°C;
- stage c) comprises a nitridation of the surface of the epitaxial layer of silicon, so as to form a passivation layer made of amorphous silicon nitride;
- the passivation layer exhibits a thickness of at least 10 nm;
- the charge-trapping layer has a thickness of greater than 5 or 10 microns;
- the charge-trapping layer is made of polycrystalline silicon;
- stages b), c) and d) are all carried out successively *in situ* in epitaxy equipment;
- stage b) is carried out in a first reactor and stages c) and d) are carried out in a second reactor, and in which the transfer of the base substrate from the first reactor to the second reactor is carried out without breaking the vacuum.

BRIEF DESCRIPTION OF THE DRAWINGS

Other characteristics and advantages of the invention will become apparent from the detailed description of the invention below, which refers to the attached figures, among which:

[Fig. 1] Figure 1 represents a handle substrate according to the invention;

[Fig. 2] Figure 2 represents a composite structure according to the invention.

DETAILED DESCRIPTION OF THE INVENTION

In the descriptive part, the same references can be used in the figures to denote elements of the same type. The figures are diagrammatic representations which, for the purposes of readability, are not to scale. In particular, the thicknesses of the layers along the z axis are not to scale with respect to the lateral dimensions along the x and y axes; and the thicknesses of the layers with respect to one another are not necessarily respected in the figures.

Figure 1 diagrammatically represents a handle substrate 100 for a composite substrate according to the present invention. The handle substrate 100 can be provided in the form of a circular slice, of standardized size, for example 200 mm or 300 mm, indeed even 450 mm, in diameter. However, the present invention is in no way limited to these dimensions or to this shape.

The handle substrate 100 comprises a base substrate 12 formed by an epitaxial layer 2 of silicon positioned on a silicon wafer 1. The said silicon wafer 1 generally has a thickness of

several hundred microns and exhibits a standard resistivity ranging from 10 to 500 ohm.cm. It may preferentially concern monocrystalline silicon obtained by Czochralski pulling, which is a type of material widely available.

The epitaxial layer 2 of silicon exhibits a resistivity of greater than 2000 ohm.cm, preferentially of between 2000 ohm.cm and 20 000 ohm.cm. In this way, the density of the charges, holes or electrons liable to move in the epitaxial layer of silicon is limited. The said epitaxial layer 2 has a thickness ranging from 2 to 100 microns.

The handle substrate 100 also comprises, on the base substrate 12, a charge-trapping layer 4. The function of the charge-trapping layer 4 is to trap any charge carrier possibly present in the handle substrate 100 and to limit its mobility.

For reasons of availability and of cost, the charge-trapping layer 4 is preferentially made of polycrystalline silicon. However, it can be formed from another semiconductor and polycrystalline material, or it can comprise a part made from another semiconductor and polycrystalline material. It may concern, for example, germanium, silicon-germanium, and the like.

In all cases, the polycrystalline charge-trapping layer 4 exhibits a high resistivity, generally of greater than 3000 ohm.cm. To this end, this layer is not intentionally doped, that is to say that it exhibits a concentration of dopants of less than 10^{14} atoms/cm³. It can be rich in nitrogen or in carbon in order to improve its resistivity characteristic.

The polycrystalline charge-trapping layer 4 can have a thickness of greater than 0.5 micron, or of greater than 5

microns, indeed even of greater than 10 microns. Whether its thickness is greater or less than these limits, the charge-trapping layer 4 can be composed of grains with a size of between 10 nm and 1000 nm.

The handle substrate 100 also comprises an amorphous or polycrystalline passivation layer 3 interposed between the base substrate 12 and the polycrystalline charge-trapping layer 4. The passivation layer 3 is formed directly on the epitaxial layer 2 of silicon and makes it possible to grow on it the polycrystalline charge-trapping layer 4. This layer is necessary to prevent the charge-trapping layer 4 from recrystallizing during high temperature treatments.

The passivation layer 3 can thus remain in amorphous or polycrystalline form throughout the duration of implementation of the high temperature processes necessary to manufacture the handle substrate 100 and, later, the composite structure 110 and the RF devices. Generally, the thermal budget to be endured by the handle substrate 100 is of the order of a few hours to 10 hours, at temperatures ranging from 950°C to 1200°C.

The passivation layer 3 can be of different natures. Advantageously, it consists of a layer of polycrystalline silicon carbide formed by carbonization of the free surface of the epitaxial layer 2 of silicon. Alternatively, it can consist of a layer of silicon nitride formed by nitridation of the surface of the epitaxial layer of silicon.

Of course, other materials of a different nature might be used for the passivation layer 3, provided that it meets the requirements of microelectronics and retains its amorphous or polycrystalline structure after the global thermal balance up to completion of the RF devices.

In general, the passivation layer 3 can have a thickness of at least 2 nm and preferably a thickness of at least 10 nm.

The handle substrate 100 thus consists of the base substrate 12, formed by an epitaxial layer 2 of silicon positioned on a monocrystalline silicon wafer 1, of the passivation layer 3 directly in contact with the epitaxial layer 2 of silicon and of a polycrystalline charge-trapping layer 4 on, and directly in contact with, the passivation layer 3. It is not intended to incorporate other layers, in particular electrically insulating layers, which might modify the properties of the handle substrate 100 proposed.

The handle substrate 100 can optionally comprise a dielectric layer 5 positioned directly on the charge-trapping layer 4. The said dielectric layer 5, which is optional, can facilitate the assembly of the handle substrate 100 with another substrate. The dielectric layer 5 can, for example, be made of silicon oxide or of silicon nitride.

Figure 2 represents a composite structure 110 according to the present invention, which comprises a handle substrate 100 as described above. As emerges very clearly from this figure, the composite structure comprises a dielectric layer 5 on the handle substrate 100 and a thin film 6, preferably made of monocrystalline material, on the dielectric layer 5. For example, and without limitation, the thin film 6 can be made of semiconductor material, such as silicon, or of piezoelectric material, such as lithium tantalate (LiTaO_3), lithium niobate (LiNbO_3), lithium aluminium oxide (LiAlO_3), barium titanate (BaTiO_3), lead zirconate titanate (PbZrTiO_3), potassium niobate (KNbO_3), barium zirconate (BaZrO_3), calcium titanate (CaTiO_3), lead titanate (PbTiO_3), potassium tantalite (KTaO_3), and the like.

The composite structure 110 of Figure 2 can be formed in several ways from the handle substrate 100 but advantageously this formation comprises a stage of transfer of the thin film 6 onto the handle substrate 100. As is well known per se, this transfer is generally carried out by assembling the face of a donor substrate on the handle substrate 100. This can be carried out in the presence or absence of the dielectric layer 5.

When the thin film 6 is made of piezoelectric material, its crystalline orientation is chosen depending on the intended application. For surface acoustic wave filters made of lithium tantalate LiTaO_3 , it is usual to choose an orientation of between 30° and 60° XY, or between 40° and 50° XY. For lithium niobate LiNbO_3 , it is common to choose an orientation around 128° XY. However, the invention is in no way limited to a particular crystalline orientation of a piezoelectric thin film. The donor substrate may have been withdrawn from an ingot made of ferroelectric material so that the donor substrate exhibits the chosen crystalline orientation. Alternatively, the donor substrate can comprise a thick layer made of ferroelectric material assembled with a support substrate.

After this assembly stage, the thickness of the donor substrate is reduced in order to form the thin film 6. This reduction stage can be carried out by mechanical or chemical thinning. It can also be carried out by fracturing at a fragile zone introduced beforehand into the donor substrate, for example in accordance with the principles of the Smart Cut™ technology.

Stages for finishing the thin film 6, such as a polishing stage, a heat treatment under a reducing or neutral atmosphere or a sacrificial oxidation, can be linked together following the stage of reduction in thickness.

When the donor substrate is a bulk substrate, that is to say not comprising an integrated device, a composite structure 110 of the "semiconductor on insulator" type is formed, in which the thin film 6 is a virgin semiconductor layer, comprising the handle substrate 100 according to the invention. The composite structure 110 can then be used to form integrated devices.

When the donor substrate has been pretreated in order to form integrated devices on its surface, a thin film 6 which comprises the said devices can be transferred onto the handle substrate 100, forming a composite structure 110 with a layer of integrated devices on the handle substrate 100 according to the invention.

The manufacture of the handle substrate 100 according to the present description is achievable by being provided with standard materials and by using conventional epitaxy/deposition equipment of the industry.

First, the method comprises a stage a) consisting in providing a wafer 1 of monocrystalline silicon obtained by Czochralski pulling and having a resistivity ranging from 10 to 500 ohm.cm.

The following stage b) consists in growing an epitaxial layer 2 of silicon on the silicon wafer 1, in order to form a base substrate 12. To do this, the silicon wafer 1 is placed in the reactor (or chamber) of epitaxy equipment. The silicon wafer 1 can be prepared before epitaxial growth, in order to clean its surface (that is to say, to remove organic or metallic dopants or particulate contaminations) and to remove from its surface a layer of native oxide. Cleaning is generally carried out with conventional wet cleaning treatments. The deoxidation can be

carried out by wet or dry chemical etching, prior to placing the silicon wafer 1 in the reactor; it can also be carried out by exposing the silicon wafer 1 in the reactor to a reducing atmosphere at a temperature of at least 900°C.

Stage b) is targeted at growing an epitaxial layer 2 of intrinsic silicon. Its resistivity is greater than 2000 ohm.cm and its thickness ranges from 2 to 100 microns.

Advantageously, the epitaxial growth of the silicon layer is carried out at high temperatures, ranging from 1000°C to 1200°C, under atmospheric or reduced pressure with conventional sources of gaseous silicon, such as trichlorosilane (TCS), dichlorosilane (DCS) or silane (SiH_4).

The process according to the invention then comprises a stage c) consisting in forming an amorphous or polycrystalline passivation layer 3 on the epitaxial layer 2 of silicon.

According to a first option, the formation of the said passivation layer 3 is carried out in the same reactor as that used for the epitaxial growth. This is advantageous since the base substrate 12 remains *in situ*, under a controlled atmosphere. On the one hand, this avoids breaking the vacuum and thus improves the crude treatment time and the overall efficiency of the process; on the other hand, it prevents the base substrate 12 from catching contaminants originating from the ambient atmosphere, such as boron particles or residues which may be present in the clean room. It is thus possible to protect and maintain the interface between the epitaxial layer 2 of silicon and the passivation layer 3 with a high resistivity.

According to a second option, the formation of the passivation layer 3 is carried out in a second reactor sharing

the same transfer module with the first reactor used for the epitaxial layer of silicon, under vacuum or an argon or nitrogen atmosphere. Here again, the vacuum is not broken and the base substrate 12 remains *in situ*, under a controlled atmosphere, preventing *ex situ* contaminations and guaranteeing that the interface between the epitaxial layer 2 of silicon and the passivation layer 3 exhibits a high resistivity. In addition, this second option facilitates the cleaning of the reactors. This is because the epitaxial silicon material deposited on the interior walls of the first reactor (from a few microns to a few tens of microns) during the epitaxial growth can be removed more easily if no carbonization or nitridation has been carried out over it. The passivation layer 3 formed by carbonization or nitridation in the second reactor is formed only on the silicon material, that is to say only on the epitaxial layer of silicon. Consequently, this has no impact on the parts positioned inside the second reactor since the carbonization and the nitridation are reactions occurring between the source gases and the silicon surface. The fact of carrying out stages b) and c) in separate first and second reactors makes possible better management of the cleaning and of the performance qualities of the chambers.

Of course, according to a third option, the base substrate 12 can be removed from the first reactor in order to return it to the atmosphere of the clean room. In such a case, the base substrate 12 can be prepared before formation of the passivation layer, in order to clean the surface of the epitaxial layer of silicon (that is to say, to remove organic or metallic dopants or particulate contaminants) and to remove from said surface a layer of native oxide. The cleaning can be carried out with conventional wet cleaning treatments. The deoxidation can be carried out by wet or dry chemical etching. The deoxidation can alternatively be carried out after loading the base substrate 12 into the reactor, by exposing it to a reducing

atmosphere at a temperature of at least 800°C. This stage is not, however, compulsory and this native oxide can be retained. This is because it is thin enough, from 1 to 2 nm in thickness, not to have an insulating effect (conduction through this layer by tunnel effect) in so far as future heat treatments will not have made it completely disappear by dissolution.

According to any one of the abovementioned options, after having been placed in a reactor, the base substrate 12 undergoes the formation of the passivation layer 3.

According to a first embodiment, stage c) comprises a carbonization of the free surface of the epitaxial layer 2 of silicon, so as to form a passivation layer 3 made of polycrystalline silicon carbide.

To do this, the base substrate 12, and more particularly the free surface of the epitaxial layer 2 of silicon, is exposed to a single carbon precursor gas at a pressure below atmospheric pressure, for example of between 0.01 Torr and 760 Torr. The carbon precursor gas can be composed of methane (CH_4), ethane (C_2H_6), propane (C_3H_8), acetylene (C_2H_2), ethylene (C_2H_4), and the like. The precursor gas can be introduced into the reactor (or heated inside the reactor) at a temperature of between 700°C and 1200°C, so that the carbon-based entities carry out a nucleation on the surface of the epitaxial layer 2 of silicon. A stream of carrier gas (such as H_2) can also be introduced simultaneously into the chamber but no other precursor gas than the carbon precursor gas flows over the base substrate 12. By avoiding the reaction of the carbon-based entity with other entities of a second precursor, the deposition of carbon-based compound on the wall of the reactor is limited and the generation of particles is avoided.

It has surprisingly been observed that, when this carbonization stage is carried out under a reduced partial carbon pressure, of less than 760 Torr, the nucleation of the carbon-based entity takes place on isolated islets on the surface. The silicon atoms of the base wafer then diffuse into the carbon islets, forming islets of silicon carbide which are stoichiometric or close to the state of stoichiometry of 3C/6H and 4H type. The islets coalesce to form a relatively thick layer of polycrystalline silicon carbide. When the stream of carbon precursor gas is maintained for a few minutes, the thickness of the polycrystalline layers increases up to several nanometres.

In a particular example, a carbon precursor gas made of C_3H_8 , mixed with H_2 in a 180 sccm/5 slm ratio, is introduced into and circulated for 5 minutes at a pressure of 10 Torr in the chamber and is heated to 1000°C. A polycrystalline passivation layer 3 made of silicon carbide having a thickness of 10 nm is then observed on the surface of the epitaxial layer 2 of silicon.

When the carbonization stage is carried out at a higher partial carbon pressure, of greater than 760 Torr, a completely different phenomenon takes place on the surface of the base substrate 12. The carbon-based entities carry out a nucleation with a high density on the surface and block the diffusion of the silicon atoms from this surface. A crystalline or partially crystalline layer of carbon then grows slowly on the surface, aligned with the silicon lattice, in a 3C structure. Such a layer typically exhibits a thickness of 2 nm after 10 minutes of deposition.

It consequently appears that circulating a single carbon precursor gas at reduced partial carbon pressure over the base substrate 12 is a very effective means for forming a relatively

thick (greater than 5 nm or 10 nm) layer of polycrystalline silicon carbide. Such a passivation layer 3 is advantageous because, by virtue of its polycrystalline nature, it thus makes it possible to prepare and to preserve the polycrystalline nature of the charge-trapping layer 4 which is grown on it. In addition, the relatively large thickness of the passivation layer is formed quite rapidly and constitutes an effective barrier to diffusion for preventing the migration of doping entities from the base substrate 12 to the charge-trapping layer 4.

In addition, it has been observed that such a carbonization stage, under reduced partial carbon pressure, incorporated very little in the way of dopants (such as boron) in the passivation layer 3 made of silicon carbide. Measurements have shown a boron concentration of less than 10^{14} atoms/cm³ in such a layer. It is believed that the dopant entities (possibly present at the surface of the base substrate 12 or incorporated in the latter) are diffused out of the silicon carbide layer during its formation and evacuated from the deposition chamber (or reactor) with the precursor gas and carrier gas.

According to a second embodiment, stage c) comprises a nitridation of the free surface of the epitaxial layer 2 of silicon, so as to form a passivation layer 3 made of silicon nitride.

To do this, the base substrate 12, and more particularly the free surface of the epitaxial layer 2 of silicon, is exposed to a nitrogen-precursor gas at a pressure of, for example, between 0.1 Torr and 760 Torr. The precursor gas can be composed of ammonia (NH₃). The precursor gas can be introduced into the chamber (or heated inside the chamber) at a temperature of

between 800°C and 1300°C, so that the nitrogen-based entities nucleate on the surface of the epitaxial layer 2 of silicon.

After stage c), a passivation layer made of silicon nitride is obtained. Such a passivation layer typically exhibits a thickness of less than 10 nm after 10 seconds to 60 minutes of nitridation.

Such a passivation layer 3 is advantageous because, by virtue of its non-epitaxial nature on silicon, it thus makes it possible to prepare and to preserve the polycrystalline nature of the charge-trapping layer 4 which is grown on it. The passivation layer 3 is formed quite rapidly only on the silicon and constitutes an effective barrier to diffusion for preventing the migration of doping species from the base substrate 12 to the charge-trapping layer.

On the basis of either one of the first and second embodiments, after the growth of the passivation layer 3 on the base substrate 12, another stream of precursor gas, at a temperature of the order of 1000°C, is passed through the reactor in order to form, in a conventional way, a polycrystalline charge-trapping layer 4: this is stage d) of the process according to the invention. The duration of circulation of the precursor gas determines the thickness of the polycrystalline layer 4 and this duration can be chosen so as to grow a layer of 5 microns, 10 microns or more.

Advantageously, the passivation layer 3 and the polycrystalline charge-trapping layer 4 are formed *in situ*, in the same reactor or chamber. This avoids contaminating the stack of layers with dopants or contaminants originating from the ambient atmosphere and preserves the characteristics of high resistivity of the handle substrate 100.

To be complete, the handle substrate 100 can be provided with a dielectric layer 5, for example a silicon oxide or a silicon nitride, deposited in a conventional way. The said dielectric layer 5 and/or the polycrystalline charge-trapping layer 4 can also be polished, in order to provide an upper surface of the handle substrate 100 compatible with a conventional stage of transfer of a thin film 6 onto the said handle substrate 100.

Of course, the invention is not limited to the embodiment described and alternative embodiments can be contributed thereto without departing from the scope of the invention as defined by the claims.

CLAIMS

1. Handle substrate (100) for a composite structure comprising:

- a base substrate (12) formed of an epitaxial layer ((2) of silicon on a monocrystalline silicon wafer (1) obtained by Czochralski pulling, having a resistivity of between 10 and 500 ohm.cm, the said epitaxial layer (2) of silicon exhibiting a resistivity of greater than 2000 ohm.cm and a thickness ranging from 2 to 100 microns,
- a passivation layer (3) on and in contact with the epitaxial layer (2) of silicon, the said passivation layer (3) being amorphous or polycrystalline,
- a charge-trapping layer (4) on and in contact with the passivation layer (3),

the handle substrate (100) being characterized in that:

- the passivation layer (3) is a layer of silicon carbide formed by carbonization of the surface of the epitaxial layer (2) of silicon, or
- the passivation layer (3) is a layer of silicon nitride formed by nitridation of the surface of the epitaxial layer (2) of silicon.

2. Composite structure (110) for radiofrequency applications comprising:

- a handle substrate (100) according to the preceding claim,
- a dielectric layer (5) on and in contact with the charge-trapping layer (4),
- a thin film (6) on the dielectric layer (5), suitable for radiofrequency devices.

3. Process for the formation of a handle substrate (100) for a composite structure, the process comprising:

- a) the provision of a monocrystalline silicon wafer (1) obtained by Czochralski pulling having a resistivity of between 10 and 500 ohm.cm;
- b) the growth of an epitaxial layer (2) of silicon on the monocrystalline silicon wafer (1) obtained by Czochralski pulling to form a base substrate (12), the said epitaxial layer (2) of silicon exhibiting a resistivity of greater than 2000 ohm.cm and a thickness ranging from 2 to 100 microns;
- c) the formation of a passivation layer (3) on the epitaxial layer (2) of silicon, the said passivation layer (3) being amorphous or polycrystalline;
- d) the growth of a polycrystalline charge-trapping layer (4) on the passivation layer (3);

the process being characterized in that stage c) comprises:

- a carbonization of the surface of the epitaxial layer (2) of silicon, so as to form a passivation layer (3) made of polycrystalline silicon carbide, or
- a nitridation of the surface of the epitaxial layer (2) of silicon, so as to form a passivation layer (3) made of silicon nitride.

4. Process according to the preceding claim, in which the carbonization of stage c) comprises the exposure of the base substrate (12) to a single carbon precursor at a pressure below atmospheric pressure in order to form a passivation layer (3) of polycrystalline silicon carbide of at least 5 nm on the surface of the epitaxial layer (2) of silicon.

5. Process according to the preceding claim, in which the said single carbon precursor exhibits a temperature of between 700°C and 1200°C.

6. Process according to any one of Claims 3 to 5, in which the passivation layer (3) exhibits a thickness of at least 10 nm.
7. Process according to any one of Claims 3 to 6, in which the charge-trapping layer (4) has a thickness of greater than 5 or 10 microns.
8. Process according to any one of Claims 3 to 7, in which the charge-trapping layer (4) is made of polycrystalline silicon.
9. Process according to any one of Claims 3 to 8, in which stages b), c) and d) are all carried out successively *in situ* in epitaxy equipment.
10. Process according to the preceding claim, in which stage b) is carried out in a first reactor and stages c) and d) are carried out in a second reactor, and in which the transfer of the base substrate (12) from the first reactor to the second is carried out without breaking the vacuum.