

Description

The present invention relates to a green light emitting phosphor, particularly a green light emitting phosphor of high excitation, which can be applied to, for example, a projector tube or a high-brightness phosphor display tube.

Among the known Tb (terbium) activated green light emitting phosphors, the phosphor $Y_3(Al, Ga)_5O_{12}:Tb$ provides excellent brightness and saturation characteristic through the addition of Ga (gallium) as a green light emitting phosphor which is excited by electron beams of high energy. This is disclosed, for example, in Japanese Laid-Open Patent Gazette No. 60-101175.

A disadvantage of this known green light emitting phosphor is that it will deteriorate through the irradiation of electron beams. In other words, the body color of the green light emitting phosphor is changed by a so-called "burning". The burning occurs when the green light emitting phosphor is heated by the irradiation of electron beams. For example, when a phosphor screen of a projector tube or of a high-brightness phosphor display tube is formed using this type of known phosphor, and electron beams continuously impinge on the phosphor screen, in order to display a still image or a still picture portion of an image, the "electron beam burning" occurs locally, and deteriorates the image quality.

Figure 1 shows the measured results of relative brightness versus aging time of phosphor screens. In the example used with this figure, the phosphor screens for an 8-inch projector tube were formed of green light emitting phosphors, $Y_3Al_xGa_{5-x}O_{12}:Tb$ of 7 mol percent, and the amount of Ga was changed, respectively. These phosphors were continuously irradiated with electron beams under conditions where the phosphor screen voltage (anode voltage, i.e. excitation voltage) was 32 kV and the anode current was 5 $\mu A/cm^2$. An initial brightness was taken as a reference (100%).

In Figure 1, an open square, an open circle, and an open triangle chart the measured results of the relative brightness of the green light emitting phosphors where $x = 0, 3$, and 5 in $Y_3Al_xGa_{5-x}O_{12}:Tb$, respectively. When comparing curves 1, 2, and 3, which follow from the measured results, it is shown that as the amount of Ga increases, the amount of electron beam burning, i.e. the amount of deterioration of brightness of the green light emitting phosphor by the irradiation of electron beams, is increased. Although the brightness and saturation characteristics of the green light emitting phosphor are improved by the substitution of Ga, it is unavoidable that the irradiation of electron beams will cause the brightness of the green light emitting phosphor to deteriorate.

One of the reasons for the deterioration of the brightness of the green light emitting phosphor is the valence state of Tb. Tb enters this type of phosphor at a so-called Y site, in the form of a trivalent. Unfortunately, Tb is in a stable condition when it is in the form of a tetravalent. If the phosphor is irradiated by electron beams, Tb's valence state can easily shift to that of a tetravalent element which causes the body color of the green light emitting phosphor to become brownish. In addition, Tb enters the Y site in an unstable state which causes a deterioration of the brightness characteristic of the green light emitting phosphor.

It is an object of the present invention to provide an improved green light emitting phosphor which can eliminate the defects encountered with known green light emitting phosphors. A further object is to provide a green light emitting phosphor which can resolve the problem of electron beam burning in the known $Y_3(Al, Ga)_5O_{12}:Tb$ green light emitting phosphor. Another object of the present invention is to provide a green light emitting phosphor which improves on preventing the lowering of the brightness of the phosphor by the excitation of high energy. Another object is to provide a green light emitting phosphor which is suitable for being applied to a projector tube, a phosphor display tube of high brightness or the like.

To this end, the present invention provides a green light emitting phosphor comprising a green light emitting phosphor having a formula $Y_3(Al, Ga)_5O_{12}:Tb$ and a tetravalent element by a molar ratio relative to a sum of Y and Tb ranging from 1×10^{-5} to 5×10^{-1} .

In an embodiment, the molar ratio ranges from approximately 1×10^{-5} to 1×10^{-3} .

In an embodiment, the tetravalent element is chosen from the group consisting of Si^{4+} , Ge^{4+} , Ti^{4+} , Zr^{4+} , Hf^{4+} , and Sn^{4+} .

In an embodiment, the phosphor is particularly suitable for being applied to a projector tube or a high-brightness phosphor display tube.

In an embodiment, the method for producing the phosphor includes adding a green light emitting phosphor $Y_3(Al, Ga)_5O_{12}:Tb$ to a tetravalent element by a molar ratio relative to the sum of Y and Tb ranging from 1×10^{-5} to 5×10^{-1} .

Figure 1 is a graph showing the measured results of aging time versus relative brightness of the phosphor screen when the electron beam impinges on the phosphor screen;

Figure 2 is a graph displaying a relationship between the amount of Si added to a phosphor and the relative brightness of the phosphor;

Figure 3 is a spectrum diagram of a small angle x-ray diffraction analysis; and

Figure 4 is a graph showing measured results of the inclination of a current versus brightness curve.

The present invention relates to a green light emitting phosphor and, particularly, a green light emitting phosphor of high excitation which is suitable for being applied, for example, to a projector tube, a high-brightness phosphor display tube or the like.

Examples:

By way of example, and not limitation, examples of the present invention will now be given.

Example 1:

A green light emitting phosphor of high excitation type, $Y_3Al_3Ga_2O_{12}:Tb$ phosphor was made. The molar ratio of Al/Ga was 1.5. The ratio of Tb/(Y + Tb) was 0.07, and the Si/(Y + Tb) ratio was 2.8×10^{-3} . As raw materials, the following powders were prepared:

Y_2O_3	31.05g
Al_2O_3	15.29g
Ga_2O_3	18.74g
Tb_4O_7	3.93g
SiO_2	0.05g

(purity of each of these powders is a so-called four nine, i.e. 99.99%). These powders were added together, along with the highest class reagent, BaF_2 which forms residual flux. The materials were then mixed with a solvent of 120cc of ethanol with a ball mill. According to this ball mixing-process, an alumina ball, which was 5mm in diameter and had a purity of more than 99.8%, was prepared. The raw materials in the alumina balls, whose amount was about 2 to 3 times that of the raw materials, for example 150g in weight, were then put into a 0.5 liter receptacle which was made of a polyethylene-system material. The raw materials and alumina balls were mixed for five hours. The receptacle was rotated at a rotation rate of 60 rpm.

The alumina balls and the mixed raw materials were then separated by a filtering-process or the like. The ethanol was removed from the product by a drying-process. The dried raw material was then put into a crucible, which had a lid of alumina of a high purity (higher than 99.8%). The lid and the crucible body were shielded by a heat-resistant bonding agent, for example, Aron Ceramic D (trade name, manufactured by Toagosei Chemical Industry Co., Ltd.). The crucible was placed in a furnace and heated up to $1500^\circ C$ by raising the temperature by $200^\circ C$ per hour. The crucible was kept at that temperature, i.e. $1500^\circ C$, for two hours, and then cooled in the furnace. The burned phosphor was rinsed with 10cc of nitric acid with the normal 1.5 per 1g of burned phosphor for 60 minutes in order to remove residual flux (BaF_2) in the burned phosphor. The phosphor was then rinsed with water to provide a pH of 7. Finally, it was filtered and dried. Thus, the green light emitting phosphor $Y_3Al_3Ga_2O_{12}:Tb$, with 7 mol percent of Tb, was produced.

The phosphor was then used in the manufacture of a phosphor screen of an 8-inch projector tube. The screen was manufactured by a printing-process. This phosphor screen was then aged under conditions where the anode voltage was 32 kV and the anode current was $5\mu A/cm^2$. Figure 1 shows the measured results of the aging time versus the relative brightness of the phosphor screen. In the figure, a solid square, a solid circle, and a solid triangle, respectively, plot respective brightness of the phosphors in which x was selected to be 0, 3, and 5, in the phosphor composition, $Y_3Al_xGa_{1-x}O_{12}:Tb$ of 7 mol percent of Tb, respectively. Comparing characteristic curves 11, 12, and 13 with the prior art curves 1, 2, and 3, the graph illustrates that when Si was added to the phosphor in Example 1, the deterioration of brightness, i.e. electron beam burning, could be considerably reduced.

Example 2:

A green light emitting phosphor was made similar to the phosphor of Example 1. The phosphor without Si was used as the basis for this example. The phosphor's initial relative brightness was then measured while the amount of Si added was changed. The measured results are represented in Figure 2. In Figure 2, a solid square, a solid circle, and a solid triangle, respectively, represent relative brightness of the green

light emitting phosphors in which x was selected to be 0, 3, and 5 in composition, $Y_3Al_xGa_{5-x}O_{12}:7$ and 1% Tb, respectively. Figure 2 reveals that the addition of Si can prevent the initial brightness of the green light emitting phosphors from being lowered.

Example 3:

A $Y_3Al_2Ga_3O_{12}:Tb$ of 7 mol percent was produced according to the method of Example 1 where 5×10^{-1} mol of Si was added. Figure 3 is a spectrum diagram of a small x-ray diffraction of the phosphor of this example and a phosphor without Si. Characteristic curve 31 represents the phosphor of Example 3, and curve 32 represents the phosphor without Si. Comparing curves 31 and 32, the diagram illustrates that the change of spectrum is not observed and also, that Si is absorbed into the phosphor. Therefore, when Si is added thereto, Si is not deposited as SiO_2 , and the generation of single-phase YAG is not affected.

More specifically, Figure 4 shows the measured results of the inclination of a current versus brightness curve, i.e. the relationship between a so-called gamma (γ) value and the added amount of Ga. In Figure 4, a solid circle represents the measured results of gamma values in which Si of 5×10^{-1} mol was added. An open circle represents the measured results of gamma values in which Si was not added to the phosphor. The graph in Figure 4, shows that the current brightness saturation characteristic does not change substantially, regardless of the addition of Si.

While Si^{4+} is added to $Y_3Al_xGa_{5-x}O_{12}:Tb$ in the above examples, other tetravalent elements, Ge^{4+} , Ti^{4+} , Zr^{4+} , Hf^{4+} and Sn^{4+} can be added to the phosphor and achieve similar results as when Si^{4+} was added. Table 1 shows the observed results of electron beam burning when certain amounts of the above tetravalent elements were added to $Y_3Al_xGa_{5-x}O_{12}:Tb$. A so-called demountable apparatus, in which a phosphor screen panel of a cathode ray tube can be demounted, was employed in this experiment. Electron beams were impinged on the phosphor screen panel for 60 minutes under the excitation conditions of an anode voltage of 18 kV and an anode current of $100\mu A/cm^2$. The decrease of brightness, i.e. electron beam "burning", was measured in the table. In the table, an open circle represents a phosphor where the decrease in brightness is less than 10% of the initial brightness of the phosphor before it was irradiated with electron beams. An open triangle represents a phosphor where the decrease in brightness is 10 to 20% of the initial brightness of the phosphor before it was irradiated with electron beams. A cross mark represents a phosphor where the decrease in brightness is more than 20% of the initial brightness of the phosphor before it was irradiated with electron beams.

TABLE 1

Elements to be added	Adding amount (molar ratio)	Electron beam "burning"
None		×
Si ⁴⁺	1 × 10 ⁻⁶	△
	1 × 10 ⁻⁵	○
	1 × 10 ⁻³	○
	5 × 10 ⁻¹	○
	1.0	△
Ge ⁴⁺	1 × 10 ⁻⁶	△
	1 × 10 ⁻⁵	○
	1 × 10 ⁻³	○
	5 × 10 ⁻¹	○
	1.0	×
Ti ⁴⁺	1 × 10 ⁻⁶	△
	1 × 10 ⁻⁵	○
	1 × 10 ⁻³	○
	5 × 10 ⁻¹	○

Elements to be added	Adding amount (molar ratio)	Electron beam "burning"
	1.0	×
Zr ⁴⁺	1 × 10 ⁻⁶	×
	1 × 10 ⁻⁵	○
	1 × 10 ⁻³	○
	5 × 10 ⁻¹	○
	1.0	×
Hf ⁴⁺	1 × 10 ⁻⁶	×
	1 × 10 ⁻⁵	○
	1 × 10 ⁻³	○
	5 × 10 ⁻¹	○
	1.0	×
Sn ⁴⁺	1 × 10 ⁻⁶	△
	1 × 10 ⁻⁵	○
	1 × 10 ⁻³	○
	5 × 10 ⁻¹	○
	1.0	△

From the results in Table 1, it is shown that when a tetravalent element is added to Y₃Al_xGa_{5-x}O₁₂:Tb in a molar ratio of the sum of Y and Tb ranging from 1×10⁻⁵ to 5×10⁻¹, the electron beam burning can be effectively improved.

Therefore, since the electron beam burning can be effectively improved, the green light emitting phosphor of the present invention can be suitably used for various kinds of display tubes and image

reproducing apparatus of the electron beam excitation type. According to the present invention, when the phosphor screen of the projector tube or the phosphor display tube of high brightness is formed of the green light emitting phosphor of the present invention, the image quality can be prevented from deteriorating. This is so even if a still picture is displayed on the phosphor screen or the phosphor screen is continuously impinged with electron beams in order to display a still portion of an image, or the phosphor screen is driven for a long period of time. Furthermore, the green light emitting phosphor of the present invention makes it possible to display a high-definition image which is very beneficial in practice.

Claims

10

1. A green light emitting phosphor comprising
 - a) a green light emitting phosphor having the formula $Y_3(Al,Ga)_5O_{12}:Tb$; and
 - b) a tetravalent element selected from the group consisting of Si^{4+} , Ge^{4+} , Ti^{4+} , Zr^{4+} , Hf^{4+} and Sn^{4+} , wherein the molar ratio of the tetravalent element to the sum of Y and Tb ranges from 1×10^{-5} to 5×10^{-1} .
2. The phosphor of claim 1, wherein the molar ratio ranges from 1×10^{-5} to 1×10^{-3} .
3. A method for producing the green light emitting phosphor according to claims 1 and 2 comprising adding a green light emitting phosphor having the formula $Y_3(Al,Ga)_5O_{12}:Tb$ to a tetravalent element selected from the group consisting of Si^{4+} , Ge^{4+} , Ti^{4+} , Zr^{4+} , Hf^{4+} and Sn^{4+} in a molar ratio of the tetravalent element to the sum of Y and Tb in the range of from 1×10^{-5} to 5×10^{-1} .
4. The use of the green light emitting phosphor according to claims 1 and 2 for projector tubes and high-brightness phosphor display tubes.

Patentansprüche

1. Grünlichtemittierender Leuchtstoff, umfassend
 - a) einen grünlichtemittierenden Leuchtstoff der Formel $Y_3(Al,Ga)_5O_{12}:Tb$; und
 - b) ein vierwertiges Element, welches aus der aus Si^{4+} , Ge^{4+} , Ti^{4+} , Zr^{4+} , Hf^{4+} und Sn^{4+} bestehenden Gruppe gewählt ist, wobei das Molverhältnis des vierwertigen Elements zu der Summe aus Y und Tb im Bereich von 1×10^{-5} bis 5×10^{-1} liegt.
2. Leuchtstoff nach Anspruch 1, wobei das Molverhältnis im Bereich von 1×10^{-5} bis 1×10^{-3} liegt.
3. Verfahren zur Herstellung des grünlichtemittierenden Leuchtstoffs nach den Ansprüchen 1 und 2, umfassend das Zugabe eines grünlichtemittierenden Leuchtstoffs der Formel $Y_3(Al,Ga)_5O_{12}:Tb$ zu einem vierwertigen Element, welches aus der aus Si^{4+} , Ge^{4+} , Ti^{4+} , Zr^{4+} , Hf^{4+} und Sn^{4+} bestehenden Gruppe gewählt wird, in einem Molverhältnis des vierwertigen Elements zu der Summe aus Y und Tb im Bereich von 1×10^{-5} bis 5×10^{-1} .
4. Verwendung des grünlichtemittierenden Leuchtstoffs nach den Ansprüchen 1 und 2 für Projektorröhren und Leuchtstoff-Anzeigeröhren hoher Helligkeit bzw. Leuchtstärke.

Revendications

1. Luminophore émettant une lumière verte comprenant :
 - a) un luminophore émettant une lumière verte ayant la formule $Y_3(Al,Ga)_5O_{12}:Tb$; et
 - b) un élément tétravalent sélectionné dans le groupe se composant de Si^{4+} , Ge^{4+} , Ti^{4+} , Zr^{4+} , Hf^{4+} et Sn^{4+} , Dans laquelle le rapport moléculaire de l'élément tétravalent sur la somme de Y et de Tb est compris dans la plage de 1×10^{-5} à 5×10^{-1} .
2. Luminophore selon la revendication 1 dans laquelle le rapport moléculaire est compris dans la plage de 1×10^{-5} à 1×10^{-3} .



reproducing apparatus of the electron beam excitation type. According to the present invention, when the phosphor screen of the projector tube or the phosphor display tube of high brightness is formed of the green light emitting phosphor of the present invention, the image quality can be prevented from deteriorating. This is so even if a still picture is displayed on the phosphor screen or the phosphor screen is continuously impinged with electron beams in order to display a still portion of an image, or the phosphor screen is driven for a long period of time. Furthermore, the green light emitting phosphor of the present invention makes it possible to display a high-definition image which is very beneficial in practice.

Claims

1. A green light emitting phosphor comprising
 - a) a green light emitting phosphor having the formula $Y_3(Al,Ga)_5O_{12}:Tb$; and
 - b) a tetravalent element selected from the group consisting of Si^{4+} , Ge^{4+} , Ti^{4+} , Zr^{4+} , Hf^{4+} and Sn^{4+} , wherein the molar ratio of the tetravalent element to the sum of Y and Tb ranges from 1×10^{-5} to 5×10^{-1} .
2. The phosphor of claim 1, wherein the molar ratio ranges from 1×10^{-5} to 1×10^{-3} .
3. A method for producing the green light emitting phosphor according to claims 1 and 2 comprising adding a green light emitting phosphor having the formula $Y_3(Al,Ga)_5O_{12}:Tb$ to a tetravalent element selected from the group consisting of Si^{4+} , Ge^{4+} , Ti^{4+} , Zr^{4+} , Hf^{4+} and Sn^{4+} in a molar ratio of the tetravalent element to the sum of Y and Tb in the range of from 1×10^{-5} to 5×10^{-1} .
4. The use of the green light emitting phosphor according to claims 1 and 2 for projector tubes and high-brightness phosphor display tubes.

Patentansprüche

1. Grünlichtemittierender Leuchtstoff, umfassend
 - a) einen grünlichtemittierenden Leuchtstoff der Formel $Y_3(Al,Ga)_5O_{12}:Tb$; und
 - b) ein vierwertiges Element, welches aus der aus Si^{4+} , Ge^{4+} , Ti^{4+} , Zr^{4+} , Hf^{4+} und Sn^{4+} bestehenden Gruppe gewählt ist, wobei das Molverhältnis des vierwertigen Elements zu der Summe aus Y und Tb im Bereich von 1×10^{-5} bis 5×10^{-1} liegt.
2. Leuchtstoff nach Anspruch 1, wobei das Molverhältnis im Bereich von 1×10^{-5} bis 1×10^{-3} liegt.
3. Verfahren zur Herstellung des grünlichtemittierenden Leuchtstoffs nach den Ansprüchen 1 und 2, umfassend das Zugabe eines grünlichtemittierenden Leuchtstoffs der Formel $Y_3(Al,Ga)_5O_{12}:Tb$ zu einem vierwertigen Element, welches aus der aus Si^{4+} , Ge^{4+} , Ti^{4+} , Zr^{4+} , Hf^{4+} und Sn^{4+} bestehenden Gruppe gewählt wird, in einem Molverhältnis des vierwertigen Elements zu der Summe aus Y und Tb im Bereich von 1×10^{-5} bis 5×10^{-1} .
4. Verwendung des grünlichtemittierenden Leuchtstoffs nach den Ansprüchen 1 und 2 für Projektorröhren und Leuchtstoff-Anzeigeröhren hoher Helligkeit bzw. Leuchtstärke.

Revendications

1. Luminophore émettant une lumière verte comprenant :
 - a) un luminophore émettant une lumière verte ayant la formule $Y_3(Al,Ga)_5O_{12}:Tb$; et
 - b) un élément tétravalent sélectionné dans le groupe se composant de Si^{4+} , Ge^{4+} , Ti^{4+} , Zr^{4+} , Hf^{4+} et Sn^{4+} , Dans laquelle le rapport moléculaire de l'élément tétravalent sur la somme de Y et de Tb est compris dans la plage de 1×10^{-5} à 5×10^{-1} .
2. Luminophore selon la revendication 1 dans laquelle le rapport moléculaire est compris dans la plage de 1×10^{-5} à 1×10^{-3} .



3. Procédé pour produire le luminophore émettant une lumière verte selon les revendications 1 et 2 comprenant l'addition d'un luminophore émettant une lumière verte ayant la formule $Y_3(Al, Ga)_5O_{12}:Tb$ à un élément tétravalent sélectionné à partir du groupe se composant de Si^{4+} , Ge^{4+} , Ti^{4+} , Zr^{4+} , Hf^{4+} et Sn^{4+} avec un rapport moléculaire de l'élément tétravalent sur la somme de Y et de Tb compris dans la gamme de 1×10^{-5} à 5×10^{-1} .
4. L'utilisation du luminophore émettant une lumière verte selon les revendications 1 et 2 pour des tubes de projection des tubes de visualisation à base de luminophore de luminosité élevée.

10

15

20

25

30

35

40

45

50

55