

TITLE: METHOD FOR THE PRODUCTION OF HYDROGEN FROM AMMONIA BORANE

FIELD OF THE DISCLOSURE

The present disclosure relates to methods of producing hydrogen, in particular from the transition-metal catalyzed hydrolysis or solvolysis of ammonia borane and its derivatives.

BACKGROUND

The world is currently experiencing a severe environmental crisis due to high atmospheric carbon dioxide levels, in addition to an impending energy shortage. Both of these problems are a direct result from excessive fossil fuel utilization. The use of hydrogen (H_2) as a fuel offers one highly attractive solution to these problems since the combustion of hydrogen (in a fuel cell, for example) produces only water and hence is free of emissions containing carbon and other pollutants.

Hydrogen gas contains more energy per mass unit than any known combustible fuel (approximately three times as much as gasoline). However, the use of hydrogen as a fuel has some drawbacks, since under ambient conditions it is an extremely low density gas. Hydrogen can be liquefied, cryogenically or with very high pressures (b.p., 1 atm.: $-253\text{ }^{\circ}\text{C}$). These extreme conditions limit the potential widespread and large scale use of hydrogen.

A simple solution to these problems is to store the hydrogen chemically in a material that contains a very high weight percentage of hydrogen in a system that is capable of releasing the hydrogen on demand. Various compounds are known that contain a high gravimetric amount of hydrogen. Many of these compounds (e.g. lithium hydride (LiH , 12.8 wt% hydrogen) or lithium aluminum hydride ($LiAlH_4$, 10.6 wt% hydrogen)) or alane (AlH_3 , 9 wt% hydrogen, Sandrock, G.; Reilly, J.; Graetz, J.; Wegrzyn, J. "Activated Aluminum Hydride Hydrogen Storage Compositions and Uses Thereof" U.S. Patent Application Publication No. 2007-0025908) suffer from being highly reactive or even potentially explosive and thus it is unlikely that commercial applications utilizing these compounds will be developed. Hydrogen generation by hydrolysis of magnesium hydride (MgH_2) is a safer method but

usage of metal hydrides will be problematic due to their inherent water sensitivity (U.S. Patent 5,198,207, "Method for the Preparation of Active Magnesium Hydride-Magnesium Hydrogen Storage Systems, Which Reversibly Absorb Hydrogen", Wilfried Knott, Klaus-Dieter Klein, Gotz Koerner, Th. Goldschmidt AG, October 30, 1991) which can easily cause hydrogen formation under unwanted conditions.

The relatively benign compound ammonia borane (AB = NH_3BH_3 , 19.6 wt% hydrogen) has been indicated by the United States Department of Energy to be number two on the list of potential hydrogen storage materials in terms of hydrogen content; the number one material is methane (CH_4), combustion of which will lead to the obvious problem of further carbon dioxide emissions. Clearly, AB has significant advantages over all other known materials in applications where hydrogen is required as an energy carrier.

The United States Department of Energy has funded a significant amount of research, summarized below, that is relevant to this work. For example, a very efficient homogenous iridium catalyst for the dehydrogenation of AB was discovered by Goldberg's group which demonstrates fast release of H_2 gas within 20 minutes at room temperature (Denney, M. C.; Pons, V.; Hebden, T. J.; Heinekey, D. M.; Goldberg, K. I. *J. Am. Chem. Soc.* 2006, 128, 12048-12049). However, the system can only generate one equivalent of hydrogen and the insoluble boron-nitrogen containing materials (borazanes) that are formed are very difficult to recycle. Baker and co-workers described the acid initiation of AB dehydrogenation for hydrogen storage. (Stephens, F. H.; Baker, R. T.; Matus, M. H.; Grant, D. J.; Dixon, D. A. *Angew. Chem. Int. Ed.* 2007, 46, 746 – 749). However, their use of an air sensitive, strong Brønsted acid (e.g. trifluoromethanesulfonic acid) or strong Lewis acid (e.g. tris(pentafluorophenyl)borane) may prohibit their actual on-board applications. Baker has also reported the use of a homogeneous nickel containing catalyst that is capable of effecting ammonia borane dehydrogenation (R. J. Keaton, J. M. Blacquiere, R. T. Baker *J. Am. Chem. Soc.* 2007, 129, 1844). This highly air sensitive system exhibits very poor efficiency and requires heating to 60 °C for three hours to afford a 94 % yield of hydrogen.

Several reports have appeared from Xu and coworkers regarding heterogeneous ammonia borane hydrolysis catalysts containing noble metals

(a) Xu, Q.; Chandra, M. *J. Alloys Compd.* **2007**, 446-447, 729-732; (b) Chandra, M.; Xu, Q. *J. Power Sources* **2007**, 168, 125-142) or base metals ((a) Chandra, M.; Xu, Q. *J. Power Sources* **2006**, 163, 364; (b) Man, J.-M.; Zhang, X.-B.; Han, S.; Shioyama, H.; Xu, Q. *Angew. Chem., Int. Ed.* **2008**, 47, 2287). Mohajeri et al have reported a similar system using K_2PtCl_6 as a precatalyst (Mohajeri, M.; T-Raissi, A.; Adebisi, O. *J. Power Sources* **2007**, 167, 482-485) as well as using other noble metal catalysts (Mohajeri, M.; T-Raissi, A.; Bokerman, G. US Patent No. 7,285,142, issued October 23, 2007). These systems all use relatively high catalyst loadings and are expected to exhibit limited air stability. Additionally, the systems produce nanoparticles as the active catalysts which have unknown and potentially problematic health effects. Manners has reported heterogeneous catalysts that are capable of hydrolyzing ammonia borane which contain cobalt, rhodium or iridium (Clark, T. J.; Whittel, G. R.; Manners, I. *Inorg. Chem.* **2007**, 46, 7522). Again, the catalysts are relatively inefficient (cobalt), and require somewhat high catalyst loadings (rhodium, iridium). Xu and Chandra have demonstrated an ammonia borane hydrolysis system utilizing the solid acids Amberlyst or Dowex (Chandra, M.; Xu, Q. *J. Power Sources* **2006**, 159, 855-860, Japan patent JP 2006213563). The acids need to be regenerated periodically to retain activity. Ramachandran et al have reported catalytic hydrogen generation from ammonia borane via methanolysis (Ramachandran, P. V.; Gagare, P. D. *Inorg. Chem.* **2007**, 46, 7810, WO 2007106459). A non-catalytic system has been reported by Varma and coworkers which contains ammonia borane, aluminum powder and water (Diwan, M.; Diakov, V.; Shafirovich, E.; Varma, A. *Int. J. Hydrogen Energy* **2008**, 33, 1135-1141) and produces hydrogen via a combustion process. The system is expected to be problematic owing to the highly exothermic and potentially dangerous reaction between aluminum powder, water and ammonia borane, in addition to its non-catalytic nature. Xu and coworkers have demonstrated an electrochemical cell that utilizes a platinum or gold electrode for direct oxidation of ammonia borane (Zhang, X.-B.; Han, S.; Yan, J.-M.; Chandra, M.; Shioyama, H.; Yasuda, K.; Kuriyama, N.; Kobayashi, T.; Xu, Q. *J. Power Sources* **2007**, 168, 167-171). The authors note that the efficiency of the system must be improved before usage is feasible. Sneddon and co-workers have reported a heterogeneous system

using ammonia triborane ($\text{NH}_3\text{B}_3\text{H}_7$, 17.9 wt% hydrogen) and rhodium for chemical storage of hydrogen (Yoon, C. W.; Sneddon, L. G. *J. Am. Chem. Soc.* 2006, 128, 13993). However, ammonia triborane requires more synthetic steps and contains a lower gravimetric amount of hydrogen than ammonia borane and these facts will limit the application of ammonia triborane as a hydrogen storage material. Another ammonia borane derivative that has been reported recently is MNH_2BH_3 ($\text{M} = \text{Li}$ or Na). The material releases approximately 11 wt% ($\text{M} = \text{Li}$) or 7.5 wt% ($\text{M} = \text{Na}$) upon heating to 90 °C over ca. 19 hours (Xiong, Z.; Yong, W. K.; Wu, G.; Chen, P.; Shaw, W.; Karkamkar, A.; Autrey, T.; Jones, M. O.; Johnson, S. R.; Edwards, P. P.; David, W. I. F. *Nature Materials* 2008, 7, 138). The rate of hydrogen release will need to be improved upon dramatically before this system could be commercialized. A closely related material is $\text{Ca}(\text{NH}_2\text{BH}_3)_2$ (Diyabalanage, H. V. K.; Shrestha, R. P.; Semelsberger, T. A.; Scott, B. L.; Bowden, M. E.; Davis, B. L.; Burrell, A. K. *Angew. Chem. Int. Ed.* 2007, 46, 8995-8997). Heating this material results in hydrogen release, although it suffers from the same problem as MNH_2BH_3 ($\text{M} = \text{Li}$ or Na) in that the process occurs over a long time period. Other heterogenous systems that have been investigated include the use of polyhedral borane anion salts (such as $\text{B}_{11}\text{H}_{14}^-$, $\text{B}_{12}\text{H}_{12}^{2-}$ and $\text{B}_{10}\text{H}_{10}^{2-}$) and rhodium boride (RhB), but these studies are still very preliminary (Hawthorne, M. F. *et al.* "Chemical Hydrogen Storage Using Polyhedral Borane Anion Salts", FY 2006 Annual Progress Report, DOE Hydrogen program, IV.B.4f, 416-417). The use of anionic polyhedral borane salts will be problematic since their cost will be significantly higher than ammonia borane. Another material that is used for hydrogen generation via transition metal catalyzed hydrolysis is sodium borohydride (NaBH_4 ; 10.7 wt% hydrogen; Amendola et al, US Patent 6,534,033 granted to Millennium Cell). Sodium borohydride suffers from water sensitivity and contact of these two materials can result in hydrogen liberation in circumstances where it was not intended, dramatically increasing the risk of fire or explosion. Compared to sodium borohydride, ammonia borane forms relatively stable aqueous solutions and hence the risk of fire with ammonia borane is much lower than with sodium borohydride. Heterogeneous transition metal-catalyzed dissociation and

hydrolysis of AB has been reported (Chandra, M.; Xu. Q. *J. Power Sciences*, 2006, 156, 190-194).

SUMMARY OF THE DISCLOSURE

The present disclosure describes a method for extremely rapid
5 hydrogen generation from the relatively benign compound ammonia borane
(AB), and its derivatives $R^1R^2HNBHR^3R^4$, by metal catalyzed hydrolysis (with
water) and solvolysis (with alcohols). This method produces easily recyclable
and environmentally friendly ammonium borate salts as the only detectable
boron containing residue. The method typically produces hydrogen from AB
10 in approximately 80-98 % yield (2.4 to 2.9 equivalents hydrogen) within
minutes.

The AB hydrolysis and solvolysis reactions disclosed herein utilize
ligand-stabilized homogeneous catalysts. Several remarkably active and
reusable catalysts have been discovered which contain Co, Ru or Ir and other
15 metals with a variety of ligand systems. These include phosphines (PR_3),
bis(phosphinoxy)benzenes, bis(phosphineamino)benzenes,
bis(alkylphosphino)benzenes, aminophosphines ($H_2NCH_2CH_2PR_2$),
aminodiphosphines ($HN(CH_2CH_2PR_2)_2$), imidazolidenes, and related ligands.
AB and its derivatives form relatively stable aqueous solutions and hence the
20 risk of fire with AB is much lower than with other boron hydride materials.

Accordingly, in one aspect, there is provided a method for the
production of hydrogen comprising

(a) contacting a solution comprising at least one homogeneous ligand-
stabilized metal catalyst with at least one compound of the formula I,
25 $R^1R^2HNBHR^3R^4$ (I),
in a solvent under conditions for the solvolysis of the compound of
formula (I) to form a homogeneous solution,
wherein R^1 , R^2 , R^3 and R^4 are each simultaneously or independently
selected from H, branched or unbranched fluoro-substituted- C_{1-20} alkyl,
30 branched or unbranched C_{1-20} alkyl and C_{6-14} aryl or any two of R^1 , R^2 ,
 R^3 and R^4 are linked to form a branched or unbranched C_{2-10} alkylene,
which together with the nitrogen and/or boron atoms to which they are
attached, forms a ring, and

(b) optionally collecting hydrogen produced in the solvolysis of the compounds of formula (I).

In another aspect, there is provided a method for the solvolysis of a compound of formula (I) comprising contacting at least one compound of formula (I) with at least one homogenous ligand-stabilized metal catalyst in the presence of a solvent under conditions for the solvolysis of the compound of formula (I).

In still another aspect, there is provided a method for the hydrolysis of a compound of formula (I) as defined above comprising contacting the compound of formula (I) with at least one homogeneous ligand-stabilized metal catalyst in the presence of water under conditions for the hydrolysis of the compound of formula (I).

When the solvent comprises water the solvolysis reaction is referred to as a hydrolysis reaction.

In yet another aspect, there is provided a hydrogen generation system comprising at least one amine borane of the formula (I) as defined above, at least one homogeneous ligand-stabilized metal catalyst and a solvolytic and/or hydrolytic solvent. In an embodiment of the disclosure, the hydrogen generation system comprises a first compartment comprising the at least one amine borane of the formula (I) as defined above, a second compartment comprising the at least one ligand-stabilized metal catalyst, wherein the first or second compartment further comprises the solvent. The hydrogen generation system further comprises a means for combining the contents of the first compartment with the second compartment so that when the contents are combined, hydrogen is generated. At least one flow controller controls a flow rate of the at least one catalyst or the at least one amine borane.

In a further embodiment of the present disclosure, a proton exchange membrane fuel cell (PEMFC) is used as an electrical generator. The PEMFC comprises an ion-exchange membrane located between an anode and a cathode, said membrane, anode and cathode forming a membrane/electrode assembly (MEA), said MEA being located between a fuel gas diffusion layer and an oxidant gas diffusion layer. An oxidant flow network is in fluid connection with the fuel gas diffusion layer, the oxidant network having an input portion for supplying oxidant, and a fuel flow network fluid in fluid connection with the fuel gas diffusion layer. The fuel network has an input portion for supplying fuel, wherein the fuel flow network is fluidly connected to an amine borane dehydrogenation *in-situ* hydrogen generator. The generator comprises a first compartment that comprises at least one amine borane of the formula (I) as defined above, a second compartment comprising at least one ligand-stabilized metal catalyst, wherein the first or said second

compartment comprises a solvolytic and/or hydrolytic solvent. A means for combining the contents of the first compartment with the second compartment so that when the contents are combined, hydrogen is generated is included. At least one flow controller controls a flow rate of the at least one catalyst or
 5 the at least one amine borane.

Other features and advantages of the present disclosure will become apparent from the following detailed description. It should be understood, however, that the detailed description and the specific examples while indicating preferred embodiments of the disclosure are given by way of
 10 illustration only, since various changes and modifications within the spirit and scope of the disclosure will become apparent to those skilled in the art from this detailed description.

BRIEF DESCRIPTION OF THE DRAWINGS

The present disclosure will now be described in greater detail with
 15 reference to the following drawings in which:

Figure 1 is a schematic showing the equipment used for the metal-catalyzed hydrolysis of AB when less than 100 ml of hydrogen was generated.

Figure 2 is a schematic showing the equipment used for the metal-catalyzed hydrolysis of AB when 2000 to 8000 ml of hydrogen was generated.

20 Figure 3 is an ORTEP diagram of bis(2-(diisopropylphosphino)ethyl)aminedichlorocobalt(II).

Figure 4 is an ORTEP diagram of bis(2-(di-*tert*-butylphosphino)ethyl)aminechlorocyclooct-1-enylhydrido-iridium(III).

Figure 5 is an ORTEP diagram of bis(2-(di-
 25 cyclohexylphosphino)ethyl)aminedichlorohydrido-iridium(III).

Figure 6 is an ORTEP diagram of bis(2-(di-*tert*-butylphosphino)ethyl)methylaminechlorohydrido-phenyliridium(III).

Figure 7 is an ORTEP depiction of bis(2-(di-*iso*-propylphosphino)ethyl)aminedichlororuthenium(II) dimer [RuCl(μ -

30 Cl){NH(CH₂CH₂P^{*i*}Pr₂)₂}]₂.

Figure 8 is an ORTEP diagram of bis(2-(diisopropylphosphino)ethyl)aminecopper(I)chloride.

Figure 9 is a graph showing the volume of hydrogen gas generated over time for the hydrolysis of AB using [Co{HN(CH₂CH₂P^{*i*}Pr₂)₂Cl₂] as the catalyst.

Figure 10 is a graph showing the volume of hydrogen gas generated over time for the hydrolysis of AB using $[\text{Co}\{\text{HN}(\text{CH}_2\text{CH}_2\text{PPh}_2)_2\}\text{Cl}_2]$ as the catalyst.

Figure 11 is a graph showing the volume of hydrogen gas generated over time for the hydrolysis of AB using N^1, N^2 -bis(2-(di-*p*-tolylphosphino)benzyl)cyclohexane-1,2-diamine cobalt dichloride as the catalyst.

Figure 12 is a graph showing the volume of hydrogen gas generated over time for the hydrolysis of AB using $[\text{Ru}(\text{binap})(\text{H}_2\text{NCH}_2\text{CH}_2\text{PPh}_2)\text{Cl}_2]$ as the catalyst.

Figure 13 is a graph showing the volume of hydrogen gas generated over time for the hydrolysis of AB using $[\text{Ir}\{\text{HN}(\text{CH}_2\text{CH}_2\text{P}^t\text{Bu}_2)_2\}_2(\text{C}_8\text{H}_{13})(\text{H})(\text{Cl})]$ as the catalyst.

Figure 14 is a ^{31}P NMR spectrum of bis(2-(ditertiarybutylphosphine)-ethyl)amine(cyclooctene)iridium(I) in benzene- D_6 .

Figure 15 is an ORTEP diagram of bis(2-(ditertiarybutyl)ethyl)aminechlorodihydrido-iridium(III).

Figure 16 is a graph showing the effect of *n*-butanol concentration in bis(2-(di-*tert*-butylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) catalyzed hydrogen generation (40 °C).

Figure 17 is a graph showing the effect of isopropanol concentration in bis(2-(di-*tert*-butylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III) catalyzed hydrogen generation (40 °C).

Figure 18 shows the effect of methanol concentration in bis(2-(di-*tert*-butylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III) catalyzed hydrogen generation (40 °C).

DETAILED DESCRIPTION OF THE DISCLOSURE

DEFINITIONS

The term " C_{1-n} alkyl" as used herein means straight or branched chain, saturated alkyl groups containing from one to *n* carbon atoms and includes (depending on the identity of *n*) methyl, ethyl, propyl, isopropyl, *n*-butyl, *s*-butyl, isobutyl, *t*-butyl, 2,2-dimethylbutyl, *n*-pentyl, 2-methylpentyl, 3-methylpentyl, 4-methylpentyl, *n*-hexyl and the like, where the variable *n* is an integer representing the largest number of carbon atoms in the alkyl group.

The term "C_{1-n}alkenyl" as used herein means straight or branched chain, unsaturated alkyl groups containing from one to n carbon atoms and one to three double bonds, and includes (depending on the identity of n) vinyl, allyl, 2-methylprop-1-enyl, but-1-enyl, but-2-enyl, but-3-enyl, 2-methylbut-1-enyl, 2-methylpent-1-enyl, 4-methylpent-1-enyl, 4-methylpent-2-enyl, 2-methylpent-2-enyl, 4-methylpenta-1,3-dienyl, hexen-1-yl and the like, where the variable n is an integer representing the largest number of carbon atoms in the alkenyl group.

The term "C_{6-n}aryl" as used herein means a monocyclic, bicyclic or tricyclic carbocyclic ring system containing from 6 to n carbon atoms and at least one aromatic ring and includes, depending on the identity of n, phenyl, naphthyl, anthracenyl, 1,2-dihydronaphthyl, 1,2,3,4-tetrahydronaphthyl, fluorenyl, indanyl, indenyl and the like, where the variable n is an integer representing the largest number of carbon atoms in the aryl group.

The term "heteroaryl" as used herein means a monocyclic, bicyclic or tricyclic ring system containing from 5 to 14 atoms of which one or more, for example 1-8, suitably, 1-6, more suitably 1-5, and more suitably 1-4, of the atoms are a heteromoiety selected from O, S, NH and NC₁₋₆alkyl, with the remaining atoms being C or CH, said ring system containing at least one aromatic ring. Examples of heteroaryl groups, include, but are not limited to thienyl, imidazolyl, pyridyl, oxazolyl, indolyl, furanyl, benzothienyl, benzofuranyl and the like.

The suffix "ene" added on to any of the above groups means that the group is divalent, i.e. inserted between two other groups. When the group is a ring system, the two other groups may be located at any location on the ring system, including at adjacent and non-adjacent nodes. For example, if the group is phenylene, the two other groups may be located at positions 1 and 2, 1 and 3 or 1 and 4.

The term "substituted" as used herein, unless otherwise specified, means that the group is substituted with one or more, optionally one to six, suitably one to three, groups independently selected from OH, SH, NH₂, NHC₁₋₆alkyl, N(C₁₋₆alkyl)(C₁₋₆alkyl), C₁₋₆alkyl, C₁₋₆alkoxy, C₁₋₆thioalkoxy, halo, fluoro-substituted C₁₋₆alkyl, fluoro-substituted C₁₋₆alkoxy, fluoro-substituted C₁₋₆thioalkoxy, fluoro-substituted NHC₁₋₆alkyl and fluoro-substituted N(C₁₋

alkyl)(C₁₋₆alkyl). In an embodiment of the disclosure, the substituents are selected from one or more, optionally one to six, suitably one to three, groups independently selected from OH, SH, NH₂, NHCH₃, N(CH₃)₂, CH₃, OCH₃, SCH₃, halo, CF₃, OCF₃, SCF₃, NHCF₃ and N(CF₃)₂.

5 The term "halo" as used herein means halogen and includes chlorine, bromine, iodine and fluorine.

 The term "fluoro-substituted" as used herein means that one or more, including all, of the hydrogens in the group have been replaced with fluorine.

10 The term "ring system" as used herein refers to a carbon-containing ring system, that includes monocycles, fused bicyclic and polycyclic rings, bridged rings and metallocenes. Where specified, the carbons in the rings may be substituted or replaced with heteroatoms.

 The term "coordinating" as used herein refers to a chemical grouping which formally bonds to or shares electrons with the metal center in a
15 covalent bond.

 The term "non-coordinating" as used herein refers to a chemical grouping which does not formally bond to or share electrons with the metal center in a covalent bond.

20 By "ligand stabilized" it is meant that the ligand stabilizes the metal to allow easier handling of an otherwise reactive center. The coordinating atoms of such ligands include, but is not limited to phosphorus, nitrogen, oxygen, carbon, silicon, germanium, sulfur, selenium and arsenic. Such ligands include compounds having one or more type of coordinating atoms, in various combinations, including but not limited to phosphines, arsines, diphosphines,
25 imines, pyridines, amines, carbenes, aminophosphines, diamines, aminodiphosphines, diaminodiphosphines, dicarbenes, aminocarbenes, phosphinocarbenes, alcohols, ethers, aminoethers, phosphinoethers, aminoalcohols, aminothiols, aminothiophenes, imidazoles, etc.

30 The term "solvent" as used herein means a solvolytic and/or hydrolytic solvent which participates as a reactant in generating hydrogen and is known as a hydrolytic or solvolytic dehydrogenation agent (i.e. the solvent hydrolyzes or solvolyzes the amine borane). This type of solvent generally includes a hydroxyl group, such as water, methanol or ethanol, for the production of hydrogen. Also included within the term "solvent" are co-ordinating solvents

such as tetrahydrofuran, diglyme and triglyme. Generally, solvent systems will contain a mixture of a hydrolytic solvent such as water or an alcohol, and a coordinating solvent, such as tetrahydrofuran.

The term "homogeneous" as used herein means that the ligand
5 stabilized catalyst is soluble in the reaction solvent(s) and remains in solution throughout the reaction process.

In understanding the scope of the present disclosure, the term "comprising" and its derivatives, as used herein, are intended to be open ended terms that specify the presence of the stated features, elements,
10 components, groups, integers, and/or steps, but do not exclude the presence of other unstated features, elements, components, groups, integers and/or steps. The foregoing also applies to words having similar meanings such as the terms, "including", "having" and their derivatives. Finally, terms of degree such as "substantially", "about" and "approximately" as used herein mean a
15 reasonable amount of deviation of the modified term such that the end result is not significantly changed. These terms of degree should be construed as including a deviation of at least $\pm 5\%$ of the modified term if this deviation would not negate the meaning of the word it modifies.

METHODS OF THE DISCLOSURE

20 The present disclosure includes a method for the production of hydrogen comprising

(a) contacting a solution comprising at least one ligand-stabilized metal catalyst with at least one compound of the formula I,



25 in a solvent under conditions for the solvolysis of the compound of formula (I),

wherein R^1 , R^2 , R^3 and R^4 are each simultaneously or independently selected from H, branched or unbranched fluoro-substituted- C_{1-20} alkyl, branched or unbranched C_{1-20} alkyl and C_{6-14} aryl or any two of R^1 , R^2 ,
30 R^3 and R^4 are linked to form a branched or unbranched C_{2-10} alkylene, which together with the nitrogen and/or boron atoms to which they are attached, forms a ring, and

(b) optionally collecting hydrogen produced in the solvolysis of the compounds of formula (I).

In an embodiment of the disclosure, R^1 , R^2 , R^3 and R^4 are different. In a further embodiment, R^1 , R^2 , R^3 and R^4 are each simultaneously or independently selected from H, branched or unbranched fluoro-substituted- C_{1-10} alkyl, branched or unbranched C_{1-10} alkyl, and C_{6-10} aryl or any two of R^1 , R^2 , R^3 and R^4 are linked to form a branched or unbranched C_{2-6} alkylene, which together with the nitrogen and/or boron atoms to which they are attached, forms a ring. In another embodiment, R^1 , R^2 , R^3 and R^4 are each simultaneously or independently selected from H, branched or unbranched fluoro-substituted- C_{1-6} alkyl, branched or unbranched C_{1-6} alkyl, and phenyl or R^1 and R^2 and/or R^3 and R^4 are linked to form a branched or unbranched C_{2-6} alkylene, which together with the nitrogen atom and/or boron atom to which they are attached, forms a ring. In a further embodiment of the disclosure, R^1 , R^2 , R^3 and R^4 are each H.

Conditions for the solvolysis of the compound of the formula (I) can vary depending on a number of factors including, for example, the identity of the catalyst and the scale of the reaction, as would be known to a person skilled in the art. In embodiments of the present disclosure, the conditions include the use of a water-soluble or water miscible solvent, for example, ethers and tetrahydrofuran, and alcohols and ethanol, and suitable reaction temperatures, for example, but not limited to, in the range of about 20 °C to about 60 °C, suitably about 40 °C. In an embodiment, the catalyst is dissolved in a mixture of the solvent and water in a volume ratio of between about 90:10 to 10:90 (solvent:water). In this embodiment, the reaction is referred to as a hydrolysis reaction. In another embodiment, the conditions include the use of an alcohol as the solvent, for example a C_{1-10} alcohol, optionally a C_{1-4} alcohol, and suitably ethanol, methanol, 1-propanol, 2-propanol, 1-butanol or 2-butanol. In this embodiment, the reaction is referred to as a solvolysis reaction. In a suitable embodiment, the catalyst is dissolved in a mixture of the solvent and water in a volume ratio of 50:50 and the compound of formula (I) is added directly to this solution.


The hydrogen that is generated in this reaction may optionally be captured using any known means. The reaction produces, in addition to

hydrogen gas, easily recyclable and environmentally friendly ammonium borate salts as the only detectable boron-containing residue. The hydrolysis reaction has been performed in air but may also be performed in an inert atmosphere, for example, under argon, if the catalyst is air sensitive.


5 The present disclosure is the first to report that the solvolysis of AB, and its derivatives, to produce hydrogen gas may be catalyzed by ligand-stabilized metal catalysts under homogeneous reaction conditions. In the present disclosure, it has been shown that a wide variety of ligands and metals may be used to catalyze the hydrolysis or solvolysis of hydrolysis or
10 solvolysis of AB, and its derivatives. For example the metal includes all known metals, including, the alkali metals lithium (Li), sodium (Na), potassium (K), rubidium (Rb), cesium (Cs) and francium (Fr); the alkaline earth metals beryllium (Be), magnesium (Mg), calcium (Ca), strontium (Sr), barium (Ba) and radium (Ra); the p-block metals aluminum (Al), gallium (Ga), indium (In),
15 tin (Sn), thallium (Tl), lead (Pb), and bismuth (Bi); the d-block or transition metals scandium (Sc), titanium (Ti), vanadium (V), chromium (Cr), manganese (Mn), iron (Fe), cobalt (Co), nickel (Ni), copper (Cu), zinc (Zn), yttrium (Y) zirconium (Zr), niobium (Nb), molybdenum (Mo), technetium (Tc), ruthenium (Ru), palladium (Pd), silver (Ag), cadmium (Cd), hafnium (Hf),
20 tantalum (Ta), tungsten (W), rhenium (Re), osmium (Os), iridium (Ir), platinum (Pt), gold (Au) and mercury (Hg); the lanthanides lanthanum (La), cerium (Ce), praseodymium (Pr), neodymium (Nd), promethium (Pm), samarium (Sm), europium (Eu), gadolinium (Gd), terbium (Tb), dysprosium (Dy), holmium (Ho), erbium (Er), thulium (Tm), ytterbium (Yb) and lutetium; and the
25 actinides actinium (Ac), thorium (Th), protactinium (Pa), uranium (U), neptunium (Np), plutonium (Pu), americium (Am), Curium, Cm, Berkelium, (Bk), californium (Cf), einsteinium (Es), fermium (Fm), mendelevium (Md), nobelium (No) and lawrencium (Lr). In embodiments of the disclosure, the metal is a transition metal. In other embodiments of the disclosure, the metal
30 is selected from Ru, Co, Ni, Ru and Ir.

With respect to the identity of the ligands, the present disclosure extends to any ligand associated with metal-based catalysts. Ligands that may be used in the catalysts of the present disclosure, include, but are not limited to, one or more of:

(a) Phosphines of the formula (II):



- 5 which are bidentate or tridentate and are chiral or achiral monodentate phosphine ligands in which R^5 , R^6 and R^7 are simultaneously or independently selected from unsubstituted or substituted C_{1-10} alkyl, unsubstituted or substituted C_{2-10} alkenyl, unsubstituted or substituted C_{3-10} cycloalkyl, unsubstituted or substituted C_{6-14} aryl, OR^8 and $N(R^8)_2$ and R^8 is
- 10 simultaneously or independently selected from unsubstituted or substituted C_{1-10} alkyl, unsubstituted or substituted C_{2-10} alkenyl, unsubstituted or substituted C_{3-10} cycloalkyl, unsubstituted or substituted C_{6-14} aryl, or two of R^5 , R^6 , R^7 and R^8 are bonded together to form an unsubstituted or substituted ring having 4 to 8 atoms, including the phosphorous, nitrogen and/or oxygen atom
- 15 to which said groups are bonded. In an embodiment of the application R^5 , R^6 , R^7 and R^8 are independently selected from C_{6-14} aryl and C_{1-6} alkyl. In further embodiments of the disclosure, R^5 , R^6 , R^7 and R^8 are independently selected from phenyl and C_{1-6} alkyl. In still further embodiments R^5 , R^6 and R^7 are all phenyl and R^8 is independently selected from phenyl and C_{1-6} alkyl;
- 20 (b) Bis(phosphino) bi-, tri- or tetradentate ligands of the formula (III):



- wherein R^9 , R^{10} , R^{11} and R^{12} are, independently, as defined for R^5 , R^6 and R^7 ,
- 25 and Q^1 is selected from unsubstituted or substituted C_1 - C_{10} alkylene and unsubstituted or substituted C_2 - C_{10} alkenylene where adjacent or geminal substituents on Q^1 are joined together to form, including the atoms to which they are attached, one or more unsubstituted or substituted 5-14-membered monocyclic, polycyclic, heterocyclic, carbocyclic, saturated, unsaturated or
- 30 metallocenyl ring systems, and/or one or more of the carbon atoms in Q^1 is optionally replaced with a heteromoiety selected from O, S, NH and $N(C_{1-6}alkyl)$ and Q^1 is chiral or achiral. In further embodiments of the disclosure, R^9 , R^{10} , R^{11} and R^{12} are independently selected from phenyl, C_{1-6} alkyl and C_{5-10} cycloalkyl, with the phenyl being optionally substituted with one to five

substituents independently selected from C₁₋₄alkyl, fluoro-substituted C₁₋₄alkyl, halo, C₁₋₄alkoxy and fluoro-substituted C₁₋₄alkoxy and Q¹ is selected from unsubstituted or substituted C₁-C₈alkylene where the substituents on Q¹ are independently selected from one to four C₁₋₄alkyl, fluoro-substituted C₁₋₄alkyl, halo, C₁₋₄alkoxy, fluoro-substituted C₁₋₄alkoxy, unsubstituted and substituted phenyl and substituted and unsubstituted naphthyl, and/or adjacent or geminal substituents may be joined together to form, including the atoms to which they are attached, one or more unsubstituted or substituted phenyl, pyridyl, cyclohexyl, naphthyl or ferrocenyl groups, and/or one or two of the carbon atoms in Q¹ is replaced with a heteromoiety selected from O, NCH₃ and NH, and Q¹ is chiral or achiral.

Bis(phosphino) ligands of the formula (III) include, for example, 1,3-bis(di-iso-propylphosphinoxy)benzene, 1,3-bis(di-tert-butylphosphinoxy)benzene, 1,3-bis(diphenylphosphinoxy)benzene, 1,3-bis(diethylphosphinoxy)benzene, 1,3-bis((ditertiarybutylphosphino)methyl)benzene, 1,3-bis((diisopropylphosphino)methyl)benzene, 2,6-bis((di-iso-propylphosphino)methyl)pyridine, N¹,N³-bis(di-iso-propylphosphino)benzene-1,3-diamine, 2,2'-oxybis(ethane-2,1-diyl)bis(di-iso-propylphosphine), 2,2'-oxybis(ethane-2,1-diyl)bis(ditertiarybutylphosphine), bis(2-ditertiarybutylphosphino)ethyl)amine, bis(2-(di-i-propylphosphino)ethyl)amine, bis(2-(di-ethylphosphino)ethyl)amine, bis(2-(dicyclohexylphosphino)ethyl)amine, bis(2-(ditertiarybutylphosphino)ethyl)amine, bis(2-(diadamantylphosphino)ethyl)amine, bis(2-(diisopropylphosphino)ethyl)methylamine, bis(2-(ditertiarybutylphosphino)ethyl)methylamine, bis(2-(diadamantylphosphino)ethyl)methylamine, bis(2-diphenylphosphino)ethyl)methylamine, bis(2-diisopropylphosphino-4-methylphenyl) amine, bis(di-*m*-isopropylphosphino-di-*p*-tolyl)amine, N¹,N²-bis(2-(diphenylphosphino)benzyl)cyclohexane-1,2-diamine, N,N-bis(2-(di-*p*-tolylphosphino)benzyl)cyclohexane-1,2-diamine, N¹,N²-bis(2-(bis(3,5-dimethylphenyl)phosphino)-benzyl)-cyclo-hexane-1,2-diamine, N¹,N²-bis(2-

(di-phenylphosphino)-benzylidene)-cyclohexane-1,2-diamine, and (N¹E,N²E)-N¹,N²-bis(2-(diphenylphosphino)benzylidene)cyclohexane-1,2-diamine.

Other bis(phosphino) ligands include, for example, each optical isomer of 2,2'-bis-(diphenylphosphino)-1,1'-binaphthyl (abbreviated name: BINAP);

5 BINAP derivatives in which the naphthalene ring of BINAP is partially reduced, such as each optical isomer of 2,2'-bis(diphenylphosphino)-5,5',6,6',7,7',8,8'-octahydro-1,1'-binaphthyl (abbreviated name: H₈BINAP); BINAP derivatives in which the naphthalene ring of BINAP carries substituent(s), such as each optical isomer of 2,2'-bis-(diphenylphosphino)-

10 6,6'-dimethyl-1,1'-binaphthyl (abbreviated name: 6MeBINAP); BINAP derivatives in which the benzene ring on the phosphorus atom of BINAP is substituted with lower alkyl group(s), such as each optical isomer of 2,2'-bis-(di-p-tolylphosphino)-1,1'-binaphthyl (abbreviated name: Tol-BINAP), each optical isomer of 2,2'-bis[bis(3-methylphenyl)phosphino]-1,1'-binaphthyl, each

15 optical isomer of 2,2'-bis[bis(3,5-di-tert-butylphenyl)phosphino]-1,1'-binaphthyl-, each optical isomer of 2,2'-bis[bis(4-tert-butylphenyl)phosphino]-1,1'-binaphthyl, each optical isomer of 2,2'-bis[bis(3,5-dimethylphenyl)phosphino]-1,1'-binaphthyl (abbreviated name: Xyl-BINAP), and each optical isomer of 2,2'-bis[bis(3,5-dimethyl-4-

20 methoxyphenyl)phosphino]-1,1'-binaphthyl (abbreviated name: Dmany-BINAP); BINAP derivatives in which the naphthalene ring of BINAP carries substituent(s) and the benzene ring on the phosphorus atom of BINAP is substituted with from 1 to 5 lower alkyl substituents, such as each optical isomer of 2,2'-bis[bis-(3,5-dimethylphenyl)phosphino]-6,6'-dimethyl-1,1'-

25 binaphthyl (abbreviated name: Xyl-6MeBINAP); and, BINAP derivatives in which the naphthalene ring of BINAP is condensed with a saturated hydrocarbon ring, such as each optical isomer of 3,3'-bis-(diphenylphosphanyl)-13,13'-dimethyl-


12,13,14,15,16,17,12',13',14',15',16',17'-dodecahydro-11H,11'H-

30 [4,4']bi[cyclopenta[a]phenanthrenyl]. Further, particular examples include each optical isomer of 2,2'-bis[bis-(3,5-dimethylphenyl)phosphino]-1,1'-binaphthyl (abbreviated name: Xyl-BINAP); each optical isomer of 2,2'-bis[bis(3,5-dimethyl-4-methoxyphenyl)phosphino]-1,1'-binaphthyl (abbreviated name: Dmany-BINAP); and BINAP derivatives in which the naphthalene ring

of BINAP carries substituent(s) and the benzene ring on the phosphorus atom of BINAP is substituted with from 1 to 5 lower alkyl substituents, such as each optical isomer of 2,2'-bis[bis-(3,5-dimethylphenyl)phosphino]-6,6'-dimethyl-1,1'-binaphthyl (abbreviated name: Xyl-6MeBINAP).

- 5 Representative examples of the preparation of bis(phosphinoxy) ligands are found in Pandarus V. et al. Chem. Commun. 2007, 978-980; Morales-Morales, D. et al. Inorganica Chim. Acta 2004, 357, 2953-2956; and Götter-Schnetmann, I, et al. J. Am. Chem. Soc. 2004, 126, 1804-1811). Representative examples of the preparation of bis(alkylphosphino) ligands are
10 found in Gupta, M. et al. Chem. Commun. 1996, 2083-2084; Moulton, C.J. J. Chem. Soc. Dalton, 1976, 1020-1024). Representative examples of the preparation of amino-diphosphines ligands are found in Clarke, Z.E. et al. Organometallics 2006, 25, 4113-4117). Representative examples of the preparation of diaminodiphosphine ligands are found in Li, Y-Y. et al. 2004,
15 218, 153-156;

(c) Bidentate aminophosphine ligands of the formula (IV):




- 20 wherein R^{13} and R^{14} are, independently, as defined for R^5 - R^7 , Q^2 is as defined for Q^1 , and R^{15} and R^{16} are independently selected from H, C_{6-14} aryl, C_{1-10} alkyl and C_{3-12} cycloalkyl, with the C_{6-14} aryl and C_{3-12} cycloalkyl being optionally substituted. In embodiments of the disclosure, R^{13} and R^{14} are independently selected from phenyl, C_{1-6} alkyl, and C_{5-10} cycloalkyl, with the
25 phenyl and C_{5-10} cycloalkyl being optionally substituted with one to five substituents independently selected from C_{1-4} alkyl, fluoro-substituted C_{1-4} alkyl, halo, C_{1-4} alkoxy and fluoro-substituted C_{1-4} alkoxy, R^{15} and R^{16} are independently selected from H, phenyl and C_{1-6} alkyl and Q^2 is selected from unsubstituted or substituted C_1 - C_8 alkylene where the substituents on Q^2 are
30 independently selected from one to four of C_{1-6} alkyl, fluoro-substituted C_{1-6} alkyl, halo, C_{1-6} alkoxy, fluoro-substituted C_{1-6} alkoxy and unsubstituted or substituted phenyl and/or adjacent or geminal substituents on Q^2 may be joined together to form, including the carbon atoms to which they are attached, one or more unsubstituted or substituted phenyl, naphthyl or

ferrocenyl ring systems, and/or one or two of the carbon atoms in Q^1 is replaced with a heteromoiety selected from O, NCH_3 and NH, and Q^2 may be chiral or achiral.

Ligands of the formula (IV) include, for example, N,N'-
5 (phenylphosphinediyl)bis(methylene)dipropyl-2-amine;

(d) Heterocyclic ligands of the formula (V):



10 which are bi- or tridentate ligands wherein Hy is an unsubstituted or substituted aromatic or non-aromatic heterocycle containing from 3 to 10 atoms of which 1 to 3 are a heteromoiety selected from O, S, N, NH and $NC_{1-6}alkyl$ with the remaining atoms being C and Q^3 is as defined for Q^1 . In an embodiment of the application Hy is selected from imidazole, pyridine, oxazole and
15 dihydrooxazole.



Ligands of the formula (V) include, for example, 1,3-bis((R)-4-isopropyl-4,5-dihydrooxazol-2-yl)benzene, N^1,N^2 -bis(pyridin-2-ylmethylene)cyclohexane-1,2-diamine, 3'-(1,3-phenylenebis(methylene))bis(1-butyl-1H-imidazol-3-ium) chloride, bis[2-(1-butyl-1H-imidazol-3-ium)ethyl]ammonium chloride, 1,1'-(pyridine-2,6-diyl)bis(3-butyl-1H-imidazol-3-ium) chloride, 2,6-bis(1-n-butylimidazolium)pyridine dibromide and 2-bis(1-n-butylimidazolium)ethylamine.

20

Representative examples of the preparation of imidazolidenes ligands are found in Loch J.A. et al. Organomet. 2002, 21, 700-706; Poyatos, M. et al. Organomet. 2003, 22, 1110-1114;

25

(e) Diaminophosphines of the formula (VI) or (VII):




30

wherein

R^{17} - R^{18} and R^{20} , R^{21} are, independently, as defined for R^{15} and R^{16} , R^{19} is as defined for R^5 and Q^4 and Q^5 are as defined for Q^1 ;

Ligands of the formula (VI) include, for example, N,N'-(phenylphosphinediyl)bis(methylene)dipropyl-2-amine;

(f) Diamines of the formula VIII or IX:



wherein

R^{22} - R^{25} are, independently, as defined for R^{15} and R^{16} and Q^6 is as defined for Q^1 ;

10 Examples of the diamine ligands include, for example, methylenediamine, ethylenediamine, 1,2-diaminopropane, 1,3-diaminopropane, 1,4-diaminobutane, 2,3-diaminobutane, 1,2-cyclopentanediamine, 1,2-cyclohexanediamine, 1,1-diphenylethylenediamine, 1,1-di(p-methoxyphenyl)ethylenediamine, 1,1-di(3,5-
15 dimethoxyphenyl)ethylenediamine, and 1,1-dinaphthylethylenediamine. Optically active diamine compounds may be also used. Examples thereof include, for example, optically active 1,2-diphenylethylenediamine (abbreviated name: DPEN), 1,2-di(p-methoxyphenyl)ethylenediamine, 1,2-cyclohexanediamine, 1,2-cycloheptanediamine, 2,3-dimethylbutanediamine,
20 1-methyl-2,2-diphenylethylenediamine, 1-isobutyl-2,2-diphenylethylenediamine, 1-isopropyl-2,2-diphenylethylenediamine, 1-benzyl-2,2-diphenylethylenediamine, 1-methyl-2,2-di(p-methoxyphenyl)ethylenediamine (abbreviated name: DAMEN), 1-isobutyl-2,2-di(p-methoxyphenyl)-ethylenediamine (abbreviated name: DAIBEN), 1-
25 isopropyl-2,2-di(p-methoxyphenyl)ethylenediamine (abbreviated name: DAIPEN), 1-benzyl-2,2-di(p-methoxyphenyl)ethylenediamine, 1-methyl-2,2-di(3,5-dimethoxyphenyl)ethylenediamine, 1-isopropyl-2,2-di(3,5-dimethoxyphenyl)ethylenediamine, 1-isobutyl-2,2-di(3,5-dimethoxyphenyl)ethylenediamine, 1-benzyl-2,2-di(3,5-
30 dimethoxyphenyl)ethylenediamine, 1-methyl-2,2-dinaphthylethylenediamine, 1-isobutyl-2,2-dinaphthylethylenediamine, 1-isopropyl-2,2-dinaphthylethylenediamine, and 1-benzyl-2,2-dinaphthylethylenediamine. Further, optically active diamine compounds which can be used are not limited to the abovementioned optically active ethylenediamine derivatives.

Optically active propanediamine, butanediamine and cyclohexanediamine derivatives may be also used. In addition, these diamine ligands may be prepared by the process starting from .alpha.-amino acid described in the literature (Burrows, C. J., et al., Tetrahedron Letters, 34(12), pp. 1905-1908 (1993)), or by a variety of processes described in the general remark (T. Le Gall, C. Mioskowski, and D. Lucet, Angew. Chem. Int. Ed., 37, pp. 2580-2627 (1998));


(g) Thiophenes of the formula (X):



which are bidentate, wherein T is unsubstituted or substituted thiophene and Q^7 is as defined for Q^1 .

Ligands of the formula (X) include, for example, thiophen-2-ylmethanamine; and

(h) Thioamines of the formula (XI):



20 which are bidentate, wherein R^{25} is as defined for R^5 , R^6 or R^7 , S is sulphur and Q^8 is as defined for Q^1 .

Ligands of the formula (XI) include, for example, 2-(benzylthio)ethanamine.

It is to be understood that the above-described ligands are representative examples and the disclosure is not limited to such examples.

The catalysts useful in the processes of the present disclosure, may also comprise one or more of non-coordinating or coordinating, neutral or anionic and/or Lewis basic ligands, depending on the valency and size characteristics of the metal as would be known to those skilled in the art. Examples of such ligands include, but are not limited to halo (in particular Cl), OH, H, CO, pyridine, acetonitrile. The catalyst may also be monocationic or dicationic.

The catalysts may be prepared and isolated prior to use in the processes of the disclosure or they may be generated *in situ*.

The present disclosure further includes a method for the solvolysis of a compound of the formula (I) comprising contacting at least one compound of the formula (I) as defined above with at least one ligand-stabilized transition metal catalyst in the presence of a solvent under conditions for the hydrolysis of the compound of formula (I).

HYDROGEN GENERATION SYSTEMS

There are expected to be many applications for the methods of the present disclosure. In one embodiment, the methods of the disclosure are used to generate hydrogen, which is supplied to a hydrogen fuel cell, such as a PEMFC. Hydrogen generators may include a first compartment holding a catalyst-comprising solution and a second compartment holding the one or more amine boranes of the formula (I) as defined above, wherein the catalyst is a ligand-stabilized metal catalyst. Control electronics are coupled to catalyst mass flow controllers and hydrogen mass flow controllers. Catalyst mass flow controllers control the flow of the catalyst solution, which enters second compartment to achieve a desired hydrogen flow generated by the hydrogen generator. A coupling connector delivers hydrogen generated by hydrogen generator to the anode of a PEMFC.

In the embodiment of the disclosure, the one or more amine boranes of formula (I) are stored in a second compartment as a solid or as a solution in the solvent. In operation, as soon as the hydrogen generator is turned on, control electronics send a signal to a mass flow controller (or a flow controller) to allow a predetermined flow rate of the one or more ligand-stabilized metal catalysts in a solvolytic and/or hydrolytic solvent in a first compartment to flow into the second compartment which holds the one or more amine boranes. As a result, hydrogen gas is generated. The reaction by-products are captured and remain in the second compartment. In alternate embodiments the one or more amine boranes can be provided in the first compartment and be pumped into the second compartment holding the one or more metal catalysts in the solvent.

Hydrogen generators disclosed herein are capable of delivering PEMFC grade hydrogen at low reaction temperatures, safely and reliably in an integrated and self-sustaining device that offers high specific energy storage density. Hydrogen PEM fuel cells are optimal for applications in the

power range of 5-500 W where batteries and internal combustion engines do not deliver cost-effective and convenient power generation solutions. Unlike secondary batteries, the hydrogen generators disclosed here and formulations therein provide a constant source of power in a compact size that does not
5 require electrical recharging.

The systems disclosed herein can thus provide a viable solution to many military and civilian applications in need of a lightweight, highly dependable power source. Examples include, among others, auxiliary power units for small and remote applications, shelter power, emergency power,
10 external power pack, battery charger, portable power for soldiers, unmanned aerial vehicles, and robotics.

Accordingly, also included within the present disclosure is a hydrogen generation system comprising at least one amine borane of the formula (I) as defined above, at least one ligand-stabilized metal catalyst, and a solvolytic
15 and/or hydrolytic solvent. In an embodiment of the disclosure, the hydrogen generation system comprises a first compartment comprising the at least one amine borane of the formula (I) as defined above, a second compartment comprising the at least one ligand-stabilized metal catalyst, wherein the first or second compartment further comprises the solvent. The hydrogen generation
20 system further comprises a means for combining the contents of the first compartment with the second compartment so that when the contents are combined, hydrogen is generated. At least one flow controller controls a flow rate of the at least one catalyst or the at least one amine borane.

In a further embodiment of the present disclosure, a proton exchange
25 membrane fuel cell (PEMFC) is used as an electrical generator. The PEMFC comprises an ion-exchange membrane located between an anode and a cathode, said membrane, anode and cathode forming a membrane/electrode assembly (MEA), said MEA being located between a fuel gas diffusion layer and an oxidant gas diffusion layer. An oxidant flow network is in fluid
30 connection with the fuel gas diffusion layer, the oxidant network having an input portion for supplying oxidant, and a fuel flow network fluid in fluid connection with the fuel gas diffusion layer. The fuel network has an input portion for supplying fuel, wherein the fuel flow network is fluidly connected to an amine borane dehydrogenation *in-situ* hydrogen generator. The generator

comprises a first compartment that comprises at least one amine borane, a second compartment comprising at least one ligand-stabilized metal catalyst, wherein the first or said second compartment comprises a solvolytic and/or hydrolytic solvent. A means for combining the contents of the first
5 compartment with the second compartment so that when the contents are combined, hydrogen is generated is included. At least one flow controller controls a flow rate of the at least one catalyst or the at least one amine borane.

The following non-limiting examples are illustrative of the disclosure:

10 EXPERIMENTAL EXAMPLES:

MATERIALS AND METHODS

All ligands and their metal complexes were prepared under an argon atmosphere in an Innovative Technologies inert atmosphere glovebox or with standard Schlenk techniques, unless otherwise stated. All heterogeneous
15 catalysts were prepared in air unless otherwise stated. Ammonia borane was obtained from Boroscience Ltd. Ruthenium trichloride trihydrate ($\text{RuCl}_3 \cdot 3\text{H}_2\text{O}$) was obtained from Pressure Chemicals Company. Rhodium cyclooctadiene acetylacetonate $[\text{Rh}(\text{COD})(\text{acac})]$, and [iridium bis(cyclooctene) chloride] dimer $\{[\text{Ir}(\text{COE})_2\text{Cl}]_2\}$ were obtained from Colonial Metals Inc. Palladium
20 cyclooctadiene dichloride $[\text{Pd}(\text{COD})\text{Cl}_2]$ was prepared using standard procedures. All other metal salts were obtained from Sigma-Aldrich Ltd. and were used as received. Dichloromethane (CH_2Cl_2), diethyl ether (Et_2O), hexanes (C_6H_{14}), tetrahydrofuran and toluene (C_7H_8) were dried and degassed with an Innovative Technologies solvent column containing alumina
25 (CH_2Cl_2), or alumina and copper oxide catalyst (ether, hexanes and tetrahydrofuran). Isopropanol was dried and degassed by distillation from calcium hydride (CaH_2) under an argon atmosphere.


Hydrogen Measurement Experiments

These reactions were performed in a 3-neck round bottom flask that
30 was connected to a calibrated burette (<100 ml hydrogen, Figure 1) or an inverted graduated cylinder (2000 to 8000 ml hydrogen, Figure 2) and a standard vacuum manifold. The ammonia borane was added either via an L-shaped solid addition tube (<100 ml to 2000 ml hydrogen) or was added rapidly to the reaction mixture through a solid addition funnel; in the latter

case the reaction vessel was sealed rapidly and opened to the hydrogen measurement apparatus immediately. For air sensitive samples, the flask containing the catalyst precursor, L-shaped solid addition tube with AB and tetrahydrofuran were assembled in a glovebox, sealed and then connected to a vacuum manifold. Degassed water was then added with a syringe. In experiments where AB portions were added in an argon atmosphere, the L-shaped tube was removed with an argon flow and replaced with a tube containing a new sample of AB and the flask was then purged gently with argon for approximately 2 minutes. The reaction vessel was then assembled and connected to the hydrogen measurement apparatus. The system was then placed in a water bath at the desired reaction temperature and was allowed to equilibrate for approximately 5 minutes before starting each run. The water level in the burette or inverted graduated cylinder was then set to the 'zero' point, the ammonia borane was then added and the evolved hydrogen volume was measured as a function of time.

PREPARATION OF LIGANDS.

Example 1



(a) R = *iso*-propyl: 1,3-bis(di-*iso*-propylphosphinoxy)benzene

Resorcinol (3.5 g, 32 mmol) was dissolved in 100 ml of toluene and triethylamine (9.3 ml, 67 mmol) was then added to the reaction mixture. Chloro-di-*iso*-propylphosphine (10.6 ml, 67 mmol) in toluene (50 ml) was added dropwise to the reaction mixture at room temperature. After 3 hours, the reaction mixture was then concentrated in vacuo. The product was then filtered in the drybox to remove the small amount of residual salt. Yield: 9.07 g (83 %). ¹H NMR (300 MHz, C₆D₆): δ 7.07 (m, 1 H, 2-*H*), 6.8 (m, 1H, 5-*H*), 6.70 (m, 2H, 4- and 6-*H*), 1.89 (dsept., 4H, CH(CH₃)₂), 1.10 (m, 24H, CH(CH₃)₂). ³¹P{¹H} NMR (300 MHz, C₆D₆): δ 150.

(b) *R* = tertiary butyl: 1,3-bis(di-tert-butylphosphinoxy)benzene

This material was prepared according to a literature method (Göttker-Schnetmann, I.; White, P.; Brookhart, M. *J. Am. Chem. Soc.* **2004**, 126, 1804 – 1811). Yield: 4.50 g (45%) Spectroscopic data are similar to the literature value (Göttker-Schnetmann, I.; White, P.; Brookhart, M. *J. Am. Chem. Soc.* **2004**, 126, 1804 – 1811).

(c) *R* = phenyl: 1,3-bis(diphenylphosphinoxy)benzene


Resorcinol (3.5 g, 32 mmol) was dissolved in 100 ml of toluene and triethylamine (9.3 ml, 67 mmol) was added to the reaction. Chloro-diphenylphosphine (14.78 g, 67 mmol) in toluene (50 ml) was then added dropwise at room temperature. The reaction mixture was filtered after 3 hours; the filtrate was collected and the solvent was then removed in vacuo to afford a white solid. Yield: 11.6 g (75 %). ¹H NMR (400 MHz, C₆D₆): δ 7.6 – 7.4 (m, 20 H, *PPh*₂), 7.19 (m, 1H, 2-*H*), 6.98 (m, 1H, 5-*H*), 6.84 (m, 2H, 4- and 6-*H*). ³¹P{¹H} NMR (400 MHz, C₆D₆): δ 113.

(d) *R* = ethyl: 1,3-bis(diethylphosphinoxy)benzene

This product was prepared analogously to 1,3-bis(di-isopropylphosphinoxy)-benzene as described in Example 1(a). Yield: (94%). ¹H NMR (400 MHz, C₆D₆): δ 6.98 (m, 1 H, 2-*H*), 6.68 (m, 1H, 5-*H*), 6.59 (m, 2H, 4- and 6-*H*), 1.60 (dsept., 8H, *PCH*₂*CH*₃), 1.04 (m, 12H, *CH*₃). ³¹P{¹H} NMR (400 MHz, C₆D₆): δ 141.

The tridentate 'POP' ligand system was also investigated. Thus, 1,3-C₆H₄(OPR₂)₂ (*R* = isopropyl, tertiarybutyl, phenyl and ethyl) was prepared via the reaction of ClPR₂ with resorcinol in the presence of excess triethylamine. The new compound 1,3-bis(diisopropylphosphinoxy)benzene has a ³¹P NMR resonance at δ 150. An analogous reaction of chlorodiisopropylphosphine with 1,3-phenylenediamine affords the ligand N¹,N³-bis(diisopropylphosphino)benzene-1,3-diamine.


Example 2



$R = iso\text{-}propyl$: 2,6-bis((di-iso-propylphosphino)methyl)pyridine

Chloro-di-iso-propylphosphine (10.0 g, 65.5 mmol) in 50 ml of tetrahydrofuran was added dropwise to a suspension of lithium (containing ca. 0.5 % Na) granules (1.18 g, 170 mmol) in 50 ml of tetrahydrofuran and the mixture was stirred for 72 hours. The reaction mixture was then filtered, cooled to -80°C , and a solution of 2,6-bis(chloromethyl)pyridine (5.98 g, 34 mmol) in 20 ml of tetrahydrofuran was slowly added via a dropping funnel with vigorous stirring, resulting in the formation of a red solution. The mixture was allowed to warm to room temperature and was then refluxed for 1 hour; the color slowly changed from red to pale yellow with the formation of a precipitate. The reaction was followed by ^{31}P NMR spectroscopy to ensure completion and then the solvent was removed in vacuo. Hexanes (50 ml) and water (25 ml) were then added and the water layer was then removed. The hexanes layer was then filtered sequentially through a layer of sodium sulphate (Na_2SO_4) and silica gel and then the hexane was removed in vacuo to afford a yellow oil. Excess unreacted di-iso-propylphosphine was removed in vacuo at 70°C for 2 hours. Yield: 8.2 g (37%). ^1H NMR (400 MHz, C_6D_6): δ 7.28 (m, 2 H, 3- and 5-H), 7.13 (m, 1H, 4-H), 3.12 (s, 4H, CH_2), 1.89 (m, 4H, $\text{CH}(\text{CH}_3)_2$), 1.23 (m, 24H, $\text{CH}(\text{CH}_3)_2$). $^{31}\text{P}\{^1\text{H}\}$ NMR (400 MHz, C_6D_6): δ 7.

Example 3




- (a) $R = \text{Ph}$: N^1, N^2 -bis(2-(diphenylphosphino)benzyl)cyclohexane-1,2-diamine;
 (b) $R = 4\text{-CH}_3\text{-C}_6\text{H}_4$ (Tol): N, N -bis(2-(di-*p*-tolylphosphino)benzyl)cyclohexane-

1,2-diamine; (c) $R = 3,5-(CH_3)_2C_6H_3$ (Xyl): N^1,N^2 -bis(2-(bis(3,5-dimethylphenyl)phosphino)-benzyl)-cyclo-hexane-1,2-diamine.

A mixture of N^1,N^2 -bis(2-(di-phenylphosphino)-benzylidene)-cyclohexane-1,2-diamine (2.18 g, 2.83 mmol) (prepared according to the literature procedure: Laue, S.; Greiner, L.; Woltinger, J.; Liese, A. *Adv. Synth. Catal.* 2001, 343, 711) and sodium borohydride ($NaBH_4$) (0.64 g, 17 mmol) in ethanol (30 ml) was refluxed with stirring for 6 hours. The resulting solution was cooled to room temperature and water (15 ml) was added to destroy excess $NaBH_4$. The mixture was extracted with CH_2Cl_2 and the combined extracts were washed with saturated ammonium chloride solution [$NH_4Cl(aq)$] and then water. The organic layer was dried over $MgSO_4$ and then filtered through silica gel. The filtrate was then evaporated to dryness to obtain a yellow solid. Yield: 2.0 g (91%). 1H NMR (400 MHz, CD_2Cl_2): δ 7.58 – 6.80 (m, 20 H, Ph-H), 3.86 (d, 4H, NCH_2), 3.65 (br, 2H, NH), 2.21 (s, 24H, CH_3), 1.80 (m, 8H, cyclohexane-H). $^{31}P\{^1H\}$ NMR (400 MHz, CD_2Cl_2): δ -13.

The tetradentate ' P_2N_2 ' ligand N^1,N^2 -bis(2-(diphenylphosphino)-benzylidene)cyclohexane-1,2-diamine was prepared in high yield by the condensation of diaminocyclohexane with 2-(diphenylphosphino)-benzaldehyde in the presence of magnesium sulfate (J.-X. Gao, H. Zhang, X.-D. Yi, P.-P. Xu, C.-L. Tang, H.-L. Wan, K.-R. Tsai, T. Ikariya, *Chirality* 2000, 12, 383). A sodium borohydride reduction of the material readily affords another tetradentate ligand (Laue, S.; Greiner, L.; Woltinger, J.; Liese, A. *Adv. Synth. Catal.* 2001, 343, 711).

Example 4




N^1,N^3 -bis(di-iso-propylphosphino)benzene-1,3-diamine:

Chloro-di-iso-propylphosphine (5.92 g, 38.8 mmol) was added dropwise to a flask charged with 1,3-phenylenediamine (2 g, 18.5 mmol) and

triethylamine (3.92 g, 38.8 mmol) in toluene (50 ml). After 3 hours, a solid precipitate was removed by filtration and then the solvent was removed from the filtrate. The residue was then extracted with hexanes (50 ml x 2); the hexanes portions were filtered and the solvent was evaporated to give a pale yellow solid. Yield 3.92 g (62%). ^1H NMR (300 MHz, C_6D_6): δ 7.02 (m, 1 H, 2-*H*), 6.98 (m, 1H, 5-*H*), 3.30 (d, 2H, *NH*), 1.37 (dsept., 4H, $\text{CH}(\text{CH}_3)_2$), 0.88 (m, 24H, $\text{CH}(\text{CH}_3)_2$). $^{31}\text{P}\{^1\text{H}\}$ NMR (300 MHz, C_6D_6): δ 42.

Example 5




3,3'-(1,3-phenylenebis(methylene))bis(1-butyl-1H-imidazol-3-ium) chloride:

A neat solution of 1,3-bis(chloromethyl)benzene (3.5 g, 20 mmol) and *n*-butyl imidazole (5.0g, 40 mmol) was stirred at 140°C for 20 hours. After the mixture was cooled to room temperature, the residue was dissolved in CH_2Cl_2 and the product precipitated by the addition of Et_2O (500 ml), affording a very hygroscopic pale yellow solid. Yield: 6.7 g (78%). ^1H NMR (400 MHz, CDCl_3): δ 10.82 (s, 2H, NCHN), 8.26 (s, 2H, imidazole-*H*), 7.61 (d, 2H, $^3J_{\text{HH}} = 9.2$ Hz, pyridine-*H*), 7.34 (s, 2H, imidazole-*H*), 7.23 (t, 1H, $^3J_{\text{HH}} = 8$ Hz, pyridine-*H*), 5.61 (s, 4H, CH_2), 4.24 (t, 4H), 1.84 (quintet, 4H), 1.30 (sextet, 4H), 0.91 (t, 6H).

Example 6

(a) 2,2'-oxybis(ethane-2,1-diyl)bis(di-*iso*-propylphosphine)



Chloro-di-*iso*-propylphosphine (10.0 g, 65.5 mmol) in 50 ml of tetrahydrofuran was added dropwise to a suspension of lithium (containing ca.

0.5 % Na) granules (1.18 g, 170 mmol) in 50 ml of tetrahydrofuran and the mixture was stirred for 72 hours. The reaction mixture was then filtered, cooled to 0°C, and a solution of 1-chloro-2-(2-chloroethoxy)ethane (4.68 g, 32 mmol) in 20 ml of tetrahydrofuran was slowly added via a dropping funnel with vigorous stirring, resulting in the formation of a grey solution. The mixture was allowed to warm to room temperature and was then refluxed for 2 hour; the color slowly changed from grey to pale yellow and a large amount of precipitate formed. The reaction was followed by ³¹P NMR spectroscopy to ensure completion and then the solvent was removed in vacuo. Hexanes (50 ml) and water (25 ml) were then added and the water layer was then removed. The hexanes layer was then filtered sequentially through a layer of sodium sulfate (Na₂SO₄) and silica gel and then the hexane was removed in vacuo to afford a colorless liquid. Excess unreacted di-*iso*-propylphosphine and 1-chloro-2-(2-chloroethoxy)ethane can be removed in vacuo at 70°C for 2 hours. Yield: 8.3 g (83 %). ¹H NMR (400 MHz, C₆D₆): δ 3.56 (m, 8H, CH₂), 1.64 (m, 4H, CH(CH₃)₂), 1.02 (m, 24H, CH(CH₃)₂). ³¹P{¹H} NMR (400 MHz, C₆D₆): δ -7.


(b) 2,2'-oxybis(ethane-2,1-diyl)bis(ditertiarybutylphosphine)

The compound 2,2'-oxybis(ethane-2,1-diyl)bis(ditertiarybutylphosphine) was prepared according to the literature procedure (Timmer, K.; Thewissen, D. H.M. W.; Marsman, J. W. *Recl. Trav. Chim. Pays-Bas* **1988**, 107, 248).

The 'POP' pincer ligand 2,2'-oxybis(ethane-2,1-diyl)bis(diisopropylphosphine) was prepared by the reaction of 1-chloro-2-(2-chloroethoxy)ethane with lithium diisopropylphosphine. The ligand has a ³¹P NMR resonance at δ -7 and the expected ¹H NMR signals. The tertiarybutyl analogue 2,2'-oxybis(ethane-2,1-diyl)bis(ditertiarybutylphosphine) was prepared similarly.

Example 7


(a) Bis(2-ditertiarybutylphosphino)ethyl)amine
(R₂PCl; R = tertiarybutyl)



Chloroditertbutylphosphine (15.0 g, 83 mmol) in tetrahydrofuran (50 ml) was added through a dropping funnel to a suspension of lithium granules (containing ca. 0.5 % Na, 1.50 g, 216 mmol) in tetrahydrofuran (50 ml). The resulting suspension was stirred vigorously at room temperature for 72 hours. The reaction mixture was then decanted through a metal cannula; the solution was then cooled to -80 °C and a solution of bis(chloroethyl) trimethylsilyl amine (9.00 g, 42.0 mmol) in tetrahydrofuran (10 ml) was slowly added through a dropping funnel with vigorous stirring. The mixture was then allowed to warm to room temperature and refluxed for 1 hour. The reaction was then cooled to room temperature and cooled to 0°C again. Degassed sulfuric acid (2M, 42 ml) was added to the reaction mixture through a dropping funnel. It was then stirred at room temperature for 1 hour. Sodium hydroxide solution (4M, 40 ml, 160 mmol) was then added through a dropping funnel. After thirty minutes, the aqueous layer was removed by cannula and the organic layer was washed with two portions of degassed water. The organic layer was then dried with magnesium sulfate. After stirring for one hour, the magnesium sulfate was filtered off through a pad of silica gel and the solvent was removed in vacuo to yield a colorless liquid (10.34 g, 68 %). ¹H NMR (400 MHz, C₆D₆): δ 2.72 (q, 4 H, CH₂), 1.47 (m, 4H, CH₂), 1.00 (d, 36H, CH₃). ³¹P{¹H} NMR (162 MHz, C₆D₆): δ 22.2.

The tridentate 'PNP' ligands N(H)(CH₂CH₂PR₂)₂ (R = tertiarybutyl, adamantyl, isopropyl, cyclohexyl, ethyl) were prepared by reaction of the appropriate phosphide (e.g. lithium ditertiarybutyl phosphide, LiP^tBu₂) with bis(chloroethyl) trimethylsilyl amine, followed by nitrogen deprotection (Scheme 1). The ³¹P NMR resonance for bis(2-(ditertiarybutyl)ethyl)amine appears at δ 22.2 and the ¹H NMR spectrum of this material shows the expected chemical shifts. The isopropyl, ethyl, cyclohexyl, and adamantyl substituted derivatives were prepared similarly in good yield and purity.


(b) Bis(2-(di-*i*-propylphosphino)ethyl)amine
(R₂PCl; R = isopropyl)



Chlorodiisopropylphosphine (14.5 g, 95.3 mmol) in tetrahydrofuran (100 ml) was added through a dropping funnel to a suspension of lithium granules (containing ca. 0.5 % Na 1.72 g, 247 mmol) in tetrahydrofuran (50 ml). The resulting suspension was stirred vigorously at room temperature for 72 hours. The reaction mixture was then decanted through a metal cannula; the solution was then cooled to -80°C and a solution of bis(chloroethyl) trimethylsilyl amine (10.33 g, 48.2 mmol) in tetrahydrofuran (10 ml) was slowly added through a dropping funnel with vigorous stirring. The mixture was then allowed to warm to room temperature and was refluxed for four hours. The reaction was then cooled to room temperature and cooled to 0°C again. Degassed sulfuric acid (2M, 50 ml) was added to the reaction mixture through a dropping funnel and the mixture was then stirred at room temperature for one hour. Sodium hydroxide solution (4M, 50 ml) was then added through a dropping funnel. After 30 minutes, the aqueous layer was decanted by cannula and the organic layer was washed with two portions of degassed water. The organic layer was then dried with magnesium sulfate. After stirring for one hour, the magnesium sulfate was filtered off through a pad of silica gel and the solvent was removed in vacuo to yield a colorless liquid (8.0 g, 54 %). ^1H NMR (400 MHz, C_6D_6): δ 2.70 (q, 4 H, CH_2), 1.47 (t, 4H, CH_2), 1.47 (overlapped, m, 4H, CH_2), 0.90 (m, 24H, CH_3). $^{31}\text{P}\{^1\text{H}\}$ NMR (162 MHz, C_6D_6): δ -0.95.

c) $R = \text{Bis}(2\text{-(di-ethylphosphino)ethyl})\text{amine}$

(R_2PCl ; $R = \text{ethyl}$)




Chlorodiethylphosphine (10 g, 9.7 ml, 80.3 mmol) in tetrahydrofuran (15 ml) was added through a dropping funnel to a suspension of lithium granules (containing ca. 0.5 % Na) (1.46 g, 210 mmol) in tetrahydrofuran (50 ml). The resulting suspension was stirred vigorously at room temperature for 72 hours.

- 5 The reaction mixture was then decanted through a metal cannula; the solution was then cooled to -80°C and a solution of bis(chloroethyl) trimethylsilyl amine (8.56 g, 40.0 mmol) in tetrahydrofuran (10 ml) was slowly added through a dropping funnel with vigorous stirring. The mixture was then allowed to warm to room temperature and was refluxed for 6 hours. The reaction was then
- 10 cooled to 0°C . Degassed sulfuric acid (2M, 40 ml) was added to the reaction mixture through a dropping funnel. It was then stirred at room temperature for 1 hour. Sodium hydroxide solution (4 M, 40 ml, 160 mmol) was then added through a dropping funnel. After thirty minutes, the aqueous layer was decanted by cannula and the organic layer was washed with two portions of
- 15 degassed water. The organic layer was then dried with magnesium sulfate. After stirring for one hour, the magnesium sulfate was filtered off through a pad of silica gel and the solvent was concentrated to yield a colorless liquid (7 g, 70%). ^1H NMR (400 MHz, C_6D_6): δ 2.65 (q, 4 H, CH_2), 1.47 (t, 4H, CH_2), 1.25 (quartet, 8H, ethyl- CH_2), 0.96 (quintet, 12H, ethyl- CH_3). $^{31}\text{P}\{^1\text{H}\}$ NMR
- 20 (162 MHz, C_6D_6): δ -26.8.

Example 8

(a) Bis(2-(dicyclohexylphosphino)ethyl)amine

(R_2PH ; R = cyclohexyl)




25

- To dicyclohexylphosphine (5.09 g, 25.6 mmol) in tetrahydrofuran (50 ml) was added *n*-butyllithium (11.3 ml, 2.5 M in hexanes, 28.3 mmol) through a dropping funnel at 0°C . The resulting suspension was allowed to reflux for one hour at 60°C and then the solution was cooled to -80°C . A solution of
- 30 bis(chloroethyl) trimethylsilyl amine (2.75 g, 12.8 mmol) in tetrahydrofuran (30 ml) was slowly added through a dropping funnel with vigorous stirring. The

mixture was then allowed to warm to room temperature and was refluxed for 3 hours and then the reaction was cooled to room temperature and cooled to 0°C again. Degassed sulfuric acid (2 M, 13 ml, 26 mmol) was added to the reaction mixture through a dropping funnel. It was then stirred at room temperature for 1 hour. Sodium hydroxide (4 M, 13 ml, 52 mmol) was then added through a dropping funnel. After 30 minutes, the aqueous layer was decanted by cannula and the organic layer was washed with two portions of degassed water. The organic layer was then dried with magnesium sulfate. After stirring for one hour, the magnesium sulfate was filtered off through a pad of silica gel and the solvent was concentrated to yield a colorless liquid (4.8 g, 80%). ¹H NMR (400 MHz, C₆D₆): δ 2.65 (m, 4 H, CH₂), 1.60 – 1.80 (b, 20H, cyclohexyl-H), 1.50 (m, 4H, CH₂), 1.05 – 1.30 (b, 24H, cyclohexyl-H). ³¹P{¹H} NMR (162 MHz, C₆D₆): δ -16.9.


(b) Bis(2-(ditertiarybutylphosphino)ethyl)amine

(R₂PH; R = tertiarybutyl)



c) Bis(2-(diadamantylphosphino)ethyl)amine.

(R₂PH; R = adamantyl)




Prepared analogously to the R = cyclohexyl analogue. The yield and purity are similar to that obtained by method using lithium metal reduction of the chloro ditertiarybutylphosphine. Yield: (4.6g, 84%) ¹H NMR (400 MHz, C₆D₆): δ 2.60 (m, 4 H, CH₂), 1.80 (d, 20H, adamantyl-H), 1.65 (s, 24 H, adamantyl-H). ³¹P{¹H} NMR (162 MHz, C₆D₆): δ 20.9.

Example 9


a) Bis(2-(diisopropylphosphino)ethyl)methylamine

$\text{CH}_3\text{N}(\text{CH}_2\text{CH}_2\text{PR}_2)_2$ ($R = \text{isopropyl}$)



- Chlorodiisopropylphosphine (4.76g, 4.76 ml, 31 mmol) in
- 5 tetrahydrofuran (50 ml) was added through a dropping funnel to a suspension of lithium granules (containing ca. 0.5 % Na) (0.63 g) in tetrahydrofuran (50 ml). The resulting suspension was stirred vigorously at room temperature for 72 hours to afford a lithium diisopropylphosphide solution. The reaction mixture was then decanted through a metal cannula, and the solution was
- 10 then cooled to -80°C . To bis(chloroethyl) methyl ammonium chloride (3 g, 15.6 mmol) in tetrahydrofuran (30 ml) was added dropwise *n*-butyllithium (2.5 M in hexanes, 6.24 ml, 15.6 mmol) through a dropping funnel at 0°C . The reaction was stirred at 0°C for thirty minutes. This solution was then added to the above lithium diisopropylphosphide solution at 0°C with vigorous stirring.
- 15 The mixture was then allowed to warm to room temperature and was refluxed for 3 hours. Degassed water (50 ml) was then added to the reaction mixture. The aqueous layer was decanted by cannula and the organic layer was washed with two portions of degassed water. The organic layer was then dried with magnesium sulfate. After stirring for an hour, the magnesium
- 20 sulfate was filtered off through a pad of silica gel and the solvent was concentrated to yield a colorless liquid (3.5 g, 70%). ^1H NMR (400 MHz, C_6D_6): δ 2.64 (m, 4 H, CH_2), 2.21 (s, 3H, CH_3), 1.59 (overlapped, m, 4H, CH_2), 1.59 (overlapped, m, 4H, $\text{PCH}(\text{CH}_3)_2$), 1.03 (m, 24 H, $\text{PCH}(\text{CH}_3)_2$). $^{31}\text{P}\{^1\text{H}\}$ NMR (162 MHz, C_6D_6): δ 1.6.


- 25 b) Bis(2-(diisopropylphosphino)ethyl)methylamine
 $\text{CH}_3\text{N}(\text{CH}_2\text{CH}_2\text{PR}_2)_2$ ($R = \text{tertiarybutyl}$)



n -Butyllithium (12.4 ml of 2.5 M in hexanes, 31 mmol) was added dropwise to 45.4 ml of 10 wt % (31 mmol) ditertiarybutyl phosphine in tetrahydrofuran and the mixture was heated to reflux for one hour to afford a ditertiarybutylphosphide solution, which was subsequently cooled to $-80\text{ }^{\circ}\text{C}$. A suspension of 2-chloro- N -(2-chloroethyl)- N -methylethanaminium chloride (3.0 g, 15.5 mmol) was cooled to $0\text{ }^{\circ}\text{C}$ in 50 ml of tetrahydrofuran and then 6.2 ml of 2.5 M n -butyllithium (15.5 mmol, solution in hexanes) was added dropwise over ca. ten minutes. The mixture was stirred at $0\text{ }^{\circ}\text{C}$ for twenty minutes and was then cooled to $-80\text{ }^{\circ}\text{C}$. The solution was then transferred via cannula to the reaction vessel containing the lithium ditertiarybutylphosphide solution at $-80\text{ }^{\circ}\text{C}$ and was warmed to room temperature. After refluxing the mixture for 4 hours the solution was concentrated to ca. 20 ml and then 50 ml of hexanes was added. The solution was washed with three 20 ml portions of degassed water and was then dried over magnesium sulfate. After filtration through a small plug of magnesium sulfate and silica gel, the solvent was removed in vacuo to afford a colorless high purity oil. Yield 4.7 g, 80 %. ^1H NMR (400 Mhz, C_6D_6): δ 2.49 (m, 4H, CH_2); 2.01 (s, 3H, NCH_3); 1.39 (m, 4H, CH_2); 0.82 (d, $^3J_{\text{PH}} = 10.5$ Hz, 36H, $\text{C}(\text{CH}_3)_3$). ^{31}P NMR (121.5 Hz, C_6D_6): δ 25.6.

c) *Bis(2-(diadamantylphosphino)ethyl)methylamine*


$\text{CH}_3\text{N}(\text{CH}_2\text{CH}_2\text{PR}_2)_2$ ($R = \text{adamantyl}$)



The adamantyl analogue was prepared in a similar fashion except that the di-adamantylphosphide was prepared by reacting diadamantylphosphine

with *n*-butyllithium under reflux for 2 hours (Yield: 8.3 g, 77%). ^1H NMR (400 MHz, C_6D_6): δ 2.47 (m, 4 H, CH_2), 2.29 (s, 3H, CH_3), 1.73 – 1.92 (b, 60H, adamantyl-H), 1.53 (m, 4H, CH_2). $^{31}\text{P}\{^1\text{H}\}$ NMR (162 MHz, C_6D_6): δ 22.5 (ca. 60 %), 18.8 (ca. 40 %).

- 5 (d) *Bis(2-diphenylphosphino)ethyl)methylamine*
 $\text{CH}_3\text{N}(\text{CH}_2\text{CH}_2\text{PR}_2)_2$ (*R* = phenyl)



- n*-Butyllithium (6.2 ml of 2.5 M in hexanes, 15.5 mmol) was added dropwise to 3.00 g (15.5 mmol) of 2-chloro-*N*-(2-chloroethyl)-*N*-methylethan-aminium chloride in 50 ml of tetrahydrofuran at 0 °C over ca. ten minutes. The mixture was stirred for twenty minutes at 0 °C and was then cooled to -80 °C. 62 ml of 0.5 M (31 mmol) of potassium diphenylphosphide in tetrahydrofuran was added and the mixture was then heated to reflux for two hours. After concentrating the solution in vacuo to ca. 20 ml, 50 ml of hexanes was added. The solution was washed with two 20 ml portions of degassed water, dried over magnesium sulfate and then filtered through a plug of magnesium sulfate and silica gel. The solvent was removed in vacuo affording a colorless oil. Yield 5.705 g, 87%. ^1H NMR (400 Mhz, C_6D_6): δ 7.04-7.7.47 (m, 20H, C_6H_5); 2.46 (m, 4H, CH_2); 2.11 (m, 4H, CH_2); 2.02 (s, 3H, CH_3). ^{31}P NMR (162 MHz, C_6D_6): δ -18.8.


- A ligand system $\text{N}(\text{CH}_3)(\text{CH}_2\text{CH}_2\text{PR}_2)_2$ (*R* = isopropyl, tertiarybutyl, adamantyl, phenyl) was prepared via the reaction of a phosphide (e.g. lithium ditertiarybutyl phosphide, LiP^tBu_2) with bis(chloroethyl)methyl amine. This latter material was prepared in situ by the reaction of bis(chloroethyl)methyl ammonium chloride with *n*-butyl lithium at 0 °C. The ^{31}P NMR spectrum of bis(2-(ditertiarybutyl)ethyl)methylamine has a resonance at δ 25.6 whereas the ^1H NMR spectrum of this ligand indicates the presence of tertiarybutyl, methylene and methyl groups.

Other structurally similar 'PNP' ligand systems were prepared using previously reported procedures. For example, bis(2-diisopropylphosphino-4-methylphenyl) amine was synthesized (Scheme 12) as described by Ozerov and coworkers (Fan, L.; Foxman, B. M.; Ozerov, O. V. *Organometallics* **2004**, 23, 326-328), whereas 2,6-bis((diisopropylphosphino)methyl)pyridine (Scheme 13) was prepared via the reaction of lithium diisopropylphosphide with 2,6-bis(chloromethyl)pyridine. A 'PNN' ligand system N¹-(2-(diadamantylphosphino)ethyl)-N²,N²-diethylethane-1,2-diamine was prepared analogously to a literature procedure (Choualeb, A.; Lough, A. J.; Gusev, D. G. *Organometallics* **2007**, 26, 5224-5229).

Example 10


Bis(2-diisopropylphosphino-4-methylphenyl) amine

a) Synthesis of bis(2-bromo-4-methylphenyl)amine



The compound was prepared according to the literature procedure (Gilman, H.; Zuech, E. A.; *J. Org. Chem.* **1961**, 3481 – 3484). Yield: (4.51 g, 49 %). ¹H NMR (400 MHz, CDCl₃): δ 7.38 (s, 1H, PhH), 7.08 (d, 1H, PhH), 6.9 (d, 1H, PhH), 6.1 (br s, 1H, NH), 2.26 (s, 6H, CH₃).

b) Synthesis of bis(2-diisopropylphosphino-4-methylphenyl) amine




The compound was prepared according to the literature procedure (Fan, L.; Foxman, B. M.; Ozerov, O. V.; *Organometallics* **2004**, 23, 326 – 328). Yield: (2.38 g, 98%) ¹H NMR (400 MHz, C₆D₆): δ 8.28 (t, 1H, J_{P-H} = 8 H,

NH), 7.38 (d, 2H, $J = 6$ Hz, PhH), 7.19 (s, 2H, PhH), 6.91 (d, 2H, $J = 8$ Hz, PhH), 2.18 (s, 6H, PhCH₃), 2.01 (m, 4H, CH CH₃), 1.12 (dd, 12H, $J = 15$ Hz, $J = 7$ Hz, CHCH₃), 0.97 (dd, 12H, CHCH₃). ³¹P{¹H} NMR (162 MHz, C₆D₆): δ -12.9.

5


Example 11

2,6-bis((diisopropylphosphino)methyl)pyridine




10 Chloro diisopropylphosphine (10.0 g, 65.5 mmol) in 50 ml of tetrahydrofuran was added dropwise to a suspension of lithium (containing ca. 0.5 % Na) granules (1.18 g, 170 mmol) in 50 ml of tetrahydrofuran and the mixture was stirred for 72 hours. The reaction mixture was then filtered, cooled to -80°C, and a solution of 2,6-bis(chloromethyl)pyridine (5.98 g, 34 mmol) in 20 ml of tetrahydrofuran was slowly added via a dropping funnel with vigorous stirring, resulting in the formation of a red solution. The mixture was allowed to warm to room temperature and was then refluxed for one hour. The reaction was followed by ³¹P NMR spectroscopy to ensure completion and then the solvent was removed in vacuo. Hexanes (50 ml) and water (25 ml) were then added and the water layer was then removed. The hexanes layer was then filtered sequentially through a layer of sodium sulfate (Na₂SO₄) and silica gel and then the hexane was removed in vacuo to afford a yellow oil. Excess unreacted diisopropylphosphine can be removed in vacuo at 70°C for 2 hours. Yield: 8.2 g (37%). ¹H NMR (400 MHz, C₆D₆): δ 7.28 (m, 2 H, 3- and 5-H), 7.13 (m, 1H, 4-H), 3.12 (s, 4H, CH₂), 1.89 (m, 4H, CH(CH₃)₂), 1.23 (m, 24H, CH(CH₃)₂). ³¹P{¹H} NMR (162 MHz, C₆D₆): δ 7.0.

The compound 2,6-bis((ditertiarybutylphosphino)methyl)pyridine was prepared in an analogous manner. ³¹P NMR spectroscopy indicated a mixture formed. ³¹P{¹H} NMR (162 MHz, C₆D₆): δ 35.7 (40 %); 31.4 (10%); 31.1 (50%).

Example 12**(Phenylphosphinediyl)dimethanol**


5 This material was prepared according to the literature procedure: Higham, L. J.; Whittlesey, M. K.; Wood, P. T. *J. Chem. Soc., Dalton Trans.* **2004**, 4202. ^1H NMR (400 Mhz, C_6D_6): δ 7.50 (m, 2H, C_6H_5); 7.15 (m, 3H, C_6H_5); 4.10 (d, $2J_{\text{PH}} = 9.9$ Hz, CH_2); 2.41 (br s, 2H, OH). ^{31}P NMR (162 Mhz, C_6D_6): -14.9.

10

Example 13***N,N'*-(phenylphosphinediyl)bis(methylene)dipropan-2-amine**

15 Degassed isopropyl amine (1 ml, 11.6 mmol) of was added to 491 mg (2.886 mmol) of (phenylphosphinediyl)dimethanol ($\text{PhP}(\text{CH}_2\text{OH})_2$) and the mixture was stirred overnight. The excess amine was removed in vacuo to afford the product as a viscous colorless oil. ^1H NMR (400 Mhz, C_6D_6): δ 7.55 (m, 2H); 7.09 (m, 3H); 3.11 (m, 4H); 2.68 (m, 2H); 0.89 (m, 12H). ^{31}P NMR (162 Mhz, C_6D_6): -29.5.

20


Example 13***N*¹-(2-(diadamantylphosphino)ethyl)-*N*²,*N*²-diethylethane-1,2-diamine****a) *N*¹,*N*¹-diethyl-*N*²-(2-hydroxyethyl)ethane-1,2-diamine hydrochloride**

25

The compound was prepared according to the literature procedure (Choualeb, A.; Lough, A. J.; Gusev, D. G. *Organometallics* **2007**, 26, 5224 – 5229). ^1H NMR (methanol- d_4): δ 3.68 (t, $^3J_{\text{HH}} = 5.6$, 2H, CH_2O), 3.06 (t, $^3J_{\text{HH}} =$

5.6, 2H, CH_2NH), 2.97 (m, 4H, $\text{NCH}_2\text{CH}_2\text{N}$), 2.84 (q, $^3J_{\text{HH}} = 7.3$, 4H, NCH_2), 1.11 (t, $^3J_{\text{HH}} = 7.3$, 6H, CH_3).

b) *N*¹-(2-chloroethyl)-*N*²,*N*²-diethylethane-1,2-diaminium chloride




5

A solution of thionyl chloride (SOCl_2) (16.9 g, 0.14 mol) in dichloromethane (20 ml) was added dropwise to a vigorously stirred suspension of *N*¹,*N*¹-diethyl-*N*²-(2-hydroxyethyl)ethane-1,2-diaminium chloride (21 g, 0.11 mol) in dichloromethane (120 ml) which was cooled at 0°C. The ice bath was removed and the reaction mixture was allowed to stir at room temperature for 1 hour. The mixture was then allowed to reflux for 1 hour. After cooling, the suspension was filtered and the product was washed with dichloromethane (40 ml) to give a colorless solid. (20 g, 78 %). ¹H NMR (methanol-*d*₄): δ 4.03 (t, $^3J_{\text{HH}} = 6.1$, 2H, CH_2Cl), 3.68 (br s, 4 H, CH_2NH), 3.61 (t, $^3J_{\text{HH}} = 5.7$, 2H, Et_2NCH_2), 3.38 (q, $^3J_{\text{HH}} = 7.3$, 4H, CH_3CH_2), 1.43 (t, $^3J_{\text{HH}} = 7.3$, 6H, CH_3).

15

c) *N*¹-(2-(diadamantylphosphino)ethyl)-*N*²,*N*²-diethylethane-1,2-diamine



20

A solution of lithium diadamantylphosphide was prepared by refluxing 5.92 ml of 2.5 M *n*-butyllithium (14.8 mmol) in hexanes with diadamantylphosphine (4.47 g, 14.8 mmol) in tetrahydrofuran for one hour. The mixture was cooled to -80 °C and was transferred by cannula to the *N*¹-(2-chloroethyl)-*N*²,*N*²-diethyl-*N*¹-(trimethylsilyl)ethane-1,2-diamine solution (also at -80 °C). The mixture was warmed to room temperature, and then heated at reflux for one hour. 10 ml of water was then added and the mixture was heated to reflux for three hours. The volume was concentrated in vacuo to ca. 10 ml and then 50 ml of hexanes was added. The solution was washed with three 20 ml portions of degassed water and was then dried over magnesium sulfate. It was then filtered through a small plug of silica


25

30

gel/magnesium sulfate and the plug was washed with 20 ml of hexanes. The solvent was removed in vacuo to afford a colorless solid. The spectroscopic data was not obtained due to the low solubility of the ligand.

5 Example 14

(*N*¹*E*,*N*²*E*)-*N*¹,*N*²-bis(2-(diphenylphosphino)benzylidene)cyclohexane-1,2-diamine




This material was prepared according to a literature procedure (J.-X.

- 10 Gao, H. Zhang, X.-D. Yi, P.-P. Xu, C.-L. Tang, H.-L. Wan, K.-R. Tsai, T. Ikariya, *Chirality* **2000**, 12, 383). Yield: 8.0 g (92 %). ¹H NMR (400 MHz, CD₂Cl₂): δ 8.51 (m, 2H); 7.65 (m, 2H); 7.23-7.10 (m, 24H); 6.75 (m, 2H); 2.97 (m, 2H); 1.59 (m, 2H); 1.33 (m, 4H); 1.19 (m, 2H). ³¹P{¹H} NMR (162 MHz, CD₂Cl₂): δ -12.4.

15

Example 15

*N*¹,*N*²-bis(2-(diphenylphosphino)benzyl)cyclohexane-1,2-diamine




- A mixture of *N*¹,*N*²-bis(2-(diphenylphosphino)benzylidene)cyclohexane-
20 1,2-diamine (2.18 g, 2.83 mmol) (prepared according to the literature procedure: Laue, S.; Greiner, L.; Woltinger, J.; Liese, A. *Adv. Synth. Catal.* **2001**, 343, 711) and sodium borohydride (NaBH₄) (0.64 g, 17 mmol) in ethanol (30 ml) was refluxed with stirring for 6 hours. The resulting solution was cooled to room temperature and water (15 ml) was added to destroy
25 excess NaBH₄. The mixture was extracted with dichloromethane and the combined extracts were washed with saturated aqueous ammonium chloride

solution [NH_4Cl] and then water. The organic layer was dried over magnesium sulfate and then filtered through silica gel. The filtrate was then evaporated to dryness to obtain a yellow solid. Yield: 2.0 g (91%). ^1H NMR (400 MHz, CD_2Cl_2): δ 7.58 – 6.80 (m, 20 H, Ph-H), 3.86 (d, 4H, NCH_2), 3.65 (br, 2H, NH), 2.21 (s, 24H, CH_3), 1.80 (m, 8H, cyclohexane-H). $^{31}\text{P}\{^1\text{H}\}$ NMR (162 MHz, CD_2Cl_2): δ -13.


Example 16

3,3'-(1,3-phenylenebis(methylene))bis(1-butyl-1H-imidazol-3-ium) chloride




The compounds were prepared according to the literature procedure (Caballero, A.; Diez-Barra, E.; Jalon, F. A.; Merino, S.; Tejeda, J. J. *Organomet. Chem.* **2001**, 617 – 618, 395 – 398 and b) Simons, R. S.; Custer, P.; Tessier, C. A.; Youngs, W. J.; *Organometallics* **2003**, 22, 1979 – 1982). A neat solution of 1,3-bis(chloromethyl)benzene (3.5 g, 20 mmol) and n-butyl imidazole (5.0g, 40 mmol) was stirred at 140°C for 20 hours. After the mixture was cooled to room temperature, the residue was dissolved in dichloromethane and the product precipitated by the addition of diethyl ether (500 ml), affording a very hygroscopic pale yellow solid. Yield: 6.7 g (78%). ^1H NMR (400 MHz, CDCl_3): δ 10.82 (s, 2H, NCHN), 8.26 (s, 2H, imidazole-H), 7.61 (d, 2H, $^3J_{\text{HH}} = 9.2$ Hz, pyridine-H), 7.34 (s, 2H, imidazole-H), 7.23 (t, 1H, $^3J_{\text{HH}} = 8$ Hz, pyridine-H), 5.61 (s, 4H, CH_2), 4.24 (t, 4H), 1.84 (quintet, 4H), 1.30 (sextet, 4H), 0.91 (t, 6H).

A pincer ligand containing two 'NCN-carbene' fragments was synthesized by the reaction of 1,3-bis(chloromethyl)benzene with n-butyl imidazole at 140 °C. This reaction afforded the dication 3,3'-(1,3-phenylenebis(methylene))bis(1-butyl-1H-imidazol-3-ium) chloride. The ^1H NMR spectrum of this material confirms the cationic nature with a resonance for the imidazolium protons in the 3 and 3' positions appearing at δ 10.82.

Example 17*Bis(2-chloroethyl)ammonium chloride with n-butyl imidazole*

- 5 A 0.74 ml (5.63 mmol) aliquot of n-butyl imidazole was added to 0.500 g (2.8 mmol) of bis(2-chloroethyl)ammonium chloride $[H_2N(CH_2CH_2Cl)_2]Cl$ in 10 ml of toluene and the mixture was refluxed overnight. The solvent was removed in vacuo and the residue was triturated in ether for three days. The solvent was decanted and the residue dried in vacuo and was used directly
- 10 for production of the catalysts.

PREPARATION OF METAL COMPLEXES**Metal Complexes with (-P-N-P-) Ligands****Example 18**

(a) bis(2-(di-iso-propylphosphino)ethyl)amine dichloro cobalt and (b) bis(2-(di-tert-butylphosphino)ethyl)amine dichloro cobalt

R = iso-propyl and tert-butyl


- 20 These compounds were prepared in an analogous manner and only the synthesis of bis(2-(di-iso-propylphosphino)ethyl)amine dichloro cobalt is described herein. Excess bis(2-(di-iso-propylphosphino)ethyl)amine $[HN(CH_2CH_2P^iPr_2)_2]$, 1.85 g, 6.06 mmol] in 5 mL of tetrahydrofuran was added dropwise to a vigorously stirred suspension of $CoCl_2$ (0.690 g, 5.31 mmol) in

20 ml of THF. The mixture was stirred overnight and then the solvent was removed in vacuo. The solid was triturated in 50 ml of ether and was then collected on a glass frit and dried in vacuo. Yield: 2.065 g, 84%. A single crystal of bis(2-(di-*iso*-propylphosphino)ethyl)amine dichloro cobalt suitable for

5 X-ray crystallography was obtained by slow evaporation of a dichloromethane/hexanes solution of the compound and the structure is shown below in Fig. 5. The resulting crystal structure confirmed the structure of the product. The compound exhibited a good activity towards ammonia borane hydrolysis.

10 (c) *Bis*-(2-(diphenylphosphino)ethyl)amine dichloro cobalt

R = phenyl




160 μ l (1.148 mmol) of triethylamine (NEt_3) was added to 250 mg (0.523 mmol) of bis(2-(di-*iso*-propylphosphino)ethyl)amine hydrochloride

15 $[\text{HN}(\text{CH}_2\text{CH}_2\text{PPh}_2)\cdot\text{HCl}]$ in 10 ml of THF and the mixture was stirred for 10 minutes. 65 mg (0.501 mmol) of cobalt dichloride was added and the mixture was refluxed for 30 minutes. The solvent was removed in vacuo and the purple solid was washed with 3 $\times$ 5 ml of *iso*-propanol and was then dried in vacuo. Yield: 80 %. NMR spectra were not obtained. The compound

20 exhibited a good activity towards ammonia borane hydrolysis.

(d) *Bis*(2-(diadamantylphosphino)ethyl)amine dichlorocobalt(II)




In a typical experiment, to a solution of bis(2-(diadamantylphosphino)ethyl)amine (0.20 g, 0.30 mmol) in tetrahydrofuran

25 (20 ml) was added cobalt(II) chloride (0.04 g, 0.30 mmol). The reaction

mixture was then stirred and refluxed for 4 hours. The solvent was then evaporated, and the residue was precipitated by the addition of hexanes. The blue precipitate was filtered and then washed with hexanes to obtain a blue solid. Yield: 0.18 g, 75%. NMR spectra were not obtained. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a pink solution. The material was tested for ammonia borane hydrolysis.

Cobalt PNP complexes were prepared by the reactions of $N(H)(CH_2CH_2PR_2)_2$ (R = isopropyl, phenyl, adamantyl) with cobalt(II)chloride. For R = isopropyl, the product is a pink solid that was isolated in high yield. In order to characterize the paramagnetic material, a single crystal was obtained and the X-ray structure was determined (as seen in Figure 3). The structure consists of a five coordinate square pyramidal cobalt center with the PNP ligand bound meridionally. The phosphorus atoms, the nitrogen and a chlorine atom comprise the base of the square pyramid. A chloride ligand is at the apex.

Example 19



(a) Bis(2-(diisopropylphosphino)ethyl)aminechlorodihydrido-iridium(III)

R = *iso*-propyl

This was prepared according to the literature procedure (Clarke, Z. E.; Maragh, P. T.; Dasgupta, T. P.; Gusev, D. G.; Lough, A. J.; Abdur-Rashid, K. *Organometallics* **2006**, 25, 4113). Ammonia borane was added (50 mg, 1.620 mmol) and the hydrolysis rate is moderate to good. 1H NMR (C_6D_6): δ -25.13 (td, $J_{HH} = 8.0$ Hz, $J_{HP} = 14.7$ Hz, 1H, IrH); -19.83 (td, $J_{HH} = 8.0$ Hz, $J_{HP} = 13.5$ Hz, 1H, IrH); 0.84 (dd, $J_{HH} = 7.0$ Hz, $J_{HP} = 14.1$ Hz, 6H, CH_3); 1.13 (m, 12H, CH_3); 1.59 (dd, $J_{HH} = 7.0$ Hz, $J_{HP} = 14.1$ Hz, 6H, CH_3); 1.65-1.87 (m, 8H); 2.93 (m, 4H, CH_2); 3.99 (br, 1H, NH). $^{31}P\{^1H\}$ NMR (C_6D_6): δ 54.17.

(b) *Bis(2-(di-tert-butylphosphino)ethyl)amine dihydrido chloro cyclooct-1-enyl iridium*

R = tert-butyl

A mixture of [iridium bis(cyclooctene) chloride] dimer $[\text{Ir}(\text{COE})_2\text{Cl}]_2$ (0.675 g, 0.75 mmol) and bis(2-(di-tert-butylphosphino)ethyl)amine (0.540 g, 1.49 mmol) was dissolved in toluene (5 ml) and stirred for 20 minutes. Hexanes (10 ml) was added and then the precipitated solid was collected by filtration and dried in vacuo. Yield: 0.772 g, 74 %. ^1H NMR (C_6D_6), δ : -25.46 (t, broad, 1H, IrH); 1.21 (vt, $J = 6.0$ Hz, 18H, CH_3); 1.52 (vt, $J = 6.0$ Hz, 18H, CH_3); 1.68-1.92 (m, br, 12H, CH_2); 2.12 (br, 2H, CH_2); 2.34 (m, 2H, CH_2); 2.58 (m, 2H, CH_2); 3.29 (m, 2H, CH_2); 5.51 (br, 1H, CH); 6.03 (br, 1H, NH). $^{31}\text{P}\{^1\text{H}\}$ NMR (C_6D_6), δ : 31.6.

(c) *Bis(2-(dicyclohexylphosphino)ethyl)aminechlorodihydrido-iridium(III)*




15

A mixture of chlorobis(cyclooctene)iridium(I) dimer $[\text{Ir}(\text{COE})_2\text{Cl}]_2$ (0.19 g, 0.21 mmol) and bis(2-(dicyclohexylphosphino)ethyl)amine (0.20 g, 4.29 mmol) was dissolved in toluene (5 ml) and stirred for 4 hours at room temperature. The solvent was then evaporated and hexanes (20 ml) was added and then the precipitated white solid was collected by filtration and dried in vacuo. Yield: 0.18 g, 60 %. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a red solution. Ammonia borane was added (50 mg, 1.620 mmol) and the hydrolysis rate is good and is comparable to the *iso*-propyl analogue. ^1H NMR (400 MHz, C_6D_6): δ 3.15 (b, 4H, CH_2), 2.70 (b, 4H, CH_2), 1.60 – 1.80 (b, 20H, cyclohexyl-H), 1.20 – 1.40 (b, 24H, cyclohexyl-H), -25.30 (t, broad, 1H, IrH). $^{31}\text{P}\{^1\text{H}\}$ NMR (162 MHz, C_6D_6): δ 20.3. The compound transforms into bis(2-(dicyclohexylphosphino)ethyl)aminedichlorohydrido-iridium(III) in dichloromethane.


(d) *Bis(2-(diadamantylphosphino)ethyl)aminechlorodihydrido-iridium(III)*

30



A mixture of chlorobis(cyclooctene)iridium(I) dimer $[\text{Ir}(\text{COE})_2\text{Cl}]_2$ (0.13 g, 0.15 mmol) and bis(2-(diadamantylphosphino)ethyl)amine (0.20 g, 2.97 mmol) was dissolved in tetrahydrofuran (5 ml) and stirred for 4 hours at room temperature. The solvent was then evaporated and hexanes (20 ml) was added and then the precipitated white solid was collected by filtration and dried in vacuo. Yield: 0.19 g, 70 %. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a red solution. Ammonia borane was added (50 mg, 1.620 mmol) and the hydrolysis rate is exceptionally good and is comparable to the tertiarybutyl analogue. $^{31}\text{P}\{^1\text{H}\}$ NMR (162 MHz, methanol- d_4): δ 70.6. Due to the insolubility of this catalyst in many solvents, it was not possible to obtain a good ^1H NMR spectrum.

(e) Bis(2-(di-ethylphosphino)ethyl)amine with chlorobis(cyclooctene) iridium(I) dimer



The compound is prepared in a similar fashion as the cyclohexyl analogue to obtain a red color solid. Yield: 0.3 g, 31%. ^1H NMR (400 MHz, C_6D_6): δ 3.15 (b, 4 H, CH_2), 1.47 (b, 4H, CH_2), 1.30 (b, 8H, ethyl- CH_2), 0.80 (b, 12H, ethyl- CH_3). $^{31}\text{P}\{^1\text{H}\}$ NMR (162 MHz, C_6D_6): δ 42.5 (d, $^2J_{\text{PP}} = 368$ Hz); 34.9 (d, $^2J_{\text{PP}} = 368$ Hz). 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a red solution. The material was tested for ammonia borane hydrolysis.

The reaction of $(\text{R}_2\text{PCH}_2\text{CH}_2)_2\text{NH}$ (R = tertiarybutyl, adamantyl, isopropyl, cyclohexyl, ethyl) with chlorobis(cyclooctene)iridium(I) dimer readily affords 'PNP' iridium complexes. For R = tertiarybutyl, the complex bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocyclooct-1-enyldihydrido-iridium(III)

is obtained in high yield and purity. The ^1H NMR spectrum suggests the presence of a cyclooctenyl group in addition to a hydride resonance (δ - 25.46). The $^{31}\text{P}\{^1\text{H}\}$ NMR spectrum of the complex shows a chemical shift at δ 31.6. A single crystal of bis(2-(di-*tert*-butylphosphino)ethyl)-aminechlorocyclooct-1-enylidihydrido-iridium(III) was obtained and the X-ray structure (as seen in Figure 4) confirms the formulation of the complex. The structure consists of a pseudooctahedral ligand arrangement with the PNP group bound in a meridional orientation. The metal-bound chloride ligand is syn to the NH moiety and this may be due to a weak interaction between these two groups. The cyclooctenyl group is bound trans to the amine nitrogen and cis to the hydride ligand.


For $\text{R} = \text{isopropyl}$, cyclohexyl, and adamantyl, the complexes $\text{IrCl}(\text{H})_2\{\text{N}(\text{H})(\text{CH}_2\text{CH}_2\text{PR}_2)_2\}$ were obtained. The ^1H NMR spectra of these materials indicate that no cyclooctenyl group is present. For $\text{R} = \text{isopropyl}$, the ^1H NMR spectrum shows the presence of two hydride ligands with resonances at δ -25.13 and -19.83. The compound was characterized crystallographically previously (Clarke, Z. E.; Maragh, P. T.; Dasgupta, T. P.; Gusev, D. G.; Lough, A. J.; Abdur-Rashid, K. *Organometallics* **2006**, *25*, 4113) and the X-ray structure confirmed the formulation. For $\text{R} = \text{cyclohexyl}$, a single crystal of the complex was obtained from dichloromethane. The X-ray structure showed that the putative dihydride species was transformed to a dichloro hydride complex. The ORTEP depiction of the compound is shown in Figure 5.

For $\text{R} = \text{adamantyl}$, the low solubility of the compound precluded analysis via NMR but the compound is anticipated to have a structure comparable to the isopropyl analogue.

For $\text{R} = \text{ethyl}$, a material is formed that has two doublets in the $^{31}\text{P}\{^1\text{H}\}$ NMR spectrum at δ 41.0 and 34.9 ($J = 368$ Hz).

Example 20


Bis(2-(diphenylphosphino)ethyl)ammonium chloride with chlorobis(cyclooctene)iridium(I) dimer



A 170 mg (1.515 mmol) portion of potassium tertiary butoxide was added to 665 mg (1.394 mmol) of bis(2-(diphenylphosphino)ethyl)ammonium chloride in 10 ml of tetrahydrofuran and the mixture was stirred for 15 minutes. The solvent was removed and the residue was extracted with 3×5 ml of toluene. The solution was filtered through Celite and then the solvent was removed in vacuo. 10 ml of degassed isopropanol and 550 mg (0.614 mmol) of chlorobis(cyclooctene)iridium(I) dimer $[\text{IrCl}(\text{COE})_2]_2$ was added and then the mixture was refluxed for 15 minutes. The solvent volume was reduced to ca. 5 ml and then 20 ml of diethyl ether was added. The brown solid was collected on a frit and dried in vacuo (yield 550 mg). NMR spectroscopy indicated that a mixture had formed. The material was tested for ammonia borane hydrolysis.

Example 21


(a) *bis(2-(ditertiarybutylphosphino)ethyl)methylaminechloro cyclo-octenyl-hydrido-iridium(III)*



A 230 mg (0.257 mmol) sample of chlorobis(cyclooctene)iridium(I) dimer $[\text{IrCl}(\text{COE})_2]_2$ was added to 210 mg (0.559 mmol) of bis(2-(ditertiarybutylphosphino)ethyl)methylamine in ca. 3 ml of toluene. The mixture was stirred for 45 minutes and then 10 ml of hexanes was added dropwise and the precipitate was collected by vacuum filtration and dried in vacuo. ^1H NMR (400 Mhz, C_6D_6): δ 5.32 (d, $^3J_{\text{HH}} = 8.0$ Hz, =CH); 2.76 (m, 2H,


CH₂); 2.05 (s, 3H, NCH₃); 1.27-1.96 (m, 16H, CH₂); 1.22 (m, 18H, C(CH₃)₃); 0.95 (m, 18H, C(CH₃)₃); -23.06 (t, ²J_{PH} = 16.0 Hz, Ir-H). ³¹P NMR (161.2 Mhz, C₆D₆): δ 23.1.

(b) *Bis(2-(ditertiarybutylphosphino)ethyl)methylaminechloro-hydridophenyl-iridium(III)*




Upon standing for several days, a solution of the pure compound bis(2-(ditertiarybutylphosphino)ethyl)methylaminechlorocyclooctenylhydrido-iridium(I) (from procedure Example 21(a) above) in benzene deposited X-ray quality crystals. The NMR data were not obtained and the yield has not been determined.

(c) *Bis(2-(diisopropylphosphino)ethyl)methylaminechlorodihydrido-iridium(III)*



A mixture of chloro bis(cyclooctene)iridium(I) dimer [Ir(COE)₂Cl]₂ (0.28 g, 0.31 mmol) and bis(2-(diisopropylphosphino)ethyl)methylamine (0.20 g, 0.63 mmol) was dissolved in toluene (5 ml) and stirred for 4 hours at room temperature. The solvent was then evaporated and hexanes (20 ml) was added and then the precipitated pale orange solid was collected by filtration and dried in vacuo. Yield: 0.30 g, 87 %. ¹H NMR (400 MHz, C₆D₆): δ 3.95, 3.50, 1.59, 0.70 – 1.30. ³¹P{¹H} NMR (162 MHz, C₆D₆): δ 21.9. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a red solution. Ammonia borane was added (50 mg, 1.620 mmol) and the hydrolysis rate is very good and is comparable to bis(2-(diisopropylphosphino)-ethyl)aminechlorodihydrido-iridium(III) (from procedure in Example 21(a)).

The ligand system, $N(CH_3)(CH_2CH_2PR_2)_2$ (R = isopropyl, tertiarybutyl, adamantyl, phenyl), was also used to prepare iridium PNP complexes. The reaction of bis(2-(di-*tert*-butylphosphino)ethyl)methylamine with chlorobis(cyclooctene)iridium(I) dimer results in clean formation of the new complex bis(2-(di-*tert*-butylphosphino)ethyl)methylaminechlorocyclooctenyl-hydrido-
 5 iridium(I). The ^{31}P NMR spectrum of the complex has a resonance appearing at δ 23.1. The 1H NMR spectrum of the complex clearly shows the presence of a cyclooctenyl ligand in addition to a hydride resonance at δ -23.06 and based upon this evidence we propose the structure shown in the
 10 scheme below.




In benzene solution the compound transforms slowly to the new complex bis(2-(di-*tert*-butylphosphino)ethyl)methylaminechlorohydridophenyl-
 15 iridium(III). The reaction likely proceeds via reductive elimination of cyclooctene to form a putative four-coordinate bis(2-(di-*tert*-butylphosphino)-ethyl)methylaminechloroiridium(I) complex which then activates a C-H moiety of the benzene solvent to form the product.

A single crystal of bis(2-(di-*tert*-butylphosphino)ethyl)methylaminechlorohydridophenyliridium(III) was obtained and the ORTEP diagram is
 20 shown in Figure 6. The PNP ligand is bound in a meridional mode and the geometry about iridium is pseudooctahedral. The phenyl group is trans to the aminophosphine nitrogen atom.

The reaction of bis(2-(diisopropylphosphino)ethyl)methylamine with chlorobis(cyclooctene)iridium(I) dimer yielded a mixture of products were used
 25 in situ.


Example 22

(a) Bis(2-(diisopropylphosphino)ethyl)aminedichlororuthenium(II) dimer



A 300 mg (0.982 mmol) sample of bis(2-(diisopropylphosphino)ethyl)amine $[\text{HN}(\text{CH}_2\text{CH}_2\text{P}^i\text{Pr}_2)_2]$ and 246 mg (0.492 mmol) of benzenedichlororuthenium(II) dimer $[\text{Ru}(\eta^6\text{-C}_6\text{H}_6)\text{Cl}_2]_2$ were refluxed in 20 ml of tetrahydrofuran overnight, resulting in the formation of a brown suspension. The solvent was removed in vacuo and the residue was triturated with 25 ml of diethyl ether. The solid was collected on a frit, washed with 5 ml of ether and then dried in vacuo. X-ray quality crystals were obtained by diffusion of diethyl ether into a dichloromethane solution of the compound. Yield 330 mg, 66 %. ^1H NMR (400 MHz, CD_2Cl_2): δ 6.17 (2H); 3.01 (4H); 2.74 (4H); 2.48 (4H); 1.91 (4H); 1.10-1.46 (24H). ^{31}P NMR (162 MHz, CD_2Cl_2): δ 73.5. A solution of the compound in a 1:1 mixture of tetrahydrofuran and water exhibited a good activity towards ammonia borane hydrolysis.


(b) Bis(2-(dicyclohexylphosphino)ethyl)amine with benzenedichlororuthenium(II) dimer



A 220 mg (0.608 mmol) portion of bis(2-(dicyclohexylphosphino)ethyl)amine $\text{HN}(\text{CH}_2\text{CH}_2\text{PCy}_2)_2$ was added to 150 mg (0.245 mmol) of benzenedichlororuthenium(II) dimer $[\text{RuCl}_2(\eta^6\text{-benzene})]_2$ in 10 ml of tetrahydrofuran. The mixture was refluxed for 2.5 hours and then the solvent was removed in vacuo. The residue was triturated in 5 ml of hexanes and then collected on a frit and dried in vacuo. Yield 250 mg. NMR

spectroscopy indicated that a mixture had formed. The material was tested for ammonia borane hydrolysis.

(c) Reaction of bis(2-(ditertiarybutylphosphino)ethyl)amine with benzene-dichlororuthenium(II) dimer




A 181 mg (0.500 mmol) portion of bis(2-(ditertiarybutylphosphino)ethyl)amine $\text{HN}(\text{CH}_2\text{CH}_2\text{P}^t\text{Bu}_2)_2$ in 2 ml of tetrahydrofuran was added to 150 mg (0.245 mmol) of benzenedichlororuthenium(II) dimer $[\text{RuCl}_2(\eta^6\text{-benzene})]_2$ in 10 ml of tetrahydrofuran. The mixture was refluxed for 2.5 hours and then the solvent was removed in vacuo. The residue was triturated in 5 ml of hexanes, collected on a frit and dried in vacuo. Yield 200 mg. NMR spectroscopy indicated that a mixture had formed. The material was tested for ammonia borane hydrolysis.

Ruthenium PNP complexes were prepared by two methods. The reaction of bis(2-(diisopropylphosphino)ethyl)amine with dichloro benzene ruthenium dimer afforded a single compound that has a ^{31}P NMR resonance at δ 73.5. The ^1H NMR spectrum of the new material displays the expected isopropyl, methylene and NH signals. A single crystal was obtained and the X-ray structure was determined (as seen in Figure 7). The structure indicates that a dimeric complex was formed where the bis(2-(diisopropylphosphino)-ethyl)amine is bound facially to the ruthenium center. The metals are bridged by two chloride ligands and the terminal chloride is involved in a weak hydrogen bonding interaction with the NH moiety on the opposite metal center.


Example 23

(a) *Bis(2-(diisopropylphosphino)ethyl)aminedichlorotriphenylphosphine-ruthenium(II)*



A 200 mg (0.655 mmol) portion of (2-
 5 (diisopropylphosphino)ethyl)amine $\text{HN}(\text{CH}_2\text{CH}_2\text{P}^i\text{Pr}_2)_2$ in 1 ml of tetrahydrofuran was added to a suspension of 620 mg (0.647 mmol) of dichlorotris(triphenylphosphine)ruthenium(II) in 5 ml of tetrahydrofuran and the mixture was stirred for two hours. The solvent was removed in vacuo and then 2 ml of tetrahydrofuran was added, followed by the dropwise addition of
 10 20 ml of hexanes. The mixture was stirred for 30 minutes and the solid was isolated by vacuum filtration. Yield 300 mg, 63 %. ^1H NMR (400 MHz, CD_2Cl_2): δ 6.40-7.07 (m, 15H, $\text{P}(\text{C}_6\text{H}_5)_3$); 3.42 (broad s, 1H, NH); 2.26 (m, 4H, CH_2); 1.74 (m, 4H, CH_2); 2.33 (m, 2H, $\text{CH}(\text{CH}_3)_2$); 1.84 (m, 2H, $\text{CH}(\text{CH}_3)_2$); 0.40 (m, 12H, $\text{CH}(\text{CH}_3)_2$); 0.16 (m, 6H, $\text{CH}(\text{CH}_3)_2$); 0.02 (m, 6H, $\text{CH}(\text{CH}_3)_2$).
 15 ^{31}P NMR (162 MHz, CD_2Cl_2): δ 39.5 (t, $^2J_{\text{PP}} = 27.5$ Hz); 27.5 (d, $^2J_{\text{PP}} = 27.5$ Hz). The compound exhibited a good activity towards ammonia borane hydrolysis.

(b) *Bis(2-(ditertiarybutylphosphino)ethyl)aminewithdichlorotris(triphenylphosphine)ruthenium(II)*




20

A 235 mg (0.650 mmol) sample of bis(2-(ditertiarybutylphosphino)ethyl)amine in 0.5 ml of tetrahydrofuran was added to 0.600 g (0.626 mmol) of dichlorotris(triphenylphosphine)ruthenium(II) in 5 ml of tetrahydrofuran. After stirring for one hour the solvent was removed in

vacuo and then 5 ml of toluene was added. The mixture was stirred overnight and then the solid product was collected by vacuum filtration, washed with 5 ml of diethyl ether and dried in vacuo. NMR spectroscopy indicated that a mixture had formed.

- 5 (c) 2-(diphenylphosphino)-N-(2-(diphenylphosphino)ethyl)-N-methylethanamine with dichlorotris(triphenylphosphine)ruthenium(II)




- A 0.648 molar toluene solution (0.98 ml, 0.635 mmol) of a of 2-(diphenylphosphino)-N-(2-(diphenylphosphino)ethyl)-N-methylethanamine
 10 was added to 0.600 g (0.626 mmol) of dichlorotris(triphenylphosphine)ruthenium(II) $[\text{RuCl}_2(\text{PPh}_3)_3]$ in 5 ml of tetrahydrofuran and the mixture was stirred for two hours. The solvent was removed in vacuo and then 3 ml of tetrahydrofuran was added, followed by 15 ml of diethyl ether. After stirring for 30 minutes the solid was collected by
 15 vacuum filtration and dried in vacuo. NMR spectroscopy indicated that a mixture had formed.

- A related type of ruthenium PNP complex was obtained by the reaction of bis(2-(diisopropylphosphino)ethyl)amine with dichlorotris(triphenylphosphine) ruthenium(II). The ^{31}P NMR spectrum of the complex
 20 displays a triplet at δ 39.5 and a doublet at 27.5 ppm ($^2J_{\text{PP}} = 27.5$ Hz). The triplet corresponds to the triphenylphosphine ligand whereas the doublet indicates the presence of the of bis(2-(diisopropylphosphino)ethyl)amine ligand. The ^1H NMR spectrum of the complex shows that the triphenylphosphine and of bis(2-(diisopropylphosphino)ethyl)amine ligands
 25 are present in a 1:1 ratio. The trans orientation of the chloride ligands is proposed since the cis arrangement would cause unfavorable steric interactions between the triphenylphosphine ligand and the backbone of the bis(2-(diisopropylphosphino)ethyl)amine ligand. Analogous compounds have been prepared by the reactions of bis(2-(ditertiarybutyl)ethyl)amine or 2-

(diphenylphosphino)-N-(2-(diphenylphosphino)ethyl)-N-methylethanamine with dichlorotris(triphenylphosphine)ruthenium(II) and these displayed similar NMR properties.

5 Example 24

Bis(2-(ditertiarybutylphosphino)ethyl)amine-2,4-pentanedionate rhodium(I)




A solution of 135 mg (0.373 mmol) of bis(2-(ditertiarybutylphosphino)ethyl)amine in 1 ml of tetrahydrofuran was added to a solution of 106 mg (0.342 mmol) of 1,5-cyclooctadiene-2,4-pentanedionate rhodium(I) in 5 ml of tetrahydrofuran. The mixture was heated to reflux for ten minutes and then the solvent was removed in vacuo. ³¹P NMR (162 MHz, C₆D₆): δ 63.6 (d, ¹J = 161 Hz). ¹H NMR spectroscopy indicated that a mixture had formed.

A rhodium PNP complex was prepared by the reaction of bis(2-(ditertiarybutylphosphino)ethyl)amine with cyclooctadiene(2,4-pentanedionate)rhodium(I). The ³¹P NMR spectrum of the product showed a doublet at δ 63.6 (¹J_{RhP} = 161 Hz). Although the ³¹P NMR spectrum showed mostly one resonance, ¹H NMR spectrum of the material indicated that the other species were present.

Example 25


Bis(2-(diisopropylphosphino)ethyl)amine with dichlorocyclooctadienepalladium(II)



A 103 mg (0.337 mmol) sample of bis(2-(diisopropylphosphino)ethyl)amine [HN(CH₂CH₂PⁱPr₂)₂] was added to 96 mg (0.336 mmol) of dichloro-1,5-cyclooctadienepalladium(II) [Pd(COD)Cl₂] in 10 ml of tetrahydrofuran. 94 μ l (1.28 mmol) of triethylamine was added and then the mixture was refluxed for 30 minutes. NMR spectroscopy indicated that a mixture had formed. ³¹P{¹H} NMR (162 MHz, tetrahydrofuran -H₈): δ 65.6 (ca. 15 %); 45.7 (ca. 35 %); 45.1 (50 %). The material was used without further purification for ammonia borane hydrolysis experiments.

10 Example 26

Bis(2-(diisopropylphosphino)ethyl)amine with octacarbonyldicobalt(0)




In a typical experiment, to a solution of bis(2-(diisopropylphosphino)ethyl)amine (0.20 g, 0.65 mmol) in tetrahydrofuran (20 ml) was added octacarbonyldicobalt(0) (0.22 g, 0.65 mmol). The reaction mixture was then stirred at room temperature overnight. Evolution of bubbles was observed during the reaction. The solvent was then evaporated, and the residue was precipitated by the addition of hexanes. The orange precipitate was then filtered and washed with hexanes under argon to obtain an orange solid. Yield: 0.24 g, 87%. ³¹P{¹H} NMR (400 MHz, C₆D₆): δ 96.97, 74.32. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a yellow solution. Ammonia borane was added (50 mg, 1.620 mmol) and the hydrolysis rate is very good with metal deposited after ca. 30 minutes.

25 The reaction of bis(2-(diisopropylphosphino)ethyl)amine with octacarbonyldicobalt(0) afforded a mixture which displayed two resonances in the ³¹P NMR spectrum. Separation of the compounds was not achieved.

Example 30


Bis(2-(diisopropylphosphino)ethyl)amine with cobalt(II) tetrafluoroborate hydrate



The reaction was carried out analogously to 26 above. Yield: 0.42g, 58%. Black solid was deposited after a few minutes of hydrolysis of ammonia borane.

Example 28

Bis(2-(diisopropylphosphino)ethyl)amine with molybdenum(III) chloride




10

A 202 mg (0.661 mmol) sample of bis(2-(diisopropylphosphino)ethyl)amine $[\text{HN}(\text{CH}_2\text{CH}_2\text{P}^i\text{Pr}_2)_2]$ in 2 ml of tetrahydrofuran was added to 125 mg (0.618 mmol) of molybdenum(III) chloride. The mixture was stirred overnight and then the solvent was removed in vacuo. The brown solid was triturated in hexanes (5 ml); the hexanes was decanted and the solid was dried in vacuo to give 280 mg of a brown solid. NMR spectra were not obtained. The material was tested for ammonia borane hydrolysis.

20 Example 29

Bis(2-(diisopropylphosphino)ethyl)amine with of iron(II) tetrafluoroborate hydrate




A 220 mg (0.720 mmol) portion of bis(2-(diisopropylphosphino)ethyl)amine was added dropwise to a solution of 220 mg (0.652 mmol) of iron(II) tetrafluoroborate hydrate in 5 ml of acetonitrile.

- 5 The mixture was stirred for 30 minutes and then 20 ml of diethyl ether was added dropwise and the resulting solid was vacuum filtered and dried in vacuo. Yield 370 mg. NMR spectroscopy indicated that a mixture had formed. The material was tested for ammonia borane hydrolysis.

10 Example 30


Bis(2-(diphenylphosphino)ethyl)ammonium chloride with nickel(II) bromide



To a tetrahydrofuran (20 ml) solution of bis(2-(diphenylphosphino)-ethyl)ammonium chloride $[\text{HN}(\text{CH}_2\text{CH}_2\text{PPh}_2)\cdot\text{HCl}]$ (0.25 g, 0.558 mmol) and
 15 nickel(II) bromide (0.12 g, 0.558 mmol) was added dropwise 2 equivalents triethylamine (0.112 g, 1.12 mmol). The reaction mixture was then allowed to reflux overnight. The solvent was then evaporated and hexane was added to precipitate the product. The orange solid was then washed with isopropanol (5 ml). Yield: 0.25g (81.5%). ^1H NMR (300 MHz, CD_2Cl_2): δ 8.10 – 7.23 (br, 10
 20 H, Ph), 3.60 (s, 1H, NH), 2.97 – 2.12 (m, 4H, NCH_2CH_2), 1.30 – 0.77 (m, 4H, NCH_2CH_2). $^{31}\text{P}\{^1\text{H}\}$ NMR (300 MHz, CD_2Cl_2): δ 32.0 (ca. 40 %), 28.0 (ca. 40 %), -20.2 (ca. 20 %).


Example 31

- 25 (a) *Bis(2-(diisopropylphosphino)ethyl)amine with copper(I) chloride*



A 0.500 g (1.637 mmol) portion of bis(2-(diisopropylphosphino)ethyl)amine $[\text{HN}(\text{CH}_2\text{CH}_2\text{P}^i\text{Pr}_2)_2]$ in 2 ml of tetrahydrofuran was added to 0.160 g (1.616 mmol) of copper (I) chloride in 20 ml of tetrahydrofuran and the mixture was refluxed overnight. The solvent was removed in vacuo to afford a colorless crystalline solid. Yield 490 mg (90 %). The material was tested for ammonia borane hydrolysis.

(b) *Bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocopper(I)*.




A 0.500 g (1.384 mmol) portion of bis(2-(ditertiarybutylphosphino)ethyl)amine $[\text{HN}(\text{CH}_2\text{CH}_2\text{P}^t\text{Bu}_2)_2]$ in 2 ml of tetrahydrofuran was added to 134 mg (1.353 mmol) of copper(I)chloride in 20 ml of tetrahydrofuran and the mixture was heated to reflux overnight and then the solvent was removed in vacuo. The solid was washed briefly with ca. 2 ml of hexanes and was then in vacuo to afford a solid product. Yield 455 mg (73 %). ^1H NMR (300 MHz, CD_2Cl_2): δ 2.86 (m); 1.75 (m); 1.24 (m). ^{31}P NMR (121 MHz, CD_2Cl_2): δ 17.5. The material was tested for ammonia borane hydrolysis.

Copper complexes containing $\text{N}(\text{H})(\text{CH}_2\text{CH}_2\text{PR}_2)_2$ (R = isopropyl, tertiarybutyl) ligands were readily prepared by the reaction of copper chloride with a slight excess of the ligand. The ^{31}P NMR spectrum of bis(2-(ditertiarybutylphosphino)ethyl)amine chloro copper (I) displays a resonance at δ 17.5 and the ^1H NMR spectrum of the complex shows the expected resonances. A single crystal of the complex bis(2-(diisopropylphosphino)ethyl)amine chloro copper (I) was obtained and the X-

ray structure was determined (as seen in Figure 8). The structure features a distorted tetrahedral ligand arrangement about the copper.


Example 32

5 a) Synthesis of trichlorooxobis(triphenylphosphine)rhenium(V)



An aqueous solution of perrhenic acid (HReO_4) (5.0 g, 65-70 wt %, 3.25-3.50 mmol) was evaporated to a syrupy consistency, to which
 10 concentrated aqueous hydrochloric acid (7.0 ml) was added. The solution was then added to a suspension of triphenylphosphine (21.67 g, 8.26 mmol) in 250 ml of glacial acetic acid in a 500 ml round bottomed flask with a stirrer. The solution was stirred for 30 minutes, and the solid was removed by filtration and washed with glacial acetic acid (2×50 ml) and then with diethyl
 15 ether (6×50 ml). Yield: 12.9 g (90%) as a microcrystalline product. $^{31}\text{P}\{^1\text{H}\}$ NMR (162 MHz, C_6D_6): δ -17.9.

(b) Trichlorooxobis(triphenylphosphine)rhenium(V) with bis(2-(ditertiarybutylphosphino)ethyl)amine.



20 Trichlorooxybis(triphenylphosphine)rhenium(V) ($\text{ReOCl}_3(\text{Ph}_3\text{P})_2$) (0.25 g, 0.3 mmol) and bis(2-(ditertiarybutylphosphino)ethyl)amine (0.11 g, 0.3 mmol) were mixed in tetrahydrofuran (25 ml). After stirring for 5 minutes, the solid dissolved to form a brown solution. The solution was then allowed to reflux for 2 hours. The solvent was then pumped off and the solid was washed
 25 with diethyl ether. The solid was then dried under vacuum to obtain a pale brown solid. Yield: 0.137 g (74%). ^1H NMR (C_6D_6), δ : 6.90 (br, 1H, NH), 3.00 (m, 2H, CH_2), 2.15 (m, 2H, CH_2), 1.20 (vt, 18H, CH_3), 1.11 (vt, 18H, CH_3). $^{31}\text{P}\{^1\text{H}\}$ NMR (C_6D_6), δ : 20.6. 10 ml of water and 10 ml of tetrahydrofuran was added to 10 mg of the material in a scintillation vial to form a brown solution.
 30 The material was tested for ammonia borane hydrolysis.


Reactions of aminodiphosphine ligands with various other transition metal sources such as molybdenum(III) chloride, iron(II) tetrafluoroborate

hexahydrate, trichlorooxybis(triphenylphosphine)rhenium(V), dichloro(1,5-cyclooctadiene)palladium(II), or nickel (II)bromide were attempted. These reactions formed mixtures from which single compounds were not isolated but the in situ prepared complexes were used as catalysts.

5

Example 33


(a) Reaction of 2,6-bis((diisopropylphosphino)methyl)pyridine with cobalt(II) chloride



10 To a solution of 2,6-bis((diisopropylphosphino)methyl)pyridine (0.20 g, 0.58 mmol) in tetrahydrofuran (30 ml) was added cobalt(II) chloride (CoCl_2) (0.08 g, 0.58 mmol). The reaction mixture was then stirred at room temperature for 2 hours and then refluxed for 2 hours. The solvent was then evaporated, and the residue was precipitated by the addition of hexanes. The
15 precipitate was filtered and then washed with hexanes to obtain a blue solid. Yield: 0.16 g. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a pink solution. The material was tested for ammonia borane hydrolysis.

The reaction of 2,6-bis((diisopropylphosphino)methyl)pyridine with
20 cobalt(II)chloride proceeded smoothly to afford the paramagnetic blue complex 2,6-bis((diisopropylphosphino)methyl)pyridinedichlorocobalt(II).

(b) 2,6-bis((diisopropylphosphino)methyl)pyridine with chlorobis(cyclooctene)-iridium(I) dimer




25 To a solution of 2,6-bis((diisopropylphosphino)methyl)pyridine (0.20 g, 0.58 mmol) in tetrahydrofuran (30 ml) was added chlorobis(cyclooctene)iridium(I) dimer $[\text{Ir}(\text{COE})_2\text{Cl}]_2$ (0.26 g, 0.29 mmol). The reaction mixture was then stirred at room temperature for 2 hours until all of the solid dissolved. The solvent was then evaporated, and the residue was

precipitated by the addition of hexanes. The precipitate was filtered and then washed with hexanes to obtain a pale yellow solid. $^{31}\text{P}\{^1\text{H}\}$ NMR (162 MHz, C_6D_6): δ 12.1. Yield: 0.114 g. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a red solution.

- 5 Ammonia borane was added (50 mg, 1.620 mmol) and the hydrolysis rate was moderate.

Attempts to prepare iridium or rhenium complexes containing the ligand 2,6-bis((di-iso-propylphosphino)methyl)pyridine. It was found that mixtures were formed that were used in situ.

- 10 (c) 2,6-bis((diisopropylphosphino)methyl)pyridine with benzene-dichlororuthenium(II) dimer




- To a solution of 2,6-bis((diisopropylphosphino)methyl)pyridine (0.20 g, 0.58 mmol) in tetrahydrofuran (30 ml) was added
 15 benzenedichlororuthenium(II) dimer $[\text{RuCl}_2(\eta^6\text{-C}_6\text{H}_6)]_2$ (0.15 g, 0.29 mmol). The reaction mixture was then stirred at room temperature and then refluxed for 5 hours. The insoluble solid was then filtered off. The solvent was then evaporated, and the residue was precipitated by the addition of hexanes. The precipitate was filtered and then washed with hexanes to obtain a pale brown
 20 solid. ^1H NMR (400 MHz, C_6D_6): δ 7.47 (m, 1H, Ar-H), 7.22 (m, 2H, Ar-H), 3.90 (b, 2H, CH_2), 2.60 (b, 2H, CH_2), 0.80 – 1.40 (b, 28H, $-\text{CH}(\text{CH}_3)_2$). $^{31}\text{P}\{^1\text{H}\}$ NMR (162 MHz, C_6D_6): δ 43.2. Yield: 0.1 g. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a red solution. Ammonia borane was added (50 mg, 1.620 mmol) and
 25 the hydrolysis rate was moderate.

- When 2,6-bis((diisopropylphosphino)methyl)pyridine was reacted with dichloro benzene ruthenium dimer, a single compound could be isolated that displayed a single ^{31}P NMR resonance at 43.2 ppm. The ^1H NMR spectrum of the complex showed only resonances due to the metal bound 2,6-
 30 bis((diisopropylphosphino)methyl)pyridine ligand. Although the material was not characterized via X-ray crystallography, the compound 2,6-

bis((diisopropylphosphino)methyl)(pyridine)-dichlororuthenium(II) indicated in the scheme above was most likely formed.

Example 34

- 5 *N,N'*-(phenylphosphinediyl)bis(methylene)dipropylamine with cobalt(II) chloride




- 10 A 45 mg (0.347 mmol) sample of cobalt(II) chloride and 100 mg (0.396 mmol) of *N,N'*-(phenylphosphinediyl)bis(methylene)dipropylamine $\text{PhP}(\text{CH}_2\text{NH}^i\text{Pr})_2$ were mixed in 20 ml of tetrahydrofuran. The solution was heated to reflux for five minutes and the solvent was removed in vacuo. The residue was extracted into diethyl ether, filtered through Celite and then the solvent was removed in vacuo to give a green oil. The material was tested for ammonia borane hydrolysis.

15

Example 35

Bis(di-m-isopropylphosphino-di-p-tolyl)amine with *chlorobis(cyclo-octene)iridium(I) dimer*




- 20 *Bis(di-m-isopropylphosphino-di-p-tolyl)amine* (0.2 g, 0.46 mmol) and *chlorobis(cyclooctene)iridium(I) dimer* $[\text{Ir}(\text{COE})_2\text{Cl}]_2$ (0.2 g, 0.23 mmol) and toluene (10 ml) were placed into a schlenk flask. The solution was stirred overnight at room temperature and then the volatiles were removed in vacuo. Hexanes was added and then the orange solid was then filtered off and the green filtrate was evaporated to dryness to obtain a dark green solid (0.23 g, 75%). ^1H NMR (400 MHz, C_6D_6): δ 8.28 (t, 1H, $J_{\text{P-H}} = 8$ H, NH), 7.66 (dd, 1H, PhH), 6.98 (d, 1H, PhH), 6.50 (dd, 1H, PhH), 2.18 (d, 6H, PhCH_3), 1.75 (m,
- 25

4H, CHCH₃), 1.15 (b, 24H, CHCH₃), -27.00 (t, 1H, IrH). ³¹P{¹H} NMR (162 MHz, C₆D₆): δ 25.0. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a red solution. Ammonia borane was added (50 mg, 1.620 mmol) and the hydrolysis rate
 5 was good and comparable to that of the complex bis(2-(diisopropylphosphino)ethyl)aminechlorodihydrido-iridium(III).

The bis(di-*m*-isopropylphosphino-di-*p*-tolyl)amine ligand should be much more difficult to activate because of the 'phenylene' backbone and thus complexes of bis(di-*m*-isopropylphosphino-di-*p*-tolyl)amine should be more
 10 stable. The reaction of bis(di-*m*-isopropylphosphino-di-*p*-tolyl)amine with chlorobis(cyclooctene)iridium(I) dimer proceeds relatively cleanly and affords a product which displays a ³¹P NMR resonance at δ 25.0. The ¹H NMR spectrum displays the signals expected from the metal-bound ligand in addition to a hydride resonance at δ -27.00. Although the complex has not
 15 been characterized crystallographically we propose the tentative structure shown in scheme above.

Example 36

Bis(di-m-isopropylphosphino-di-p-tolyl)aminedichlororuthenium(II)




This compound was prepared according to the literature procedure (Celenligil-Cetin, R.; Watson, L. A.; Guo, C.; Foxman, B. M.; Ozerov, O. V. *Organometallics*, **2005**, 24, 186 – 189). Yield: 0.23 g, 66%. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a
 25 scintillation vial to form a red solution. Ammonia borane was added (50 mg, 1.620 mmol) and the hydrolysis rate was moderate.

The reaction of bis(di-*m*-isopropylphosphino-di-*p*-tolyl)amine with dichloro(1,5-cyclooctadiene)ruthenium(II) polymer cleanly produces the

previously reported polymeric complex bis(di-*m*-isopropylphosphino-di-*p*-tolyl)aminedichlororuthenium(II).

Example 37

5 *Bis(di-m-isopropylphosphino-di-p-tolyl)aminedichlorocobalt(II)*



A mixture of cobalt(II) chloride (CoCl_2) (0.03 g, 0.23 mmol) and di-*m*-isopropylphosphino-di-*p*-tolylamine (0.10 g, 0.23 mmol) in tetrahydrofuran (50 ml) was stirred under argon at 50°C for 3 hours. After cooling, the solvent was
 10 evaporated off and the solid was precipitated with hexanes to afford a dark purple solid. Yield: 0.1 g, 77%. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a red solution. The material was tested for ammonia borane hydrolysis.


A base metal complex of di-*m*-isopropylphosphino-di-*p*-tolylamine was
 15 prepared by heating a slight excess of bis(di-*m*-isopropylphosphino-di-*p*-tolyl)amine with cobalt(II) chloride to 50 °C. The reaction affords the dark purple paramagnetic complex bis(di-*m*-isopropylphosphino-di-*p*-tolyl)amine(dichloro)cobalt(II). The structure is expected to be analogous to that of bis(2-(diisopropylphosphino)ethyl)aminedichlorocobalt(II).

20

Metal Complexes with (-P-N-N-) Ligands

Example 38

(a) (Diadamantylphosphino)ethyl-(diethylamino)ethyl amine with chlorobis(cyclooctene)iridium(I) dimer




25

To a solution of (diadamantylphosphino)ethyl(diethylamino)ethyl amine (0.05 g, 0.12 mmol) in toluene (20 ml) was added chlorobis(cyclooctene)iridium(I) dimer $[\text{Ir}(\text{COE})_2\text{Cl}]_2$ (0.05 g, 0.06 mmol). The reaction mixture was then stirred at room temperature overnight. The solvent was then evaporated, and the residue was precipitated by the addition of hexanes. The pale brown precipitate was filtered and then washed with hexanes to obtain a yellow solid. Yield: 0.07 g, 92%. $^{31}\text{P}\{^1\text{H}\}$ NMR (162 MHz, C_6D_6): δ 63.7. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a brown solution. Ammonia borane was added (50 mg, 1.620 mmol) and the hydrolysis rate was moderate.

The reaction of (di-adamantylphosphino)ethyl(diethylamino)ethyl amine with chlorobis(cyclooctene)iridium(I) dimer afforded a poorly soluble brown material of questionable purity. A single peak was observed in the ^{31}P NMR spectrum of the material at 63.7 ppm. Although a clean ^1H NMR spectrum was not obtained we propose the tentative structure shown in the scheme above.

(b) (Diadamantylphosphino)ethyl (diethylamino)ethylamine with cobalt(II) chloride



The cobalt complexes were prepared analogously *in situ* and the reaction mixture was refluxed for 1 hour in tetrahydrofuran under reflux. Yield: 0.2g, 78%. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a pink solution. The material was tested for ammonia borane hydrolysis.


A cobalt complex of (di-adamantylphosphino)ethyl(diethylamino)ethyl amine was readily obtained by reaction with cobalt(II)chloride as depicted in the scheme above. The complex was not characterized owing to its paramagnetic nature.

Metal Complexes with (-P-O-P-) Ligands

Example 39

(a) 2,2'-oxybis(ethane-1,2-diyl)bis(di-iso-propylphosphine) dichloro cobalt

$R = {}^iPr$



5

A solution of 150 mg (0.490 mmol) of 2,2'-oxybis(ethane-1,2-diyl)bis(di-iso-propylphosphine) $O(CH_2CH_2P^iPr_2)_2$ in 5 ml of tetrahydrofuran was added to a suspension of 34 mg (0.262 mmol) of cobalt dichloride in 5 ml of tetrahydrofuran. The mixture was refluxed for 30 minutes and the solvent was then removed in vacuo. The solid was triturated in 5 ml of hexanes and was then collected on a frit and dried in vacuo. Yield: 70 mg, 50 %.

10

(b) 2,2'-oxybis(ethane-1,2-diyl)bis(di-tert-butylphosphine) cobalt dichloride

$R = {}^tBu$


A solution of 110 mg (0.303 mmol) of 2,2'-oxybis(ethane-1,2-diyl)bis(di-tert-butylphosphine) $O(CH_2CH_2P^tBu_2)_2$ in 5 ml of tetrahydrofuran was added to a mixture of 32 mg (0.246 mmol) of cobalt dichloride and 5 ml of tetrahydrofuran. The mixture was refluxed for 30 minutes and then the solvent was removed in vacuo. The solid was triturated in 5 ml of hexanes, collected on a frit and dried in vacuo. Yield: 95 mg, 77 %.

15

20


Example 40

(a) 2,2'-oxybis(ethane-2,1-diyl)bis(diisopropylphosphine) with bis(cyclooctene) iridium(I) dimer



30 ml of toluene was added to 50 mg (0.163 mmol) of 2,2'-oxybis(ethane-2,1-diyl)bis(di-*iso*-propylphosphine) and 73 mg (0.082 mmol) of [iridium bis(cyclooctene) chloride] dimer $[\text{Ir}(\text{COE})_2\text{Cl}]_2$ and the mixture was heated to 80°C for 2 hours. The solvent was removed in vacuo and 30 ml of hexanes was added. The hexanes solution was filtered and then the solvent was removed in vacuo. The solid was then dissolved in 2 ml of tetrahydrofuran and 2 ml of water. The addition of ca. 50 mg (1.62 mmol) of AB resulted in the formation of a large amount of hydrogen.

(b) 2,2'-oxybis(ethane-2,1-diyl)bis(ditertiarybutylphosphine) with bis(cyclooctene) iridium(I) dimer




30 ml of toluene was added to 50 mg (0.138 mmol) of 2,2'-oxybis(ethane-2,1-diyl)bis(di-*tert*-butylphosphine) and 62 mg (0.062 mmol) of [iridium bis(cyclooctene) chloride] dimer $[\text{Ir}(\text{COE})_2\text{Cl}]_2$ and the mixture was heated to 80°C for 2 hours. The solvent was removed in vacuo and 30 ml of hexanes was added. The hexanes solution was filtered and then the solvent was removed in vacuo. The solid was then dissolved in 2 ml of tetrahydrofuran and 2 ml of water. The addition of 50 mg (1.62 mmol) of AB resulted in the formation of a large amount of hydrogen.

The reaction of the 'POP' ligands $\text{O}(\text{CH}_2\text{CH}_2\text{PR}_2)_2$ (R = isopropyl, tertiarybutyl) with iridium and cobalt sources was examined. Thus, the reaction chlorobis(cyclooctene)iridium(I) dimer with the ligands produced mixtures of compounds which could not be separated (R = isopropyl; R = tertiarybutyl). Reaction with cobalt(II)chloride (R = isopropyl; R = tertiary butyl) afforded uniform looking materials which were not fully characterized due to the paramagnetic nature of the material.

Metal Complexes with (-P-O-phenylene-O-P-) Ligands

Example 41


(a) 1,3-bis-(di-iso-propyl-phosphinoxy)benzene and [iridium bis(cyclooctene) chloride] dimer



To a solution of [iridium bis(cyclooctene) chloride] dimer $[\text{Ir}(\text{COE})_2\text{Cl}]_2$ (1.3 g, 1.46 mmol) in degassed *iso*-propanol (50 ml) was added a solution of 1,3-bis-(di-*iso*-propyl-phosphinoxy)benzene (1g, 2.92 mmol) in *iso*-propanol (10 ml). The mixture was stirred at room temperature for 30 minutes, then at 60°C for 30 minutes, and finally refluxed at 110°C for 2 days. The solvent was then removed in vacuo, and hexanes was added to the residue. Filtration of the hexanes suspension afforded an orange solid and red solution. The filtrate was then pumped dry to afford a bright red solid. Yield: 0.584 g (35%). ^1H NMR (400 MHz, C_6D_6): δ 7.00 – 6.60 (m, 3 H, *Ph-H*), 2.20 – 1.80 (m, 4H, $\text{CH}(\text{CH}_3)_2$), 1.50 – 0.80 (m, 12H, $\text{CH}(\text{CH}_3)_2$), -20.89 (d, 1H, *Ir-H*), -36.66 (s, br, 1H, *Ir-H*). $^{31}\text{P}\{^1\text{H}\}$ NMR (400 MHz, C_6D_6): δ 169, 145, 121.

(The ^1H & ^{31}P NMR data is different from the literature reported value: Morales-Morales, D.; Redon, R.; Yung, C.; Jensen, C. M. *Inorganica Chimica Acta* 2004, 357, 2953 – 2956).


(b) 1,3-bis(di-tert-butylphosphinoxy)benzene hydrido chloro iridium



The compound was prepared according to the literature procedure (Göttker-Schnetmann, I.; White, P.; Brookhart, M. *J. Am. Chem. Soc.* 2004, 126, 1804 – 1811) Yield: 0.30 g (87%). ^1H NMR (400 MHz, CD_2Cl_2): δ 6.76 (t, $^3J_{\text{H-H}} = 8.0$ Hz, 1H, 4-H), 6.54 (d, $^3J_{\text{H-H}} = 8.0$ Hz, 2H, 3- and 5-H), 1.35 (m,

36H, 4 x *t*Bu), -41.39 (t, $^2J_{P-H} = 13.1$ Hz, 1H, IrH). $^{31}P\{^1H\}$ NMR (400 MHz, CD_2Cl_2): δ 175.8.

(c) 1,3-bis(diethylphosphinoxy)benzene hydrido chloro iridium




5

To a solution of [iridium bis(cyclooctene) chloride] dimer [Ir(COE)₂Cl]₂ (0.39 g, 0.435 mmol) in degassed *iso*-propanol (25 ml) was added a solution of 1,3-bis(diethylphosphinoxy)benzene (0.25 g, 0.87 mmol) in *iso*-propanol (10 ml). The mixture was stirred at room temperature for 30 minutes, then at 60°C for 30 minutes, and finally refluxed at 110°C for 2 days. The solvent was then removed in vacuo and hexanes was added to the residue. The precipitate was filtered off and was washed with hexanes to obtain a greenish brown solid. Yield: 0.21 g (47%). 1H NMR (400 MHz, CD_2Cl_2): δ 7.00 – 6.00 (m, 3 H, *Ph-H*), 2.50 – 1.00 (m, 8H, CH_2CH_3), 1.00 – 0.50 (m, 12H, CH_2CH_3), -20.50 (d, 1H, Ir-H). $^{31}P\{^1H\}$ NMR (400 MHz, CD_2Cl_2): δ 147, 112, 64.

15

(d) 1,3-bis(diphenylphosphinoxy)benzene hydrido chloro iridium



To a solution of [iridium bis(cyclooctene) chloride] dimer [Ir(COE)₂Cl]₂ (0.23 g, 0.261 mmol) in degassed *iso*-propanol (20 ml) was added a solution of 1,3-bis(diphenylphosphinoxy)benzene (0.25 g, 0.52 mmol) in *iso*-propanol (10 ml). The mixture was stirred at room temperature for 30 minutes, then at 60°C for 30 minutes, and was then refluxed at 110°C for 2 days. The solvent was then removed in vacuo, and the residue was precipitated by adding hexanes. The precipitate was collected by filtration and was then washed with hexanes to obtain a green solid. Yield: 0.3 g (82%). 1H NMR (400 MHz,

25


CD₂Cl₂): d 8.00 – 6.00 (m, 23 H, Ph-H), -19.02 (dd, ²J_{PH} = 15.2 Hz, 1H, Ir-H).
³¹P{¹H} NMR (400 MHz, CD₂Cl₂): d 115, 86.

Transition metal complexes of 'POP' or 1,3-C₆H₄(OPR₂)₂ ligands (R = ethyl, isopropyl, phenyl or tertiarybutyl) were prepared. For R = tertiarybutyl, the known complex 1,3-bis(ditertiarybutyloxy)benzenechlorohydrido-
 5 iridium(III) was obtained. For all other R groups attempted, mixtures were obtained which were used as catalysts in situ. These ligands were also reacted with trichlorooxybis(triphenylphosphine)rhenium(V) and ruthenium(III) chloride hydrate. Complex mixtures formed.

10

Example 42

1,3-bis(diisopropylphosphinoxy)benzenebromonickel(II)




The compound was prepared with a slight modification to the literature
 15 procedure: (Pandarus, V.; Zargarian, D. *Chem. Commun.* **2007**, 978-980).
 Yield: 0.66 g (95%). ¹H NMR (400 MHz, CDCl₃): δ 6.96 (t, J_{H-H} = 8.0 Hz, 1H, PhH), 6.42 (d, J_{H-H} = 8.0 Hz, 2H, PhH), 2.46 (m, 4H, PCH(CH₃)₂), 1.43 (dt, J_{H-H} = 7.1 Hz, J_{H-P} = 7.6 Hz, 12H, CH₃), 1.33 (dt, J_{H-H} = 7. Hz, J_{H-P} = 7.1 Hz, 12H, CH₃). ³¹P NMR (162 MHz, CDCl₃): δ 188 (s).

20

The reaction of 1,3-bis(diisopropylphosphinoxy)benzene with nickel(II) bromide in the presence of triethylamine proceeded with elimination of triethylammonium chloride to afford the known complex bis(diisopropylphosphinoxy)benzenebromonickel(II).

25 Example 43


1,3-bis(diisopropylphosphinoxy)benzene with iron(II) chloride



Iron(II) chloride (FeCl_2) (7 mg g, 0.0552 mmol) was added to a solution of 1,3-bis(diisopropylphosphinoxy)benzene (0.020 g, 0.0584 mmol) in tetrahydrofuran (30 ml). The reaction mixture was then stirred at room temperature for 30 minutes followed by 80°C for 3 hours. Solid potassium tertiary butoxide (ca. 10 mg, 0.0891 mmol) was added followed by ammonia borane (ca. 50 mg, 1.62 mmol) at room temperature, no gas evolution was observed.

10 Example 44

Bis(diisopropylphosphinoxy)benzene with cobalt(II) chloride




Cobalt(II) chloride (0.008 g, 0.0584 mmol) was added to a solution of bis(diisopropylphosphinoxy)benzene (0.020 g, 0.0584 mmol) in tetrahydrofuran (30 ml). The reaction mixture was then stirred at room temperature for 30 minutes, then at 60°C for 3 hours. The color of the reaction mixture remained blue. Then potassium tertiary butoxide (ca. 10 mg, 0.0891 mmol) was added followed by ammonia borane (ca. 50 mg, 1.62 mmol) at room temperature. No gas evolution was observed.

The reaction of bis(diisopropylphosphinoxy)benzene with both iron(II) chloride and cobalt(II) chloride were attempted but the products were not fully characterized.

Metal Complexes with (-P-phenylene-P-) Ligands

25 Example 45

1,3-bis((ditertiarybutylphosphino)methyl)benzenechlorohydrido-iridium(III)




The compound was prepared according to the literature procedure (Moulton, C. J.; Shaw, B. L. *J. C. S. Chem. Comm. Dalton Trans.* **1976**, 1020 – 1024). Yield: 0.60 g (38%). ^1H NMR (400 MHz, CD_2Cl_2): δ 7.00 (d, $^3J_{\text{H-H}} = 8.0$ Hz, 1H, 4-H), 6.98 (m, 2H, 3- and 5-H), 3.14 (m, 4H, CH_2), 1.39 (m, 36H, *t*-Bu), -43.0 (t, $^2J_{\text{P-H}} = 12.0$ Hz, 1H, IrH). $^{31}\text{P}\{^1\text{H}\}$ NMR (162 MHz, CD_2Cl_2): δ 68.0.

Pincer complexes containing 'PCP' ($1,3\text{-C}_6\text{H}_4(\text{CH}_2\text{PR}_2)_2$) ($\text{R} =$ isopropyl, tertiarybutyl) ligands have been synthesized. The reaction of 1,3-bis((di-tert-butylphosphino)methyl)benzene with chlorobis(cyclooctene)iridium(I) dimer affords the known complex 1,3-bis((di-tert-butylphosphino)methyl)benzene chlorohydrido-iridium(III).

Example 46

1,3-bis((diisopropylphosphino)methyl)benzene with chlorobis(cyclooctene)iridium(I) dimer




The compound was prepared according to the literature procedure: (Moulton, C. J.; Shaw, B. L. *J. C. S. Chem. Comm. Dalton Trans.* **1976**, 1020 – 1024). 20 mg of the solid and 7 mg (0.062 mmol) of potassium tertiary butoxide were dissolved in tetrahydrofuran and then 50 mg (1.62 mmol) of ammonia borane was added, resulting in the evolution of a large amount of hydrogen.

This reaction resulted in a mixture of compounds.

Example 47

1,3-bis(ditertiarybutylphosphine)methyl)benzenechlorotriphenylphosphineruthenium(II)



5

This compound was prepared in a similar fashion to the phenyl analogue: Karlen, T.; Dani, P.; Grove, D. M.; Steenwinkel, P., van Koten, G. *Organometallics* **1996**, *15*, 5687 – 5694. Yield: 0.448 g. $^{31}\text{P}\{^1\text{H}\}$ NMR (162 MHz, C_6D_6): δ 32.6 (ca. 65 %), -7.3 (ca. 35 %). 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a yellow solution. Ammonia borane was added (50 mg, 1.620 mmol) and the hydrolysis rate was moderate.


10

The reaction of 1,3-bis((ditertiarybutylphosphino)methyl)benzene with dichlorotris(triphenylphosphine)ruthenium(II) provided the previously reported complex 1,3-bis((ditertiarybutylphosphino)methyl)benzenechlorotriphenylphosphineruthenium(II).

15

Example 48

1,3-bis((ditertiarybutylphosphino)methyl)benzene with ruthenium(III) chloride hydrate



20

The compound was prepared according to the literature procedure (Gusev, D. G.; Madott, M.; Dolgushin, F. M.; Lyssenko, K. A.; Antipin, M. Y. *Organometallics* **2000**, *19*, 1734 – 1739). Yield: 0.05 g. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a red solution. The material was tested for ammonia borane hydrolysis. ^1H NMR (400 MHz, C_6D_6): δ 7.06 (m, 3H, C_6H_3), 3.13 (overlapped,


25

4H, CH₂), 1.10, 1.34 (vt, $J = 6.5$ Hz, 36H, CH₃). ³¹P{¹H} NMR (162 MHz, C₆D₆): δ 69.0.

Refluxing 1,3-bis((ditertiarybutylphosphino)methyl)benzene with ruthenium(III)chloride hydrate in ethanol produced the known complex 1,3-bis((ditertiarybutylphosphino)methyl)benzene(carbonyl)chlororuthenium(II). The carbonyl ligand is formed by decarbonylation of the ethanol solvent.

Example 49

1,3-bis(di-*t*-butylphosphine)methyl)benzenechlorohydridoruthenium(II)




The compound was prepared according to the literature procedure (Gusev, D. G.; Madott, M.; Dolgushin, F. M.; Lyssenko, K. A.; Antipin, M. Y. *Organometallics* **2000**, 19, 1734 – 1739). Yield: 0.126 g. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a red solution. Ammonia borane was added (50 mg, 1.620 mmol) and the hydrolysis rate is moderate. ¹H NMR (400 MHz, CD₂Cl₂): δ 7.07 (m, 2H, phenyl-*H*), 6.93 (m, 1H, phenyl-*H*), 3.06 (m, 4H, CH₂), 1.27, 1.34 (vt, $J = 9.4$ Hz, 36H, CH₃), -15.53 (t, ² $J_{\text{HP}} = 13.0$ Hz, 2H, RuH). ³¹P{¹H} NMR (162 MHz, C₆D₆): δ 63.7.

A complex was prepared by the reaction of 1,3-bis((di-*tert*-butylphosphino)methyl)benzene with dichloro(*p*-cymene)ruthenium(II) dimer. This reaction resulted in the formation of the previously reported pincer complex where the coordination sphere of the metal is taken up by two phosphine groups, a hydride and chloride ligand and an agostic interaction with a phenyl C-H bond

Metal Complexes with (-P-N-phenylene-N-P-) Ligands

Example 50

*N*¹,*N*³-bis(diisopropylphosphino)benzene-1,3-diamine with chlorobis(cyclooctene)iridium




To a solution of chlorobis(cyclooctene)iridium(I) dimer $[\text{Ir}(\text{COE})_2\text{Cl}]_2$ (0.025 g, 0.0294 mmol) in tetrahydrofuran (20 ml) was added N^1,N^3 -bis(diisopropylphosphino)benzene-1,3-diamine (0.02 g, 0.0587 mmol). The mixture was stirred at room temperature for 30 minutes, then at 80°C for 3 hours. The solvent was then removed in vacuo, and the residue was precipitated by the addition of hexanes. The precipitate was isolated by filtration and was then washed with hexanes to obtain a solid product. Yield: 15 mg (45%). The compound appears to be moisture sensitive. ^1H NMR (400 MHz, CD_2Cl_2): δ 7.6 – 6.80 (m, 3 H, Ph-H), 3.10 (s, br, 2H, NH), 2.30 – 1.80 (m, 4H, $\text{CH}(\text{CH}_3)_2$), 1.80 – 1.00 (br, 12H, $\text{CH}(\text{CH}_3)_2$), -24.6 (dd, $^2J_{\text{PH}} = 15.2$ Hz, 1H, IrH). $^{31}\text{P}\{^1\text{H}\}$ NMR (162 MHz, CD_2Cl_2): δ 84.0.

The reaction of the ligand with chlorobis(cyclooctene)iridium(I) dimer afforded a single compound that has a ^{31}P NMR resonance at δ 84.0. The ^1H NMR spectrum of the product shows the presence of the P-N-phenylene-N-P ligand and also a hydride signal at δ -24.6. We propose the tentative structure in the scheme above for the complex.

Example 51

N^1,N^3 -bis(diisopropylphosphino)benzene-1,3-diamine with cobalt(II) chloride




Cobalt(II) chloride (CoCl_2) (0.0076 g, 0.0587 mmol) was added to a solution of N^1,N^3 -bis(diisopropylphosphino)benzene-1,3-diamine (0.020 g, 0.0587 mmol) in tetrahydrofuran (30 ml). The reaction mixture was then stirred at room temperature for 30 minutes, followed by 60°C for 3 hours resulting in a change of color from blue to bluish green. The material was tested for ammonia borane hydrolysis.

The reaction of N^1, N^3 -bis(di-*iso*-propylphosphino)benzene-1,3-diamine with cobalt(II)chloride or trichlorooxybis(triphenylphosphine)rhenium(V) produced mixtures of products

5 Metal Complexes with (-P-N-N-P-) Ligands

Example 52

N^1, N^2 -bis(2-(diphenylphosphino)benzylidene)cyclohexane with cobalt(II) chloride




- 10 An 835 mg (1.268 mmol) sample of N^1, N^2 -bis(2-(diphenylphosphino)-benzylidene)cyclohexane-1,2-diamine and 150 mg (1.155 mmol) of cobalt(II) chloride were stirred in 5 ml of acetonitrile for one hour. 40 ml of diethyl ether was added dropwise and then the mixture was stirred for 30 minutes to complete precipitation. The solid was collected by vacuum filtration, washed
- 15 with 5 ml of diethyl ether and then dried in vacuo. Yield 0.900 g. NMR spectra were not obtained.

The reaction of this ligand system with cobalt(II)chloride in acetonitrile proceeds smoothly to afford a brown material

20 Example 53

Bis(acetonitrile) N^1, N^2 -bis(2-(diphenylphosphino)benzylidene)cyclohexane-1,2-diamine iron (II) tetrafluoroborate




Acetonitrile (5 ml) was added to 210 mg (0.319 mmol) of N^1,N^2 -bis(2-(diphenylphosphino)benzylidene)cyclohexane-1,2-diamine and 102 mg (0.302 mmol) of iron (II) tetrafluoroborate hexahydrate $[\text{Fe}(\text{OH}_2)_6][\text{BF}_4]_2$ and the mixture was stirred for one hour. The solution was concentrated to ca. 1 ml and then 20 ml of diethyl ether was added dropwise. The mixture was stirred for 30 minutes and then the solid was collected on a glass frit and dried in vacuo. Yield 240 mg, 82 %. ^1H NMR (300 Mhz, CD_3CN): δ 9.24 (s); 6.67-8.08 (m); 3.55 (m); 2.80 (m); 2.15 (m); 1.55 (m). ^{31}P NMR (121 Mhz, CD_3CN): δ 52.7. The material was tested for ammonia borane hydrolysis.

The addition of N^1,N^2 -bis(2-(diphenylphosphino)benzylidene)cyclohexane-1,2-diamine to iron (II) tetrafluoroborate hexahydrate in acetonitrile resulted in the immediate formation of a red solution. The dicationic compound was readily isolated via crystallization. The tentative structure indicated in the scheme above consists of a psueodooctahedral complex with a coordinated P_2N_2 ligand and a two coordinated acetonitrile ligands. The ^1H NMR spectrum of the material shows the expected resonances, and features a two proton signal at δ 9.24 which corresponds to the $\text{N}=\text{CH}$ moiety. The ^{31}P NMR spectrum of the complex has a single resonance at δ 52.7.

Example 54

N^1,N^2 -bis(2-(diphenylphosphino)benzylidene)cyclohexane-1,2-diamine with nickel(II) bromide




Acetonitrile (10 ml) was added to 751 mg (1.140 mmol) of N^1,N^2 -bis(2-(diphenylphosphino)benzylidene)cyclohexane-1,2-diamine and 249 mg (1.140 mmol) of nickel(II) bromide. The mixture was heated to reflux for one hour and then was cooled to room temperature. 40 ml of diethyl ether was added dropwise and the precipitate was collected on by vacuum filtration and was dried in vacuo. Yield 1.003 g, 78 %. NMR spectra were not obtained due to

the low solubility of the compound. The material was tested for ammonia borane hydrolysis.

A nickel complex of N^1,N^2 -bis(2-(diphenylphosphino)benzylidene)cyclohexane-1,2-diamine was prepared. The material has not
5 been fully characterized owing to its extremely low solubility.

Example 55

N^1,N^2 -bis(2-(diphenylphosphino)benzylidene)cyclohexane-1,2-diamine with
tetrakis(acetonitrile)copper(I) hexafluorophosphate




To a solution of N^1,N^2 -bis(2-(diphenylphosphino)benzyl)cyclohexane-1,2-diamine (0.7g, 1.06 mmol) in acetonitrile (20 ml) was added tetrakis(acetonitrile)copper(I) hexafluorophosphate (0.38 g, 1.01 mmol). The reaction mixture was then stirred at room temperature for 4 hours. The solvent
15 was removed in vacuo, and the residue was precipitated by the addition of hexanes. The precipitate was filtered and was washed with hexanes and dried in vacuo. The material was used without further purification for ammonia borane hydrolysis experiments. ^1H NMR (300 Mhz, CD_2Cl_2): δ 8.47 (s); 7.07-7.72 (m); 3.06 (s); 2.32 (m); 1.83 (m); 1.05 (m). ^{31}P NMR (121 Mhz, CD_2Cl_2):
20 δ -3.0. The material was tested for ammonia borane hydrolysis.

A copper containing P_2N_2 complex was prepared by the reaction of N^1,N^2 -bis(2-(diphenylphosphino)benzylidene)cyclohexane-1,2-diamine with tetrakis(acetonitrile) copper (I) hexafluorophosphate as depicted in the scheme above. The ^{31}P NMR spectrum of the complex displays a single
25 resonance at δ -3.0. The ^1H NMR spectrum shows a signal for the $\text{N}=\text{CH}$ group at δ 8.47.

Example 56

*N*¹,*N*²-bis(2-(diphenylphosphino)benzyl)cyclohexane-1,2-diamine with
chlorobis(cyclooctene)iridium(I) dimer [Ir(COE)₂Cl]₂




R = phenyl

5 To a solution of *N*¹,*N*²-bis(2-(diphenylphosphino)benzyl)cyclohexane-1,2-diamine (0.300 g, 0.417 mmol) in tetrahydrofuran (20 ml) was added chlorobis(cyclooctene)iridium(I) dimer [Ir(COE)₂Cl]₂ (0.180 g, 0.208 mmol). The reaction mixture was then stirred at room temperature for 30 minutes, and then at 80°C for 3 hours. The solvent was removed in vacuo, and the
10 residue was precipitated by the addition of hexanes. The precipitate was filtered and was washed with hexanes to obtain a solid product. The material was used without further purification for ammonia borane hydrolysis experiments. Yield: 0.28g (70%). ¹H NMR (400 MHz, CD₂Cl₂): δ 7.58 – 6.80 (m, 20 H, Ph-*H*), 4.40 – 3.50 (m, 4H, NCH₂), 2.23 (m, br, 24H, CH₃), 1.90 –
15 0.20 (m, br, 8H, cyclohexane-*H*), -21.05 (dd, ²J_{PH} = 20.5 Hz, 1H, IrH). ³¹P{¹H} NMR (400 MHz, CD₂Cl₂): δ -7.0 (ca. 50 %), -17.5 (ca. 50 %). (The ³¹P NMR data is different from the literature reported value: Li, Y. –Y.; Zhang, H.; Chen, J. –S.; Liao, X. –L.; Dong, Z. –R.; Gao, J. –X. *Journal of Molecular Catalysis A: Chemical* **2004**, 218, 153 – 156).

20 The reactivity of diamine diphosphine ligand *N*¹*N*²-bis(2-(diphenylphosphino)benzyl)cyclohexane-1,2-diamine towards chlorobis(cyclooctene)iridium(I) dimer was investigated. This reaction produced a mixture of two compounds with resonances in the ³¹P NMR spectrum at δ -2.7 and -15.1. Separation of the compounds was not
25 achieved.


Example 57

(a) N^1N^2 -bis(2-(diphenylphosphino)benzyl)cyclohexane-1,2-diaminedichloro-cobalt(II)



5 Cobalt(II) chloride (0.0015 g, 0.12 mmol) was added to a solution of N^1N^2 -bis(2-(diphenylphosphino)benzyl)cyclohexane-1,2-diamine (0.076 g, 0.115 mmol) in tetrahydrofuran (3 ml). The reaction mixture was then heated at 80°C until all cobalt(II) chloride dissolved (<3 minutes). A 1 ml portion of the reaction mixture was taken and water was added, followed by ammonia
10 borane (ca. 50 mg, 1.62 mmol), resulting in extensive hydrogen evolution.

(b) N^1,N^2 -bis(2-(di-*p*-tolylphosphino)benzyl)cyclohexane-1,2-diamine dichlorocobalt(II)



Ar = para-C₆H₄CH₃

15 Tetrahydrofuran (3 ml) of was added with stirring to 230 mg (0.320 mmol) of N^1,N^2 -bis(2-(di-*p*-tolylphosphino)benzyl)cyclohexane-1,2-diamine and 38 mg (0.293 mmol) of cobalt(II) chloride. The mixture initially turned pink and after stirring for 1 hour had turned dark green. The solvent was removed in vacuo and the solid was triturated with 2×5 ml of hexanes and was then dried in vacuo to afford an olive green powder. Yield: 230 mg, 93 %.


20 The compounds N^1N^2 -bis(2-(diphenylphosphino)benzyl)cyclohexane-1,2-diamine and N^1N^2 -bis(2-(di-*p*-tolylphosphino)benzyl)cyclohexane-1,2-diamine were reacted with cobalt(II)chloride. The dark green complexes were readily obtained by removal of the solvent in vacuo and triturating the material

in hexanes. The compounds are paramagnetic and were not characterized further.

Metal Complexes with (-N-N-N-N-) Ligands

5 Example 58


*N*¹,*N*²-bis(pyridin-2-ylmethylene)cyclohexane-1,2-diamine with iron (II) tetrafluoroborate hexahydrate



Degassed acetonitrile (10 ml) of was added to 200 mg (0.684 mmol) of
 10 *N*¹,*N*²-bis(pyridin-2-ylmethylene)cyclohexane-1,2-diamine and 210 mg (0.622 mmol) of iron(II) tetrafluoroborate hexahydrate $[\text{Fe}(\text{OH}_2)_6][\text{BF}_4]_2$ resulting in the formation of a deep purple solution. The mixture was stirred for one hour, filtered through Celite and then concentrated in vacuo to ca. 1 ml. 10 ml of diethyl ether was added dropwise resulting in the formation of a purple solid
 15 that was collected by vacuum filtration and dried in vacuo. ¹H NMR (300 Mhz, CD₂Cl₂): δ 9.41 (m, br); 7.17-8.33 (m, br); 3.61 (br); 3.24 (br); 2.96 (br); 2.35 (br); 1.11-1.83 (m). Yield 270 mg, 73 %. The material was tested for ammonia borane hydrolysis.

20 Example 59

*N*¹,*N*²-bis(pyridin-2-ylmethylene)cyclohexane-1,2-diamine with tetrakis(acetonitrile)copper(I) hexafluorophosphate




(note: proposed structure)

Degassed acetonitrile (10 ml) was added to 100 mg (0.342 mmol)
 25 *N*¹,*N*²-bis(pyridin-2-ylmethylene)cyclohexane-1,2-diamine and 110 mg (0.295

mmol) tetrakis(acetonitrile)copper(I) hexafluorophosphate $[\text{Cu}(\text{NCCH}_3)_4]\text{PF}_6$ and the mixture was stirred for one hour. The solution was filtered through Celite and then the solvent volume was reduced in vacuo to ca. 1 ml. 10 ml of diethyl ether was added dropwise and the red precipitate was collected on a frit and dried in vacuo. Yield 110 mg, 75 %. ^1H NMR (300 Mhz, CD_2Cl_2): δ 8.51 (s); 7.91 (m); 7.74 (m); 7.35-7.43 (m); 3.88 (m); 2.05 (m); 1.18-1.81 (m). The material was tested for ammonia borane hydrolysis.

Example 60


N^1,N^2 -bis(pyridin-2-ylmethylene)cyclohexane-1,2-diamine with cobalt(II) chloride



Tetrahydrofuran (10 ml) of was added to 220 mg (0.752 mmol) of N^1,N^2 -bis(pyridin-2-ylmethylene)cyclohexane-1,2-diamine and 80 mg (0.616 mmol) of cobalt(II) chloride. The mixture was heated to reflux for three hours and was then cooled to room temperature and the solid that had formed was collected by vacuum filtration and then dried in vacuo. Yield 259 mg, 99 %. NMR spectra were not obtained. The material was tested for ammonia borane hydrolysis.

Example 61

N^1,N^2 -bis(pyridin-2-ylmethylene)cyclohexane-1,2-diamine with nickel(II) bromide




A 0.700 g (2.394 mmol) sample of N^1,N^2 -bis(pyridin-2-ylmethylene)cyclohexane-1,2-diamine and 0.455 g (2.082 mmol) of nickel(II) bromide were refluxed in 10 ml of degassed acetonitrile for one hour. 40 ml of

diethyl ether was added dropwise and then the solid was collected by vacuum filtration. Yield 850 mg, 80 %. NMR spectra were not obtained due to the low solubility of the compound.

Complexes containing the 'N-N-N-N' ligand N^1,N^2 -bis(pyridin-2-ylmethylene)cyclohexane-1,2-diamine were also prepared. The reaction of the ligand with iron (II) tetrafluoroborate hexahydrate or tetrakis(acetonitrile) copper (I) hexafluorophosphate proceeded rapidly and afforded single products as indicated by ^1H NMR spectroscopy. The spectra showed the expected resonances for the "N-N-N-N" adducts. Cobalt and nickel complexes were prepared analogously. Further characterization was not attempted due to the very low solubility (metal = nickel) or paramagnetic nature (metal = cobalt) of the complexes.

Example 62

1,1'-(pyridine-2,6-diyl)bis(3-butyl-1H-imidazol-3-ium) chloride with chlorobis(cyclooctene)iridium(I) dimer




To a solution of 1,1'-(pyridine-2,6-diyl)bis(3-butyl-1H-imidazol-3-ium) chloride (1.0 g, 2.06 mmol) in tetrahydrofuran (30 ml) was added chlorobis(cyclooctene)iridium(I) dimer $[\text{Ir}(\text{COE})_2\text{Cl}]_2$ (0.92 g, 1.03 mmol) and triethylamine (0.40 g, 4.1 mmol). The reaction mixture was then stirred at room temperature for 30 minutes, then at 80°C overnight. The solvent was then evaporated, and the residue was precipitated by the addition of hexanes. The precipitate was filtered and then washed with hexanes to obtain an orange brown color solid. Yield: 0.52g (36%) ^1H NMR (400 MHz, CD_2Cl_2): δ 7.63 – 6.90 (m, 7H, imidazole & pyridine H), 4.30 (t, 4H, $\text{NCH}_2\text{CH}_2\text{CH}_2\text{CH}_3$), 1.84 – 0.14 (m, 14H, $\text{NCH}_2\text{CH}_2\text{CH}_2\text{CH}_3$), -15.5 (s, 1H, Ir-H), -23.8 (s, 1H, Ir-H).

The reaction of 1,1'-(pyridine-2,6-diyl)bis(3-butyl-1H-imidazol-3-ium) chloride with chlorobis(cyclooctene)iridium(I) dimer in the presence of excess triethylamine was performed. A complex mixture was formed as indicated by NMR spectroscopy.

5

Example 63

1,1'-(pyridine-2,6-diyl)bis(3-butyl-1H-imidazol-3-ium) chloride with cobalt(II) chloride



10

To a solution of 1,1'-(pyridine-2,6-diyl)-bis-(3-butyl-1H-imidazol-3-ium) chloride (0.2 g, 0.41 mmol) in THF (30 ml) was added cobalt dichloride (0.05 g, 0.41 mmol) and triethylamine (0.08 g, 0.82 mmol). The reaction mixture was then stirred at room temperature for 30 minutes, and then at 80°C for 3 hours. The solvent was then evaporated, and the residue was then precipitated into hexanes. The precipitate was filtered and washed with hexanes to obtain a pale blue solid. Yield: 0.12 g (48%).


15

The reaction of 1,1'-(pyridine-2,6-diyl)bis(3-butyl-1H-imidazol-3-ium) chloride with cobalt(II)chloride produced a paramagnetic blue solid material that was not completely characterized.

20

Example 64

2,6-bis(1-n-butylimidazolium)pyridine dibromide with dichloro-1,5-cyclooctadieneruthenium(II) polymer




The compound was prepared according to the literature procedure (Poyatos, M.; Mata, J. A.; Falomir, E.; Crabtree, R. H.; Peris, E. *Organometallics* **2003**, 1110 – 1114). Yield: 25%. ^1H NMR (400 MHz, $\text{DMSO-}d_6$): δ 8.39 (s, 2H, imidazole H), 8.30 (t, 1H, $^3J_{\text{H-H}} = 14.0$ Hz, pyridine H), 7.91 (d, 2H, $^3J_{\text{H-H}} = 13.5$ Hz, pyridine H), 7.61 (s, 2H, imidazole H), 4.32 (t, 4H, *n*-Bu), 1.92 (quintet, 4H, *n*-Bu), 1.38 (sextet, 4H, *n*-Bu), 0.92 (t, 6H, *n*-Bu).

When 1,1'-(pyridine-2,6-diyl)bis(3-butyl-1H-imidazol-3-ium) chloride and dichloro(1,5-cyclooctadiene)ruthenium(II) polymer were refluxed in ethanol in the presence of triethylamine the known compound 2,6- dibromo bis(1-*n*-butylimidazolium)pyridine(carbonyl)ruthenium(II) was formed. The ^1H NMR spectrum of the product agreed with the literature report.

Example 65

1,1'-(pyridine-2,6-diyl)bis(3-butyl-1H-imidazol-3-ium) chloride with chlorobis(cyclooctene)iridium(I) dimer




To a solution of 1,1'-(pyridine-2,6-diyl)bis(3-butyl-1H-imidazol-3-ium) chloride (1.0 g, 2.06 mmol) in tetrahydrofuran (30 ml) was added [iridium bis(cyclooctene) chloride] dimer $[\text{Ir}(\text{COE})_2\text{Cl}]_2$ (0.92 g, 1.03 mmol) and triethylamine (0.4 g, 0.412 mmol). The reaction mixture was then stirred at room temperature for 30 minutes, then at 80°C overnight. The solvent was

then evaporated, and the residue was precipitated by the addition of hexanes. The precipitate was filtered and then washed with hexanes to obtain an orange brown color solid. Yield: 0.52g (36%) ^1H NMR (400 MHz, CD_2Cl_2): δ 7.63 – 6.90 (m, 7H, imidazole & pyridine *H*), 4.30 (t, 4H, $\text{NCH}_2\text{CH}_2\text{CH}_2\text{CH}_3$), 1.84 – 0.14 (m, 14H, $\text{NCH}_2\text{CH}_2\text{CH}_2\text{CH}_3$), -15.5 (s, 1H, Ir-*H*), -23.8 (s, 1H, Ir-*H*).

Example 66

1,1'-(1,3-phenylenebis(methylene))bis(3-butyl-1H-imidazol-3-ium) chloride
with chlorobis(cyclooctene)iridium(I) dimer




To a solution of 1,1'-(1,3-phenylenebis(methylene))bis(3-butyl-1H-imidazol-3-ium) chloride (1.0 g, 2.36 mmol) in tetrahydrofuran (30 ml) was added chlorobis(cyclooctene)iridium(I) dimer (1.06 g, 1.18 mmol) and triethylamine (0.48 g, 4.72 mmol). The reaction mixture was then stirred at room temperature for 30 minutes, then at 80°C overnight. The solvent was then removed in vacuo, and the residue was precipitated by the addition of hexanes. The precipitate was filtered and washed with hexanes to obtain an orange brown color solid. Yield: 0.74g (48%). ^1H NMR (400 MHz, CD_2Cl_2): δ 7.14 – 6.12 (m, 7H, imidazole & pyridine-*H*), 5.61 (m, 4H, CH_2), 4.24 (t, 4H, $\text{NCH}_2\text{CH}_2\text{CH}_2\text{CH}_3$), 1.84 – 0.40 (m, br, 14H, $\text{NCH}_2\text{CH}_2\text{CH}_2\text{CH}_3$), -27.2 (s, 1H, Ir-*H*).

The synthesis of pincer complexes by the reaction of 1,1'-(1,3-phenylenebis(methylene))bis(3-butyl-1H-imidazol-3-ium) chloride with chlorobis(cyclooctene)iridium(I) dimer was attempted. The ^1H NMR spectrum of the product showed that a complex mixture had formed.

Example 67

1,1'-(1,3-phenylenebis(methylene))bis(3-butyl-1H-imidazol-3-ium) chloride
with cobalt(II) chloride




- 5 Cobalt(II) chloride (0.15 g, 1.18 mmol) was added to a solution of 1,1'-(1,3-phenylenebis(methylene))bis(3-butyl-1H-imidazol-3-ium) chloride (0.5 g, 1.18 mmol) and 2 equivalents of triethylamine (0.23 g, 2.63 mmol) in tetrahydrofuran (30 ml). The reaction mixture was then stirred at room temperature for 30 minutes, then at 80°C for 3 hours. The solvent was removed, and the residue was precipitated by the addition of hexanes. The precipitate was filtered and washed with hexanes to obtain a pale blue solid. Yield: 0.56 g (92%).

- 10 When 1,1'-(1,3-phenylenebis(methylene))bis(3-butyl-1H-imidazol-3-ium) chloride and cobalt(II)chloride were heated in the presence of excess triethylamine a paramagnetic blue solid was obtained in high yield. Further characterization was not attempted.

Example 68

(2-bis(1-*n*-butylimidazolium)ethyl)amine with chlorobis(cyclooctene)iridium(I) dimer




A 105 mg (0.117 mmol) portion of chlorobis(cyclooctene)iridium(I) dimer $[\text{IrCl}(\text{COE})_2]_2$ was added to 110 mg of (2-bis(1-n-butylimidazolium)ethyl)amine in 10 ml of degassed isopropanol. 350 ml of degassed triethylamine was added and the mixture was refluxed overnight.

5 The solution was concentrated to ca. 3 ml and then the solid was collected via filtration and dried in vacuo. NMR spectroscopy indicated that a mixture of compounds was present. The mixture displayed a low reactivity towards ammonia borane hydrolysis.

10 Metal Complexes with (N-S) Ligands

Example 69

Thiophen-2-ylmethanamine with dichlorotris(triphenylphosphine)ruthenium (II)



Thiophen-2-ylmethanamine (200 μl , 1.949 mmol) was added to

15 1.272 g of dichlorotris(triphenylphosphine)ruthenium(II) $[\text{RuCl}_2(\text{PPh}_3)_3]$ in 10 ml of tetrahydrofuran. The mixture was stirred for two hours and then the solvent was removed in vacuo. The residue was dissolved in 5 ml of tetrahydrofuran and then 30 ml of hexanes was added dropwise and the mixture was allowed to stir for 30 minutes. The solid was collected by

20 vacuum filtration and was then dried in vacuo. Yield 694 mg. ^1H NMR (400 Mhz, CD_2Cl_2): δ 6.51-7.46 (m, 15H, C_6H_5); 3.78 (s, 2H, CH_2); 3.12 (s, 2H, NH_2). ^{31}P NMR (162 Mhz, CD_2Cl_2): δ 45.7. The material was tested for ammonia borane hydrolysis.


The addition of thiophen-2-ylmethanamine to dichlorotris(triphenyl-

25 phosphine)ruthenium (II) proceeds within two hours and the product isolated had a single ^{31}P NMR resonance at δ 45.7. The ^1H NMR spectrum of the product showed the presence of triphenylphosphine and thiophen-2-ylmethanamine in a 1:1 ratio and accordingly, the structure may possess trans

chloride ligands, and the triphenylphosphine and thiophen-2-ylmethanamine ligands in the trigonal plane corresponds to the material formed in the reaction

Example 70

5 Thiophen-2-ylmethanamine with cobalt(II) chloride




Acetonitrile (5 ml) was added to 98.6 mg (0.759 mmol) of cobalt(II) chloride and the mixture was warmed gently (ca. 40 °C) until the solid dissolved. Thiophen-2-ylmethanamine (160 μ l, 1.560 mmol) of was added slowly (over ca. 3 minutes) resulting in the precipitation of a blue solid. The mixture was stirred for one hour and the solid was collected on a frit and dried in vacuo. Yield 200 mg. The material was tested for ammonia borane hydrolysis.

When two equivalents of thiophen-2-ylmethanamine were added to a solution of cobalt(II)chloride a blue precipitate rapidly formed. The material was readily isolated and the likely structure is indicated in the scheme above.

Metal Complexes with 'Pybox' Ligands

Example 71


20 1,3-bis((R)-4-isopropyl-4,5-dihydrooxazol-2-yl)benzene with cobalt(II) chloride



A sample of 1,3-bis((R)-4-isopropyl-4,5-dihydrooxazol-2-yl)benzene (30 mg, 0.100 mmol) and 20 mg (0.092 mmol) of cobalt(II) chloride were refluxed in 10 ml of tetrahydrofuran overnight. The material was tested for ammonia borane hydrolysis.

Example 72

1,3-bis((*R*)-4-isopropyl-4,5-dihydrooxazol-2-yl)benzene with chlorobis-(cyclooctene)iridium(I) dimer




A 1 ml sample of perdeutero benzene (C_6D_6) was added to 10.0 mg (0.0333 mmol) of 1,3-bis((*R*)-4-isopropyl-4,5-dihydrooxazol-2-yl)benzene and 15.0 mg (0.0167 mmol) of chlorobis(cyclooctene)iridium(I) dimer. NMR spectra recorded after one hour showed that mostly starting material was present. After three days at room temperature the mixture consisted mostly of starting material. The material was tested for ammonia borane hydrolysis.

PREPARATION OF METAL COMPLEXES IN SITU.

Example 73


Bis-(2-(di-iso-propylphosphino)ethyl)amine with iron dichloride



Iron dichloride [$FeCl_2$] (0.008 g, 0.0631 mmol) was added to a solution of bis-(2-(di-iso-propylphosphino)ethyl)amine (0.020 g, 0.0655 mmol) in tetrahydrofuran (30 ml). The reaction mixture was then stirred at room temperature for 30 minutes, then at 80°C for 3 hours. Then KO^tBu (ca. 10 mg, 0.0891 mmol) was added followed by ammonium borane (AB) (ca. 50 mg, 1.62 mmol) at room temperature. Moderate hydrogen evolution occurred which ceased rapidly.

Example 74


Trichlorooxobis(triphenylphosphine)rhenium(V) with bis(2-(diisopropylphosphino)ethyl)amine



This compound was prepared *in situ* analogously to the R = tertiarybutyl analogue above in Example 32 (b). Yield: 0.08 g (57%). 10 ml of water and 10 ml of tetrahydrofuran was added to 10 mg of the material in a scintillation vials to form a brown solution. The material was tested for ammonia borane hydrolysis.

Example 75


Bis(2-(diisopropylphosphino)ethyl)amine with nickel(II) bromide



This compound was prepared *in situ*. To a solution of bis(2-(diisopropylphosphino)ethyl)amine (0.20 g, 0.65 mmol) in tetrahydrofuran (20 ml) was added nickel(II) bromide (0.14 g, 0.65 mmol). The reaction mixture was then refluxed for 5 hours, concentrated to about 5 ml, and then precipitated by adding hexanes to obtain a pale brown color solid. Yield: 0.28 g. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a pale brown solution. The material was tested for ammonia borane hydrolysis. No metal precipitate was observed.

Example 76

2,6-bis((diisopropylphosphino)methyl)pyridine with trichlorooxybis-(triphenylphosphine)rhenium(V)




This compound was prepared *in situ*.

Trichlorooxybis(triphenylphosphine)rhenium(V) $\text{ReOCl}_3(\text{Ph}_3\text{P})_2$ (0.50 g, 0.60 mmol) was added to a solution of 2,6-bis((diisopropylphosphino)methyl)-pyridine (0.20 g, 0.58 mmol) in tetrahydrofuran (20 ml). The reaction mixture was then stirred at room temperature for 15 minutes. The greenish yellow trichlorooxybis(triphenylphosphine)rhenium(V) slowly dissolved to form a clear

dark green solution. After one hour, precipitates start to form. The product was isolated and washed with diethyl ether to remove any triphenylphosphine. Yield: 0.35 g. 5 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a yellow solution. Ammonia borane was added (50 mg, 1.620 mmol) and the hydrolysis rate was moderate.

Example 77


1,3-bis(di-iso-propylphosphinoxy)benzene with iron dichloride



Iron dichloride [FeCl_2] (7 mg g, 0.0552 mmol) was added to a solution of 1,3-bis(di-iso-propylphosphinoxy)benzene (0.020 g, 0.0584 mmol) in tetrahydrofuran (30 ml). The reaction mixture was then stirred at room temperature for 30 minutes followed by 80°C for 3 hours. The material was tested for ammonia borane hydrolysis.

Example 78

Trichlorooxybis(triphenylphosphine)rhenium(V) with 1,3-bis(ditertiarybutylphosphinoxy)benzene




This compound was prepared *in situ*. Trichlorooxybis(triphenylphosphine)rhenium(V) $\text{ReOCl}_3(\text{Ph}_3\text{P})_2$ (0.42 g, 0.50 mmol) was added to a solution of 1,3-bis(ditertiarybutylphosphinoxy)benzene (0.20 g, 0.50 mmol) in tetrahydrofuran (30 ml) with 1 equivalent of triethylamine (0.05 g, 0.50 mmol). The reaction mixture was then stirred at room temperature for 30 minutes followed by reflux overnight. The product

was purified by precipitation into diethyl ether. Yield: 0.23 g. 5 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a yellow solution. The material was tested for ammonia borane hydrolysis.

5

Example 79


1,3-bis(ditertiarybutylphosphinoxy)benzene with ruthenium(III) chloride hydrate



10 This compound was prepared *in situ*. A suspension containing ruthenium(III) chloride hydrate (0.13 g), 1,3-bis(ditertiarybutylphosphinoxy)benzene (0.20 g, 0.50 mmol) and triethylamine (0.106 g) in ethanol (20 ml) was stirred for 24 at 80°C. The solvent was removed in vacuo and the product was extracted into hexanes
15 (50 ml x 2). The solvent was then evaporated to obtain a red solid. Yield: 0.1 g. 10 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a yellow solution. Ammonia borane was added (50 mg, 1.620 mmol) and the hydrolysis rate was moderate.

20 Example 80

Bis-(di-iso-propylphosphinoxy)benzene with cobalt dichloride




CoCl₂ (0.008 g, 0.0584 mmol) was added to a solution of bis-(di-iso-propylphosphinoxy)benzene (0.020 g, 0.0584 mmol) in tetrahydrofuran (30 ml). The reaction mixture was then stirred at room temperature for 30
25

minutes, then at 60°C for 3 hours. The color of the reaction mixture remained blue. The material was tested for ammonia borane hydrolysis.

Example 81


5 *N*¹,*N*³-bis(diisopropylphosphino)benzene-1,3-diamine with trichlorooxybis(triphenylphosphine)rhenium(V)



This compound was prepared *in situ*. To a solution of *N*¹,*N*³-bis(diisopropylphosphino)benzene-1,3-diamine (0.20 g, 0.58 mmol) in tetrahydrofuran (30 ml) was added trichlorooxybis(triphenylphosphine)rhenium(V) $\text{ReOCl}_3(\text{Ph}_3\text{P})_2$ (0.49 g, 0.58 mmol) and triethylamine (0.4 g, 4.0 mmol). The reaction mixture was then stirred at room temperature for 4 hours. The trichlorooxybis(triphenylphosphine)rhenium(V) slowly dissolved to form a pale blue color solution. The solvent was then evaporated, and the residue was precipitated by the addition of diethyl ether. The precipitate was filtered and then washed with hexanes to obtain a brown color solid. Yield: 0.19 g. 5 mg of the product was dissolved in 10 ml of tetrahydrofuran and 10 ml of water in a scintillation vial to form a yellow solution. The material was tested for ammonia borane hydrolysis.

Example 82


*N*¹,*N*³-bis(di-iso-propylphosphino)benzene-1,3-diamine with cobalt dichloride



CoCl₂ (0.0076 g, 0.0587 mmol) was added to a solution of N¹,N³-bis(di-
 iso-propylphosphino)benzene-1,3-diamine (0.020 g, 0.0587 mmol) in
 tetrahydrofuran (30 ml). The reaction mixture was then stirred at room
 temperature for 30 minutes, followed by 60°C for 3 hours resulting in a
 5 change of color from blue to bluish green. The material was tested for
 ammonia borane hydrolysis.

Example 83

1,3-bis((diisopropylphosphino)methyl)benzene with ruthenium(III) chloride
 10 hydrate



This compound was prepared *in situ*. A suspension containing
 ruthenium(III) chloride hydrate (RuCl₃·3H₂O) (0.15 g, 0.60 mmol), the 1,3-
 bis((diisopropylphosphino)methyl)benzene (0.20 g, 0.60 mmol) and
 15 triethylamine (0.12 g, 1.20 mmol) in ethanol (10 ml) was stirred for 24 hours at
 80°C. After the reaction mixture was cooled down, the solids were filtered off,
 washed with ethanol (5 ml x 3), and then dried in vacuo. The product was
 purified by extraction with hexanes (50 ml x 2), followed by evaporation the
 solvent in vacuo to obtain a solid product. Yield: 0.21 g. NMR spectra showed
 20 a mixture had formed. 10 mg of the product was dissolved in 10 ml of
 tetrahydrofuran and 10 ml of water in a scintillation vial to form a brown
 solution. The material was tested for ammonia borane hydrolysis.

Example 84

25 Triphenylphosphine with cobalt dichloride




A mixture of 20 mg (0.154 mmol) of cobalt dichloride and 90 mg (0.343
 mmol) of triphenylphosphine was warmed to 60 °C in 5 ml of tetrahydrofuran

for 5 minutes and then 5 ml of water was added. AB (ca. 50 mg, 1.62 mmol) was added at room temperature resulting in hydrogen evolution.

Example 85


5 1,4-bis(diphenylphosphino)butane with cobalt dichloride



A mixture of 20 mg (0.154 mmol) of cobalt dichloride and 75 mg (0.176 mmol) of 1,4-bis(diphenylphosphino)butane was warmed to 60 °C in 5 ml of tetrahydrofuran for 5 minutes and then 5 ml of water was added. AB (ca. 50 mg, 1.62 mmol) was added at room temperature resulting in hydrogen evolution.

Example 86


15 *N*¹,*N*²-bis-(2-(diphenylphosphino)benzyl)cyclohexane-1,2-diamine with cobalt dichloride



CoCl₂ (0.0015 g, 0.115 mmol) was added to a solution of N¹,N²-bis-(2-(diphenylphosphino)benzyl)cyclohexane-1,2-diamine (0.076 g, 0.115 mmol) in tetrahydrofuran (3 ml). The reaction mixture was then heated at 80°C until all CoCl₂ dissolved (<3 minutes), resulting in the formation of a blue solution. A 1 ml portion of the reaction mixture was taken and water was added, and the color of the reaction mixture turned red. Then ammonium borane (AB) (ca. 50 mg, 1.62 mmol) was added at room temperature, resulting in extensive hydrogen evolution.

Example 87

1,3-bis(di-iso-propylphosphino)methyl)benzene with [iridium bis(cyclooctene) chloride] dimer




- 5 The title compound was prepared according to the literature procedure: (Moulton, C. J.; Shaw, B. L. *J. C. S. Chem. Comm. Dalton Trans.* **1976**, 1020 – 1024). 20 mg of the solid and 7 mg (0.062 mmol) were dissolved in tetrahydrofuran and then 50 mg (1.62 mmol) of ammonium borane (AB) was added, resulting in the evolution of a large amount of hydrogen.

10


Example 88

(a) Isolation of the free 2-(benzylthio)ethanamine ligand



- 15 To a suspension of the benzylthio ethanamine hydrochloride (0.5 g, 2.4 mmol) in dichloromethane (5 ml) was added sodium hydroxide (0.1 g, in 5 ml of water). The suspension was stirred vigorously and the two layers were separated. The solvent was removed under vacuum at 0°C. The ligand was obtained as a yellow liquid.

- 20 (b) 2-(benzylthio)ethanamine with metal complexes



This compound was prepared *in situ* as described above. In a typical experiment, benzylthio ethanamine (0.2 g, 1.2 mmol) was dissolved in toluene (5 ml) and the solution was then added to a suspension of dichloro 1,5-cyclooctadiene ruthenium polymer $[\text{RuCl}_2(\text{COD})]_n$ in toluene (5 ml). The mixture was then stirred under argon at 100°C for 2 hours. The solvent volume was reduced in vacuo to approximately 3 ml and a solid was precipitated by adding ether (10 ml) to obtain a reddish brown product. The activities of these catalysts are low for the hydrolysis of ammonia borane.

The reactions with cobalt(II) chloride (CoCl_2) and chlorobis(cyclooctene)iridium(I) dimer $[\text{IrCl}(\text{COE})_2]_2$ were performed similarly. The three catalysts prepared in the section (section b) were all tested for ammonia borane hydrolysis.

15 HOMOGENEOUS CATALYTIC AMMONIA BORANE HYDROLYSIS

Example 89: $[\text{Co}\{\text{HN}(\text{CH}_2\text{CH}_2\text{P}^i\text{Pr}_2)_2\}\text{Cl}_2]$ catalyzed AB hydrolysis

319 mg (0.732 mmol) of $[\text{Co}\{\text{HN}(\text{CH}_2\text{CH}_2\text{P}^i\text{Pr}_2)_2\}\text{Cl}_2]$ was dissolved in 20 ml of tetrahydrofuran and then 20 ml of water and 107 mg (0.350 mmol) of $\text{HN}(\text{CH}_2\text{CH}_2\text{P}^i\text{Pr}_2)_2$ were added. The flask was immersed in a water bath that was held at 40 °C and the temperature was allowed to equilibrate for 5 minutes. AB was added in portions (2.432 g, followed by five ca. 1.0 g portions) and the hydrogen evolved was measured in an inverted 8000 ml graduated cylinder. The first two AB additions were performed under an argon atmosphere and the subsequent runs were in air. 5 ml of

tetrahydrofuran and 5 ml of water were added to the mixture prior to the third run. The results are shown in Figure 9.

Example 90: [Co{HN(CH₂CH₂PPh₂)₂}Cl₂] catalyzed AB hydrolysis

5 24 mg (0.042 mmol) of [Co{HN(CH₂CH₂PPh₂)₂}Cl₂] was dissolved in 10 ml of tetrahydrofuran and 10 ml of water at 41 °C in an argon atmosphere to form a yellow solution. AB was added in ca. 50 mg (1.620 mmol) portions (with the initial addition resulting in the formation of a red colored solution) and the hydrogen evolution was measured with a 100 ml burette. The results are
10 shown in Figure 10.

Example 91: N¹,N²-bis(2-(di-p-tolylphosphino)benzyl)cyclohexane-1,2-diamine cobalt dichloride.

15 A sample of 55 mg of N¹,N²-bis(2-(di-p-tolylphosphino)benzyl)cyclohexane-1,2-diamine cobalt dichloride (0.0648 mmol) was dissolved in 10 ml of tetrahydrofuran and 10 ml of water under an argon atmosphere and the mixture was warmed to 40 °C. AB (945 mg, 30.61 mmol) was added and the hydrogen that formed was measured with a 2 L graduated cylinder. The results are shown in Figure 11.

20

Example 92

[Ru(binap)(H₂NCH₂CH₂PPh₂)Cl₂]

25 A sample of 6 mg (0.00586 mmol) of [Ru(binap)-(H₂NCH₂CH₂PPh₂)Cl₂] was dissolved in 20 ml of a 1:1 mixture of tetrahydrofuran and water. The flask was sealed and connected to an inverted 2000 ml graduated cylinder, and then placed in a water bath at ca. 40 °C and the temperature was allowed to stabilize for 5 minutes. Ammonia borane was added to the mixture in ca. 1.0 g (0.0324 mol) portions. The first five runs were performed under an argon atmosphere and the last run was performed in air. The results are
30 shown in Figure 12.


Example 93

[Ir{HN(CH₂CH₂P^tBu₂)₂}₂(C₈H₁₃)(H)(Cl)]

0.5 ml of a 10 mg/ml tetrahydrofuran solution (5 mg, 0.00715 mmol) of $[\text{Ir}\{\text{HN}(\text{CH}_2\text{CH}_2\text{P}^t\text{Bu}_2)_2\}_2(\text{C}_8\text{H}_{13})(\text{H})(\text{Cl})]$ was added in air to 20 ml of tetrahydrofuran and then 20 ml of water was added. The flask was connected to an inverted graduated cylinder (ca. 8000 ml) and was then immersed in a water bath at 41 °C. Ammonia borane (6.00 g, 0.194 mol) was added rapidly through a solid addition funnel and the flask was sealed and then opened to the hydrogen measurement apparatus. The results are shown in Figure 13.

Example 94

- 10 *Chlorocyclooctenylhydridobis(2-(ditertiarybutylphosphino)ethyl)amine-iridium(III) catalyzed ammonia borane hydrolysis*



(Note: the following two experiments are the 25 °C and 40 °C standards to which 'std. 1-3' in the following Figures refer)

- 15 Standard ammonia borane hydrolysis conditions utilizing bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) $[\text{Ir}(\text{H})(\text{Cl})(\text{C}_8\text{H}_{13})\{\text{NH}(\text{CH}_2\text{CH}_2\text{P}^t\text{Bu}_2)_2\}]$ at 25 °C or 40 °C:

- a) (25 °C): 1.0 ml (10.0 mg, 0.0143 mmol) of a 10.0 mg/ml tetrahydrofuran solution of bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) $[\text{Ir}(\text{H})(\text{Cl})(\text{C}_8\text{H}_{13})\{\text{NH}(\text{CH}_2\text{CH}_2\text{P}^t\text{Bu}_2)_2\}]$ was added in air to 80 ml of a 1:1 mixture of tetrahydrofuran/water that had been immersed for five minutes in a water bath held at 25.0 °C. Ammonia borane was added in three ca. 0.5 g portions (run 1: 0.5000 g; run 2: 0.4992 g; run 3: 0.4997 g) and the hydrogen formation was measured after each addition. The results are shown in Table 1.

- b) (40 °C): 1.0 ml (1.0 mg, 1.43×10^{-3} mmol) of a 10.0 mg/ml tetrahydrofuran solution of bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) $[\text{Ir}(\text{H})(\text{Cl})(\text{C}_8\text{H}_{13})\{\text{NH}(\text{CH}_2\text{CH}_2\text{P}^t\text{Bu}_2)_2\}]$ was added in air to 80 ml of a 1:1 mixture of tetrahydrofuran/water that had been immersed for five minutes in a water bath held at 40.0 °C. Ammonia borane was added in three


ca. 0.5 g portions (run 1: 0.5000 g; run 2: 0.5004 g; run 3: 0.5002 g) and the hydrogen formation was measured after each addition. The results are shown in Table 2.

The present disclosure demonstrates that iridium complexes with the
5 (R₂PCH₂CH₂)₂NH ligand system (R = tertiarybutyl, isopropyl and related groups) exhibited good to remarkably high activities. In particular, it was found that the complex bis(2-(ditertiarybutyl)ethyl)aminechlorocyclooctenylhydrido-
10 iridium(III) is capable of producing a 78 % yield of hydrogen in 7-8 minutes at 25 °C with a catalyst loading of 0.03 mol % (for ca. 1.5 g of ammonia borane). Since a PEM fuel cell is expected to operate at 60 °C or higher the catalyst efficiency at a higher temperature was determined. At 40 °C, it was found that the catalyst bis(2-(ditertiarybutylphosphine)-ethyl)aminechlorocyclooctenylhydrido-
15 iridium(III) can effect hydrogen formation in yields approaching 78 % in 10-11 minutes with a remarkably low catalyst loading of 3×10⁻³ mol %. The runs described above at 25 and 40 °C are now the standard runs to which all other catalysts are compared. Higher hydrogen yields can be obtained with higher purity ammonia borane. A high purity ammonia borane sample, prepared in house gave hydrogen yields ranging from 91 to 93 % within 10 minutes at 40 °C.

20 When the catalyst is added to the water/tetrahydrofuran or to neat methanol or ethanol, a red solution is immediately formed. The red species forms reversibly and upon removing the solvent the starting material bis(2-(ditertiarybutylphosphine)ethyl)aminechlorocyclooctenylhydrido-
25 iridium(III) was recovered. Indeed, X-ray quality crystals of the starting material bis(2-(ditertiarybutylphosphine)ethyl)aminechlorocyclooctenylhydrido-
30 iridium(III) were obtained from a deep red ethanol solution of the compound at -45 °C. ³¹P NMR spectroscopy of the mixture in methanol-D₄ shows that a new phosphorus containing species is present that exhibits two ³¹P resonances at δ 45.9 and 41.2 which display a large P-P coupling of 325 Hz. The ¹H NMR spectrum shows the presence of the bis(2-(ditertiarybutyl)ethyl)amine and cyclooctenyl ligands. Hydride and the N-H resonances were observed although this may be due to rapid hydrogen/deuterium exchange with the solvent methanol.

A product with a similar ^{31}P NMR spectrum (as seen in Figure 14) has been obtained via the reaction of bis(2-(ditertiarybutyl)ethylphosphine)aminechlorocyclooctenylhydrido iridium(III) with potassium tertiary butoxide. The ^{31}P NMR spectrum of the product shows two doublets at δ 56.8 and 52.7 ($J_{\text{PP}} = 368$ Hz) and the ^1H NMR spectrum shows the presence of cyclooctene and bis(2-(ditertiarybutylphosphine)ethyl)amine ligands.


A single crystal was obtained and a preliminary X-ray structure indicated that hydrochloric acid elimination from the molecule had been effected and the complex bis(2-(ditertiarybutylphosphine)-ethyl)amine(cyclooctene)iridium(I) had formed. Without being bound by theory, it is possible that the reaction proceeds via formation of intermediate bis(2-(ditertiarybutylphosphine)ethyl)aminecyclooctenylhydrido-iridium(III) species (B in the scheme below) which then reductively eliminates cyclooctene to form the product. The asymmetry indicated by the ^{31}P NMR spectrum is presumably a result of restricted rotation of the η^2 -cyclooctene ligand caused by the bulky phosphorus-bound tertiary butyl groups.



Synthesis of bis(2-(ditertiarybutyl)ethyl)amine(cyclooctene)iridium

It was observed that a solution of bis(2-(ditertiarybutylphosphine)-ethyl)amine chlorocyclooctenylhydrido-iridium(III) in either tetrahydrofuran- D_8 or benzene- D_6 *spontaneously* loses hydrochloric acid to form the η^2 -cyclooctene complex upon standing overnight under an argon atmosphere (as seen in the scheme below). This indicates that the formation of this complex is thermodynamically favorable. That bis(2-(ditertiarybutylphosphine)-ethyl)aminechlorocyclooctenylhydrido-iridium(III) can be isolated from these solvents indicates that the reactions occurring are completely reversible.

Accordingly, it is proposed that the red complex formed in alcohol or tetrahydrofuran/water solvents is the η^2 -cyclooctene complex and that it forms immediately in these solvents due to the highly favorable solvation of the liberated hydrochloric acid by the polar solvent environment (as seen in the scheme below).



It is believed that the differences in ^{31}P NMR shifts in the benzene or tetrahydrofuran and tetrahydrofuran/water are due to solvent effects. We also note that the ^{31}P NMR spectra obtained in methanol- D_4 and tetrahydrofuran/water are very similar. Significantly, the N-CH_3 analogue 2-(ditertiarybutylphosphino)- N -(2-(ditertiarybutylphosphino)ethyl)- N -methylethanaminechlorocyclooctenylhydrido-iridium(III) (vide infra), which cannot lose hydrochloric acid in an analogous fashion, shows a singlet only in the ^{31}P NMR spectrum upon dissolution in methanol- D_4 .

A single complex from the tetrahydrofuran/water mixture was isolated after a large excess of ammonia borane was hydrolyzed. The material displays a $^{31}\text{P}\{^1\text{H}\}$ NMR resonance at δ 64.0 (in dichloromethane- D_2) and the ^1H NMR spectrum of the complex shows resonances due to the bis(2-(ditertiarybutyl)ethyl)amine ligand in addition to a hydrido signal at δ -23.99. We obtained an X-ray structure of the complex which indicated that the complex bis(2-(ditertiarybutyl)ethyl)aminechlorodihydrido-iridium(III) had formed. The structure (as seen in Figure 15) features a pseudooctahedral ligand arrangement with a meridionally coordinated bis(2-(ditertiarybutyl)ethyl)amine ligand. The hydride ligands are bound to the metal center in a cis orientation.

Example 95

Effect of ammonia borane purity upon utilizing bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) [Ir(H)(Cl)(C₈H₁₃){NH(CH₂CH₂P^tBu₂)₂] catalyzed ammonia borane hydrolysis

The reaction was carried out as described in procedure 1b above. The results are shown in Table 3.

Example 96

Solvent effects upon bis(2-(ditertiarybutylphosphino)ethyl)aminechloro-cyclo-octenylhydrido-iridium(III) [Ir(H)(Cl)(C₈H₁₃){NH(CH₂CH₂P^tBu₂)₂] catalyzed ammonia borane hydrolysis

The reaction was carried out as described in procedure 1a (25 °C) or 1b (40 °C) above except that the solvent mixture utilized was a) 1:1 diglyme/water at 25.0 °C or b) 1:1 triglyme/water at 25 °C or c) 1:1 ethanol/water at 40.0 °C. The results are shown in Tables 4 and 5.

The catalytic reaction described above was performed in a 1:1 mixture of tetrahydrofuran and water. The anticipated environmental concerns regarding the utilization of a solvent such as tetrahydrofuran led to the examination of a variety of other solvents. Diethylene glycol dimethyl ether and triethylene glycol dimethyl ether (diglyme and triglyme, respectively) were chosen as suitable ether substitutes owing to their low volatility. It was found that the reaction proceeds with an almost identical rate in a 1:1 mixture of diglyme and water and with a significantly lower rate in triglyme/water. The potential of ethanol as a solvent, which is expected to have a significantly lower environmental impact than tetrahydrofuran or diglyme, was also examined. Significantly, at 40 °C it was found that substituting tetrahydrofuran/water (1:1) with ethanol/water (25:75) results in no change in the rate of the reaction. If the solvent composition was changed to a 75:25 ethanol:water ratio, a remarkable effect on reactivity was observed: the hydrogen yield was increased to 98% after 10 minutes (as compared to 72% after 10 minutes in our standard run). In absolute ethanol, the rate of hydrogen evolution was increased further and the reaction was completed (99 % yield of hydrogen) in ca. four minutes. In the latter case the reaction is likely proceeding by *alcoholysis*, rather than a hydrolysis reaction.

Example 97

Effect of ethanol concentration on rate of bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) $[\text{Ir}(\text{H})(\text{Cl})(\eta^1\text{-C}_8\text{H}_{13})\{\text{NH}(\text{CH}_2\text{-CH}_2\text{P}^t\text{Bu}_2)_2\}]$ catalyzed ammonia borane hydrolysis at 40 °C

- 5 The reaction was described as in (i) above except the solvent composition was either (a) ethanol:water 25:75; (b) ethanol:water 19:81; (c) ethanol:water 12.5:87.5 or (d) ethanol:water 75:25. The results are shown in Table 6.

10 *Example 98*


Effect of added inorganic salts (i.e. sodium chloride, lithium chloride or tetraethyl ammonium chloride) in bis(2-(ditertiarybutylphosphino)ethyl)-amine-chlorocyclooctenylhydrido-iridium(III) $[\text{Ir}(\text{H})(\text{Cl})(\eta^1\text{-C}_8\text{H}_{13})\{\text{NH}(\text{CH}_2\text{CH}_2\text{P}^t\text{Bu}_2)_2\}]$ catalyzed ammonia borane hydrolysis

- 15 The reaction was carried out as described in (i) above except water was replaced with either (a) 40 ml of saturated aqueous sodium chloride, (b) lithium chloride (548 mg) dissolved in 40 ml of water, or (c) two equivalents (4.6 mg) of tetraethylammonium chloride dissolved in 40 ml of water. The results are shown in Table 7.

- 20 The effect of a limited number of additives on the bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) catalyzed reaction was also examined. When the reaction was performed in a 1:1 mixture of saturated aqueous sodium chloride and tetrahydrofuran the activity was substantially lower. This likely due to the lower water
25 concentration in the organic phase due to the separation of two liquid phases under these conditions. In a 1:1 water/tetrahydrofuran that contained either 0.162 M lithium chloride or two equivalents (based on iridium) of tetraethylammonium chloride little effect on the reaction rate was observed.

30 *Example 99*

Effect of hydrogen (structure I) vs. methyl (structure II) substituents on nitrogen in bis(2-(ditertiarybutylphosphino)ethyl)amine type iridium complexes in catalytic ammonia borane hydrolysis




Used standard conditions as described in procedure 94b above: 1 ml of a 1.03 mg/ml solution of 2-(ditertiarybutylphosphino)-N-(2-(ditertiarybutylphosphino)ethyl)-N-methylethanaminechlorocyclooctenyl-hydrido-iridium(III) was added 80 ml of a 1:1 mixture of tetrahydrofuran/water that had been preheated to 40 °C for five minutes. Ammonia borane was added in ca. 0.5 g portions (run 1: 500.3 mg; 2: 499.5 mg; 3: 500.0 mg) and the hydrogen evolution was measured. The results are shown in Table 8.

Ligand substituent effects on the catalytic reaction were examined. For example, substituting the NH in bis(2-(ditertiarybutyl)ethylphosphine)aminechlorocyclooctenyl hydrido-iridium(III) for a N(CH₃) group in 2-(ditertiarybutyl)-N-(2-(di-tertiarybutylphosphino)ethyl)-N-methylethanaminechlorocyclooctenylhydrido-iridium(III) (as seen in structure II in the scheme above) results in a slight drop in activity in catalytic ammonia borane hydrolysis. This indicates that the NH moiety is not essential for excellent catalytic activities and will allow for the study of a range of ligands where the N-H moiety is substituted for N-R groups (R = alkyl, aryl, etc.).

Example 100

Bis(2-(diadamantylphosphino)ethyl)aminechlorodihydrido-iridium(III) catalyzed ammonia borane hydrolysis at 25 °C or 40 °C




a) 25.0 °C: A 14.8 mg (0.0158 mmol) sample of bis(2-(diadamantylphosphino)ethyl)aminechlorodihydrido-
 iridium(III) was added to 80 ml of a 1:1 mixture of tetrahydrofuran and water that had been equilibrated
 in a 25.0 °C water bath for five minutes. Ammonia borane was added in three
 5 ca. 0.500 g portions (run 1: 0.5005 g; run 2: 0.4982 g; run 3: 0.5026 g) and
 the hydrogen evolved was measured. The results are shown in Table 9.

b) 40.0 °C: A methanol solution of bis(2-(diadamantylphosphino)ethyl)aminechlorodihydrido-
 iridium(III) (1.0 ml, 1.5 mg/ml, 1.60×10^{-3} mmol) was added to 80 ml of a 1:1 mixture of
 10 tetrahydrofuran and water that had been equilibrated in a 40.0 °C water bath
 for five minutes. Ammonia borane was added in three ca. 0.500 g portions
 (run 1: 0.4995 g; run 2: 0.5001 g; run 3: 0.5002 g) and the hydrogen evolved
 was measured. The results are shown in Table 10.

When the substituents on phosphorus are changed from tertiarybutyl to
 15 adamantyl, then the catalytic reaction proceeds at a very similar rate at 25 °C
 to the standard test run. At 40 °C, the adamantyl substituted catalyst showed
 a slightly lower activity than the standard test run.

Example 101

20 *Bis(2-(dicyclohexylphosphino)ethyl)aminechlorodihydrido-
 iridium(III) catalyzed ammonia borane hydrolysis at 25 °C or 40 °C*



25 a) 25.0 °C: A 10.2 mg sample of bis(2-(dicyclohexylphosphino)ethyl)aminechlorodihydrido-
 iridium(III) was added to 80 ml of a 1:1 mixture of tetrahydrofuran and water that had been equilibrated
 in a 25.0 °C water bath for five minutes. Ammonia borane (500.0 mg) was
 added in portions and the hydrogen evolved was measured.

30 b) 40.0 °C: A methanol solution of bis(2-(dicyclohexylphosphino)ethyl)aminechlorodihydrido-
 iridium(III) (1.0 ml, 1.5


mg/ml, 1.60×10^{-3} mmol) was added to 80 ml of a 1:1 mixture of tetrahydrofuran and water that had been equilibrated in a 40.0 °C water bath for five minutes. Ammonia borane (500.0 mg) was added and the hydrogen evolved was measured. The results are shown in Tables 11 and 12.

- 5 For the cyclohexyl substituted catalyst, a significant drop in catalytic activity was observed at both 25 °C and 40 °C.

Example 102

2,6-Bis((diisopropylphosphino)methyl)pyridinedichlorohydrido-iridium(III)

- 10 catalyzed ammonia borane hydrolysis.




This reaction was performed under an argon atmosphere. 1.0 ml of a ca. 0.8 mg/ml tetrahydrofuran solution of 2,6-bis((diisopropylphosphino)methyl)pyridinedichlorohydrido-iridium(III) was added to 80 ml of a 1:1 mixture of tetrahydrofuran and water that had been immersed in a 25.5 °C water bath for 5 minutes. 0.5027 g of ammonia borane was added the hydrogen evolution was measured. The results are shown in Table 13.

20

Example 103

Catalytic ammonia borane hydrolysis by catalyst derived from bis(2-(diisopropylphosphino)-4-methylphenyl)amine and chlorobis(cyclooctene)iridium(I) dimer

25




The reaction was performed as described in procedure Example 94b above except 0.95 mg in 1 ml of tetrahydrofuran of the iridium containing catalyst was used and the reaction was performed under an argon atmosphere. 0.5004 g of ammonia borane was added and the evolved hydrogen was measured. The results are shown in Table 14.

Other PNP ligand containing iridium complexes that we have tested include 2,6-bis((diisopropylphosphino)methyl)pyridinedichlorohydrido-iridium(III) and the bis(2-(diisopropylphosphino)-4-methylphenyl)amine derived iridium catalyst. The ammonia borane hydrolysis rate for these catalysts were of a similar magnitude to the bis(2-(dicyclohexylphosphino)-ethyl)amine derived iridium catalyst.

Example 104

Bis(2-(ditertiarybutylphosphino)ethyl)amine-2,4-pentanedionate-rhodium(I)
catalyzed ammonia borane hydrolysis at 40 °C




One ml of a 8.3 mg/ml tetrahydrofuran solution of bis(2-(ditertiarybutylphosphino)ethyl)amine-2,4-pentanedionaterhodium(I) was added to 80 ml of a 1:1 mixture of tetrahydrofuran/water mixture that had been equilibrated in a 39.5 °C water bath for five minutes. 0.4994 g of ammonia borane was added and the hydrogen evolution was measured. The results are shown in Table 15.

A PNP ligand containing rhodium complex has also been tested. This catalyst also had an ammonia borane hydrolysis rate that was comparable to that of the bis(2-(dicyclohexylphosphino)ethyl)amine iridium catalyst.

Example 105

Bis(2-(dialkylphosphino)ethyl)amine (alkyl = isopropyl, cyclohexyl) and bis(diphenylphosphino)ethyl)aminedichlorocobalt(II) catalyzed ammonia borane hydrolysis



a) *Bis(2-(diisopropylphosphino)ethyl)aminedichlorocobalt(II)*

[Co{HN(CH₂CH₂PⁱPr₂)₂}Cl₂] catalyzed ammonia borane hydrolysis:

A 319 mg (0.732 mmol) sample of *Bis(2-*

(diisopropylphosphino)ethyl)aminedichlorocobalt(II) *[Co{HN(CH₂-*

CH₂PⁱPr₂)₂}Cl₂] was dissolved in 20 ml of tetrahydrofuran and then 20 ml of

water and 107 mg (0.350 mmol) of bis(2-(diisopropylphosphino)ethyl)amine

HN(CH₂CH₂PⁱPr₂)₂ were added. The flask was immersed in a water bath that

was held at 40 °C and the temperature was allowed to equilibrate for 5

minutes. Ammonia borane was added in portions (2.432 g, followed by five

ca. 1.0 g portions) and the hydrogen evolved was measured in an inverted

8000 ml graduated cylinder. The first two ammonia borane additions were

performed under an argon atmosphere and the subsequent runs were in air.

5 ml of tetrahydrofuran and 5 ml of water were added to the mixture prior to

the third run. The results are shown in Table 16.

b) *Bis(2-(diphenylphosphino)ethyl)aminedichlorocobalt(II)*

[Co{HN(CH₂-CH₂PPh₂)₂}Cl₂] catalyzed ammonia borane hydrolysis:

24 mg (0.042 mmol) of *bis(2-(diphenylphosphino)ethyl)aminedichlorocobalt(II)*

[Co{HN(CH₂-CH₂PPh₂)₂}Cl₂] was dissolved in 10 ml of tetrahydrofuran and 10 ml of water

at 41 °C in an argon atmosphere to form a yellow solution. Ammonia borane

was added in 50 mg (1.62 mmol) portions (with the initial addition resulting in

the formation of a red colored solution) and the hydrogen evolution was

measured with a 100 ml burette. The results are shown in Table 17.

c) *Bis(2-(dicyclohexylphosphino)ethyl)aminedichlorocobalt(II)*

[CoCl₂{NH(CH₂CH₂PCy₂)₂}] catalyzed ammonia borane hydrolysis utilizing

standard 40 °C conditions: A 1.0 ml sample of a 0.98 mg/ml (0.98mg, 0.002

mmol) dichloromethane solution was added to a 500 ml three-necked flask

under an argon atmosphere and the solvent was removed with an argon flush.


80 ml of a 1:1 tetrahydrofuran/water mixture was added and then the flask

was connected to the hydrogen measurement apparatus and equilibrated in a 40.0 °C water bath for five minutes. 0.5003 g (16.2 mmol) of ammonia borane was added and then the hydrogen evolved was measured. The results are shown in Table 18.

5 For base metal complexes containing $N(H)(CH_2CH_2PR_2)_2$ ligands (R = tertiarybutyl, isopropyl, phenyl, cyclohexyl), the cobalt containing catalysts proved to be the most active. The tertiarybutyl substituted complex proved to have low activity. In contrast, the isopropyl, phenyl and cyclohexyl substituted complexes were more active than the tertiarybutyl analogue and these latter
10 exmples had similar activities to one another. Table 16 shows that for bis(2-(diisopropylphosphino)ethyl)aminedichlorocobalt(II), ammonia borane could be added in multi-gram quantities and the catalyst still retained activity. Table 17 shows that the complex bis(2-(diphenylphosphino)ethyl)-aminedichlorocobalt(II) is capable of hydrolyzing ammonia borane when
15 added in multiple portions, and Table 18 shows the activity of the complex bis(2-(dicyclohexylphosphino)ethyl)aminedichloro-cobalt(II).

Example 106

Bis(2-(diisopropylphosphino)ethyl)aminedichlorocobalt(II) $[CoCl_2\{NH(CH_2CH_2P^iPr_2)_2\}]$ vs. *bis(2-(diisopropylphosphino)ethyl)aminedibromonickel(II)* $[NiBr_2\{NH(CH_2CH_2P^iPr_2)_2\}]$ catalyzed ammonia borane hydrolysis with
20 standardized conditions (25.0 °C)



a) *Bis(2-(diisopropylphosphino)ethyl)aminedichlorocobalt(II)*: 6.8 mg
25 (0.0156 mmol) of bis(2-(diisopropylphosphino)ethyl)aminedichlorocobalt(II) in


ca. 3 ml of tetrahydrofuran was added to 80 ml of a 1:1 mixture of tetrahydrofuran and water (equilibrated in a 25.0 °C water bath for five minutes). 500.2 mg of ammonia borane was added and the hydrogen evolution was measured.

- 5 *b) Bis(2-(diisopropylphosphino)ethyl)aminedibromonickel(II)*: 8.0 mg of bis(2-(diisopropylphosphino)ethyl)aminedibromonickel(II) was dissolved in 40 ml of water and 40 ml of tetrahydrofuran and placed in a 500 ml three-necked flask. The vessel was placed in a 25.0 °C water bath and allowed to equilibrate for five minutes. 498.4 mg of ammonia borane was added and the hydrogen evolution was measured. The results are shown in Table 19.

The complex bis(2-(di-iso-propylphosphino)ethyl)aminedibromonickel(II) was slightly less active than bis(2-(diisopropylphosphino)ethyl)aminedichlorocobalt(II).

15 Example 107

Bis(2-(diisopropylphosphino)ethyl)aminedichlororuthenium(II) dimer catalyzed ammonia borane hydrolysis at 40 °C




- 20 A 1 ml sample of a 6.8 mg/ml solution of bis(2-(diisopropylphosphino)-ethyl)aminedichlororuthenium(II) dimer was added to 80 ml of a 1:1 mixture of tetrahydrofuran/water. The flask was sealed and connected to an inverted 2000 ml graduated cylinder, and then placed in a water bath at ca. 40 °C and the temperature was allowed to stabilize for 5 minutes. Ammonia borane (0.5013 g, 16.2 mmol) was added to the mixture and the hydrogen volume was recorded at one minute intervals. The results are shown in Table 20.

25 The complex bis(2-(diisopropylphosphino)ethyl)aminedichlororuthenium(II) dimer was tested under the standardized conditions. The activity of the catalyst is quite high but is lower than the iridium standard bis(2-(di-tertiarybutylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III).

Example 108

2,2'-Bis(diphenylphosphino)-1,1'-binaphthyl 2-(diphenylphosphino)-ethanaminedichlororuthenium(II) $[Ru(binap)(H_2NCH_2CH_2PPh_2)Cl_2]$ catalyzed ammonia borane hydrolysis




A sample of 6 mg (0.0059 mmol) of 2,2'-bis(diphenylphosphino)-1,1'-binaphthyl 2-(diphenylphosphino)ethanaminedichlororuthenium(II) was dissolved in 20 ml of a 1:1 mixture of tetrahydrofuran and water. The flask was sealed and connected to an inverted 2000 ml graduated cylinder, and then placed in a water bath at ca. 40 °C and the temperature was allowed to stabilize for 5 minutes. Ammonia borane was added to the mixture in ca. 1.0 g (0.0324 mol) portions. The first five runs were performed under an argon atmosphere and the last run was performed in air. The results are shown in Table 21.

A ruthenium diphosphine aminophosphine complex 2,2'-bis(diphenylphosphino)-1,1'-binaphthyl 2-(diphenylphosphino)ethanamine-dichlorideruthenium(II) was also tested. As indicated in Table 21, ammonia borane can be added repeatedly with the catalyst retaining significant activity over time.

Example 109

1,3-Bis((ditertiarybutylphosphino)methyl)benzenecarbonylchloro-ruthenium(II) catalyzed ammonia borane hydrolysis




A 7.8 mg (0.0140 mmol) sample of 1,3-bis((ditertiarybutylphosphino)methyl)benzenecarbonylchlororuthenium(II) was dissolved in 80 ml of 1:1 tetrahydrofuran/water and the reaction vessel was placed in a water bath at 25.0 °C. 500.3 mg of ammonia borane was added and the hydrogen evolution was measured. The results are shown in Table 22.

The activity of the 'PCP pincer complex 1,3-bis((ditertiarybutylphosphine)methyl)benzenecarbonylchlorideruthenium(II) towards ammonia borane hydrolysis was determined and was found to be of a similar magnitude to bis(2-(dicyclohexylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III).

Example 110

Catalytic ammonia borane hydrolysis by catalyst derived from bis(2-(ditertiarybutylphosphino)ethyl)amine and trichlorooxybis(triphenylphosphine)-rhenium(V)



Rhenium catalyzed ammonia borane hydrolysis: 10 ml of tetrahydrofuran and 10 ml of water were added to 22 mg of the material formed in the reaction of trichlorooxybis(triphenylphosphine)rhenium(V) with bis(dialkylphosphino)ethylamine (where alkyl = tertiarybutyl or isopropyl) above. 54 mg (1.749 mmol) of ammonia borane was added and the hydrogen evolution was recorded. A black solid appeared in the reaction mixture after ca. 14 minutes. The results are shown in Table 23.

Example 111


Solvent effects upon bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) $[\text{Ir}(\text{H})(\text{Cl})(\text{C}_8\text{H}_{13})\{\text{NH}(\text{CH}_2\text{CH}_2\text{P}^t\text{Bu}_2)_2\}]$ catalyzed ammonia borane hydrolysis or solvolysis under pressure

These reactions were carried out in a similar fashion and only the tetrahydrofuran/water sample is described: (a) A 1.980 g (0.641 mol) sample of ammonia borane was added to 150 ml of a 1:1 mixture of tetrahydrofuran/water in a ca. 600 ml Parr bomb. The bomb was sealed and sealed and the solution was pressurized to 24 psi with argon and then vented to atmospheric pressure (this process was repeated four times). A 1.03 mg (1 ml of a 1.03 mg/ml tetrahydrofuran solution, 1.5×10^{-3} mmol) of bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) was added via syringe and then the vessel was sealed and the gas pressure was measured as a function of time. (b) For the ethanol/water run the ammonia borane mass was 2.0010 g (0.0648 mol) and the catalyst mass was 1.02 mg (1.5×10^{-3} mmol). (c) For the 100% ethanol run the ammonia borane mass was 1.999 g (0.0648 mol) and the catalyst mass was 1.0 mg (1.4×10^{-3} mmol). The results are shown in Table 24.

Catalytic ammonia borane hydrolysis under pressure was investigated using bis(2-(ditertiarybutylphosphine)ethyl)aminechlorocyclooctenylhydrido-iridium(III) as the catalyst. The ethanol/water (1:1) and tetrahydrofuran/water (1:1) runs afforded similar results. In absolute ethanol the reaction proceeded faster than in either ethanol/water (1:1) or tetrahydrofuran/water (1:1).

Table 25 provides a summary of the catalysts tested and their respective catalytic activity with respect to ammonia borane hydrolysis.

Example 112: Effect of alcohol solvents on the production of hydrogen from ammonia borane



Experimental procedure:

An 80 ml sample of the solvent was added to a 500 ml 3-necked flask and was heated to ca. 40°C for 5 minutes. An L-shaped solid addition tube containing ca. 500 mg of ammonia borane was connected to the flask and then ca. 1 mg (1 ml of a 1 mg/ml solution of the catalyst in the appropriate

solvent) of the catalyst bis(2-(di-tert-butylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) was added. The flask was sealed and was then inverted several times to add the ammonia borane to the reaction mixture. The gas volume was then recorded
5 at one minute intervals.

a) Solvent = 100 % ethanol. Amount of ammonia borane: 500.3 mg (16.21 mmol); amount of bis(2-(di-tert-butylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III): 1.00 mg (0.0014 mmol); T = 40.0 °C.

10 b) Solvent = 50 % ethanol, 50 % water. Amount of ammonia borane: 500.0 mg (16.20 mmol); amount of bis(2-(di-tert-butylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III): 0.99 mg (0.0014 mmol); T = 40.0 °C.

15 c) Solvent = 100 % n-butanol. Amount of ammonia borane: 501.7 mg (16.25 mmol); amount of bis(2-(di-tert-butylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III): 1.03 mg (0.0015 mmol); T = 40.0 °C.

d) Solvent = 50 % n-butanol, 50 % water. Amount of ammonia borane 500.7 mg (16.22 mmol); amount of bis(2-(di-tert-butylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III): 0.98 mg (0.0014 mmol); T = 41.0 °C.

20 e) Solvent = 100 % isopropanol. Amount of ammonia borane: 503.3 mg (16.30 mmol); amount of bis(2-(di-tert-butylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III): 1.02 mg (0.0015 mmol); T = 40.7 °C.

25 f) Solvent = 75% isopropanol, 25% water. Amount of ammonia borane: 499.9 mg (16.19 mmol); amount of bis(2-(di-tert-butylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III): 1.00 mg (0.0014 mmol); T = 41.0 °C.

30 g) Solvent = 50% isopropanol, 50% water. Amount of ammonia borane: 500.0 mg (16.20 mmol); amount of bis(2-(di-tert-butylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III): 1.02 mg (0.0015 mmol); T = 42.0 °C.

h) Solvent = 25 % isopropanol, 75 % water. Amount of ammonia borane: 500.8 mg (16.22 mmol); amount of bis(2-(di-tert-

butylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III): 0.99 mg (0.0014 mmol); T = 41.0 °C.

i) Solvent = 100 % methanol. Amount of ammonia borane: 502.8 mg (16.29 mmol); amount of bis(2-(di-tert-butylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III): 1.00 mg (0.0014 mmol); T = 40.3 °C.

j) Solvent = 75 % methanol, 25 % water. Amount of ammonia borane: 502.7 mg (16.28 mmol); amount of bis(2-(di-tert-butylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III): 1.06 mg (0.0015 mmol); T = 40.0 °C.

k) Solvent = 50 % methanol, 50 % water. Amount of ammonia borane: 499.6 mg (16.18 mmol); amount of bis(2-(di-tert-butylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III): 1.07 mg (0.0015 mmol); T = 40.0 °C.

Results:

The effect of n-butanol concentration in bis(2-(di-tert-butylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) catalyzed hydrogen generation (40 °C) is shown in Figure 16.

The effect of isopropanol concentration in bis(2-(di-tert-butylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III) catalyzed hydrogen generation (40 °C) is shown in Figure 17.

The effect of methanol concentration in bis(2-(di-tert-butylphosphino)ethyl)aminechlorocyclooctenyl-hydrido-iridium(III) catalyzed hydrogen generation (40 °C) is shown in Figure 18.

While the present disclosure has been described with reference to what are presently considered to be the preferred examples, it is to be understood that the disclosure is not limited to the disclosed examples. To the contrary, the disclosure is intended to cover various modifications and equivalent arrangements included within the spirit and scope of the appended claims.

All publications, patents and patent applications are herein incorporated by reference in their entirety to the same extent as if each individual publication, patent or patent application was specifically and individually indicated to be incorporated by reference in its entirety. Where a

term in the present application is found to be defined differently in a document incorporated herein by reference, the definition provided herein is to serve as the definition for the term.

TABLE 1: Bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) catalyzed ammonia borane hydrolysis at 25 °C.

Time (min)	Vol H ₂ (run 1, ml)	Vol H ₂ (run 2, ml)	Vol H ₂ (run 3, ml)
0	0	0	0
1	98	240	240
2	285	490	510
3	515	675	710
4	705	800	835
5	830	860	900
6	890	900	920
7	915	915	925
8	920	920	925
9	920	920	925
10	920	920	925

5

TABLE 2: Bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) catalyzed ammonia borane hydrolysis at 40 °C.

Time (min)	Run 1 (vol H ₂ , ml)	Run 2 (vol H ₂ , ml)	Run 3 (vol H ₂ , ml)
0	0	0	0
1	120	165	115
2	290	345	255
3	440	485	380
4	565	605	485
5	670	710	570
6	745	765	645
7	810	810	710
8	855	850	760
9	890	870	800
10	910	895	830
11	925	905	830

10

TABLE 3: Effect of ammonia borane purity in bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) catalyzed ammonia borane hydrolysis at 40 °C.

Time (min)	Vol (ml, std 1)	Vol (ml, std 2)	Vol (ml, pure ammonia borane 1)	Vol (ml, pure ammonia borane 2)	Vol (ml, impure ammonia borane 1)	Vol (ml, impure ammonia borane 2)
0	0	0	0	0	0	0
1	120	165	80	225	20	120
2	290	345	270	435	145	280
3	440	485	485	605	290	430
4	565	605	670	745	415	520
5	670	710	820	855	500	590
6	745	765	925	940	570	640
7	810	810	1000	1005	610	670
8	855	850	1040	1050	640	690
9	890	870	1070	1080	650	700
10	910	895	1085	1110	660	710

5

TABLE 4: Solvent comparison (diglyme, triglyme or tetrahydrofuran) in bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) catalyzed ammonia borane hydrolysis at 25 °C.

Time (min)	Vol (ml, std 1)	Vol (ml, std 2)	Vol (ml, diglyme 1)	Vol (ml, diglyme 2)	Triglyme (ml, run 2)
0	0	0	0	0	0
1	120	165	100	182	40
2	290	345	325	378	75
3	440	485	522	535	115
4	565	605	665	660	155
5	670	710	765	752	195
6	745	765	832	820	235
7	810	810	875	865	272
8	855	850	905	895	310
9	890	870	920	920	345
10	910	895	925	925	380

10

TABLE 5: Solvent comparison (ethanol vs. tetrahydrofuran) in bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) catalyzed ammonia borane hydrolysis at 40 °C.

5

Time (min)	Vol (ml, std1)	Vol (ml, std2)	Vol (ml, std 3)	Vol (ml, EtOH 1)	Vol (ml, EtOH 2)	Vol (ml, EtOH 3)
0	0	0	0	0	0	0
1	120	165	115	90	160	120
2	290	345	255	240	320	260
3	440	485	380	400	460	390
4	565	605	485	540	580	500
5	670	710	570	660	670	590
6	745	765	645	740	750	670
7	810	810	710	820	810	745
8	855	850	760	870	860	800
9	890	870	800	915	890	850
10	910	895	830	940	920	890
11	925	905	830	960	940	920

TABLE 6: Effect of ethanol concentration on rate of bis(2-(ditertiarybutylphosphino)ethyl)aminechlorocyclooctenylhydrido-iridium(III) [Ir(H)(Cl)(η^1 -C₈H₁₃){NH(CH₂CH₂P^tBu₂)₂}] catalyzed ammonia borane hydrolysis at 40 °C.

10

Time (min)	Std run 1	25% ethanol	19% ethanol	12.5% ethanol	75% ethanol	100% ethanol
0	0	0	0	0	0	0
1	120	150	100	100	180	110
2	290	320	200	200	480	350
3	440	460	300	300	740	710
4	565	580	380	380	900	1050
5	670	660	460	440	1020	1160
6	745	740	530	510	1080	1180
7	810	800	600	580	1120	1180
8	855	850	660	620	1140	1180
9	890	900	720	680	1160	1180
10	910	920	780	720	1160	1180
11	925	960	820	760	1160	1180

TABLE 7: Effect of added inorganic salts (i.e. sodium chloride, lithium chloride or tetraethyl ammonium chloride) in bis(2-(ditertiarybutylphosphino)ethyl)-aminechlorocyclooctenylhydrido-iridium(III) $[\text{Ir}(\text{H})(\text{Cl})(\eta^1\text{-}$

5 $\text{C}_8\text{H}_{13})\{\text{NH}(\text{CH}_2\text{CH}_2\text{P}^t\text{Bu}_2)_2\}$ catalyzed ammonia borane hydrolysis.

Time (min)	Vol (ml, std. 1)	Vol (ml, NaCl)	Vol (ml, LiCl)	Vol (ml, Et ₄ NCl)
0	0	0	0	0
1	120	0	90	50
2	290	10	210	180
3	440	20	330	320
4	565	25	430	445
5	670	35	505	550
6	745	40	565	640
7	810	50	605	710
8	855	60	640	755
9	890	65	665	790
10	910	75	680	810

TABLE 8: Effect of hydrogen (structure I) vs. methyl (structure II) substituents on nitrogen in bis(2-(ditertiarybutylphosphino)ethyl)amine type iridium complexes in catalytic ammonia borane hydrolysis at 40 °C.

10

Time (min)	Structure I			Structure II		
	Vol (ml, std 1)	Vol (ml, std 2)	Vol (ml, std 3)	Vol (ml, run 1)	Vol (ml, run 2)	Vol (ml, run 3)
0	0	0	0	0	0	0
1	120	165	115	40	80	80
2	290	345	255	125	150	135
3	440	485	380	210	220	190
4	565	605	485	295	280	250
5	670	710	570	370	340	300
6	745	765	645	435	410	350
7	810	810	710	495	500	450
8	855	850	760	550	550	495
9	890	870	800	605	595	540
10	910	895	830	655	605	580
11	925	905	830	700	630	620

15

20

TABLE 9: Bis(2-(diadamantylphosphino)ethyl)aminechlorodihydroiridium(III) catalyzed ammonia borane hydrolysis at 25 °C.

Time (min)	Vol H ₂ (ml, std. 1)	Vol H ₂ (ml, run 1)	Vol H ₂ (ml, run 2)	Vol H ₂ (ml, run 3)
0	0	0	0	0
1	220	285	255	240
2	535	510	490	490
3	710	625	635	675
4	770	680	715	800
5	790	690	745	860
6	790	700	745	900

5

TABLE 10: Bis(2-(diadamantylphosphino)ethyl)aminechlorodihydroiridium(III) catalyzed ammonia borane hydrolysis at 40 °C.

Time (min)	Vol (std 1 ml)	Vol (ml, run 1)	Vol (ml, run 2)	Vol (ml, run 3)
0	0	0	0	0
1	120	70	55	65
2	290	165	130	110
3	440	255	200	160
4	565	340	270	210
5	670	415	310	250
6	745	470	355	285
7	810	525	395	320
8	855	560	420	350
9	890	590	445	375
10	910	605	465	400

10

TABLE 11: Bis(2-(dicyclohexylphosphino)ethyl)aminechlorodihydroiridium(III) catalyzed ammonia borane hydrolysis at 25 °C.

Time (min)	Vol H ₂ (ml, std. 1)	Vol H ₂ (ml, run 1)
0	0	0
1	220	15
2	535	25
3	710	40
4	770	55
5	790	70
6		85
7		100
8		115
9		125
10		140

15

TABLE 12: Bis(2-(dicyclohexylphosphino)ethyl)aminechlorodihydrido-iridium(III) catalyzed ammonia borane hydrolysis at 40 °C.

Time (min)	Vol H ₂ (ml, std. 1)	Vol H ₂ (ml, run 1)
0	0	0
1	120	10
2	290	22
3	440	45
4	565	65
5	670	80
6	745	100
7	810	115
8	855	130
9	890	145
10	910	160
11	925	170
12		185
13		195
14		207
15		220
16		230
17		240
18		250
19		260
20		270

5

TABLE 13: 2,6-Bis((diisopropylphosphino)methyl)pyridinedichlorohydrido-iridium(III) catalyzed ammonia borane hydrolysis at 25 °C.

Time (min)	Volume H ₂ (ml)
0	0
1	10
2	15
3	20
4	25
5	30
6	35
7	40
8	42
9	45
10	50
15	65
30	150

10

TABLE 14: Catalytic ammonia borane hydrolysis by catalyst derived from bis(2-(diisopropylphosphino)-4-methylphenyl)amine and chlorobis(cyclooctene)iridium(I) dimer.

Time (min)	Vol (ml)
0	0
1	10
2	30
3	45
4	60
5	75
6	80
7	90
8	100
9	105
10	110

TABLE 15: Bis(2-(ditertiarybutylphosphino)ethyl)amine-2,4-pentanedionaterhodium(I) catalyzed ammonia borane hydrolysis at 40 °C.

Time (min)	Volume H ₂ (ml)
0	0
1	20
2	25
3	35
4	40
5	40
6	40
7	45
8	55
9	60
10	65
11	75
12	80
13	90
14	100
15	115
16	120
17	125
18	135
20	150
22	165
27	200
30	225
40	285

TABLE 16: Bis(2-(diisopropylphosphino)ethyl)aminedichlorocobalt(II) [Co{HN(CH₂CH₂PⁱPr₂)₂}Cl₂] catalyzed ammonia borane hydrolysis at 40 °C.

5

Time (min)	Total Vol. H ₂ (ml)	Amount ammonia borane	Time (min)	Total Vol. H ₂ (ml)	Amount ammonia borane
0	0	2.423 g	9.5	10940	
0.5	125		10	11160	
1	688		10.5	11400	
1.5	2888		11	11587	
2	5250		11.5	11775	
3	6010	954 mg	12	11900	
3.5	6625		12.5	12000	
4	6925		13.5	12150	
4.5	7488	980 mg	14	12338	960 mg
5	8445		14.5	12713	
5.5	8738		15	13030	
6	8800		15.5	13290	
6.5	9040	880 mg	16	13525	
7	9550		16.5	13650	
7.5	10050		17	13750	
8	10200		17.5	13800	
8.5	10400		18	13850	
9	10640	955 mg	19	14000	

TABLE 17: Bis(2-(diphenylphosphino)ethyl)aminedichlorocobalt(II) [Co{HN(CH₂CH₂PPh₂)₂}Cl₂] catalyzed ammonia borane hydrolysis (41 °C).

Time (min)	Total Vol H ₂ (ml)	Amount Ammonia Borane
0	0	
0.5	2.4	48 mg
1	10.6	
1.5	28.8	
2	54.6	
2.5	76	
3	80.4	
3.5	81.1	
4	81.2	
4.5	81.4	
5	81.5	
5.5	118.5	
6	146	49 mg
6.5	155.7	
7	159	
7.5	159.9	
8	160.3	
8.5	160.7	
9	160.8	
10.5	223.9	
11	229.6	
11.5	232.2	
12	233.5	
12.5	234.2	
13	234.6	

Time (min)	Total Vol H ₂ (ml)	Amount Ammonia Borane
13.5	234.8	
14	235	
14.5	264	
15	277.4	51 mg
15.5	291.8	
16	300.2	
16.5	305	
17	307.7	
17.5	309.3	
18	310.1	
18.5	310.9	
19	311.2	
19.5	319.3	
20	331.6	55 mg
20.5	342.4	
21	351.5	
21.5	359.4	
22	365.4	
22.5	370.7	
23	375	
23.5	378.8	
24	381.9	
25	386.6	
26	390	
29	396.1	

TABLE 18: Bis(2-(dicyclohexylphosphino)ethyl)aminedichlorocobalt(II) [CoCl₂{NH(CH₂CH₂PCy₂)₂}] catalyzed ammonia borane hydrolysis utilizing standard 40 °C conditions.

Time (min)	Vol (ml)
0	0
1	15
2	20
3	30
4	30
5	40
6	40
7	42
8	45
9	50
10	55

5

TABLE 19: Bis(2-(diisopropylphosphino)ethyl)aminedichlorocobalt(II) [CoCl₂{NH(CH₂CH₂PⁱPr₂)₂}] vs. bis(2-(diisopropylphosphino)ethyl)aminedibromonickel(II) [NiBr₂{NH(CH₂CH₂PⁱPr₂)₂}] catalyzed ammonia borane hydrolysis with standardized conditions (25.0 °C).

10

Time (min)	Vol H ₂ (ml, cobalt)	Vol H ₂ (ml, nickel)
0	0	0
1	5	0
2	10	5
3	15	5
4	20	10
5	30	12
6	40	20
7	55	25
8	62	30
9	75	35
10	85	50
11	100	55
12	110	65
13	120	70
14	130	80
15	140	90
16	145	95
17	155	100
18	163	110
19	175	112
20	180	120
25	220	140

TABLE 20: Bis(2-(diisopropylphosphino)ethyl)aminedichlororuthenium(II) dimer vs. iridium standard catalyzed ammonia borane hydrolysis at 40 °C.

Time (min)	Vol H ₂ (std 1)	Vol H ₂ (std 2)	Vol H ₂ (std 3)	Vol H ₂ (Ru complex)
0	0	0	0	0
1	120	165	115	5
2	290	345	255	35
3	440	485	380	70
4	565	605	485	120
5	670	710	570	165
6	745	765	645	180
7	810	810	710	220
8	855	850	760	260
9	890	870	800	300
10	910	895	830	340
11	925	905	830	380

TABLE 21: 2,2'-Bis(diphenylphosphino)-1,1'-binaphthyl 2-(diphenylphosphino)ethanaminedichlororuthenium(II) [Ru(binap)(H₂NCH₂CH₂PPh₂)Cl₂] catalyzed ammonia borane hydrolysis.

Time (min)	Volume (ml)
0	0
1	60
2	210
3	570
4	1540
5	1960
6	2000
7	2110
8	2430
9	2920
10	3550
11	3960
12	4200
13	4630
14	5230
15	5775
16	6095
17	6625
18	7255
19	7720
20	7960
21	8100
22	8450
23	8740
24	8950
25	9230
27	9645
28	9755
29	9855
30	9900
32	10025
33	10130
34	10315
35	10620
36	11060
37	11490
38	11780
39	11900

TABLE 22: 1,3-Bis((ditertiarybutylphosphino)methyl)benzenecarbonylchloro-ruthenium(II) catalyzed ammonia borane hydrolysis.

Time (min)	Vol H ₂ (ml)
0	0
1	2
2	5
3	15
4	20
5	25
6	30
7	35
8	40
9	40
10	45
11	45
12	50
13	50
14	55
15	55
16	59
17	60
18	60
19	60
20	62
25	80

5

TABLE 23: Catalytic ammonia borane hydrolysis by catalyst derived from bis(2-(ditertiarybutylphosphino)ethyl)amine and trichlorooxybis(triphenylphosphine)rhenium(V) (40 °C).

10






Time(min)	Volume (ml)
0	0
1	6
2	7.8
3	9.2
4	10.6
5	12.5
6	14.1
7	15.6
8	17.4
9	18.9
10	20.8
15	28.7








TABLE 24: Solvent effects on bis(2-di-tert-butylphosphine)ethyl)aminechlorocyclooct-1-enyldihydrido-iridium(III) catalyzed ammonia borane hydrolysis under pressure at 40°C.








Time (min)	THF/Water (psi)	Ethanol/Water (psi)	Ethanol (psi)
1	5	7.5	5
2	12.5	20	11
3	19	25	20
4	26	35	32
5	32.5	42	42
6	39	48	52
7	45	53	63
8	51	58	72
9	56	62	80
10	61	65	87
11	66	68	92
12	71	73	96
13	73.5	75	100
14	77.5	78	102
15	81	83	102
16	83	84	103
17	85.5	85	105
18	88	87	105
19	91	87	105
20	92	90	105
21	94	92	105
22	95	93	105
23	97	94	105
24	98	95	105
25	98.5	96	105
26	99.5	96	105
27	100	97	105
28	101	98	105
29	102	99	105
30	103	100	105








TABLE 25: Summary of Catalysts and Catalytic Ammonia Borane Hydrolysis. Note that low activity = $\leq$ ca. 10 ml/min; moderate activity = 10 – 50 ml/minute, high activity = $\geq$ ca. 50 ml/minute.





Catalyst	NH_3BH_3 / water
	Moderate hydrogen evolution
	Excellent hydrogen evolution
	Active
$\text{R} = \text{iPr}, \text{tBu}, \text{Ph}$	Moderate hydrogen evolution
	Moderate hydrogen evolution
	Good hydrogen evolution

	Good activity
	Good activity
 R = iPr, Ph	Moderate
	Hydrogen evolution
$(\text{Ph}_3\text{P})_3\text{RuCl}_2$	Good hydrogen evolution, deposits black solid slowly.
 R = iPr, Ph	Moderate

 Ar = para-C₆H₄CH₃	Hydrogen evolution
	Moderate activity
 R = iPr, tBu	Moderate hydrogen formation, deposits black solid.
 R = iPr, tBu	Active, deposits black solid
	Moderate hydrogen evolution, black solid deposited
	Moderate hydrogen evolution, deposits black solid.
	Moderate hydrogen evolution, deposits black solid.

	Excellent hydrogen evolution, long lifetime.
	Excellent activity, long lifetime
	Moderate hydrogen evolution, long lifetime.
	Good activity
	Moderate hydrogen evolution
	Moderate activity
	Excellent hydrogen evolution

	Excellent hydrogen evolution
	Moderate hydrogen evolution
	Hydrogen evolution
	Hydrogen evolution
	Moderate hydrogen evolution
	Good hydrogen evolution
	Excellent hydrogen evolution

	Moderate activity
	Moderate hydrogen evolution, black solid deposited
	Good hydrogen evolution, short lifetime
(Ph ₃ P) ₂ NiCl ₂	Moderate hydrogen evolution, deposits black solid in air.
Pd(PPh ₃) ₄	Moderate hydrogen evolution, deposits black solid in air
	Moderate hydrogen evolution

WE CLAIM:

1. A process for the production of hydrogen comprising:
 - (a) contacting a solution comprising at least one homogeneous
5 ligand-stabilized metal catalyst with at least one compound of the formula I,
$$R^1R^2HNBHR^3R^4 \quad (I),$$
in a solvent under conditions for the solvolysis of the compound of formula (I) to form a homogeneous solution,
10 wherein R^1 , R^2 , R^3 and R^4 are each simultaneously or independently selected from H, branched or unbranched fluoro-substituted- C_{1-20} alkyl, branched or unbranched C_{1-20} alkyl and C_{6-14} aryl or any two of R^1 , R^2 , R^3 and R^4 are linked to form a branched or unbranched C_{2-10} alkylene, which together with the nitrogen and/or boron atoms to which they are
15 attached, forms a ring; and
 - (b) optionally collecting hydrogen produced in the solvolysis of the compounds of formula (I).
2. The process according to claim 1, wherein R^1 to R^4 are different.
20
3. The process according to claim 1 or 2, wherein R^1 , R^2 , R^3 and R^4 are each simultaneously or independently selected from H, branched or unbranched fluoro-substituted- C_{1-10} alkyl, branched or unbranched C_{1-10} alkyl, and C_{6-10} aryl or any two of R^1 , R^2 , R^3 and R^4 are linked to form a branched or
25 unbranched C_{2-6} alkylene, which together with the nitrogen and/or boron atoms to which they are attached, forms a ring.
4. The process according to any one of claims 1 to 3, wherein R^1 , R^2 , R^3 and R^4 are each simultaneously or independently selected from H, branched or unbranched fluoro-substituted- C_{1-6} alkyl, branched or unbranched C_{1-6} alkyl, and phenyl or R^1 and R^2 and/or R^3 and R^4 are linked to form a branched or
30 unbranched C_{2-6} alkylene, which together with the nitrogen atom and/or boron atom to which they are attached, forms a ring.

5. The process according to claim 1, wherein R^1 , R^2 , R^3 and R^4 are each H.

6. The process according to any one of claims 1 to 5, wherein the solution
5 is a mixture of water and a water miscible solvent.

7. The process according to claim 6, wherein the ratio by volume of water to the water miscible solvent is between about 90:10 to about 10:90.

10 8. The process according to claim 7, wherein the ratio by volume is 50:50.

9. The process according to claim 8, wherein the water miscible solvent is an ether or an alcohol.

15 10. The process according to claim 9, wherein the ether is tetrahydrofuran.

11. The process according to claim 9, wherein the alcohol is ethanol.

12. The process according to any one of claims 1 to 5, wherein the solution
20 is an alcohol.

13. The process according to claim 12, wherein the alcohol is a C_{1-10} alcohol.

25 14. The process according to claim 13, wherein the alcohol is a C_{1-4} alcohol.

15. The process according to claim 14, wherein the alcohol is ethanol, methanol, 1-propanol, 2-propanol, 1-butanol or 2-butanol.

30

16. The process according to claim 1, wherein the metal catalyst comprises an alkali metal.

17. The process according to claim 16, wherein the alkali metal is lithium (Li), sodium (Na), potassium (K), rubidium (Rb), cesium (Cs) or francium (Fr).

18. The process according to claim 1, wherein the metal catalyst
5 comprises an alkaline earth metal.

19. The process according to claim 18, wherein the alkaline earth metal is beryllium (Be), magnesium (Mg), calcium (Ca), strontium (Sr), barium (Ba) or radium (Ra).

10

20. The process according to claim 1, wherein the metal catalyst comprises a p-block metal.

15

21. The process according to claim 20, wherein the p-block metal is aluminum (Al), gallium (Ga), indium (In), tin (Sn), thallium (Tl), lead (Pb), or bismuth (Bi).

22. The process according to claim 1, wherein the metal catalyst comprises a d-block or transition metal.

20

23. The process according to claim 22, wherein the d-block or transition metal is scandium (Sc), titanium (Ti), vanadium (V), chromium (Cr), manganese (Mn), iron (Fe), cobalt (Co), nickel (Ni), copper (Cu), zinc (Zn), yttrium (Y), zirconium (Zr), niobium (Nb), molybdenum (Mo), technetium (Tc),
25 ruthenium (Ru), palladium (Pd), silver (Ag), cadmium (Cd), hafnium (Hf), tantalum (Ta), tungsten (W), rhenium (Re), osmium (Os), iridium (Ir), platinum (Pt), gold (Au) or mercury (Hg).

24. The process according to claim 23, wherein the transition metal is
30 ruthenium (Ru), cobalt (Co), nickel (Ni), rhodium (Rh) or iridium (Ir).

25. The process according to claim 1, wherein the metal catalyst comprises a lanthanide.

26. The process according to claim 25, wherein the lanthanide is lanthanum (La), cerium (Ce), praseodymium (Pr), neodymium (Nd), promethium (Pm), samarium (Sm), europium (Eu), gadolinium (Gd), terbium (Tb), dysprosium (Dy), holmium (Ho), erbium (Er), thulium (Tm), ytterbium (Yb) or lutetium (Lu).

27. The process according to claim 1, wherein the metal catalyst comprises an actinide.

28. The process according to claim 27, wherein the actinide is actinium (Ac), thorium (Th), protactinium (Pa), uranium (U), neptunium (Np), plutonium (Pu), americium (Am), curium (Cm), berkelium (Bk), californium (Cf), einsteinium (Es), fermium (Fm), mendelevium (Md), nobelium (No) or lawrencium (Lr).


29. The process according to claim 1, wherein the catalyst comprises one or more ligands having at least one co-ordinating atom.

30. The process according to claim 29, wherein the co-ordinating atom is phosphorous, nitrogen, oxygen, carbon, silicon, germanium, sulfur, selenium or arsenic.

31. The process according to claim 29, wherein the ligand comprises a phosphine, arsine, diphosphine, imine, pyridine, amine, carbene, aminophosphine, diamine, aminodiphosphine, diaminodiphosphine, dicarbene, aminocarbene, phosphinocarbene, alcohol, ether, aminoether, phosphinoether, aminoalcohol or aminothiol group.


32. The process according to claim 29, wherein the ligands are selected from, one or more of:

(a) phosphines of the formula (II):




which bidentate or tridentate and are chiral or achiral monodentate phosphine ligands in which R^5 , R^6 and R^7 are simultaneously or independently selected from unsubstituted or substituted C_{1-10} alkyl, unsubstituted or substituted C_{2-10} alkenyl, unsubstituted or substituted C_{3-10} cycloalkyl, unsubstituted or substituted C_{6-14} aryl, OR^8 and $N(R^8)_2$ and R^8 is simultaneously or independently selected from unsubstituted or substituted C_{1-10} alkyl, unsubstituted or substituted C_{2-10} alkenyl, unsubstituted or substituted C_{3-10} cycloalkyl, unsubstituted or substituted C_{6-14} aryl, or two of R^5 , R^6 , R^7 and R^8 are bonded together to form an unsubstituted or substituted ring having 4 to 8 atoms, including the phosphorous, nitrogen and/or oxygen atom to which said groups are bonded;

(b) bis(phosphino) bi-, tri- or tetradentate ligands of the formula (III):



wherein R^9 , R^{10} , R^{11} and R^{12} are, independently, as defined for R^5 , R^6 and R^7 , and Q^1 is selected from unsubstituted or substituted C_1-C_{10} alkylene and unsubstituted or substituted C_1-C_{10} alkenylene where adjacent or geminal substituents on Q^1 are joined together to form, including the atoms to which they are attached, one or more unsubstituted or substituted 5-14-membered monocyclic, polycyclic, heterocyclic, carbocyclic, saturated, unsaturated or metallocenyl ring systems, and/or one or more of the carbon atoms in Q^1 is optionally replaced with a heteromoiety selected from O, S, NH and $N(C_{1-6}alkyl)$ and Q^1 is chiral or achiral;

(c) bidentate ligands of the formula (IV):



wherein R^{13} and R^{14} are, independently, as defined for R^5 - R^7 , Q^2 is as defined for Q^1 , and R^{15} and R^{16} are independently selected from H, C_{6-14} aryl, C_1 -


alkyl and C₃₋₁₂cycloalkyl, with the C₆₋₁₄aryl and C₃₋₁₂cycloalkyl being optionally substituted;

(d) heterocyclic ligands of the formula (V):



which are bi- or tridentate ligands wherein Hy is unsubstituted or substituted aromatic or non-aromatic heterocycle containing from 3 to 10 atoms of which 1 to 3 are a heteromoiety selected from O, S, N, NH and NC₁₋₆alkyl with the remaining atoms being C and Q³ is as defined for Q¹;


(e) diaminophosphines of the formula (VI) or (VII):



wherein

R¹⁷-R²¹ are, independently, as defined for R¹⁵ and R¹⁶, R¹⁹ is as defined for R⁵ and Q⁴ and Q⁵ are as defined for Q¹;


(f) diamines of the formula VIII or IX:



wherein


R²²-R²⁴ are, independently, as defined for R¹⁵ and R¹⁶ and Q⁶ is as defined for Q¹;

(g) thiophenes of the formula (X):



which are bidentate, wherein T is unsubstituted or substituted thiophene and Q⁷ is as defined for Q¹; and

(h) amines of the formula (XI):



which are bidentate, wherein R^{25} is as defined for R^5 , R^6 or R^7 , S is sulphur and Q^8 is as defined for Q^1 .

5

33. The process according to any one of claims 1-32, wherein the process is performed at a temperature of between about 20°C to about 60°C.

34. The process according to claim 33, wherein the process is performed
10 at a temperature of 40°C.

35. The process according to claim 6, wherein the catalyst is dissolved in the mixture of water and the water miscible solvent to form a homogenous mixture.

15

36. The process according to claim 35, wherein the compound of formula I is added directly to the homogenous mixture.

37. The process according to claim 1, wherein the ligand-stabilized metal
20 catalyst is soluble in the solution.

38. The process according to claim 1, wherein the process is performed in an inert atmosphere.

25 39. The process according to claim 38, wherein the process is performed in an argon atmosphere.

40. A method for the hydrolysis of a compound of formula (I) as defined in claim 1 comprising contacting the compound of formula (I) with at least one
30 homogeneous ligand-stabilized metal catalyst in the presence of water under conditions for the hydrolysis of the compound of formula (I).

41. A method for the solvolysis of a compound of formula (I) as defined in claim 1 comprising contacting the compound of formula (I) with at least one homogeneous ligand-stabilized metal catalyst in the presence of a solvent under conditions for the solvolysis of the compound of formula (I).

5

42. A hydrogen generation system comprising at least one amine borane of the formula (I) as defined in claim 1, at least one homogeneous ligand-stabilized metal catalyst, and a solvolytic and/or hydrolytic solvent.

10 43. The hydrogen generation system according to claim 42, comprising a first compartment comprising the at least one amine borane of the formula (I), a second compartment comprising the at least one homogeneous ligand-stabilized metal catalyst, wherein the first or second compartment further comprises the solvent and a means for combining the contents of the first
15 compartment with the second compartment so that when the contents are combined, hydrogen is generated.

44. The hydrogen generation system according to claim 43, further comprising at least one flow controller to control a flow rate of the at least one
20 catalyst or the at least one amine borane.

45. The hydrogen generation system according to any one of claims 42-44, wherein said system is fluidly connected to a proton exchange membrane fuel cell (PEMFC).

25