Abstract

Method and device for the laser drilling of organic materials

For the laser drilling of organic materials, in particular for making blind holes in dielectric layers, a frequency-doubled Nd-vanadate laser with the following parameters is used:

pulse width	< 40 ns
pulse frequency	≥ 20 kHz
wavelength	= 532 nm.



162162



G00002