

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
6 January 2005 (06.01.2005)


PCT

(10) International Publication Number
WO 2005/000938 A1

- (51) International Patent Classification⁷: **C08G 63/00**
- (21) International Application Number:
PCT/US2004/014343
- (22) International Filing Date: 7 May 2004 (07.05.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
10/434,914 9 May 2003 (09.05.2003) US
10/748,394 5 May 2004 (05.05.2004) US
- (71) Applicant (for all designated States except US): **GENERAL ELECTRIC COMPANY** [US/US]; 1 River Road, Schenectady, NY 12345 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **BERZINIS, Albin, Peter** [US/US]; RR #7, Box 38AAA, Marietta, OH 45750 (US). **GAGGAR, Satish, Kumar** [US/US]; 204 Sunset Boulevard, Parkersburg, WV 26101 (US).
- (74) Agents: **WINTER, Catherine, J.** et al.; General Electric Company, 3135 Easton Turnpike W3C, Fairfield, CT 06828 (US).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: **IMPACT-MODIFIED COMPOSITIONS AND METHOD**



(57) Abstract: The present invention relates to a rubber modified thermoplastic resin composition comprising a discontinuous elastomeric phase dispersed in a rigid thermoplastic phase, wherein at least a portion of the rigid thermoplastic phase is grafted to the elastomeric phase, which is prepared by a method comprising the steps of. (a) polymerizing a mixture of monomers in a first stage in the presence of the elastomeric phase, at least one of which monomers is selected from the group consisting of vinyl aromatic monomers and at least one of which monomers is selected from the group consisting of monoethylenically unsaturated nitrile monomers, followed by (b) polymerizing one or more monomers in at least one subsequent stage in the presence of the elastomeric phase from (a), wherein the one or more monomers comprise at least one monomer selected from the group consisting of (C₁-C₁₂)alkyl- and aryl(meth)acrylate monomers. The method is also provided.