

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
27 May 2004 (27.05.2004)

PCT

(10) International Publication Number
WO 2004/044075 A2

(51) International Patent Classification⁷: **C09G**

(21) International Application Number:
PCT/US2003/034242

(22) International Filing Date: 29 October 2003 (29.10.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/425,690 12 November 2002 (12.11.2002) US
10/685,730 14 October 2003 (14.10.2003) US

(71) Applicant: **ATOFINA CHEMICALS, INC.** [US/US];
2000 Market Street, Philadelphia, PA 19103 (US).

(72) Inventors: **MARTYAK, Nicholas, M.**; 307 Hedgerow
Lane, Doylestown, PA 18901 (US). **CARROLL, Glenn**;
2437 Chestnut Avenue, Norristown, PA 19403 (US).

(74) Agents: **RUDMAN, Gilbert, W.** et al.; Atofina Chemicals,
Inc., 2000 Market Street, Philadelphia, PA 19103 (US).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,

CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC,
SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,
UG, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:

— as to applicant's entitlement to apply for and be granted a
patent (Rule 4.17(ii)) for all designations

Published:

— without international search report and to be republished
upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: **COPPER CHEMICAL MECHANICAL POLISHING SOLUTIONS USING SULFONATED AMPHIPROTIC AGENTS**

(57) Abstract: A family of slurries useful in modifying exposed surfaces of wafers for semiconductor fabrication are provided along with methods of modifying exposed surfaces of wafers for semiconductor fabrication utilizing such a family of working slurries, and semiconductor wafers. The slurries of the invention are a solution of initial components, the components comprising: a sulfonated zwitterion selected from 2-(N-Morpholino)ethanesulfonic acid, (3-[N-Morpholino])propanesulfonic acid, 2-[(2-Amino-2-oxoethyl)amino]ethanesulfonic acid, Piperazine-N, N'-bis(2-ethanesulfonic acid), 3-(N-Morpholino)-2-hydroxypropanesulfonic acid, N, N-Bis(2-hydroxyethyl)-2-aminoethanesulfonic acid, 3-(N-Morpholino)propanesulfonic acid, N-(2-Hydroxyethyl)piperazine-N'-(2-ethanesulfonic acid), N-Tris(hydroxymethyl)methyl-2 aminoethanesulfonic acid, 3-[N, N-Bis(2-hydroxyethyl)amino]-2-hydroxypropanesulfonic acid, 3-[N -Tris(hydroxymethyl)methylamino]- 2-hydroxypropanesulfonic acid, N-(2-hydroxyethyl)piperazine-N'-(2-hydroxypropanesulfonic acid), Piperazine-N, N'-bis(2-hydroxypropanesulfonic acid), N-(2-Hydroxyethyl)piperazine-N'-(3-propanesulfonic acid), N-Tris(hydroxymethyl)methyl-3-aminopropanesulfonic acid, 3-[(1,1 -Dimethyl 1- 2-hydroxyethyl)amino]-2-hydroxypropanesulfonic acid, 2-(N- Cyclohexylamino)ethanesulfonic acid, 3-(Cyclohexylamino)-2-hydroxy-1-propanesulfonic acid, 2-Amino-2-methyl-1-propanol, 3-(Cyclohexylamino)-1-propanesulfonic acid, an oxidizing agent; optionally, a passivating agent; optionally a chelating agent, optionally abrasive particles, optionally a surfactant, optionally a secondary buffering agent and water. The method of the invention comprises the steps of: a) providing a wafer comprising a first material having a surface etched to form a pattern and a second material deposited over the surface of the first material; b) contacting the second material of the wafer with abrasive in the presence of the working slurry; and c) relatively moving the wafer or polishing pad or both while the second material is in contact with the slurry and abrasive particles until an exposed surface of the wafer is planar and comprises at least one area of exposed first material and one area of exposed second material.

WO 2004/044075 A2