

A Waveguide



159159

FIELD OF THE INVENTION

The present invention relates to a waveguide.



G00002

BACKGROUND

Research on thin interconnect structures has been directed to reducing cost and reducing complexity in manufacturing, to attempt compete with printed circuitry. Development of thin interconnect structures for high data transfer is particularly tough due to problems with high frequency signals. Stability of Electro-Magnetic (EM) propagation, as well as consistent signal strength may be desirable for establishing effective data communication inside electronics devices.

SUMMARY

Here, a composite material is proposed to enable the production of waveguides having good EM wave confinement with low dissipation loss.

The invention relates to an architecture and method for directing travelling Electro-Magnetic (EM) waves by means of connecting a thin stripe between electronic integrated circuit (IC) chips on, particularly printed-circuit assembly. This invention aims to achieve high dielectric constant and low dielectric loss that are essential for high frequency interconnectivity.

In this method, a polymer-ceramic composite having controllable dielectric constant and low loss tangent is proposed. This material comprises fine powder of metal

oxide, mixed with dispersion solution of PolyTetraFluoroEthylene particles suspended in water. By thorough mixing, a slurry mixture can be generated at room condition.

Particularly, a formation of thin dielectric sheet is proposed using coating method to dispense viscous paste containing organic binder and ceramic powder. Its dielectric
5 characteristics are adjusted by the mixing ratio of ceramic content to attain high dielectric constant. This composite can be easily pressed or rolled to give uniform and consistent thin layer which may be sliced into desired patterns.

Such architecture of thin layer allows conformal surface contact on flat Printed Circuit Board (PCB). In this regard, the EM waves can be fed into thin layers and
10 propagate between IC components at different locations with minimum EM radiation and absorption in electronics devices.

The present invention aims to provide a method for focusing and confinement of EM communication signal in thin waveguides by tuning their dielectric behaviours at high frequency range.

15 In general terms, the invention proposes a uniformly developed thin sheet that can be cut or machined into specific patterns for attaching on PCB to improve the interconnectivity between IC components.

A second aspect, the invention provides a method to enable a low cost processing method for making narrow stripes with multiple bends which fit between IC
20 components, without modifying the production of PCB.

BRIEF DESCRIPTION OF THE DRAWINGS

One or more example embodiments of the invention will now be described, with reference to the following figures, in which:

FIG. 1 shows the proposed mixing of ceramic powder and polymeric binder.

FIG. 2 shows the proposed dispensing of composite slurry to form thin sheet.

FIG. 3 shows the schematic of composite sheet after polymerization.

FIG. 4 shows the proposed cutter assembly for composite sheet.

5 FIG. 5 shows the proposed cutting process of waveguide.

FIG. 6 shows the schematic of interconnect on PCB using waveguides.

DETAILED DESCRIPTION

In a high data transfer rate system, the material for interconnects plays an
10 important role in achieving stable and robust Electro-Magnetic (EM) propagation. When
the electronics assembly becomes smaller and more compact, the design of thin and
narrow interconnects between integrated circuit (IC) components may become more
difficult for high data volume.

Polymers are usually low in dielectric constant. A low dielectric constant may not
15 desirable in waveguides as it makes the focusing and confinement of EM wave
propagation less effective. However in liquid form, polymers may offer easier and
cheaper production using coating and printing processes.

Ceramic particles may be processed in a complex heat sintering process to form
a high dielectric constant medium. However, the process may be expensive.

20 In one embodiment, liquid polymer is used as a binder for ceramic particles. The
fine ceramic particles are glued to form a thin sheet by curing the polymer, which avoids
a complex heat sintering processes.

The liquid polymer-ceramic may comprises Metal Oxide powder 101, for example, Strontium Titanate (SrTiO_3), or Titanium Dioxide (TiO_2), is stirred into liquid polymer 102, for example, Poly-Tetra-Fluoro-Ethylene (PTFE), Poly-Styrene (PS) or Poly-Propylene (PP). The composite 103 is a viscous slurry with smooth texture, similar to paint, and carrying uniformly dispersed particles, which can be dispensed or coated to a desired mould.

The electrical behaviours of the mentioned ingredients are as follows:

Chemical	Dielectric Constant	Loss Tangent
Strontium Titanate	300	0.0050
Titanium Dioxide	100	0.0050
Poly-Tetra-Fluoro-Ethylene	2.5	0.0002

* Published at 1~10GHz

Next, as illustrated in FIG. 2, the mixture is dispensed onto a flat tray 201 with a containing depth of about 0.5mm ~ 1.0mm. The depth of the tray determines the thickness of the dielectric sheet. Likewise, the surface area of the desired sheet may be adjusted by the size of tray 201. Any excess from pouring the mixture 103 will overflow outside of the tray 201.

Then dispensed liquid mixture 103 in the tray 201 is transferred into a low-pressure chamber for degassing. For degassing purpose, the painted composite layer may be placed in a low pressure desiccator at the range 50~80kPa, for at least 5 hours. This helps to remove the air bubbles in the dispensed layer generated from the mixing process.

Thermal curing of the liquid mixture 103 is used to dry and polymerize the organic content in the binder. This is carried out at about 300-350°C for about 1 hour. Subsequently, the dried layer can be lifted off from the tray 201 as soon as it is cooled.

As in FIG. 3, this sheet 301 made of the composite material should inherit to some extent, the high dielectric constant of ceramic with low loss tangent.

Depending on the desired interconnect shape, a mechanical cutting assembly 400 can be customised. As shown in FIG. 4, in the case which 'Z'-shape is desired, the tailored cutting knife 401, together with steel slotted dies 402,403 are designed, according to the dimensions and shape of the desired waveguide. The composite sheet 301 is clamped between two steel blocks 402,403, positioned where the through patterned slots 404 in each block 403 were aligned. Following that, as in FIG. 5, the cutter knife 401 is pressed down through the slots 404 in the two steel blocks 402,403 sandwiching the composite sheet 301, and a waveguide interconnect 501 is ejected from the slot 404 at the base of the cutter assembly 400.

The waveguide interconnect 501 can be glued on PCB; as shown in FIG. 6, with both ends placed in contact with the IC chips or any other electronics components. The material properties of the composite should help to focus and retain the EM wave during the data transmission operations. The waveguide can be placed touching the IC chips, without any additional interface. Ideally, there should be minimum gap between the ends of waveguide and IC components.

While example embodiments of the invention have been described in detail, many variations are possible within the scope of the invention as will be clear to a skilled reader.

CLAIMS:

1. A method of fabricating a waveguide comprising:
providing a ceramic powder and polymer binder slurry,
forming the waveguide from the slurry.
2. The method in claim 1 further comprising forming a film from the slurry
3. The method in claim 2 further comprising curing the film
4. The method in claim 3 further comprising punching the waveguide from the cured film.
5. The method in any of the preceding claims wherein the ceramic powder is Strontium Titanate or Titanium Dioxide and the polymer binder is Poly-Tetra-Fluoro-Ethylene, Poly-Styrene or Poly-Propylene.
6. A waveguide produced according to the method of any one of the preceding claims.
7. An interconnect waveguide comprising a ceramic powder and polymer binder composite.
8. The waveguide in claim 7 wherein the dielectric constant of the composite is above 10.

9. The waveguide in claim 7 or 8 wherein the dielectric loss tangent of the composite is below 0.005.
- 5 10. The waveguide in any one of claims 7 to 9 wherein the ceramic powder is Strontium Titanate or Titanium Dioxide and the polymer binder is Poly-Tetra-Fluoro-Ethylene, Poly-Styrene or Poly-Propylene.
- 10 11. The ceramic powder in claim 8 wherein the dielectric constant is in the range 50 to 300.
12. The polymer binder in claim 9 wherein the dielectric loss tangent is below 0.001.
13. A PCB comprising a plurality of IC components connected by one or more
15 waveguides according to any one of the preceding claims.