

DESCRIPTION

[Title of Invention]

METHOD FOR MANUFACTURING GLASS SUBSTRATE FOR MAGNETIC
5 DISK

[Technical Field]

[0001] The present invention relates to a method for manufacturing a glass
substrate for a magnetic disk that includes processing for cutting out a glass
10 blank from a glass plate using a laser beam.

[Background Art]

[0002] Nowadays, to record data, hard disk apparatuses are used in personal
computers, notebook-sized personal computers, DVD (Digital Versatile Disc)
recording apparatuses, data centers for cloud computing, and the like. A
15 magnetic disk obtained by providing a magnetic layer on a glass substrate for a
magnetic disk, which is a disk-shaped non-magnetic material, is used in a hard
disk apparatus. The magnetic disk is incorporated into a DFH (Disk Flying
Height) type magnetic head that has a flying height of about 5 nm, for example.

[0003] In such a DFH type magnetic head, the flying height is short, and
20 accordingly attachment of minute particles etc., to main surfaces of the magnetic
disk is to be avoided. In order to suppress attachment of minute particles, it is
desirable to precisely polish not only main surfaces of a glass substrate but also
edge surfaces of the glass substrate to reduce surface roughness. Also, it is
desirable for a disk-shaped magnetic disk to have a high degree of roundness so
25 that the magnetic disk can stably rotate at a high speed.

[0004] In order to satisfy these requirements for magnetic disks, edge surface
polishing is performed to reduce the surface roughness of edge surfaces (an inner
edge surface and an outer edge surface) of a glass substrate for a magnetic disk
and improve the roundness.

30 A glass substrate for a magnetic disk is obtained by cutting a glass plate,

chamfering edge surfaces, polishing edge surfaces, grinding and polishing main surfaces, and washing the glass plate.

A technology for cutting out a glass blank from a glass plate using a laser beam, instead of performing scribing using a cutter and splitting, in the above-described cutting of a glass plate, is proposed (Patent Literature 1).

[0005] In the above-described technology, a plurality of defect lines (perforations) are formed by repeatedly causing the generation of a defect line (perforation) along a laser beam focal line of a pulsed laser beam within a glass plate by directing the laser beam focal line into the glass plate at a predetermined angle of incidence to the glass plate while moving the glass plate and the laser beam parallel to each other. At this time, cracks propagate between adjacent defect lines (perforations), and accordingly a glass blank having a desired shape can be cut out from the glass plate. The defect lines (perforations) are spaced apart from each other by a distance of 2 μm .

[Citation List]

[Patent Literature]

[0006] [PLT1]: JP 2017-511777A

[Summary of Invention]

[Technical Problem]

[0007] Although a disk-shaped glass blank can be manufactured from a glass plate using the above-described technology, the glass blank is cut out based on the defect lines (perforations), and accordingly portions of cross-sectional shapes of holes constituting the defect lines remain in edge surfaces of the obtained glass blank. Therefore, edge surface polishing needs to be performed to obtain a glass substrate for a magnetic disk that has a small surface roughness not only on the main surfaces but also on the edge surfaces from the obtained glass blank. Edge surface polishing takes a long time and is not preferable in terms of not only manufacturing efficiency but also manufacturing cost. It is preferable to perform cutting using a laser beam in such a manner that, even if edge surface polishing is performed, polishing time can be reduced when compared to that

required in conventional technologies, or the need for edge surface polishing can be eliminated.

[0008] Therefore, an object of the present invention is to provide a method for manufacturing a glass substrate for a magnetic disk including processing with
5 which it is possible to significantly reduce edge surface polishing time compared to that required in conventional technologies, and preferably, it is possible to cut out a glass blank that has an edge surface having a surface roughness and a roundness that eliminate the need for edge surface polishing, when the glass blank, from which the glass substrate for a magnetic disk is to be obtained, is
10 cut out from a glass plate using a laser beam.

[Solution to Problem]

[0009] If a disk-shaped glass blank is cut out based on a plurality of defect lines formed by perforating a glass plate as described above, an edge surface does not have a preferable shape that simultaneously satisfies requirements of the
15 surface roughness and the roundness.

On the other hand, a glass blank can be cut out by emitting a laser beam such that a focal position of the laser beam is located on a main surface of a glass plate to form defects on the main surface, and causing cracks to develop from the defects into the glass plate, but in this case as well, an edge surface does not
20 have a preferable shape that simultaneously satisfies requirements of the surface roughness and the roundness. The inventor of the present invention found that, in contrast, if a glass blank is cut out by forming defects inside a glass plate and causing cracks to develop from the defects toward both main surfaces of the glass plate, the surface roughness of an edge surface is small and
25 the degree of roundness is high.

Also, the inventor of the present invention found that, even if a glass blank does not have a shape that simultaneously satisfies requirements of the surface roughness of an edge surface and the roundness, if a laser beam is emitted toward a cut surface, i.e., a separation surface, of the glass blank from
30 the direction of a normal to the separation surface to melt glass in the vicinity

of the separation surface and form a chamfered surface on the glass blank, the separation surface of the glass blank formed through emission of the laser beam toward the separation surface has a small surface roughness and a high degree of roundness. Based on these facts, the inventor of the present invention
5 arrived at the following aspects of the present invention.

[0010] One aspect of the present invention is a method for manufacturing a glass substrate for a magnetic disk. The method includes:

separation processing in which a crack starting portion is formed inside a glass plate by moving a first laser beam relative to the glass plate such that a
10 focal position of the laser beam is located in an inner portion of the glass plate in a thickness direction thereof and the focal position forms a circle when viewed from a main surface of the glass plate, thereafter cracks are caused to develop from the crack starting portion toward main surfaces of the glass plate, and the glass plate is split to separate a glass blank from the glass plate, the glass blank
15 including a separation surface that has an arithmetic average surface roughness R_a smaller than $0.01\text{ }\mu\text{m}$ and a roundness not larger than $15\text{ }\mu\text{m}$; and

grinding/polishing processing in which grinding or polishing is performed on main surfaces of the glass blank.

[0011] It is preferable that the focal position is located at a distance within a
20 range of one third to two thirds of a thickness of the glass plate from a main surface of the glass plate.

[0012] It is also preferable that the focal position is located at a distance that is shorter than one third of a thickness of the glass plate from a main surface of the glass plate.

25 [0013] It is preferable that the method further includes chamfering processing for chamfering a corner portion that is formed by a main surface of the glass blank and the separation surface using a second laser beam of a different type from the first laser beam, the chamfering processing being performed between the separation processing and the grinding/polishing processing.

30 [0014] Another embodiment of the present invention is a method for

manufacturing a glass substrate for a magnetic disk. The method includes:

separation processing in which defects are intermittently formed on a circular separation boundary line that is defined on a main surface of a glass plate, by emitting a first laser beam while moving the first laser beam relative to the glass plate, a line-shaped defect is formed by connecting the formed defects, and a glass blank is separated from the glass plate;

chamfering processing in which a second laser beam of a different type from the first laser beam is emitted from a direction of a normal to a separation surface of the glass blank to form a chamfered surface on the separation surface and form a glass blank that has the separation surface having an arithmetic average surface roughness R_a smaller than $0.01\text{ }\mu\text{m}$ and a roundness not larger than $15\text{ }\mu\text{m}$; and

grinding/polishing processing in which at least one of grinding and polishing is performed on main surfaces of the glass blank.

[0015] It is preferable that a thickness of the glass plate is not larger than 0.6 mm .

Also, it is preferable that a thickness of the glass blank after the grinding/polishing processing is smaller than 0.52 mm .

[0016] It is preferable that the second laser beam is a pulsed laser beam that has a pulse width not larger than 10^{-12} seconds.

[0017] It is preferable that, in the grinding/polishing processing, at least one of grinding and polishing is performed on the main surfaces of the glass blank while maintaining the roundness of the glass blank obtained through the separation processing and a surface roughness of at least a portion of the separation surface.

[0018] It is preferable that the roundness is 0.1 to $15\text{ }\mu\text{m}$.

[Advantageous Effects of the Invention]

[0019] According to the above-described method for manufacturing a glass substrate for a magnetic disk, it is possible to significantly reduce edge surface polishing time compared to that required in a conventional technology, and

preferably, it is possible to cut out a glass blank that has an edge surface having a surface roughness and a roundness that eliminate the need for edge surface polishing.

[Brief Description of Drawings]

5 [0020] FIG. 1(a) is a perspective view of one example of a glass substrate for a magnetic disk manufactured in the present embodiment, and FIG. 1(b) is a diagram showing one example of a cross section of an outer edge surface of the glass substrate for a magnetic disk shown in FIG. 1(a).

FIGS. 2(a) and 2(b) are diagrams showing one example of a method for
10 cutting out a glass blank from a glass plate according to the present embodiment.

FIG. 3 is a diagram showing one example of the method for cutting out a glass blank from a glass plate according to the present embodiment.

FIG. 4 is a diagram showing one example of chamfering processing performed in the present embodiment.

15 FIG. 5 is a diagram showing one example of chamfered surface forming processing performed in the present embodiment.

[Description of Embodiments]

[0021] In a method for manufacturing a glass substrate for a magnetic disk according to the present embodiment, the glass substrate for a magnetic disk
20 is manufactured by cutting out a disk-shaped glass blank from a glass plate along an inner circle and an outer circle that are concentric to each other, chamfering corner portions that connect edge surfaces (separation surfaces) and main surfaces of the obtained disk-shaped glass blank, and then grinding and polishing the main surfaces.

25 Here, in the case of a glass blank that is cut out from a glass plate using a laser beam in a conventional manner, an arithmetic average roughness Ra, which is a surface roughness, and roundness of edge surfaces (an inner edge surface and an outer edge surface), i.e., separation surfaces, of the glass blank do not fall within required ranges for edge surfaces of a glass substrate for a
30 magnetic disk. Although the arithmetic average roughness Ra can be adjusted

to fall within a required range by performing edge surface polishing on the glass blank cut out in a conventional manner, edge surface polishing takes a long time and manufacturing efficiency is reduced. On the other hand, it is difficult to improve the roundness of a glass blank with a low degree of roundness through
 5 adjustment.

Taking these points into consideration, in the present embodiment, a glass blank is cut out from a glass plate using a laser beam in a manner that differs from a conventional manner.

[0022] Specifically, in first processing according to one embodiment, a circular crack starting portion is formed inside a glass plate by moving a first laser beam
 10 relative to the glass plate such that a focal position of the first laser beam is located in an inner portion of the glass plate in its thickness direction and the focal position forms a circle when viewed from a main surface of the glass plate. Thereafter, cracks are caused to develop from positions at the circular crack
 15 starting portion toward main surfaces of the glass plate to split the glass plate, and thus a glass blank that includes separation surfaces (split surfaces) having an arithmetic average surface roughness R_a smaller than $0.01\ \mu\text{m}$ and a roundness not larger than $15\ \mu\text{m}$ is separated from the glass plate.

The crack starting portion is a portion in which the formation of blemishes, melting, degradation, or alteration occurs through irradiation with a
 20 laser beam, for example. As a result of the glass plate being heated, for example, cracks develop from the crack starting portion toward both main surfaces of the glass plate.

Thereafter, chamfering processing for forming chamfered surfaces using
 25 a second laser beam is performed before performing grinding/polishing processing, which will be described later. Accordingly, corner portions that are formed by the main surfaces and the separation surfaces of the glass blank are chamfered using the second laser beam of a different type from the first laser beam between separation processing for separating the glass blank from the
 30 glass plate and the grinding/polishing processing.

[0023] In second processing according to another embodiment, defects are intermittently formed on a circular separation boundary line that is defined on a main surface of a glass plate, by emitting a first laser beam while moving the first laser beam relative to the glass plate, and a line-shaped defect is formed by
 5 connecting the formed defects to separate a glass blank from the glass plate. A second laser beam is emitted from the direction of a normal to a separation surface of the separated glass blank to form a chamfered surface on the separation surface and form a glass blank that has the separation surface having an arithmetic average surface roughness Ra smaller than 0.01 μm and
 10 a roundness not larger than 15 μm .

[0024] Defects include blemishes, molten portions, degraded portions, and altered portions (hereinafter referred to as “blemishes etc.”) that are formed in glass, holes (including through holes and bottomed holes) that are sharply recessed from the main surface of the glass plate and have small cross sections,
 15 cracks, etc. These defects serve as cores in the generation of cracks that are to develop.

Intermittently forming defects includes forming blemishes etc., or a plurality of holes (including through holes and bottomed holes) having small cross sections, which serve as cores in the generation of cracks, in the depth
 20 direction of the glass plate such that there are spaces between the blemishes etc., or the holes.

Forming a line-shaped defect includes forming a line-shaped crack that connects intermittently formed defects. Cracks include apparent cracks that form physical gaps in a glass material, as well as potential cracks that do not
 25 form physical gaps but form a boundary surface.

Separating a glass blank from a glass plate includes removing an outer portion that surrounds the glass blank such that a separated edge defines a circular outer circumference and removing an inner portion that is surrounded by the glass blank such that a circular inner hole is formed.

30 [0025] The roundness is measured by, for example, arranging a plate-shaped

probe that is thicker than the glass blank such that the probe faces an edge surface of the glass blank in a direction perpendicular to the main surfaces of the glass substrate, acquiring an outline while rotating the glass blank in the circumferential direction, and calculating a difference between the radius of an inscribed circle and the radius of a circumscribed circle of the outline, as the roundness of the glass substrate. Note that the roundness can be measured using a roundness and cylindrical shape measuring apparatus, for example.

[0026] The arithmetic average roughness Ra is a value in accordance with JIS B0601:2001. In order to determine the arithmetic average roughness Ra, a surface shape of an edge surface of the glass blank is measured using a laser microscope in an evaluation region of $50\ \mu\text{m} \times 50\ \mu\text{m}$ under the following conditions.

Observation magnification: 3000x magnification

Measurement pitch in height direction (Z axis): $0.01\ \mu\text{m}$

Cut-off value λ_s : $0.25\ \mu\text{m}$

Cut-off value λ_c : $80\ \mu\text{m}$

Note that resolution in the height direction is preferably not larger than 1 nm. Although the observation magnification is 3000x magnification in the present embodiment, the observation magnification is appropriately selected from within a range of about 1000x to about 3000x magnification depending on the size of the surface to be measured.

[0027] In the above-described first processing, an optical system of a laser beam source is adjusted such that the focal position of the first laser beam is located in an inner portion of the glass plate in its thickness direction, and accordingly light energy concentrates at the focal position and the focal position is locally heated to form the crack starting portion inside the glass. Thereafter, cracks are caused to develop from the crack starting portion toward the main surfaces by heating the glass plate, for example. A split surface that is formed through cracking has a small surface roughness. Also, the circle formed by the trajectory of the focal position can have a high degree of roundness by using a

moving mechanism that can precisely move the first laser beam relative to the glass plate, for example. Although precision of the roundness of the glass blank accordingly depends on the straightness of cracks that extend from the focal position toward the main surfaces, cracks extend from the inner portion in the thickness direction of the glass plate, and therefore the distance by which cracks develop is short, when compared to a case in which cracks develop from one main surface toward the other main surface. Therefore, impairment of the roundness can be suppressed.

In the second processing, although the arithmetic average roughness R_a of the separation surface may be large and the degree of roundness may be low if a glass blank is separated by forming a crack connecting defects that are intermittently formed through irradiation with the first laser beam, a chamfered surface is formed by melting glass in the vicinity of the separation surface with heat by emitting the second laser beam from the direction of the normal to the separation surface, and therefore the surface roughness of the separation surface can be reduced and precision of the roundness can be improved through irradiation with the second laser beam at the same time that the chamfered surface is formed through irradiation with the second laser beam.

Thus, the arithmetic average surface roughness R_a of the separation surface can be set to be smaller than $0.01\text{ }\mu\text{m}$ and the roundness can be set to be not larger than $15\text{ }\mu\text{m}$. According to one embodiment, the roundness can be set to 0.1 to $15\text{ }\mu\text{m}$. The roundness is preferably not larger than $10\text{ }\mu\text{m}$, more preferably not larger than $7\text{ }\mu\text{m}$, and further preferably not larger than $5\text{ }\mu\text{m}$.

[0028] The following describes a method for manufacturing a glass substrate for a magnetic disk according to the present embodiment with reference to the drawings. FIG. 1(a) is a perspective view of one example of a glass substrate for a magnetic disk manufactured in the present embodiment. FIG. 1(b) is a diagram showing one example of a cross section of an outer edge surface of the glass substrate for a magnetic disk shown in FIG. 1(a).

A glass substrate for a magnetic disk (hereinafter referred to as a “glass

substrate”) 1 shown in FIG. 1(a) is a glass substrate constituted by an annular thin plate. Although the size of the glass substrate for a magnetic disk is not limited, the glass substrate for a magnetic disk has the size of a glass substrate for a magnetic disk that has a nominal diameter of 2.5 inches or 3.5 inches, for example. In the case of a glass substrate for a magnetic disk having a nominal diameter of 2.5 inches, the outer diameter is 65 mm and the diameter of a center hole is 20 mm, for example. The thickness of the glass substrate 1 is not larger than 1.0 mm, and is 0.6 mm to 1.0 mm, for example. Alternatively, the thickness is smaller than 0.6 mm, e.g., smaller than 0.52 mm. A magnetic disk is obtained by forming magnetic layers on main surfaces of the glass substrate 1.

[0029] The glass substrate 1 includes a pair of main surfaces 11p and 12p, a side wall surface 11w that is formed on an outer edge surface, chamfered surfaces 11c and 12c that are respectively located between the side wall surface 11w and the main surfaces 11p and 12p, a side wall surface (not shown) that is formed on an inner edge surface similarly to the outer edge surface, and chamfered surfaces (not shown) that are respectively located between the side wall surface formed on the inner edge surface and the main surfaces 11p and 12p.

The glass substrate 1 includes a circular hole in a central portion. The side wall surface 11w includes a center position in the thickness direction of the glass substrate 1. The inclination angle of the chamfered surfaces 11c and 12c with respect to the main surfaces 11p and 12p is not specifically limited, and is 45°, for example. The shape of boundaries between the side wall surface 11w and the chamfered surfaces 11c and 12c is not limited to a shape that includes an edge as illustrated, and may also be a smooth continuously curved shape. The chamfered surfaces 11c and 12c may also be curved in a cross section, rather than being linearly inclined as shown in FIG. 1(b).

[0030] First Processing

In manufacture of such a glass substrate 1, separation processing for

cutting out a glass blank from a glass plate, which is manufactured in advance, using a laser beam is performed. FIGS. 2(a), 2(b), and 3 are diagrams showing separation processing for cutting out a glass blank from a glass plate 20 according to one embodiment.

5 The glass plate 20 is a glass plate that is obtained using a floating method or a down draw method, for example, and has a constant thickness. Alternatively, the glass plate 20 may also be obtained through press molding using a mold. The thickness of the glass plate 20 is larger than a target thickness of a glass substrate for a magnetic disk, which is the end product, by
10 an amount to be removed through grinding and polishing, which is about several micrometers, for example.

[0031] A laser beam source 30 is an apparatus that emits a laser beam L1 (first laser beam), and a solid-state laser, such as a YAG laser or an ND:YAG laser, is used, for example. Therefore, the wavelength of the laser beam is in a range of
15 1030 nm to 1070 nm, for example.

The laser beam L1 is a pulsed laser, and according to one embodiment, the pulse width of the laser beam L1 is preferably not larger than 10^{-12} seconds (not larger than 1 picosecond) in terms of suppressing excessive alteration of glass at a focal position F of the laser beam L1.

20 Light energy of the laser beam L1 can be appropriately adjusted according to the pulse width and the repetition frequency of the pulse width. If light energy that is excessively high relative to the pulse width and the repetition frequency is provided, the glass is likely to be excessively altered and a residue is likely to remain at the focal position F.

25 [0032] An optical system of the laser beam source 30 is adjusted such that the focal position F of the laser beam L1 is located in an inner portion of the glass plate 20 in its thickness direction as shown in FIG. 2(b), and therefore light energy concentrates at the focal position F and the focal position F is locally heated, and a crack starting portion (core in the generation of cracks) is formed
30 through the formation of blemishes, melting, degradation, or alteration. The

focal position F is moved relative to the glass plate 20 to form a circle when viewed from a surface of the glass plate 20, and therefore the crack starting portion has a circular shape. By heating the glass plate 20, for example, cracks C are generated at respective positions in the crack starting portion inside the glass and caused to develop toward the main surfaces as shown in FIG. 3. As a result, a glass blank can be easily separated from the glass plate 20 without applying a strong force for splitting.

Thus, a glass blank that has a separation surface (split surface) having an arithmetic average surface roughness Ra smaller than 0.01 μm and a roundness not larger than 15 μm can be obtained. The roundness is preferably not larger than 10 μm , more preferably not larger than 7 μm , and further preferably not larger than 5 μm . This separation surface (split surface) is an edge surface that satisfies requirements for edge surfaces of a glass substrate for a magnetic disk. Therefore, the separation surface (split surface) need not be polished.

[0033] Note that, according to one embodiment, it is preferable that the focal position F is located at a distance in a range of one third to two thirds of the thickness of the glass plate 20 from a main surface of the glass plate 20. If the focal position F is set in this range, the separation surface (split surface) satisfying requirements of the roundness and the surface roughness can serve as the side wall surface 11w shown in FIG. 1(b) as is, and accordingly extra processing, such as edge surface polishing, need not be performed and manufacturing efficiency can be improved.

[0034] According to one embodiment, it is also preferable that the focal position F is located at a distance that is shorter than one third of the thickness of the glass plate from a main surface of the glass plate. In this case, the vicinity of the focal position F, in which a residue is likely to be formed and the surface roughness is impaired, when compared to a separation surface (split surface) formed through cracking, is removed through chamfering processing described later. Therefore, in order to further improve the surface roughness, it is

preferable that the focal position F is located at a distance that is shorter than one third of the thickness of the glass plate from a main surface of the glass plate.

[0035] According to one embodiment, it is preferable that the laser beam L1 is
5 a pulsed laser beam that has a pulse width not larger than 10^{-12} seconds. If the pulse width is larger than 10^{-12} seconds, the surface roughness is likely to be impaired as a result of light energy concentrating at the focal position F and the glass in the vicinity of the focal position F being altered.

[0036] Chamfering processing is performed to chamfer corner portions that are
10 formed by the main surfaces and the edge surfaces, which are the separation surfaces (split surfaces), of the glass blank separated from the glass plate 20 as described above. Specifically, the corner portions are chamfered using a laser beam L2 (second laser beam) of a different type from the laser beam L1. FIG. 4 is a diagram showing one example of the chamfering processing. The laser
15 beam L2 is emitted from a direction that is inclined at an angle of 30° to 60° with respect to the main surface to heat a corner portion 40, and thus the corner portion 40 is softened, evaporated, and chamfered. A CO_2 laser can be preferably used, for example. In this case, it is preferable that the laser beam L2 is a pulsed laser, the repetition frequency of the laser beam L2 is not lower
20 than 5 KHz, and the power density of the laser beam L2 per pulse in a unit area is not higher than 100 W/cm^2 . A chamfered surface that has a small surface roughness and a high degree of roundness can be formed through the above-described chamfering.

Thus, a corner portion that is formed by a lower main surface and the
25 side wall surface shown in FIG. 3 can also be chamfered using a similar laser beam L2. Since the corner portion 40 is chamfered using the laser beam L2, manufacturing efficiency is high, when compared to a case in which chamfering is performed using a grindstone etc.

As described above, edge surface polishing need not be performed in the
30 processes from cutting out the glass blank 30 to chamfering, and accordingly

manufacturing efficiency is improved.

[0037] Second Processing

In second processing according to another embodiment, defects are intermittently formed on a circular separation boundary line defined on the glass plate 20, by emitting the laser beam L1 (first laser beam) while moving the laser beam L1 relative to the glass plate 20, and a line-shaped defect is formed by connecting the formed defects to separate a glass blank from the glass plate 20. The distance between adjacent defects that are intermittently formed is about several micrometers, e.g., 1 to 10 μm .

In this case, the focal position F of the laser beam L1 is not limited and need not necessarily have to be located in an inner portion of the glass plate 20 in its thickness direction as shown in FIG. 2(b). The focal position F may be located on a main surface of the glass plate 20, for example. Through irradiation with the laser beam L1, light energy concentrates at an irradiated position, the irradiated position is locally heated, and a defect is formed as a crack starting portion (core in the generation of cracks) through the formation of blemishes, melting, degradation, or alteration. As a result of the glass plate 20 being heated, for example, cracks develop from respective positions of crack starting portions and connect to adjacent defects while forming a line. Thus, a line-shaped defect is formed on the separation boundary line, and a glass blank can be separated from the glass plate 20. In order that the glass blank can be easily separated from the glass plate 20, the glass plate 20 may be heated using a heater or a laser beam to form gaps between the glass blank and portions other than the glass blank due to a difference in thermal expansion.

[0038] As the laser beam L1 (first laser beam) used to intermittently form defects, a solid-state laser, such as a YAG laser or an ND:YAG laser, is used, for example. Therefore, the wavelength of the laser beam is in a range of 1030 nm to 1070 nm, for example.

The laser beam L1 is a pulsed laser, and according to one embodiment, the pulse width of the laser beam L1 is preferably not larger than 10^{-12} seconds

(not larger than 1 picosecond) in terms of suppressing excessive alteration.

Light energy of the laser beam L1 can be appropriately adjusted according to the pulse width and the repetition frequency of the pulse width. If light energy that is excessively high relative to the pulse width and the repetition frequency is provided, the glass is likely to be excessively altered and a residue is likely to remain at the irradiated position.

[0039] In the case of the second processing, a crack starting end is not necessarily located in an inner portion of the glass plate 20, and accordingly, in some cases, the surface roughness of a separation surface of the separated glass blank is not sufficiently small and the degree of roundness is not sufficiently high. However, when a chamfered surface is formed on the separation surface, the laser beam L2 is emitted toward the separation surface from the direction of a normal to the separation surface as shown in FIG. 5 to heat and melt a portion of glass in the vicinity of the separation surface through irradiation with the laser beam L2. Therefore, the surface roughness of the separation surface can be reduced and the roundness can be improved through irradiation with the second laser beam. FIG. 5 is a diagram showing one example of chamfered surface forming processing. By appropriately setting the intensity of the laser beam L2 and a spot diameter, the surface roughness of the separation surface can be reduced and the roundness can be improved while the chamfered surface is being formed. By adjusting the intensity of light energy of the second laser beam emitted toward the separation surface and the spot diameter at the separation surface, a chamfered surface having a desired shape and a preferable separation surface having a small surface roughness and a high degree of roundness can be formed.

[0040] The laser beam L2 is emitted from a laser beam source, formed into a parallel beam while being passed through an optical system that includes a collimator etc., then caused to converge using a converging lens 34, and then emitted toward the separation surface while spreading.

On the other hand, the glass plate 20 is rotated about the center position

of the glass plate 20 at a constant speed. Thus, the entire circumference of the separation surface of the glass plate 20 is irradiated with the laser beam L2 while the laser beam L2 and the separation surface are moved relative to each other in the circumferential direction of the glass plate 20.

5 Here, the laser beam L2 is emitted toward the separation surface from the direction of a normal to the separation surface to be irradiated, and the direction of the normal includes, as allowable tolerances, directions that are inclined at an inclination angle of $0 \pm 10^\circ$ with respect to the direction of the normal, in addition to the exact direction of the normal (inclination angle: 0°).

10 In the example shown in FIG. 5, the chamfered surface is formed on the separation surface, which is an outer circumferential edge surface 24 of the glass plate 20, but a chamfered surface may also be formed on a separation surface that is an inner circumferential edge surface 26 extending along the inner hole of the disk-shaped glass plate 20.

15 [0041] Although a CO₂ laser beam is used as one example of the laser beam L2, the laser beam L2 is not limited to the CO₂ laser beam and only required to have an oscillation wavelength that can be absorbed by glass. For example, a CO laser (oscillation wavelength: 5 μm), an Er-YAG laser (oscillation wavelength: 2.94 μm), etc., can be used.

20 [0042] Thus, a glass blank that has a separation surface having an arithmetic average surface roughness Ra smaller than 0.01 μm and a roundness not larger than 15 μm can be obtained. The roundness is preferably not larger than 10 μm , more preferably not larger than 7 μm , and further preferably not larger than 5 μm . This separation surface is an edge surface that satisfies
25 requirements for edge surfaces of a glass substrate for a magnetic disk. Therefore, the edge surface need not be polished.

[0043] The above-described second processing is effective for an extremely thin glass plate that has a thickness not larger than 0.6 mm because, as the thickness of the glass plate is reduced, glass in the vicinity of the separation surface can
30 be more easily melted in a short period of time by emitting the laser beam L2

toward the separation surface. In this case, the glass blank preferably has a thickness not larger than 0.52 mm after grinding/polishing processing described later.

By performing the above-described first and second processing, a disk-shaped glass blank that has a circular outer circumference and an inner hole that is concentric to the circular shape of the outer circumference can be obtained.

[0044] Main Surface Grinding/Polishing Processing

Grinding/polishing processing is performed on the main surfaces of a glass blank that is separated from a glass plate and provided with chamfered surfaces.

In the grinding/polishing processing, the glass blank is ground and then polished.

In grinding processing, grinding is performed on the main surfaces of the glass blank using a double-side grinding apparatus provided with a planetary gear mechanism. Specifically, both main surfaces of the glass blank are ground while the outer circumferential edge surface of the glass blank is held in a holding hole provided in a holding member of the double-side grinding apparatus. The double-side grinding apparatus has a pair of upper and lower surface plates (an upper surface plate and a lower surface plate), and the glass blank is sandwiched between the upper surface plate and the lower surface plate. The glass blank and the surface plates are moved relative to each other by moving one or both of the upper surface plate and the lower surface plate while supplying a coolant, and thereby both main surfaces of the glass blank can be ground. The grinding processing can be performed in a state in which grinding members obtained by forming fixed abrasive particles, which are obtained by fixing diamonds using resin, into a sheet-shape are attached to the surface plates, for example.

[0045] Next, first polishing is performed on the ground main surfaces of the glass blank. Specifically, both main surfaces of the glass blank are polished

while the outer circumferential edge surface of the glass blank is held in a holding hole provided in a carrier for polishing of a double-side polishing apparatus. The first polishing is for removing blemishes and warping or adjusting minute surface unevenness (microwaviness, roughness) remaining on the main surfaces after the grinding processing.

[0046] In the first polishing processing, the glass blank is polished using a double-side polishing apparatus having a configuration similar to that of the double-side grinding apparatus used in the above-described grinding processing with fixed abrasive particles, while a polishing slurry is provided. In the first polishing processing, a polishing slurry containing loose abrasive particles is used. Cerium oxide abrasive particles, zirconia abrasive particles, etc., are used as the loose abrasive particles in the first polishing, for example. Similarly to the double-side grinding apparatus, the double-side polishing apparatus sandwiches the glass blank between a pair of upper and lower surface plates. Tabular polishing pads (resin polisher, for example) having an annular shape overall are attached to the upper surface of the lower surface plate and the bottom surface of the upper surface plate. The glass blank and the surface plates are moved relative to each other by moving one or both of the upper surface plate and the lower surface plate, and thereby both main surfaces of the glass blank are polished. It is preferable that polishing abrasive particles have an average particle diameter (D50) in a range of 0.5 to 3 μm .

[0047] After the first polishing, the glass blank may be chemically strengthened. In this case, a melt in which potassium nitrate and sodium sulfate are mixed, for example, is used as a chemical strengthening liquid, and the glass blank is immersed in the chemical strengthening liquid. Thus, a compressive stress layer can be formed on the surface of the glass blank through ion exchange.

[0048] Next, second polishing is performed on the glass blank. The second polishing processing is for mirror-polishing the main surfaces. In the second polishing as well, a double-side polishing apparatus having a configuration similar to that of the double-side polishing apparatus used in the first polishing

is used. Specifically, both main surfaces of the glass blank are polished while the outer circumferential edge surface of the glass blank is held in a holding hole provided in a carrier for polishing of the double-side polishing apparatus. The second polishing processing differs from the first polishing processing in that
5 the type and particle size of the loose abrasive particles are different, and the hardness of the resin polishers is different. The hardness of the resin polishers is preferably lower than that of the resin polishers used in the first polishing processing. For example, a polishing liquid containing colloidal silica as loose abrasive particles is supplied between the polishing pads of the double-side
10 polishing apparatus and the main surfaces of the glass blank, as a result of which the main surfaces of the glass blank are polished. It is preferable that the polishing abrasive particles used in the second polishing have an average particle diameter (d50) in a range of 5 to 50 nm.

In one embodiment, whether not to perform chemical strengthening
15 processing may be appropriately selected taking the glass composition or the necessity into account. Another type of polishing processing may be added to the first polishing processing and the second polishing processing, and two types of polishing processing performed on the main surfaces may be performed as single polishing processing. The order of the above-described processing may
20 be appropriately changed.

As a result of the main surfaces of the glass blank 20 being polished as described above, a glass substrate for a magnetic disk that satisfies requirements for glass substrates for magnetic disks can be obtained.

Note that it is not always necessary to perform both grinding and
25 polishing of the main surfaces of the glass blank 20, and it is only required to perform at least either of grinding and polishing. For example, a configuration is also possible in which grinding is not performed and polishing is performed. [0049] Note that edge surface polishing processing for polishing the edge surfaces (separation surfaces) of the glass blank 20 may also be performed before
30 the first polishing, for example, after the grinding and before the first polishing,

or before the grinding.

Even if such edge surface polishing processing is performed, the edge surface polishing processing takes little time because the arithmetic average roughness Ra of the edge surfaces of the glass blank 20 is smaller than 0.01 μm and the roundness is not larger than 15 μm .

The edge surface polishing processing may be performed using a polishing brush method in which polishing is performed using a polishing brush while loose abrasive particles are supplied to the edge surfaces or a polishing method in which a magnetic functional fluid is used. In the polishing method in which a magnetic functional fluid is used, a slurry obtained by adding abrasive polishing particles to a magnetic viscous fluid is formed into a mass using a magnetic field, the edge surfaces of the glass blank 20 are thrust into the mass, and the edge surfaces are polished by moving the mass and the glass blank 20 relative to each other.

[0050] However, it is preferable not to perform the edge surface polishing processing to increase manufacturing efficiency. In this case, the main surfaces of the glass blank are ground or polished in the grinding/polishing processing of the main surfaces while maintaining the roundness of the glass blank obtained through cutting processing and the surface roughness of at least a portion of the separation surfaces.

[0051] As a material of the glass substrate for a magnetic disk according to the present embodiment, aluminosilicate glass, soda-lime glass, borosilicate glass, etc., can be used. In particular, aluminosilicate glass can be preferably used from the standpoint that chemical strengthening can be performed and a glass substrate for a magnetic disk that has high strength and includes main surfaces having a high degree of flatness can be manufactured. Amorphous aluminosilicate glass is further preferable.

[0052] Although the composition of the glass substrate for a magnetic disk according to the present embodiment is not limited, the glass substrate according to the present embodiment is preferably amorphous aluminosilicate

glass that has the following composition in which ratios of components are shown in terms of oxides using mol%: 50 to 75% of SiO_2 , 1 to 15% of Al_2O_3 , a total of 5 to 35% of at least one component selected from Li_2O , Na_2O , and K_2O , a total of 0 to 20% of at least one component selected from MgO , CaO , SrO , BaO , and ZnO , and a total of 0 to 10% of at least one component selected from ZrO_2 , TiO_2 , La_2O_3 , Y_2O_3 , Ta_2O_5 , Nb_2O_5 , and HfO_2 .

[0053] Preferably, the glass substrate according to the present embodiment may be, for example, amorphous aluminosilicate glass that has the following composition in which ratios of components are shown using mass%: 57 to 75% of SiO_2 , 5 to 20% of Al_2O_3 (under the provision that a total of SiO_2 and Al_2O_3 is 74% or more), a total of more than 0% and not more than 6% of ZrO_2 , HfO_2 , Nb_2O_5 , Ta_2O_5 , La_2O_3 , Y_2O_3 , and TiO_2 , more than 1% and not more than 9% of Li_2O , 5 to 28% of Na_2O (under the provision that a mass ratio $\text{Li}_2\text{O}/\text{Na}_2\text{O}$ is not larger than 0.5), 0 to 6% of K_2O , 0 to 4% of MgO , more than 0% and not more than 5% of CaO (under the provision that a total of MgO and CaO is not more than 5% and the amount of CaO is larger than the amount of MgO), and 0 to 3% of $\text{SrO}+\text{BaO}$.

[0054] The glass substrate for a magnetic disk according to the present embodiment may have a composition that includes, as essential components, SiO_2 , Li_2O , Na_2O , and at least one alkaline earth metal oxide selected from the group consisting of MgO , CaO , SrO , and BaO , and in which the mole ratio ($\text{CaO}/(\text{MgO}+\text{CaO}+\text{SrO}+\text{BaO})$) of the amount of CaO to a total amount of MgO , CaO , SrO , and BaO is not larger than 0.20, and the glass transition temperature of the glass substrate may be at least 650°C . A glass substrate for a magnetic disk having such a composition is preferable as a glass substrate for a magnetic disk that is used for a magnetic disk for energy assisted magnetic recording.

[0055] Although the method for manufacturing a glass substrate for a magnetic disk according to the present invention has been described in detail, the method for manufacturing a glass substrate for a magnetic disk according to the present invention is not limited to the above-described embodiments, and it goes without

saying that various modifications and changes can be made within a scope not departing from the gist of the present invention.

[List of Reference Numerals]

5	[0056]	1	Glass substrate for magnetic disk
		11p, 12p	Main surface
		11w	Side wall surface
		11c, 12c	Chamfered surface
		20	Glass plate
10		24	Outer circumferential edge surface
		26	Inner circumferential edge surface
		30	Laser beam source
		34	Converging lens
		40	Corner portion

CLAIMS

1. A method for manufacturing a disk-shaped glass blank, comprising:
separation processing in which a circular crack starting portion
5 corresponding to a focal position of the laser beam is formed inside a glass plate
by moving a first laser beam relative to the glass plate such that the focal
position of the laser beam is located in an inner portion of the glass plate in a
thickness direction thereof and the focal position forms a circle when viewed
from a main surface of the glass plate, thereafter cracks are caused to develop
10 from the crack starting portion toward main surfaces of the glass plate, and the
glass plate is split to separate a glass blank from the glass plate, the glass blank
including a separation surface that has an arithmetic average surface roughness
Ra smaller than $0.01\text{ }\mu\text{m}$ and a roundness not larger than $15\text{ }\mu\text{m}$;
- 15 2. The method for manufacturing a disk-shaped glass blank according to
claim 1,
wherein the focal position is located at a distance within a range of one
third to two thirds of a thickness of the glass plate from a main surface of the
glass plate.
20
3. The method for manufacturing a disk-shaped glass blank according to
claim 1,
wherein the focal position is located at a distance that is shorter than
one third of a thickness of the glass plate from a main surface of the glass
25 substrate.
4. The method for manufacturing a disk-shaped glass blank according to
any one of claims 1 to 3, comprising:
chamfering processing for chamfering a corner portion that is formed by
30 a main surface of the glass blank and the separation surface using a second laser

beam of a different type from the first laser beam after the separation processing.

5. A method for manufacturing a disk-shaped glass blank, comprising:

separation processing in which a crack starting portion is formed inside
5 a glass plate by moving a first laser beam relative to the glass plate such that
the focal position of the laser beam is located in an inner portion of the glass
plate in a thickness direction thereof and the focal position forms a circle when
viewed from a main surface of the glass plate, thereafter cracks are caused to
develop from the crack starting portion toward main surfaces of the glass plate,
10 and the glass plate is split to separate a glass blank from the glass plate, the
glass blank including a separation surface that has an arithmetic average
surface roughness Ra smaller than 0.01 μm and a roundness not larger than 15
 μm ; and

chamfering processing for chamfering a corner portion that is formed by
15 a main surface of the glass blank and the separation surface using a second laser
beam of a different type from the first laser beam after the separation processing,

wherein the focal position is located at the part that is removed through
chamfering processing.6. The method for manufacturing a disk-shaped
20 glass blank according to claim 5,

wherein the focal position is located at a distance within a range of one
third to two thirds of a thickness of the glass plate from a main surface of the
glass plate.7. The method for manufacturing a disk-shaped glass blank
according to claim 5,

25 wherein the focal position is located at a distance that is shorter than
one third of a thickness of the glass plate from a main surface of the glass
substrate.8. A method for manufacturing a disk-shaped glass blank,
comprising:

separation processing in which defects are intermittently formed on a circular
30 separation boundary line that is defined on a main surface of a glass plate, by

emitting a first laser beam while moving the first laser beam relative to the glass plate, a line-shaped defect is formed by connecting the formed defects by cracks, and a glass blank is formed by separating a removal target portion from the glass plate; and

5 chamfering processing in which a second laser beam of a different type from the first laser beam is emitted from a direction of a normal to a separation surface of the glass blank separated from the removal target portion during the glass blank is rotating to form a chamfered surface on the separation surface and form a glass blank that has the separation surface having an arithmetic
10 average surface roughness Ra smaller than $0.01\text{ }\mu\text{m}$ and a roundness not larger than $15\text{ }\mu\text{m}$.

9. The method for manufacturing a disk-shaped glass blank according to
15 claim 8,

 wherein in the chamfering processing, a second laser beam is emitted from a direction of a normal to an entire separation surface during the glass plate is rotating at a constant speed about the center position of the glass plate while the second laser beam and the separation surface are moved relative to
20 each other in the circumferential direction of the glass plate to form a chamfered surface and improving the surface roughness of the separation surface and the roundness.

10. The method for manufacturing a disk-shaped glass blank according to
25 any one of claims 1-9, wherein a thickness of the glass plate is not larger than 0.6 mm .

11. The method for manufacturing a disk-shaped glass blank according to any one of claims 1-10,
30 wherein the first laser beam is a pulsed laser beam that has a pulse

width not larger than 10^{-12} seconds.

12. The method for manufacturing a disk-shaped glass blank according to any one of claims 1 to 11,

5 wherein the roundness is 0.1 to 15 μm .

13. A method for manufacturing a glass substrate for a magnetic disk, comprising:

 grinding/polishing processing in which at least one of grinding and
10 polishing is performed on main surfaces of the glass blank manufactured by the method according to any one of claims 1-12.

14. The method for manufacturing a glass substrate for a magnetic disk, according to claim 13,

15 wherein a thickness of the glass blank after the grinding/polishing processing is smaller than 0.52 mm.

15. The method for manufacturing a glass substrate for a magnetic disk, according to claim 13 or 14,

20 wherein the edge surface polishing processing of the edge surface of the disk-shaped glass blank is not performed after the separation processing.