

CORRECTED VERSION

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
20 September 2001 (20.09.2001)

PCT

(10) International Publication Number
WO 01/068246 A1

- (51) International Patent Classification⁷: **B01J 29/06**, 21/00, 29/00, 23/00, 23/40, 23/42, 23/72, 23/70, 23/74, H01M 4/86, 4/90, 4/96, 8/08, 8/14, 4/32, 4/52, 4/58
- (74) Agents: **SCHLAZER, Philip, H.** et al.; Energy Conversion Devices, Inc., 2956 Waterview Drive, Rochester Hills, Michigan 48309 (US).
- (21) International Application Number: PCT/US01/08565
- (81) Designated States (*national*): AU, BR, CA, CN, IN, JP, KR, MX, NO, RU, SG, UA.
- (22) International Filing Date: 12 March 2001 (12.03.2001)
- (84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR).
- (25) Filing Language: English
- (26) Publication Language: English
- Published:
— with international search report
- (30) Priority Data:
09/523,820 13 March 2000 (13.03.2000) US
- (48) Date of publication of this corrected version:
20 February 2003
- (71) Applicant: **OVONIC BATTERY COMPANY, INC.**
[US/US]; 1707 Northwood, Troy, MI 48084 (US).
- (15) Information about Correction:
see PCT Gazette No. 08/2003 of 20 February 2003, Section II
- (72) Inventors: **FETCENKO, Michael, A.**; 1513 Pondsider Court, Rochester, MI 48307 (US). **OVSHINSKY, Stanford, R.**; 2700 Squirrel Road, Bloomfield Hills, MI 48304 (US). **YOUNG, Kwo**; 4131 Morehead Drive, Troy, MI 48098 (US).
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: FINELY DIVIDED METAL CATALYST AND METHOD FOR MAKING SAME

(57) Abstract: An inexpensive, highly catalytic material preferably formed by a leaching process. The catalyst comprises a finely divided metal particulate and a support. The active material may be a nickel and/or nickel alloy particulate having a particle size less than about 100 Angstroms. The support may be one or more metal oxides.



WO 01/068246 A1