

This Sheet Has Been Replaced



- 1 -

✓	1318	1318
✓	15	15
✓	17	17

Novel antistatic agent for a polymer composition, use of this agent in polymer compositions and compositions obtained.

The present invention relates generally to antistatic agents for polymer compositions.

It is known, in order to prevent dust from being deposited on articles moulded from polymer compositions, such as moulded articles made of acrylonitrile-butadiene-styrene (ABS) resin, to incorporate an antistatic or antidust agent into these compositions.

In moulding compositions, in particular ones based on ABS resin, C_{13} - C_{15} ethoxylated amines have usually been used as antistatic agents. These ethoxylated amines are in liquid form.

In industrial production, the liquids are difficult to handle. The liquid antistatic agent is generally injected during extrusion of the polymer composition close to the die, which gives rise to the risk of fire.

Moreover, when the technique of stock mixtures is used, that is to say the technique consisting in preparing a premix of the adjuvants with some of the resinous components of the polymer composition, the premix has a tendency to form agglomerates which stick to the walls of the supply and metering system during the formation of the final composition on a twin-screw extruder.

Furthermore, the liquid antistatic agent is packaged in drums and it is not possible to extract all of the contents of the drum, which leads to a loss of starting material and an increase in the manufacturing costs.

Lastly, when such a liquid antistatic agent is used, dispersed in an article made of moulded plastic, for example one based on ABS resin, the additive has a tendency to migrate towards the surface of the moulded article and to form a whitish film there, which reduces the sheen and the aesthetic appearance of this moulded article.



In order to overcome the drawbacks of liquid antistatic agents, it has been envisaged to use solid antistatic agents. Solid antistatic agents which have been envisaged are C_{16} - C_{18} ethoxylated amines which are in pasty form. Another solid antistatic agent, which is commercially available from the company CECA, consists of 75 parts by weight of C_{16} - C_{18} ethoxylated amines and 25 parts by weight of calcium stearate.

However, these known solid antistatic agents still have the drawback of forming agglomerates when they are used in the stock mixture technique, in particular with ABS resins loaded with pigments and dyes such as TiO_2 . The formation of these brittle agglomerates greatly disrupts the supply and metering of the stock mixture during the formulation of the final composition on a twin-screw extruder.


The object of the present invention is thus to provide a novel solid antistatic agent which overcomes the drawbacks mentioned above for liquid/solid antistatic agents and which avoids the formation of brittle agglomerates, in particular when it is used in the technique of stock mixtures.

According to the invention, the above aims are achieved by preparing an antistatic agent which comprises:

(a) 40 to 99% by weight of a C_{15} - C_{20} , preferably C_{16} - C_{18} , ethoxylated amine or a mixture of C_{15} - C_{20} , preferably C_{16} - C_{18} , ethoxylated amines; and

(b) 60 to 1% by weight, relative to the total weight of the components (a) and (b), of a solidification component chosen from magnesium oxide (MgO), zinc oxide (ZnO), titanium dioxide (TiO_2), barium sulphate ($BaSO_4$), talc, ethylenebis(stearamide) wax, synthetic hydro-talcites of formula $(Mg)_a(Al)_b(CO_3)_x(OH)_y(H_2O)_z$, in which $2 \leq a \leq 6$, $1 \leq b \leq 3$, $1 \leq x \leq 5$, $8 \leq y \leq 14$ and $0 \leq z \leq 3$, and mixtures thereof.

Preferably, the antistatic agent according to the invention comprises 40 to 95%, and better still 40 to 90%, by weight of C_{15} - C_{20} ethoxylated amines and 60 to 5%,



and better still 60 to 10%, by weight of solidification component.

Even more preferably, the solid antistatic agent comprises from 70 to 90% by weight of a C_{15} - C_{20} ethoxylated amine or a mixture thereof and 30 to 10% by weight of the solidification component.

The solidification components recommended are magnesium oxide, ethylenebis(stearamide) wax, hydrotalcites and mixtures of TiO_2 and $BaSO_4$ with $(Mg)_a(Al)_b(CO_3)_x(OH)_y(H_2O)_z$ where a, b, x, y and z are defined as above.

The use of hydrotalcite as a solidification component also has the advantage that, when mixed with the ethoxylated amine, this compound leads to a synergum which improves the antistatic properties of the final compositions surprisingly.

Synthetic hydrotalcites are known compounds, which are commercially available, for example under the name DHT4A from the company Kowa or L55R2 from the company Reheis.

The C_{15} - C_{20} ethoxylated amines are well-known compounds which are commercially available from various companies, such as Akzo, ICI and Ceca-Atochem.

Recommended antistatic compositions according to the invention comprise, relative to the total weight of the antistatic agent, 6% by weight of MgO , ZnO , talc, ethylenebis(stearamide) wax, TiO_2 or $BaSO_4$, 7% by weight of $(Mg)_a(Al)_b(CO_3)_x(OH)_y(H_2O)_z$ and 87% by weight of one or more C_{15} - C_{20} ethoxylated amines. Among the latter antistatic compositions, the ones most recommended are those containing 6% by weight of TiO_2 , $BaSO_4$ or of ethylenebis(stearamide) wax.

The present invention also relates to polymer compositions comprising, per 100 parts by weight of polymer components, from 0.1 to 40, preferably 0.1 to 15, parts by weight of an antistatic agent according to the invention. Preferably, the antistatic agent is present in an amount of from 0.5 to 2.5 parts by weight relative to the weight of the polymer components of the composition.

In addition, the compositions according to the invention can contain up to 6% by weight, relative to the total weight of the composition, of silica, of alumina or of a mixture of silica and alumina, so as to improve the resistance to caking of these compositions.

The polymer components which are useful in the antistatic compositions according to the invention are olefin polymers and copolymers, styrene polymers and copolymers, acrylic and methacrylic polymers and copolymers, vinyl polymers and copolymers, and alloys thereof.

Among the olefin polymers and copolymers which are useful in the compositions of the present invention, mention may be made of polyolefins such as polyethylenes, polypropylenes, polybutylenes and olefin copolymers such as ethylene-propylene copolymers.

Among the styrene polymers and copolymers which are useful in the compositions of the present invention, mention may be made of styrene homopolymers, homopolymers of alkylstyrene such as α -methylstyrene, high impact shock strength (HIPS) polystyrenes and grafted styrene polymers.

A recommended class of styrene polymers which are useful in the compositions of the present invention are high impact shock strength (HIPS) polystyrenes. These high impact shock strength polymers are generally prepared by polymerization by grafting mixtures of styrene and optionally one or more additional copolymerizable vinyl monomers in the presence of a rubbery polymer trunk. Similar resins may also be prepared by mixing a polymer of rigid matrix with a grafted rubbery trunk. The comonomers which may be used in mixtures with styrene for the preparation of rigid styrene copolymers, as well as for use as grafting monomers, comprise monomers chosen from the ethylstyrene form, halostyrenes, vinylalkylbenzenes such as vinyltoluene, vinylxylene and butylstyrene, acrylonitrile, methacrylonitrile, lower alkyl esters of methacrylic acid, and mixtures thereof. In the high impact strength styrene resins, the rubbery polymer trunk normally constitutes from 5 to 80%, preferably from

5 to 50%, of the total weight of the grafted polymer, and comprises rubbery copolymers chosen from polybutadiene, polyisoprene, rubbery styrene-diene copolymers, acrylic rubber, nitrile rubber and olefin rubbers, such as PDM and PR. In addition, other styrene polymers known in the art may be used in the alloy compositions of the invention.

As specific examples of grafted polymers which are useful in the compositions of the present invention, mention may be made of resins of emulsion and bulk acrylonitrile/butadiene/styrene (ABS) polymer type, methyl methacrylate/butadiene/acrylonitrile/styrene (MABS) resins, resins of styrene/butadiene (HIPS) grafted polymer type and methyl methacrylate/butadiene/styrene (MBS) resins.

As specific examples of styrene polymers which may be used in the present invention, mention may be made of polystyrene and styrene copolymers such as styrene/acrylonitrile (SAN) copolymers, styrene/methacrylic ester copolymers, resins of styrene/acrylonitrile/maleic anhydride (SAMA) terpolymer type, resins of styrene/maleic anhydride (SMA) copolymer type, similar polymers comprising N-phenyl substituted and differently and similarly substituted N-phenylmaleimides, and mixtures thereof. In addition, styrene-butadiene-styrene (SBS) copolymers and synthetic butyl rubbers (SBR) may also be used. Moreover, similar copolymer resins in which some of the styrene monomer component is replaced by other styrene monomers such as α -methylstyrene, halostyrenes or vinyltoluene may also be used. It is also possible to use mixtures or alloys of the above styrene polymers. Lastly, mixtures of the above styrene polymers and one or more polyphenylene ethers, polymers of polyvinyl chloride, polyamide and polycarbonate type and other polymers known generally in the art for alloying with styrene polymers may also be used. These additional polymers are generally known in the art and are described in Modern Plastic Encyclopedia, 1986-1987, McGraw-Hill, Inc., New York, USA.

The styrene polymers which are useful in the present invention also comprise polymers with a core-shell structure. The styrene polymers are generally prepared by emulsion or bulk polymerization bulk emulsion or bulk suspension.

The styrene polymers particularly recommended for the compositions of the present invention are ABS resins, in particular ABS resins containing from 4 to 70% by weight of butadiene relative to the total weight of the resin, and alloys of ABS resins and styrene/acrylonitrile (SAN) copolymers. When the ABS resin is in powder form, it preferably contains 10 to 70% by weight of butadiene. When the ABS resin is in granular form, it preferably contains 4 to 40% by weight of butadiene, and better still 4 to 30% by weight.

The alloys particularly recommended for the compositions of the invention are ABS/SAN alloys containing 10 to 80 parts by weight of ABS resin and 90 to 20 parts by weight of SAN copolymer. Preferably, the resins recommended for the compositions of the invention are ABS/SAN alloys containing 10 to 40 parts by weight of ABS resin and 90 to 60 parts by weight of SAN copolymer [sic].

Among the acrylic and methacrylic polymers and copolymers which are useful in the present invention, mention may be made of the copolymers [sic] derived from acrylic acid, for example acrylic esters, with styrene, vinyl chloride, methacrylic acid derivatives and acetic acid esters, poly(alkyl methacrylates) such as poly(methyl methacrylate) and poly(alkyl acrylates).

Among the vinyl polymers and copolymers which may be mentioned are poly(vinyl chloride), poly(vinyl acetate), poly(vinylbenzenes), ethylene-vinyl acetate copolymers and polyvinyl alcohols.

The compositions according to the invention may also contain adjuvants generally used in styrene polymer and polyolefin compositions, such as lubricants, pigments, dyes, UV stabilizers, antioxidants, flame retardants and stretching and/or reinforcing fillers.

Among the lubricants which may be used in the compositions of the present invention, mention may be made, for example, of magnesium stearate, zinc stearate, polyethylene wax, paraffin wax, ethylene oxide and propylene oxide wax, butyl stearate, glyceryl monostearate, barium stearate, sodium stearate, stearyl alcohol and octyl behenate.

Among the inorganic fillers which may be used in the compositions of the present invention, mention may be made of talc, barium sulphate, calcium carbonate, magnesium aluminium hydroxycarbonate and calcium aluminium hydroxycarbonate.

The flame retardants which may be used in the compositions of the present invention are any flame retardants or mixture of flame retardants known to impart a flame-retardant nature to compositions based on styrene polymers or polyolefins. Among the flame retardants which may be mentioned are flame-retardant organic compounds such as tetrabromobisphenol, bis(tribromophenoxyethane), polybromodiphenyl ether, polybromophenol, poly(bromophenylalkyl ethers), poly(bromobenzyl acrylate) or polyacrylate, polybromocyclododecane, polybromostyrene, polybromophenylmaleimide, bromoepoxy monomers or polymers, and copolycarbonates derived from a halo-substituted diphenol and a diphenol, the halogen preferably being chlorine or bromine.

Phosphate compounds, in particular organic phosphates, may also be used as flame retardant.

Preferably also, the haloorganic flame retardant is used in combination with a synergistic compound such as an antimony compound, for example antimony oxide.

The compositions of the present invention may also contain dyes and pigments such as, for example, titanium oxide, ultramarine blue or carbon black.

When the antistatic agent used in the compositions of the invention contains no magnesium oxide, it is necessary to add magnesium oxide to the composition according to the invention. The aim of the magnesium oxide in this case is to remove the residual traces of

acid and thus to avoid corrosion of the moulds during moulding of the compositions. It is recommended in this case to use an amount of from 0.1 to 0.15 parts by weight of magnesium oxide per 100 parts of polymer components of the composition. Obviously, when an antistatic agent according to the invention which already contains magnesium oxide or hydrotalcite is used, it is not necessary to make a further addition thereof to the compositions.

The examples which follow are intended to illustrate the invention. In the examples, except where otherwise mentioned, all the percentages and parts are expressed by weight.

Comparative example A and Examples 1 to 3

In Examples 1 to 3, antistatic agents according to the invention were prepared by mixing together the constituents indicated in Table 1 below. Table 1 also indicates an antistatic additive (A) marketed by the company Ceca and comprising 75% by weight of C₁₆-C₁₈ ethoxylated amines and 25% by weight of calcium stearate.

Table 1 also indicates the physical properties of these antistatic additives.

This Sheet Has Been Replaced



TABLE 1

Example No.	A	1	2	3
<u>Composition</u>				
- C ₁₆ -C ₁₈ ethoxylated amines	75	87	70	82
- Calcium stearate	25	-	-	-
- MgO	-	13	30	-
- Ethylenebis(stearamide) wax	-	-	-	18
<u>Physical properties</u>				
Melting peak °C (differential scanning calorimetry)	44	49	47	49
Humidity (Karl-Fisher) %	1.45	1.15	0.8	1
<u>Thermogravimetric analysis</u> (volatility) °C				
Weight loss:				
- 1%	90	125	-	-
- 2%	125	200	-	-
- 3%	200	225	-	-
- 5%	230	250	-	-
Form	White flakes	Yellowish flakes		
Flowability	Reference	+ ¹	+	NT ²

1 : higher

2 : not tested

Table 1 shows that the antistatic additives, according to the invention, of Examples 1 to 3 have better physical properties than "A" the commercial antistatic agent. In particular, they have a markedly higher melting peak, a lesser residual humidity and, for the antistatic additives of Examples 1 and 2, much better flowability.

Comparative Examples B and C and Examples 4 and 5

Stock mixtures are prepared by mixing together the ingredients indicated in Table 2 in a Henschel mixer having a rotor rotating at a speed of 730 rpm. The mixing time was 3 minutes and the ingredients were loaded in the following order: half of the grafted ABS resin was intro-

duced first, followed by introduction, in order, of titanium oxide, ultramarine blue 51, antistatic agent, then optionally magnesium oxide and, lastly, the remainder of the grafted ABS resin. The grafted ABS resin used was a resin marketed by the company General Electric Plastics ABS SA G350, having the following composition: 37.5% by weight of styrene, 50% by weight of butadiene, 12.5% by weight of acrylonitrile.

The temperature while the ingredients were mixed together in order to obtain the stock mixtures in the mixer was 60°C.

The compositions of the various stock mixtures obtained as indicated above are collated in Table 2.

The appearance of the stock mixtures obtained, as well as the oven caking temperature for the various antistatic agents, are indicated in Table 3.

The oven caking test is performed in the following manner:

A 3 cm layer of antistatic agent is placed in a crystallizing dish 11 cm in diameter. A moulded disc 10 cm in diameter made of ABS is then placed on this layer and a 700 g metal weight is placed on top of this disc. The assembly is then placed in a ventilated oven at a determined temperature for 4 hours. After cooling for 15 minutes, an observation is made as to whether flakes or grains of powder have adhered to the ABS disc and whether there are agglomerates of flakes. Tests were carried out at four different oven temperatures: 35, 40, 45 and 50°C. The temperature selected is that for which no agglomerates of flakes were observed.

This oven caking test is an indication of the tendency of the antistatic agent to form agglomerates on storage of a palette of sacks containing the antistatic agent during hot periods in summer. Consequently, the higher the caking temperature of the antistatic agent, the lower the risk of formation of agglomerates during the manufacture of the stock mixtures.

TABLE 2

Example No.	grafted ABS resin (kg)	TiO ₂ (kg)	Ultramarine blue S1 (kg)	Antistatic agent		MgO (kg)
				A (kg)	Ex 1 (kg)	
Comparative B.	422	209	1.18	24.964	-	3.121
Comparative C	422	209	1.18	71.771	-	3.121
Example 4	422	209	1.18	-	24.264	-
Example 5	422	209	1.18	-	71.771	-

TABLE 3

Appearance of the stock mixture	Comparative Ex. B Agglomerates 20 to 50 mm in diameter	Comparative Ex. C Agglomerates 20 to 50 mm in diameter	Ex. 3 No agglomerates	Ex. 4 No agglomerates
	Antistatic agent Ex. 1			
	75% by weight C ₁₆ -C ₁₈ ethoxylated amines			
	25% by weight calcium stearate			
Oven caking temperature °C	40	50		

Comparative Example D and Examples 5 to 7

Compositions according to the invention and a comparative composition were manufactured by mixing together the ingredients as indicated in Table 4. The physical properties of these compositions have also been indicated in Table 5.

Table 5 shows that the compositions according to the invention have properties which are similar to, if not better than, the compositions of the prior art containing a commercial solid antistatic additive.

TABLE 4
Composition (parts by weight)

Ex. No.	ABS resin ¹	SAN resin ²	Internal lubricant	Antistatic agent			MgO	Carbon black
				A	Ex. 1	Ex. 2	Ex. 3	
Comp.D	30	70	1.3	0.8	-	-	-	0.1
Ex. 5	30	70	1.3	-	0.8	-	-	-
Ex. 6	30	70	1.3	-	-	0.8	-	-
Ex. 7	30	70	1.3	-	-	-	0.8	-

TABLE 5
Physical properties

	Comparative Ex. D	Example 5	Example 6	Example 7
Melt index (220°C/10 kg) g/10 minutes	26.1	24	21.5	24
Capillary rheometer (230°C/1000 s ⁻¹) Pa s	227	227	235	228
Izod impact strength kJ/m ² (1A - 23°C)	13	12.2	12.1	13.2
VICAT B120 °C softening temperature	101	102	102.5	101.5
Brilliance:				
at 20°	54.5	55.5	54	54
at 60°	89	90	91	89.5
Film	204	200	215	216

COMPARATIVE EXAMPLE AND EXAMPLES 8 AND 9

The compositions of Table 6 below were prepared, as in Examples 5 to 7. The physical properties of the compositions were determined as in the above examples. A "dust-repellent" test was also carried out. The results are given in Table 7 below.

TABLE 6
Composition (parts by weight)

Ex. No.	ABS resin ⁴	SAN resin ⁵	Internal Lubricant ³	Antistatic agent			Carbon black
				Ethoxy- lated amines	MgO	Hydro- talcite DHT 4A	
Comp.E	26	74	2	-	-	-	1
Ex 8	26	74	2	0.73	0.07	-	1
Ex 9	26	74	2	0.73	-	0.07	1

TABLE 7

	COMPARATIVE EXAMPLE E	EXAMPLE 8	EXAMPLE 9
Hot melt index (220°C/10kg) g/10min	22.5	24.8	25.8
Capillary rheometer (230°C/1000s ⁻¹) Pa.s	241	236	234
Izod impact strength (1A-23°C) hJ/m ²	11.8	13.2	14.2
VICAT B softening temperature (120°C) °C	103.5	103	102.5
Brilliance			
at 20°	77.5	78	77
at 60°	94	94	93.5
Film	138	104	102
Dust-repellent test	-	+	++
- Poor			
+ Moderate			
++ Good			

The dust-repellent test is performed by spraying iron powder of given particle size for one minute onto plates obtained by injection-moulding of the

compositions. The amount of iron powder which adheres to the plates is determined visually. The lower the amount, the better is the dust-repellent nature of the composition.

1. Resin ABS G350 (GENERAL ELECTRIC PLASTICS ABS S.A.) styrene 37.6%/butadiene 50%/acrylonitrile 12.5%.
2. Resin SAN-S 2856 - acrylonitrile 28%/styrene 72%.
3. Ethylene bis-stearamide wax.
4. TAG 63E (GENERAL ELECTRIC PLASTICS ABS S.A)
5. SAN S 3457 (GENERAL ELECTRIC PLASTICS ABS S.A.)



CLAIMS

1. Solid antistatic agent for a polymer composition, characterized in that it comprises:
 - (a) 40 to 99%, preferably 40 to 95% and better still from 40 to 90%, by weight of a C_{15} to C_{20} ethoxylated amine or a mixture of C_{15} to C_{20} ethoxylated amines; and
 - (b) 60 to 1%, preferably 60 to 5% and better still 60 to 10%, by weight, relative to the total weight of (a) and (b), of a solidification agent chosen from the group consisting of magnesium oxide, zinc oxide, titanium dioxide, barium sulphate, talc, ethylenebis(stearamide) wax, synthetic hydrotalcites of formula $(Mg)_a(Al)_b(CO_3)_x(OH)_y(H_2O)_z$, in which $2 \leq a \leq 6$, $1 \leq b \leq 3$, $1 \leq x \leq 5$, $8 \leq y \leq 14$ and $0 \leq z \leq 3$, and mixtures thereof.
2. Solid antistatic agent according to Claim 1, characterized in that it comprises 70 to 90% by weight of the component (a) and 30 to 10% by weight of the component (b).
3. Solid antistatic agent according to Claim 1 or 2, characterized in that the component (b) is chosen from magnesium oxide, ethylenebis(stearamide) wax and mixtures of one or more compounds chosen from ethylenebis(stearamide), TiO_2 and $BaSO_4$ with $(Mg)_a(Al)_b(CO_3)_x(OH)_y(H_2O)_z$.
4. Antistatic agent according to Claim 1 or 2, characterized in that it comprises 6% by weight of ethylenebis(stearamide) wax, TiO_2 , $BaSO_4$ or mixtures thereof, 7% by weight of $(Mg)_a(Al)_b(CO_3)_x(OH)_y(H_2O)_z$ and 87% by weight of C_{15} - C_{20} ethoxylated amines.
5. Antistatic agent according to any one of Claims 1 to 4, characterized in that the component (a) is a C_{16} - C_{18} ethoxylated amine or a mixture of C_{16} - C_{18} ethoxylated amines.
6. Polymer composition, characterized in that it comprises, per 100 parts by weight of polymer components, from 0.1 to 40, preferably 0.1 to 15, parts by weight of an antistatic agent according to any one of Claims 1 to 5.
7. Composition according to Claim 6, characterized





- 16 -

in that it comprises 0.5 to 2.5 parts by weight of anti-static agent.

8. Composition according to Claim 6 or 7, characterized in that the polymer component is chosen from the group formed by olefin polymers and copolymers and alloys thereof, styrene polymers and alloys thereof, acrylic and methacrylic polymers and copolymers and alloys thereof and vinyl polymers and copolymers and alloys thereof.

9. Composition according to Claim 8, characterized in that the styrene polymers are chosen from polystyrenes, polyalkylstyrenes, high impact strength polystyrenes, emulsion and bulk acrylonitrile/butadiene/styrene (ABS) resins, styrene/acrylonitrile resins, styrene/butadiene/styrene resins and synthetic butyl rubbers, and alloys thereof.

10. Composition according to Claim 9, characterized in that the polymer composition comprises an ABS resin containing from 4 to 70% by weight of butadiene relative to the total weight of the ABS resin.

ABSTRACT

**NOVEL ANTISTATIC AGENT FOR A POLYMER COMPOSITION, USE OF THIS
AGENT IN POLYMER COMPOSITIONS AND COMPOSITIONS OBTAINED**

A solid antistatic agent comprising :

(a) 40 to 99% by weight of a C_{15} - C_{20} ethoxylated amines or a mixture of C_{15} - C_{20} ethoxylated amines; and

(b) 35 to 1% by weight, relative to the total weight of the components (a) and (b) of a solidification component chosen from Magnesium oxide (MgO), Zinc Oxide (ZnO), titanium dioxide, talc, Ethylenebis (Stearamide) wax, barium sulphate ($BaSO_4$), synthetic hydrotalcites and mixtures.

Application and fabrication of compositions of ABS antistatic resins.

This Sheet Has Been Replaced



A 211

- 17 -

ABSTRACT

NOVEL ANTISTATIC AGENT FOR A POLYMER COMPOSITION, USE OF THIS AGENT IN POLYMER COMPOSITIONS AND COMPOSITIONS OBTAINED

A solid antistatic agent comprising :

(a) 40 to 99% by weight of a C_{15} - C_{20} ethoxylated amines or a mixture of C_{15} - C_{20} ethoxylated amines; and

(b) 60 to 1% by weight, relative to the total weight of the components (a) and (b) of a solidification component chosen from Magnesium oxide (MgO), Zinc Oxide (ZnO), titanium dioxide, talc, Ethylenebis (Stearamide) wax, barium sulphate ($BaSO_4$), synthetic hydrotalcites and mixtures.


Application and fabrication of compositions of ABS antistatic resins.

THIS SHEET HAS BEEN
REPLACED


15 SEP 1997

This Sheet Has Been Replaced





- 1 -



Novel antistatic agent for a polymer composition, use of this agent in polymer compositions and compositions obtained.

The present invention relates generally to antistatic agents for polymer compositions.

It is known, in order to prevent dust from being deposited on articles moulded from polymer compositions, such as moulded articles made of acrylonitrile-butadiene-styrene (ABS) resin, to incorporate an antistatic or antidust agent into these compositions.

In moulding compositions, in particular ones based on ABS resin, ethoxylated C_{13} - C_{15} amines have usually been used as antistatic agents. These ethoxylated amines are in liquid form.

In industrial production, the liquids are difficult to handle. The liquid antistatic agent is generally injected during extrusion of the polymer composition close to the die, which gives rise to the risk of fire.

Moreover, when the technique of stock mixtures is used, that is to say the technique consisting in preparing a premix of the adjuvants with some of the resinous components of the polymer composition, the premix has a tendency to form agglomerates which stick to the walls of the supply and metering system during the formation of the final composition on a twin-screw extruder.

Furthermore, the liquid antistatic agent is packaged in drums and it is not possible to extract all of the contents of the drum, which leads to a loss of starting material and an increase in the manufacturing costs.

Lastly, when such a liquid antistatic agent is used, dispersed in an article made of moulded plastic, for example one based on ABS resin, the additive has a tendency to migrate towards the surface of the moulded article and to form a whitish film there, which reduces the sheen and the aesthetic appearance of this moulded article.

22 FEB 1999

- 2 -

In order to overcome the drawbacks of liquid antistatic agents, it has been envisaged to use solid antistatic agents. Solid antistatic agents which have been envisaged are ethoxylated $C_{16}-C_{18}$ amines which are in pasty form. Another solid antistatic agent, which is commercially available from the company CECA, consists of 75 parts by weight of ethoxylated $C_{16}-C_{18}$ amines and 25 parts by weight of calcium stearate.

However, these known solid antistatic agents still have the drawback of forming agglomerates when they are used in the stock mixture technique, in particular with ABS resins loaded with pigments and dyes such as TiO_2 . The formation of these brittle agglomerates greatly disrupts the supply and metering of the stock mixture during the formulation of the final composition on a twin-screw extruder.

The object of the present invention is thus to provide a novel solid antistatic agent which overcomes the drawbacks mentioned above for liquid/solid antistatic agents and which avoids the formation of brittle agglomerates, in particular when it is used in the technique of stock mixtures.

According to the invention, the above aims are achieved by preparing an antistatic agent which com-

(a) 40 to 99% by weight of a ethoxylated $C_{15}-C_{20}$ amine, preferably ethoxylated $C_{16}-C_{18}$ amine or a mixture of ethoxylated $C_{15}-C_{20}$ amine, preferably ethoxylated $C_{16}-C_{18}$ amines; and

(b) 50 to 1% by weight, relative to the total weight of the components (a) and (b), of a solidification component chosen from magnesium oxide (MgO), zinc oxide (ZnO), titanium dioxide (TiO_2), barium sulphate ($BaSO_4$), talc, ethylenebis(stearamide) wax, synthetic hydro-talcites of formula $(Mg)_a(Al)_b(CO_3)_x(OH)_y(H_2O)_z$, in which $2 \leq a \leq 6$, $1 \leq b \leq 3$, $1 \leq x \leq 5$, $8 \leq y \leq 14$ and $0 \leq z \leq 3$, and mixtures thereof.

Preferably, the antistatic agent according to the invention comprises 40 to 95%, and better still 40 to 90%, by weight of ethoxylated $C_{15}-C_{20}$ amines and 60 to 5%,

22 FEB 1999

- 3 -

and better still 60 to 10%, by weight of solidification component.

Even more preferably, the solid antistatic agent comprises from 70 to 90% by weight of a ethoxylated C₁₅-C₂₀ amine or a mixture thereof and 30 to 10% by weight of the solidification component.

The solidification components recommended are magnesium oxide, ethylenebis(stearamide) wax, hydrotalcites and mixtures of TiO₂ and BaSO₄ with (Mg)_a(Al)_b(CO₃)_x(OH)_y(H₂O)_z where a, b, x, y and z are defined as above.

The use of hydrotalcite as a solidification component also has the advantage that, when mixed with the ethoxylated amine, this compound leads to a synergum which improves the antistatic properties of the final compositions surprisingly.

Synthetic hydrotalcites are known compounds, which are commercially available, for example under the name DHT4A from the company Kowa or L55R2 from the company Reheis.

The ethoxylated C₁₅-C₂₀ amines are well-known compounds which are commercially available from various companies, such as Akzo, ICI and Ceca-Atochem.

Recommended antistatic compositions according to the invention comprise, relative to the total weight of the antistatic agent, 6% by weight of MgO, ZnO, talc, ethylenebis(stearamide) wax, TiO₂ or BaSO₄, 7% by weight of (Mg)_a(Al)_b(CO₃)_x(OH)_y(H₂O)_z and 87% by weight of one or more ethoxylated C₁₅-C₂₀amines. Among the latter antistatic compositions, the ones most recommended are those containing 6% by weight of TiO₂, BaSO₄ or of ethylenebis(stearamide) wax.

The present invention also relates to polymer compositions comprising, per 100 parts by weight of polymer components, from 0.1 to 40, preferably 0.1 to 15, parts by weight of an antistatic agent according to the invention. Preferably, the antistatic agent is present in an amount of from 0.5 to 2.5 parts by weight relative to the weight of the polymer components of the composition.


acid and thus to avoid corrosion of the moulds during moulding of the compositions. It is recommended in this case to use an amount of from 0.1 to 0.15 parts by weight of magnesium oxide per 100 parts of polymer components of the composition. Obviously, when an antistatic agent according to the invention which already contains magnesium oxide or hydrotalcite is used, it is not necessary to make a further addition thereof to the compositions.

The examples which follow are intended to illustrate the invention. In the examples, except where otherwise mentioned, all the percentages and parts are expressed by weight.

Comparative example A and Examples 1 to 3

In Examples 1 to 3, antistatic agents according to the invention were prepared by mixing together the constituents indicated in Table 1 below. Table 1 also indicates an antistatic additive (A) marketed by the company Ceca and comprising 75% by weight of ethoxylated C_{16} - C_{18} amines and 25% by weight of calcium stearate.

Table 1 also indicates the physical properties of these antistatic additives.



CLAIMS

1. Solid antistatic agent for a polymer composition consisting of:

(a) 40 to 99% by weight of an ethoxylated C_{15} to C_{20} amine or a mixture of ethoxylated C_{15} to C_{20} amines;

(b) 60 to 1% of a solidification agent selected from the group consisting of:

magnesium oxide, zinc oxide, titanium oxide, barium sulfate, talc, ethylenebis (stearamide) wax, synthetic hydrotalcites of the formula $(Mg)_a(Al)_b(CO_3)_x(OH)_y(H_2O)_z$, in which $2 \leq a \leq 6$, $1 \leq b \leq 3$, $1 \leq x \leq 5$, $8 \leq y \leq 14$ and $0 \leq z \leq 3$, and mixtures thereof, and

(c) from 0 to 6% by weight of silica, alumina or a mixture thereof, each based on the combined weight of (a), (b) and (c).

2. Solid antistatic agent according to Claim 1, characterized in that it comprises 70 to 90% by weight of the component (a) and 30 to 10% by weight of the component (b).

3. Solid antistatic agent according to Claim 1 or 2, characterized in that the component (b) is selected from the group consisting of:

magnesium oxide and ethylenebis (stearamide) wax and mixtures thereof.

4. Antistatic agent according to Claim 1 or 2, characterized in that it comprises 6% by weight of ethylenebis(stearamide) wax, TiO_2 , $BaSO_4$ or mixtures thereof, 7% by weight of $(Mg)_a(Al)_b(CO_3)_x(OH)_y(H_2O)_z$ and 87% by weight of ethoxylated C_{15} - C_{20} amines.

5. Antistatic agent according to any one of Claims 1 to 4, characterized in that the component (a) is a ethoxylated C_{16} - C_{18} amine or a mixture of ethoxylated C_{16} - C_{18} amines.


6. Polymer composition, characterized in that it comprises, per 100 parts by weight of polymer components, from 0.1 to 40, preferably 0.1 to 15, parts by weight of an antistatic agent according to any one of Claim 1 to 5.

7. Composition according to Claim 6, characterized

REPLACEMENT SHEET

22 FEB 1999

ABSTRACT



NOVEL ANTISTATIC AGENT FOR A POLYMER COMPOSITION, USE OF THIS
AGENT IN POLYMER COMPOSITIONS AND COMPOSITIONS OBTAINED

A solid antistatic agent comprising:

(a) 40 to 99% by weight of a ethoxylated C_{15} - C_{20} amines or a mixture of ethoxylated C_{15} - C_{20} amines; and

(b) 35 to 1% by weight, relative to the total weight of the components (a) and (b) of a solidification component chosen from Magnesium oxide (Mgo), Zinc Oxide (ZnO), titanium dioxide, talc, Ethylenebis (stearamide) wax, barium sulphate ($BaSO_4$), synthetic hydrotalcites and mixtures.

Application and fabrication of compositions of ABS antistatic resins.

This Sheet Has Been Replaced

