

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08J 3/12, C09D 127/12, 5/03, B29B 9/08 // C08L 27:12		A1	(11) International Publication Number: WO 00/58389
			(43) International Publication Date: 5 October 2000 (05.10.00)
(21) International Application Number: PCT/US00/08361		(81) Designated States: AU, BR, CN, IN, JP, KR, MX, RU, SG, TR, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 30 March 2000 (30.03.00)			
(30) Priority Data: 60/127,112 31 March 1999 (31.03.99) US 60/154,742 17 September 1999 (17.09.99) US		Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.	
(71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).			
(72) Inventors: FELIX, Vinci, Martinez; 437 East Street Road, Kennett Square, PA 19348 (US). HUESMANN, Peter, L.; 1103 Carcroft Boulevard, Wilmington, DE 19803 (US).			
(74) Agent: STEINBERG, Thomas, W.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		 *G00001*	
(54) Title: SPRAYABLE POWDER OF NON-FIBRILLATABLE FLUOROPOLYMER			
(57) Abstract			
The invention provides for sprayable powder comprising friable granules of agglomerated primary particles of non-fibrillatable fluoropolymer and, optionally, at least one other component, the powder having a bulk density of at least 20g/100cc and average particle size of 5 to 100 micrometers. The sprayable powder is preferably free of water immiscible liquid, and more preferably free of halocarbon liquid. Included among the other components are inorganic fillers, pigments, high temperature resistant polymer binders. In an other embodiment, the invention provides for a sprayable powder comprising friable granules of agglomerated primary particles of a first non-fibrillatable fluoropolymer and at least one other non-fibrillatable component. The invention further provides for a process for preparing the sprayable powder by spray drying a liquid dispersion. In a preferred embodiment, the process includes densifying the granules of agglomerated primary particles that result from spray drying. Densifying may be carried out by mechanical compaction or by contacting the granules with a heated gas to form a fluidized bed. Optional steps of communication and heat treatment may be employed to achieve a desired bulk density and particle size for specific applications.			
 *162162*			