

DESCRIPTION

Title of Invention

5 ETCHING SOLUTION FOR TITANIUM-BASED METAL, TUNGSTEN-BASED
METAL, TITANIUM/TUNGSTEN-BASED METAL OR THEIR NITRIDES

Technical Field

10 The present invention relates to an etching solution
for titanium-based metals, tungsten-based metals,
titanium/tungsten-based metals, or their nitrides. In
particular, the invention relates to an etching solution
with excellent selective etching properties for titanium-
based metals, tungsten-based metals, titanium/tungsten-
based metals or their nitrides, with respect to metals
15 other than titanium-based metals, tungsten-based metals
and titanium/tungsten-based metals.

Background Art

20 Titanium metal (Ti), titanium nitride (TiN) and
titanium alloys, as titanium-based metals, are utilized
for semiconductor devices, liquid crystal displays, MEMS
(Micro Electro Mechanical Systems), printed wiring boards
and the like, and as ground layers and cap layers for
precious metal, aluminum (Al) and copper (Cu) wiring. In
25 semiconductor devices, they are also used as barrier
metals and gate metals.

Methods of treatment with hydrofluoric acid/nitric
acid mixtures and hydrogen peroxide/hydrofluoric acid
mixtures are known for common titanium-based metal
30 etching, but because these contain hydrofluoric acid,
they introduce the drawback of corrosion of silicon
substrates and glass substrates as well. Another problem
is that metals in the devices that are prone to
corrosion, such as Al wirings, also undergo etching.

35 Hydrogen peroxide/ammonia/EDTA
(ethylenediaminetetraacetic acid) mixtures and hydrogen
peroxide/phosphate mixtures have been disclosed as means

of overcoming the drawbacks of such solutions (PTL 1 and 2). However, these have low titanium-based metal etching rates, while decomposition of hydrogen peroxide is rapid, making stable etching impossible, and therefore etching solutions comprising hydrogen peroxide/phosphoric acid/ammonia mixtures have been proposed as modifications of such solutions (PTL 3). With such etching solutions, however, the etching rate is improved but intense foaming of the etching solution causes attachment of bubbles onto the substrate surface, and etching does not proceed at the bubble-attached parts. Another problem is the low etching rate due to foaming and decomposition of the hydrogen peroxide water. Such mixtures are used with adjustment to a designated pH with ammonia, but even slight differences in pH alter the etching rate and foaming condition, and can be problematic from the viewpoint of stability of the etching conditions.

There is also disclosed a semiconductor cleaning solution comprising an organic acid ammonium salt in hydrogen peroxide/ammonia/water, as a hydrogen peroxide-containing cleaning solution (PTL 4). However, the semiconductor cleaning solution is a cleaning solution that removes extraneous contaminant such as fine particles adhering to the substrate in the semiconductor production process, and although it is stated that the difference in etching rates between doped oxide films and non-doped oxide films is minimal, nothing at all is mentioned regarding etching of titanium-based metals. In PTL 5 there is disclosed a composition for removal of resist residue, comprising hydrogen peroxide/carboxylate/water. The purpose of the composition is removal of resist residue after ashing of the resist, and it is not intended for etching of titanium-based metals.

Tungsten or tungsten alloys are used for gate electrodes of thin-film transistors, wirings, barrier layers, or for filling of contact holes or via holes in

liquid crystal displays and semiconductor devices. They are also used as tungsten heaters in MEMS (Micro Electro Mechanical Systems).

5 Tungsten or tungsten alloys are usually formed into films by CVD or sputtering. When films are formed by these methods, however, they also adhere on substrate (wafer) back sides, on substrate (wafer) edges, on the external walls of film-forming apparatuses and in exhaust pipes, in addition to the actual element-forming areas in the semiconductor devices, and they peel off and cause to produce extraneous material on the element-forming areas. This is sometimes countered by removing the unwanted film with an etching solution. In addition to measures against extraneous material, it is preferable to employ highly productive wet etching instead of dry etching for tungsten or tungsten alloys in the production steps of semiconductor devices, liquid crystal display apparatuses and MEMS devices. Wet etching is particularly suitable for liquid crystal displays and MEMS devices which do not require the same level of working precision as semiconductor devices.

20 Mixtures of hydrofluoric acid and nitric acid are widely known as etching solutions and removing solutions for tungsten-based metals (Non-PTL 1, for example), but these are not preferred because silicon substrates or silicon dioxide films and glass substrates also dissolve. Another problem is that metals that are prone to corrosion, such as Al wirings, in the devices are also etched. Hydrogen peroxide water-based etching solutions are also known from PTL 6-9, for example, and PTL 9 summarizes in detail the problems of conventional hydrogen peroxide-based etching solutions. According to this publication, the etching speed is slow and the pH varies as tungsten dissolves, resulting in a variable etching rate and poor etching selectivity. In addition, it is stated that dissolution of tungsten drastically increases the hydrogen peroxide decomposition rate. A

mixture of azole added to hydrogen peroxide is disclosed as a solution for this problem (PTL 8), but inhibition of hydrogen peroxide decomposition is still insufficient, and the etching rate is not stable. Thus, no practical hydrogen peroxide water-based etching solution yet exists which has a stable tungsten etching rate, high tungsten etching selectivity and a long solution life.

Prior Art Reference

Patent literature

- PTL 1 Japanese Unexamined Patent Publication No. 08-013166
PTL 2 Japanese Unexamined Patent Publication No. 2000-311891
PTL 3 Japanese Unexamined Patent Publication No. 2005-146358
PTL 4 Japanese Unexamined Patent Publication No. 10-284452
PTL 5 Japanese Unexamined Patent Publication No. 2005-183525
PTL 6 Japanese Unexamined Patent Publication SHO No. 62-143422
PTL 7 Japanese Unexamined Patent Publication No. 8-250462
PTL 8 Japanese Unexamined Patent Publication No. 2002-53984
PTL 9 Japanese Unexamined Patent Publication No. 2004-31791

Non-patent literature

- Non-PTL 1: Sakamoto, M., ed., Shima, K., publ., "Semiconductor Production Process Materials and Chemicals", September 30, 2006, 1st Edition, p.144.

Summary of the Invention

Problems to be Solved by the Invention

- The invention, which overcomes the problems mentioned above, provides an etching solution for titanium-based metals, tungsten-based metals,

titanium/tungsten-based metals or their nitrides, which reduces non-uniform etching of targets to be etched and has a stable etching rate, by minimizing foaming of the etching solution during etching. In addition, it provides an etching solution with no corrosion of substrates and with excellent selective etching properties for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, with respect to metals other than titanium-based metals, tungsten-based metals and titanium/tungsten-based metals.

Means for Solving the Problems

As a result of much diligent research directed toward solving the aforementioned problems, the present inventors have found that using an aqueous solution comprising hydrogen peroxide and an organic acid salt can minimize foaming of the etching solution and reduce non-uniform etching of targets to be etched, and can stabilize the etching rate. It was further found that using an etching solution of the invention allows selective etching of titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, without etching of other metals such as nickel, copper or aluminum or base materials (glass, silicon, silicon oxide, silicon nitride), and the present invention has been completed upon this finding.

Specifically, the invention comprises the following aspects, for example.

[1] An etching solution for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, which comprises 10-40 mass% hydrogen peroxide, 0.1-15 mass% of an organic acid salt, and water.

[2] An etching solution for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, which consists of 10-40 mass% hydrogen peroxide, 0.1-15 mass% of an organic acid salt, and

water.

[3] An etching solution for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, according to [1], which further comprises
5 0.005-4.5 mass% ammonia.

[4] An etching solution for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, according to any one of [1] to [3], wherein the organic acid salt is at least one selected
10 from among ammonium salts of citric acid, formic acid, oxalic acid, acetic acid, tartaric acid, benzoic acid and succinic acid.

[5] An etching solution for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, according to [4], wherein the ammonium
15 salt of an organic acid is at least one selected from among diammonium hydrogen citrate, triammonium citrate, ammonium oxalate, ammonium formate and ammonium acetate.

[6] An etching solution for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, according to any one of [1] to [5], wherein the ratio of the etching rate for titanium-based
20 metals or their nitrides to that for Al, Ni, Cu, Cr, Ru, Ta, Si or alloys composed mainly of these elements, is at least 20.
25

[7] An etching solution for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, according to any one of [1] to [5], wherein the ratio of the etching rate for titanium-based
30 metals or their nitrides to that for glass, silicon, silicon oxide or silicon nitride, is at least 20.

[8] A method for producing an electronic device, which comprises a step of etching a titanium-based metal, tungsten-based metal, titanium/tungsten-based metal or a
35 nitride thereof using an etching solution according to any one of [1] to [7].

Effect of the Invention

The etching solution of the invention has an excellent selective etching property for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, with respect to metals other than titanium-based metals, tungsten-based metals and titanium/tungsten-based metals, or base materials (glass, silicon, silicon oxide), as well as little foaming, and therefore using the etching solution of the invention allows uniform etching to be accomplished for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides.

Brief Description of the Drawings

Fig. 1 is a graph showing the change in titanium etching rate with time for etching solutions having the compositions of Example 1 and Comparative Example 3.

Fig. 2 is a photograph showing the foamed state of a Ti film-attached sample piece when dipped in the etching solution of Example 1.

Fig. 3 is a photograph showing the foamed state of a Ti film-attached sample piece when dipped in the etching solution of Comparative Example 3.

Fig. 4 is a graph showing the change in titanium/tungsten (TiW) etching rate with time for etching solutions having the compositions of Example 12 and Comparative Example 2.

Modes for Carrying Out the Invention

The invention will now be explained in greater detail.

The etching solution for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, according to the invention, comprises an aqueous solution containing hydrogen peroxide and an organic acid salt.

The hydrogen peroxide is present in the etching

solution at 10-40 mass%, more preferably 15-35 mass% and even more preferably 20-35 mass%. If the hydrogen peroxide concentration is lower than 10 mass%, the etching rate for titanium, tungsten or titanium/tungsten alloys will be reduced, making it impractical. If the hydrogen peroxide concentration is higher than 40 mass%, on the other hand, more hydrogen peroxide will decompose, likewise making it impractical.

The organic acid salts useful for the invention are not particularly limited, but when an organic acid salt is used for production of an electronic device such as a semiconductor which is preferably void of metal impurities, it is more preferred to use an ammonium salt.

The organic acid salt is present in the etching solution at 0.1-15 mass%, more preferably 1-10 mass% and even more preferably 3-8 mass%. If the organic acid salt concentration is lower than 0.1 mass%, the etching rate will be reduced, making it impractical. If the concentration is higher than 15 mass%, there will be no significant increase in the etching rate.

The organic acid salt is not particularly restricted, and may be a salt of citric acid, formic acid, oxalic acid, acetic acid, tartaric acid, succinic acid, malic acid, maleic acid, malonic acid, glutaric acid, adipic acid, D-glucanic acid, itaconic acid, citraconic acid, mesaconic acid, 2-oxoglutaric acid, trimellitic acid, endothal, glutamic acid, methylsuccinic acid, citramalic acid or the like. As a result of evaluating etching properties for titanium-based metals, tungsten-based metals or their nitrides, the present inventors have found that neutral etching solutions rather than acidic ones tend to have higher etching rates. An organic acid salt is used for this reason. Salts of citric acid, formic acid, oxalic acid, acetic acid, tartaric acid and succinic acid are preferred, with diammonium hydrogen citrate, triammonium citrate, ammonium oxalate, ammonium formate and ammonium

acetate being even more preferred. These may be used alone or in combinations of two or more. An organic acid ammonium salt may be used as the organic acid ammonium salt itself, or it may be used as the reaction product of the organic acid and ammonia in the etching solution, without any particular restrictions.

Ammonia may be added as necessary to increase the etching rate of the titanium-based metal, tungsten-based metal, titanium/tungsten-based metal or its nitride. When ammonia is added, the concentration in the etching solution is in the range of 0.005-4.5 mass%, more preferably 0.05-2 mass% and even more preferably 0.1-0.5 mass%. If the ammonia concentration is higher than 4.5 mass%, the etching rate for titanium-based metals, tungsten-based metals or their nitrides will increase, but metals in the device that are prone to corrosion by alkalis, such as Al, will also be etched, and this is therefore undesirable.

The etching solution of the invention having the composition described above has little foaming during etching of titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, and it therefore allows uniform etching. The etching solution of the invention is superior in that it has a low etching rate for metals other than titanium-based metals, tungsten-based metals and titanium/tungsten-based metals, or base materials (glass, silicon, silicon oxide, silicon nitride), and the selective etching property for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides (the ratio of the etching rate for titanium-based metals, tungsten-based metals or their nitrides with respect to the etching rate for metals other than titanium-based metals and tungsten-based metals or base materials (glass, silicon, silicon oxide, silicon nitride)) is at least 20. The etching solution of the invention may also contain components other than those mentioned above, such

as moistening agents, surfactants, coloring agents, foam inhibitors and organic solvents, in ranges that do not affect the etching property.

5 The term "titanium-based metal" as used herein means titanium metal (Ti), or an alloy comprising titanium as the main component (at least 70 mass%). A titanium-based metal nitride means a nitride of titanium metal or a titanium alloy, of which titanium nitride is a typical example. A specific example of a titanium alloy is 10 titanium silicide (TiSi). Similarly, "tungsten-based metal" means tungsten metal (W) or an alloy comprising tungsten as the main component (at least 70 mass%). A nitride of a tungsten metal is a nitride of tungsten metal or a tungsten alloy, of which tungsten nitride is a 15 typical example. Specific examples of tungsten alloys include molybdenum-tungsten (MoW) and tungsten silicide (WSi).

 The term "titanium/tungsten-based metal" as used herein means an alloy including both titanium and 20 tungsten, with a total of at least 70 mass% of both. A nitride of a titanium/tungsten-based metal is a nitride of such a titanium/tungsten alloy.

 The method of forming a film of the titanium-based metal, tungsten-based metal or titanium/tungsten-based 25 metal on the substrate is not particularly restricted, and any method such as CVD, sputtering or vapor deposition may be used, while the film-forming conditions also are not restricted. A metal other than a titanium-based metal, tungsten-based metal or titanium/tungsten-based 30 metal, as used herein, is Al, Ni, Cu, Cr, Ru, Ta, Si or an alloy comprising any of these elements as the main component (70 mass% or greater) (or a total of 70 mass% or greater when it contains more than one element), and it may contain the other elements.

35 There are no particular restrictions on the device employing the titanium-based metal, tungsten-based metal, titanium/tungsten-based metal or its nitride, and it may

be used in general electronic devices. An electronic device in this case is a liquid crystal display, semiconductor device, MEMS device, printed wiring board, organic EL display, field emission display, electronic
5 paper, plasma display, or the like. The term "etching" as used herein refers to a process utilizing the etching phenomenon, and it naturally includes patterning of titanium-based metals, tungsten-based metals and titanium/tungsten-based metals, as well as purposes of
10 cleaning off of titanium-based metal, tungsten-based metal or titanium/tungsten-based metal residues. Thus, the electronic device may further include electronic devices of which production process has a step of dissolving off of the entirety of the titanium-based
15 metal, tungsten-based metal or titanium/tungsten-based metal by an etching solution, even if no titanium, tungsten or titanium/tungsten alloy remains on the final product.

Treatment of a titanium-based metal, tungsten-based
20 metal or titanium/tungsten-based metal, or a nitride thereof, with an etching solution according to the invention will usually be accomplished by a dipping method, but other methods such as spraying or spin etching may be used for the treatment. The conditions
25 for treatment by dipping cannot be specified for all cases since they will differ depending on the hydrogen peroxide concentration, the organic acid ammonium salt type and content, and the film thickness of the titanium-based metal, tungsten-based metal, titanium/tungsten-
30 based metal or nitride thereof, but generally the treatment temperature will be 20-80°C and more preferably 30-60°C. Such treatment may also be carried out while applying ultrasonic waves.

35 Examples

The present invention will now be explained in greater detail based on examples and comparative

examples, with the understanding that the invention is not limited to these descriptions.

Measurement of Ti, W and Al etching rates

5 Sample substrates having Ti, W and Al films formed by sputtering (film thickness: 50 nm each) of Ti, W or Al on a non-alkaline glass substrate for an LCD (liquid crystal display) were each cut to approximately 0.5 cm square to obtain sample pieces. In a 100 ml beaker there was loaded 20 ml of an etching solution having the
10 composition of each of the examples and comparative examples listed in Table 1 below, and heating was performed to 50°C. One each of the Ti, W, Al film-attached sample pieces was simultaneously loaded into the etching solution, and the time until total disappearance of each sputtering film was visually observed. The same
15 measurement was conducted 3 times, and the average values for the etching rates of Ti, W and Al were calculated. Table 1 summarizes the etching rates for each of the examples and comparative examples. The portion in
20 addition to the constituent components of each etching solution shown in Table 1 is water (ultrapure water). The etching solutions of the examples and comparative examples were each prepared with their compositions, with ultrapure water as necessary, using a specialty product
25 of 35 mass% hydrogen peroxide water by Kishida Chemical Co., Ltd., EL grade 28 mass% ammonia water by Kanto Kagaku Co., Ltd., and a commercially available organic acid ammonium salt.

30 Measurement of etching rates for metals other than Ti, W and Al

Ni, Cu, Cr, Ru, Ta, Si film-attached sample pieces were used for measurement in the same manner as measurement of the Ti, W and Al etching rates, except
35 that the sputtering film materials were changed from Ti, W and Al to Ni, Cu, Cr, Ru, Ta and Si, and the etching rates were calculated. Table 2 below shows the results

of measurement using etching solutions having the compositions of Examples 1, 2 and 3.

Measurement of change in Ti etching rate

5 In a 100 ml beaker there was loaded 20 ml of an etching solution having the composition of Example 1 in Table 1, and heating was performed to 50°C. One Ti film-attached sample piece was loaded into the etching solution kept at 50°C. With the sample piece-loading point as the starting point (0 hours), one Ti film-attached sample piece was loaded every hour thereafter while keeping the temperature at 50°C, and the etching rate up to 6 hours thereafter was measured. The method of measuring the etching rate was the same as the method described above. As a comparative example, an experiment was conducted in the same manner using an etching solution comprising 30 mass% hydrogen peroxide, 0.3 mass% phosphoric acid, 0.02 mass% ammonia and 69.68 mass% ultrapure water (Comparative Example 3). The results are shown in Fig. 1.

Evaluation of foaming condition of etching solution

 An etching solution having the composition of Example 1 in Table 1 was prepared and kept at a constant temperature of 50°C. A 0.5 cm-square Ti film (50 nm thickness)-attached sample piece was dipped in the etching solution for 1 minute. The foaming condition of the solution at that time was recorded in a photograph. As a comparative example, the foaming condition was evaluated in the same manner using an etching solution comprising 30 mass% hydrogen peroxide, 0.3 mass% phosphoric acid, 0.02 mass% ammonia and 69.68 mass% ultrapure water (Comparative Example 3). The results are shown in Figs. 2 and 3.

Measurement of change in TiW etching rate

In a 50 ml beaker there was loaded 20 ml of an etching solution having the composition of Example 12 in Table 1, and heating was performed to 45°C. One TiW film-attached silicon wafer piece (approximately 0.5 cm square, TiW film thickness: 200 nm) was loaded into the etching solution kept at 45°C. With the sample piece-loading point as the starting point (0 hours), one TiW film-attached sample piece was loaded every 6 hours thereafter while keeping the temperature at 45°C, and the etching rate was measured up to 66 hours thereafter. The method of measuring the etching rate was the same as the method described above. As a comparative example, an experiment was conducted in the same manner using an etching solution comprising 30 mass% hydrogen peroxide and 70 mass% ultrapure water (Comparative Example 2). The results are shown in Fig. 4. The TiW composition used was 10 mass% Ti, 90 mass% W.

Table 1

		H ₂ O ₂ (mass%)	NH ₃ (mass%)	Organic acid/organic acid salt		Etching rate (nm/min)			Selectivity	
				Type	Conc. mass%	Ti	W	Al	Ti/Al	W/Al
Examples	1	30	0.1	Triammonium citrate	5.0	100	375	<1.0	>100	>375
	2	30	0.1	Ammonium formate	5.0	91	250	1.4	65	179
	3	30	0.1	Ammonium oxalate	5.0	83	333	1.1	75	302
	4	30	0.01	Ammonium acetate	5.0	60	600	<1.0	>60	>600
	5	30	0.1	Ammonium tartrate	5.0	64	250	<1.0	>64	>250
	6	30	0.1	Ammonium benzoate	5.0	55	300	<1.0	>55	>300
	7	30	0.1	Ammonium succinate	5.0	75	333	<1.0	>75	>333
	8	20	0.1	Triammonium citrate	5.0	75	300	<1.0	>75	>300
	9	20	0.5	Triammonium citrate	3.0	86	800	3.8	23	211
	10	30	2.0	Diammonium hydrogen citrate	5.0	250	800	4.0	63	200
	11	30	0.1	Triammonium citrate	15	75	375	<1.0	>75	>375
	12	30	0.0	Triammonium citrate	5.0	55	300	<1.0	>55	>300
	13	30	0.0	Ammonium formate	5.0	60	215	<1.0	>60	>215
	14	30	0.0	Ammonium oxalate	5.0	33	231	<1.0	>33	>231
	15	30	0.0	Ammonium acetate	5.0	60	300	<1.0	>60	>300
	16	30	0.0	Ammonium tartrate	5.0	25	200	<1.0	>25	>200
	17	30	0.0	Ammonium benzoate	5.0	33	200	<1.0	>33	>200
	18	30	0.0	Ammonium succinate	5.0	55	300	<1.0	>55	>300
	19	30	0.0	Tripotassium citrate	5.0	50	300	<1.0	>50	>300
	20	30	0.0	Trisodium citrate	5.0	50	300	<1.0	>50	>300
	21	30	0.0	Sodium oxalate	5.0	23	200	<1.0	>23	>200
	22	30	0.0	Sodium acetate	5.0	50	300	<1.0	>50	>300
	23	30	0.0	Potassium benzoate	5.0	24	200	<1.0	>24	>200
	24	30	0.0	Sodium benzoate	5.0	25	200	<1.0	>25	>200
	25	30	0.1	Triammonium citrate	0.5	67	210	<1.0	>67	>65
	26	15	0.2	Triammonium citrate	5.0	51	180	<1.0	>51	>180
Comp. Examples	1	5	0.1	Triammonium citrate	5.0	15	40	<1.0	>15	>40
	2	30	0.0	-	0.0	11	150	<1.0	>11	>150

Table 2

	Cu	Ni	Ru	Ta	Cr	Si	SiO ₂	Si ₃ N ₄
Example 1	<1.0	<1.0	<1.0	<1.0	<1.0	<1.0	<1.0	<1.0
Example 2	<1.0	<1.0	<1.0	<1.0	<1.0	<1.0	<1.0	<1.0
Example 3	<1.0	<1.0	<1.0	<1.0	<1.0	<1.0	<1.0	<1.0

5 As shown in Table 1, the ratio of the etching rate
for Ti and W to the etching rate for Al, using etching
solutions having the compositions of Examples 1-26, was
20 or higher, indicating an excellent selective etching
property for Ti and W. The etching rate was generally
10 satisfactory, at greater than 50 nm/min, although the Ti
etching rate was somewhat lower with some of the
compositions. On the other hand, all of the W etching
rates were satisfactory at 150 nm/min or greater. In
contrast, both the Ti and W etching rates were
15 inadequately low at below 50 nm/min with the etching
solution of Comparative Example 1. The Ti etching rate
was also inadequately low at below 50 nm/min in
Comparative Example 2.

20 Table 2 shows that the etching solutions of the
invention had low etching rates for Ni, Cu, Cr, Ru, Ta,
Si, SiO₂ and Si₃N₄ as for Al, and therefore had
satisfactory selective etching properties for titanium
and tungsten with respect to these as well. In addition,
Fig. 1 shows that the reduction in titanium etching rate
25 with time was lower with the etching solutions of the
invention, and therefore excellent stability was
exhibited. With the etching solution of Comparative
Example 3, on the other hand, the initial Ti etching rate
(150 nm/min) was higher than the etching solution in
30 Example 1, but the change (reduction) in the etching rate
with time was large, and therefore the stability was
inferior.

35 When the etching rates were measured for WN, TiW and
TiN in the same manner as the composition of Example 1,
they were found to be 320 nm/min, 200 nm/min and 120

nm/min, respectively. The TiW composition was 10 mass% and 90 mass% for Ti and W, respectively. The WN and TiN used had the compositions represented by their chemical formulas.

5 Figs. 2 and 3 show the foaming conditions of the etching solutions when a Ti film-attached sample piece was loaded into each etching solution. The photographs are taken from above the beaker. Considerable foaming of the etching solution is seen in Fig. 3 (the etching
10 solution of Comparative Example 3), but virtually none is seen in Fig. 2 (the etching solution of Example 1). This demonstrated that an etching solution of the invention is advantageous for uniform etching of titanium-based metals, because it has little foaming during etching.

15 Fig. 4 shows that the reduction in TiW etching rate with time was lower with the etching solutions of the invention, and therefore excellent stability was exhibited. With the etching solution of Comparative
20 Example 2, on the other hand, the change (reduction) in the TiW etching rate (50 nm/min) with time was large, and therefore the stability was inferior.

Industrial Applicability

25 By using an etching solution according to the invention it is possible to accomplish uniform etching of titanium, tungsten and alloys thereof, or their nitrides. In addition, an etching solution of the invention has a low etching rate for other metals such as copper, nickel and aluminum, and for glass, silicon and silicon oxide
30 films, and is therefore useful for production of electronic devices such as semiconductor devices and liquid crystal displays, without damage to substrates and silicon oxide films.

CLAIMS

1. An etching solution for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, which comprises 10-40 mass% hydrogen peroxide, 0.1-15 mass% of an organic acid salt, and water.

2. An etching solution for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, which consists of 10-40 mass% hydrogen peroxide, 0.1-15 mass% of an organic acid salt, and water.

3. An etching solution for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, according to claim 1, which further comprises 0.005-4.5 mass% ammonia.

4. An etching solution for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, according to any one of claims 1 to 3, wherein the organic acid salt is at least one selected from among ammonium salts of citric acid, formic acid, oxalic acid, acetic acid, tartaric acid, benzoic acid and succinic acid.

5. An etching solution for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, according to claim 4, wherein the ammonium salt of an organic acid is at least one selected from among diammonium hydrogen citrate, triammonium citrate, ammonium oxalate, ammonium formate and ammonium acetate.

6. An etching solution for titanium-based metals, tungsten-based metals, titanium/tungsten-based metals or their nitrides, according to any one of claims 1 to 5, wherein the ratio of the etching rate for titanium-based metals or their nitrides to that for Al, Ni, Cu, Cr, Ru, Ta, Si or alloys composed mainly of these elements, is at least 20.

7. An etching solution for titanium-based metals,

tungsten-based metals, titanium/tungsten-based metals or
their nitrides, according to any one of claims 1 to 5,
wherein the ratio of the etching rate for titanium-based
metals or their nitrides to that for glass, silicon,
5 silicon oxide or silicon nitride, is at least 20.

8. A method for producing an electronic device,
which comprises a step of etching a titanium-based metal,
tungsten-based metal, titanium/tungsten-based metal or a
nitride thereof using an etching solution according to
10 any one of claims 1 to 7.