



**Halogenated polysilane and plasma-chemical process for
producing the same**

5 The present invention relates to a halogenated
polysilane as a pure compound or a mixture of compounds
each having at least one direct Si-Si bond, whose
substituents consist exclusively of halogen or of
halogen and hydrogen and in the composition of which
the atomic ratio of substituent to silicon is at least
10 1:1.

Chlorinated polysilanes of this kind are known in the
prior art [references: DE 10 2005 024 041 A1; DE 10
2006 034 061 A1; WO 2008/031427 A2; WO 81/03168; US
15 2005/0142046 A1; M. Schmeisser, P. Voss "Über das
Siliciumchlorid $[\text{SiCl}_2]_x$ ", Z. anorg. allg. Chem. (1964)
334, 50-56 (Schmeisser, 1964); US 2007/0078252 A1; DE
31 26 240 C2; UK 703,349]. On the one hand they can be
produced in a purely thermal reaction (Schmeisser,
20 1964) by heating chlorosilanes in vapor form with or
without a reducing agent at relatively high
temperatures (above 700°C). The chlorinated polysilanes
obtained have a faint coloration from dirty-yellow to
yellowish-light-brown (Schmeisser, 1964; "slightly
25 greenish-yellow, glass-like, high-polymer").
Spectroscopic investigations have shown that these
polysilanes produced purely thermally have a high
proportion of short-chain, branched and cyclic
molecules. Furthermore, the mixture obtained is heavily
30 contaminated with AlCl_3 owing to the production
conditions (very high temperatures).

GB 702,349 discloses that when silicon alloys are
reacted with chlorine gas at 190-250°C a mixture of
35 chlorinated polysilanes is condensed from the gas
stream. The average molecular weight of these mixtures
is relatively low, because on distillation only 2% of
the silanes have n greater than 6.



DE 31 26 240 C2 describes the wet-chemical production of chlorinated polysilanes from Si_2Cl_6 by reaction with a catalyst. The mixtures obtained still contain the catalyst and are therefore washed with organic solvents, so that traces of this solvent and of the catalyst remain. Moreover, PCS obtained in this way are strongly branched. Other wet-chemical methods are presented in US 2007/0078252 A1:

10

1. Reduction of halogenated aryloligosilanes with sodium followed by cleavage with HCl/AlCl_3 aromatics.

15

2. Transition-metal-catalyzed dehydrogenating polymerization of arylated H-silanes and subsequent dearylation with HCl/AlCl_3 .

20

3. Anionically catalyzed ring-opening polymerization (ROP) of $(\text{SiCl}_2)_5$ with TBAF (Bu_4NF).

4. ROP of $(\text{SiAr}_2)_5$ with TBAF or Ph_3SiK and subsequent dearylation with HCl/AlCl_3 .

25

With all these methods, once again PCS contaminated with solvent/catalyst are obtained.

30

In H. Stüger, P. Lassacher, E. Hengge, Zeitschrift für allgemeine und anorganische Chemie 621 (1995) 1517-1522, $\text{Si}_5\text{Cl}_9\text{H}$ is converted to the corresponding bis-cyclopentasilane $\text{Si}_{10}\text{Cl}_{18}$ by boiling with $\text{Hg}(\text{tBu}_2)$ in heptane. Alternatively, cyclization of $\text{Si}_5\text{Ph}_9\text{Br}$ with naphthyllithium or K and/or Na/K can be performed in various solvents with subsequent halogenation with HCl/AlCl_3 .

35

Production of halogenated polysilanes of this kind by a plasma-chemical process is also known. For example, DE 10 2005 024 041 A1 relates to a method of production of silicon from halosilanes, in which in a first step the
5 halosilane is converted to a halogenated polysilane with production of a plasma discharge, and this is then decomposed to silicon in a second step, with heating. In this known method, in connection with production of the plasma, high energy densities are used (above 10
10 Wcm^{-3}), and the end product is a not very compact, waxy-white to yellowish-brown or brown solid. Spectroscopic investigations showed that the end product obtained has a relatively high degree of crosslinking. The high energy densities used lead to products of high
15 molecular weights, resulting in insolubility and low fusibility.

Furthermore, WO 81/03168 describes a high-pressure plasma process for synthesis of HSiCl_3 , in which PCS are
20 formed as minor by-products. As these PCS are produced at extremely high gas temperatures, they are relatively short-chained and strongly branched. Moreover, this PCS has a high H content, owing to the hydrogenating conditions (HSiCl_3 synthesis!). US 2005/0142046 A1
25 describes PCS production by silent electric discharge in SiCl_4 at normal pressure. Only short-chain polysilanes are formed, as is demonstrated by the author with the selective reaction of SiH_4 to Si_2H_6 and Si_3H_8 by connecting several reactors in series. The
30 situation is similar according to DE 10 2006 034 061 A1, in which a similar reaction is described, in which gaseous and liquid PCS are obtained, with Si_2Cl_6 as the main constituent (p. 3, [00161]). Admittedly the authors describe how the molecular weights of the PCS
35 can be increased by using several reactors connected in series, but it is only possible to obtain material that can be converted undecomposed to the gas phase. This

situation is also expressed by the authors in the claims, in which they envisage distillations for all PCS mixtures obtained.

- 5 In addition to chlorinated polysilanes, other halogenated polysilanes Si_xX_y ($\text{X} = \text{F}, \text{Br}, \text{I}$) are also known in the prior art.

10 E. Hengge, G. Olbrich, Monatshefte für Chemie 101 (1970) 1068-1073 describes the production of a polymer with a sheet structure $(\text{SiF})_x$. The sheet-structure polymers $(\text{SiCl})_x$ or $(\text{SiBr})_x$ are obtained from CaSi_2 by reaction with ICl or IBr . A halogen exchange is then performed with SbF_3 . However, partial degradation of the
15 Si layer structure occurs. The resultant product contains the amount of CaCl_2 based on stoichiometry from CaSi_2 , and this cannot be washed out.

The production of polyfluorosilane $(\text{SiF}_2)_x$ is described
20 for example in M. Schmeisser, Angewandte Chemie 66 (1954) 713-714. SiBr_2F_2 reacts at room temperature in ether with magnesium to a yellow, high-polymer $(\text{SiF}_2)_x$. Compounds such as $\text{Si}_{10}\text{Cl}_{22}$, $(\text{SiBr})_x$ and $\text{Si}_{10}\text{Br}_{16}$ can be rehalogenated with ZnF_2 to the corresponding fluorides.
25 The standard method of production of $(\text{SiF}_2)_x$ is presented for example in P.L. Timms, R.A. Kent, T.C. Ehlert, J.L. Margrave, Journal of the American Chemical Society 87 (1965) 2824-2828. In this, $(\text{SiF}_2)_x$ is produced by leading SiF_4 over silicon at 1150°C and 0.1-
30 0.2 torr and freezing out the resultant SiF_2 at -196°C with polymerization during subsequent thawing. The colorless to pale yellow plastic polymer melts on heating to $200-350^\circ\text{C}$ in vacuum and releases perfluorinated silanes from SiF_4 to at least $\text{Si}_{14}\text{F}_{30}$. A
35 silicon-rich polymer $(\text{SiF})_x$ remains, which at $400 \pm 10^\circ\text{C}$ decomposes vigorously to SiF_4 and Si. The lower perfluoropolysilanes are colorless liquids or

crystalline solids, which can be isolated by fractional condensation in purities > 95%.

Traces of secondary or tertiary amines catalyze the
5 polymerization of perfluoro-oligosilanes.

FI 82232 B discloses a reaction at even higher temperature. SiF_4 reacts with Si in an Ar-plasma flame to SiF_2 (0.8 : 1 mol, 70% SiF_2 content).

10 Short-chain perbrominated polysilanes are formed, according to A. Besson, L. Fournier, Comptes rendus 151 (1911) 1055-1057. An electric discharge in gaseous HSiBr_3 produces SiBr_4 , Si_2Br_6 , Si_3Br_8 and $\text{Si}_4\text{Br}_{10}$.

15 K. Hassler, E. Hengge, D. Kovar, Journal of molecular structure 66 (1980) 25-30 prepare cyclo- Si_4Br_8 by reaction of $(\text{SiPh}_2)_4$ with HBr under AlBr_3 catalysis.

In H. Stüger, P. Lassacher, E. Hengge, Zeitschrift für allgemeine und anorganische Chemie 621 (1995) 1517-
20 1522, $\text{Si}_5\text{Br}_9\text{H}$ is converted to the corresponding bis-cyclopentasilane $\text{Si}_{10}\text{Br}_{18}$ by boiling with $\text{Hg}(\text{tBu}_2)$ in heptane. Alternatively, cyclization of $\text{Si}_5\text{Ph}_9\text{Br}$ with naphthyllithium or K or Na/K can be performed in various solvents with subsequent halogenation with
25 HBr/ AlBr_3 .

High-molecular silicon sub-bromides can be prepared, according to M. Schmeisser, Angewandte Chemie 66 (1954) 713-714, on the one hand by reaction of SiBr_4 with
30 magnesium in ether in the form of the yellow, solid $(\text{SiBr})_x$, and on the other hand by the action of SiBr_4 on elemental Si at 1150°C , which in addition to $(\text{SiBr})_x$ also produces Si_2Br_6 and other oligosilanes such as $\text{Si}_{10}\text{Br}_{16}$.

35

DE 955414 B also discloses a reaction at high temperature. If SiBr_4 or Br_2 in vapor form are led in

vacuum at 1000-1200°C through silicon grit, there is mainly formation of $(\text{SiBr}_2)_x$, along with a little Si_2Br_6 .

5 The ring-opening polymerization of cyclo- $\text{Si}_5\text{Br}_{10}$ and cyclo- Si_5I_{10} by the action of Bu_4NF in THF or DME is claimed in US 2007/0078252 A1.

For example E. Hengge, D. Kovar, Angewandte Chemie 93 (1981) 698-701 or K. Hassler, U. Katzenbeisser, Journal
10 of organometallic chemistry 480 (1994) 173-175 report on the production of short-chain periodated polysilanes. By reacting the phenylcyclosilanes $(\text{SiPh}_2)_n$ ($n = 4-6$) or Si_3Ph_8 with HI under AlI_3 catalysis, the periodated cyclosilanes $(\text{SiI}_2)_n$ ($n = 4-6$) or Si_3I_8 are
15 formed. M. Schmeisser, K. Friederich, Angewandte Chemie 76 (1964) 782 describe various routes for the production of periodated polysilanes. $(\text{SiI}_2)_x$ is produced at approx. 1% yield when SiI_4 vapor is led over elemental silicon at 800-900°C at high vacuum. The
20 pyrolysis of SiI_4 in the same conditions gives the same product, which is very sensitive to hydrolysis and is soluble in benzene. Under the action of a glow discharge on SiI_4 vapors at high vacuum, a solid, amorphous, reddish-yellow silicon sub-iodide of the
25 composition $(\text{SiI}_{2.2})_x$, insoluble in all the usual solvents, is obtained at a yield of 60 to 70% (relative to SiI_4). Pyrolysis of this substance at 220 to 230°C at high vacuum leads to a dark red $(\text{SiI}_2)_x$, with SiI_4 and Si_2I_6 being formed simultaneously. The chemical
30 properties of the resultant compounds $(\text{SiI}_2)_x$ coincide - except for solubility in benzene. Pyrolysis of $(\text{SiI}_2)_x$ at 350°C at high vacuum produces SiI_4 , Si_2I_6 and an orange-red, friable solid with the composition $(\text{SiI})_x$. $(\text{SiI}_2)_x$ reacts with chlorine or bromine between -30°C
35 and +25°C to benzene-soluble, mixed silicon subhalides such as $(\text{SiClI})_x$ and $(\text{SiBrI})_x$. At higher temperatures the Si-Si chains are cleaved by chlorine or bromine

with simultaneous total substitution of the iodine. Compounds of the type $\text{Si}_n\text{X}_{2n+2}$ ($n = 2-6$ for $\text{X} = \text{Cl}$, $n = 2-5$ for $\text{X} = \text{Br}$) are obtained. $(\text{SiI}_2)_x$ reacts with iodine at 90 to 120°C in a bomb tube completely to SiI_4 and
5 Si_2I_6 .

The present invention is based on the task of creating a halogenated polysilane of the stated type that is particularly soluble and fusible. Furthermore, a method
10 of production of said halogenated polysilane is to be provided.

According to a first embodiment, for a halogenated polysilane of the stated type, this task is solved in
15 that

- a) the halogen is chlorine,
- b) the hydrogen content of the polysilane is less
20 than 2 atom-%,
- c) the polysilane contains hardly any short-chain branched chains and rings, the content of branching points of the short-chain fraction
25 relative to the total product mixture being less than 1%,
- d) it has a Raman molecular vibrational spectrum of $I_{100}/I_{132} > 1$, where I_{100} denotes the Raman intensity
30 at 100 cm^{-1} and I_{132} denotes the Raman intensity at 132 cm^{-1} , and
- e) in ^{29}Si -NMR spectra its significant product signals are in the range of chemical shift from +15 ppm to
35 -7 ppm.

In a second embodiment of the invention, for a halogenated polysilane of the stated type, the stated task is solved in that

- 5 a) the halogen is bromine, and
- b) in ^{29}Si -NMR spectra its significant product signals are in the range of chemical shift from -10 ppm to -42 ppm, from -48 ppm to -52 ppm and/or from -65
10 ppm to -96 ppm.

The halogenated polysilane described above preferably has typical Raman intensities at 110 cm^{-1} to 130 cm^{-1} , at 170 cm^{-1} to 230 cm^{-1} , at 450 cm^{-1} to 550 cm^{-1} and at
15 940 cm^{-1} to 1000 cm^{-1} .

The hydrogen content of this polysilane is preferably less than 4 atom-%.

20 In a third embodiment of the invention, the aforementioned task is solved according to the invention in that

- a) the halogen is fluorine, and
- 25 b) in its ^{29}Si -NMR spectrum it has significant product signals in the range of chemical shift from 8 ppm to -30 ppm and/or from -45 ppm to -115 ppm.

30 This fluorinated polysilane preferably has typical Raman intensities at approx. 180 cm^{-1} to 225 cm^{-1} , at approx. 490 cm^{-1} to 550 cm^{-1} and at approx. 900 cm^{-1} to 980 cm^{-1} .

35 The hydrogen content of this polysilane is preferably less than 4 atom-%.

In a fourth embodiment of the invention the aforementioned task is solved according to the invention in that

- 5 a) the halogen is iodine, and
- b) in its ^{29}Si -NMR spectrum it has significant product signals in the range of chemical shift from -20 ppm to -55 ppm, from -65 ppm to -105 ppm and/or
- 10 from -135 ppm to -181 ppm.

This iodated polysilane preferably has typical Raman intensities at approx. 95 cm^{-1} to 120 cm^{-1} , at 130 cm^{-1} to 140 cm^{-1} , at 320 cm^{-1} to 390 cm^{-1} and at 480 cm^{-1} to

15 520 cm^{-1} .

The hydrogen content of this polysilane is preferably less than 4 atom-%.

- 20 The invention also relates to a halogenated polysilane, which contains halogen substituents of several different halogens.

The ^{29}Si -NMR spectra were recorded on a 250 MHz

25 instrument of the Bruker DPX 250 type with the pulse sequence zg30 and were referenced against tetramethylsilane (TMS) as external standard [$d(^{29}\text{Si})=0.0$]. The acquisition parameters are: TD=32k, AQ=1.652 s, D1=10 s, NS=2400, OlP=-40, SW=400.

30

The Raman molecular vibrational spectra were determined with an XY 800 spectrometer from the company Dilor with tunable laser excitation (T-sapphire laser, pumped by Ar-ion laser) and a confocal Raman and luminescence

35 microscope, with liquid-nitrogen-cooled CCD detector, measurement temperature equal to room temperature,

excitation wavelengths in the visible region of the spectrum, among others 514.53 nm and 750 nm.

5 The term short-chain used here relates to those compounds for which $n = 2-6$, where n is the number of Si atoms bound to each other directly. Therefore polymers for which n is greater than 6 are regarded as long-chain.

10 "Almost no" means that the mixture contains less than 2%. "Mainly" means that the content of the relevant constituent in the mixture is more than 50%.

15 "Backbone chain" comprises all silicon atoms of a compound that are joined together by Si-Si bonds.

The halogenated polysilane formed according to the invention is produced with considerably "milder" (energy density) plasma conditions. As a result, the
20 polysilane produced, with relatively high average chains lengths ($n = 9-25$), is readily soluble and readily fusible.

The degree of branching of the chlorinated polysilane
25 was determined by ^{29}Si -NMR spectroscopy. It was found that the chlorinated polysilanes produced using the process according to the invention have a low content of branched short-chain compounds, and their branching points represent a proportion of the total mixture of
30 less than 1%. The branchings appeared in the ^{29}Si -NMR spectrum in a region from $\delta = -20$ to -40 ppm and $\delta = -65$ to -90 ppm. In standard ^{29}Si -NMR spectra of the chlorinated polysilanes according to the invention, only very few or even no resonances appear in these
35 regions, which is a clear distinguishing feature compared with e.g. thermally produced chlorinated polysilanes, which have a high proportion of branching

points. This is connected with the fact that the latter chlorinated polysilanes are thermodynamically more favorable than chlorinated polysilanes with unbranched chains and are therefore formed preferentially in the thermal reaction, whereas in the plasma process, which takes place far away from thermodynamic equilibrium, the thermodynamically more favorable branchings are less preferred.

10 The content of cyclosilanes was also determined by ^{29}Si -NMR and Raman spectroscopy, and it was found that the content of small rings (Si_4 , Si_5 , Si_6) is very low.

15 Moreover, the chlorinated polysilanes formed according to the invention have a Raman molecular vibrational spectrum of $I_{100}/I_{132} > 1$. In particular, in the low-frequency region there are strong Raman signals in the range from $95\text{-}110\text{ cm}^{-1}$, whereas far weaker Raman intensities were measured in the range $120\text{-}135\text{ cm}^{-1}$.

20 Chlorinated polysilanes produced purely thermally have an I_{100}/I_{132} ratio of < 1 .

This may be explained as follows. For cyclic chlorinated polysilanes, theoretical, quantum-mechanical calculations show inter alia intensive characteristic modes between 120 cm^{-1} and 135 cm^{-1} . In contrast, such calculations for linear halogenated polysilanes do not show any pronounced modes in this region. In contrast, the lowest-frequency, intensive modes of the linear compounds are displaced with increasing chain length to smaller wavenumbers. In the mixture of halogenated polysilanes they appear as Raman bands between 95 and 110 cm^{-1} . To that extent, the I_{100}/I_{132} criterion provides information on the content of cyclic or linear molecules.

The halogenated polysilane produced according to the invention is further characterized in that it is soluble in many solvents, so that it can easily be removed from a reactor used for production. In particular the halogenated polysilane formed according to the invention has good solubility in inert solvents, such as SiCl_4 , benzene, toluene, paraffin etc., and both at room temperature and in cold and hot or boiling solvents. This contrasts with the halogenated polysilane produced according to the aforesaid publication DE 10 2005 024 041 A1, which is not soluble at all or only to a slight extent in such solvents.

The halogenated polysilane according to the invention is preferably characterized in that its substituents consist exclusively of halogen or of halogen and hydrogen.

The halogenated polysilane formed according to the invention preferably has mainly long chains (on average: $n=8$ to 20).

The halogenated polysilane formed according to the invention also differs from the plasma-chemically produced polysilane of the stated prior art in that the polysilane raw mixture produced has a smaller average chain length. Thus, the average chain length of the resultant raw mixture of halogenated polysilane (average size of the backbone chain) is preferably $n = 8-20$. After distilling-off the short-chain polysilanes n is preferably 15-25.

Another distinguishing criterion relative to the prior art is that the halogenated polysilane according to the invention has a low hydrogen content (less than 2 atom-% or less than 4 atom-%) and in particular contains less than 1 atom-% hydrogen.

Furthermore, the polysilane according to the invention, because it is produced in a plasma process, is of high purity with respect to contamination with doping
5 agents/metals and solvents, which is another distinguishing feature relative to the wet-chemical methods of production of polysilanes, because in the last-mentioned methods, traces of solvents and metal-salt-type reagents always remain in the product. In
10 particular, the high-purity polysilane obtained in a plasma process according to the invention meets the requirements for use in photovoltaics, i.e. it is of photovoltaic grade.

15 The halogenated polysilane is highly viscous to solid. As chlorinated polysilane it has a greenish-yellow to bright orange or reddish brown color and as brominated polysilane it is colorless to yellow.

20 The task stated above is further solved by a method of production of halogenated polysilane of the type described above by reacting halosilane with hydrogen with production of a plasma discharge, which is characterized in that it uses a mixture ratio of
25 halosilane to hydrogen of 1:0-1:2 and, with respect to plasma discharge, with an energy density of less than 10 Wcm^{-3} .

The method according to the invention is characterized
30 in that it employs "milder" plasma conditions than in the prior art, which with respect to the plasma discharge is reflected in an energy density of less than 10 Wcm^{-3} . Thus, the plasma-chemical process of the prior art employs energy densities of more than
35 10 Wcm^{-3} , whereas the process according to the invention preferably has energy densities of $0.2\text{-}2 \text{ Wcm}^{-3}$.

Energy density means the input of power at the moment of the gas discharge, divided by the excited gas volume.

5 Moreover, the process according to the invention is characterized, relative to the prior art, by a smaller proportion of hydrogen in the starting mixture. Thus, a mixture ratio of halosilane to hydrogen of 1:0-1:2 is employed according to the invention, so that there is a
10 further marked reduction in the energy input per equivalent of halosilane to be decomposed. This is preferably about 850-1530 kJ/mol halosilane.

The process according to the invention is preferably
15 carried out in a pressure range of 0.8-10 hPa. Generally this pressure range is higher than in the prior art for low-pressure gas discharges (e.g. DE 10 2005 024 041 A1), and it is decisive that in the process according to the invention the higher pressures
20 can be achieved without supporting measures for the plasma discharge (for example high-voltage discharge), whereas this is definitely necessary in the prior art (DE 10 2005 024 041 A1). Without the aforementioned support, in the prior art it was only possible to work
25 at pressures of less than 1 hPa.

The coupling-in of the desired lower powers is also achieved in the process according to the invention without supporting measures. Thus, in the process
30 according to the invention, ignition can take place without any problem at 100 W.

Whereas, as mentioned, a mixture ratio of halosilane to hydrogen of 1:0-1:2 is employed in the process
35 according to the invention, in the plasma-chemical process of the prior art this mixture ratio is 1:2-1:20 (DE 10 2005 024 041 A1; WO 81/03168).

Regarding the temperature of the reactor in which the process according to the invention is carried out, the reactor parts on which the halogenated polysilane is to be deposited are preferably maintained at a temperature from -70°C to 300°C, in particular -20°C to 280°C. Generally the temperature of the reactor is kept relatively low, to avoid formation of Si.

With the process according to the invention, product mixtures can preferably be produced whose molecules on average have 13-18 Si atoms.

For the process according to the invention, for example an electrical voltage or alternating electromagnetic fields can be used for producing the plasma discharge. High-frequency glow discharges at relatively low pressures (a few hPa) are preferred.

For the process according to the invention, a halosilane is used as the starting substance. Halosilane means, in the sense of the process according to the invention, compounds of the type H_nSiX_{4-n} ($X = F, Cl, Br, I; n = 0-3$) and mixtures thereof. However, halosilanes with mixed halogen substitution can also be used in the process according to the invention.

The gas mixture (halosilane and hydrogen) used in the process according to the invention can additionally be diluted with an inert gas and/or can contain admixtures, which promote plasma production. The admixture of inert gases is not, however, absolutely necessary in the process according to the invention.

In another embodiment of the process according to the invention, halosilane is added to the hydrogen stream, after the latter has passed through a plasma zone

(remote plasma). In this case both the hydrogen gas and the halosilane can be diluted with an inert gas and/or can contain admixtures that promote plasma production. The halosilane can also be used diluted with hydrogen.

5

In the process according to the invention, preferably fluorosilanes or chlorosilanes are used as halosilane. An especially preferred starting compound is SiCl_4 .

10 The halosilane : hydrogen volume ratio in the production of the halogenated polysilane is preferably 1:0 to 1:20, more preferably 1:0 to 1:2.

15 The invention is described below on the basis of examples.

Example 1

20 A mixture of 500 sccm H_2 and 500 sccm SiCl_4 (1:1) is fed into a reactor made of quartz glass, the process pressure being kept constant in the range 1.6-1.8 hPa. Transition of the gas mixture to the plasma state is then effected by a high-frequency discharge, and the chlorinated polysilane that forms is deposited on the
25 cooled (20°C) quartz glass walls of the reactor. The power input is 400 W. After 2 hours the yellow to orange-yellow product is removed from the reactor by dissolving in a little SiCl_4 . After removal of the SiCl_4 under vacuum, 91.1 g polysilane is left behind in the
30 form of an orange-yellow viscous mass.

The average molecular weight is determined by cryoscopy as approx. 1700 g/mol, which for the chlorinated polysilane $(\text{SiCl}_2)_n$ or $\text{Si}_n\text{Cl}_{2n+2}$ corresponds to an average
35 chain length of approx. $n=17$ for $(\text{SiCl}_2)_n$ or approx. $n=16$ for $\text{Si}_n\text{Cl}_{2n+2}$.

The ratio of Si to Cl in the product mixture is determined after decomposition by chloride titration according to Mohr as Si:Cl=1:2 (which corresponds to the empirical (analytical) formula SiCl_2).

5

The hydrogen content is 0.0005 mass-% and accordingly well below 1 mass-% (as well as below 1 atom-%), as can be seen from the following ^1H -NMR spectrum (Fig. 1). For this, the integrals of the solvent are compared at δ =
10 7.15 ppm and of the product at δ = 4.66 ppm. The content of the solvent C_6D_6 is approx. 25 mass-% and its degree of deuteration is 99%.

Typical ^{29}Si -NMR shifts at approx. 3.7 ppm, -0.4 ppm,
15 -4.1 ppm and -6.5 ppm can be seen from the following spectrum (Fig. 2). These signals are within the range of shifts for (1) and (2), which is typical of signals of SiCl_3 end groups (primary Si atoms), and (2), which is typical of signals of SiCl_2 groups (secondary Si
20 atoms), such as they are present for example as connecting links in the region of linear chains.

The low content of short-chain branched compounds, e.g. decachloroisotetrasilane (among others δ = -32 ppm),
25 dodecachloroneopentasilane (among others δ = -80 ppm) can also be seen from the next ^{29}Si -NMR spectrum (Fig. 2). By integration of the ^{29}Si -NMR spectra it can be seen that the content of silicon atoms, which form the branching points of the short-chain fraction, relative
30 to the total product mixture is 0.6 mass-% and so is less than 1 mass-%.

Low-molecular cyclosilanes cannot be detected in the mixtures. In the ^{29}Si -NMR spectra these would show sharp
35 signals at δ = 5.8 ppm (Si_4Cl_8), δ = -1.7 ppm ($\text{Si}_5\text{Cl}_{10}$), δ = -2.5 ppm ($\text{Si}_6\text{Cl}_{12}$), but these are not found.

A typical Raman molecular vibrational spectrum of the chlorinated polysilane is shown below (Fig. 3). The spectrum has an I_{100}/I_{132} ratio greater than 1, i.e. the Raman intensity at 100 cm^{-1} (I_{100}) is markedly higher than that at 132 cm^{-1} (I_{132}). The spectrum of a thermally produced perchloropolysilane mixture and the calculated spectrum of octachlorocyclotetrasilane (Si_4Cl_8) are given for comparison, and in each case the ratio reverses to I_{100}/I_{132} less than 1.

This diagram also shows, as an example, a section of a theoretical curve. For this, the quantum-chemically calculated modes [Hohenberg P, Kohn W. 1964. Phys. Rev. B 136:864-71; Kohn W, Sham LJ. 1965. Phys. Rev. A 140:1133-38, W. Koch and M.C. Holthausen, A Chemist's Guide to Density Functional Theory, Wiley, Weinheim, 2nd edn., 2000] are adjusted with a Multi-Lorentz peak function, which roughly simulates the experimental spectral resolution. With respect to the absolute intensity, the theoretical curve was normalized, so that it fits well in the diagram for viewing. The relative intensities of the peaks in the theory originate directly from the calculation from first principles calculation. This should show that certain intensities are typical of cyclic polysilanes. The data of the Raman spectrum point to a lower content of cyclic polysilanes in the plasma-chemically produced polysilane mixture, which is consistent with the NMR data (see above).

Example 2

A mixture of 300 sccm H_2 and 600 sccm SiCl_4 (1:2) is fed into a reactor made of quartz glass, the process pressure being kept constant in the range 1.5-1.6 hPa. Transition of the gas mixture to the plasma state is then effected by a high-frequency discharge, and the

chlorinated polysilane that forms is deposited on the cooled (20°C) quartz glass walls of the reactor. The power input is 400W. After 4 hours the orange-yellow product is removed from the reactor by dissolving in a little SiCl_4 . After removal of the SiCl_4 under vacuum, 187.7g of chlorinated polysilane is left behind in the form of an orange-yellow viscous mass.

The average molecular weight is determined by cryoscopy and is approx. 1400 g/mol, which for the chlorinated polysilane $(\text{SiCl}_2)_n$ or $\text{Si}_n\text{Cl}_{2n+2}$ corresponds to an average chain length of approx. $n=14$ for $(\text{SiCl}_2)_n$ or approx. $n=13$ for $\text{Si}_n\text{Cl}_{2n+2}$.

The ratio of Si to Cl in the product mixture is determined after decomposition by chloride titration according to Mohr as $\text{Si}:\text{Cl}=1:1.8$ (which corresponds to the empirical (analytical) formula $\text{SiCl}_{1.8}$).

The hydrogen content is well below 1 mass-% (0.0008%) (also below 1 atom-%), as can be seen from the following ^1H -NMR spectrum (Fig. 4). For this, the integrals of the solvent are compared at $\delta=7.15$ ppm and of the product at $\delta=3.75$ ppm.

The content of the solvent C_6D_6 is approx. 27 mass-% and its degree of deuteration is 99%.

Typical ^{29}Si -NMR shifts at approx. 10.9 ppm, 3.3 ppm, -1.3 ppm and -4.8 ppm can be seen from the following spectrum (Fig. 5). These signals are within the range of shifts at (1) and (2), which is typical of signals of SiCl_3 end groups (primary Si atoms), and (2), which is typical of signals of SiCl_2 groups (secondary Si atoms), such as they are present for example as connecting links in the region of linear chains.

The low content of short-chain branched compounds, e.g. decachloroisotetrasilane (among others $\delta = -32$ ppm), dodecachloroneopentasilane (among others $\delta = -80$ ppm) (these signals are within the range of shifts at (3), which is typical of signals of Si-Cl groups (tertiary Si atoms), and (4), which is typical of signals of Si groups with exclusively Si substituents (quaternary Si atoms)), can be seen from the following spectrum (Fig. 5). By integration of the ^{29}Si -NMR spectra it can be seen that the content of silicon atoms, which form said branching points (Si-Cl groups (tertiary Si atoms) and Si groups with exclusively Si substituents (quaternary Si atoms)) of the short-chain fraction, relative to the total product mixture is 0.3 mass-% and so is less than 1 mass-%.

Low-molecular cyclosilanes could not be detected in the mixtures. These ought to show sharp signals at $\delta = 5.8$ ppm (Si_4Cl_8), $\delta = -1.7$ ppm ($\text{Si}_5\text{Cl}_{10}$), $\delta = -2.5$ ppm ($\text{Si}_6\text{Cl}_{12}$) in the ^{29}Si -NMR spectra, but cannot be identified with certainty in the spectrum, as the spectrum has a large number of signals in this region.

The peak at approx. -20 ppm originates from the solvent SiCl_4 .

Example 3

A mixture of 200 sccm H_2 and 600 sccm SiCl_4 vapor (1:3) is fed into a reactor made of quartz glass, the process pressure being kept constant in the range 1.50-1.55 hPa. Transition of the gas mixture to the plasma state is then effected by a high-frequency discharge, and the chlorinated polysilane that forms is deposited on the cooled (20°C) quartz glass walls of the reactor. The power input is 400W. After 2h 9 min the orange-yellow product is removed from the reactor by dissolving in a

little SiCl_4 . After removal of the SiCl_4 under vacuum, 86.5 g of chlorinated polysilane is left behind in the form of an orange-yellow viscous mass.

- 5 The average molecular weight is determined by cryoscopy and is approx. 1300 g/mol, which for the chlorinated polysilane $(\text{SiCl}_2)_n$ or $\text{Si}_n\text{Cl}_{2n+2}$ corresponds to an average chain length of approx. $n=13$ for $(\text{SiCl}_2)_n$ or approx. $n=12$ for $\text{Si}_n\text{Cl}_{2n+2}$.

10

The ratio of Si to Cl in the product mixture is determined after decomposition by chloride titration according to Mohr as $\text{Si}:\text{Cl}=1:1.7$ (which corresponds to the empirical (analytical) formula $\text{SiCl}_{1.7}$).

15

The hydrogen content is well below 1 mass-% (0.0006%) (also below 1 atom-%), as can be seen from the following ^1H -NMR spectrum (Fig. 6). For this, the integrals of the solvent are compared at $\delta=7.15$ ppm and
20 of the product at $\delta=3.74$ ppm. The content of the solvent C_6D_6 is approx. 30 mass-% and its degree of deuteration is 99%.

The typical ^{29}Si -NMR shifts at approx. 10.3 ppm, 3.3
25 ppm, -1.3 ppm and -4.8 ppm and the low content of short-chain branched compounds, e.g. decachloroisotetrasilane (among others $\delta= -32$ ppm), dodecachloroneopentasilane (among others $\delta= -80$ ppm) (these signals are within the range of shifts at (3),
30 which is typical of signals of Si-Cl groups (tertiary Si atoms), and (4), which is typical of signals of Si groups with exclusively Si substituents (quaternary Si atoms)), can be seen from the following spectrum (Fig. 7).

35

The low content of short-chain branched compounds, e.g. decachloroisotetrasilane (among others $\delta= -32$ ppm),

dodecachloroneopentasilane (among others $\delta = -80$ ppm) (these signals are within the range of shifts at (3), which is typical of signals of Si-Cl groups (tertiary Si atoms), and (4), which is typical of signals of Si groups with exclusively Si substituents (quaternary Si atoms)), can be seen from the following spectrum (Fig. 7). By integration of the ^{29}Si -NMR spectra it can be seen that the content of silicon atoms, which form the stated branching points (Si-Cl groups (tertiary Si atoms) and Si groups with exclusively Si substituents (quaternary Si atoms)) of the short-chain fraction, relative to the total product mixture is 0.6 mass-% and so is less than 1 mass-%.

Low-molecular cyclosilanes cannot be detected in the mixtures. These ought to show sharp signals at $\delta = 5.8$ ppm (Si_4Cl_8), $\delta = -1.7$ ppm ($\text{Si}_5\text{Cl}_{10}$), $\delta = -2.5$ ppm ($\text{Si}_6\text{Cl}_{12}$) in the ^{29}Si -NMR spectra, but cannot be identified with certainty in the spectrum, as the spectrum has a large number of signals in this region.

The peak at approx. -20 ppm originates from the solvent SiCl_4 .

25 Example 4

A mixture of 300 sccm H_2 and 240 sccm SiBr_4 vapor is fed into a reactor made of quartz glass, the process pressure being kept constant in the region of 0.8 hPa. Transition of the gas mixture to the plasma state is then effected by a high-frequency discharge, and the brominated polysilane that forms is deposited on the cooled (20°C) quartz glass walls of the reactor. The power input is 140 W. After 2 hours the colorless product is removed from the reactor by dissolving in benzene. After removal of the benzene under vacuum,

55.2 g of brominated polysilane remains in the form of a white mush of crystals.

5 The average molecular weight is determined by cryoscopy and is approx. 1680 g/mol, which for the brominated polysilane $(\text{SiBr}_2)_n$ or $\text{Si}_n\text{Br}_{2n+2}$ corresponds to an average chain length of approx. $n=9$ for $(\text{SiBr}_2)_n$ or approx. $n=8$ for $\text{Si}_n\text{Br}_{2n+2}$.

10 The ratio of Si to Br in the product mixture is determined after decomposition by bromide titration according to Mohr as $\text{Si}:\text{Br}=1:2.3$ (which corresponds to the empirical (analytical) formula $\text{SiBr}_{2.3}$).

15 The hydrogen content is well below 1 mass-% (0.01%) (also below 1 atom-%), as can be seen from the following ^1H -NMR spectrum (Fig. 8). For this, the integrals of the solvent are compared at $\delta=7.15$ ppm and of the product at $\delta=3.9$ ppm. The content of the solvent C_6D_6 is approx. 30 mass-% and its degree of deuteration is 99%.

25 The typical ^{29}Si -NMR shifts (Fig. 9) appear in the range from -15 ppm to -40 ppm, from -49 ppm to -51 ppm and from -72 ppm to -91 ppm.

The peak at approx. -90 ppm originates from the educt SiBr_4 .

30 A typical Raman molecular vibrational spectrum of the brominated polysilane is shown below (Fig. 10). The spectrum has typical Raman intensities at approx. 110 cm^{-1} to 130 cm^{-1} , at 170 cm^{-1} to 230 cm^{-1} , at 450 cm^{-1} to 550 cm^{-1} and at 940 cm^{-1} to 1000 cm^{-1} .

35

Example 5

A mixture of 100 sccm H_2 and 50 sccm SiF_4 gas is fed into a plasma reactor, the process pressure being kept constant in the region of 1.2 hPa. Transition of the gas mixture to the plasma state is then effected by a high-frequency discharge, and the fluorinated polysilane that forms is deposited on the cooled ($20^\circ C$) walls of the reactor. The power input is 100 W. After 2 h the colorless to yellowish-beige-white product is removed from the reactor by dissolving in cyclohexane. After removal of the solvent under vacuum, 0.8 g of fluorinated polysilane remains in the form of a white to yellowish-beige solid.

The average molecular weight is determined by cryoscopy and is approx. 2500 g/mol, which for the fluorinated polysilane $(SiF_2)_n$ ($M=66.08$) or Si_nF_{2n+2} corresponds to an average chain length of approx. $n=38$ for $(SiF_2)_n$ or approx. $n=37$ for Si_nF_{2n+2} .

The hydrogen content is well below 1 mass-% (also under 1 atom-%), as can be seen from the following 1H -NMR spectrum (Fig. 11).

The typical ^{29}Si -NMR shifts of the fluorinated polysilane appear in the range from -4 ppm to -25 ppm and/or from -50 ppm to -80 ppm.

A Raman molecular vibrational spectrum of the fluorinated polysilane has typical Raman intensities at approx. 183 cm^{-1} to 221 cm^{-1} , at approx. 497 cm^{-1} to 542 cm^{-1} and at approx. 900 cm^{-1} to 920 cm^{-1} .

Example 6

A mixture of 60 sccm H_2 and 60 sccm SiI_4 vapor is fed into a reactor made of quartz glass, the process
5 pressure being kept constant in the region of 0.6 hPa. Transition of the gas mixture to the plasma state is then effected by a high-frequency discharge, and the iodated polysilane that forms is deposited on the cooled ($20^\circ C$) quartz glass walls of the reactor. The
10 power input is 100 W. After 2 h the reddish-yellow product is removed from the reactor by dissolving in cyclohexane. After removal of the cyclohexane under vacuum, 8 g of iodated polysilane remains in the form of a reddish-yellow to brownish solid.

15 The average molecular weight is determined by cryoscopy and is approx. 2450 g/mol, which for the iodated polysilane $(SiI_2)_n$ or Si_nI_{2n+2} corresponds to an average chain length of approx. $n=9$ for $(SiI_2)_n$ or approx. $n=8$
20 for Si_nI_{2n+2} .

The ratio of Si to I in the product mixture is determined as Si:I=1:2.3 (which corresponds to the empirical (analytical) formula $SiI_{2.3}$).

25 The hydrogen content is well below 1 mass-% (also under < 1 atom-%).

The typical ^{29}Si -NMR shifts of the iodated polysilane
30 appear in the range from -28 ppm to -52 ppm, from -70 ppm to -95 ppm and/or from -138 ppm to -170 ppm.

A typical Raman molecular vibrational spectrum of the iodated polysilane has typical Raman intensities at
35 approx. 98 cm^{-1} to 116 cm^{-1} , at 132 cm^{-1} to 138 cm^{-1} , at 325 cm^{-1} to 350 cm^{-1} and at 490 cm^{-1} to 510 cm^{-1} .

Patent claims

1. A halogenated polysilane as pure compound or mixture of compounds each having at least one direct Si-Si bond, whose substituents consist of halogen or of halogen and hydrogen and in the composition of which the atomic ratio of substituent to silicon is at least 1:1, characterized in that
- a) the halogen is chlorine,
 - b) the hydrogen content of the polysilane is less than 2 atom-%,
 - c) the polysilane contains hardly any short-chain branched chains and rings, and the content of branching points of the short-chain fraction relative to the total product mixture is less than 1%,
 - d) it has a Raman molecular vibrational spectrum of $I_{100}/I_{132} > 1$, where I_{100} denotes the Raman intensity at 100 cm^{-1} and I_{132} denotes the Raman intensity at 132 cm^{-1} ,
 - e) in ^{29}Si -NMR spectra it has its significant product signals in the range of chemical shift from +15 ppm to -7 ppm.
2. A halogenated polysilane as pure compound or mixture of compounds each having at least one direct Si-Si bond, whose substituents consist of halogen or of halogen and hydrogen and in the composition of which the atomic ratio of

substituent to silicon is at least 1:1,
characterized in that

a) the halogen is bromine, and

b) in ^{29}Si -NMR spectra it has its significant
product signals in the range of chemical shift
from -10 ppm to -42 ppm, from -48 ppm to -52
ppm and/or -65 ppm to -96 ppm.

3. The halogenated polysilane according to claim 2,
characterized in that it has typical Raman
intensities at 110 cm^{-1} to 130 cm^{-1} , 170 cm^{-1} to
 230 cm^{-1} , at 450 cm^{-1} to 550 cm^{-1} and at 940 cm^{-1} to
 1000 cm^{-1} .

4. The halogenated polysilane according to claim 2 or
3, characterized in that the hydrogen content of
the polysilane is less than 4 atom-%.

5. A halogenated polysilane as pure compound or
mixture of compounds each having at least one
direct Si-Si bond, whose substituents consist of
halogen or of halogen and hydrogen and in the
composition of which the atomic ratio of
substituent to silicon is at least 1:1,
characterized in that

a) the halogen is fluorine, and

b) in ^{29}Si -NMR spectra it has its significant
product signals in the range of chemical shift
from 8 ppm to -30 ppm and/or from -45 ppm to
-115 ppm.

6. The halogenated polysilane according to claim 5, characterized in that it has typical Raman intensities at approx. 180 cm^{-1} to 225 cm^{-1} , at approx. 490 cm^{-1} to 550 cm^{-1} and at approx. 900 cm^{-1} to 980 cm^{-1} .
7. The halogenated polysilane according to claim 5 or 6, characterized in that the hydrogen content of the polysilane is less than 4 atom-%.
8. A halogenated polysilane as pure compound or mixture of compounds each having at least one direct Si-Si bond, whose substituents consist of halogen or of halogen and hydrogen and in the composition of which the atomic ratio of substituent to silicon is at least 1:1, characterized in that
- a) the halogen is iodine, and
 - b) in ^{29}Si -NMR spectra it has its significant product signals in the range of chemical shift from -20 ppm to -55 ppm , from -65 ppm to -105 ppm and/or from -135 ppm to -181 ppm .
9. The halogenated polysilane according to claim 8, characterized in that it has typical Raman intensities at approx. 95 cm^{-1} to 120 cm^{-1} , at 130 cm^{-1} to 140 cm^{-1} , at 320 cm^{-1} to 390 cm^{-1} and at 480 cm^{-1} to 520 cm^{-1} .
10. The halogenated polysilane according to claim 8 or 9, characterized in that the hydrogen content of the polysilane is less than 4 atom-%.

11. The halogenated polysilane according to one of the preceding claims, characterized in that it contains halogen substituents of several different halogens.
- 5
12. The halogenated polysilane according to one of the preceding claims, characterized in that its substituents consist exclusively of halogen or of halogen and hydrogen.
- 10
13. The halogenated polysilane according to one of the preceding claims, characterized in that it mainly contains long linear chains.
- 15
14. The halogenated polysilane according to one of the preceding claims, characterized in that the average size of the backbone chain of the raw mixture of the halogenated polysilane is $n = 8-20$.
- 20
15. The halogenated polysilane according to one of the preceding claims, characterized in that the average size of the backbone chain of the raw mixture of the halogenated polysilane after distilling-off the short-chain polysilanes is $n =$
- 25
- 15-25.
16. The halogenated polysilane according to one of the preceding claims, characterized in that it is highly viscous to solid.
- 30
17. The halogenated polysilane according to one of the preceding claims, characterized in that as chlorinated polysilane it has a greenish-yellow to bright orange or reddish brown color and as brominated polysilane it is colorless to yellow.
- 35

18. The halogenated polysilane according to one of the preceding claims, characterized in that it is readily soluble in inert solvents.
- 5 19. The halogenated polysilane according to one of the preceding claims, characterized in that it contains less than 1 atom-% hydrogen.
- 10 20. A process for production of halogenated polysilane according to one of the preceding claims by reacting halosilane with hydrogen with production of a plasma discharge, characterized in that it is carried out with a mixture ratio of halosilane to hydrogen of 1:0-1:2 and, with respect to the plasma discharge, with an energy density of less than 10 Wcm^{-3} .
- 15 21. The process according to claim 20, characterized in that, with respect to the plasma discharge, it employs an energy density of $0.2-2 \text{ Wcm}^{-3}$.
- 20 22. The process according to claim 20 or 21, characterized in that the energy input per halosilane equivalent used is 850-1530 kJ/mol halosilane.
- 25 23. The process according to one of claims 20 to 22, characterized in that it employs a pressure range from 0.8-10 hPa.
- 30 24. The process according to one of claims 20 to 23, characterized in that the reactor parts on which the halogenated polysilane is deposited are maintained at a temperature from -70°C to 300°C , in particular -20°C to 280°C .
- 35