

DESCRIPTION

TITLE: METHOD OF FABRICATING A DEVICE COMPRISING A MEMBRANE
OVERHANGING A CAVITY

FIELD OF THE INVENTION

The present invention relates to the field of microelectronics and microsystems. In particular, it relates to a process of fabricating a device comprising a membrane overhanging a useful cavity.

TECHNOLOGICAL BACKGROUND OF THE INVENTION

MEMS devices (MEMS being the acronym of microelectromechanical systems) are widely used to fabricate various sensors, for a multitude of applications: mention may for example be made of pressure sensors, microphones, radio-frequency switches, electro-acoustic and ultrasonic transducers (piezoelectric micromachined ultrasonic transducers (pMUT) for example), etc.

Many of these MEMS devices are based on a flexible membrane overhanging a useful cavity. In operation, the bowing of the membrane, which is related to a physical parameter (for example the propagation of an acoustic wave for a pMUT), is converted into an electrical signal (or vice versa, depending on whether the device is in receiver or emitter mode).

Depending on the type of device implemented, the geometry of each useful cavity (shape, lateral dimensions, depth), of the membrane (thickness) and their planar distribution (inter-cavity distance) will be different.

The publication by Lu Yipeng and David A. Horsley, "Modeling, fabrication, and characterization of piezoelectric

micromachined ultrasonic transducer arrays based on cavity SOI wafers." (*Journal of Microelectromechanical Systems* 24.4 (2015) 1142-1149) presents an example of fabrication of a pMUT device from an SOI (silicon on insulator) substrate having buried useful cavities. This process takes advantage of useful cavities formed beforehand in a substrate to limit the number of levels of photolithographic masks needing to be employed.

This approach is attractive, but it means that some of the effort made designing the acoustic device must be borne by the manufacturer of the substrate. Specifically, the manufacturer of the substrate must be able to design and fabricate a substrate including useful cavities conforming precisely to the topology (geometry of the cavities, inter-cavity spacing) required for the device. However, device topology is often a piece of valuable and sensitive information that the device manufacturer generally does not want to divulge.

In addition, the substrate manufacturer must develop substrate-fabricating processes specific to each topology. The effort required to do this makes rapid and economical development of the device more difficult.

It would therefore be desirable to be able to provide a substrate that can be used to fabricate a wide range of devices based on a membrane overhanging a useful cavity, and which would therefore not require the ad hoc development, for each device, of a substrate-specific fabricating process.

OBJECTIVE OF THE INVENTION

The purpose of the present invention is to achieve the aforementioned aim. It relates to a process of fabricating a device comprising a membrane overhanging a useful cavity, which is simplified due to the use of a generic substrate.

BRIEF DESCRIPTION OF THE INVENTION

The invention relates to a process of fabricating a device including a membrane overhanging a useful cavity, the process comprising:

- providing a generic structure including a superficial layer extending in a main plane and arranged on a first side of a carrier substrate, said carrier substrate including elementary cavities opening under the superficial layer and partitions delimiting each elementary cavity, upper surfaces of said partitions forming all or some of the first side of the carrier substrate;
- defining a group of adjacent elementary cavities, such that a contour of said group of elementary cavities corresponds, in the main plane, to a contour of the useful cavity;
- removing the partitions located inside the contour of the group of elementary cavities, in order to form the useful cavity, and in order to free up the superficial layer arranged above said useful cavity and making up the membrane.

According to other advantageous and non-limiting features of the invention, taken alone or in any technically feasible combinations:

- the partitions separate the elementary cavities from one another;
- the partitions are distributed in the main plane according to a network of partitions allowing communication between the elementary cavities, each elementary cavity being delimited by an elementary pattern of the network of partitions;
- providing the generic structure comprises:
 - providing a donor substrate,
 - providing the carrier substrate including the opening elementary cavities and the partitions delimiting each elementary cavity and the upper surfaces of which form all or some of the first side of the carrier substrate,
 - joining the donor substrate and the carrier substrate at the first side of the carrier substrate,
 - thinning the donor substrate so as to form the superficial layer;
- providing the donor substrate comprises implanting light species in said donor substrate, so as to form a buried fragile region that lies between a first portion of the donor substrate, which portion is intended to form the superficial layer, and a second portion of the donor substrate, which portion is intended to form the rest of the donor substrate;
- thinning the donor substrate comprises separating, via the buried fragile region, the superficial layer from the rest of the donor substrate;
- the first portion of the donor substrate has a thickness comprised between 0.2 micron and 2 micron;

- the joining comprises bonding via molecular adhesion, on the one hand, the donor substrate, and, on the other hand, the first side of the carrier substrate;
- removing the partitions located inside the contour of the group of elementary cavities comprises the local etching of the superficial layer in order to form at least one aperture passing through said superficial layer, and the chemical etching of said partitions via said aperture;
- the at least one aperture is made plumb with the partitions;
- an aperture is made plumb with each elementary cavity of the group of elementary cavities;
- removing the partitions located inside the contour of the group of elementary cavities comprises the local etching of a second side of the carrier substrate in order to form at least one aperture opening into one of the cavities of the group of elementary cavities, and the chemical etching of said partitions via said aperture;
- the partitions comprise at least one material chosen from silicon oxide, silicon nitride, single-crystal silicon, polycrystalline silicon, amorphous silicon or porous silicon;
- the donor substrate comprises at least one semiconductor or piezoelectric material.

BRIEF DESCRIPTION OF THE FIGURES

Other features and advantages of the invention will become apparent from the following detailed description of the

invention, which description is given with reference to the appended figures, in which:

[Fig. 1a]

[Fig. 1b]

[Fig. 1c]

[Fig. 1d]

[Fig. 1e]

[Fig. 1f] Figures 1a to 1f show a process of fabricating a device comprising a membrane arranged on a useful cavity, in accordance with the invention;

[Fig. 2a]

[Fig. 2b] Figures 2a to 2b show steps of a fabricating process according to the invention;

[Fig. 3a]

[Fig. 3b]

[Fig. 3c] Figures 3a to 3c show other steps of a fabricating process according to the invention;

[Fig. 4a]

[Fig. 4b]

[Fig. 4c]

[Fig. 4d]

[Fig. 4e]

[Fig. 4f]

[Fig. 4g]

[Fig. 4h]

[Fig. 4i]

[Fig. 4j] Figures 4a to 4j show an example of an embodiment of the fabricating process according to the invention;

[Fig. 5a]

[Fig. 5b]

[Fig. 5c]

[Fig. 5d]

[Fig. 5e] Figures 5a to 5e show steps of a fabricating process according to the invention.

DETAILED DESCRIPTION OF THE INVENTION

In the description, the same references in the figures might be used for elements of the same type. The figures are schematic representations which, for the sake of legibility, are not to scale. In particular, the thicknesses of the layers along the z-axis are not to scale with respect to the lateral dimensions along the x- and y-axes; and the relative thicknesses of the layers with respect to one another are not necessarily respected in the figures.

The invention relates to a process of fabricating a device 200 including a membrane 210 overhanging a useful cavity 230 (figures 1e and 1f). For example, said device 200 can consist of an ultrasonic or acoustic transducer.

The fabricating process according to the invention firstly comprises a step of providing a generic structure 100 including a superficial layer 10 extending in a main plane (x,y) and arranged on a first side 21 of a carrier substrate 20. The carrier substrate 20 includes elementary cavities 23 opening under the the superficial layer 10 and partitions 24 normal to the main plane (x,y), delimiting each elementary cavity 23 (figures 1a, 5a). The upper surfaces of the partitions 24 at least partly form the first side 21 of the carrier substrate 20.

By way of example, and in a non-limiting manner, the partitions 24 comprise at least one material from silicon oxide,

silicon nitride, single-crystal silicon, polycrystalline silicon, amorphous silicon or porous silicon.

According to a first advantageous embodiment, the partitions 24 completely separate the elementary cavities 23 from one another. As illustrated in plan view in Figure 1b, the partitions 24 advantageously form partitions organized in a grid in the main plane (x,y) making it possible to separate each elementary cavity 23 from the neighbouring cavities thereof and therefore delimit each elementary cavity 23.

The elementary cavities 23 are, in this case, represented as being square-shaped, but alternatively they could have a rectangular, circular or any other geometric shape.

According to a second embodiment of the invention, the elementary cavities 23 are not separated from one another. The partitions 24 are distributed, preferentially in a uniform manner, in the main plane (x,y), according to a network of partitions 24, like the example illustrated in figure 5b. None of the partitions 24 mutually meet and they form local partitions and/or pillars. In this embodiment, an elementary cavity 23 refers to the cavity inside an elementary pattern 23e of the network of partitions 24. In the example of figure 5b, the elementary pattern 23e corresponds to a square pattern fictitiously defined by four adjacent partitions 24; the elementary cavity 23 is delimited by the four adjacent partitions 24 and corresponds to the interior region of this elementary pattern 23e.

The upper surface (in the main plane (x,Y)) of a partition 24 is represented in this case as being square-shaped, but it could have a rectangular, circular or any other geometric shape. The partitions 24 could also be distributed according to a grid network or another uniform distribution. By way of example, and in a non-limiting manner, the dimensions of a

partition 24 in the main plane (x,y) can be approximately 5 micron, 7 micron, 10 micron or 15 micron.

The manufacturing process then comprises a step for defining a group 23g of adjacent elementary cavities 23, the outer contour of which, in the main plane (x,y), corresponds to a contour of the useful cavity 230 (figures 1c, 5c). Of course, reference is made in this case to the definition of at least one group 23g of elementary cavities: indeed, in the case of a generic structure 100 formed from a carrier substrate 20 with a diameter of between 100 mm and 300 mm, a plurality of groups 23g will be defined, according to a determined distribution, in the main plane (x,y).

This defining step depends on the type of intended device 200, and, in particular, it depends on the required lateral dimensions of the useful cavity (cavities) 230 in the main plane (x,y); these lateral dimensions can vary from a few tens of microns to a few hundred microns, or a few millimetres. The defining step also depends on the spacing between useful cavities that is required for said device 200: this spacing can for example vary from a few tens of microns to a few hundred microns, or a few millimetres.

It will be noted that this defining step and the subsequent steps can be preferentially performed by the device manufacturer, the substrate manufacturer being only responsible for providing the generic structure 100. Alternatively, the substrate manufacturer can implement the defining step at the request of the client and according to specifications set by the latter.

The fabricating process according to the invention then comprises a step of removing partitions 24 located inside the

contour of the group 23g of elementary cavities 23; said partitions will be called temporary partitions 24g hereafter.

The removal of the temporary partitions 24g advantageously comprises the local etching of the superficial layer 10 in order to form at least one aperture 13 passing through said superficial layer 10, in the defined region of the group 23g of elementary cavities (figures 2a and 2b).

Such local etching may be carried out by photolithography and dry or wet chemical etching. In particular, a mask (not represented) deposited on the free side 12' of the superficial layer 10 makes it possible to delimit the regions to be etched in order to form the apertures 13, and to protect the rest of the free surface 12'. It will be noted that alignment marks, defined on the periphery of the carrier substrate 20 and/or in regions provided for cutting lanes on the first side 21 thereof and/or at the second side 22 thereof, during the formation of the elementary cavities 23 and of the partitions 24 on the carrier substrate 20, allow a precise positioning to be achieved with respect to said partitions 24 and buried cavities 23 during this removing step. These marks can also be used for subsequent steps requiring an alignment with respect to the useful cavity (cavities) 230 of the device 200.

According to a first variant, illustrated in figure 2b, the (at least one) aperture 13 is made plumb with the temporary partitions 24g.

According to a second variant, which can be used in particular for the first embodiment of the invention, the aperture 13 is formed plumb with at least one of the elementary cavities 23 of the group 23g of elementary cavities (which is not represented).

For the aforementioned variants, it is possible to re-plug the (at least one) aperture 13, for example by depositing

polycrystalline silicon, under vacuum or in a controlled atmosphere.

According to a third variant (not represented), removing the temporary partitions 24g may comprise forming at least one aperture 13 by local etching the second side 22 of the carrier substrate 20, up to the cavities of the group 23g of elementary cavities 23. Advantageously, such etching at the second side 22 is carried out at the end of the fabrication of the MEMS device 200, in particular when the carrier substrate 20 is thinned for example to 400, 200, 100, 50 micron or less. This allows an aperture 13 of small size to be produced while remaining within ratios of etched thickness/dimensions of the aperture that are accessible using known chemical etching techniques. It will be noted that this variant allows the membrane (portion of the superficial layer 10 located plumb with the group 23g of elementary cavities 23) to be left intact by avoiding passage of the aperture 13 therethrough.

In either of the stated variants, a dry or wet chemical etching suitable for attacking the material of the partitions 24 is then performed, via the aperture 13, in order to eliminate the temporary partitions 24g (figures 1d, 5d) and free up the superficial layer 10 (forming the membrane 210) across the entire useful cavity 230.

At the end of the step for removing the temporary partitions 24g, a device 200 including a membrane 210 overhanging a useful cavity 230 (figure 1e) is obtained.

The fabricating process according to the invention for this device 200 is simplified by the use of a so-called generic structure 100, which does not require, during the development thereof, knowledge of the geometry and of the distribution of

the useful cavities 230. The generic structure 100 includes a plurality of elementary cavities 23 and a plurality of partitions 24, some of which 24g are temporary since they are intended to be eliminated, in order to form one (or more) useful cavity (cavities) 230 defined from one (or more) group (groups) 23g of elementary cavities.

In the first embodiment of the invention, in which the generic structure 100 comprises elementary cavities 23 separated from one another by the partitions 24, the membrane 210 located above the useful cavity 230 following the removal of the temporary partitions 24g is held over the entire perimeter thereof by partitions 24 (figures 1d and 1e). In the second embodiment of the invention, in which the partitions 24 of the generic structure 100 do not mutually separate the elementary cavities 23, the membrane 210 located above the useful cavity 230 following the removal of the temporary partitions 24g is held locally over the perimeter thereof by partitions 24 (figures 5d and 5e). Either of the embodiments can be envisaged depending on the type of intended device 200.

The generic structure 100 therefore has the advantage of being able to be used to fabricate a multitude of devices 200 based on varied topologies of useful cavities 230, which can be formed from a group 23g of elementary cavities 23.

Moreover, the development of the useful cavity 230 by removing the temporary partitions 24g is advantageous in that it only requires a small elimination of material, the partitions having a reduced width, and this limits the etching time and makes it possible to achieve precise dimensions for the useful cavity 230.

The fabricating process (irrespective of the embodiment) can also comprise additional steps for fabricating the device

200 on the superficial layer 10 and in particular on the membrane 210 and at the periphery thereof. These additional steps can notably comprise steps of photolithography, etching and depositing insulating and/or electrically conductive layers in order to define and form, for example, electrodes 220, above each membrane 210 (Figure 1f).

It will be noted that these additional steps can alternatively be performed before the step for removing the temporary partitions 24g, in order to utilize the mechanical strength of the superficial layer 10 as a result of said underlying temporary partitions 24g, across (in the main plane (x,y)) the entire structure 100.

According to an advantageous mode of implementing the invention, the step for providing the generic structure 100 firstly comprises providing a donor substrate 1. The donor substrate 1 has a front side 11, intended to be joined to the carrier substrate 20 and a back side 12. By way of example, and in a nonlimiting manner, the donor substrate 1 will possibly comprise at least one semiconductor, for example silicon, silicon carbide, etc., or a piezoelectric material, for example lithium tantalate, lithium niobate, aluminium nitride, zinc oxide, PZT, etc.

Secondly, the step for providing the generic structure 100 comprises providing the carrier substrate 20 including a first side 21, intended to be joined to the donor substrate 1, and a second side 22. The carrier substrate further includes the elementary cavities 23 opening at the first side 21 and partitions 24, the upper surface of which forms all or part of the first side 21.

By way of nonlimiting example, the carrier substrate 20 can comprise silicon, glass, sapphire, etc.

The shape of the elementary cavities 23 in the main plane (x,y) can be circular, square, rectangular or polygonal. The lateral dimensions of the elementary cavities 23 in the main plane (x,y) are advantageously less than 50 micron, or less than 25 micron, or less than 10 micron. The spacing between elementary cavities 23, corresponding to the width of the partitions 24, can vary from one micron to a few tens of microns. By way of example and in a nonlimiting manner, the width of the partitions 24 can be approximately 5 micron, 7 micron, 10 micron or 15 micron. The upper surface of the partitions 24 can have a circular, square, rectangular or polygonal shape.

The depth of the elementary cavities 23, along the z-axis normal to the main plane (x,y) (also corresponding to the height of the partitions 24) can vary from a few tens of nanometres to a few tens of microns, or a few hundred microns, depending on the intended device 200.

Thirdly, the step for providing the generic structure 100 comprises joining the front side 11 of the donor substrate 1 and the first side 21 of the carrier substrate 20. The joining operation preferentially comprises direct bonding by molecular adhesion. The principle of molecular adhesion, which is well known in the prior art, will not be described in further detail here. It will be noted that the substrates to be joined must have a very good surface finish (cleanness, low roughness, etc.) for a joint of good quality to be obtained.

Advantageously, in order to guarantee a joint of good quality, the joining step comprises cleaning the to-be-joined surfaces of the donor substrate 1 and of the carrier substrate 20, before said surfaces are brought into contact. By way of example, a conventional sequence used in microelectronics, especially for silicon-based substrates, comprises an ozone clean, an SC1 clean (SC1 being the acronym of Standard Clean 1) and an SC2 clean (SC2 being the acronym of Standard Clean 2)

with intermediate rinses. The surfaces to be joined will also possibly be activated, for example using a plasma, before being brought into contact, in order to promote a high bonding energy between said surfaces.

Optionally, the donor substrate 1 and/or the carrier substrate 20 will possibly comprise a bonding layer, on the front side 11 and/or on the first side 21, respectively, in order to promote bond quality and the bonding energy of their interface.

Fourthly, the step for providing the generic structure 100 comprises the thinning of the donor substrate 1 so as to form the superficial layer 10.

According to a first variant of this advantageous mode of implementation, the thinning of the donor substrate 1 is carried out by mechanical grinding, by chemical-mechanical polishing and/or by chemical etching at the back side 12 thereof. At the end of the thinning step, the superficial layer 10 arranged on the carrier substrate 20 and having a thinned free side 12' is obtained (Figure 1a).

According to this variant, the thickness of the superficial layer 10 can be between a few microns and several tens, or hundreds of microns.

According to a second variant of this advantageous mode of implementation, the thinning is carried out using the Smart Cut™ process, which is based on an implantation of light ions and a detachment at the implanted region.

Thus, according to this second variant, the aforementioned step of providing the donor substrate 1 comprises implanting light species in said donor substrate 1, so as to form a buried fragile region 2 that lies between a first portion 3 of the donor substrate, which portion is intended to form the superficial layer 10, and a second portion 4 of the donor

substrate 1, which portion is intended to form the rest of the donor substrate (Figure 3a). Preferentially, an intermediate layer 5 is arranged on the front side 11 of the donor substrate 1, before the implantation. This intermediate layer 5 can be retained, removed and/or replaced by a bonding layer prior to the joining step.

The thickness of the first portion 3, and therefore of the future superficial layer 10, is dependent on the implantation energy of the light species (hydrogen or helium for example). Advantageously, the implantation energy is chosen so that the first portion 3 of the donor substrate 1 has a thickness of about 0.2 micron - 2 micron.

The donor substrate 1 is then joined to the carrier substrate 20 in accordance with the joining step of the process (Figure 3b).

Still according to this second variant, the step of thinning the donor substrate 1 comprises separating, at the buried fragile region 2, the superficial layer 10 (formed by the detached first portion 3) and the rest 4 of the donor substrate 1 (Figure 3c). This separation preferably occurs during a heat treatment at a temperature comprised between a few hundred degrees and 700°C. It may alternatively be mechanically assisted or achieved after the heat treatment, by means of a mechanical stress.

At the end of the thinning step, the superficial layer 10 transferred to the carrier substrate 20 is obtained (Figure 3c). It will be recalled that the Smart Cut™ process allows thin layers having an excellent thickness uniformity to be obtained.

In certain cases where the thickness of the superficial layer 10 transferred using the Smart Cut™ process is insufficient, it is possible to again increase this thickness by depositing an additional layer on the free surface 12' of the superficial layer 10, for example by epitaxial growth or other

known deposition processes, during a finishing processing that is mentioned below.

In both the thinning variants stated above, when the superficial layer 10 is arranged on the carrier substrate 20, the thinning step may comprise finishing processing aiming to improve the crystal quality (removal of defects from the layer), the surface quality (removal of residual roughness from the free surface 12') and/or to modify the thickness of the superficial layer 10. This finishing processing will possibly include one or more heat treatments, chemical-mechanical polishes, chemical etches, epitaxial growth, and/or deposition of additional layers.

Example of implementation

In the present example, the intended device 200 requires a silicon membrane 210 having a thickness of 1.5 micron overhanging a useful cavity 230 with a square shape of approximately 104 micron per side and one micron in depth.

The fabricating process according to the invention firstly proposes the provision of a generic structure 100 including a silicon superficial layer of 1.5 micron and elementary cavities 23 with a square shape of 20 micron per side, one micron in depth and spaced apart by 8 micron.

The donor substrate 1 is a substrate made of silicon (Figure 4a). A silicon oxide layer 5, for example of about 100 nm, is formed (for example by thermal oxidation) on the front side 11 prior to the implantation of the light species. The implantation energy is set to 210 keV, with hydrogen species at a dose of $7 \times 10^{16}/\text{cm}^2$. Thus, a buried fragile region 2 is formed, which lies in the main plane (x,y) between a first part 3 and a

second part 4 of the substrate 1 and located at a depth of approximately 1.9 micron.

The oxide layer 5 will possibly be preserved or removed prior to the step of joining to the carrier substrate 20.

The carrier substrate 20 is a substrate made of silicon. A thermal-oxide layer 24a having a thickness of 2 micron is formed on said substrate 20. This thermal-oxide layer 24a is formed on the first side 21 and the second side 22 of the substrate 20. The thermal-oxide layer present on the second side 22 will possibly be entirely or partially preserved or removed depending on the circumstances. Alternatively, an oxide layer will possibly be deposited (using a known deposition technique) solely on the first side 21 of the carrier substrate 20.

By photolithography, a mask 25 is then defined on the first side 21 of the carrier substrate 20, including unmasked regions at which the thermal-oxide layer 24a will be able to be etched and masked regions at which said layer 24a will be protected (Figure 4b). It will be noted that alignment marks are also defined on the periphery of the carrier substrate 20 and/or in regions of the cutting lanes, for the subsequent photolithography steps that will be aimed at re-determining the coordinates of the elementary cavities 23, when they are buried under the superficial layer 10.

The unmasked regions are defined according to the size and the target planar distribution of the elementary cavities 23 of the generic structure 100. At these unmasked regions, dry or wet chemical etching of the thermal-oxide layer 24a is carried out right through the thickness thereof, i.e. 2 micron (Figure 4c). The mask 25 is then removed (figure 4d).

Typically, in this example, each elementary cavity 23 measures 20 microns per side, and partitions 24 distributed in

a grid, of 8 micron in width, separate the elementary cavities 23 from one another (figure 4e).

After a cleaning and activating sequence, the front side 11 of the donor substrate 1 and the first side 21 of the carrier substrate 20 are brought into contact and bonded by molecular adhesion (Figure 4f). It will be noted that the direct bonding will possibly be carried out under ambient atmosphere or under a controlled atmosphere (pressure and nature of the gas). An anneal for consolidating the bonding interface may be applied to the bonded structure at a temperature of about 350°C.

The separation via the buried fragile zone 2 is carried out during a detaching heat treatment, at a temperature of about 500°C.

This then results in the generic structure 100, comprising the superficial layer 10 arranged on the plurality of elementary cavities 23 of the carrier substrate 20 (figure 4g).

Finishing processing operations, such as a thermal oxidizing process and a chemical-mechanical polish are preferably carried out in order to guarantee that the transferred superficial layer 10 has a good surface and structural quality and to obtain a thickness of 1.5 micron.

The step for defining at least one group 23g of adjacent elementary cavities 23, the outer contour of which, in the main plane, corresponds to a contour of the useful cavity 230, is then carried out. As illustrated in figure 4h, a group 23g of sixteen elementary cavities 23 is defined in order to form a useful cavity 230 of approximately 104 micron per side. The partitions separating these sixteen elementary cavities 23 are the temporary cavities 24g intended to be eliminated during the next step of the fabricating process.

For the step of removing the temporary partitions 24, a mask 14, for example made of silicon nitride, is defined by photolithography, using the alignment marks provided on the carrier substrate 20, in order to delimit unmasked regions at which the apertures 13 passing through the superficial layer 10 will be formed, the rest of the free side 12 of the superficial layer 10 being masked and therefore protected. Dry or wet local etching of the superficial layer 10 made of silicon is carried out in order to form the apertures 13, the cross-sectional area of each aperture 13 here being chosen to be smaller than the upper surface of the partitions 24g (figure 4i) and being positioned at intersections of the grid forming the temporary partitions 24g.

In the presence of the apertures 13, a chemical etch, for example a dry chemical etch, based on hydrofluoric acid (HF) vapours, is carried out to remove the thermal oxide from which the temporary partitions 24g are made, and thus free up the superficial layer 10 across the entire useful cavity 230 in order to form the membrane 210.

The mask 14 may be removed, before the chemical etching of the temporary partitions 24g or at the end of the step of removing the partitions 24g.

It will be noted that, depending on the process chosen for the step of removing the temporary partitions 24g, over-etching can be carried out at the partitions 24 defining the useful cavity 230, and therefore substantially modify the dimensions of said useful cavity 230 and of the associated membrane 210. It will therefore be necessary to take into account these potential effects of over-etching and/or adapt the process chosen for the step of removing the temporary partitions 24g, to obtain a useful cavity 230 with the right dimensions.

The apertures 13 may then be re-plugged if necessary.

This results in the intended device 200, including a membrane 210 overhanging a useful cavity 230, and the thickness of the superficial layer 10 (membrane 210) and the geometry of the useful cavity 230 are compliant with the specifications set out above.

Of course, the invention is not limited to the described modes of implementation and examples, and variant embodiments may be introduced therein without departing from the scope of the invention as defined by the claims.

CLAIMS

1. Process of fabricating a device (200) including a membrane (210) overhanging a useful cavity (230), the process comprising:
 - providing a generic structure (100) including a superficial layer (10) extending in a main plane (x,y) and arranged on a first side (21) of a carrier substrate (20), said carrier substrate (20) including elementary cavities (23) opening under the superficial layer (10) and partitions (24) delimiting each elementary cavity (23), said partitions (24) having upper surfaces which form all or some of the first side (21) of the carrier substrate (20);
 - defining a group (23g) of adjacent elementary cavities (23), such that a contour of said group (23g) of elementary cavities (23) corresponds, in the main plane (x,y), to a contour of the useful cavity (230);
 - removing the partitions (24g) located inside the contour of the group (23g) of elementary cavities (23), in order to form the useful cavity (230), and in order to free up the superficial layer (10) arranged above said useful cavity (230) and making up the membrane (210).
2. Fabricating process according to the preceding claim, wherein the partitions (24) separate the elementary cavities (23) from one another.
3. Fabricating process according to Claim 1, wherein the partitions (24) are distributed in the main plane (x,y) according to a network of partitions allowing communication between the elementary cavities (23), each elementary cavity (23) being delimited by an elementary pattern (23e) of the network of partitions.

4. Fabricating process according to one of the preceding claims, wherein providing the generic structure (100) comprises:
 - providing a donor substrate (1),
 - providing the carrier substrate (20) including the opening elementary cavities (23), and the partitions (24) delimiting each elementary cavity (23) and the upper surfaces of which form all or some of the first side (21) of the carrier substrate (20),
 - joining the donor substrate (1) and the carrier substrate (20) at the first side (21) of the carrier substrate (20),
 - thinning the donor substrate (1) so as to form the superficial layer (10).
5. Fabricating process according to the preceding claim, wherein:
 - providing the donor substrate (1) comprises implanting light species in said donor substrate (1), so as to form a buried fragile region (2) that lies between a first portion (3) of the donor substrate (1), which portion is intended to form the superficial layer (10), and a second portion (4) of the donor substrate (1), which portion is intended to form the rest of the donor substrate (1),
 - thinning the donor substrate (1) comprises separating, via the buried fragile region (2), the superficial layer (10) from the rest (4) of the donor substrate (1).
6. Fabricating process according to the preceding claim, wherein the first portion (3) of the donor substrate (1) has a thickness comprised between 0.2 micron and 2 micron.
7. Fabricating process according to one of the three preceding claims, wherein the joining comprises bonding by molecular adhesion, on the one hand, the donor substrate (1), and, on

the other hand, the first side (21) of the carrier substrate (20).

8. Fabricating process according to one of the preceding claims, wherein removing the partitions (24g) located inside the contour of the group (23g) of elementary cavities (23) comprises the local etching of the superficial layer (10) in order to form at least one aperture (13) passing through said superficial layer (10), and the chemical etching of said partitions (24g) via said aperture (13).
9. Fabricating process according to the preceding claim, wherein the at least one aperture (13) is made plumb with the partitions (24g).
10. Fabricating process according to Claim 8, wherein an aperture (13) is made plumb with each elementary cavity (23) of the group (23g) of elementary cavities.
11. Fabricating process according to one of Claims 1 to 7, wherein removing the partitions (24g) located inside the contour of the group (23g) of elementary cavities (23) comprises the local etching of a second side (22) of the carrier substrate (20) in order to form at least one aperture (13) opening into one of the cavities (23) of the group (23g) of elementary cavities (23), and the chemical etching of said partitions (24g) via said aperture (13).
12. Fabricating process according to one of the preceding claims, wherein the partitions (24) comprise at least one material chosen from silicon oxide, silicon nitride, single-crystal silicon, polycrystalline silicon, amorphous silicon or porous silicon.

13. Fabricating process according to one of Claims 4 to 12, wherein the donor substrate (1) comprises at least one semiconductor or piezoelectric material.