

**Closure element for a vacuum valve
with pressed-off, vulcanized-on seal**

The invention relates to a closure element for a vacuum valve for the gastight closing of a flow path, according to
5 the preamble of claim 1, a corresponding vacuum valve, according to the preamble of claim 11, and a tool and a method for manufacturing such a closure element, according to claim 12 and 14 respectively.

Vacuum valves for the substantially gastight closing of a
10 flow path which leads through an opening shaped in a valve housing are commonly known in different embodiments from the prior art. Vacuum gate valves are used, in particular, in the field of IC and semiconductor production, which must take place in a protected atmosphere, as far as possible
15 without the presence of contaminating particles. For instance, in a production plant for semiconductor wafers or liquid crystal substrates, the highly sensitive semiconductor or liquid crystal elements pass sequentially through a plurality of process chambers, in which the
20 semiconductor elements located within the process chamber are machined by means of, in each case, a machining device. Both during the machining process within the process chamber and during the transport from process chamber to process chamber, the highly sensitive semiconductor
25 elements must be constantly in a protected atmosphere - in particular in a vacuum. The process chambers are connected to each other, for instance, via connecting passages, wherein the process chambers can be opened by means of vacuum gate valves for transfer of the parts from one to
30 the next process chamber and, subsequent to implementation of the respective production step, closed in a gastight manner. Due to the described field of application, valves

of this type are also referred to as vacuum transfer valves and, due to their rectangular opening cross section, also as rectangular gate valves.

Since transfer valves are used, inter alia, in the
5 manufacture of highly sensitive semiconductor elements, the particle generation caused, in particular, by the actuation of the valve, and the number of free particles in the valve chamber, must be kept as low as possible. The particle generation is primarily a consequence of friction, for
10 instance by metal-metal contact and by abrasion.

The sealing can be effected, for example, either via a seal disposed on the closure side of the closure plate, which seal is pressed onto the valve seat surrounding the opening, or via a sealing ring on the valve seat, against
15 which the closure side of the closure plate is pressed. Different sealing devices are known from the prior art, for instance from US 6,629,682 B2 (Duelli). A suitable material for sealing rings is, for instance, the elastic sealing material known under the trade name Viton®.

20 The requirements which are placed on the seals used in vacuum valves are very high. On the one hand, in the closed state of the valve, the leak-tightness of the valve must be ensured. This is a big challenge, above all due to the, in the vacuum sector, high differential pressures, and the
25 thus generated large forces acting on the valve shutter. Since, in the case of excessively high compressions, the seals used are subjected to above-average, high wear or are destroyed, the structure of the valve must be such that the differential pressure forces cannot, or can only to a
30 limited degree, act on the seals. The compression of the seal should be effected as evenly as possible along its course, which calls for a uniform pressing force of the

valve disk upon the valve seat throughout the contact zone. Above all, transverse loads and longitudinal loads upon the seal should be kept as low as possible. In the case of transverse loads transversely to the longitudinal direction
5 of the seal, in O-ring seals there is the danger that they will be torn out of their mounting, in particular the groove, in which they are fixed. Vulcanized-on seals, too, may only be exposed to very limited transverse forces. Both in the open and in the closed state of the valve, the seals
10 are in part exposed to aggressive mediums and must therefore either be of such a nature that they can withstand the influences, and/or are moved out of the flow path of the medium, also in order to avoid abrasion. Excessively high wear upon the seal represents an
15 uncertainty factor for process reliability and calls for a regular exchange of the seal, which in turn leads to increased downtimes within the process.

Different embodiments of vacuum valves, in particular their sealing and drive technologies, are known from the prior
20 art, which embodiments have, inter alia, the aim of increasing the service life of the seals used and also have improved process reliability.

Depending on the respective drive technologies, a distinction is drawn, in particular, between gate valves, also termed spool valves or rectangular gate valves, and
25 shuttle valves, wherein in the prior art the closing and opening is generally effected in two steps. In a first step, a valve shutter member, in particular a closure plate or a closure element, in the case of a gate valve, as is
30 known, for instance, from US 6,416,037 (Geiser) or US 6,056,266 (Blecha), in particular an L-type gate valve, is linearly displaced over an opening in a motion substantially parallel to the valve seat, or in the case of

a shuttle valve, as is known, for instance, from US 6,089,537 (Olmsted), is pivoted over the opening about a pivot axis, without contact being made between the closure plate and the valve seat of the valve housing. In a second
5 step, the closure plate is pressed with its closure side onto the valve seat of the valve housing, so that the opening is closed in a gastight manner. The sealing can be realized, for example, either via a seal disposed on the closure side of the closure plate, which seal is pressed
10 onto the valve seat surrounding the opening, or via a sealing ring on the valve seat, against which the closure side of the closure plate is pressed. The seal, in particular the sealing ring, can be held in a groove and/or vulcanized on.

15 The described two-stage motion, in which the closure member is firstly slid transversely over the opening without the seal making contact with the valve seat, and the closure member is subsequently pressed substantially perpendicularly onto the valve seat, has, besides the
20 possibility of precise regulation of the flow, above all the advantage that the seal is compressed almost exclusively perpendicularly, without this resulting in a transverse or longitudinal load on the seal. The drive has a relatively complex structure, which in particular is
25 formed either by a single drive, which enables an L-shaped motion of the closure member, or by a plurality of drives, for instance two linear drives or one linear drive and a spreading drive. Spreading drives, which are generally disposed directly behind the closure plate and displace
30 this, relative to the shank on which they are found, in the perpendicular direction onto the valve seat, have inside the valve a multiplicity of mechanical parts which perform relative motions with respect to one another.

Wedge valves, which are adjusted only linearly, enable a significantly higher adjustment speed, yet, due to the transverse loading of the seal, are in part barely suitable for the vacuum sector, and if at all, then only for a small number of adjustment cycles.

This problem is solved by means of gate valves in which, even though the closing and sealing operation is effected via a single linear motion, the sealing geometry is such that a transverse loading of the seal is wholly avoided. Such a valve is, for instance, the transfer valve known under product designation "MONOVAT Series 02 and 03", and configured as a rectangular insert valve, of the company VAT Vakuumventile AG in Haag, Switzerland. The structure and working method of such a valve are described, for instance, in US 4,809,950 (Geiser) and US 4,881,717 (Geiser).

The valve which is described there possesses in its housing a sealing surface, which, viewed in the direction of the axis of the valve passage opening, possesses portions situated one behind the other, which, via smooth curves, pass into laterally outward running, flat sealing surface portions, wherein the imaginary generatrices of this sealing surface, which is in one piece yet has a plurality of portions, lie parallel to the axis of the valve passage opening. The sealing surface is machine-worked. The closure member possesses a thereto corresponding bearing surface for the peripherally closed seal. Described in greater detail, the so-called valve slide possesses a valve housing and a valve passage opening, which can be closed with a closure member which is displaceable in its plane. In the region of the valve passage opening is provided a sealing surface, against which, in the closing position of the closure member, bears a peripherally closed seal disposed

on said closure member, wherein the imaginary, straight
generatrices of the sealing surface lie parallel to the
axis of the valve passage opening. The peripherally closed,
one-piece seal has portions of different lengths and/or
5 shapes, which lie in different planes, wherein two main
portions of the peripherally closed seal lie in planes
which stand at right angles to the axis of the valve
passage opening and are spaced apart. The two main portions
of the seal are connected by side portions. The closure
10 member possesses, in relative to the course of the sealing
surface of the housing, a correspondingly running face
supporting the peripherally closed seal. The side portions
of the peripherally closed seal extend in a U-shape.
Respectively the branches of these side portions extending
15 in a U-shape lie in one plane. Those portions of the
sealing surface which, viewed in the axial direction of the
valve passage opening, lie one behind the other, for the
contact of the main portions of the seal in that region in
which they possess a common, straight, axis-parallel
20 generatrix, pass into laterally outward running flat
sealing surface portions. These flat sealing surface
portions lie in planes lying parallel to one another and to
the axis of the valve passage opening.

A suitable drive for such a transfer valve which can be
25 closed by means of a linear motion is represented in JP
6241344 (Buriida Fuuberuto). The drive which is described
there possesses eccentrically mounted levers for the linear
displacement of the push rods on which the closure member
is mounted.

30 Substantially independent of the above-stated drive
technologies for valve shutters are the designs for seals
provided or applied on the closure element. As mentioned
above, such a seal is typically realized as an O-ring in a

groove or - for improved durability - is vulcanized onto the closure element by means of a special tool.

For the vulcanization of the seal, overflow gaps are provided in order that an excess of sealing material, for example elastomer, can be led off and the seal 100 can be created in accordance with the shape predefined by the tool (cf. fig. 1a). However, the material 101,101' discharged through the overflow gaps remains on the plate blank 110, which is produced, for instance, from aluminum or special steel and has to be mechanically removed subsequent to the vulcanization. This removal is currently generally effected by means of trimming in the region of the metal/sealing material transition zone and results in a removal of both sealing material and metal, as shown in the regions 101 and 101' of fig. 1b.

However, a major drawback with this process is the formation of particles and the formation of burrs in the removal of material by the trimming. Since precisely this particle formation and the lingering of such particles on the valve shutter element is extremely critical for the machining processes to be carried out in the vacuum sector, every effort has to be made to reduce or, ideally, totally avoid such particles.

It is therefore an object of the invention to provide a closure plate or closure element for a vacuum valve, in particular a vacuum transfer valve, having a vulcanized-on seal, wherein improved process reliability is obtained.

In particular, it is an object to provide an appropriate closure element, wherein a production-related burr formation or the formation of residual particles at least in the part facing toward the process volume to be shut off is minimized or wholly avoided.

These objects are achieved by the realization of the characterizing features of the independent claims. Features which refine the invention in an alternative or advantageous manner can be derived from the dependent
5 patent claims.

In accordance with an aspect of the invention, closure element, in particular a valve disk, for a vacuum valve and configured for the gastight close-off of a process volume by means of cooperation with a vacuum valve opening,
10 provided for the process volume, of the vacuum valve is disclosed. The closure element includes a first sealing surface, corresponding, in particular in terms of shape and size, to a second sealing surface of the vacuum valve opening wherein the second sealing surface surrounds the
15 vacuum valve opening, and a sealing material vulcanized onto the first sealing surface and in accordance with the course thereof and having a defined height in the direction of the surface normal of the first sealing surface, wherein the sealing material has a defined shape with respect to a
20 sealing material cross section. The sealing material includes a first seal portion, provided, in particular, on the process volume side, and a second seal portion, provided, in particular, facing away from the process volume. The closure element has a compression adjoining the
25 first seal portion and having a pressing edge, and the pressing edge is shaped, and is configured with respect to the first seal portion, such that the surface course of the sealing material, which surface course is given by the shape of the first seal portion and tapers into the
30 pressing edge, is continued substantially homogeneously, in particular linearly.

The invention relates to a closure element for vacuum valves, wherein the seal is applied to the closure element such that a following material-removing machining of the closure element, at least in those regions which during use
5 are facing toward the process volume to be shut off, in particular are in direct contact with this volume, can be dispensed with. Thus no machine-cutting reworking of the closure element in these regions, for example trimming, is any longer necessary, whereby, broadly speaking, there is
10 no formation of microparticles or burrs.

The closure element is generally the shutter (also referred to as the valve disk, closure plate or closure member) by means of which the opening in the vacuum valve can be closed in a gastight manner. In an arrangement in a vacuum
15 valve of the generic type, the closure element, which can be configured, for instance, as a valve disk, is typically displaceable at least linearly along a geometric adjustment axis, running transversely to the opening axis, in a closure element plane between an open position and a closed
20 position. Preferably, the adjustment axis runs perpendicular to the opening axis and lies on a plane which is breached perpendicularly by the opening axis. Alternatively, the adjustment axis runs obliquely and non-parallel to the opening axis, wherein the angle of
25 intersection is in particular between 90 degrees and 45 degrees.

In particular, the closure element is movable, moreover, in the direction of the opening axis, so that a closure of the valve opening by a substantially perpendicular pressing of the closure element onto the valve seat can be effected in
5 a second stage of the motional sequence (L-type). As a result, a transverse loading of the vulcanized-on seal can be kept as small as possible, whereby the formation of abrasion particles is correspondingly reduced.

In concrete terms, the invention relates to a closure
10 element, in particular a valve disk, for a vacuum valve, wherein the closure element is configured for the gastight close-off of a vacuum process volume by means of cooperation with a vacuum valve opening, provided for the process volume, of the vacuum valve.

15 The closure element is thus configured for the gastight closing of a valve opening for a flow path under vacuum conditions. By the flow path should be understood, in general terms, an opening path, which is to be closed, between two regions - in particular between two coating
20 plants of any type, for instance for solar or other applications, or between a process chamber for semiconductor production and either a further process chamber or the outside world. The flow path is, for instance, a connecting passage between two interconnected
25 process chambers, wherein the process chambers can be opened by means of the vacuum valve for transfer of the semiconductor parts from one to the next process chamber and, subsequent to implementation of the respective production step, can be closed in a gastight manner. Due to
30 the described field of application, valves of this type are also referred to as vacuum transfer valves and, due to their often rectangular opening cross section, also as rectangular gate valves. Naturally, any other chosen

application of the vacuum valve according to the invention for the substantially gastight closure of a chosen flow path is also possible, however.

The closure element has a first sealing surface
5 corresponding, in particular in terms of shape and size, to a second sealing surface of the vacuum valve opening, wherein the second sealing surface surrounds the vacuum valve opening. The first sealing surface of the closure
10 element thus corresponds, in particular in terms of shape and size, to the sealing surface surrounding the valve opening (in particular to the shape of the valve seat).

Moreover, the closure element has a sealing material which is vulcanized onto the first sealing surface and, in accordance with the course thereof, has a defined height in
15 the direction of the surface normal of the first sealing surface, wherein the sealing material has a defined shape with respect to a sealing material cross section (cross section through the sealing material perpendicular to its direction of extent), comprising a first seal portion
20 provided, in particular, on the process volume side (i.e. a portion which, given an arrangement in a vacuum valve and in the closed state, faces toward the process volume to be shut off or is in contact with this same), and a second seal portion, provided facing away from the process volume.
25 Typically, closure elements of this type - thus also the closure element according to the invention - are configured such that, already on the basis of the design of the closure element, it is defined which part of the closure element and also of the sealing material, during use, comes
30 into or is in contact with the process volume to be separated off (vacuum sector) and which second part remains outside this volume, i.e. in the closed state is not (directly) exposed to this process volume.

In terms of product quality, in particular with respect to purity, i.e. the presence of any particles or burrs, the first seal portion (i.e. that which in the closed valve state is facing toward the process volume) is the process-
5 critical portion. In particular, this portion must not, as far as possible, have any impurities or material residues.

The closure element therefore has a compression adjoining the first seal portion and having a pressing edge. Moreover, the pressing edge is shaped and is configured
10 with respect to the first seal portion such that the surface course of the sealing material, which surface course is given by the shape of the first seal portion and tapers into the pressing edge, (with respect to the cross section through the sealing material), is continued
15 substantially homogeneously, in particular linearly, by the pressing edge (i.e. by virtue of the position and direction of the pressing edge relative to the tapering sealing material). This also comprises a slightly angled continuation of the surface course by means of the pressing
20 edge.

The compression in the closure element is formed in the application and vulcanization of the sealing material. As a result, a material overflow in at least that direction which corresponds to the later (i.e. where the closure
25 element is used in a vacuum valve) process side is prevented and, at the same time, the sealing material is formed on such that a homogeneous material transition is formed. A reworking of this (sealant/metal) transit region is thus no longer necessary, whereby a burr formation and a
30 thereby induced particle formation can be largely prevented.

According to one specific embodiment of the invention, the closure element has a further compression having a further pressing edge, which adjoins the second seal portion. This second compression or pressing edge and the second seal
5 portion are positioned relative to each other and respectively shaped such that the surface line, according to the principle of the first seal portion, is guided, on this side too, substantially homogeneously throughout.

With respect to the shaping of the first seal portion,
10 according to one embodiment of the invention this is shaped, in a region adjoining the compression, such that in this region the surface course of the sealing material (in the cross sectional direction) is homogeneous and has a homogeneous curvature which produces an edgeless change of
15 direction of the surface course, in particular between 75° and 105° , in particular 90° . As a result, a continuous transition of the surface line of the sealing material into the carrier material of the closure element is enabled, so that a flush-molded, neat seal can be created.

20 According to one particular embodiment of the invention, the curvature (in the region adjoining the compression) is free from turning points. In particular, the curvature has a constant direction of curvature. As a result of such a design of the first seal portion, a homogeneous course of
25 the seal surface (in accordance with the seal cross section) and a corresponding transition to the carrier material is given.

In addition, according to one specific embodiment of the invention, the change of direction of the surface course in
30 the region adjoining the compression amounts substantially to 90° .

With the creation of the compression in the closure element, in the course of the vulcanization of the sealing material an appropriate close-off of the vulcanization chamber can be procured. In order that this close-off is
5 formed flush with and tight with the surface of the closure element, a pressing into the carrier material (= material of the closure element), in particular with a particular depth, is necessary. At the same time, moreover, the structure and stability of the closure element should
10 remain unaffected. When the excess sealing material is removed according to the prior art, a material removal (for example by trimming) of the carrier material of the closure element (metal or alloy) in the region of 0.2 mm is created.

15 A further embodiment of the invention thus relates to the compression of the closure element, wherein the compression has a depth in the direction of the surface normal of the first sealing surface and with respect to the surface of this sealing surface within the range from 0.15 to 0.25 mm.

20 In particular, the pressing edge which is created by the compression has a length between 0.15 and 0.25 mm.

With respect to the shape of the compression, one embodiment of the invention has in particular the pressing edge such that this runs substantially parallel to the
25 surface normal of the first sealing surface (viewed in cross section).

In terms of the surface properties created by the vulcanization process, it is advantageous that the surface, without a necessary reworking of the material, has a
30 significantly lower surface roughness - compared with a vulcanization and a partial removal of the sealing material, wherein, following the machining, surface

roughnesses of around $R_a = 0.8 \mu\text{m}$ or $R_z = 7.0 \mu\text{m}$ obtain. A lower surface roughness at the same time implies a diminution of the working surface in terms of, for example, a possible particle release.

- 5 According to the invention, the first seal portion has in particular, at least in the region adjoining the compression, a mean surface roughness R_s between $0.02 \mu\text{m}$ and $0.15 \mu\text{m}$, in particular between $0.05 \mu\text{m}$ and $0.1 \mu\text{m}$.

- Alternatively or additionally, the first seal portion has
10 in particular, at least in the region adjoining the compression, an average surface roughness depth R_z between $0.2 \mu\text{m}$ and $1.5 \mu\text{m}$, in particular between $0.5 \mu\text{m}$ and $1 \mu\text{m}$.

- A surface state of this type is here achieved by an appropriately smooth tool surface, in particular of the
15 recess in the tool, which recess is provided for the vulcanization.

- According to one specific embodiment of the closure element, the sealing material consists at least partially, yet preferably mainly, of an elastomer. For instance, the
20 sealing material has a fluoroelastomer, which is marketed, for example, under the designation Viton®-fluoroelastomer, for example Viton® A or Viton® B, or as Dai-el®-fluoroelastomer, for example Dai-el® G 902 etc., as Tecnoflon™ or Tecnoflon™-fluoroelastomer. The sealing
25 material can also be based on a peroxide-curable fluorinated rubber compound, as is described, for instance, in DE 10 2007 048 252 A1 of the Applicant. Materials of this type offer, in particular, high resistance also to aggressive chemical mediums, such as, for example, a
30 process gas present in the process volume.

According to a further embodiment according to the invention, the closure element has a coupling for connecting to a drive unit of a vacuum valve in order to provide a controlled motion of the closure element in the vacuum valve, in particular a receptacle for a push rod of the drive unit. In particular, the receptacle is shaped in the side of the closure element (with respect to a closure side of the closure element), for the removable mounting of the closure element on the push rod by engagement of a connecting portion of the push rod in the receptacle. Moreover, the push rod is supported and adjustable by means of the drive unit in particular such that the valve opening is closable by displacement of the closure element substantially along the push rod axis over a valve opening and pressing of the closure element with its sealing material onto a valve seat surrounding the valve opening.

By virtue of this coupling, the closure element is thus specifically configured for use in a vacuum valve, in particular of the L-type, and can thereby be connected to the drive unit and moved in the valve according to a defined pattern.

According to a further embodiment of the invention, the closure element has at least one grip recess, which is shaped in a side lying opposite the closure side with the vulcanized-on sealing material (of the closure element), for the manual application of force to the closure plate substantially along the push rod axis, in particular for the removal or mounting of the closure plate from or on the push rod.

For improved handling of the closure element during disassembly, for example, two grip recesses, for instance, are shaped in the side opposite the closure side in order

to be able to manually apply a force to the closure element in a substantially upward direction for removal of the closure plate from the push rod and/or for better handling of the closure plate following disassembly. The grip
5 recesses can be provided on the inside with a non-slip coating for improved grip.

The invention further relates to a vacuum valve for the gastight close-off of a process volume, comprising a valve housing, which has a vacuum valve opening and a valve seat
10 surrounding the vacuum valve opening and having a second sealing surface. In addition, the vacuum valve has a closure element for the substantially gastight closure of the vacuum valve opening, having a first sealing surface corresponding to the second sealing surface, wherein the
15 first sealing surface has a vulcanized-on sealing material having a defined height in the direction of the surface normal of the first sealing surface, and the sealing material has a defined shape with respect to a sealing material cross section, having a first seal portion,
20 provided, in particular, on the process volume side, and a second seal portion, provided, in particular, facing away from the process volume.

The vacuum valve additionally has a drive unit coupled with the closure element, which drive unit is configured such
25 that the closure element is adjustable at least substantially along a geometric longitudinal axis in a longitudinal closing direction from an open position, in which the closure element frees the vacuum valve opening, into a closing position, in which the first sealing surface
30 of the closure element is pressed onto the second sealing surface and closes the vacuum valve opening in a substantially gastight manner, and back.

According to the invention, the closure element has a compression adjoining the first seal portion and having a pressing edge. Moreover, the pressing edge is shaped, and configured with respect to the first seal portion, such
5 that the surface course of the first seal portion, which surface course is given by the shape of the first seal portion and tapers into the pressing edge, is continued (in relation to a cross section through the sealing material) homogeneously, in particular linearly.

10 In particular, the first seal portion is shaped, in a region adjoining the compression, such that in this region the surface course of the sealing material in a cross-sectional direction is homogeneous and has a homogeneous curvature which produces an edgeless change of direction of
15 the surface course, in particular between 75° and 105°.

In particular, the closure element, by virtue of a mobility of the closure element substantially along a geometric transverse axis running at right angles to the longitudinal axis, can be adjustable by means of the drive unit in a
20 transverse closing direction into an intermediate position (L-type valve shutter, i.e. L-shaped motional sequence), in which the closure element covers the opening and a closure side of the closure element is in a remote opposite position to the valve seat, and back.

25 Furthermore, the closure element of the vacuum valve according to corresponding specific embodiments of the invention is in particular configured according to one of the versions described above.

The invention further relates to a multifunctional tool for
30 the application and shaping of a sealing material, in particular to an above closure element, to or on a material blank, comprising a recess defining the shape of the

resulting, vulcanized sealing material, a press-off edge forming a first end of the recess with respect to a tool cross section, a slot connecting to the recess at its second end, and a receptacle for sealing material.

5 The recess is shaped, in a region adjoining the press-off edge, such that a course of the press-off edge with respect to the tool cross section is continued in this region by an adapted tool surface course substantially homogeneously, in particular linearly (i.e. also embracing a slight angular
10 offset between press-off edge and further tool surface). Moreover, the multifunctional tool, upon closure of the tool, cooperates with the introduced material blank such that the press-off edge is compressed into the material blank and closes off the recess at its first end with the
15 material blank, the slot forms an overflow channel, and the sealing material present in the receptacle is forced and/or flows through the overflow channel into the recess. In addition, the tool is configured such that the sealing material can then, in a closed tool state, be fully
20 vulcanized.

In particular, the multifunctional tool, the material blank and/or the receptacle for the sealing material can be tempered according to a predetermined cross-linking curve. The material blank here forms, in particular, the closure
25 element or a part of the closure element.

According to a further embodiment of the multifunctional tool, the recess is shaped, in the region adjoining the press-off edge, such that in this region the tool surface course along the tool cross section is homogeneous and has
30 a homogeneous curvature producing an edgeless change of direction of the tool surface course, in particular between 75° and 105°. Alternatively or additionally, the tool can

have a homogeneous transition of the surface line along the tool cross section from the press-off edge to the recess.

The invention further relates to a method for manufacturing a closure element having a seal for a vacuum valve,
5 comprising a multifunctional tool as described, and comprising a material blank embodying the closure element or at least a part of the closure element.

In an open tool state, the material blank and a sealing material are introduced into the multifunctional tool, in
10 particular into the receptacle for the sealing material. In a compression step, by closing of the multifunctional tool, the press-off edge is pressed into the material blank. As a result, a compression corresponding to the press-off edge and having a pressing edge is created in the material blank
15 and the recess is shut off at its first end. Furthermore, the sealing material is deformed and/or liquefied such that at least a part of the sealing material makes its way into the recess through the overflow channel formed in the compression step by the slot of the multifunctional tool
20 and fills said recess.

In a vulcanization step, a full vulcanization of the sealing material is then effected substantially in accordance with the shape of the recess in such a way that the sealing material is shaped, and configured with respect
25 to the pressing edge, such that the surface course, created by the pressing edge, in the material blank is continued substantially homogeneously, in particular linearly (embracing a possibly slight angular offset) - by the surface course of the sealing material - and the sealing
30 material is adhesively connected to the material blank (is vulcanized on).

In particular, the sealing material is shaped, in a region adjoining the press-off edge, such that in this region a surface course of the sealing material in the cross-sectional direction is homogeneous and has a homogeneous
5 curvature producing an edgeless change of direction of the surface course, in particular between 75° and 105°.

In particular, the multifunctional tool is tempered during the vulcanization step according to a predetermined cross-linking curve.

10 For a necessary adhesion quality of the sealant to the carrier material of the material blank, an adhesive is preferably provided on the material blank.

A closure element acquired by implementation of the above method, in particular wherein the closure element is
15 configured according to a previously mentioned embodiment, is likewise the subject of the present invention.

The method according to the invention and the device according to the invention are described in greater detail below on a purely exemplary basis with reference to
20 concrete illustrative embodiments represented schematically in the drawings, wherein further advantages of the invention are also discussed. More specifically:

figs. 1a-b show a detail of a closure element according to the prior art in cross section;

25 fig. 2 shows a first embodiment of an L-type vacuum gate valve according to the invention in an intermediate position of the closure element in schematic cross-sectional side view;

figs. 3a-b show an embodiment of a substantially
30 rectangular closure element for a vacuum valve

according to the invention in top view
representation;

5 *figs. 4a-b* show two embodiments of a seal vulcanized on a
 valve disk (closure element) and of a
 compression according to the invention,
 adjoining the seal, in cross-sectional view;
 and

10 *figs. 5a-b* show a tool according to the invention for
 manufacturing a closure element according to
 the invention, in an open tool state and a
 closed tool state.

15 In figure 2, a first embodiment of a vacuum gate valve
 according to the invention is represented. The vacuum gate
 valve possesses a valve housing 10 having a valve wall 1,
 which latter has an opening 2 having an opening axis 13 and
 having an elongate, substantially rectangular valve seat 3
 surrounding the opening 2. A closure element 20 having a
 closure side 21, which latter is provided, in particular,
 on the process side and has a somewhat larger cross section
20 then the opening 2, serves for the substantially gastight
 closure of the opening 2 by pressing of the closure side 21
 onto the valve seat 3. The closure element 20 is supported
 by two mutually parallel valve rods 6. Since the valve rods
 in figure 2 are shown in side view, only one valve rod 6 is
25 evident there. According to alternative embodiments
 according to the invention, it is also possible for just a
 single valve rod 6 to be provided and for the closure
 element 20 to be supported by this same.

30 The valve housing 10 is divided into a vacuum region 11, in
 which the opening 2, the valve seat 3 and the closure plate
 20 are disposed, and a drive region 12, which lies outside
 the vacuum region 11. The two valve rods 6 are guided

through two gastight bushings, realized as diaphragm seals or diaphragm bellows having seals on their end pieces (for example O-rings), in the valve housing 10 from the vacuum region 11 into the drive region 12. The diaphragm seals or
5 diaphragm bellows are realized such that the valve rods 6 are movable within a certain motional range along a longitudinal axis 8 and a transverse axis 9, while maintaining the gastight seal. Since the drive region 12 is separated in a gastight manner from the vacuum region 11,
10 an atmospheric pressure can prevail in the drive region 12. Abrasive particles present in the drive region 12 cannot make their way into the sensitive vacuum region. In the drive region 12 is disposed a drive unit 7.

The drive unit 7 is configured such that the closure plate
15 20 is adjustable by displacement of the two valve rods 6, along the geometric longitudinal axis 8, in a longitudinal closing direction z from an open position into the intermediate position (shown here), and by displacement of the two valve rods 6, along the geometric transverse axis 9
20 running at right angles to the longitudinal axis 8, in a transverse closing direction y from the intermediate position into a closing position, and back (the motion of the closure plate is L-shaped, therefore the designation L-type).

25 The closure element 20 has a circumferential, vulcanized-on seal 22, which, by means of a compression, is delimited in the direction of the inner region of the closure side 21, i.e. in the direction of that area on the closure side 21 which is shut off by the seal.

30 A detailed representation and description of the inventive design of the sealing region and of the seal/metal transition region is set out below (figures 4a and 4b).

A further embodiment of the invention relates to a valve gate valve (not shown here), which is known, for instance, under the product designation "MONOVAT Series 02 and 03" and, as a transfer valve, designed as a rectangular insert valve, of the company VAT Vakuumventile AG in Haag, Switzerland, has a rectangular opening cross section, the width of which is substantially greater than its height. Such valve types having complex seal structures are also known, for example from EP 2 420 709 A1 of the Applicant.

Such valves are likewise intended for the gastight closing of a flow path, yet solely by means of a linear motion of the closure element. The closure member is linearly displaceable along a geometric adjustment axis running transversely to the opening axis, in the plane of a closure member, from an opened position which frees the opening into a closed position pushed linearly over the opening, in a motion in a closing direction, and conversely back in an opening direction. In a closing position, the sealing material applied to the sealing surface of the closure element is pressed onto the sealing surface surrounding the opening.

Such a vacuum valve which is known from the prior art and is closable by means of a single linear motion has advantages over the transfer valves, which are closable by means of two motions (fig. 2) and which have a relatively complexly constructed drive, or over the wedge valves, in which the seals are subjected to transverse load. Since the closure member of the above-described vacuum valve is in one piece, it can be exposed to high acceleration forces, so that this valve can also be used for rapid and emergency closures. The closing and sealing can be effected by means of a single linear motion, so that a very rapid closing and opening of the valve is possible. The circumferential seal,

in all its portions, finds clearly reproducible conditions in the diverse closing operations. Since the seal, in the closing operation and with the emergence of the closing pressure, is loaded substantially only in the direction of the linear closing motion in perpendicular direction to the seal or partially in the longitudinal direction, yet not transversely to its longitudinal extent, so that transverse forces on the seal are avoided, this vacuum valve is suitable for high-level sealing functions in the vacuum and high vacuum sector.

According to the invention, the sealing material on the part of the closure element (closure member) is in turn configured by compression and vulcanization, so that the sealing material and the shape of the compression provide a homogeneous transition between metal and sealing material, and reworking following the vulcanization can be dispensed with.

Figure 3a shows a substantially rectangular closure element 20' for a vacuum valve according to the invention, in particular for an L-type vacuum valve, in top view representation. The closure element 20' is constructed of a metal or a metal alloy, for example aluminum or special steel, wherein a sealing surface 22 having a seal applied thereto is provided circumferentially on the rim of the closure element 20'.

The seal is created by means of vulcanization of a cross-linkable sealing material on the sealing surface 22. For this purpose, the sealing surface 22 has been provided, in particular prior to the vulcanization process and the application of the sealing material, with an adhesive layer, for example an adhesive agent or primer, in order to provide an appropriately good adherence of the seal on the

carrier material of the closure element 20'. Alternatively or additionally, the sealing surface 22 can itself be pretreated in order to provide the required adhesive properties. Such pretreatment can be conducted, for
5 instance, by mechanical roughening, by etching of the surface or by irradiation of the surface with a plasma, corona treatment or UV irradiation. Generally speaking, on the sealing surface 22 prior to application of the sealing material, a surface state is established - whether by means
10 of a surface treatment or by the creation of an additional adhesive layer - which surface state provides the required adhesion.

The area 23 which is enclosed by the sealing surface 22 or the vulcanized-on seal is that region of the closure
15 element 20' which, in the intended use of the closure element 20' in a vacuum valve, is facing toward the process volume to be shut off, wherein, moreover, in a closing position of the valve, a part of the seal likewise remains facing toward the process volume.

20 The dimensioning and shape of the seal tapers in the direction of the enclosed area 23 into a compression in the closure element 20'. This transition (cf. arrowed region) is represented schematically, likewise in top view, in fig. 3b.

25 As can be seen from figure 3b, the applied seal 25 adjoins a compression 24 in the material. The compression passes further along into the uncoated, and in the course of the creation of the seal 25, unworked, free closure element area 23.

30 Figure 4a shows in cross sectional view a seal 25' vulcanized onto a valve disk 20'' (closure element) and, adjoining the seal, a compression 24' according to the

invention. The sealing material 25' has a first seal portion 26, which in the shown embodiment - since this, in use with a corresponding vacuum valve, lies on the side of the process volume which is intended to be shut off -
5 constitutes the sensitive seal portion in terms of particle residues and contamination. The seal is produced such that reworking after the sealing material 25' has been vulcanized on is unnecessary, at least for this portion 26, and thus no particles or burrs are formed, for example by
10 material removal.

The first seal portion 26 further has a region 27 which adjoins the compression 24' in the valve disk 25'' and can be regarded as critical with respect to a possibly necessary reworking operation.

15 At least in this region 27, the surface of the sealing material 25' runs homogeneously without forming an edge. Moreover, the surface course here has a homogeneous curvature (in particular without a turning point), whereby a continuous change of direction of the surface course,
20 here of around 90°, is produced.

Moreover, the compression 24' has a pressing edge 28, which, in terms of its direction and position relative to the sealing material, is configured such that the homogeneous surface course of the sealing material 25' is
25 continued just as homogeneously and linearly by the pressing edge 28. The transition from sealing material 25' to the carrier material of the closure element 20'' is here shaped substantially without interruption or discontinuity of the common surface lines.

30 Such a transition, comprising just such a homogeneous surface course in the region 27 and comprising a continuation of this course by a specific shaping of the

pressing edge 28, is created according to the invention by means of a special tool (described below) already during the process of applying the sealing material and the vulcanization process and obviates the need for reworking
5 for the removal of excess sealing material, at least for this region.

Should reworking of the sealing material and/or of the carrier material in accordance with the prior art be necessary, then such a homogeneous course would be
10 unattainable due to resulting machine cutting operations and burr formation.

Moreover, the sealing material 25' has a surface roughness which substantially corresponds to that of the tool surface and is thus is significantly lower than in embodiments of
15 the prior art (for instance $R_a = 0.05$ or $0.1 \mu m$). According to the invention, a closure element for a vacuum valve, which closure element has improved material quality and neatness, is thus provided.

Moreover, the compression has a particular depth t with
20 respect to the surface of the closure element 20''. This depth is defined by a tool structure which creates the compression, and lies round about, for instance, $t = 0.2$ mm. Preferably, the pressing edge 28 has a corresponding length in the direction of (parallel to) the
25 surface normal of the sealing surface 22.

Figure 4b shows a further embodiment of the closure element 20'' according to the invention. At variance with the embodiment according figure 4a, the pressing edge 28' of the compression 24'' is not guided parallel to the
30 surface normal of the sealing surface 22, but is shaped at an angle thereto, though a homogeneous transition of the

course of the seal surface is maintained by means of the course of the pressing edge 28'.

An alternative, inventively embraced embodiment is also conceivable (not shown), with respect to which the
5 direction of the pressing edge has a slight angular offset to the tapering surface line of the sealing material. An embodiment of this type should be perceived within the scope of the present invention as a substantially homogeneous continuation of the surface course.

10 Figures 5a and 5b show a tool 30 according to the invention in an open tool state (Figure 5a) and a closed tool state (Figure 5b).

The tool has a forming part 31 and a bottom part 32. In addition, the forming part 31 has a recess 34, which at one
15 end is delimited by a press-off edge 33 of the forming part 31 and at the second end is kept open by a provided slot 35. Moreover, a receptacle 36 for the sealing raw material 37, for example a cord produced from the sealing material, is provided, wherein this receptacle 36 is here
20 assigned to the bottom part 32 or to an interspace between the bottom part 32 and the forming part 31.

Also shown in a material blank 40, which, in cooperation with the tool 30, is to be compressed by means of the press-off edge 33 and, moreover, is to be provided with the
25 sealing material. The blank 40 consists, for instance, at least partially of aluminum, an aluminum alloy, steel, special steel, or an alternative suitable metal alloy. In particular, the blank 40 embodies at least a part of a closure element for a vacuum valve, wherein that side of
30 the closure side which is to be provided with the sealing material, i.e. the side which is facing toward a process volume to be shut off, interacts with the forming part 31.

Upon closing of the tool 30, the material blank 40 is moved in the z direction up to the forming part 31 and the press-off edge 33 is pressed into the material. The contact pressure and the maximum press stroke are adjustable by
5 pressure regulating elements, for example cup springs, and an appropriate stop. Moreover, the bottom part 32 of the tool 30 is displaced in the opposite direction, so that the volume of the receptacle 36 is reduced and the sealing raw material 37 makes its way into the recess 34 via an
10 overflow 38 which, when the tool 30 is closed, remains as a result of the slot 35.

In the closed tool state (figure 5b), the (compressed) press-off edge 33 of the forming part 31 can be seen, which press-off edge engages in the blank 40 and, as a result of
15 the compression, procures a close-off of the recess 34 that is leak-tight for the sealing raw material 37. The space of the recess 34 is completely filled with the sealing raw material 37.

As a result of the specific design of the tool 30, between
20 the forming part 31 and the bottom part 32 and between the bottom part 32 and the material blank 40 gaps 39', 39'' are respectively kept open, so that excess sealing material can be led off through these.

Precisely that material excess must be removed after the
25 vulcanization process. The removal is effected by means of trimming of the appropriate places, whereby impurities and burrs remain at these places. According to the prior art, an analogous trimming is necessary also for the opposite side of the seal, since here too gaps are provided for the
30 evacuation of excess sealing material and material residues of this type are formed. Only as a result of the inventive pressing-off of the seal form at the first end of the

recess 34, whereby a material overflow is prevented there,
can such reworking, at least on this side, be relinquished.

In this closed tool state, the sealing raw material 37 can
be fully vulcanized after the tool 30 has been closed. As a
5 result, the sealing raw material 37 is cross-linked,
whereby a seal which is stable and adheres to the material
blank 40 is created.

Self-evidently, the represented figures show schematically
only possible illustrative embodiments. According to the
10 invention, the various approaches can equally be
intercombined and combined with methods and devices of the
prior art for the closure of process volumes under vacuum
conditions.

Patent claims

1. Closure element, in particular a valve disk, for a vacuum valve and configured for the gastight close-off of a process volume by means of cooperation with a vacuum valve opening, provided for the process volume, of the vacuum valve, comprising

- a first sealing surface, corresponding, in particular in terms of shape and size, to a second sealing surface of the vacuum valve opening wherein the second sealing surface surrounds the vacuum valve opening, and

- a sealing material vulcanized onto the first sealing surface and in accordance with the course thereof and having a defined height in the direction of the surface normal of the first sealing surface, wherein the sealing material has a defined shape with respect to a sealing material cross section, comprising

- a first seal portion, provided, in particular, on the process volume side, and

- a second seal portion, provided, in particular, facing away from the process volume,

characterized in that

- the closure element has a compression adjoining the first seal portion and having a pressing edge, and

- the pressing edge is shaped, and is configured with respect to the first seal portion, such that the surface course of the sealing material, which surface course is given by the shape of the first seal portion and tapers into the pressing edge, is continued substantially homogeneously, in particular linearly.

2. Closure element according to Claim 1,
characterized in that

the first seal portion is shaped, in a region adjoining
the compression, such that in this region the surface
course of the sealing material is homogeneous and has a
homogeneous curvature which produces an edgeless change
of direction of the surface course, in particular
between 75° and 105°.

3. Closure element according to Claim 2,
characterized in that

- the curvature is free from turning points, in particular has a constant direction of curvature, and/or
- the change of direction of the surface course in the region adjoining the compression amounts substantially to 90°.

4. Closure element according to any one of Claims 1 to 3,
characterized in that

the compression has a depth (t) in the direction of the surface normal of the first sealing surface and with respect to the surface of the first sealing surface within the range from 0.15 to 0.25 mm.

5. Closure element according to any one of Claims 1 to 4,
characterized in that
the pressing edge has a length between 0.15 mm and 0.25 mm.

6. Closure element according to any one of Claims 1 to 5,
characterized in that
the pressing edge runs substantially parallel to the
surface normal of the first sealing surface.

5

7. Closure element according to any one of Claims 1 to 6,
characterized in that
the first seal portion has, at least in the region
adjoining the compression, a mean surface roughness R_a
10 between 0.02 μm and 0.15 μm , in particular between 0.05
 μm and 0.1 μm .

8. Closure element according to any one of Claims 1 to 7,
characterized in that
15 the first seal portion has, at least in the region
adjoining the compression, an average surface roughness
depth R_z between 0.2 μm and 1.5 μm , in particular
between 0.5 μm and 1 μm .

- 20 9. Closure element according to any one of Claims 1 to 8,
characterized in that
the sealing material has an elastomer, in particular a
fluoroelastomer.

- 25 10. Closure element according to any one of Claims 1 to 9,
characterized in that
the closure element has

- a coupling for connecting to a drive unit of a vacuum valve in order to provide a controlled motion of the closure element in the vacuum valve, in particular a receptacle for a push rod of the drive unit, in particular wherein

- the receptacle is shaped in the side of the closure element, for the removable mounting of the closure element on the push rod by engagement of a connecting portion of the push rod in the receptacle, and

- the push rod is supported and adjustable by means of the drive unit such that the vacuum valve opening is closable by displacement of the closure element substantially along the push rod axis over the vacuum valve opening and pressing of the closure element with its sealing material onto a valve seat surrounding the vacuum valve opening,

and/or

- at least one grip recess, which is shaped in a side lying opposite a closure side with the vulcanized-on sealing material of the closure element, for the manual application of force to the closure element substantially along the push rod axis, in particular for the removal or mounting of the closure element from or on the push rod.

11. Vacuum valve for the gastight close-off of a process volume, comprising

- a valve housing, which has a vacuum valve opening and a valve seat surrounding the vacuum valve opening and having a second sealing surface,
- 5 • a closure element for the substantially gastight closure of the vacuum valve opening, having a first sealing surface corresponding to the second sealing surface, wherein the first sealing surface has a vulcanized-on sealing material having a defined height in the direction of the surface normal of the first sealing surface, and the sealing material has a defined shape with respect to a sealing material cross section, having
 - 10 ▪ a first seal portion, provided, in particular, on the process volume side, and
 - 15 ▪ a second seal portion, provided, in particular facing away from the process volume,
- a drive unit coupled with the closure element, which drive unit is configured such that the closure element is adjustable at least substantially along a geometric longitudinal axis in a longitudinal closing direction from
 - 20 ▪ an open position, in which the closure element frees the vacuum valve opening, into
 - 25 ▪ a closing position, in which the first sealing surface of the closure element is pressed onto the second sealing surface and closes the vacuum valve opening in a substantially gastight manner, and back,
 - 30 ▪ in particular by virtue of a mobility of the closure element substantially along a

geometric transverse axis running at right angles to the longitudinal axis, is adjustable in a transverse closing direction into an intermediate position, in which the closure element covers the vacuum valve opening and a closure side of the closure element is in a remote opposite position to the valve seat, and back,

characterized in that

- the closure element has a compression adjoining the first seal portion and having a pressing edge, and

- the pressing edge is shaped, and configured with respect to the first seal portion, such that the surface course of the first seal portion, which surface course is given by the shape of the first seal portion and tapers into the pressing edge, is continued substantially homogeneously, in particular linearly,

in particular wherein the closure element is configured according to any one of Claims 1 to 10.

12. Multifunctional tool for the application and shaping of a sealing material, in particular to a closure element according to any one of Claims 1 to 10, on a material blank, comprising

- a recess defining the shape of the resulting, vulcanized sealing material,
 - a press-off edge forming a first end of the recess with respect to a tool cross section,
 - a slot connecting to the recess at its second end,
- and

- a receptacle for the sealing material,
wherein

- the recess is shaped, in a region adjoining the
press-off edge, such that a course of the press-off
5 edge with respect to the tool cross section is
continued in this region by an adapted tool surface
course substantially homogeneously, in particular
linearly,

- the multifunctional tool, upon closure of the tool,
10 cooperates with the introduced material blank such
that

- the press-off edge is compressed into the material
blank and closes off the recess at its first end
with the material blank,

- 15 ▫ the slot forms at the second end an overflow
channel, and

- a sealing material present in the receptacle is
forced and/or flows through the overflow
channel into the recess, and

- 20 • the sealing material, in a closed tool state, is
vulcanizable,

in particular wherein

- the multifunctional tool can be tempered according to
a predetermined cross-linking curve and/or

- 25 • the material blank forms a closure element or a part
of the closure element according to any one of Claims
1 to 10.

13. Multifunctional tool according to Claim 12,

30 characterized in that

- the recess, in the region adjoining the press-off edge has a homogeneous curvature producing an edgeless change of direction of the tool surface course, in particular between 75° and 105°, and/or
- 5 • has a homogeneous transition of the surface line along the tool cross section from the press-off edge to the recess.

14. Method for manufacturing a closure element having a seal for a vacuum valve, comprising
- 10 • a multifunctional tool according to Claim 12 or 13 and
- a material blank embodying the closure element or a part of the closure element,
- 15 wherein
- in an open tool state, the material blank and a sealing material are introduced into the multifunctional tool, in particular into the receptacle for the sealing material,
 - 20 • in a compression step, by closing of the multifunctional tool,
 - the press-off edge is pressed into the material blank, whereby
 - a compression corresponding to the press-off edge
 - 25 and having a pressing edge is created in the material blank, and
 - the recess is shut off at its first end, and
 - the sealing material is deformed and/or liquefied such that at least a part of the sealing
 - 30 material makes its way into the

recess through the overflow channel formed in the compression step by the slot and fills said recess, and

- in a vulcanization step, a vulcanization of the sealing material is effected substantially in accordance with the shape of the recess in such a way that

- the sealing material is shaped, and configured with respect to the pressing edge, such that the surface course, created by the pressing edge, in the material blank is continued substantially homogeneously, in particular linearly, and

- the sealing material is adhesively connected to the material blank,

in particular wherein

- the sealing material is shaped, in a region adjoining the pressing edge, such that in this region the surface course of the sealing material is homogeneous and has a homogeneous curvature producing an endless change of direction of the surface course, in particular between 75° and 105°, and/or

- the multifunctional tool is tempered during the vulcanization step according to a predetermined cross-linking curve.

15. Closure element acquired by implementation of a method according to Claim 14, in particular wherein a closure element is configured according to any one of Claims 1 to 10.