

Description

The present invention relates to a method and an apparatus for detecting electrically-conductive material (hereinafter simply referred to as "conductive material") contained in glass fiber in a state of maldistribution, and relates to a method and an apparatus in which existence of fine conductive material which is possibly contained in glass fiber can be detected easily and accurately when the glass fiber is running in a manufacturing process of the glass fiber.

Fine particles of conductive material may sometimes be contained in a state of maldistribution in glass fiber such as glass filaments, glass yarns or strands, and the like, constituting glass roving or glass cloth. This is because glass may contain metal components due to batch material, clay brick, or the like. The conductive material contained in glass fiber may cause a problem that electrical insulating properties are deteriorated when the glass fiber is applied to printed circuit substrates or the like. Accordingly, it is necessary to remove such a part of the glass fiber which contains conductive material during the manufacturing process of the glass fiber.

The following methods for detecting conductive material contained in a very small amount in glass fiber, are conventionally known: a method which utilizes changes in dielectric constant, a method which utilizes a phase difference in a microwave, and a method which utilizes electric discharge. In the detection method utilizing changes in dielectric constant, it is necessary to directly measure the dielectric constant of glass fiber. In the detection method utilizing a phase difference in a microwave, conductive material or a fault in glass fiber is detected by a phase difference between a transmitting waveform and a receiving waveform of a microwave (JP-A-60-20138). In the detection method utilizing electric discharge, conductive material contained in glass fiber is detected by causing high-frequency discharge on the conductive material (JP-A-59-214748).

In the detection method utilizing changes in dielectric constant, there is such a problem that when the amount of conductive material contained in glass fiber is extremely small, the value of a dielectric constant to be measured is so small that a measuring instrument becomes insufficient to indicate the value of a measured dielectric constant so that measurement becomes impossible. Unless glass fiber is in a stationary state, generally, it is impossible to measure a dielectric constant, and therefore the detection method utilizing changes in dielectric constant cannot be applied to the case where glass fiber is moving. Accordingly, there is a problem that this method cannot be utilized at all in production management of glass fiber. In the detection method utilizing a phase difference in a microwave as well as in the detection method utilizing electric discharge, there is a disadvantage that the capability of detecting conductive material contained in glass fiber may be considerably lowered owing to an influence of a hiding action of moisture, size, dust, or the like, attached on the surfaces of the glass fiber. Granting that there is not such a hiding action due to those factors, among various kinds of conductive material contained in glass fiber, it has been impossible to detect those smaller than 2 mm in length in the axial direction of the glass fiber.

The non-published document WO 86/06364 describes a device for detection and identification of metal items including a marginal oscillator with a resonant circuit. The resonant circuit includes an inductor surrounding a path along which any metal items are caused to travel. The frequency and amplitude changes in the oscillation produced by the oscillator due to the presence of a metal item in the inductor are displayed on orthogonal axes of a graph and the graph is used to identify the detected metal.

DE-A-2 508 067 describes a device for detecting metal particles in a flow of dielectric material which measures the frequency shift of an oscillator upon passage of such a particle through a self-induction coil which is part of the oscillator.

It is an object of the present invention to provide a method and an apparatus for detecting electrically conductive material contained in glass fiber, in which the conductive material can be detected even in the case where the glass fiber is moving in the process of manufacturing the glass fiber, in which only the conductive material maldistributed in the glass fiber can be detected without being affected by moisture, size, dust, or the like, attached on the surfaces of the glass fiber, and in which the conductive material can be detected even if it is a minute one having a length smaller than 2 mm in the axial direction of the fiber.

The above object is achieved, in accordance with the invention by a method of detecting electrically conductive material in a dielectric material comprising the steps of; making an oscillator oscillate, said oscillator including a reactance element, moving the dielectric material, which may contain electrically conductive material to be detected, in the vicinity of said reactance element; detecting a change in reactance of said reactance element during movement of said dielectric material; and FM detecting with a first detector an output of said oscillator and producing an FM detection signal, and AM detecting with a second detector an output of said oscillator and producing an AM detection signal; combining said AM and FM detection signals to produce a composite signal, and comparing said composite signal with a reference

value to produce a further signal only when said composite signal is larger than said reference value, thereby indicating that the change in reactance is caused by the presence of electrically conductive material in said dielectric material, said dielectric material being a glass fiber.

The object of the invention is also achieved by an apparatus detecting conductive material in a dielectric material comprising a reactance element disposed in the vicinity of said dielectric material; means for moving said dielectric material; an oscillator including said reactance element as a circuit component thereof; and a first detector for FM detecting an output of said oscillator to thereby produce an FM detection signal; and a second detector for AM detecting the output of said oscillator to thereby produce an AM detection signal; a composite wave generator for combining said AM and FM detection signals to thereby produce a composite signal, and a comparator for comparing said composite signal with a reference value to thereby produce a further signal only when a change in reactance is caused by the presence of electrically conductive material in said dielectric material, said dielectric material being a glass fiber.

Other objects, features and advantages of the present invention will be apparent more fully from the following description taking in conjunction with the accompanying drawings, wherein:

Fig. 1 is a block diagram showing the detection apparatus according to the present invention;
 Fig. 2 is a schematic view showing an arrangement of the detection coil in the manufacturing process;
 Fig. 3 is a waveform diagram of an output signal of an LC oscillator showing two states of oscillation; and
 Fig. 4 is a waveform diagram showing states of generation of signals S_1 , S_2 , and S_3 and relation therebetween.

An embodiment according to the present invention will be described hereunder with reference to the accompanying drawings.

Fig. 1 is a block diagram showing the apparatus for detecting conductive material maldistributed in glass fiber according to the present invention. In Fig. 1, an oscillation coil 1, which is a reactance element, is connected to a loose coupling LC oscillator 2 so that the oscillation coil 1 functions as a circuit component for determining the state of oscillation of the LC oscillator 2. As the LC oscillator 2, a known one may be employed. The frequency of oscillation of the LC oscillator 2 is generally selected to be within a range of from 10 MHz to 50 MHz in which few noises are generally generated, and preferably, a frequency of 30 MHz is used. Further, in the manufacturing process of glass fiber products, the oscillation coil 1 is disposed at a position just below a size applicator at a position (A in the drawing) between a cake 3 and a bobbin 4 in the rewinding step, or at a position between a winder and a strand guide. The dimensions of the oscillation coil 1 are selected to be small so as to have a diameter of 3-10 mm and a length of 3-10 mm. The reference numeral 5 represents a part of glass fiber which is in the manufacturing process, the glass fiber being arranged so as to pass through an inner space of the oscillation coil 1 as shown in Fig. 2 or through an external space in the vicinity of the oscillation coil 1. In such an arrangement of the oscillation coil 1 as described above, when a portion of the glass fiber 5 containing maldistributed exceedingly fine conductive material passes through a space in the vicinity of the oscillation coil 1, the reactance (inductance) of the oscillation coil 1 is changed to thereby change the state of oscillation of the LC oscillator 2.

An oscillating current produced from the LC oscillator 2 is supplied to an AM detector 6 and an FM detector 7 which are connected to the output of the LC oscillator 2 in parallel with each other. An AM detection signal S_1 taken out by the AM detector 6 and an FM detecting signal S_2 taken out by the FM detector 7 are supplied to a composite wave generator 8, in which respective amplitudes of these two signals S_1 and S_2 are added to each other. The thus obtained composite signal S_3 is amplified by an AC amplifier 9 in the next stage. The thus amplified signal S_4 is applied to one of the two input terminals of a comparator 10. A reference voltage V_0 is applied to the other input terminal of the comparator 10 from a voltage setter 11, so that the signal S_4 is compared with the reference voltage V_0 . On the basis of the result of comparison, it is possible to detect whether target conductive material is contained in the glass fiber 5 or not. The voltage setter 11 is arranged so as to be able to desirably change the set value of the reference voltage V_0 . Accordingly, if a desired value of the reference voltage V_0 is set as a threshold, it is possible to detect conductive material having a desired length and a desired diameter. That is, when the signal S_4 is larger than the reference voltage V_0 , a detection signal S_5 is produced at the output of the comparator 10 so as to prove the detection of conductive material.

Next, description will be made as to the detecting operation of the thus arranged detection apparatus.

Fig. 3 shows waveforms of the oscillating current produced from the LC oscillator 2 in two states, a waveform 20 being in a normal state, a waveform 21 being in a changed state. The waveform 20 in the normal state is generated in the case where the glass fiber 5 is not passing through the inside of or the outside vicinity of the oscillation coil 1, or in the case where no conductive material is contained in the glass fiber 5 even though the glass fiber 5 is actually passing through or by the oscillation coil 1. That is, the waveform 20 is generated in the condition that the inductance of the oscillation coil 1 is not changed but

kept in its initial value so that the LC oscillator 2 is kept to continue oscillation in the initially set state. In this case, generally, moisture or size attached on the surface of the glass fiber 5 is being detected. The waveform 21 in the changed state, on the contrary, is generated in the case where glass fiber containing conductive material is passing in the vicinity of the oscillation coil 1. That is, the waveform 21 is generated under the condition that the inductance of the oscillation coil 1 is changed by the existence of the conductive material to thereby change the state of oscillation of the LC oscillator 2. However, when the conductive material is contained in the glass fiber by a very small amount, the change in waveform of the oscillating current is small even though the waveform is changed, and therefore it is difficult to distinguish the waveform of the oscillating current in the changed state from that in the normal state. Thus, the inductance of the oscillation coil 1 is changed in accordance with the existence of conductive material in the glass fiber 5, so that the output signal of the LC oscillator 2 has either one of the waveforms 20 and 21. The waveforms 20 and 21 are different from each other in amplitude as well as in frequency.

The output signal of the LC oscillator 2 is branched so as to be supplied to the AM detector 6 and FM detector 7. The AM detector 6 is arranged to detect the oscillation signal in AM manner, and the FM detector 7 is arranged to detect the oscillation signal in FM manner. The diagrams (A) and (B) of Fig. 4 show voltage waveforms of the AM detection signal S_1 and the FM detection signal S_2 respectively. It is empirically known that the AM detection signal S_1 and the FM detection signal S_2 have the following features with respect to the changes in waveform. That is, when a portion of the glass fiber 5 containing conductive material passes in the vicinity of the oscillation coil 1, the inductance of the oscillation coil 1 is changed to thereby change the respective waveforms of the signals S_1 and S_2 towards the positive side (portions 22 and 23 in the drawing). Thereafter, when only a portion of the glass fiber 5 on which moisture or size is attached passes through or by the oscillation coil 1, on the contrary, the inductance of the oscillation coil 1 is changed again to thereby change the respective waveforms of the signals S_1 and S_2 towards the negative and positive sides respectively (portions 24 and 25 in the drawing). In this case, the AM detection signal S_1 and the FM detection signal S_2 are adjusted in advance to have the same amplitudes as each other by means of any proper circuit component. As described above, in the case of the FM detection signal S_2 , conductive material is detected in the same signal state as that in the case of moisture and size, and therefore, the former cannot be distinguished from the latter. In the case of the AM detection signal S_1 , on the contrary, the waveform is generally inverted between detection of conductive material and detection of moisture or the like, and therefore the former can be clearly distinguished from the latter. However, strictly speaking, even in case of the AM detection signal S_1 , there is a possibility that in the case of detection of moisture or the like, the waveform is changed towards the positive side by a hunting phenomenon due to an influence of the moisture attached on the surface of the glass fiber 5, and therefore conductive material and moisture or the like cannot be strictly distinguished from each other by use of only the AM detection signal S_1 .

Therefore, the signals S_1 and S_2 are supplied to the composite wave generator 8 in the next stage so as to be combined with each other synchronously at a point in time when both the signals S_1 and S_2 are changed. As a result, in the output signal S_3 of the composite wave generator 8, a waveform 26 which is a result of summation of the signals S_1 and S_2 is generated as shown in the diagram (C) of Fig. 4 when the signals S_1 and S_2 are in phase (waveforms 22 and 23 respectively) upon detection of conductive material, while substantially no change is generated upon detection of moisture or the like because the signals S_1 and S_2 are different in phase by 180 degrees (waveforms 24 and 25 respectively) so that the signals S_1 and S_2 are canceled by each other. Further, in the case of the output signal S_3 , even if a waveform is generated to a certain extent, the generated waveform can be clearly distinguished from the above-mentioned waveform 26. As described above, the inductance of the oscillation coil 1 is changed in either case of detection of conductive material and detection of only moisture or the like. However, the detection apparatus of this embodiment is arranged such that the change in signal is detected as a change in amplitude as well as in frequency in the AM detection signal S_1 and the FM detection signal S_2 and both the detection signals S_1 and S_2 are combined with each other by the composite wave generator 8, so that only the detection of conductive material can be accurately performed with no erroneous recognition.

The thus obtained signal S_3 is then amplified by the AC amplifier 9 to a desired level, and the thus amplified signal S_4 is applied to the comparator 10 so as to be compared with the reference voltage V_0 . In the case where the signal S_4 is larger than the reference voltage V_0 , a conductive material detection signal S_5 is produced. The signal S_5 is further supplied to an alarm device 12 in the next stage so as to inform a worker of detection of conductive material. At the same time, the signal S_5 is transferred to an automatic removal apparatus 13 to actuate the latter to cut the glass fiber by a cutter so as to remove a portion of the glass fiber containing the conductive material. Then, the worker connects the cut glass fiber again. It is possible to automatize all the steps of the work described above by using the signal S_5 .

The coil is used as a reactance element in the foregoing embodiment. The shape of the coil may be desirably modified. Further, in place of the coil, a capacitor having a predetermined shape may be used. Moreover, according to the present invention, conductive material contained in glass fiber can be detected to a minimum diameter is 0.5 μm and a minimum length of 0.5 mm.

In the detection apparatus according to the present invention, particularly, existence of conductive material can be checked with respect to all the portions of glass fiber in every step in the manufacturing process, so that satisfactory detection can be performed.

In the detection apparatus according to the present invention, however, it is not always required that the glass fiber and the reactance element included in the detection apparatus move relative to each other. Even in the case where glass fiber is stationarily disposed in the vicinity of the reactance element, if conductive material is contained in the glass fiber, the detection apparatus according to the present invention can detect the conductive material.

Next, description will be made as to an example to which the detection apparatus according to the present invention is actually applied. As shown in Fig. 2, a cylindrical oscillation coil 1 having a length of 7 mm and an inner diameter of 5 mm was disposed between a cake 3 and a spindle 14 of a rewinder, and glass fiber 5 was caused to run through an inside space of the oscillation coil 1. The oscillation coil 1 is arranged as shown in Fig. 1 so that a change in inductance corresponding to conductive material (mainly, iron sulfide, nickel sulfide, chromium, iron, nickel, copper, or gold) contained in the glass fiber 5 is detected as a change in voltage signal S_4 . The glass fiber 5 was running, for example, at a speed of 100 m/min. Assuming that a composite wave signal S_3 having a voltage value of L [mV] is generated when conductive material having a length of K [mm] is contained the glass fiber 5. This signal S_3 was amplified with 94 dB in the AC amplifier 9 and transferred to the comparator 10 in which a reference voltage V_0 was so that conductive material having a length of 0.5 mm can be detected. When the signal S_4 having a value larger than the voltage value V_0 was applied to the comparator 10, the signal S_5 was produced from the comparator 10. The automatic removal apparatus 13 was actuated to cut the glass fiber 5 so as to remove a portion of the glass fiber containing conductive material. Then, the operator stopped the spindle 14 and carried out the succeeding processing such as connection of the glass fiber 5, or the like. In this case, arrangement may be made such that a printer or the like is actuated through a relay to record the time when conductive material is detected, the time of working such as cutting, or the like. Data recorded by the printer are utilized for study of working efficiency. The frequency used in the LC oscillator 2 was 30 MHz. The following table shows the results of the experiment.

Moving speed of Glass fiber	K [mm]	$\cdot L$ [mV]
100 m/min	0.5	50
	1.0	100
	1.5	170
	2.0	300
	3.0	500
	5.0	800
	7.0	1700
	10.0	3500

As apparent from the foregoing explanation, the detection apparatus according to the present invention is arranged such that a reactance element which is a constituent component of an oscillator set in a predetermined state of oscillation is disposed in a manufacturing process of glass fiber so that conductive material contained in the glass fiber can be detected on the basis of a change in state of oscillation of the oscillator due to a mutual action between the conductive material and the reactance element. Therefore, only the conductive material maldistributed in glass fiber can be detected easily and accurately under the condition that the glass fiber is running, with no influence of moisture or the like attached on the glass fiber. Further, even extremely fine conductive material can be detected. Moreover, it is possible to carry out checking for all the products of glass fiber. Accordingly, there is such an advantage that all the inferior portions of glass fiber can be removed.

Claims

1. A method of detecting electrically conductive material in a dielectric material comprising the steps of: making an oscillator (2) oscillate, said oscillator (2) including a reactance element (1);

The coil is used as a reactance element in the foregoing embodiment. The shape of the coil may be desirably modified. Further, in place of the coil, a capacitor having a predetermined shape may be used. Moreover, according to the present invention, conductive material contained in glass fiber can be detected to a minimum diameter is 0.5 μm and a minimum length of 0.5 mm.

In the detection apparatus according to the present invention, particularly, existence of conductive material can be checked with respect to all the portions of glass fiber in every step in the manufacturing process, so that satisfactory detection can be performed.

In the detection apparatus according to the present invention, however, it is not always required that the glass fiber and the reactance element included in the detection apparatus move relative to each other. Even in the case where glass fiber is stationarily disposed in the vicinity of the reactance element, if conductive material is contained in the glass fiber, the detection apparatus according to the present invention can detect the conductive material.

Next, description will be made as to an example to which the detection apparatus according to the present invention is actually applied. As shown in Fig. 2, a cylindrical oscillation coil 1 having a length of 7 mm and an inner diameter of 5 mm was disposed between a cake 3 and a spindle 14 of a rewinder, and glass fiber 5 was caused to run through an inside space of the oscillation coil 1. The oscillation coil 1 is arranged as shown in Fig. 1 so that a change in inductance corresponding to conductive material (mainly, iron sulfide, nickel sulfide, chromium, iron, nickel, copper, or gold) contained in the glass fiber 5 is detected as a change in voltage signal S_4 . The glass fiber 5 was running, for example, at a speed of 100 m/min. Assuming that a composite wave signal S_3 having a voltage value of L [mV] is generated when conductive material having a length of K [mm] is contained the glass fiber 5. This signal S_3 was amplified with 94 dB in the AC amplifier 9 and transferred to the comparator 10 in which a reference voltage V_0 was so that conductive material having a length of 0.5 mm can be detected. When the signal S_4 having a value larger than the voltage value V_0 was applied to the comparator 10, the signal S_5 was produced from the comparator 10. The automatic removal apparatus 13 was actuated to cut the glass fiber 5 so as to remove a portion of the glass fiber containing conductive material. Then, the operator stopped the spindle 14 and carried out the succeeding processing such as connection of the glass fiber 5, or the like. In this case, arrangement may be made such that a printer or the like is actuated through a relay to record the time when conductive material is detected, the time of working such as cutting, or the like. Data recorded by the printer are utilized for study of working efficiency. The frequency used in the LC oscillator 2 was 30 MHz. The following table shows the results of the experiment.

Moving speed of Glass fiber	K [mm]	L [mV]
100 m/min	0.5	50
	1.0	100
	1.5	170
	2.0	300
	3.0	500
	5.0	800
	7.0	1700
	10.0	3500

As apparent from the foregoing explanation, the detection apparatus according to the present invention is arranged such that a reactance element which is a constituent component of an oscillator set in a predetermined state of oscillation is disposed in a manufacturing process of glass fiber so that conductive material contained in the glass fiber can be detected on the basis of a change in state of oscillation of the oscillator due to a mutual action between the conductive material and the reactance element. Therefore, only the conductive material maldistributed in glass fiber can be detected easily and accurately under the condition that the glass fiber is running, with no influence of moisture or the like attached on the glass fiber. Further, even extremely fine conductive material can be detected. Moreover, it is possible to carry out checking for all the products of glass fiber. Accordingly, there is such an advantage that all the inferior portions of glass fiber can be removed.

Claims

1. A method of detecting electrically conductive material in a dielectric material comprising the steps of: making an oscillator (2) oscillate, said oscillator (2) including a reactance element (1);



moving said dielectric material, which may contain electrically conductive material to be detected, in the vicinity of said reactance element (1);

detecting a change in reactance of said reactance element (1) during movement of said dielectric material; and

FM detecting with a first detector (7) an output of said oscillator (2) and producing an FM detection signal (S_2);

characterized by

AM detecting with a second detector (6) an output of said oscillator (2) and producing an AM detection signal (S_1); combining said AM and FM detection signals (S_1, S_2) to produce a composite signal (S_3, S_4), and

comparing said composite signal (S_3, S_4) with a reference value (V_0) to produce a further signal (S_5) only when said composite signal (S_3, S_4) is larger than said reference value (V_0), thereby indicating that the change in reactance is caused by the presence of electrically conductive material in said dielectric material, said dielectric material being a glass fiber (5).

2. An apparatus detecting electrically conductive material in a dielectric material comprising:
 - a reactance element (1) disposed in the vicinity of said dielectric material;
 - means for moving said dielectric material;
 - an oscillator (2) including said reactance element (1) as a circuit component thereof; and
 - a first detector (7) for FM detecting an output of said oscillator (2) to thereby produce an FM detection signal (S_2);
 - characterized by
 - a second detector (6) for AM detecting the output of said oscillator (2) to thereby produce an AM detection signal (S_1);
 - a composite wave generator (8) for combining said AM and FM detection signals (S_1, S_2) to thereby produce a composite signal (S_3, S_4), and
 - a comparator (10) for comparing said composite signal (S_3, S_4) with a reference value (V_0) to thereby produce a further signal (S_5) only when a change in reactance is caused by the presence of electrically conductive material in said dielectric material, said dielectric material being a glass fiber (5).
3. A conductive material detection apparatus according to claim 2, wherein said reference value (V_0) is made to be adjustable to a desired value.
4. A conductive material detection apparatus according to claim 3, wherein said reactance element (1) includes a coil.
5. A conductive material detection apparatus according to claim 4, wherein said glass fiber (5) is arranged so as to pass through the inside of said coil.
6. A conductive material detection apparatus according to any of claims 1 to 5, wherein said oscillator (2) is an LC-oscillator.

Revendications

1. Procédé pour détecter un matériau électriquement conducteur dans un matériau diélectrique comprenant les étapes de :
 - mise en oscillation d'un oscillateur (2), ledit oscillateur (2) comprenant un élément à réactance (1) ;
 - mise en mouvement dudit matériau diélectrique, qui peut contenir un matériau électriquement conducteur à détecter, dans le voisinage dudit élément à réactance (1) ;
 - détection d'une modification de la réactance dudit élément à réactance (1) pendant le mouvement dudit matériau diélectrique ; et
 - détection FM par un premier détecteur (7) d'une sortie dudit oscillateur (2) produisant un signal de détection FM (S_2) ;
 - caractérisé par :
 - une détection AM par un second détecteur (6) d'une sortie dudit oscillateur (2) produisant un signal de détection AM (S_1) ;
 - combinaison desdits signaux de détection AM et FM (S_1, S_2) afin de produire un signal



composite (S_3 , S_4) ; et

- comparaison dudit signal composite (S_3 , S_4) avec une valeur de référence (V_0) afin de produire ensuite un signal (S_5) uniquement quand ledit signal composite (S_3 , S_4) est supérieur à ladite valeur de référence (V_0), indiquant ainsi que la modification de la réactance est provoquée par la présence d'un matériau électriquement conducteur dans ledit matériau diélectrique, ledit matériau diélectrique étant une fibre de verre (5).

2. Appareil pour détecter un matériau électriquement conducteur dans un matériau diélectrique comprenant :

- un élément à réactance (1) disposé au voisinage dudit matériau diélectrique ;
- des moyens pour mettre en mouvement ledit matériau diélectrique ;
- un oscillateur (2) comprenant ledit élément à réactance (1) comme composant de son circuit ; et
- un premier détecteur (7) pour la détection FM d'une sortie dudit oscillateur (2) afin de produire ainsi un signal de détection FM (S_2) ;
- caractérisé par :
- un second détecteur (6) pour la détection AM de la sortie dudit oscillateur (2) afin de produire ainsi un signal de détection AM (S_1) ;
- un générateur d'onde composite (8) afin de combiner lesdits signaux de détection AM et FM (S_1 , S_2) pour produire ainsi un signal composite (S_3 , S_4) ; et
- un comparateur (10) afin de comparer ledit signal composite (S_3 , S_4) avec une valeur de référence (V_0) pour produire ainsi un autre signal (S_5) uniquement quand une modification de réactance est provoquée par la présence d'un matériau électriquement conducteur dans ledit matériau diélectrique, ledit matériau diélectrique étant une fibre de verre (5).

3. Appareil pour détecter un matériau conducteur suivant la revendication 2, dans lequel ladite valeur de référence (V_0) est prévue pour être ajustable à une valeur souhaitée.

4. Appareil pour détecter un matériau conducteur suivant la revendication 3, dans lequel ledit élément à réactance (1) comprend une bobine.

5. Appareil pour détecter un matériau conducteur suivant la revendication 4, dans lequel ladite fibre de verre (5) est agencée de telle sorte qu'elle passe à l'intérieur de ladite bobine.

6. Appareil pour détecter un matériau conducteur suivant l'une quelconque des revendications 1 à 5, dans lequel ledit oscillateur (2) est un oscillateur LC.

Patentansprüche

1. Verfahren zum Ermitteln von elektrisch leitfähigem Material in einem dielektrischen Material, mit den Schritten:
Veranlassen eines Oszillators (2) zu schwingen, wobei der Oszillator (2) ein Reaktanzelement (1) einschließt;
Bewegen des dielektrischen Materials, welches zu ermittelndes, elektrisch leitfähiges Material enthalten mag, in die Umgebung des Reaktanzelementes (1);
Ermitteln einer Reaktanzänderung des Reaktanzelementes (1) während einer Bewegung des dielektrischen Materials; und
FM Detektieren einer Ausgabe des Oszillators (2) mit einem ersten Detektor (7), und Erzeugen eines FM Detektionssignales (S_2);
gekennzeichnet durch
AM Detektieren einer Ausgabe des Oszillators (2) mit einem zweiten Detektor (6), und Erzeugen eines AM Detektionssignales (S_1);
Kombinieren der AM und FM Detektionssignale (S_1 , S_2), um ein Verbundsignal (S_3 , S_4) zu erzeugen, und
Vergleichen des Verbundsignales (S_3 , S_4) mit einem Referenzwert (V_0), um ein weiteres Signal (S_5) nur zu erzeugen, wenn das Verbundsignal (S_3 , S_4) größer ist als der Referenzwert (V_0), um dadurch anzuzeigen, daß die Reaktanzänderung durch die Gegenwart von elektrisch leitfähigem Material in dem dielektrischen Material verursacht wird, wobei das dielektrische Material eine Glasfaser (5) ist.



2. Vorrichtung, welche elektrisch leitfähiges Material in einem dielektrischen Material ermittelt, mit einem in der Umgebung des dielektrischen Materials angeordneten Reaktanzelement;
einer Einrichtung zum Bewegen des dielektrischen Materials;
einem Oszillator (2), welcher das Reaktanzelement (1) als einen Schaltkreisbestandteil davon einschließt; und
einem ersten Detektor (7) zum FM Detektieren einer Ausgabe des Oszillators (2), um dadurch ein FM Detektionssignal (S_2) zu erzeugen;
gekennzeichnet durch
einen zweiten Detektor (6) zum AM Detektieren der Ausgabe des Oszillators (2), um dadurch ein AM Detektionssignal (S_1) zu erzeugen;
einen Verbundwellengenerator (8) zum Kombinieren der AM und FM Detektionssignale (S_1 , S_2), um dadurch ein Verbundsignal (S_3 , S_4) zu erzeugen, und
einen Komparator (10) zum Vergleichen des Verbundsignales (S_3 , S_4) mit einem Referenzwert (V_0), um dadurch ein weiteres Signal (S_5) nur zu erzeugen, wenn eine Reaktanzveränderung durch die Gegenwart von elektrisch leitfähigem Material in dem dielektrischen Material bewirkt wird, wobei das dielektrische Material eine Glasfaser (5) ist.
3. Vorrichtung zum Ermitteln von leitfähigem Material nach Anspruch 2, worin der Referenzwert (V_0) auf einen gewünschten Wert abgleichbar ausgelegt ist.
4. Vorrichtung zum Ermitteln von leitfähigem Material nach Anspruch 3, worin das Reaktanzelement (1) eine Spule einschließt.
5. Vorrichtung zum Ermitteln von leitfähigem Material nach Anspruch 4, worin die Glasfaser (5) angeordnet ist, durch das Innere der Spule hindurch zu gehen.
6. Vorrichtung zum Ermitteln von leitfähigem Material nach einem der Ansprüche 1 bis 5, worin der Oszillator (2) ein LC-Oszillator ist.

