

CLAIMS

1. A method of polymerizing an olefin using a Ziegler-Natta catalyst and an unsupported molecular catalyst in a same reactor at the same time, the method comprising simultaneously contacting at least one polymerizable olefin in the reactor with the Ziegler-Natta catalyst and the unsupported molecular catalyst in a saturated or aromatic hydrocarbon liquid under effective conditions to give a polyolefin product comprising a mixture of a first polyolefin made by a first polymerization reaction catalyzed by the Ziegler-Natta catalyst and a second polyolefin made by a second polymerization reaction catalyzed by the unsupported molecular catalyst.
2. The method of claim 1 wherein the Ziegler-Natta catalyst is either an enhanced Ziegler-Natta catalyst that consists essentially of a product of a first activation reaction of (A) a hydrocarbylaluminoxane and (B) a magnesium halide-supported titanium procatalyst in (C) a saturated or aromatic hydrocarbon liquid; or the Ziegler-Natta catalyst is a magnesium halide-supported titanium catalyst, wherein the magnesium halide-supported titanium catalyst is a product of a second activation reaction of (B) a magnesium halide-supported titanium procatalyst with a trialkylaluminum compound; wherein the (B) magnesium halide-supported titanium procatalyst has been prepared by contacting (D) a solid particulate consisting essentially of magnesium halide with (E) titanium tetrachloride in the (C) saturated or aromatic hydrocarbon liquid so as to give the (B) magnesium halide-supported titanium procatalyst; and wherein the unsupported molecular catalyst consists essentially of a product of a third activation reaction of an unsupported molecular ligand-metal complex procatalyst with (A) a hydrocarbylaluminoxane.
3. The method of claim 1 or 2 wherein the contacting comprises: (i) adding a first feed of the Ziegler-Natta catalyst and a second feed of the unsupported molecular catalyst into the reactor, which contains the at least one polymerizable olefin, wherein the first and second feeds are different; (ii) adding a first feed of the Ziegler-Natta catalyst into the reactor and preparing the unsupported molecular catalyst *in situ* in the reactor, wherein the unsupported molecular catalyst is prepared *in situ* in the reactor by adding a third feed containing the unsupported molecular ligand-metal complex procatalyst and a fourth feed containing the (A) hydrocarbylaluminoxane into the reactor, which contains the at least one polymerizable olefin, wherein the first and third feeds are the same or different and wherein the first and fourth feeds are the same or different, with the proviso that the third and fourth feeds are different; (iii) adding a second feed of the unsupported molecular catalyst into the reactor

and preparing the Ziegler-Natta catalyst *in situ* in the reactor, wherein the Ziegler-Natta catalyst is prepared *in situ* in the reactor by adding a fifth feed containing the suspension of the (B) magnesium halide-supported titanium procatalyst in the (C) saturated or aromatic hydrocarbon liquid and free of (lacking) the trialkylaluminum and a sixth feed containing the (A) hydrocarbylaluminoxane and containing the trialkylaluminum, into the reactor, which contains the at least one polymerizable olefin, wherein the second and fifth feeds are the same or different and wherein the second and sixth feeds are the same or different, with the proviso that the fifth and sixth feeds are different; or (iv) adding a seventh feed of the suspension of the (B) magnesium halide-supported titanium procatalyst in the (C) saturated or aromatic hydrocarbon liquid and the unsupported molecular ligand-metal complex procatalyst and an eighth feed of the (A) hydrocarbylaluminoxane or a mixture of the (A) hydrocarbylaluminoxane and the trialkylaluminum into the reactor, which contains the at least one polymerizable olefin, wherein the seventh and eighth feeds are different.

4 The method of aspect 2 or 3 wherein the first or second activation reaction further comprises contacting at least one of the (B) magnesium halide-supported titanium procatalyst with (G) an organoborate or (H) an organoboron; and/or the third activation reaction further comprises contacting the unsupported molecular ligand-metal complex procatalyst with (G) an organoborate or (H) an organoboron.

5. The method of any one of claims 1 to 4 wherein: (i) the at least one polymerizable olefin is ethylene and the polyolefin product comprises a polyethylene; (ii) the at least one polymerizable olefin is at least one (C₃-C₄₀)alpha-olefin and the polyolefin product comprises a poly((C₃-C₄₀)alpha-olefin); or (iii) the at least one polymerizable olefin comprises a combination of ethylene and at least one (C₃-C₄₀)alpha-olefin and the polyolefin product comprises a poly(ethylene-co-(C₃-C₄₀)alpha-olefin) copolymer.

6. The method of any one of claims 1 to 5 wherein: (i) the (B) magnesium halide-supported titanium procatalyst is free of Al (molar ratio Al/Mg = 0); (ii) the (B) magnesium halide-supported titanium procatalyst has molar ratio Al/Mg from > 0 to < 0.05 ; (iii) the magnesium halide of the (B) magnesium halide-supported titanium procatalyst is magnesium chloride; (iv) the magnesium halide of the (B) magnesium halide-supported titanium procatalyst is magnesium bromide; (v) both (i) and (iii); (vi) both (i) and (iv); (vii) both (ii) and (iii); (viii) both (ii) and (iv).

7. The method of any one of claims 1 to 6 wherein: (i) the (D) solid particulate consisting essentially of magnesium halide has a Brunauer, Emmett, Teller (BET) surface area of ≥ 200 square meters per gram (m^2/g) as measured by BET Surface Area Method; or (ii) the (D) solid particulate consisting essentially of magnesium halide has been prepared by contacting a solution of (F) a dialkylmagnesium compound dissolved in the (C) saturated or aromatic hydrocarbon liquid with 1.95 to 2.05 mole equivalents of hydrogen halide to give a suspension of the (D) solid particulate consisting essentially of magnesium halide in the (C) saturated or aromatic hydrocarbon liquid; or (iii) both (i) and (ii).
8. The method of any one of claims 1 to 7 wherein the (C) saturated or aromatic hydrocarbon liquid is: (i) a saturated hydrocarbon liquid; or (ii) an aromatic hydrocarbon liquid; or (iii) a mixture of saturated hydrocarbon and aromatic hydrocarbon liquids.
9. The method of any one of claims 1 to 8 wherein the (A) hydrocarbylaluminoxane is an alkylaluminoxane, a polymethylaluminoxane, an arylaluminoxane, an aralkylaluminoxane, or a combination of any two or more thereof.
10. The method of any one of claims 1 to 9 wherein the unsupported molecular ligand-metal complex procatalyst comprises an unsupported form of: (i) a cyclopentadienyl ligand-metal complex procatalyst; (ii) a cyclopentadienyl-free ligand-metal complex procatalyst; or (iii) both (i) and (ii).
11. A polyolefin product made by the polymerization method of any one of claims 1 to 10.
12. A polymerization method of polymerizing an olefin using an enhanced Ziegler-Natta catalyst and an unsupported or supported molecular catalyst in solution-phase process in a same reactor at the same time, wherein the enhanced Ziegler-Natta catalyst consists essentially of a product of a first activation reaction of (A) a hydrocarbylaluminoxane and (B) a magnesium halide-supported titanium procatalyst in (C) a saturated or aromatic hydrocarbon liquid, wherein the (B) magnesium halide-supported titanium procatalyst has been prepared by contacting (D) a solid particulate consisting essentially of magnesium halide with (E) titanium tetrachloride in the (C) saturated or aromatic hydrocarbon liquid so as to give the (B) magnesium halide-supported titanium procatalyst; and wherein the unsupported or supported molecular catalyst consists essentially of a product of a third

activation reaction of an unsupported or supported molecular ligand-metal complex procatalyst with (A) a hydrocarbylaluminoxane and/or (G) an organoborate or (H) an organoboron; the method comprising simultaneously contacting at least one polymerizable olefin in the solution phase in the reactor with the enhanced Ziegler-Natta catalyst and the unsupported or supported molecular catalyst in a saturated or aromatic hydrocarbon liquid under effective conditions to give a polyolefin product comprising a mixture of a third polyolefin made by a third polymerization reaction catalyzed by the Ziegler-Natta catalyst and a fourth polyolefin made by a fourth polymerization reaction catalyzed by the unsupported or supported molecular catalyst.

13. A catalyst system comprising the enhanced Ziegler-Natta catalyst and unsupported or supported molecular catalyst as described in claim 12.