

1 **SULFUR CONTAINING LUBRICATING OIL**
2 **ADDITIVE SYSTEM PARTICULARLY USEFUL FOR**
3 **NATURAL GAS FUELED ENGINES**
4

5 **BACKGROUND**

6 This invention relates to lubricating oil comprising a combination of a
7 hindered phenol and Group II, III and IV base oil. The lubricating oil of this
8 invention may be used in any manner, however its enhanced properties make
9 it particularly applicable for use in engines fueled by natural gas.

10 Natural gas has a higher specific heat content than liquid hydrocarbon
11 fuels and therefore it burns hotter than liquid hydrocarbon fuels under typical
12 conditions. In addition, since it is already a gas, natural gas does not cool
13 intake air by evaporation as liquid hydrocarbon fuel droplets do. Furthermore,
14 many natural gas fueled engines are run either at or near stoichiometric
15 conditions, at which less excess air is available to dilute and cool combustion
16 gases. As a result, natural gas fueled engines generate higher combustion
17 gas temperatures than engines burning liquid hydrocarbon fuels. Since the
18 rate of formation of NO_x increases exponentially with temperature, natural gas
19 fueled engines may generate NO_x concentrations high enough to cause
20 severe nitration of lubricating oil.

21 In most cases, natural gas fueled engines are used continuously at
22 70 to 100% load, whereas an engine operating in vehicular service may only
23 spend 50% of its time at full load. Lubricating oil drain intervals may vary in
24 vehicular service, but are typically shorter than those for natural gas fueled
25 engines.

26 It is important to ensure the reliability of natural gas fueled engines
27 because natural gas fueled engines may be located in remote areas where
28 service is not readily available. Lubricating oil used in natural gas engines
29 therefore requires high resistance to oxidation and nitration.

30 Good valve wear control is important for keeping engine operating
31 costs down and may be achieved by providing the proper amount and
32 composition of ash. Minimizing combustion chamber deposits and spark plug
33 fouling are also considerations in setting the ash content and composition in
34 these oils. Lubricating oil ash levels are limited, so detergents must be

carefully selected to minimize piston deposits and ring sticking. Good wear protection is required to prevent scuffing and corrosion.


If lubricating oils for natural gas fueled engines are not formulated to handle typical environments for those engines, the lubricating oil will deteriorate rapidly during use. This deterioration will typically cause the lubricating oil to thicken, which results in engine sludge, piston deposits, oil filter plugging, and in severe cases, accelerated ring and liner wear.

The general industry approach to reduce deterioration of lubricating oil and the resultant engine sludge, piston deposits, oil filter plugging and accelerated ring and liner wear is to add antioxidants such as hindered phenols as well as diphenyl amines and sulfurized compounds. Increasing the amount of these antioxidants in lubricating oil is increasingly effective to avoid lubricating oil deterioration. But at some point the solubility limit of the additional antioxidant reaches maximum effectiveness and at times further addition of antioxidant may even detrimentally affect piston deposit control.

While it is no surprise that increasing the amount of antioxidant is effective in increasing the life of lubricating oil, this invention provides a method to increase the life of lubricating oil with out necessarily increasing the amount of antioxidant.

SUMMARY

The lubricating oil of this invention may comprise a minor amount of one or more hindered phenols of the general formula:



wherein R is a C₇-C₉ alkyl group

and a major amount of at least one of Group II, III and IV base oils. More specifically, the lubricating oil of this invention may comprise about

1 0.20 wt. % to about 3 wt. % of one or more hindered phenols having this
2 general formula. Liquid hindered phenols are preferred. Unless otherwise
3 specified the term "wt. %" as used herein means wt. % of lubricating oil. One
4 embodiment of this invention comprises a lubricating oil of Claim 1 having a
5 total base number of about 2.15 milligrams Potassium Hydroxide per gram of
6 sample (mg KOH/gr) to about 8.88 mg KOH/gr as determined by
7 ASTM D 2896. One embodiment of this invention comprises a lubricating oil
8 having a total ash content of about 0.10 wt. % to about 1.50 wt. % as
9 determined by ASTM D874. Lubricating oil of this invention may have less
10 than 4000 ppm sulfur. One embodiment of this invention comprises combining
11 the hindered phenol of the invention with the base oil in any order and mixing.
12 Another embodiment of this invention comprises a method of lubricating
13 engines comprising contacting one or more engines with the lubricating oil of
14 this invention. Lubricating oil of this invention may comprise a major amount
15 of at least one of Group II, III and IV base oil and a minor amount of
16 2-(4-hydroxy-3, 5-di-t-butyl benzyl thiol) acetate of formula (1), above, also
17 known as acetic acid, [[[3,5-bis(1,1-dimethyl ethyl)-4-
18 hydroxyphenyl]methyl]thio]-, C₇-C₉ alkyl ester. Lubricating oil of this invention
19 may comprise about 0.20 wt. % to about 3 wt. 2-(4-hydroxy-3, 5-di-t-butyl
20 benzyl thiol) acetate, preferably about 0.6 wt % to about 2.5 wt. %. 2-(4-
21 hydroxy-3, 5-di-t-butyl benzyl thiol) acetate may be liquid. One embodiment of
22 this invention may comprise an additive formulation comprising 2-(4-hydroxy-
23 3, 5-di-t-butyl benzyl thiol) acetate; one or more dispersants; one or more
24 wear inhibitors; and one or more detergents. Lubricating oil of this invention
25 may comprise about 1 wt. % to about 8 wt. % of one or more dispersants,
26 about 1 wt. % to about 8.5 wt. % of one or more detergents, about 0.2 wt. %
27 to about 1.5 wt. % of one or more wear inhibitors, about 0.5 wt. % to about 3
28 wt. % 2-(4-hydroxy-3, 5-di-t-butyl benzyl thiol) acetate, and about 40 wt. % to
29 about 97 wt. % of at least one of Group II, III and IV base oil or preferably
30 about 80 wt. % to about 97 wt. % of at least one of Group II, III and IV base oil
31 or more preferably about 60 wt. % to about 97 wt. % of at least one of
32 Group II, III and IV base oil. Lubricating oil of this invention may comprise
33 about 1.25 wt. % to about 6 wt. % of one or more dispersants; about 2 wt. % to

1 about 6 wt. % of one or more detergents; about 0.3 wt. % to about 0.8 wt. % of
2 one or more wear inhibitors, about 0.6 to about 2.5 wt. % 2-(4-hydroxy-3, 5-di-t-
3 butyl benzyl thiol) acetate and about 40 wt. % to about 97 wt. % of at least
4 one of Group II, III and IV base oil or preferably about 80 wt. % to about 97 wt.
5 % of at least one of Group II, III and IV base oil or more preferably about 60
6 wt. % to about 97 wt. % of at least one of Group II, III and IV base oil.

7 8 **DETAILED DESCRIPTION OF THE INVENTION**

9 This invention provides lubricating oil that may be used in any engine,
10 but that has exhibited a surprisingly long life when tested in a natural gas fueled
11 engine.

12 The lubricating oil of this invention may comprise one or more of the
13 hindered phenols described herein and Group II, III and IV base oils. A
14 preferred lubricating oil of this invention comprises a major amount of one or
15 more base oils from Groups II through IV and a minor amount of the hindered
16 phenols described herein. The term "major amount" when used herein means
17 more than 40 wt. %. The term "minor amount" when used herein means less
18 than 20 wt. %.

19 One embodiment of this invention comprises an additive formulation
20 comprising one or more of the hindered phenols described herein, one or more
21 dispersants, one or more detergents and one or more wear inhibitors.

22 A preferred lubricating oil of this invention may comprise a major amount
23 of base oils from Group II through Group IV, a minor amount of one or more of
24 the additive formulations comprising the hindered phenols described herein,
25 one or more detergents, one or more dispersants and one or more wear
26 inhibitors.

27 Another embodiment of this invention comprises lubricating oils
28 comprising additive formulations comprising the hindered phenols described
29 herein.

30 Preferred lubricating oil of this invention may comprise the hindered
31 phenols described herein and Group II through IV base oils in a formulation
32 that has about 0.10 wt. % to about 1.50 wt. % ash in the finished lubricating oil
33 and more preferably about 0.3 wt. % ash to about 0.95 wt. % ash in the finished

1 lubricating oil as determined by ASTM D874. When ash contents are discussed
2 herein, the ash contents were determined by ASTM D874.

3 One embodiment of the lubricating oil of this invention may have a
4 Total Base Number (TBN) of about 2.15 milligrams Potassium Hydroxide
5 per gram of sample (mg KOH/gr) to about 8.88 mg KOH/gr. A more preferable
6 embodiment would have a TBN from about 3 mg KOH/gr to about
7 8 mg KOH/gr. Unless otherwise specified, TBNs, as used herein, are
8 determined by using the method ASTM D2896.

9 The lubricating oil of this invention may have a sulfur content of less than
10 4000 ppm or 0.4 wt. %.

11 Another embodiment of this invention comprises methods of making the
12 lubricating oils of this invention or the additive formulations of this invention by
13 combining the components with agitation until all components are mixed. The
14 ingredients may be combined in any order and at a temperature sufficient to
15 blend the components but not high enough to degrade the components. A
16 temperature of about 120 degrees F. to about 160 degrees F. may be used.
17 Heating may occur at any time during the process.

18 Another embodiment of this invention comprises the method of
19 lubricating one or more engines by contacting one or more of the lubricating oils
20 of this invention with one or more engines.

21 Another embodiment of this invention comprises the method of
22 lubricating one or more natural gas engines by contacting one or more of the
23 lubricating oils of this invention with one or more natural gas engines.

24 Another embodiment of this invention comprises the method of
25 lubricating one or more engines by lubricating one or more of the lubricating oils
26 of this invention with one or more engines.

27 Another embodiment of this invention comprises the method of
28 lubricating one or more natural gas engines by lubricating one or more of the
29 lubricating oils of this invention with one or more natural gas engines.

30 The lubricating oil of this invention has shown a surprisingly long life in a
31 natural gas fueled engine when the hindered phenols described herein are
32 used in an additive formulation with Group II, III and IV base oils over that seen
33 when the hindered phenols described herein were used in a similar additive

1 formulation with Group I base oils or when other types of hindered phenols
2 were used in a similar additive formulation with Group I or Group II base oils.
3 The surprising long life exhibited by the lubricating oil of this invention may be
4 the result of a synergistic effect of the Group II, III and IV base oils with the
5 hindered phenols described herein and/or a synergistic effect of the Group II, III
6 and IV base oils and the additive formulation comprising the hindered phenols
7 described herein.

8 9 **I. BASE OIL**

10 Base Oil as used herein is defined as a base stock or blend of base
11 stocks. Base Stock as used herein is defined as a lubricant component that is
12 produced by a single manufacturer to the same specifications (independent of
13 feed source or manufacturers location): that meets the same manufacturer's
14 specification; and that is identified by a unique formula, product identification
15 number, or both. Base stocks may be manufactured using a variety of
16 different processes including but not limited to distillation, solvent refining,
17 hydrogen processing, oligomerization, esterification, and rerefining. Rerefined
18 stock shall be substantially free from materials introduced through
19 manufacturing, contamination, or previous use. The base oil of this invention
20 may be any natural or synthetic lubricating base oil fraction particularly those
21 having a kinematic viscosity at 100 degrees Centigrade (C) and about
22 5 centistokes (cSt) to about 20 cSt, preferably about 7 cSt to about
23 16 cSt, more preferably about 9 cSt to about 15 cSt. Hydrocarbon synthetic
24 oils may include, for example, oils prepared from the polymerization of
25 ethylene, i.e., polyalphaolefin or PAO, or from hydrocarbon synthesis
26 procedures using carbon monoxide and hydrogen gases such as in a
27 Fisher-Tropsch process. A preferred base oil is one that comprises little, if
28 any, heavy fraction; e.g., little, if any, lube oil fraction of viscosity 20 cSt or
29 higher at 100 degrees C.

30 The base oil may be derived from natural lubricating oils, synthetic
31 lubricating oils or mixtures thereof. Suitable base oil includes base stocks
32 obtained by isomerization of synthetic wax and slack wax, as well as
33 hydrocrackate base stocks produced by hydrocracking (rather than solvent

extracting) the aromatic and polar components of the crude. Suitable base oils include those in API categories II, III, IV and V. Saturates levels and viscosity indices for Group I, II and III base oils are listed in Table 1. Group IV base oils are polyalphaolefins (PAO). Group V base oils include all other base oils not included in Group I, II, III, or IV. Suitable base oils for use in this invention include those in API categories II, III and IV as defined in API Publication 1509, 14th Edition, Addendum I, December 1998. A summary of the characteristics of Group I, II, and III base oil is presented in Table I. Though Group II, III and IV base oils are preferred for use in this invention, these preferred Group II, III and IV base oils may be prepared by combining one or more of Group I, II, III, IV and V base stocks or base oils.

TABLE 1
Saturates, Sulfur and
Viscosity Index of Group I, II and III Base Stocks

Group	Saturates (As determined by ASTM D 2007) Sulfur (As determined by ASTM D 2270)	Viscosity Index (As determined by ASTM D 4294, ASTM D 4297 or ASTM D 3120)
I	Less than 90 % saturates and/or Greater than to 0.03 % sulfur	Greater than or equal to 80 and less than 120
II	Greater than or equal to 90 % saturates and less than or equal to 0.03 % sulfur	Greater than or equal to 80 and less than 120
III	Greater than or equal to 90 % saturates and less than or equal to 0.03% sulfur	Greater than or equal to 120

Natural lubricating oils may include animal oils, vegetable oils (e.g., rapeseed oils, castor oils and lard oil), petroleum oils, mineral oils, and oils derived from coal or shale.

Synthetic oils may include hydrocarbon oils and halo-substituted hydrocarbon oils such as polymerized and inter-polymerized olefins, alkylbenzenes, polyphenyls, alkylated diphenyl ethers, alkylated diphenyl sulfides, as well as their derivatives, analogues and homologues thereof, and the like. Synthetic lubricating oils also include alkylene oxide polymers, interpolymers, copolymers and derivatives thereof wherein the terminal hydroxyl groups have been modified by esterification, etherification, etc.

1 Another suitable class of synthetic lubricating oils comprises the esters of
2 dicarboxylic acids with a variety of alcohols. Esters useful as synthetic oils
3 also include those made from C₅ to C₁₂ monocarboxylic acids and polyols and
4 polyol ethers. Tri-alkyl phosphate ester oils such as those exemplified by
5 tri-n-butyl phosphate and tri-iso-butyl phosphate are also suitable for use as
6 base oils.

7 Silicon-based oils (such as the polyakyl-, polyaryl-, polyalkoxy-, or
8 polyaryloxy-siloxane oils and silicate oils) comprise another useful class of
9 synthetic lubricating oils. Other synthetic lubricating oils include liquid esters
10 of phosphorus-containing acids, polymeric tetrahydrofurans, polyalphaolefins,
11 and the like.

12 The base oil may be derived from unrefined, refined, rerefined oils, or
13 mixtures thereof. Unrefined oils are obtained directly from a natural source or
14 synthetic source (e.g., coal, shale, or tar sand bitumen) without further
15 purification or treatment. Examples of unrefined oils include a shale oil
16 obtained directly from a retorting operation, a petroleum oil obtained directly
17 from distillation, or an ester oil obtained directly from an esterification process,
18 each of which may then be used without further treatment. Refined oils are
19 similar to the unrefined oils except that refined oils have been treated in one
20 or more purification steps to improve one or more properties. Suitable
21 purification techniques include distillation, hydrocracking, hydrotreating,
22 dewaxing, solvent extraction, acid or base extraction, filtration, and
23 percolation, all of which are known to those skilled in the art. Rerefined oils
24 are obtained by treating used oils in processes similar to those used to obtain
25 the refined oils. These rerefined oils are also known as reclaimed or
26 reprocessed oils and often are additionally processed by techniques for
27 removal of spent additives and oil breakdown products.

28 Base oil derived from the hydroisomerization of wax may also be used,
29 either alone or in combination with the aforesaid natural and/or synthetic base
30 oil. Such wax isomerase oil is produced by the hydroisomerization of natural or
31 synthetic waxes or mixtures thereof over a hydroisomerization catalyst.

32 It is preferred to use a major amount of base oil in the lubricating oil of
33 this invention. A major amount of base oil as defined herein comprises

1 40 wt. % or more. Preferred amounts of base oil comprise about 40 wt. % to
2 about 97 wt. % of at least one of Group II, III and IV base oil or preferably about
3 80 wt. % to about 97 wt. % of at least one of Group II, III and IV base oil or
4 more preferably about 60 wt. % to about 97 wt. % of at least one of
5 Group II, III and IV base oil. (When wt. % is used herein, it is referring to
6 wt. % of the lubricating oil unless otherwise specified.) A more preferred
7 embodiment of this invention may comprise an amount of base oil that
8 comprises about 85 wt. % to about 95 wt. % of the lubricating oil.

9 A preferred lubricating oil of this invention may comprise Group II base
10 oil. Preferred base oils may comprise base oil that is commercially available
11 from Chevron Corporation in San Ramon, California,
12 Pennzoil Quaker State Company in Houston, Texas, Conoco in Houston,
13 Texas, Motiva Enterprises in Houston, Texas, ExxonMobil in Irving, Texas
14 and Petro Canada Lubricants in Mississauga, Ontario Canada. Other
15 base oils useful in this invention may be commercially available throughout
16 the world from other base oil suppliers.

17 18 **II. ADDITIVE FORMULATION**

19 When incorporated in lubricating oil, the additive formulation of this
20 invention provides enhanced oxidation inhibition, nitration inhibition, total base
21 retention, reduction in acid formation and reduction percent viscosity increase
22 of lubricating oil.

23 One embodiment of the additive formulation of this invention may
24 comprise of one or more dispersants, one or more detergents, one or more
25 wear inhibitors and one or more hindered phenols described herein.


26 The lubricating oil of this invention may comprise an additive formulation
27 that provides the lubricating oil with about 1 wt. % to about 8 wt. % of one or
28 more dispersants, about 1 wt. % to about 8.5 wt. % of one or more detergents,
29 about 0.2 wt. % to about 1.5 wt. % of one or more wear inhibitors and about
30 0.2 wt. % to about 3 wt. % and one or more hindered phenols described
31 herein. The additive formulation of this invention may also comprise other
32 additives traditionally used in the lubricating oil industry.

Another embodiment of a lubricating oil of this invention may comprise an additive formulation that provides the lubricating oil with about 1.25 wt. % to about 6 wt. % of one or more dispersants, about 2 wt. % to about 6 wt. % of one or more detergents, about 0.3 wt. % to about 0.8 wt. % of one or more wear inhibitors and about 0.6 wt. % to about 2.5 wt. % of one or more hindered phenols described herein. These components make up one embodiment of the additive formulation of this invention. The additive formulation of this invention may also comprise other additives traditionally used in the lubricating oil industry.

The additive formulation of this invention may comprise diluent oil. It is known in the art to add diluent oil to additive formulations and this is called "trimming" the additive formulation. A preferred embodiment may be trimmed with any diluent oil typically used in the industry. This diluent oil may be a Group I or above oil. A preferred amount of diluent oil may comprise about 4.00 wt. %.

A. Hindered Phenol Antioxidant

One embodiment of this invention comprises one or more hindered phenols having the general formula:



wherein R is a C₇-C₉ alkyl group.

The lubricating oil of this invention may comprise the additive formulation of this invention that provides the lubricating oil with about 0.2 wt. % to about 3 wt. % of one or more hindered phenols having the general structural formula (1). Preferred lubricating oils of this invention may comprise an additive formulation that provides the lubricating oil with about 0.6 wt. % to about 2.5 wt. % of one or more hindered phenols having the general structural formula (1).

Another embodiment of the lubricating oil of this invention may comprise an additive formulation that provides the lubricating oil containing 2-(4-hydroxy-3, 5-di-t-butyl benzyl thiol) acetate having the formula (1) above. The hindered phenol, 2-(4-hydroxy-3, 5-di-t-butyl benzyl thiol) acetate, also known as acetic acid, [[[3,5-bis(1,1-dimethylethyl)-4-hydroxyphenyl]methyl]thio]-, C₇-C₉ alkyl esters may be available commercially from Ciba Specialty Chemicals at 540 White Plains Road, Tarrytown, NY 10591 as IRGANOX L118®. IRGANOX L 118® is a liquid high molecular weight phenolic antioxidant of formula (1) for use in lubricating oils.

Liquid hindered phenol is preferred.

Lubricating oil of this invention may comprise greater than about 0.2 wt. % to more than about 3 wt. % 2-(4-hydroxy-3, 5-di-t-butyl benzyl thiol) acetate. Preferred lubricating oils of this invention comprise about 0.6 wt. % to about 2.5 wt. % 2-(4-hydroxy-3, 5-di-t-butyl benzyl thiol) acetate.

B. Detergent

Any detergents commonly used in lubricating oils may be used in this invention. These detergents may or may not be overbased detergents or they may be low, neutral, medium, or high overbased detergents. For example, detergents of this invention may comprise sulfonates, salicylates and phenates. Metal sulfonates, salicylates and phenates are preferred. When the term metal is used with respect to sulfonates, salicylates and phenates herein, it refers to calcium, magnesium, lithium, magnesium, potassium and barium.

The detergent may be incorporated into the lubricating oil of this invention in an amount of about 1.0 wt. % to about 8.5 wt. %, preferably from about 2 wt. % to about 6 wt. %.

C. Dispersant

A preferred embodiment of the lubricating oil of this invention may comprise one or more nitrogen containing ashless dispersants of the type generally represented by succinimides (e.g., polyisobutylene succinic acid/anhydride (PIBSA)-polyamine having a PIBSA molecular weight of about 700 to 2500). The dispersants may or may not be borated or non-borated.

1 The dispersant may be incorporated into the lubricating oil of this invention in
2 an amount of about 1 wt. % to about 8 wt. %, more preferably in the amount
3 of about 1.5 wt. % to about 6 wt. %.

4 Preferred dispersants for this invention comprise one or more ashless
5 dispersants having an average molecular weight (mw) of about 1000 to about
6 5000. Dispersants prepared from polyisobutylene (PIB) having a mw of about
7 1000 to about 5000 are such preferred dispersants.

8 A preferred dispersant of this invention may be one or more
9 succinimides. The term "succinimide" is understood in the art to include many
10 of the amide, imide, etc. species that are also formed by the reaction of a
11 succinic anhydride with an amine and is so used herein. The predominant
12 product, however, is succinimide and this term has been generally accepted
13 as meaning the product of a reaction of an alkenyl- or alkyl-substituted
14 succinic acid or anhydride with a polyamine. Alkenyl or alkyl succinimides are
15 disclosed in numerous references and are well known in the art. Certain
16 fundamental types of succinimides and related materials encompassed by the
17 term of art "succinimide" are taught in U.S. Pat. Nos. 2,992,708; 3,018,250;
18 3,018,291; 3,024,237; 3,100,673; 3,172,892; 3,219,666; 3,272,746;
19 3,361,673; 3,381,022; 3,912,764; 4,234,435; 4,612,132; 4,747,965;
20 5,112,507; 5,241,003; 5,266,186; 5,286,799; 5,319,030; 5,334,321;
21 5,356,552; 5,716,912, the disclosures of which are hereby incorporated by
22 reference.

23 This invention may comprise one or more succinimides, which may be
24 either a mono or bis-succinimide. This invention may comprise a lubricating oil
25 involving one or more succinimide dispersants that have or have not been
26 post treated.

27

28 **D. Wear inhibitor**

29 Wear inhibitors such as metal dithiophosphates (e.g., zinc dialkyl
30 dithiophosphate, ZDDP), metal dithiocarbamates, metal xanthates or
31 tricresylphosphates may be included. Wear inhibitors may be present in the
32 amount of about 0.24 wt. % to 1.5 wt. %, more preferably in the amount of

1 about 0.3 wt. % to about 0.80 wt. %, most preferably in the amount of about
2 0.35 wt. % to about 0.75 wt. % of the lubricating oil.

3 A preferred wear inhibitor is zinc dithiophosphate. Other wear inhibitors
4 that may be included are zinc dialkyldithiophosphate and/or zinc
5 diaryldithiophosphate (ZnDTP). The wear inhibitor may be incorporated into
6 the lubricating oil of this invention in an amount of about 0.2 wt. % to
7 1.5 wt. %, more preferably in the amount of about 0.3 wt. % to about
8 0.8 wt. % of the lubricating oil. These values may include a small amount of
9 hydrocarbon oil that was used in preparing zinc dithiophosphate. Preferred
10 ranges of phosphorus in the finished lubricating oil are about 0.01 wt. % to
11 about 0.11 wt. %, more preferably about 0.02 wt. % to about 0.07 wt. %.

12 The alkyl group in the zinc dialkyldithiophosphate may be, for example,
13 a straight or branched primary, secondary or tertiary alkyl group of about
14 2 to about 18 carbon atoms. Examples of the alkyl groups include ethyl,
15 propyl, iso-propyl, butyl, pentyl, hexyl, heptyl, octyl, decyl, dodecyl, and
16 octadecyl.

17 The alkylaryl group of the zinc dialkylaryldithiophosphate is, for
18 example, a phenyl group having an alkyl group of about 2 to about
19 18 carbon atoms, such as butylphenyl group, nonylphenyl group, and
20 dodecylphenyl group.

21

22 **III. OTHER ADDITIVE COMPONENTS**

23 The following additive components are examples of some of the
24 components that may be favorably employed in this invention. These
25 examples of additives are provided to illustrate this invention, but they are not
26 intended to limit it:


27

28 **A. Antioxidants**

29 If desired, additional antioxidants may be used. Other antioxidants may
30 reduce the tendency of mineral oils to deteriorate in service. In addition to the
31 antioxidant systems of this invention, the additive formulation may also
32 include but is not limited to such antioxidants as phenol type (phenolic)
33 oxidation inhibitors, such as 4,4'-methylene-bis(2,6-di-tert-butylphenol),

1 4,4'-bis(2,6-di-tert-butylphenol), 4,4'-bis(2-methyl-6-tert-butylphenol),
 2 2,2'-methylene-bis(4-methyl-6-tert-butylphenol),
 3 4,4'-butylidene-bis(3-methyl-6-tert-butylphenol),
 4 4,4'-isopropylidene-bis(2,6-di-tert-butylphenol),
 5 2,2'-methylene-bis(4-methyl-6-nonylphenol),
 6 2,2'-isobutylidene-bis(4,6-dimethylphenol),
 7 2,2'-methylene-bis(4-methyl-6-cyclohexylphenol),
 8 2,6-di-tert-butyl-4-methylphenol, 2,6-di-tert-butyl-4-ethylphenol,
 9 2,4-dimethyl-6-tert-butyl-phenol, 2,6-di-tert-l-dimethylamino-p-cresol,
 10 2,6-di-tert-4-(N,N'-dimethylaminomethylphenol),
 11 4,4'-thiobis(2-methyl-6-tert-butylphenol),
 12 2,2'-thiobis(4-methyl-6-tert-butylphenol),
 13 bis(3-methyl-4-hydroxy-5-tert-butylbenzyl)-sulfide, and
 14 bis(3,5-di-tert-butyl-4-hydroxybenzyl). Diphenylamine-type oxidation inhibitors
 15 include, but are not limited to, alkylated diphenylamine,
 16 phenyl-.alpha.-naphthylamine, and alkylated-.alpha.-naphthylamine. Other
 17 types of oxidation inhibitors include metal dithiocarbamate (e.g., zinc
 18 dithiocarbamate), and methylenebis (dibutyldithiocarbamate).

19 One embodiment of this invention comprises one or more hindered
 20 phenols having the general formula:
 21



(1)

22
 23
 24 wherein R is a C₇-C₉ alkyl group
 25 and no other antioxidant additive. Another embodiment of this invention
 26 comprises 2-(4-hydroxy-3, 5-di-t-butyl benzyl thiol) acetate of formula (1)
 27 commercially available from Ciba Specialty Chemicals at 540 White Plains
 28 Road, Tarrytown, NY 10591 as IRGANOX L118® and no other antioxidant.
 29
 30

1 **B. Wear Inhibitors**

2 In addition to the wear inhibitors mentioned in the additive formulation
3 section, other traditional wear inhibitors may be used. As their name implies,
4 these agents reduce wear of moving metallic parts. Examples of such agents
5 include, but are not limited to, phosphates, phosphites, carbamates, esters,
6 sulfur containing compounds, and molybdenum complexes.

7
8 **C. Rust Inhibitors (Anti-Rust Agents)**

9 Applicable rust inhibitors include:

- 10 1. Nonionic polyoxyethylene surface active agents:
11 polyoxyethylene lauryl ether, polyoxyethylene higher alcohol ether,
12 polyoxyethylene nonyl phenyl ether, polyoxyethylene octyl phenyl ether,
13 polyoxyethylene octyl stearyl ether, polyoxyethylene oleyl ether,
14 polyoxyethylene sorbitol monostearate, polyoxyethylene sorbitol mono-oleate,
15 and polyethylene glycol mono-oleate; and
16 2. Other compounds: stearic acid and other fatty acids,
17 dicarboxylic acids, metal soaps, fatty acid amine salts, metal salts of heavy
18 sulfonic acid, partial carboxylic acid ester of polyhydric alcohol, and
19 phosphoric ester.

20

21 **D. Demulsifiers**

22 Demulsifiers that may be used include addition products of alkylphenol
23 and ethylene oxide, polyoxyethylene alkyl ether, and polyoxyethylene sorbitan
24 ester.

25

26 **E. Extreme Pressure Agents (EP Agents)**

27 EP Agents that may be used include Zinc dialkyldithiophosphate
28 (primary alkyl, secondary alkyl, and aryl type), sulfurized oils, diphenyl sulfide,
29 methyl trichlorostearate, chlorinated naphthalene, fluoroalkylpolysiloxane, and
30 lead naphthenate.

31

32 **F. Friction Modifiers**

1 Fatty alcohol, fatty acid, amine, borated ester, and other esters.

2

3 **G. Multifunctional Additives**

4 Sulfurized oxymolybdenum dithiocarbamate, sulfurized
5 oxymolybdenum organo phosphorodithioate, oxymolybdenum monoglyceride,
6 oxymolybdenum diethylate amide, amine-molybdenum complex compound,
7 and sulfur-containing molybdenum complex compound may be used.

8

9 **H. Viscosity Index Improvers**

10 Polymethacrylate type polymers, ethylene-propylene copolymers,
11 styrene-isoprene copolymers, hydrated styrene-isoprene copolymers,
12 polyisobutylene, and dispersant type viscosity index improvers may be used.

13

14 **I. Pour Point Depressants**

15 Polymethyl methacrylate may be used.

16

17 **J. Foam Inhibitors**

18 Alkyl methacrylate polymers and dimethyl silicone polymers may be
19 used.

20

21 **IV. LUBRICATING OIL FOR NATURAL GAS FUELED ENGINES**

22 There is a difference in the lubricating oil requirements for natural gas
23 fueled engines and engines that are fueled by liquid hydrocarbon fuels. The
24 combustion of liquid hydrocarbon fuels such as diesel fuel often results in a
25 small amount of incomplete combustion (e.g., exhaust particulates). In a liquid
26 hydrocarbon fueled engine, these incombustibles provide a small but critical
27 degree of lubrication to the exhaust valve/seat interface, thereby ensuring the
28 durability of both cylinder heads and valves. The combustion of natural gas
29 fuel is often very complete, with virtually no incombustible materials.

30 Therefore, the durability of the cylinder head and valve is controlled by the
31 ash content and other properties of the lubricating oil and its consumption
32 rate. There are no incombustible materials to aid in lubrication to the exhaust
33 valve/seat interface in a natural gas fueled engine. Natural gas fueled engines

1 burn fuel that is introduced to the combustion chamber in the gaseous phase.
 2 This has a significant affect on the intake and exhaust valves because there is
 3 no fuel-derived lubricant for the valves like liquid droplets or soot.
 4 Consequently, gas engines are solely dependent on the lubricant ash to
 5 provide lubricant between the hot valve face and its mating seat. Too little ash
 6 or the wrong type can accelerate valve and seat wear, while too much ash
 7 may lead to valve guttering and subsequent valve torching. Too much ash can
 8 also lead to detonation from combustion chamber deposits. Consequently,
 9 gas engine builders frequently specify a narrow ash range that they have
 10 learned provides the optimum performance. Since most gas is low in sulfur,
 11 excess ash is generally not needed to address alkalinity requirements, and
 12 ash levels are largely optimized around the needs of the valves. There may
 13 be exceptions to this in cases where sour gas or landfill gas is used.

14 Natural gas fueled engine lubricating oils are classified according to
 15 their ash content. The lubricant ash acts as a solid lubricant to protect the
 16 valve/seat interface in place of naturally occurring exhaust particles in a
 17 hydrocarbon fueled engine. The oil industry has accepted guidelines that
 18 classify natural gas fueled engine lubricating oil according to their ash level.
 19 The classifications of natural gas fueled engine lubricating oil according to
 20 their ash levels are presented in Table 2.

21
22
23
24

TABLE 2
Classifications of Lubricating Oils for
Natural Gas Fueled Engines According To Ash Levels

<u>Ash Designation</u>	<u>Sulfated Ash Level</u> (wt. %. Determined by ASTM D874)
Ashless	0 < Ash < 0.15
Low Ash	0.15 < Ash < 0.6
Medium Ash	0.6 < Ash < 1.0
High Ash	Ash > 1.0

25
26
27
28
29
30

The ash level of lubricating oil is often determined by its formulation components. Metal-containing detergents (e.g., barium, calcium) and metallic-containing wear inhibitors contribute to the ash level of lubricating oils. For correct engine operation, gas engine manufacturers define lubricating oil ash requirements as part of the lubricating oil specifications. For example,

1 manufacturers of 2-cycle engines often require natural gas engine lubricating
2 oil to be Ashless to minimize the extent of harmful deposits that form on the
3 piston and combustion chamber area. Manufacturers of 4-cycle engines often
4 require natural gas engine lubricating oils to be Low, Medium or High Ash
5 levels, refer to Table 2, to provide the correct balance of engine cleanliness
6 and durability of the cylinder head and valves. Running the engine with
7 lubricating oil with too low an ash level will likely result in shortened life for the
8 valves or cylinder head. Running the engine with lubricating oil having too
9 high an ash level will likely cause excessive deposits in the combustion
10 chamber and upper piston area.

11 The degree of nitration of the lubricating oil may vary significantly
12 depending on the engine design and operating conditions. Lean burn engines
13 produce less NO_x than their stoichiometric counterparts, so they tend to
14 nitrate the oils less. Some operators may richen the air/fuel mixture on natural
15 gas fueled engines to increase power output and consequently increase oil
16 nitration levels. Lubricating oils with good nitration resistance are required in
17 most natural gas engine installations because the lubricating oil may be used
18 to lubricate a number of engines including stoichiometric and lean-burn
19 models.

20 This invention will be further illustrated by the following examples that set
21 forth particularly preferred embodiments. While the examples are provided to
22 illustrate this invention, they are not intended to limit it.

23

24

EXAMPLES

25 The Examples describe experiments performed using Samples A
26 through C. Multiple experiments were performed in each example using a
27 variety of detergents such as, but not limited to, sulfonate, phenate and
28 salicylate detergents; succinimide dispersants; and zinc dithiophosphate wear
29 inhibitors. The examples are explained using the terms detergent, dispersant
30 and wear inhibitor because no significant difference was found when these
31 components were varied.

32 Sample A was prepared by combining about 2 wt. % 2-(4-hydroxy-3,
33 5-di-t-butyl benzyl thiol) acetate, about 3 wt. % dispersant, about

1 3.4 wt. % detergent, about 0.38 wt. % wear inhibitor, 5 ppm foam inhibitor and
2 Group II base oil. Sample A was prepared by combining the components at
3 140 degrees Fahrenheit (F) (60 degrees Celsius) with agitation until all
4 components were mixed.

5 Sample B was prepared by combining about 2 wt. % 2-(4-hydroxy-3,
6 5-di-t-butyl benzyl thiol) acetate, about 3 wt. % dispersant, about
7 3.4 wt. % detergent, about 0.38 wt. % wear inhibitor, 5 ppm foam inhibitor and
8 Group I base oil. Sample B was prepared by combining the components at
9 140 degrees F (60 degrees Celsius) with agitation until all components were
10 mixed.

11 Sample C was prepared by using OLOA 1255, commercially available
12 from Chevron Oronite Company in Houston, Texas. The OLOA 1255 was
13 mixed with Group I base oil under typical blending conditions of about
14 140 degrees F (60 degrees Celsius) with agitation until all components were
15 thoroughly mixed. As explained in of U.S. Pat. No. 5,726,133 lubricating oil
16 made by combining OLOA 1255 is one of the most widely sold gas engine oil
17 additive formulations and represents, therefore, a "benchmark standard"
18 against which other formulations useful as engine oils may be measured.

19

20

EXAMPLE 1

21

The Oxidation-Nitration And Viscosity Increase Resistance Test

22

23

24

25 The Oxidation-Nitration and Viscosity Increase Resistance bench test
26 demonstrates the capacity of lubricating oil to resist oxidation, nitration and
27 viscosity increase. This test is a tool to help determine the performance of oils
28 as they relate to the actual service of lubricating engines that use natural gas as
29 a fuel source. The level of oxidation and nitration of oil, may also be compared
30 by monitoring the viscosity increase of the oil. The lower the values for
31 oxidation, nitration and viscosity increase at the end the test, the more superior
32 the product's performance. The Oxidation-Nitration and Viscosity Increase
33 Resistance bench test was designed to simulate Caterpillar 3500 series engine
34 conditions as related to actual field performance of the Caterpillar 3516 model.
Oxidation-Nitration and Viscosity Increase Resistance tests were performed on

1 Samples A, B, C, and D. The samples were placed in a heated glassware bath
2 and subjected to calibrated levels of nitrous oxide gas over a specific period of
3 time. The tests were run on each sample in duplicate and the results are an
4 average of the two runs. The samples were evaluated using differential infra
5 red spectroscopy before placing them in the heated glassware bath to
6 determine a base line for each sample. The samples were re-evaluated at the
7 end of testing period. The differential between the base line data, absorbance
8 units at 5.8 and 6.1 microns, and the data taken at the end of test cycle
9 provides an indication of the oxidation-nitration resistance of the samples.

10 Differential infra red spectroscopy measures the amount of light that is
11 absorbed by an oil sample and provides a unit of measure called an
12 absorbance unit. DIR (Differential Infrared) spectra was determined by
13 subtracting the fresh oil spectra from the used oil spectra to observe changes
14 that have occurred due to oxidation, nitration, fuel dilution, soot accumulation,
15 and or contamination. Typically a 0.1 millimeter (mm) cell is used, however an
16 ATR crystal setup may be used after determining its associated path length. If
17 the instrument does not have software that determines path length, the path
18 length may be back calculated by measuring oxidation with a calibrated
19 0.1 mm cell. The variation between ATR and vertical cell measurements is
20 minimal if restricted to the narrow area of oxidation and nitration
21 (~ 1725 to 1630 cm^{-1}).


22 DIR Oxidation was measured from peak maximum at $\sim 1715 \pm 5\text{ cm}^{-1}$ to
23 the spectra baseline (in units of absorbance).

24 DIR Nitration was measured from peak maximum at $\sim 1630 \pm 1\text{ cm}^{-1}$ to
25 peak baseline (in units of absorbance).

26

GRAPH I

Infrared Spectra



Oxidation (&/or Nitration) Number Reported (abs/cm) = peak absorbance divided by path length in cm^{-1} (report in whole numbers)

During the Oxidation-Resistance Bench Test, the viscosity increases of the samples were measured at 100°C by ASTM D 445. The viscosity increase is a percentage that compares the initial “fresh” kinematic viscosity with the end of test “used” oil kinematic viscosity. The formula to calculate for % viscosity difference is:

$$\% \text{ Viscosity difference} = (\text{Sample (x)}_{\text{initial}} - \text{Sample (x)}_{\text{final}}) / \text{Sample (x)}_{\text{initial}} \times 100 \%$$

Oxidation levels of 5.8 microns and Nitration levels of 6.1 microns were used as peak height comparisons.

Measurements are reported on a relative measurement basis so that large results or values represent greater levels of oxidation-nitration and viscosity increase resistance. Lower numbers represent shorter oil life. Sample C was used as a reference oil and the results in the Tables 3, 4 and 5 were reported as a ratio in the first row of each table. This ratio was calculated by dividing measurements for Sample C by the measurements taken using the sample being compared to sample C. The second row of each table

displays the percent difference between the reference Sample C and the samples being compared to Sample C. The larger the percentage difference between Sample C and the other samples, the better performing the sample in respect to oxidation resistance. Sample C was the reference sample for the results reported in Table 3-5. The formula to calculate percentage difference of the ratios compared to Sample C for Tables 3-5 is:

$$\% \text{ difference} = (\text{Sample (x)} - \text{Sample C}) / \text{Sample (x)} \times 100 \%$$

TABLE 3
Oxidation Resistance Test Results

	Sample A	Sample B	Sample C
Ratio*	3.8	1.5	1.0
% Difference compared to Sample D**	74	32	0

*Ratio – These numbers are relative ratios compared to Sample C's performance in this test. Numbers larger than 1.00 perform better than Sample C and less than 1.00 perform worse than the reference. The higher the ratio number, the higher the performance of the sample.

**% Difference – These numbers are the percentage difference between Sample C and the comparative Sample. A negative number indicates worse performance than Sample C.

The results presented in Table 3 indicate that Sample A and B exhibited a 74 % and 32 % improvement, respectively, in oxidative resistance over the reference Sample C.

TABLE 4
Nitration Resistance Test Results

	Sample A	Sample B	Sample C
Ratio*	8.7	1.8	1.0
% Difference compared to Sample D**	89	44	0

*Ratio – These numbers are relative ratios compared to Sample C's performance in this test. Numbers larger than 1.00 perform better than Sample C and less than 1.00 perform worse than the reference. The higher the ratio number, the higher the performance of the sample.

**% Difference – These numbers are the percentage difference between Sample C and the comparative Sample. A negative number indicates worse performance than Sample C.

The results in Table 4 indicate the improved performance of Samples A and B over the reference sample. The improvement ranged from 89 % to 44 % over the reference sample in nitration resistance.

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22

TABLE 5
Viscosity Increase Resistance Test Results

	Sample A	Sample B	Sample C
Ratio*	7.0	3.0	1.0
% Difference compared to Sample C**	86	67	0

*Ratio – These numbers are relative ratios compared to Sample C's performance in this test. Numbers larger than 1.00 perform better than Sample C and less than 1.00 perform worse than the reference. The higher the ratio number, the higher the performance of the sample.


**% Difference – These numbers are the percentage difference between Sample C and the comparative Sample. A negative number indicates worse performance than Sample C.

The results in Table 5 indicate the improved performance of Samples A and B over the reference sample. The improvement ranged from 86 % to 67 % over the reference sample in viscosity increase resistance.

Samples A and B perform superior to the reference sample with respect to oxidation, nitration and viscosity increase. These tests that quantify a lubricating oil's resistance to oxidation and nitration and the resultant viscosity increase are used to determine whether samples are good candidates for extending the life of lubricating oil particularly those lubricating oils for use in natural gas fueled engines. Absorbing oxygen and nitrogen and the resultant viscosity increase associated with absorbing oxygen and nitrogen are undesirable for lubricating oil particularly lubricating oils for use in natural gas fueled engines.

WHAT IS CLAIMED IS:

1. Lubricating oil comprising a minor amount of one or more hindered phenols of the general formula:



wherein R is a C₇-C₉ alkyl group
and a major amount of at least one of Group II, III and IV base oils.

2. Lubricating oil of Claim 1 wherein about 0.2 wt. % to about 3 wt. % of the lubricating oil comprises the hindered phenol of Claim 1.
3. Lubricating oil of Claim 1 wherein the hindered phenol is liquid.
4. A additive formulation comprising the hindered phenol of Claim 1 and one or more dispersants, one or more detergents and one or more wear inhibitors.
5. Lubricating oil of Claim 1 having a total base number of about 2.15 to about 8.88 as determined by ASTM D 2896.
6. Lubricating oil of Claim 1 having a total ash content of about 0.1 wt. % to about 1.5 wt. % as determined by ASTM D874.
7. Lubricating oil of Claim 1 having less than 4000 ppm sulfur.
8. A method of making the lubricating oil of Claim 1 by combining the hindered phenol of Claim 1 with the base oil of Claim 1 in any order and mixing.

- 1 9. A method of lubricating engines comprising lubricating one or more
2 engines with lubricating oil comprising the hindered phenol of Claim 1.
3
- 4 10. Lubricating oil comprising a major amount of at least one of
5 Group II, III and IV base oil and a minor amount of 2-(4-hydroxy-3,
6 5-di-t-butyl benzyl thiol) acetate.
7
- 8 11. Lubricating oil of Claim 10 having less than 4000 ppm sulfur.
9
- 10 12. Lubricating oil of Claim 10, wherein about 0.2 wt. % to about 3 wt. % of
11 the lubricating oil comprises 2-(4-hydroxy-3, 5-di-t-butyl benzyl thiol)
12 acetate.
13
- 14 13. Lubricating oil of Claim 10, wherein the 2-(4-hydroxy-3, 5-di-t-butyl
15 benzyl thiol) acetate is liquid.
16
- 17 14. Lubricating oil of Claim 10 having a total base number of about 2.15 to
18 about 8.88 as determined by ASTM D 2896.
19
- 20 15. Lubricating oil of Claim 10 having a total ash content of about 0.1 wt. %
21 to about 1.5 wt. % as determined by ASTM D874.
22
- 23 16. A method of lubricating engines comprising contacting the engine with
24 the lubricating oil of Claim 10.
25
- 26 17. A method for making the lubricating oil of Claim 10 comprising
27 combining the 2-(4-hydroxy-3, 5-di-t-butyl benzyl thiol) acetate with at
28 least one of Group II, III and IV base oil in any order and mixing.
29
- 30 18. An additive formulation comprising 2-(4-hydroxy-3, 5-di-t-butyl benzyl
31 thiol) acetate; one or more dispersants; one or more wear inhibitors;
32 and at least one of sulfonate, salicylate and phenate detergents.
33

- 1 19. Lubricating oil comprising a minor amount of the additive formulation of
2 Claim 18 and a major amount of at least one of
3 Group II, III and IV base oil.
4
- 5 20. Lubricating oil of Claim 19 comprising about 4 wt. % to about
6 16.50 wt. % of the additive formulation and about 40 wt. % to about
7 97 wt. % of the base oil.
8
- 9 21. A method for lubricating a natural gas fueled engine comprising
10 lubricating the natural gas fueled engine with the lubricating oil of
11 Claim 19.
12
- 13 22. A method for making the additive formulation of Claim 18, comprising
14 combining one or more detergents; one or more dispersants; one or
15 more wear inhibitors; and 2-(4-hydroxy-3, 5-di-t-butyl benzyl thiol)
16 acetate in any order and agitating until mixed.
17
- 18 23. Lubricating oil comprising:
19
20 about 1 wt. % to about 8 wt. % of one or more dispersants;
21
22 about 1 wt. % to about 8.5 wt. % of one or more detergents;
23
24 about 0.2 wt. % to about 1.5 wt. % of one or more wear inhibitors;
25
26 about 0.2 wt. % to about 3 wt. % 2-(4-hydroxy-3, 5-di-t-butyl benzyl
27 thiol) acetate; and
28
29 about 6 wt. % to about 97 wt. % of at least one of
30 Group II, III and IV base oil.
31

1 24. A method for lubricating a natural gas fueled engine comprising
2 lubricating the natural gas fueled engine with the lubricating oil of
3 Claim 23.

4
5 25. Lubricating oil comprising:

6
7 about 1 wt. % to about 8 wt. % of one or more dispersants;

8
9 about 1 wt. % to about 8.5 wt. % of one or more detergents;

10
11 about 0.2 wt. % to about 1.5 wt. % of one or more wear inhibitors;


12
13 about 0.6 wt. % to about 2.5 wt. % 2-(4-hydroxy-3, 5-di-t-butyl benzyl
14 thiol) acetate; and

15
16 about 6 wt. % to about 97 wt. % of at least one of
17 Group II, III and IV base oil.

18
19 26. A method of lubricating engines comprising contacting one or more
20 engines with the lubricating oil of Claim 25.

21
22 27. A method of reducing oxidation in an internal combustion engine which
23 comprises operating an engine with a composition comprising

24
25 a minor amount of one or more hindered phenols of the general
26 formula:




30 wherein R is a C₇-C₉ alkyl group

and a major amount of at least one of Group II, III and IV base oils.

1 28. A method of reducing oxidation in an internal combustion engine
2 according to claim 27 wherein said internal combustion engine is a natural
3 gas engine.

4
5 29. The use of an antioxidant system comprising

6
7 a minor amount of one or more hindered phenols of the general
8 formula:



11 wherein R is a C₇-C₉ alkyl group

12 and a major amount of at least one of Group II, III and IV base oils, to reduce
13 oxidation in an internal combustion engine.

14
15 30. The use of an antioxidant system according to claim 29 wherein said
16 internal combustion engine is a natural gas engine.

17