



COMPOSITE MAGNETIC MATERIAL

5 TECHNICAL FIELD

The present invention relates to a magnetic body of metallic composite material of high performance level for use in choke coils and the like devices; more specifically, a composite magnetic body for use as a soft magnetic material of a magnetic core.

10

BACKGROUND ART

In line with the prevailing trend of down-sizing among the recent electric and electronic equipment, demand for a smaller but efficient magnetic body is increasing. For example, in many of the choke coils at high frequency circuit, a ferrite magnetic core formed of a soft magnetic ferrite and a dust core compression-formed of soft magnetic metal powder are used.

Of them, the ferrite magnetic core is noted for its defect of a small saturation magnetic flux density. In order to suppress the decline of the inductance L value and assure the direct-current superposing characteristic, a gap of several hundred microns is provided in a direction vertical to the magnetic path. Such a wide gap, however, may be a source of beat sound, or when used in a high frequency band, in particular, the leakage flux generated in the gap may extremely increase the copper loss in the winding.

By contrast, the dust core fabricated by forming the magnetic metal powder has an extremely large saturation magnetic flux density as compared with the soft magnetic ferrite, therefore it is advantageous in reducing the size of a core down. Also, generation of the beat sound and the copper loss caused by leakage magnetic flux are small, since it can be used without providing the gap.

30 However, in terms of the magnetic permeability and the electric power



loss, dust core is not superior to the ferrite core. When a dust core is used in a choke coil or an inductor, it results in a greater temperature rise corresponding to the greater core loss; so it is hard to make the core size smaller. In order to improve the magnetic characteristics, the dust cores are usually formed by applying a compression force higher than 5 tons/cm² or even more than 10 tons/cm², depending on the kind of application. Therefore, it is quite difficult to form a dust core in a compact and complicated core shape; for example, a core for a low profile choke coil for use in a computer DC-DC converter. Thus, there is a greater limitation in the shape of the dust cores, as compared with the case of the ferrite cores. Down-sizing is not easy with the dust cores.

The core loss with the dust cores normally consists of hysteresis loss and eddy current loss. The eddy current loss increases in proportion to the square of frequency and the square of a flowing size of eddy current. Therefore, to suppress the generation of eddy current, surface of the magnetic powder is covered with an electric insulating resin or the like material.

Since the dust cores are formed with a high compression force, the magnetic permeability is deteriorated by the distortion caused in the magnetic body, which brings about a hysteresis loss. To avoid this to happen, a high temperature heat treatment is applied on the compression-formed pieces for relieving from the distortion. In such a case, the use of an insulating binder is essential to ensure a good insulation between the magnetic powder particles while keeping good mutual adhesion.

A conventional magnetic dust core is disclosed in Japanese Laid-open Patent No.1-215902, which core is formed of a mixture of a magnetic alloy powder, Fe-Al-Si alloy (sendust) or Fe-Ni alloy (permalloy), and an alumina cement powder, which mixture is compression-molded after annealing at 700 - 1200°C. Japanese Laid-open Patent No. 6-342714 teaches a magnetic dust core which is formed of a mixture of an Fe-Al-Si alloy magnetic powder and a silicone resin, which mixture is compression-molded and then annealed in

non-oxidizing atmosphere of 700 - 1200°C. Further, Japanese Laid-open Patent No. 8-45724 discloses a magnetic dust core that is formed of a mixture of an Fe-P alloy magnetic powder, a silicone resin and an organic titanium, which mixture is compression-molded and then annealed in 700 - 1200°C atmosphere.

With the ferrite core having a gap, the inductance L value declines suddenly from a certain point in the direct-current superposing current. In the dust core, by contrast, it declines smoothly along with the direct-current superposing current, but the core can comply with a large current because of the high saturation magnetic flux density. For implementing a high magnetic permeability with the dust core, it is effective to increase the packing rate of alloy powder in a core piece and to reduce the distance between the powder particles.

However, increasing the packing rate contradicts to securing the insulation between the particles; as a result, it is difficult to realize the both requirements at a same time, the high packing rate and the insulation between the powder particles. Furthermore, it is difficult for a dust core to take a complicated shape, which means that there is a substantial restriction in the core shapes available.

DISCLOSURE OF THE INVENTION

The present invention addresses the above described problems existed in the conventional magnetic cores, and it is an objective to offer a composite magnetic body that satisfies both of the requirements at the same time, the high magnetic permeability and the small core loss. Furthermore, the composite magnetic body of the present invention can be formed into a core piece whose shape is of high complexity.

According to a first mode of the present invention, there is provided a composite magnetic body of a compressed compact comprising a mixture of a magnetic alloy powder containing iron and nickel as main components, a silicone resin binder for binding the powder particles together, and a thermal diffusion inhibitor, wherein a packing rate of the magnetic alloy powder in the compressed compact falls within a range of 88-95% by volume, and the compressed compact is heated at a temperature of 500 to 900°C in non-oxidizing atmosphere.

The mixture may be compression-moulded. The alloy powder containing iron and nickel as the main components exhibits a high magnetic flux density, and admits a substantial plastic deformation during compression-moulding process attaining a high packing rate of the powder in the compressed compact; thus it provides a high magnetic permeability. By combining the magnetic powder with a silicone resin working as a binder, insulation between the alloy powder particles after the compression moulding is secured, and the eddy current loss is reduced; hence, a low core loss is realised.

Another composite magnetic body of a compressed compact in accordance with the present invention comprises a mixture of a magnetic alloy powder containing iron and nickel as the main components, an insulating material and an acrylic resin binder for binding these together, said compressed compact being heated at a temperature of 500 to 900°C in non-oxidizing atmosphere.

The mixture may be compression-moulded. The composite magnetic body in the present mode exhibits, like the magnetic body in the earlier described mode, a high magnetic permeability, and the insulating material assures good insulation between the alloy powder particles after the compression moulding to a decreased eddy current loss; hence, a low core loss. The acrylic resin provided as a binder improves the compatibility, which contributes to the formation of a core having a high complexity shape.

Still another mode of a composite magnetic body of a compressed compact in accordance with the present invention comprises a mixture of a magnetic iron powder, or a magnetic alloy powder containing silicon of not more than 7.5% by weight (not including 0%) and iron for the rest, an insulating and an acrylic resin binder for binding these together, said compressed compact being heated at a temperature of 500 to 900°C in non-oxidizing atmosphere.

The mixture may be compression-moulded. Also in the present mode, the magnetic body exhibits both a high magnetic permeability and a low core loss, and the

acrylic resin used as a binder improves the compatibility, which contributes to the formation of a core having a high complexity shape.

BEST MODE FOR CARRYING OUT THE PRESENT INVENTION

(Embodiment 1)

First, Fe-Ni alloy powder of 45 % by weight of Ni and the remainder of Fe was prepared as the magnetic powder by atomizing method. Mean
5 particle diameter of the powder is 50 μm . Next, a silicone resin (a methyl system silicone resin, having a remainder of approximately 70 - 80 % by weight after heating), a PVB (polyvinyl butyl resin) and water glass were prepared as a binder. Also a silane monomer was prepared as a thermal diffusion inhibitor, and a stearic acid as a fatty acid. These materials were
10 used for making the samples number 1 through 13 of Table 1.

Those samples containing the thermal diffusion inhibitor were provided in the following manner: To 100 parts by weight of the magnetic powder, 0.5 parts by weight of the thermal diffusion inhibitor and 3 parts by weight of ethanol as solvent are mixed by using a mixing agitator. The
15 mixture is dried for 1 hour at 150°C; and then mixed with 1 part by weight of one of respective binders of Table 1, further 3 parts by weight of xylene as solvent to be mixed again by a mixing agitator. After the mixing is finished, it is dried to remove the solvent. The dried mixture is crushed, and granulated so that it flows smoothly into a mold. Those samples containing
20 the fatty acid are made with the granulated powder by adding 0.1 part by weight of fatty acid and mixing these together by a cross rotary mixer.

Those samples without having the thermal diffusion inhibitor were provided in the following manner: To 100 parts by weight of the magnetic powder, 1 part by weight of one of the respective binders and 3 parts by weight
25 of xylene as solvent are added to be mixed together by a mixing agitator. After the mixing is finished, it is dried to remove the solvent. The dried mixture is crushed, and granulated so that it flows smoothly into a mold. Those samples containing the fatty acid are made with the above granulated powder by adding 0.1 part by weight of fatty acid and mixing these together
30 by a cross rotary mixer.

TABLE 1

	Sample No.	Binder	Thermal diffusion inhibitor	Fatty acid	Heating temperature (°C)	Magnetic permeability	Core loss (kW/m ³)	Packing rate (vol%)	
Embodi- ment	1	Silicone resin	none	none	700	88	480	90	
	2		○	none		90	515	89	
	3		none	○		98	470	91	
	4		○	○	500	95	450	90	
	5					82	620		
	6					111	920		
	7	PVB	○	none	700	82	660	88	
	8		○	○		90	710	90	
Compari- son	9	Water glass	none	none	700	60	2500	88	
	10	PVB	none	none	none	50	3200	89	
	11	Silicone resin	○	○		45	2400	90	
	12					61	1500		
	13			950	83	3000			

The granulated powder was put in a mold, and compressed by a uniaxial press at a pressure of 10 t/cm^2 for three seconds. As a result, a toroidal formed piece of 25 mm in outside diameter, 15 mm in inside diameter, and about 10 mm in thickness was obtained.

5 The obtained formed piece was put in a heat treatment oven, and heated in nitrogen atmosphere at a heat treatment temperature shown in Table 1. The holding time at the heat treatment temperature was 0.5 hour.

These samples were measured in the magnetic permeability, the core loss and the packing rate of alloy powder in a core. The results of these
10 measurements are shown in Table 1. The magnetic permeability was measured by using an LCR meter at frequency of 10 kHz, and the core loss by an alternating current B-H curve measuring instrument at measuring frequency of 50 kHz, and measuring magnetic flux density of 0.1 T. The packing rate shown in the table is the value, (core density / real density of
15 alloy powder) $\times 100$. Sample numbers 1 to 8 represent embodiments of the present invention, and sample numbers 9 to 13 are comparative examples.

The selection standard in the choke coil for countermeasure against harmonic distortion is core loss of 1000 kW/m^3 or less, in the conditions of the current measuring frequency of 50 kHz and measuring magnetic flux density
20 of 0.1 T. Magnetic permeability should be 60 or more.

As clear from the results shown in Table 1, the samples of number 1 to 8 satisfy the above selection standard. Especially, the samples number 1 to 6, which being the combination of Fe-Ni alloy powder and silicone resin binder, show excellent characteristics; namely, great magnetic permeability and small
25 core loss. The thermal diffusion inhibitor is also seen to be effective; compare the samples number 7 and 10, a binder which by itself can not clear the core loss requirement satisfies the standard when it is combined with thermal diffusion inhibitor. The fatty acid contributes to increase packing rate of alloy powder in a core, and improves the magnetic permeability. The heat
30 treatment of $500 - 900^\circ\text{C}$ applied on a compression-formed piece improves the

magnetic permeability and the core loss. The heat treatment should preferably be made in a non-oxidizing atmosphere of 500 - 900°C, more preferably within a temperature range 700 - 900°C. The higher the heat treatment temperature the more effective for reducing the hysteresis loss, in
5 so far as the alloy powder does not start getting sintered.

In a compression-molded piece having a packing rate exceeding 88 %, there exists a least pore (vacancy), and there is hardly any pore coming from the inside leading to the outside (open pore). When such a molded core piece undergoes a heat treatment, if a binder used in the piece had much
10 evaporating content in it the evaporation can not take place sufficiently because of the small number of pores existing, as the result, the evaporated substance remains staying within the core. This leads to deteriorated characteristics. Therefore, a silicone resin, which keeps a high insulating capability up to a high temperature and contains only a small evaporating
15 content, is suitable for use in a core piece of high packing rate.

For further enhancing the insulating capability with the magnetic alloy powder, it is effective to provide a thermal diffusion inhibitor on the surface of the alloy powder. Preferred material for the thermal diffusion inhibitor is a low molecular weight material having a high temperature
20 insulating capability; practical example includes a silane monomer which can form a siloxane layer on the surface of alloy powder. During heat treatment applied to the compression-formed piece, such layer changes itself in part into silica, which provides a rigid insulation layer. The above thermal diffusion inhibitor leaves a room for the use, in a small quantity, of an ordinary organic
25 binder, such as an epoxy, a polyvinyl acetal and the like. Thus a broader range is provided for the resin selection. In this way, cores or other pieces of complex shape can now be provided through a compression-molding process. In the past, complicated pieces were not available through the compression-molding method.

30 The fatty acid plays a role of lubrication, which improves the mold

separation, the plasticity of mixed substance and raises the packing rate of alloy powder in a compression-molded piece higher. Among the fatty acids, such metal fatty acids as zinc stearate, magnesium stearate and calcium stearate are significantly effective to increase the fluidity and the transmitting property of the granulated powder during molding process; which altogether leads to a higher packing rate. Use of the metal fatty acid contributes to insure a homogeneous compression, which property makes it suitable for the manufacture of compact and complex-shaped pieces by compression-molding. Such fatty acids as stearic acid and myristic acid, which evaporate at a relatively low temperature and hardly keep staying within a compression-formed piece after the heat treatment, are especially suitable to those pieces having a high packing rate of alloy powder.

Although an Fe-Ni alloy of 45 % by weight of Ni is used in the present embodiment, other Fe-Ni alloys of different compositions may also be used depending on the field of application, in so far as the Ni content does not exceed approximately 90 % by weight. Also, Fe-Ni alloys added with Cr, Mo or the like elements may be used instead.

(Embodiment 2)

To 100 parts by weight of the magnetic alloy powder of embodiment 1, 0.5 parts by weight of silicone resin and 3 parts by weight of xylene as solvent were added and mixed together by using a mixing agitator. After the mixing was finished, it was dried to remove the solvent. The dried mixture was crushed, and granulated so that it flowed smoothly into a mold. Samples number 14 to 18 were prepared through the same way as in embodiment 1, except that packing rate of the alloy powder in a compression-formed piece was varied by changing the compression force of uniaxial press. The samples number 14 to 16 represent embodiments of the present invention; while the sample 17 and the sample 18, silicone resin content in the latter sample has been changed to 0.3 parts by weight, are examples for comparison.

Table 2 shows packing rate, magnetic permeability and core loss of

these samples. Method of the measurement remains the same as in embodiment 1, so description of which method is not repeated here.

TABLE 2

	Sample No.	Packing rate (vol%)	Magnetic permeability	Core loss (kW/m ³)
Embodi- ment	14	88	65	590
	15	92	103	450
	16	95	125	420
Compari- son	17	87	58	610
	18	96	180	1200

10

As clear from the results in Table 2, the samples well meet the above described selection standards when the packing rate falls within a range 88 - 95 % by volume. Where, the higher the packing rate the better performance in both the magnetic permeability and the core loss. The sample whose packing rate is lower than 87 % by volume can not satisfy the standard. A packing rate higher than 96 % was not available with the samples having 0.5 parts by weight of silicone resin despite an increased compression force; therefore, the sample 18 was prepared with a reduced silicone content. Although the sample 18 attained an increased packing rate, it failed to insure the insulation between the alloy powder particles, and the core loss increased.

20

For providing favorable characteristics, it is preferred that the packing rate of alloy powder in a compression-formed piece falls within a range 88 - 95 % in terms of volume. Within the range, the higher the packing rate the better the characteristics.

25 (Embodiment 3)

Samples number 19 to 24 were prepared through the same way as in the sample number 4 of embodiment 1, except that the mean particle diameter of magnetic alloy powder was varied. The samples were measured in the characteristic items. Samples number 19 to 22 represent embodiments of the present invention, while samples number 23 and 24 are for comparison. The

30

packing rate of alloy powder is within a range 88 - 95% with all of the samples.

Table 3 shows the results of measurement.

TABLE 3

	Sample No.	Mean particle diameter (μm)	Magnetic permeability	Core loss (kW/m^3)
Embodi- ment	19	1	60	680
	20	10	63	280
	21	50	95	450
	22	100	125	880
Compari- son	23	110	135	1350
	24	0.8	56	1430

As shown in Table 3, the above described selection standard is satisfied with the samples whose mean particle diameter of magnetic alloy powder is not smaller than 1 μm , not greater than 100 μm .

The eddy current loss increases in proportion to the square of frequency and the square of a flowing size of eddy current. The loss can be suppressed by covering the surface of magnetic particle with an insulating material. The eddy current is dependent on particle diameter of the magnetic powder; the finer the particle the smaller the eddy current loss. However, when particle diameter goes smaller the relative surface area of a particle normally increases. Accordingly, the size of eddy current increases and eddy current loss goes high, unless surface of the magnetic powder is covered enough with an insulating material.

With the choke coils for countermeasure against harmonic distortion, for example, the core loss should preferably be 1000 kW/m^3 or less, more preferably 500 kW/m^3 or less, in the conditions of the current measuring frequency of 50 kHz and measuring magnetic flux density of 0.1 T. In order to satisfy the above requirements and lower the eddy current loss in the frequency band higher than 50 kHz, the mean particle diameter should preferably be not smaller than 1 μm not greater than 100 μm , more preferably not smaller than 10 μm not greater than 50 μm .

(Embodiment 4)

Fe-Ni alloy powder of 45 % by weight of Ni and remainder of Fe was prepared as the magnetic alloy powder by atomizing method, mean particle size of which powder being 20 μm . Next, alumina (particle diameter 0.3 μm),
5 or an inorganic powder, silicone resin, or an organic silicon compound, (a methyl system silicone resin, having a remainder of approximately 70 - 80 % by volume after heating), silane monomer and silicone oil were prepared as the insulating material. Acrylic resin (polymethacrylate), silicone resin (a
10 methyl system silicone resin, having a remainder of approximately 70 - 80 % by volume after heating), epoxy resin and water glass were prepared as the binder. Stearic acid was prepared as the fatty acid. These materials were used for making the samples number 25 through 43 of Table 4.

To 100 parts by weight of magnetic alloy powder, 0.5 parts by weight of the insulating material and 3 parts by weight of xylene as solvent were
15 mixed together by using a mixing agitator. The mixture was dried; and then mixed with 1 part by weight of one of the respective binders of Table 4, and further 3 parts by weight of xylene as solvent to be mixed again by a mixing agitator. After the mixing was finished, it was dried to remove the solvent. The dried mixture was crushed, and granulated so that it flows smoothly into
20 a mold. Those samples containing the fatty acid were made with the granulated powder by adding 0.1 part by weight of fatty acid, and mixing together by a cross rotary mixer.

The granulated powder was put in a mold, and compressed by a uniaxial press at a pressure of 10 t/cm^2 for three seconds. As a result, a
25 toroidal formed piece of 25 mm in outside diameter, 15 mm in inside diameter, and about 10 mm in thickness was obtained.

The obtained formed piece was put in a heat treatment oven to be treated under the conditions as shown in Table 4. The heat treatment in oxidizing atmosphere was conducted at heat-up speed $1^\circ\text{C}/\text{min.}$, holding time
30 0.5 hour. That in non-oxidizing atmosphere was conducted at heat-up speed

5°C/min., holding time 0.5 hour. The toroidal formed samples were thus prepared.

For the purpose of ascertaining whether the pieces of higher complexity can be formed, namely for the purpose of evaluating the compactibility, cores shaped in a letter "E" were also manufactured for the samples of Table 4, using a uniaxial press at a pressure of 10 t/cm² for three seconds. The E-shaped core has a square contour whose side is 12 mm long, and the thickness is 5 mm; the middle foot is shaped in a column of 4 mm in the diameter, the outer feet have a 1 mm width, the back has a 1 mm width.

The toroidal shape samples were used for measuring the magnetic permeability, the core loss and the packing rate of magnetic alloy powder in the core; while the E-shaped samples were inspected with respect to the finished conditions of the core piece. The results are shown in Table 4. The magnetic permeability was measured by using an LCR meter at frequency of 100 kHz, a direct-current magnetic field of 5000 A/m, and the core loss was measured by an alternating current B-H curve measuring instrument at measuring frequency of 300 kHz, measuring magnetic flux density of 0.1 T. The packing rate shown in the table is the value, (core density / real density of alloy powder) x 100. With respect to the evaluation of compactibility, those which do not bear any defect in the appearance are marked with "O", while those bearing crack or other defect are marked with "x". Samples number 25 to 33 represent embodiments of the present invention, while samples number 34 to 43 are comparative examples.

The selection standard in the choke coil for countermeasure against harmonic distortion is the core loss of 4500 kW/m³ or less, in the conditions of the current measuring frequency of 300 kHz and measuring magnetic flux density of 0.1 T; the magnetic permeability of 50 or more, in the conditions of the measuring frequency of 100 kHz and direct-current magnetic field of 5000 A/m.

TABLE 4

	Sample No.	Insulating material	Binder	Fatty acid	Heating temp. /oxidizing (°C)	Heating temp. /non-oxidizing (°C)	Permeability	Core loss (kW/m ²)	Packing rate (vol%)	Compactibility		
Em-bodiedment	25	Silicone resin	Acrylic resin	○	none	700	58	2900	89	○		
	26					500	52	3100	89	○		
	27					900	60	4300	89	○		
	28				700	57	3000	89	○			
	29					58	3000	89	○			
	30					53	3500	87	○			
	31	Silane monomer	Acrylic resin	none	700	59	4200	91	○			
	32	Silicone oil				58	4200	90	○			
	33	Alumina				50	4400	86	○			
	Com-parison	34	Silicone resin	Acrylic resin	○	none	none	30	9000	89	○	
35		450					42	7200	89	○		
36		950					58	10300	89	○		
37		700					40	9500	89	○		
38				Silicone resin		51	3500	87	×			
39				Epoxy resin		48	5500	84	×			
40		Water glass		45		12500	85	×				
41		Water glass	Silicone resin	39		13100	84	×				
42		Alumina							50	3800	85	×
43		none										

As clear from the results in Table 4, the samples of numbers 25 to 33 satisfy the selection standard in both the magnetic permeability and the core loss. Those containing acrylic resin as the binder show an excellent compactibility in forming a core piece of complex shape. Use of an insulating material proved to be effective for improving the core loss; an organic silicon compound, among others, proved to be especially effective. The fatty acid contributes to increase the packing rate of alloy powder in a core piece, and improves the magnetic permeability.

The high plasticity of acrylic resin contributes to keeping the shape of a compression-formed piece as it is. Therefore, it is suitable to the formation of a shape of high complexity. Acrylic resin is further advantageous in its high thermal decomposition property in the oxidizing and in the non-oxidizing atmospheres; it hardly leaves any ash behind.

The heat treatment in oxidizing atmosphere of 250 - 350°C conducted on compression-formed pieces does not deteriorate the core characteristics. The heat treatment in non-oxidizing atmosphere of 500 - 900°C improves the magnetic permeability and the core loss of the compression-formed pieces. This heat treatment should preferably be made within a temperature range 700 - 900°C. The higher the heat treatment temperature the more effective it is in reducing the hysteresis loss, in so far as the alloy powder does not start getting sintered.

In case where binder resin remains within a core after heat treatment as residual carbon, it deteriorates the magnetic characteristics. Therefore, it should be avoided. Acrylic resin has a superior thermal decomposition property, and leaves hardly any residual carbon after heat treatment in the non-oxidizing atmosphere; thus, favorable characteristics can be realized. While in the oxidizing atmosphere, acrylic resin decomposes in a temperature range not higher than 350°C; therefore, the binder resin can be degreased without substantially oxidizing the alloy powder. By degreasing in the oxidizing atmosphere of 250 - 350°C prior to the heat treatment in non-

oxidizing atmosphere, good cores of complex shape can be manufactured without inviting deformation or crack during the heat treatment procedure.

An insulating material for enhancing the insulation between alloy powder particles should be such that can withstand the temperature of heat treatment applied with an aim of lowering the hysteresis loss. Inorganic example for the insulating material includes oxide particles (alumina, magnesia, silica, titania, etc.) and inorganic high polymer. Organic high polymer is also suitable to the insulating material, in so far as it is least reactive to the alloy powder during heat treatment and maintains insulating property at the heat treatment temperature. An organic silicon compound, among others, that covers the surface of alloy powder in the form of siloxane layer is preferred. Preferred organic silicon compound includes silicone resin, silane monomer and silicone oil. Preferred properties the organic silicon compound should preferably have are; that it readily covers the surface of the alloy powder and that it exhibits a small heating loss. The layer thus formed changes in part into silica during the heat treatment applied on compression-formed pieces, making itself a rigid insulation layer.

The fatty acid plays a role of lubrication, which improves the mold separation, the plasticity of the mixed substance and the packing rate of alloy powder higher. Among the fatty acids, such metallic fatty acids as zinc stearate, magnesium stearate and calcium stearate, for example, are significantly effective to increase the fluidity of granulated powder and the transmission of compression force during compression process, which improvement factors lead to a higher packing rate of alloy powder in a compression-formed piece. Metallic fatty acid contributes to insure the homogeneous compression and homogeneous formation of a compression-formed piece; therefore it is especially suitable for the formation of a small piece of complex shape. Such fatty acids as stearic acid and myristic acid evaporate at a relatively low temperature and rarely stay within a compression-formed piece after the heat treatment; therefore, these are

especially suitable to those pieces of high alloy powder packing rate.

(Embodiment 5)

Samples number 44 to 48 were prepared through the same way as in the sample 25 of embodiment 4, except that the packing rate of the magnetic alloy powder in a compression-formed piece was varied by changing the compression force of uniaxial press. The samples number 44 to 46 represent embodiments of the present invention; while the sample number 47 and the sample 48, the silicone resin content in the latter sample has been changed to 0.3 parts by weight, are examples for comparison.

TABLE 5

	Sample No.	Packing rate (vol%)	Magnetic permeability	Core loss (kW/m ³)
Embodi- ment	44	85	51	3300
	45	89	58	2900
	46	95	62	3300
Compari- son	47	84	49	3400
	48	96	62	4700

Table 5 shows the packing rate, the magnetic permeability and the core loss of these samples. Method of the measurement remains the same as in embodiment 4, so description of which method is not repeated here.

As clear from the results in Table 5, the samples of number 44 to 46 satisfy the selection standard for a choke coil described in embodiment 4 in both of the characteristic items, the magnetic permeability and the core loss. The magnetic permeability improves along with the increasing packing rate of alloy powder. If the packing rate is lower than 84 %, it can not satisfy the selection standard in magnetic permeability. The sample 48 having a packing rate 96 %, which has been prepared with a reduced silicone resin content because the addition of 1 part by weight of acrylic resin makes it impossible to attain the targeted packing rate 96 % despite a high compression force, can not satisfy the standard due to increased core loss

caused by the failure in securing rigid insulation between the alloy powder particles.

As described in the above, the packing rate of alloy powder should preferably be falling within a range 85 - 95 % in terms of volume for a compression-formed piece of composite magnetic material to exhibit superior characteristics. In so far as it stays within the above-described range, the higher the packing rate the higher the performance.

(Embodiment 6)

Samples number 49 to 54 were prepared through the same way as in the sample 25 of embodiment 4, except that the mean particle diameter of the magnetic alloy powder was varied. The samples number 49 to 52 represent embodiments of the present invention; while the samples number 53 and 54 are examples for comparison. The packing rate of alloy powder fell within the range 85 - 95 % with all of the samples.

Table 6 shows the results of measurement.

TABLE 6

	Sample No.	Mean particle diameter (μm)	Magnetic permeability	Core loss (kW/m^3)
Embodi- ment	49	1	50	3800
	50	10	55	2600
	51	20	95	2900
	52	50	125	4300
Compari- son	53	60	135	5000
	54	0.7	43	6500

As clear from the results shown in Table 6, those samples whose mean particle diameter of the magnetic alloy powder is not smaller than 1 μm not greater than 50 μm satisfy the standard for the choke coil described earlier in embodiment 4.

Since the eddy current loss increases in proportion to the square of frequency and the square of a flowing size of eddy current, it can be

suppressed by covering the surface of the magnetic particle with an insulating material. The eddy current is dependent on particle diameter of the magnetic powder; the finer the particle the smaller the eddy current loss.

However, when the particle diameter goes smaller the relative surface area of a particle normally increases. Accordingly, the size of eddy current increases and eddy current loss goes high unless surface of the magnetic powder is covered enough with an insulating material. With the choke coils for countermeasure against harmonic distortion, for example, the core loss should preferably be 4500 kW/m³ or less, more preferably 3500 kW/m³ or less, in the conditions of the current measuring frequency of 300 kHz and measuring magnetic flux density of 0.1 T. In order to reduce the eddy current loss at a frequency higher than 300 kHz, it is preferred that the mean particle diameter of the magnetic alloy powder is not smaller than 1 μm not greater than 50 μm, more preferably not smaller than 10 μm not greater than 20 μm.

(Embodiment 7)

Pure iron powder as well as Fe-Si alloy powders of 3.5 % by weight of Si, 6.8 % by weight of Si, 7.5 % by weight of Si, 7.7 % by weight of Si, respectively, and remainder of Fe were prepared as the magnetic powders by atomizing method. Mean particle diameter of the powder is 30 μm. Next, silicone resin (a methyl system silicone resin, having a remainder of approximately 70 - 80 % by volume after heating) was prepared as the insulating material, acrylic resin (polymethacrylate), silicone resin (a methyl system silicone resin, having a remainder of approximately 70 - 80 % by volume after heating), epoxy resin and water glass were prepared as the binder, and stearic acid was prepared as the fatty acid. These materials were used for making the samples number 55 to 86 of Table 7.

To 100 parts by weight of magnetic powder, 0.45 parts by weight of the insulating material was added and 4 parts by weight of xylene was added as solvent: these were mixed by using a mixing agitator. The mixture was

dried; and then further provided with one of the respective binders for 0. 9 parts by weight as shown in Table 7, further 4 parts by weight of xylene was added as solvent. These were mixed again by a mixing agitator. After the mixing was finished, it was dried to remove the solvent. The dried mixture
5 was crushed, and granulated so that it flowed smoothly into a mold. Those samples containing the fatty acid were made with the above granulated powder by adding 0. 15 part by weight of fatty acid and mixing these together using a cross rotary mixer.

The granulated powder was put in a mold, and compressed by a
10 uniaxial press at a pressure of 12 t/cm² for three seconds. As a result, a toroidal formed piece of 25 mm in outside diameter, 15 mm in inside diameter, and about 10 mm in thickness was obtained.

The obtained formed piece was put in a heat treatment oven to be treated under the respective conditions as shown in Table 7. The heat
15 treatment in oxidizing atmosphere was conducted at the heat-up speed 1°C/min., holding time 0. 5 hour. That in non-oxidizing atmosphere was conducted at the heat-up speed 5°C/min., holding time 0. 5 hour. In this way, the toroidal sample pieces were prepared.

For the purpose of ascertaining whether pieces of more complicated
20 shapes can be formed, namely for evaluating the compactibility, cores shaped in a letter "E" were also manufactured for the samples of Table 7, using a uniaxial press at a pressure of 12 t/cm² for three seconds. The E-shaped core has a square contour having a side of 12 mm long and thickness of 5 mm; the middle foot is shaped in a column of 4 mm diameter, the outer feet have a
25 width of 1 mm, the back has a width of 1 mm.

The toroidal shape samples were used for measuring the magnetic permeability, the core loss and the packing rate of magnetic powder in the core piece, while the E-shaped samples were inspected with respect to the finished conditions of the core piece. The results are shown in Table 7. The
30 magnetic permeability was measured by using an LCR meter at frequency

TABLE 7

	Sample No.	Metal particle	Insulating material	Binder	Fatty acid	Heating temp. /oxidizing (°C)	Heating temp. /non-oxidizing (°C)	Permeability	Core loss (kW/m ²)	Packing rate (vol%)	Com-pactibility
Em-bodiment	55	Fe	Silicone resin	Acrylic resin	○	none	750	66	820	87	○
	56						500	60	880	87	○
	57						900	67	800	88	○
	58					250	750	63	860	87	○
	59					350		62	860	87	○
	60					none		60	830	86	○
	61	Fe-3.5Si	Silicone resin	Acrylic resin	○	none	830	65	770	88	○
	62						500	61	890	85	○
	63						900	67	720	89	○
	64					250	830	64	800	88	○
	65					350		63	810	88	○
	66					none		63	750	87	○
	67	Fe-6.8Si	Silicone resin	Acrylic resin	○	none		61	570	86	○
	68	Fe-7.5Si						60	610	85	○

TABLE 7 (Continued)

	Sample No.	Metal particle	Insulating material	Binder	Fatty acid	Heating temp. /oxidizing (°C)	Heating temp. /non-oxidizing (°C)	Permeability	Core loss (kW/m ²)	Packing rate (vol%)	Com-pactibility
Com- pari- son	69	Fe	Silicone resin	Acrylic resin	○	none	none	25	2800	87	○
	70						450	66	1050	87	○
	71						950	67	2000	89	○
	72						400	35	1800	87	○
	73			none		58		930	85	×	
	74					54		1650	82	×	
	75					54		1700	82	○	
	76					Fe-3.5Si	Silicone resin	Acrylic resin	○	none	20
	77	450	56	1100	88						○
	78	950	67	1800	88						○
	79	400	38	1600	88						○
	80		none	59	1050			86		×	
	81			56	1400			83		×	
	82			54	1750			84		×	
	83	Fe-7.7Si		Silicone resin	○			none		830	56
	84		53			940	83		×		
85	50		1300			80	×				
86	47		1700			81	×				

of 10 kHz, a direct-current magnetic field of 5000 A/m, and the core loss was measured by an alternating current B-H curve measuring instrument at measuring frequency of 50 kHz, measuring magnetic flux density of 0.1 T. The packing rate shown in the table is the value, (core density / real density of powder) x 100. With respect to the compactibility evaluation, those which do not bear any defect in the appearance are marked with "O", while those having crack or other defect are marked with "x". Samples number 55 to 68 represent embodiments of the present invention, and samples number 69 to 86 are comparative examples.

10 The selection standard in the choke coil for countermeasure against harmonic distortion is the core loss of 1000 kW/m³ or less, in the conditions of current measuring frequency of 50 kHz and measuring magnetic flux density of 0.1 T, and the magnetic permeability needs to be 60 or more.

15 As clear from the results in Table 7, the samples number 55 to 68 satisfy the selection standard in both of the characteristic items, the magnetic permeability and the core loss. Those samples in which acrylic resin was used as the binder show an excellent compactibility in forming a core of complex shape. Use of an organic silicon compound proved to be effective for improving the core loss. The fatty acid contributes to increase the packing rate of powder in a core piece, and improves the magnetic permeability.

20 It is observed that the heat treatment in oxidizing atmosphere of 250 - 350°C does not deteriorate the core characteristics of the compression-formed pieces, and that the heat treatment in non-oxidizing atmosphere of 500 - 900°C improves the magnetic permeability and the core loss.

25 Further, it is observed that the pure iron or Fe-Si alloy powder containing Si for ≤ 7.5 % by weight (0% not included) and remainder of Fe exhibits excellent characteristics with a high magnetic permeability and a low core loss.

30 The high plasticity of acrylic resin contributes to maintain the shape of a compression-formed piece as it is. Therefore, it is suitable to the

formation of high complexity pieces. Acrylic resin is further advantageous in its high thermal decomposition property in the oxidizing and in the non-oxidizing atmospheres; it hardly leaves any ash behind.

The preferred temperature of heat treatment is 500 - 900°C in non-oxidizing atmosphere, more preferably 700 - 900°C. The higher the heat treatment temperature the more effective it is for the reduction of hysteresis loss, in so far as the magnetic powder does not start getting sintered. If binder resin leaves any residual carbon in a core piece after the heat treatment, it deteriorates the magnetic characteristics. Acrylic resin has a superior thermal decomposition property, and leaves hardly any residual carbon after the heat treatment in non-oxidizing atmosphere. Thus, favorable characteristics can be realized. While in the oxidizing atmosphere, acrylic resin decomposes in a temperature range not higher than 350°C; therefore, the binder resin can be degreased without much oxidizing the magnetic powder. Therefore, also in forming a core piece of complex shape, it is preferred that it is degreased in oxidizing atmosphere of 250 - 350°C prior to heat treatment in non-oxidizing atmosphere. By so doing, good core pieces can be provided without inviting deformation or crack during the heat treatment.

An insulating material for enhancing the insulation between the powder particles should be such that can withstand the temperature of the earlier described heat treatment process applied for lowering the hysteresis loss. Inorganic example for the insulating material includes oxide particles (alumina, magnesia, silica, titania, etc.) and inorganic high polymer. Organic silicon compound can also be used for the purpose. Other insulating materials can also be used, in so far as it is least reactive to the powder during heat treatment, and maintains the insulating property at the temperature during heat treatment procedure. More preference is on an organic silicon compound, which covers the surface of powder particle in the form of a siloxane layer. Among the organic silicon compounds, silicone resin, silane

monomer, silicone oil, etc. are suitable to the purpose. These which have a property readily covering the powder surface and exhibit a small heating loss are preferred. The layer thus formed changes in part into silica during the heat treatment applied on compression-formed pieces, making itself a rigid insulation layer.

The fatty acid plays a role of lubrication, which improves the mold separation, the plasticity of the mixed substance and the packing rate of the powder higher. Among the fatty acids, such metallic fatty acids as zinc stearate, magnesium stearate and calcium stearate are significantly effective to increase the fluidity of granulated powder and transmission of force during compression process, which properties leading to a higher packing rate of the powder in a compression-formed piece. Metallic fatty acid contributes to insure the homogeneous compression and homogeneous formation of a compression piece; therefore, it is suitable for manufacturing a small piece of complex shape. Such fatty acids as stearic acid and myristic acid, which evaporate at a relatively low temperature and hardly stay behind within a compression-formed piece after heat treatment, are especially suitable to those pieces of high packing rate.

(Embodiment 8)

Samples number 87 to 91 were prepared through the same way as in the sample 55 of embodiment 7, except that the packing rate of the powder in a compression-formed piece was varied by changing the compression force of uniaxial press. The samples number 87 to 89 represent embodiments of the present invention; while the sample 90 and the sample 91, the silicone resin content in the latter sample has been changed to 0.3 parts by weight, are examples for comparison.

Table 8 shows the packing rate, the magnetic permeability and the core loss of these samples. Method of the measurement remains the same as in embodiment 7, so the description of which method is not repeated here.

As clear from the results in Table 8, the samples number 87 to 89

satisfy the selection standard for a choke coil described in embodiment 7 in both of the characteristics, the magnetic permeability and the core loss. The magnetic permeability improves along with the increasing packing rate of the powder. If the packing rate is lower than 84 %, it can not satisfy the selection
 5 standard in magnetic permeability. The sample 91 having a packing rate 96 %, which has been prepared with reduced silicone resin content because the addition of 0.9 parts by weight of the acrylic resin makes it impossible to attain the targeted packing rate 96 % despite high compression, can not satisfy the standard due to the increased core loss caused by failure of
 10 securing rigid insulation between the powder particles.

TABLE 8

	Sample No.	Composition	Packing rate (vol%)	Magnetic permeability	Core loss (kW/m ³)
15	Embodi- ment	Fe	85	51	850
	88		88	66	800
	89		95	68	870
	Compara- son		84	58	920
	91		96	68	1400

As described in the above, the packing rate of the powder should
 20 preferably be falling within a range 85 - 95 % in terms of volume, in order to provide a compression-formed piece with superior characteristics as the composite magnetic material. In so far as it stays within the range, the higher the packing rate the higher the performance.

Further, in a case where a Fe-Si alloy powder containing Si for ≤ 7.5 %
 25 by weight and remainder of Fe is used, it exhibits excellent characteristics with a high magnetic permeability and a low core loss, in so far as the packing rate of the alloy powder in a compression-formed piece falls within the range 85 - 95 % in terms of volume.

(Embodiment 9)

30 Samples number 92 to 97 were prepared through the same way as in

the sample 55 of embodiment 7, and samples 98 to 103 were prepared through the same way as in the sample 61 of embodiment 7, except that the mean particle diameters of Fe powder and Fe-Si alloy powder were varied. These samples underwent the measurement of characteristics. The samples number 92 to 95, and those number 98 to 101 represent embodiments of the present invention; while the samples number 96, 97, 102 and 103 are examples for comparison. The packing rate of the magnetic powder fell within the range 85 - 95 % with all of the samples.

Table 9 shows the results of measurement.

TABLE 9

	Sample No.	Composition	Mean particle diameter	Magnetic permeability	Core loss (kW/m ³)
Embodi- ment	92	Fe	1	61	880
	93		10	63	790
	94		30	66	820
	95		50	69	980
	96		0.9	58	1300
Compara- son	97		65	70	2000
Embodi- ment	98	Fe-3.5Si	1	60	850
	99		10	61	740
	100		30	64	770
	101		50	67	980
Compara- son	102		0.8	67	1150
	103		60	58	1700

As clear from the results shown in Table 9, those samples whose mean particle diameter of the magnetic powder is not smaller than 1 μm not greater than 50 μm satisfy the standard for a choke coil described earlier in embodiment 7.

Since the eddy current loss increases in proportion to the square of frequency and the square of a flowing size of eddy current, it can be

suppressed by covering the surface of magnetic particle with an insulating material. The eddy current is dependent on particle diameter of the magnetic powder; the finer the particle the smaller the eddy current loss. With the choke coils for countermeasure against harmonic distortion, for example, the core loss is preferred to be 1000 kW/m³ or less, in the conditions of the current measuring frequency of 50 kHz and measuring magnetic flux density of 0.1 T. In order to reduce the eddy current loss at a frequency higher than 50 kHz, it is preferred that the mean particle diameter of the magnetic powder is not smaller than 1 μ m not greater than 50 μ m.

Further, in a case where a Fe-Si alloy powder containing Si for $\leq 7.5\%$ by weight and remainder of Fe is used, it exhibits excellent characteristics with a high magnetic permeability and a low core loss, in so far as the mean particle diameter of the alloy powder falls within a range not smaller than 1 μ m not greater than 50 μ m.

INDUSTRIAL APPLICABILITY

The present invention offers a composite magnetic body that exhibits a small core loss and a high magnetic permeability even when it is used in a high frequency band region. The composite magnetic body may be formed in various compression-formed core pieces of complex shapes.

CLAIMS

1. A composite magnetic body of a compressed compact comprising a mixture of a magnetic alloy powder containing iron and nickel as main components, a binder of a silicone resin for binding the magnetic alloy powder together, and a thermal diffusion inhibitor,

wherein a packing rate of the magnetic alloy powder in the compressed compact falls within a range of 88-95% by volume, and the compressed compact is heated at a temperature of 500 to 900°C in non-oxidizing atmosphere.

2. The composite magnetic body of claim 1, wherein a mean particle diameter of the magnetic alloy powder falls within a range of 1-100 μm .

3. A composite magnetic body of a compressed compact comprising a mixture of a magnetic alloy powder containing iron and nickel as main components, an insulating material and a binder of an acrylic resin for binding these together, said compressed compact being heated at a temperature of 500 to 900°C in non-oxidizing atmosphere.

4. A composite magnetic body of a compressed compact comprising a mixture of a magnetic iron powder or a magnetic alloy powder comprising 7.5% by weight or less (0% is not included) of silicon and remainder of iron, an insulating material and a binder of an acrylic resin for binding these together, said compressed compact being heated at a temperature of 500 to 900°C in non-oxidizing atmosphere.

5. The composite magnetic body of claim 3 or 4, wherein the insulating material is an organic silicon compound.

6. The composite magnetic body of claim 1, 3 or 4, wherein the compressed compact contains a fatty acid.

7. The composite magnetic body of claim 3 or 4, wherein a packing rate of the magnetic powder in the compressed compact falls within a range of 85-95% by volume.

8. The composite magnetic body of claim 3 or 4, wherein a mean particle diameter of the magnetic powder falls within a range of 1-50 μm .

9. The composite magnetic body of claim 3 or 4, wherein the compressed compact is heated at a temperature of 250-350°C in oxidizing atmosphere, and then further is heated at a temperature of 500-900°C in non-oxidizing atmosphere.