

2165474

An improved casting apparatus.

The use of a melt-out metal core of complex shape to provide a detailed internal configuration to a subsequently moulded part of plastics material is an area of developing technology, especially in the automobile industry. Such cores are made of a low melting point alloy and are removed from the moulded component by melting.

The prime requirement for these metallic cores is that they should provide accurate dimensional forms, as well as predetermined surface finishes. The metals from which such cores can be made have solidus temperatures in the range of 35 to 300°C.

There are a number of established methods of casting such alloys, ranging from simply pouring the liquid metal into a suitable metallic or non-metallic mould, either by hand or mechanically, through a range of various pressure devices to introduce the metal into the mould cavity, examples of which are centrifugal rubber mould casting, low pressure gravity die-casting, high pressure diecasting, and the Durville casting method.

For the present application it has been found by experience that none of the available techniques provides castings with specific required characteristics of dimensional tolerance, surface finish and lack of internal porosity or cavitation. While diecasting as normally practised produces a good surface finish, there is a tendency to porosity in the castings which is unacceptable in the above-mentioned cores.

The object of the invention is to enable low melting point alloys with solidus temperatures in the range 35 - 300°C to be accurately and reproducibly cast.

According to this invention an apparatus for producing a casting from a low melting point alloy having a solidus temperature in the range of 35 to 300°C, comprises a die, a tank capable of containing the metal to be cast in a molten condition, a cylinder positioned so it can be immersed in the metal in the tank and having at one end an inlet to enable it to fill with the metal and at the other end an outlet communicating with the die, a piston in the cylinder, an outlet valve controlling said outlet and a control system operable to impart to the piston, in successive operating cycles, a preliminary stroke starting from an initial position and sufficient for it to close the inlet while the outlet valve is closed so as to enable it to subject molten metal in the cylinder to pre-pressurization, thereafter to open the outlet valve, thereafter to impart a further stroke to the piston to enable it to deliver molten metal at a flow rate of 0.1 to 1 kg/sec from the cylinder and through the outlet valve into the die, the outlet valve remaining open to enable the metal to be maintained within the die under pressure for a period longer than that required to fill the die, and thereafter to close the outlet valve and return the piston to its initial position in readiness for a further cycle of operations.

One embodiment of the invention is illustrated diagrammatically in the accompanying diagrammatic drawing.

It includes a tank 8 containing liquid metal and a

(2)

- 2a -

dispensing cylinder 11, having an inlet 10 for liquid at its upper end and an outlet 16 at its lower end which is connected to a lock-off valve 12. The upper end of the cylinder 11 is disposed below the level 8A of liquid in the tank. Operating within the dispensing cylinder 11 is a piston 9 connected to a piston

5

rod 4, carrying a stop bracket 6, which rod is actuated by a pneumatic or hydraulic cylinder 3.

The cylinder 3 is movable by means of a toggle system 2 actuated by a pneumatic or hydraulic cylinder 1
5 and constrained to move vertically by a guide 5.

The outlet 16 controlled by the valve is connected to a nozzle 13, to the outlet 13A of which, before commencement of a casting cycle, a die 15 is brought into sealing engagement. When the die 15 is to
10 be filled from the side or from below, it is fitted with a valve 14 for retaining liquid metal within it. When provided the valve 14 is opened and closed simultaneously with the valve 12. A microprocessor 17 is provided for effecting sequential operation of the cylinders 1,3
15 and the valves 12 and 14. Alternatively the cylinders 1, 3 and the valves 12,14 may be actuated by a pneumatic control system including solenoids.

At the start of the casting cycle the valve 12 is closed. The microprocessor 17 first causes the
20 cylinder 1 to close the toggle system 2 and move the piston 9 downwardly to an extent sufficient to cover the liquid metal inlet 10 of the cylinder 11. This serves to effect pre-pressurisation of liquid metal in the cylinder and thus avoids any gravitational surge of metal
25 into the die 15 at a later stage. The valve 12 is then opened and the cylinder 3 is actuated to cause metal to be dispensed into the die 15 by means of the piston 9 until the stop bracket 6 contacts a fixed stop bracket 7.

As the flow rate of metal is critical, it is
30 important that the valve 12 should not open until the piston 9 has closed the inlet 10. This prevents any free fall of metal once the valve 12 is opened. Typical pressures exerted on the column of metal to be delivered are 0.25 - 3.0 bar.

The volume of liquid metal delivered to the die depends on the position of adjustment of the stop 6 on the rod 4.

5 After the piston 9 has completed its downward stroke, the valve 12 is held open for a dwell time exceeding the time required for the delivery stroke of the piston 9, so maintaining the metal in the die 15 under pressure until solidification.

10 The valve 12 then closes and the piston 9 is returned to its initial position in preparation for the next casting cycle.

The die 15 is normally maintained in sealing engagement with the injection mechanism for a time after the valve 12 has closed, to ensure that the 15 still molten inner portion of the casting does not melt its way out. However, it may be required in some cases to cast a hollow core for special conditions of the subsequent plastics moulding. In this case, the seal may immediately be broken to allow part of the 20 molten metal to drain out of the casting.

The stops 6 and 7 need not necessarily be a single mechanical device but may include a proximity switch and/or electro optical technique.

25 A "swan-neck" 13B in the through passageway of the nozzle 13 ensures that at the end of the stroke of piston 9 and the closing of the valve 12, the liquid metal runs out until the "knife edge" of the "swan-neck" is reached at which point no more metal is released and there is a positive cut off with no dripping.

30 The apparatus described may constitute an adjunct to a plastics moulding machine, the core metal melted out after the plastics moulding operation being returned to the tank 8, the level in which is maintained high enough to cover the inlet 10.

35 In one example of use of the apparatus for casting a core of a plastics automobile pump, the composition

of the metal in the tank 8 was 56% tin, 3% antimony, the balance lead, the tank was maintained at a temperature of 200-230°C and the die 15 at a temperature of 50-70°C. The weight of each cast core was 0.6 kg. The duration
 5 of the second and delivery stroke of the piston 9 was 3 seconds and the dwell time after delivery and before closing of the valve 12 was 7-12 seconds.

In another example of use of the apparatus for casting a core of an automobile injection manifold
 10 the metal in the tank 8 was a eutectic alloy of bismuth and tin, the tank was maintained at a temperature of 180°C and the die at a temperature of 35°C, the weight of each cast core was 20 kg, the duration of the delivery stroke of the piston 9 was 35 seconds and the dwell
 15 time was 8 seconds.

It is useful in some cases, e.g. the casting of a core for a plastics automobile intake manifold, to use in the tank 8 a number of injection cylinders 11 and pistons 9 operating as described above to deliver
 20 molten metal simultaneously, each to the inlet of a different die.

CLAIMS:

1. Apparatus suitable for producing a casting from a metal alloy having a solidus temperature in the range of 35 - 300°C, comprising a die, a tank capable of containing the metal to be cast in a molten
5 condition, a cylinder positioned so it can be immersed in the metal in the tank and having at one end an inlet to enable it to fill with the metal and at the other end an outlet communicating with the die, a piston in the cylinder, an outlet valve controlling said outlet
10 and a control system operable to impart to the piston, in successive operating cycles, a preliminary stroke starting from an initial position and sufficient for it to close the inlet while the outlet valve is closed so as to enable it to subject molten metal in the cylinder
15 to pre-pressurization, thereafter to open the outlet valve, thereafter to impart a further stroke to the piston to enable it to deliver molten metal at a flow rate of 0.1 to 1 kg/sec from the cylinder and through the outlet valve into the die, the outlet valve
20 remaining open to enable the metal to be maintained within the die under pressure for a period longer than that required to fill the die, and thereafter to close the outlet valve and return the piston to its initial position in readiness for a further cycle of
25 operations.

2. Apparatus according to claim 1, which includes between the outlet valve and the die a nozzle having a through passageway, a swan-neck providing



positive cut-off of the flow of molten metal through the nozzle.

3. Apparatus according to either of claims 1 and 2, wherein the die has an inlet valve arranged to be opened and closed simultaneously with the outlet valve of the cylinder.
4. Apparatus according to any one of the preceding claims, comprising first and second power actuators for respectively imparting to the piston its outlet-closing and metal delivery strokes, the second power actuator being a power cylinder aligned with the piston and movable bodily by the first power actuator to impart the delivery stroke.
5. Apparatus according to claim 4, wherein the first power actuator is power cylinder connected to the second power actuator by a toggle linkage.
6. Apparatus according to claim 1, substantially as described herein with reference to the accompanying drawing.

