

Description

This invention relates to an optical fiber and to a process for producing the same and, more particularly, to an optical fiber having a cladding comprising fluorine-containing quartz glass around a core glass and to a process for producing the same.

In optical fibers composed of quartz glass materials, in order to obtain fibers having a high numerical aperture (NA) by increasing a difference of refractive index (Δn) between a core and a cladding and to use pure SiO_2 glass having excellent radiation resistance as a core material, it is heretofore known to use quartz glass containing fluorine which decreases the refractive index of the quartz glass as a material for the cladding, as disclosed in, for example, U.S. patents 4,082,420 and 4,161,505. However, quartz glass containing a large amount of fluorine, though having a decreased refractive index by, for example, 0.5% than that of pure SiO_2 glass, is soft as reported by K. Rau et al., Topical Meeting on Optical Fiber Transmission (1977), and likely to be scratched and also inferior in terms of chemical resistance and the like.

In order to overcome the above-described disadvantage, it has been proposed that a fiber preform composed of a glass rod 1 for a core and a glass layer 3 for a cladding as shown in Fig. 1 is inserted in a quartz tube and united into one body, thereby to form a fiber preform having a quartz-jacketed structure 5 as shown in Fig. 2. However, this improved process has many problems such that bubbling frequently occurs from the interface between the cladding and the jacket upon uniting the fiber preform with the quartz tube; the fiber diameter tends to vary or breaking of the fiber occurs upon drawing jacketed preform; and the like. Further, when a plurality of fibers prepared from the preform as shown in Fig. 1 are bundled up to constitute an image fiber, etc., a bubbling phenomenon is frequently observed in a collapsing step for uniting the fiber into a bundle, thus making it difficult to obtain satisfactory products.

Accordingly, an object of the present invention is to provide an optical fiber having a high numerical aperture and excellent radiation resistance.

Another object of the present invention is to provide a process for producing an optical fiber which lessens the troubles such as variation of the outer diameter, breaking, bubbling, etc.

A further object of the present invention is to provide a process for producing an optical fiber which does not cause air bubbles during a collapsing step in the production of image fibers or light guides from a fiber bundle.

A still further object of the present invention is to provide a process for producing an optical fiber which makes it possible to produce image fibers, etc., free from the lack of picture elements or dark spots.

GB-A-2105488 discloses a single-mode

optical fibre comprising a core of pure silica (or pure silica lightly doped with Ge) concentrically surrounded by a fluorine-containing quartz glass cladding. This cladding is composed of an inner cladding having a constant fluorine content through its thickness and an outer cladding whose fluorine content is smaller than that of the inner cladding. The outer cladding has a refractive index intermediate in value between the refractive indices of the core and the inner cladding. The optical fibre may include a further cladding, for instance, derived from a fused silica preform starting tube (see Figure 2).

If the difference in refractive index between a silica outer cladding (22) and the further cladding (23) in Fig. 2 is 0.4% or more, gas bubbles tend to remain at the boundary and thus it is very difficult to satisfactorily produce such a structure.

According to the present invention and to meet the aforesaid objects, we provide an optical fibre having a core comprising silica glass which may contain a dopant and having therearound a cladding comprising fluorine-containing quartz glass and composed of inner and outer portions, the inner portion having a prescribed thickness and a constant fluorine content through said thickness, characterized in that in said cladding the outer portion has its fluorine content gradually decreasing in a radial direction towards its outer surface so that its outermost surface has a fluorine content of about 0.7% by weight or below relative to the SiO_2 .

We also provide a process for producing this optical fiber.

The term Δn_1 is used herein to refer to a difference in refractive index between the inner and outer portions of the cladding.

In the accompanying drawings:

Figs. 1 and 2 each shows a structure of a conventional fiber preform with a distribution of the refractive index thereof;

Figs. 3 and 4 show an embodiment of the present invention, in which a fiber preform for producing an optical fiber is illustrated with a distribution of the refractive index thereof;

Figs. 5 and 6 show another embodiment of the present invention, in which a fiber preform for producing an optical fiber is illustrated with a distribution of the refractive index thereof;

Fig. 7 is a partial enlargement of Fig. 4;

Fig. 8 is a graph showing a preferred relationship between a difference in refractive index and thickness of an outer portion of a cladding according to the present invention.

Examples of dopants which can be used for the core glass according to the present invention are GeO_2 , P_2O_5 , Al_2O_3 and TiO_2 , preferably GeO_2 . For example, in a step-index type fiber, GeO_2 can be generally added in the range of from about 15 wt% to about 40 wt%, based on the weight of core glass. In an embodiment hereinafter described in Example 3, GeO_2 is present in an amount of about 18 wt% to a peripheral portion of the core glass rod and in an amount of 36 wt% in a center portion of the core glass rod, based on

the weight of core glass rod.

The inner portion of the cladding generally contain fluorine in an amount of about 1.5 wt% to about 4 wt% based on the weight of quartz glass.

The thickness proportion (t/t_0) between the inner portion (t_0) of cladding where the fluorine content is constant and the outer portion (t) of cladding where the fluorine content gradually decreases in a radial direction, is generally in the range of 0.04 to 0.2.

The thickness of cladding and jacket, if any, relative to the core diameter, can be varied widely. In a fiber comprising a core and a cladding, the thickness of cladding is generally in the range of from 1/20 to 1/2 times the core diameter. The thickness of jacket can be typically in the range of about 1 to about 3 times the thickness of the cladding, but the present invention is not limited to the above proportions.

In a glass rod comprising a core and cladding, the thickness of the cladding where the fluorine content is constant is preferably 5 to 50% based on the core diameter. For example, when the core has a diameter of 25 mm and the cladding has a total thickness of 5 mm, the outer portion of the cladding (t) is preferably 0.2 to 1.25 mm. The difference in the refractive index (Δn_1) between the inner portion of the cladding and the outer portion of cladding is preferably about 0.4% to about 1.2%. For example, when the outer portion of the cladding has a thickness of 0.2 mm, the difference in the refractive index (Δn_1) is preferably about 0.4% or more, and when the outer portion of the cladding is about 1.2 mm, the difference (Δn_1) is preferably about 1.2%.

The optical fiber prepared by drawing the glass rod generally has a diameter of about 100 μ m to about 500 μ m, typically 125 μ m, 140 μ m, 150 μ m or 280 μ m as standards.

The present invention will be illustrated in greater detail with reference to the accompanying drawings.

Figs. 3 through 8 show embodiments according to the present invention illustrating a process for producing a fiber of the invention. In Figs. 3 and 4, GeO_2 -containing SiO_2 glass is used as a glass rod 1 for a core aiming at production of a high NA fiber or a high luminance image fiber. In Figs. 5 and 6, high purity SiO_2 glass is used as a glass rod 1 for a core aiming at production of a radiation resistant fiber or a radiation resistant image fiber.

In manufacturing fiber preforms according to the present invention, a fluorine-doped SiO_2 glass layer 3 is formed around the glass rod 1 as a cladding as shown in Figs. 3 and 5. Formation of the fluorine-doped SiO_2 glass layer can be carried out by, for example, introducing a fluorine-containing gas, e.g., CCl_2F_2 or CF_4 , SiCl_4 and O_2 to high frequency plasma flame to produce fluorine-doped glass in the plasma flame, blowing the fluorine-doped glass in a molten state onto the periphery of the rotating and reciprocating glass rod 1 to accumulate a glass film, and repeating the accumulation until the glass layer thus formed reaches a prescribed thickness (Figs. 3 and 5). In

this step, a proportion of the fluorine-containing gas to the other starting gases is maintained substantially constant so as to give a substantially constant fluorine content to the accumulated glass layer throughout its thickness. For the sake of convenience, this portion of the glass layer 3 which has a constant fluorine content through its thickness will be hereinafter referred to as "inner portion".

Then, the gaseous phase fluorine concentration to be introduced to plasma flame is gradually reduced with the passage of time while continuing accumulation of glass film so that the composition of the thus accumulated glass film is gradually changed in such a manner that the final fluorine content in the outermost surface becomes almost zero. For the sake of convenience, this portion of the glass layer 3 having a gradually decreased fluorine content in its radial direction will be referred to as "outer portion". Thus, by decreasing the fluorine content in the outer portion of the glass layer 3 to a final content of zero in the outermost surface, the refractive index of the fiber preform thus produced and also fibers obtained therefrom shows an uneven distribution as shown in Figs. 4 and 6. If the rate of decreasing the fluorine content in the outer portion of the glass layer is too high, bubbles are likely to generate on the surface of the preform during the formation of the glass layer for cladding. In this connection, Figs. 7 and 8 show a relationship between a glass thickness (t) and a difference of refractive index (Δn_1) in the outer portion wherein a fluorine content is changed. In order to avoid the above-described generation of bubbles, a preferred range of this relationship is indicated by slant lines in Fig. 8.

The resulting fiber preform having the fluorine content in the outer portion of the glass cladding being varied is then drawn to obtain a desired fiber without causing problems such as variation of diameter, breaking etc. Further, when the above fiber preform is inserted in a quartz tube and united therewith into a jacketed structure, bubbles are not produced between the cladding and the jacket, and the preform having the jacketed structure can be drawn to form fibers without substantially causing troubles such as variation of diameter, breaking etc. Furthermore, when a plurality of the fibers prepared from the above preforms are bundled up to constitute image fibers, etc., air bubbles are not formed during the collapsing step and satisfactory products can be obtained.

It is thought that the prevention of production of bubbles in the cladding-jacket interface according to the present invention results from the following mechanism. That is, fluorine-doped quartz glass has a lower viscosity and melts at a lower temperature as compared with quartz glass. Therefore, in the case of melting both the glass highly doped with fluorine and quartz glass under a high temperature condition to meet-fusing the boundary surface, it is necessary to maintain a temperature at which both of them are

co-melting, i.e., about 1600°C. In this situation, though the fluorine-doped glass *per se* has a considerably reduced viscosity and is in a molten state to a high extent, SiF₄, an easily vaporable component, is vaporized to give a high vapor pressure and comes to be present between the two phases. To the contrary, according to the present invention wherein the composition of the glass cladding is varied by degrees until it becomes near to that of quartz glass in its outermost surface which is to be melted together with the quartz glass tube, the vapor pressure of SiF₄ is supposed to be suppressed so that no gas be present in the interface, thus preventing formation of bubbles.

The present invention has been described for the embodiment where substantially no fluorine is present in the outermost surface of the cladding, but it is to be understood that the object of the present invention can be achieved by decreasing the fluorine content to about 0.7% by weight or below, and the refractive index ratio to 0.2% or more with respect to SiO₂. Also, in another embodiment, an additional pure silica layer can be provided over the outermost layer of the cladding having no fluorine content. These embodiments are also within the scope of this invention.

The present invention will now be illustrated in greater detail by way of the following test examples.

Example 1

Into high pressure plasma flame (output power 3.4 MHz, 6 kV, 2.3 A) were introduced CCl₂F₂ and SiCl₄ at rates of 300 cc/min and 400 cc/min, respectively, and the flame flow was directed to a rotating and reciprocating starting quartz glass rod for a core having a diameter of 25 mm and a length of 200 mm, thereby to form a glass layer around the periphery of the rod. At the point when the diameter of the glass layer thus formed reached 35 mm, the rates of introducing CCl₂F₂ and SiCl₄ were gradually reduced by 10 cc/min and 8 cc/min, respectively, each time the rod reciprocated. Finally, the rate of introducing CCl₂F₂ became 0, and that of SiCl₄ was decreased to 160 cc/min. The thickness of layer where the fluorine content gradually decreased was 1 mm. The thus obtained core having therearound an accumulated glass layer as a cladding was drawn in a drawing furnace set at about 2,000°C into a fiber having an outer diameter of 140 μm. The resulting fiber showed a variation of outer diameter almost within ±0.5 μm. The fiber (140 μmφ) was cut into a length of 30 cm, and 5,000 cut fibers were bundled up. The fiber bundle was inserted in a quartz tube and then united therewith by heating the outside of the quartz tube by use of an H₂/O₂ burner to prepare a united bundle (preform) for an image fiber. The resulting preform had an almost transparent appearance substantially free from incorporation of bubbles. When this preform was drawn so as to have an outer diameter of 3 mm to form an image fiber, a satisfactory image fiber substantially free from lack of picture elements could be produced.

Example 2

The core-cladding structure as obtained in Example 1 was drawn so as to have an outer diameter of 7.5 mm and inserted into a quartz tube having an outer diameter of 15 mm and an inner diameter of 10 mm. The quartz glass tube was heated by an H₂/O₂ burner for uniting, thereby obtaining a transparent core-cladding-jacket structure entirely free from bubbles. The resulting structure was drawn in a drawing furnace set at a temperature of about 2,000°C to obtain an optical fiber having an outer diameter of 250 μm. The resulting optical fiber showed a variation of diameter of within ±1 μm and a difference in refractive index between the core and the cladding (Δn₀) of 0.9% and was excellent in radiation resistance, strength and weather resistance.

Example 3

An image fiber was prepared in the same manner as in Example 1 except for using, as a core glass, a GeO₂-containing glass rod having an outer diameter of 25 mm and a difference of refractive index of 2% from that of quartz glass in its central portion. The difference of refractive index (Δn₀) between the core and the cladding of the resulting image fiber was about 3%, and the image fiber gave an extremely bright image without any lack of picture elements, dark spots, etc.

Claims

1. An optical fiber having a core comprising silica glass which may contain a dopant and having therearound a cladding comprising fluorine-containing quartz glass and composed of inner and outer portions, the inner portion having a prescribed thickness and a constant fluorine content through said thickness, characterized in that in said cladding the outer portion has its fluorine content gradually decreasing in a radial direction towards its outer surface so that its outermost surface has a fluorine content of about 0.7% by weight or below relative to the SiO₂.

2. A process for producing an optical fiber as claimed in Claim 1, which comprises forming an inner portion of a quartz glass layer for a cladding containing a prescribed amount of fluorine around the periphery of a glass rod for a core to a prescribed thickness, forming an outer portion of a quartz glass layer for a cladding around the periphery of the inner portion while gradually decreasing the fluorine content of the fluorine-containing quartz glass layer to about 0.7% by weight or below relative to SiO₂ in the outermost surface of the quartz glass layer by accumulating glass films which are formed by introducing a fluorine-containing gas into a high frequency plasma flame, and drawing the resulting structure comprising a core and cladding so as to have a prescribed diameter.

3. A process as claimed in Claim 2, wherein the core-cladding structure is inserted in a quartz glass tube, the structure is united with said quartz glass tube by heating to form a core-cladding-jacket

co-melting, i.e., about 1600°C. In this situation, though the fluorine-doped glass *per se* has a considerably reduced viscosity and is in a molten state to a high extent, SiF_4 , an easily vaporable component, is vaporized to give a high vapor pressure and comes to be present between the two phases. To the contrary, according to the present invention wherein the composition of the glass cladding is varied by degrees until it becomes near to that of quartz glass in its outermost surface which is to be melted together with the quartz glass tube, the vapor pressure of SiF_4 is supposed to be suppressed so that no gas be present in the interface, thus preventing formation of bubbles.

The present invention has been described for the embodiment where substantially no fluorine is present in the outermost surface of the cladding, but it is to be understood that the object of the present invention can be achieved by decreasing the fluorine content to about 0.7% by weight or below, and the refractive index ratio to 0.2% or more with respect to SiO_2 . Also, in another embodiment, an additional pure silica layer can be provided over the outermost layer of the cladding having no fluorine content. These embodiments are also within the scope of this invention.

The present invention will now be illustrated in greater detail by way of the following test examples.

Example 1

Into high pressure plasma flame (output power 3.4 MHz, 6 kV, 2.3 A) were introduced CCl_2F_2 and SiCl_4 at rates of 300 cc/min and 400 cc/min, respectively, and the flame flow was directed to a rotating and reciprocating starting quartz glass rod for a core having a diameter of 25 mm and a length of 200 mm, thereby to form a glass layer around the periphery of the rod. At the point when the diameter of the glass layer thus formed reached 35 mm, the rates of introducing CCl_2F_2 and SiCl_4 were gradually reduced by 10 cc/min and 8 cc/min, respectively, each time the rod reciprocated. Finally, the rate of introducing CCl_2F_2 became 0, and that of SiCl_4 was decreased to 160 cc/min. The thickness of layer where the fluorine content gradually decreased was 1 mm. The thus obtained core having therearound an accumulated glass layer as a cladding was drawn in a drawing furnace set at about 2,000°C into a fiber having an outer diameter of 140 μm . The resulting fiber showed a variation of outer diameter almost within $\pm 0.5 \mu\text{m}$. The fiber (140 $\mu\text{m}\phi$) was cut into a length of 30 cm, and 5,000 cut fibers were bundled up. The fiber bundle was inserted in a quartz tube and then united therewith by heating the outside of the quartz tube by use of an H_2/O_2 burner to prepare a united bundle (preform) for an image fiber. The resulting preform had an almost transparent appearance substantially free from incorporation of bubbles. When this preform was drawn so as to have an outer diameter of 3 mm to form an image fiber, a satisfactory image fiber substantially free from lack of picture elements could be produced.

Example 2

The core-cladding structure as obtained in Example 1 was drawn so as to have an outer diameter of 7.5 mm and inserted into a quartz tube having an outer diameter of 15 mm and an inner diameter of 10 mm. The quartz glass tube was heated by an H_2/O_2 burner for uniting, thereby obtaining a transparent core-cladding-jacket structure entirely free from bubbles. The resulting structure was drawn in a drawing furnace set at a temperature of about 2,000°C to obtain an optical fiber having an outer diameter of 250 μm . The resulting optical fiber showed a variation of diameter of within $\pm 1 \mu\text{m}$ and a difference in refractive index between the core and the cladding (Δn_0) of 0.9% and was excellent in radiation resistance, strength and weather resistance.

Example 3

An image fiber was prepared in the same manner as in Example 1 except for using, as a core glass, a GeO_2 -containing glass rod having an outer diameter of 25 mm and a difference of refractive index of 2% from that of quartz glass in its central portion. The difference of refractive index (Δn_0) between the core and the cladding of the resulting image fiber was about 3%, and the image fiber gave an extremely bright image without any lack of picture elements, dark spots, etc.

Claims

1. An optical fiber having a core comprising silica glass which may contain a dopant and having therearound a cladding comprising fluorine-containing quartz glass and composed of inner and outer portions, the inner portion having a prescribed thickness and a constant fluorine content through said thickness, characterized in that in said cladding the outer portion has its fluorine content gradually decreasing in a radial direction towards its outer surface so that its outermost surface has a fluorine content of about 0.7% by weight or below relative to the SiO_2 .

2. A process for producing an optical fiber as claimed in Claim 1, which comprises forming an inner portion of a quartz glass layer for a cladding containing a prescribed amount of fluorine around the periphery of a glass rod for a core to a prescribed thickness, forming an outer portion of a quartz glass layer for a cladding around the periphery of the inner portion while gradually decreasing the fluorine content of the fluorine-containing quartz glass layer to about 0.7% by weight or below relative to SiO_2 in the outermost surface of the quartz glass layer by accumulating glass films which are formed by introducing a fluorine-containing gas into a high frequency plasma flame, and drawing the resulting structure comprising a core and cladding so as to have a prescribed diameter.

3. A process as claimed in Claim 2, wherein the core-cladding structure is inserted in a quartz glass tube, the structure is united with said quartz glass tube by heating to form a core-cladding-jacket



structure, and said core-cladding jacket structure is drawn so as to have a prescribed diameter.

Patentansprüche

1. Optische Faser, die einen Kern aus Siliciumoxid-Glas enthält, welches ein Dotierungsmittel enthalten kann und darum herum eine Verkleidung, die fluorhaltiges Quarz-Glas enthält, aufweist und aus inneren und äusseren Teilen zusammengesetzt ist, wobei der innere Teil eine vorbestimmte Dicke und einen Konstanten Fluorgehalt durch die genannte Dicke aufweist, dadurch gekennzeichnet, dass in der genannten Beschichtung der äussere Teil einen Fluorgehalt besitzt, welcher graduell in radialer Richtung gegen die äussere Oberfläche abnimmt, so dass seine äusserste Oberfläche einen Fluorgehalt von etwa 0,7 Gew.-% oder weniger, bezogen auf das SiO_2 , aufweist.

2. Verfahren zur Herstellung einer optischen Faser gemäss Anspruch 1, umfassend die Bildung eines inneren Teiles einer Quarz-Glasschicht für eine Verkleidung, welche einen vorgeschriebenen Fluorgehalt um die Peripherie eines Glasstabes für einen Kern enthält in vorgeschriebener Dicke, Bildung eines äusseren Teils einer Quarz-Glasschicht für die Verkleidung rund um die Peripherie des inneren Teils, wobei der Fluorgehalt der fluorhaltigen Quarz-Glasschicht graduell auf etwa 0,7 Gew.-% oder weniger, bezogen auf das SiO_2 , in der äussersten Oberfläche der Quarz-Glasschicht abnimmt, indem Glasfilme akkumuliert werden, welche durch Einführung eines Fluor enthaltenden Gases in einer Hochfrequenz-Plasmaflamme gebildet werden und Ziehen der resultierenden Struktur, welche einen Kern und eine Verkleidung aufweist, bis sie den vorgeschriebenen Durchmesser aufweist.

3. Verfahren gemäss Anspruch 2, worin die Kernverkleidungs-Struktur in ein Quarz-Glasrohr eingesetzt wird, die Struktur mit dem genannten Quarz-Glasrohr durch Erwärmen vereinigt wird, wobei eine Kernverkleidung-Mantelstruktur gebildet wird und die genannte Kernverkleidungs-

Mantelstruktur gezogen wird, bis sie den vorgeschriebenen Durchmesser aufweist.

Revendications

1. Fibre optique ayant un noyau comprenant du verre silicieux qui peut contenir un agent de dopage et qui est entouré d'une gaine comprenant du verre de quartz contenant du fluor et qui est composée de parties intérieure et extérieure, la partie intérieure ayant une épaisseur prescrite et une teneur en fluor constante à travers toute la dite épaisseur, caractérisée en ce que la portion extérieure dans la dite gaine a une teneur en fluor qui diminue graduellement en direction radiale vers sa surface extérieure de sorte que sa surface extérieure extrême présente une teneur en fluor d'environ 0,7% en poids ou moins par rapport au SiO_2 .

2. Procédé de fabrication d'une fibre optique selon la revendication 1, qui consiste entre autres à former d'une couche de verre de quartz une partie intérieure de gaine contenant une quantité prescrite de fluor et à épaisseur prescrite, autour de la périphérie d'une tige de verre de noyau, à former d'une couche de verre de quartz une partie extérieure de gaine autour de la périphérie de la partie intérieure, tandis qu'on diminue graduellement la teneur en fluor de la couche de verre de quartz à contenance de fluor jusqu'à environ 0,7% en poids ou moins par rapport au SiO_2 dans la surface extérieure extrême de la couche de verre de quartz, par accumulation des films de verre qui se forment par introduction d'un gaz contenant du fluor dans une flamme plasmatique à haute fréquence, et à tirer la structure résultante comprenant un noyau et une gaine jusqu'à ce qu'elle ait le diamètre prescrit.

3. Procédé selon la revendication 2, dans lequel la structure corps-gaine est insérée dans un tube de verre de quartz, la structure est unie au tube de verre de quartz en la chauffant pour former une structure noyau-gaine-enveloppe, et la dite structure noyau-gaine enveloppe est tirée jusqu'à elle soit d'un diamètre prescrit.

