Claims

What is claimed is:

1. A crumb for forming a bale, which is of a conjugated diene polymer, wherein the crumb has a specific surface area of 0.7 m^2/g to 3.2 m^2/g, and the conjugated diene polymer is a random copolymer of an aromatic vinyl compound and a conjugated diene compound, and a component that does not pass through a sieve with an aperture size of 4.0 mm is comprised at least 20 % by mass of the whole crumb.

2. The crumb for forming a bale according to claim 1, wherein the conjugated diene polymer contains 30 to 90 % by mass of a component having a molecular weight of 1 million or more.

3. The crumb for forming a bale according to claim 1 or 2, which contains 1 to 20 parts by mass of process oil with respect to 100 parts by mass of the conjugated diene polymer.

4. A bale of a conjugated diene polymer, wherein the bale has a specific surface area of 0.005 m^2/g to 0.05 m^2/g, wherein the conjugated diene polymer is a random copolymer of an aromatic vinyl compound and a conjugated diene compound.

5. A method for producing a bale by preparing a crumb of a conjugated diene polymer, wherein the crumb has a specific surface area of 0.7 m^2/g to 3.2 m^2/g, and compression molding the crumb,
wherein the conjugated diene polymer is a random copolymer of an aromatic vinyl compound and a conjugated diene compound, and the crumb is a random copolymer, and a component that does not pass through a sieve with an aperture size of 4.0 mm is comprised at least 20 % by mass of the whole crumb.

6. The method for producing a bale according to claim 5, further comprising a step of sieving the crumb of the conjugated diene polymer.