

DESCRIPTION



166166

ANTIFOULING PAINT COMPOSITION



G00001

TECHNICAL FIELD

The present invention relates to an antifouling paint composition. More particularly, it relates to an antifouling paint composition which is capable of inhibiting attachment and accumulation of marine organisms and seaweeds on the underwater structures, fishing nets and the ship bottom.

BACKGROUND ART

The submerged portions of the ships and marine structures are provided with an antifouling coating containing rosin or organic tin for the purpose of preventing corrosion or the drop of cruising speed of the ships due to attachment of marine creatures such as barnacles, teredos, and algae. Such an antifouling coating is also provided on the nets used at the nurseries of fishes or marine products for the purpose of preventing fatal effect on the reared fishes and shellfishes by the attachment of marine organisms on the nets.

The antifouling effect of these antifouling coatings is demonstrated as the rosin and antifouling substance(s) contained in the coating are eluted into

seawater. Therefore, when the coating is left immersed in seawater for a long period of time, the eluting substance is gradually decreased while the non-eluting matter is left in the coating, and at the same time the coating surface becomes jagged, which tends to excessively reduce the effect of the coating to prevent attachment and accumulation of marine organisms. In the case of organotin-containing self polishing type paint, the coating surface is gradually dissolved away to constantly renew the surface so that the antifouling substance will be always kept exposed on the coating surface to allow long-time retention of its antifouling effect. This type of antifouling paint, however, has a possibility to give baneful influence to fishes and shellfishes because of strong toxicity of organic tin contained therein. Thus, request is intensifying in the industry for the development of a self polishing type antifouling paint composition which is low in toxicity and capable of exhibiting its antifouling effect in the sea for a prolonged period of time. Many studies have been made on the self polishing type paints free of organic tin. For example, JP-A-62-57464 and JP-A-62-84168 describe the antifouling paint compositions using the copolymers having a metal-containing group at the end of the side chain. Also, JP-A-5-171066 discloses an antifouling paint composition containing a copolymer comprising a metal-containing monomer having 2 to 3 double bonds, as a vehicle.

However, the antifouling paints using metal-containing copolymers such as described in JP-A-62-57464 and JP-A-62-84168 mentioned above are reduced in their self polishing action with time, so that their antifouling effect can hardly last for a long period of time. If the metal content per polymer molecular weight is increased for improving the self polishing characteristics of these antifouling paints, the formed coating becomes hard and frail and tends to develop cracks or exfoliate.

On the other hand, the antifouling paint using a copolymer such as described in JP-A-5-171066, although capable of maintaining its self polishing action for a long period of time tends to have an insufficient rate of consumption of the coating, hence is not necessarily satisfactory in long-time antifouling effect of coating. Also, the foamed coating tends to become hard and fragile with the lapse of time, and further this type of paint is unsatisfactory in its recoatability on the old coating formed from an organotin-based paint and so on, so that the recoating film tends to crack or exfoliate.


DISCLOSURE OF THE INVENTION

An object of the present invention is to provide a self polishing type antifouling paint composition which is capable of displaying an excellent antifouling effect in seawater for a prolonged period of time and also shows excellent crack resistance and

recoating properties on the old coating formed from an organotin-based paint and so on.


As a result of extensive studies on the subject matter, the present inventors found that an antifouling paint containing as vehicle a metal-containing copolymer consisting of specific polymerizable monomers is capable of maintaining an excellent antifouling effect in seawater for a long period of time and also has excellent recoatability on the old coating formed from an organotin-based paint and so on.

The present invention provides an antifouling paint composition containing as vehicle a copolymer from a mixture of (a₁) a metal-containing polymerizable monomer having two unsaturated groups and (a₂) a metal-containing monomer represented by the following formula (I):



wherein R¹ represents a hydrogen atom or a methyl group; M represents Mg, Zn or Cu; and R² represents an organic acid residue.

The present invention also provide an antifouling paint composition containing as vehicle a copolymer from a mixture of (a) a metal-containing polymerizable monomer and (b) a polymerizable monomer represented by the following formula (II):



wherein R³ represents a hydrogen atom or a methyl group;
 R⁴ represents an alkyl group having 1 to 10 carbon atoms,
 5 a cycloalkyl group or a phenyl group; and R⁵ represents
 an alkyl group having 1 to 10 carbon atoms, a cycloalkyl
 group or a phenyl group.

BEST MODE FOR CARRYING OUT THE INVENTION

10 The metal-containing polymerizable monomer (a)
 used as a constituent of the copolymer serving as a
 vehicle in the present invention is a substance which can
 afford a long-lasting high self polishing characteristics
 to the formed coating and also shows an excellent
 15 antifouling effect. Preferably, it is selected from the
 metal-containing polymerizable monomers (a₁) having two
 unsaturated groups or the metal-containing polymerizable
 monomers (a₂) represented by the formula (I) shown above.

Examples of the metal-containing polymerizable
 20 monomers (a₁) having two unsaturated groups usable in the
 present invention include magnesium acrylate
 $[(\text{CH}_2=\text{CHCOO})_2\text{Mg}]$, magnesium methacrylate $[\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}]_2$
 $\text{Mg}]$, zinc acrylate $[(\text{CH}_2=\text{CHCOO})_2\text{Zn}]$, zinc methacrylate
 $[(\text{CH}_2=\text{C}(\text{CH}_3)\text{COO})_2\text{Zn}]$, copper acrylate $[(\text{CH}_2=\text{CHCOO})_2\text{Cu}]$, and
 25 copper methacrylate $[(\text{CH}_2=\text{C}(\text{CH}_3)\text{COO})_2\text{Cu}]$. These metal-

containing polymerizable monomers (a₁) may be used either singly or as a mixture of two or more of them as required. Zinc (meth)acrylate is especially preferred. When the term "(meth)acrylate" is used in the present specification, it means "acrylate or methacrylate".

The metal-containing polymerizable monomers (a₁) usable in the present invention are those represented by the above-shown formula (I). In the formula (I), R¹ represents a hydrogen atom or a methyl group; M represents Mg, Zn or Cu as a metal; and R² represents an organic acid residue. The organic acid residues include, for instance, those derived from monovalent organic acids such as monochloroacetic acid, monofluoroacetic acid, propionic acid, octylic acid, versatic acid, isostearic acid, palmitic acid, cresotinic acid, α -naphthoic acid, β -naphthoic acid, benzoic acid, 2,4,5-trichlorophenoxyacetic acid, 2,4-dichlorophenoxyacetic acid, quinolinecarboxylic acid, nitrobenzoic acid, nitronaphthalenecarboxylic acid and pulvinic acid. Of these organic acid residues, the fatty acid type is especially preferred for the antifouling paints and can provide a coating which can stay free of cracks or exfoliation for a long period of time.

Examples of the metal-containing polymerizable monomers (a₁) represented by the above formula (I) include, for example, magnesium monochloroacetate (meth)acrylate ((meth)acrylate meaning acrylate or methacrylate in the specification) zinc monochloroacetate

- (meth)acrylate, copper monochloroacetate (meth)acrylate,
magnesium monofluoroacetate (meth)acrylate, zinc
monofluoroacetate (meth)acrylate, copper
monofluoroacetate (meth)acrylate, magnesium propionate
5 (meth)acrylate, zinc propionate (meth)acrylate, copper
propionate (meth)acrylate, magnesium octylate
(meth)acrylate, zinc octylate (meth)acrylate, copper
octylate (meth)acrylate, magnesium versatate
(meth)acrylate, zinc versatate (meth)acrylate, copper
10 versatate (meth)acrylate, magnesium palmitate
(meth)acrylate, zinc palmitate (meth)acrylate, copper
palmitate (meth)acrylate, magnesium cresotinate
(meth)acrylate, zinc cresotinate (meth)acrylate, copper
cresotinate (meth)acrylate, magnesium α -naphthoate
15 (meth)acrylate, zinc α -naphthoate (meth)acrylate,
copper α -naphthoate (meth)acrylate, magnesium β -
naphthoate (meth)acrylate, zinc β -naphthoate
(meth)acrylate, copper β -naphthoate (meth)acrylate,
magnesium benzoate (meth)acrylate, zinc benzoate
20 (meth)acrylate, copper benzoate (meth)acrylate,
magnesium 2,4,5-trichloroacetate (meth)acrylate, zinc
2,4,5-trichlorophenoxyacetate (meth)acrylate, copper
2,4,5-trichlorophenoxyacetate (meth)acrylate, magnesium
2,4-dichlorophenoxyacetate (meth)acrylate, zinc 2,4-
25 dichlorophenoxyacetate (meth)acrylate, copper 2,4-
dichlorophenoxyacetate (meth)acrylate, magnesium
quinolinecarboxylate (meth)acrylate, zinc
quinolinecarboxylate (meth)acrylate, copper

quinolinecarboxylate (meth)acrylate, magnesium
nitrobenzoate (meth)acrylate, zinc nitrobenzoate
(meth)acrylate, copper nitrobenzoate (meth)acrylate,
magnesium nitronaphthalenecarboxylate (meth)acrylate,
5 zinc nitronaphthalenecarboxylate (meth)acrylate, copper
nitronaphthalenecarboxylate (meth)acrylate, magnesium
pulvinate (meth)acrylate, zinc pulvinate (meth)acrylate,
and copper pulvinate (meth)acrylate. These metal-
containing polymerizable monomers (a_2) may be used either
10 singly or as a mixture of two or more of them as
required. Zinc-containing polymerizable monomers are
especially preferred.

Combined use of a metal-containing
polymerizable monomer (a_1) having two unsaturated groups
15 and a metal-containing polymerizable monomer (a_2)
represented by the formula (I) as the metal-containing
polymerizable monomer (a) is preferred as the self
polishing of the formed coating are maintained for a long
time and a sufficient rate of consumption of the coating
20 is exhibited. The combination of zinc (meth)acrylate and
fatty acid type zinc (meth)acrylate is especially
preferred.

The composition of the metal-containing
polymerizable monomer (a) in the copolymer used as a
25 vehicle in the present invention is not subject to any
specific restrictions, but preferably it is within the
range of 10 to 80% by weight. A composition of 10% by
weight or more of said monomer (a) tends to afford a

pertinent self polishing characteristics to the formed coating, while the antifouling properties of the coating tend to be maintained for a long period of time when said composition is made 80% by weight or less. The more
5 preferred range of said composition is from 20 to 50% by weight.

In case a metal-containing polymerizable monomer (a_1) having two unsaturated groups and a metal-containing polymerizable monomer (a_2) represented by the
10 formula (I) are used as the metal-containing polymerizable monomer (a) which is a constituent of the vehicle-forming copolymer, the ratio (mol%) of (a_1) units/(a_2) units in the copolymer preferably falls within the range from 20/80 to 80/20. This is for the reason
15 that the ratio of 80/20 or below tends to provide a satisfactory self polishing characteristics, while the ratio of 20/80 or above tends to enable the formed coating to maintain its self polishing characteristics for a long period of time. The more preferred range of
20 said ratio is from 30/70 to 70/30.

The polymerizable monomer (b) used as another constituent of the vehicle copolymer is the one represented by the formula (II) and can afford excellent rate of consumption and long-time self polishing
25 characteristics, as well as excellent crack resistance and peel resistance, to the formed coating by being combined with the above (a) component. Particularly, when the above (a_1) component is combined with the above

(b) component, the rate of consumption of the coating can be more enhanced as compared with the use of the (a₁) component alone. Also, when the above (a₁) component is combined with the above (b) component, the long-time self polishing characteristics of the coating can be more improved as compared with the use of the (a₁) component alone.

Examples of the polymerizable monomers (b) include 2-methoxyethyl (meth)acrylate, 2-ethoxyethyl (meth)acrylate, phenoxyethyl (meth)acrylate, 2-(2-ethylhexaoxy)ethyl (meth)acrylate, 1-methyl-2-methoxyethyl acrylate, 3-methoxybutyl acrylate, 3-methyl-3-methoxybutyl acrylate, m-methoxyphenyl (meth)acrylate, p-methoxyphenyl (meth)acrylate, o-methoxyphenylethyl (meth)acrylate, m-methoxyphenylethyl (meth)acrylate, and p-methoxyphenylethyl (meth)acrylate. These monomers may be used either singly or as a mixture of two or more of them as required. Of these monomers, 2-methoxyethyl acrylate and 3-methoxybutyl acrylate are preferred.

No specific restrictions are imposed on the composition of the polymerizable monomer (b) in the vehicle copolymer used in the present invention, but the composition preferably falls within the range from 1 to 90% by weight. When the composition is set to be 1% by weight or above, the formed coating tends to improve in flexibility and crack and peel resistance, while a composition of 90% by weight or below of said monomer (b) tends to make better the balance between crack and peel

resistance of the formed coating and its long-time self polishing characteristics. The more preferred range of said composition is from 5 to 60% by weight, even more preferably from 10 to 50% by weight.

5 If necessary, there can be used an unsaturated monomer

(c) copolymerizable with said monomer (a₁), (a₂) or (b) as still another constituent of the copolymer used as vehicle in the present invention. The monomer (c) used
10 in the present invention is not subject to any specific restrictions as far as it is copolymerizable with said monomer (a₁), (a₂) or (b). As such monomer (c), there can be used, for instance, (meth)acrylic acid ester nibiners such as methyl (meth)acrylate, ethyl
15 (meth)acrylate, n-propyl (meth)acrylate, i-propyl (meth)acrylate, n-butyl (meth)acrylate, i-butyl (meth)acrylate, t-butyl (meth)acrylate, 2-ethylhexyl (meth)acrylate, lauryl (meth)acrylate, stearyl (meth)acrylate, benzyl (meth)acrylate, phenyl
20 (meth)acrylate, isobonyl (meth)acrylate, cyclohexyl (meth)acrylate, and glycidyl (meth)acrylate; hydroxyl group-containing monomers such as 2-hydroxyethyl (meth)acrylate, 2-hydroxypropyl (meth)acrylate, 3-hydroxypropyl (meth)acrylatte, 2-hydroxybutyl
25 (meth)acrylate and 4-hydroxybutyl (meth)acrylate; adducts of 2-hydroxyethyl (meth)acrylate with ethylene oxide, propylene oxide, γ-butyrolactone or ε-caprolactone; dimers or trimers such as 2-hydroxyethyl (meth)acrylate

and 2-hydroxypropyl (meth)acrylate; monomers having plural hydroxyl groups such as glycerol (meth)acrylate; vinyl monomers containing primary and secondary amino groups such as butylaminoethyl (meth)acrylate and (meth)acrylamide; vinyl monomers containing tertiary amino groups such as dimethylaminoethyl (meth)acrylate, diethylaminoethyl (meth)acrylate, dimethylaminopropyl (meth)acrylate, dimethylaminobutyl (meth)acrylate, dibutylaminoethyl (meth)acrylate, dimethylaminoethyl (meth)acrylate, and dimethylaminopropyl (meth)acrylate; heterocyclic basic monomers such as vinylpyrrolidone, vinylpyridine, and viny carbazole; and vinyl monomers such as styrene, vinyltoluene, α -methylstyrene, (meth)acrylonitrile, vinyl acetate and vinyl propionate.

15 These monomers may be used either singly or as a mixture of two or more of them.

The composition of the unsaturated monomer (c) in the copolymer as a vehicle copolymer used in the present invention is not specifically defined, but it is preferably in the range from 0 to 89% by weight for the reason that by defining the composition to be 89% by weight or below, the formed coating is provided with favorable hydrolyzing properties and tends to be made better in balance between the long-time self polishing characteristics and crack and peel resistance. The more preferred range of said composition is from 7 to 75% by weight, even more preferably from 10 to 60% by weight.

25

The preparation process for the copolymer used

as vehicle in the present invention is not specified; it can, for instance, be produced from a process which comprises mixing said monomers and reacting this mixture in the presence of a radical polymerization initiator at 5 60 to 180°C for 5 to 14 hours. As the polymerization method, there can be employed solution polymerization in which the reaction is carried out in an organic solvent, as well as other methods such as emulsion polymerization and suspension polymerization, but employment of solution 10 polymerization using an ordinary organic solvent such as toluene, xylene, methyl isobutyl ketone, n-butyl acetate or the like is advantageous in terms of productivity and product performance.

The copolymer serving as a vehicle in the 15 antifouling paint composition of the present invention is preferably used in a ratio of usually 20 to 25% by weight (solids) as resin component in the composition. This is based on the fact that the presence of the resin component in a proper content is conducive to the 20 improvement of coating properties such as crack resistance and also makes it easier to contain a sufficient amount of the antifouling toxicant in the antifouling paint composition to let it maintain high antifouling performance.

25 The antifouling paint composition of the present invention comprises said copolymer as vehicle, so that the formed coating can hold antifouling performance. The antifouling performance can be further enhanced by

containing an antifouling toxicant.

The antifouling toxicant used in the antifouling paint composition of the present invention can be properly selected according to the product performance requirement. There can be used, for instance, coppery antifouling toxicant such as cuprous oxide, copper thiocyanate and copper powder, compounds of other metals such as lead, zinc, nickel, etc., amine derivatives such as diphenylamine, nitrile compounds, benzothiazole compounds, maleimide compounds, pyridine compounds, and the like. These substances may be used either singly or as a mixture of two or more of them.

In the antifouling paint composition of the present invention, it is also possible to blend a silicon compound such as dimethyl polysiloxane or silicone oil or a fluorine-containing compound such as carbon fluoride for the purpose of imparting lubricity to the coating surface to prevent attachment of organisms. It is further possible to blend where necessary an extender pigment, color pigment, plasticizer, various types of paint additives, other resins, etc., in the composition of the present invention.

For forming a coating by using the antifouling paint composition of the present invention, said composition is coated either directly or after applying a primer coat with a washer primer, chlorinated rubber or epoxy primer, or an intercoat, on the surface of a base such as ship, fishing net, or underwater structure such

as port facility, oil fence, bridge, submarine infrastructure, etc., by a means such as brush coating, spray coating, roller coating, deposition coating, etc. The amount of coating of the composition is usually such
5 as will provide a coating thickness of 50 to 400 μm as dry film. Drying of the coat is usually conducted at room temperature, but it may be performed under heating.

The present invention is further illustrated by the following examples and comparative examples, but the
10 present invention is not restricted by these examples in any way. In the following Examples and Comparative Examples, all "parts" are by weight unless otherwise noted.

15 Examples 1-13 and Comparative Examples 1-4

Thirty parts of propylene glycol methyl ether (PGM) and 40 parts of xylene were supplied into a four-necked flask provided with a condenser, a thermometer, a dropping funnel and a stirrer, and heated to 100°C with
20 stirring. Then a mixture of the monomers and polymerization initiator shown in Table 1 was added dropwise from the dropping funnel at a constant rate over a period of 3 hours. After completion of the dropwise addition, one part of t-butyl peroctoate and 10 parts of
25 xylene were further added dropwise over a period of 2 hours, followed by 2-hour stirring and succeeding addition of 20 parts of xylene to obtain the vehicle copolymer solutions A1-A13 and B1-B4 having the property

values shown in Table 1.

Using the thus obtained copolymer solutions A1-A13, there were prepared the antifouling paint compositions (Examples 1-13) according to the formulations shown in Table 2. Also, using the copolymer solutions B1-B4, there were prepared the antifouling paint compositions of Comparative Examples 1-4 according to the formulations shown in Table 2. Further, using a tributyltin methacrylate/methyl methacrylate copolymer solution C1 (solid content: 50%; tin content in solids: 20%; solvent: xylene), there was prepared an antifouling paint composition of Referential Example 1 according to the formulation shown in Table 2.

The above antifouling paint compositions were then subjected to a coating consumption test, an antifouling test and a crack and peel test in the following ways.

(1) Coating consumption test

Each of the antifouling paint compositions was applied on a 50 x 50 x 2 mm thick hard vinyl chloride plate to a dry coating thickness of 240 μ m, and the coated plate was secured to a submerged rotary drum. The drum was rotated at a peripheral speed of 15 knots, and the consumed coating thickness on the plate secured to the drum was measured every three months. The results are shown in Table 3.

(2) Antifouling test

Each of the antifouling paint compositions was

applied on a sandblasted and antirust-coated steel plate to a dry coating thickness of 240 μm to make a test plate. The test plate was kept stationarily immersed in seawater in Hiroshima Bay, Hiroshima Prefecture, for 36 months, and the area (%) of the plate incrustated with extraneous matter was examined every six months. The results are shown in Table 4.

(3) Crack and peel test

Each of the antifouling paint compositions of Examples 1-13 and Comparative Examples 1-4 was applied on the following bases (1), (2) and (3) to a dry coating thickness of 240 μm to make the test plates (A), (B) and (C). The test plate (C) has been coated with the same antifouling paint as used in making the base (3).

Base (1): A sandblasted steel plate with antirust coating.

Base (2): A 240 μm thick coating of the antifouling paint composition of Referential Example 1 was formed on the base (1), and this was immersed in sterilized and filtered seawater for three months and then dried at room temperature for one week.

Base (3): A 240 μm thick coating of each of the antifouling paint compositions of Examples 1-13 and Comparative Examples 1-4 was formed on the base (1), and this was immersed in sterilized and filtered seawater for three months and then dried at room temperature for

one week.

The test plates (A), (B) and (C) were immersed in sterilized and filtered seawater for 12 months. They were taken out of seawater every 6 months and dried at room temperature (20°C) for one week, and the condition of cracking and peeling of the coating was observed. The condition was indicated by ⊙ when the coating was free of cracks and peeling; ○ when the coating was partly cracked; △ when the coating was partly peeled; and × when the coating was cracked and peeled all over. The results are shown in Table 5.

In the case of the antifouling paint compositions of Comparative Examples 1-4, although some of them showed self polishing characteristics for a prolonged period of time, these compositions had a tendency to deteriorate in recoatability on the old coating of an organotin-containing coating, etc.. Also, the coatings formed with these compositions were cracked and peeled. In contrast, the antifouling paint compositions of the present invention (Examples 1-13) using the copolymers A1-A12 showed long-time self polishing characteristics and excellent antifouling performance, and had good recoatability on the old coating of an organotin-containing coating etc., and their coatings had high crack and peel resistance.

Industrial Applicability

The coating formed from the antifouling paint

composition of the present invention exhibits excellent antifouling effect as it is dissolved into seawater constantly at a pertinent rate and capable of maintaining its self polishing characteristics for a long period of time, and also has excellent recoatability on the old coating such as formed from an organotin-based paint and so on. Thus, the product of the present invention is very beneficial to the industries as an antifouling coating for preventing attachment of marine organisms and seaweeds to submerged structures, fishing nets and the bottom of ship.

Table 1

		A1	A2	A3	A4	A5
Metal-containing polymerizable monomers (a ₁)(parts)	Zinc acrylate	12	16		8	12
	Zinc methacrylate					
	Copper acrylate			16		
Metal-containing polymerizable monomers (a ₂)(parts)	Zinc versatate acrylate	18	24		12	18
	Zinc versatate methacrylate					
	Zinc isostearate acrylate					
	Zinc isostearate methacrylate					
	Copper versatate acrylate			24		
Polymerizable monomers (b)(parts)	2-Methoxyethylacrylate				25	35
	3-Methoxybutylacrylate					
	3-Methyl-3-methoxybutyl acrylate					
Unsaturated monomers (c)(parts)	Methyl methacrylate	20	10	10	30	
	Ethyl acrylate	50	50	50	25	35
Polymerization initiator (parts)	t-Butyl peroctoate	5	4	6	7	3
Property value	Gardner viscosity (25°C)	-21	-2	-23	+2	+V
	Heating residue (wt%)	50.2	49.9	49.4	50.9	50.1

Table 1 (Cont'd)

A6	A7	A8	A9	A10	A11	A12	A13	B1	B2	B3	B4
16			6				8				
	12		6	35			8	35			
		16			40				40		
24			9								
	28		9			35				35	
							12				
							12				
		24									
		10	10	10	10	10	13				40
40		40		30	40	30					
	25										
10			13				13	5	10	5	40
10	35	10	47	25	10	25	34	60	50	60	20
4	3	7	5	4	4	6	5	3	3	1.5	0.7
-Z1	+W	+Z1	+X	-Y	+Z2	+Z	-Y	+S	+W	+R	+L
50.6	50.3	51.1	49.7	50.4	50.9	50.5	49.7	50.3	49.3	50.2	49.8

Table 2

		Example													Comparative Example				Referential Example
		1	2	3	4	5	6	7	8	9	10	11	12	13	1	2	3	4	1
Copolymer	A1	40																	
	A2		40																
	A3			40															
	A4				40														
	A5					40													
	A6						40												
	A7							40											
	A8								40										
	A9									40									
	A10										40								
	A11											40							
	A12												40						
	A13													40					
	B1														40				
	B2															40			
	B3																40		
	B4																	40	
	C1																		40

Table 2 (Cont'd)

Cuprous oxide	20	20	20	20	20	20	20	20	20	20	20	20	20	20	20	20	20	20
Zinc oxide	15	15	15	15	15	15	15	15	15	15	15	15	15	15	15	15	15	15
Silica powder	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3
Disperon 4200	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Xylene	8	8	10	8	5	8	5	10	8	8	10	8	8	5	5	5	5	5

(Note) Disperon 4200 (made by Kusumoto Kasei K.K., anti-sagging agent)

Table 3

		Example												
		1	2	3	4	5	6	7	8	9	10	11	12	13
Consumed coating thickness (μm)	3 months	16	28	8	16	32	35	28	15	18	19	13	30	52
	6 months	30	53	14	29	56	63	51	25	34	33	23	55	95
	9 months	48	79	21	43	82	90	75	35	51	47	32	79	137
	12 months	64	106	25	56	108	115	100	44	68	60	40	104	181
	15 months	81	130	32	71	137	144	127	55	85	76	52	130	222
	18 months	96	152	37	84	161	170	141	64	100	90	61	154	-
	21 months	110	174	42	97	186	196	165	74	115	102	71	180	-
	24 months	123	197	46	110	210	221	188	82	131	124	80	203	-
Monthly average of consumed coating thickness (μm)		5.1	8.2	1.9	4.6	8.6	9.2	7.8	3.4	5.5	5.2	3.3	8.5	14.8

Note) In Example 13 the coating applied of about 240 μm was entirely consumed after 18 months.

Table 3 (Cont'd)

Comparative Example			
1	2	3	4
3	4	17	4
5	6	18	4
8	9	18	4
10	12	18	4
14	16	18	4
17	19	18	4
19	21	18	4
21	24	18	4
0.9	1.0	0.8	0.1

Table 4


		Example													Comparative Example			
		1	2	3	4	5	6	7	8	9	10	11	12	13	1	2	3	4
Incrusted area (%)	6 months	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	10	70
	12 months	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	70	100
	18 months	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	100	100
	24 months	0	0	0	0	0	0	0	0	0	0	0	0	0	10	0	100	100
	30 months	0	0	0	0	0	0	0	0	0	0	0	0	0	30	30	100	100
	36 months	0	0	10	0	10	0	0	0	0	0	0	0	0	70	50	100	100

Table 5

			Example													Comparative Example			
			1	2	3	4	5	6	7	8	9	10	11	12	13	1	2	3	4
Crack and peel resistance	6 months	A	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
		B	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
		C	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
	12 months	A	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
		B	○	○	○	△	△	○	○	○	○	○	○	○	○	○	×	×	○
		C	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○


CLAIMS

1. An antifouling paint composition comprising, as a vehicle, a copolymer from a monomer mixture comprising of (a₁) a metal-containing polymerizable monomer having two unsaturated groups and (a₂) a metal-containing polymerizable monomer represented by the following formula (I):



wherein R¹ represents a hydrogen atom or a methyl group; M represents Mg, Zn or Cu; and R² represents an organic acid residue.

2. An antifouling paint composition comprising, as a vehicle, a copolymer from a monomer mixture comprising (a) a metal-containing polymerizable monomer and (b) a polymerizable monomer represented by the following formula (II):




wherein R¹ represents a hydrogen atom or a methyl group; R⁴ represents an alkyl group having 1 to 10 carbon atoms, a cycloalkyl group or a phenyl group; and R⁵ represents

an alkyl group having 1 to 10 carbon atoms, a cycloalkyl group or a phenyl group.

3. An antifouling paint composition according to Claim 2, wherein the metal-containing polymerizable monomer (a) is a metal-containing polymerizable monomer (a₁) having two unsaturated groups.

4. An antifouling paint composition according to Claim 2, wherein the metal-containing polymerizable monomer (a) is a metal-containing polymerizable monomer (a₂) represented by the formula (I):



wherein R¹ represents a hydrogen atom or a methyl group; M represents Mg, Zn or Cu; and R² represents an organic acid residue.

5. An antifouling paint composition according to Claim 2, wherein the metal-containing polymerizable monomer (a) is a mixture of (a₁) a metal-containing polymerizable monomer having two unsaturated groups and (a₂) a metal-containing polymerizable monomer represented by the formula (I).