

METHOD OF PURIFYING A BIOLOGICAL MATERIAL OF INTEREST IN A SAMPLE USING NANOFIBER ULTRAFILTRATION MEMBRANES OPERATED IN TANGENTIAL FLOW FILTRATION MODE

Cross-Reference to Related Applications

[0001] This application claims the benefit of priority of U.S. Provisional Patent Application No. 62/148,793, filed on April 17, 2015, the entire content of which is incorporated by reference herein in its entirety.

[0002] Embodiments disclosed herein relate to nanofiber ultrafiltration compositions capable of operating in tangential filtration mode and methods of using the same.

Background

[0003] Membrane filtration is a separation technique widely used both for bench scale as well as process scale purification of biological materials. There are different types of membranes used in filtration, which are classified as microfiltration or ultrafiltration membranes depending on the pore size. Microfiltration membranes generally have pore size ranging between 0.1 μm and 10 μm ; whereas, ultrafiltration membranes have a much smaller pore size, ranging between 0.001 and 0.1 μm . Because of the difference in the pore size, these membranes are used for different purposes. For example, microfiltration membranes are generally used for clarification, sterilization, and removal of microparticulates or for cell harvesting and ultrafiltration membranes are generally used for fractionation or for concentrating molecules (such as, for example, proteins, peptides, nucleic acids, carbohydrates, and other biological materials). Ultrafiltration membranes are typically classified by molecular weight cutoff, rather than pore size.

[0004] There are two main types of filtration modes which are generally employed with microfiltration and ultrafiltration membranes. One of the filtration modes is called Normal Flow Filtration (NFF) mode, also known as "dead-end" filtration, which generally applies the feed stream perpendicular to the membrane face and attempts to pass 100% of the fluid through the membrane. Another filtration mode is called Tangential Flow Filtration (TFF), where the feed stream is parallel to the membrane face, where one portion passes through the membrane (i.e., permeate) while the remainder is retained and may be recirculated back to the feed reservoir (i.e., retentate).

[0005] TFF mode of filtration is preferred for the purification of certain types of biological materials, for example those having a size of 500 kDa or larger than 500

kDa, where TFF is employed for concentration and impurity clearance. Most TFF applications employ ultrafiltration membranes which are useful for concentration and buffer exchange steps etc. One example of an ultrafiltration membrane which is used in TFF mode for manufacturing of certain biological materials (e.g., proteins, vaccines and virus-like particles) is a solution immersion cast ultrafiltration membrane made from polyethersulfone (PES).

[0006] Most ultrafiltration membranes widely used in TFF mode are required to be shipped in wet state and also with preservatives to prevent contamination by microorganisms. However, not only is shipping in wet state difficult as it requires controlling the environmental conditions to prevent drying out and freezing of the membrane but the preservatives added to the membrane material often have to be removed prior to use in the purification of biological materials in order to avoid the preservatives from ending up in the sample containing the final product, e.g., a therapeutic protein or a vaccine.

Summary

[0007] Embodiments disclosed herein demonstrate the applicability of electrospun nanofiber membrane compositions in the manufacturing of biological materials such as, for example, virus-like particles, proteins and conjugated polysaccharide vaccines (generally biological materials having a molecular weight about or greater than 500KDa) and provide an alternative to and an improvement over currently used solution immersion cast PES membranes. Specifically, in contrast to the solution immersion cast PES membranes, the electrospun nanofiber membranes can be shipped in a dry state and also do not require the use of preservatives.

[0008] The electrospun nanofiber membranes used in the embodiments described herein have an equivalent or improved performance to the solution immersion cast PES ultrafiltration membrane in Tangential Flow Filtration (TFF) mode.

[0009] In various embodiments, method of purifying a biological material of interest in a sample is provided, wherein the method comprises the steps of: (a) providing a sample containing the biological material of interest having a molecular weight equal to or greater than 500 KDa; (b) contacting the sample in tangential filtration mode with an electrospun nanofiber membrane composition comprising nanofibers having an average fiber diameter less than 15 nm, thereby resulting in a permeate and a retentate; and (c) collecting the retentate containing the biological material of interest, thereby to purify the biological material of interest.

[0010] In some embodiments, the biological material of interest is selected from a therapeutic protein, a conjugated polysaccharide vaccine and a virus-like particle.

[0011] In some embodiments, the collecting step comprises increasing the concentration of the biological material of interest. In other embodiments, the collecting step comprises diafiltration.

[0012] In some embodiments, the electrospun nanofiber compositions exhibit higher water permeability in TFF mode compared to a solution cast polymeric membrane.

[0013] In some embodiments, the electrospun nanofiber membrane compositions exhibit a higher flux in TFF mode compared to a solution cast polymeric membrane.

[0014] In some embodiments, the electrospun nanofiber membrane composition is made from Nylon-6.

[0015] In some embodiments, the methods of purification result in at least 90% yield or greater than 90% yield of the biological material of interest.

[0016] In various embodiments, the electrospun nanofiber membrane composition is incorporated into a device suitable for TFF, such as, for example, a cassette, or a spiral wound device.

Brief Description of the Drawings

[0017] Figure 1 depicts a scanning electron micrograph of an electrospun Nylon-6 nanofiber ultrafiltration membrane (referred to as “NF UF”) at 100,000 times magnification.

[0018] Figure 2 depicts a scanning electron micrograph of the polyethersulfone ultrafiltration membrane (referred to as “PES UF”) at 100,000 times magnification that is made using solution immersion casting.

[0019] Figure 3 depicts a graph measuring the diameter of the NF UF membrane fibers. The NF UF random fiber radius measurements are made using a Scanning Electron Micrograph (SEM) similar to that in Figure 1 and a custom Euclidean Distance Map (EDM) routine within Image Pro Plus v6.0. The x-axis is the radius of the fibers in nanometers. The y-axis is the frequency or number of measurements for each radius in nanometers on the x-axis.

[0020] Figure 4 is a graph depicting the average water permeability in LMH/psi (y-axis) versus mean flow bubble point in psi (x-axis) for six different samples of the NF UF membrane and four different samples of the PES UF membranes. The six NF UF membrane samples are: NF UF 1000 kDa (R1-1); (R1-2); (R2-1); (R2-2); and NF UF 1500 kDa (R2-3); and (E2-1), as shown in the figure key. The four PES UF

membrane samples are: PES UF 800 kDa; 1200 kDa; 1700 kDa; and 4800 kDa, as shown in the figure key. The numbers before the unit kDa (kiloDaltons) indicate the Dextran sieving R90 cutoffs for the UF membranes, where a membrane retains 90% of Dextrans with a molecular weight above the kDa value. The water permeability units are Liters of water per square meter of membrane X hours X pounds per square inch of applied pressure (LMH/psi) on the y-axis. The mean flow bubble point unit is pounds per square inch (psi) for the solvent 2-propanol.

[0021] Figure 5 is a graph depicting the Dextran sieving curves for duplicate samples of PES UF membrane with Dextran R90 values of 800, 1200, 1700, and 4800 kDa and four samples of the NF UF membrane with Dextran R90 values of 1000 kDa and three samples at 1500 kDa, as shown in the figure key. The plot is a $\log_{10}$ versus $\log_{10}$, where the x-axis is Dextran molecular weight in the unit Daltons (Da) and the y-axis is the Dextran sieving $\log_{10}$ scale from 0.001 – 1, obtained from comparing the membrane sample permeate gel permeation chromatogram relative to the feed gel permeation chromatography (GPC) of the initial challenge solution on the membrane retentate side.

[0022] Figure 6 is a graph depicting the average Dextran sieving R90 in kiloDaltons (kDa) on $\log_{10}$ scale (y-axis) versus mean flow bubble point in psi (on x-axis) for six samples of the NF UF membrane and four different PES UF membrane samples. The six NF UF membrane samples are: NF UF 1000 kDa (R1-1); (R1-2); (R2-1); (R2-2) and NF UF 1500 kDa (R2-3); and (E2-1), as shown in the figure key. The four PES UF membrane samples are: PES UF 800 kDa; 1200 kDa; 1700 kDa; and 4800 kDa, as shown in the figure key. The numbers before the unit kDa (kiloDaltons) indicates the membranes Dextran sieving R90 cutoffs from Figure 5.

[0023] Figure 7 is a graph depicting the average water permeability in LMH/psi (y-axis) versus average Dextran sieving R90 in kiloDaltons (kDa) on $\log_{10}$ scale (on x-axis) for six samples of the NF UF membrane and four different PES UF membrane samples. The six NF UF membrane samples are: NF UF 1000 kDa (R1-1); (R1-2); (R2-1); (R2-2) and NF UF 1500 kDa (R2-3); (E2-1), as shown in the figure key. The four PES UF membrane samples are the PES UF 800 kDa; 1200 kDa; 1700 kDa; and 4800 kDa, as shown in the figure key. The numbers before the unit kDa (kiloDaltons) indicate the membranes Dextran sieving R90 cutoffs from Figure 5.

[0024] Figure 8 is a gel permeation chromatogram of Feed A (0.0385% w/w) at pH 7.0, 50 mM phosphate buffer from Example 4. The x-axis is Dextran molecular

weight in Daltons (Da) on a $\log_{10}$ scale. The area on the y-axis translates from refractive index detector response in milliVolts after integration with the GPC molecular weight standards.

[0025] Figure 9 is a gel permeation chromatogram of Feed B (0.844% w/w) at pH 7.0, 50 mM phosphate buffer from Example 4. The x-axis is Dextran molecular weight in Daltons (Da) on a $\log_{10}$ scale. The area on the y-axis translates from refractive index detector response in milliVolts after integration with the GPC molecular weight standards.

[0026] Figure 10 is a graph depicting the average flux of Feed A in LMH (y-axis) versus trans-membrane pressure (TMP) in psi (x-axis) for duplicate samples of the NF UF membrane and PES UF membrane for Feed A from Example 5. The flux units are Liters of Feed A per square meter of membrane X hours (LMH) on the y-axis. Trans-membrane pressure (TMP) is pounds per square inch of pressure (psi) on the x-axis across the membrane.

[0027] Figure 11 is a graph depicting the average flux of Feed B in LMH (y-axis) versus trans-membrane pressure (TMP) in psi (x-axis) for duplicate samples of the NF UF membrane and PES UF membrane for Feed B from Example 5. The flux units are Liters of Feed B per square meter of membrane x hours (LMH) on the y-axis. Trans-membrane pressure (TMP) is pounds per square inch of pressure (psi) on the x-axis across the membrane.

[0028] Figure 12 is a graph depicting the average flux of Feed C in LMH (y-axis) versus trans-membrane pressure (TMP) in psi (x-axis) for duplicate samples of the NF UF membrane and PES UF membranes for Feed C from Example 5. The flux units are Liters of Feed C per square meter of membrane X hours (LMH) on the y-axis. Trans-membrane pressure (TMP) is pounds per square inch of pressure (psi) on the x-axis across the membrane.

[0029] Figure 13 depicts a gel permeation chromatograms of Feed A (0.0385% w/w) samples of feed and permeate collected from Example 5 at each TMP. In Figure 13, the gel permeation chromatograms of Feed A permeates for 1 of the 2 duplicates of the NF UF and their feeds are shown. The x-axis is Dextran molecular weight in Daltons (Da) on a $\log_{10}$ scale. The area on the y-axis translates from refractive index detector response in milliVolts after integration with the GPC molecular weight standards.

[0030] Figure 14 depicts a gel permeation chromatograms of Feed A (0.0385% w/w) samples of feed and permeate collections during Example 5 at each TMP. Figures 14 shows the gel permeation chromatograms of Feed A permeates through 1 of the 2 duplicates of the PES UF membrane and their feeds. The x-axis is Dextran molecular weight in Daltons (Da) on a $\log_{10}$ scale. The area on the y-axis translates from refractive index detector response in milliVolts after integration with the GPC molecular weight standards.

[0031] Figure 15 is a graph depicting the mass/concentration transport or average C_P / C_F of D7250, D2000, D110 on the y-axis for the NF UF and PES UF membranes using Feed A with the Flux versus TMP (psi) experiment from Example 5. Example 6 details how to obtain the Dextran mass/concentration transport from Example 5 by collecting feed and permeate samples at each TMP (psi) on the x-axis for GPC analysis.

[0032] Figure 16 is a graph depicting the mass/concentration transport or average C_P / C_F of D7250, D2000, D110 on the y-axis for the NF UF and PES UF membranes using Feed B with the Flux versus TMP (psi) experiment from Example 5. As in case of Figure 15, Example 6 details how to obtain the Dextran mass/concentration transport from Example 5 by collecting feed and permeate samples at each TMP (psi) on the x-axis for GPC analysis.

[0033] Figure 17 is a graph depicting the average selectivity of D110/D2000 and D110/D7250 versus average flux in LMH for the NF UF and PES UF membranes using Feed A with the Flux versus TMP (psi) experiment from Examples 5 and 6. Example 7 details how to calculate the selectivity factor from the equation $[(C_P / C_F)_{D110} / (C_P / C_F)_{D2000 \text{ or } D7250}]$ on the y-axis to determine the average passage selectivity of D110/D2000 and D110/D7250 versus average flux (LMH) on the x-axis.

[0034] Figure 18 is a graph depicting the average selectivity of D110/D2000 and D110/D7250 versus average flux in LMH for the NF UF and PES UF membranes using Feed B with the Flux versus TMP (psi) experiment from Examples 5 and 6. Example 7 details how to calculate the selectivity factor from the equation $[(C_P / C_F)_{D110} / (C_P / C_F)_{D2000 \text{ or } D7250}]$ on the y-axis to determine the average passage selectivity of D110/D2000 and D110/D7250 versus average flux (LMH) on the x-axis.

[0035] Figure 19 depicts gel permeation chromatograms of the feed, retentates and permeates during Diafiltration of Feed A at 30 LMH and 640 RPM using the NF UF membrane. The x-axis is Dextran molecular weight in Daltons (Da) on a $\log_{10}$ scale. The area on the y-axis translates from refractive index detector response in milliVolts after integration with the GPC molecular weight standards. Figure 19 shows the feed as the largest peak and the retentates in solid lines at each increasing diavolume in decreasing height. The permeates are shown by dashed lines where increasing diavolumes results in lower peaks.

[0036] Figure 20 depicts gel permeation chromatograms of the feed, retentates, and permeates during Diafiltration of Feed A at 30 LMH and 640 RPM using the PES UF membrane. The x-axis is Dextran molecular weight in Daltons (Da) on a $\log_{10}$ scale. The area on the y-axis translates from refractive index detector response in milliVolts after integration with the GPC molecular weight standards. Figure 20 shows the feed as the largest peak and the retentates in solid lines at each increasing diavolume in decreasing height. The permeates are shown by dashed lines where increasing diavolumes results in lower peaks.

[0037] Figure 21 is a graph depicting the average retentate C / C_o of D7250, D2000, D110 on the y-axis versus diavolume number on the x-axis for the NF UF and PES UF membranes using Feed A from the Diafiltration experiment in Example 8. The diafiltration of Feed A is at a constant Flux of 30 LMH with stirring at 640 RPM.

[0038] Figure 22 is a graph depicting the average retentate selectivity D7250/D110 and D2000/D110 on the y-axis versus diavolume number on the x-axis for the NF UF and the PES UF membranes using Feed A from the Diafiltration experiment in Example 8. The diafiltration of Feed A is at a constant Flux of 30 LMH with stirring at 640 RPM. The average retentate selectivities are from the Figure 21 values as $D7250/D110 = (C/C_o)_{D7250}/(C/C_o)_{D110}$ and $D2000/D110 = (C/C_o)_{D2000}/(C/C_o)_{D110}$.

[0039] Figure 23 is a graph depicting the average retentate C / C_o of D7250, D2000, D110 on the y-axis versus diavolume number on the x-axis for the NF UF and the PES UF membranes using Feed A from the Diafiltration experiment in Example 8. The diafiltration of Feed A is at a constant Flux of 60 LMH and stirring at 320 RPM.

[0040] Figure 24 is a graph depicting the average retentate selectivity of D7250/D110 and D2000/D110 on the y-axis versus diavolume number on the x-axis for the NF UF and the PES UF membranes using Feed A from the Diafiltration experiment in Example 8. The diafiltration of Feed A is at a constant Flux of 60 LMH and stirring

at 320 RPM. The average retentate selectivities are from the Figure 23 values as $D7250/D110 = (C/C_o)_{D7250}/(C/C_o)_{D110}$ and $D2000/D110 = (C/C_o)_{D2000}/(C/C_o)_{D110}$.

[0041] Figure 25 is a graph depicting the average flux in LMH on the y-axis versus concentration factor on the x-axis during 2,4, and 8x ultrafiltration concentration of Feed A for the NF UF and the PES UF membranes at 0.5 psi constant TMP and 600 RPM in Example 9. The flux units are Liters of Feed A per square meter of membrane x hours (LMH) on the y-axis. Permeate volume over time determines the flux and tracks concentration factors.

[0042] Figure 26 is a graph depicting the average C / C_{theo} on the y-axis versus concentration factor on the x-axis during 2,4, and 8x ultrafiltration concentration of Feed A for the NF UF and the PES UF membranes at 0.5 psi constant TMP and 600 RPM in Example 9. Permeate volume over time determines the flux and tracks concentration factors.

[0043] Figure 27 is a graph depicting the average C / C_{theo} on the y-axis versus average feed flux in LMH on the x-axis during 2,4, and 8x (Left to Right) ultrafiltration concentration of Feed A for the NF UF and the PES UF membranes at 0.5 psi constant TMP and 600 RPM in Example 9. Permeate volume over time determines the flux and tracks concentration factors. Retentate samples are taken at each concentration factor for GPC analysis to determine yield and selectivity of D7250, D2000, and D110 as described in Example 4. The flux units are Liters of Feed A per square meter of membrane times hours (LMH) on the y-axis.

[0044] Figure 28 is a graph depicting the average C / C_{theo} on the y-axis versus average feed flux in LMH on the x-axis during 2,4, and 8x (Left to Right) ultrafiltration concentration of Feed B for NF UF and the PES UF membranes at 5 psi constant TMP and 600 RPM in Example 9. Permeate volume over time determines the flux and tracks concentration factors. Retentate samples are taken at each concentration factor for GPC analysis to determine yield and selectivity of D7250, D2000, and D110 as described in Example 4. The flux units are Liters of Feed B per square meter of membrane times hours (LMH) on the y-axis.

[0045] Figure 29 is a graph depicting the average C / C_{theo} on the y-axis versus average feed flux in LMH on the x-axis during 2, 4, and 8x (Left to Right) ultrafiltration concentration of Feed B for the NF UF and the PES UF membranes at 7 psi constant TMP and 600 RPM in Example 9. Permeate volume over time determines the flux and tracks concentration factors. Retentate samples are taken at

each concentration factor for GPC analysis to determine yield and selectivity of D7250, D2000, and D110 as described in Example 4. The flux units are Liters of Feed B per square meter of membrane times hours (LMH) on the y-axis.

[0046] Figure 30 is a graph depicting the average flux in LMH on the y-axis versus concentration factor on the x-axis during 2 and 3x ultrafiltration concentration of Feed C for the NF UF and the PES UF membranes at 5 psi constant TMP and 300 RPM in Example 9. The flux units are Liters of Feed A per square meter of membrane times hours (LMH) on the y-axis. Permeate volume over time determines the flux and tracks concentration factors.

[0047] Figure 31 is a graph depicting the average C / C_{theo} on the y-axis versus average feed flux in LMH on the x-axis during 2 and 3x (Left to Right) ultrafiltration concentration of Feed C for the NF UF and the PES UF membranes at 5 psi constant TMP and 300 RPM in Example 9. Permeate volume over time determines the flux and tracks concentration factors. Retentate samples are taken at each concentration factor for GPC analysis to determine yield and selectivity of D7250, D2000, and D110 as described in Example 4. The flux units are Liters of Feed C per square meter of membrane times hours (LMH) on the y-axis.

[0048] Figure 32 is a graph depicting the average C / C_{theo} on the y-axis versus average feed flux in LMH on the x-axis during 2 and 3x (Left to Right) ultrafiltration concentration of Feed C for the NF UF and the PES UF membranes at 7 psi constant TMP and 300 RPM in Example 9. Permeate volume over time determines the flux and tracks concentration factors. Retentate samples are taken at each concentration factor for GPC analysis to determine yield and selectivity of D7250, D2000, and D110 as described in Example 4. The flux units are Liters of Feed C per square meter of membrane times hours (LMH) on the y-axis.

[0049] Figure 33 is a schematic of a TFF system or unit operation employing the NF UF membrane, useful for the purification of a biological material of interest.

Detailed Description

[0050] The embodiments described herein employ electrospun nanofiber membrane compositions, as previously described in PCT Publication no. WO2014093345, in TFF mode for the purification of biological materials of interest such as, for example, therapeutic proteins, virus-like particles and conjugated polysaccharide vaccines. The electrospun nanofiber membrane compositions used in the methods described herein are of exceptionally high uniformity and exhibit increased permeability and a higher

process flux relative to solution immersion cast ultrafiltration membranes which are typically used in the purification of biological materials.

[0051] Most conventional polymeric ultrafiltration membranes are made by the solution phase inversion process. This process involves the conversion of a homogeneous polymer solutions of two or more components into a two-phase system with a solid, polymer-rich phase forming the rigid membrane structure and a liquid, polymer-poor phase forming the membrane pores. (see, for example, *Membranes and Membrane Processes*, 1986 Springer US, Drioli, Enrico; Nakagaki, Masayuki. *Preparation of Microporous Membranes by Phase Inversion Processes*, Strathmann, H., p 115-135). This can be accomplished with a variety of polymers and mixtures but is often challenging because of the sensitive kinetic and thermodynamic conditions required to generate membranes with the desired properties. Multiple variables exist that can affect membrane formation including polymer molecular weight, concentration, temperature, miscibility, solvent and non-solvent properties and composition, humidity, and substrates and often require complex process and environmental controls.

[0052] However, electrospun nanofiber ultrafiltration membranes (e.g., NF UF described herein) can be made using a much simpler manufacturing process using polymers such as Nylon-6. Nanofibers are simply drawn out of polymer solution using a high voltage source. Electrospinning does not rely on the complexity and sensitive nature of phase inversion (like traditional membranes), which depends on a variety parameters and is usually much more difficult to control.

[0053] The embodiments described herein are based, at least in part, on the surprising and unexpected finding that the electrospun nanofiber membrane compositions perform similarly to or better than solution immersion cast ultrafiltration membranes made from polymers such as polyethersulfone (PES), when used in TFF mode for the purification of biological materials having at least 500 KDa molecular weight such as, for example, certain therapeutic proteins, virus-like particles and conjugated polysaccharide vaccines and other similar sized biological materials. In some embodiments, the electrospun nanofiber compositions used in the embodiments described herein result in at least 90% product yield, or greater than 90% product yield, or at least 95% product yield, or greater than 95% product yield.

[0054] The NF UF membranes exhibit a higher water permeability that translates into higher process flux and greater mass transport when used in TFF mode over

conventional membranes that are used in TFF mode, e.g., a polyethersulfone ultrafiltration membrane. This also results in faster process times and smaller membrane area required to process the same feed amount, in turn translating into lower costs. As demonstrated by the Examples herein, an improvement of about 30% is observed in case of the NF UF membrane relative to PES UF membrane.

[0055] Electrospun nanofiber membrane or mat compositions are highly porous polymeric materials, where the “pore” size of the composition is linearly proportional to the fiber diameter of the electrospun nanofiber, while the porosity of the membrane or mat is relatively independent of the fiber diameter and usually falls in the narrow range of 85-90%.

[0056] The random nature of electrospun nanofiber mat or membrane formation has led to the general assumption that such compositions are generally unsuitable for any critical filtration of liquid streams. Applications of electrospun compositions for the removal of relatively large particles (such as bacteria) from solutions using normal filtration have recently begun to appear in the literature (see, for example, International PCT Publication No. WO2010/107503; Wang et al., ‘Electrospun nanofibrous membranes for high flux microfiltration’, *Journal of Membrane Science*, 392–393 (2012) 167–174)). However, there have been no published reports describing the use of electrospun nanofiber mats/membranes in TFF mode for the purification of biological materials of interest, as described herein.

[0057] In order that the embodiments disclosed herein may be more readily understood, certain terms are first defined. Additional definitions are set forth throughout the detailed description.

I. Definitions

[0058] The phrase “Tangential Flow Filtration” or “TFF” refers to a mode of filtration which is useful for clarifying, concentrating and purifying biological materials, e.g., proteins and vaccines. In Tangential Flow Filtration (TFF) mode of filtration, the fluid is pumped tangentially along the surface of the membrane. An applied pressure serves to force a portion of the sample through the membrane to the filtrate side (referred to as the permeate). Biological materials and particulates that are too large to pass through the membrane pores are retained on the upstream side (referred to as retentate). However, in contrast to normal filtration mode, the retained materials do not build up at the surface of the membrane. Instead, they are swept along the face of

the membrane by tangential flow of fluid. TFF may also be referred to as “cross-flow filtration.”

[0059] The phrase “Transmembrane Pressure” or “TMP” refers to the average applied pressure from the feed to the filtrate side of the membrane. TMP is calculated as follows: $TMP [bar] = [(P_F + P_R)/2] - P_f$, where [bar] is a metric unit of pressure exactly equal to 100000 Pascal, where Pascal is defined as one Newton per square meter; P_F is the applied pressure of the feed; P_R is the pressure of the retentate; and P_f is the pressure of the filtrate

[0060] The term “ultrafiltration” or “UF” refers to membrane filtration technique which employs controlled pore, semi permeable membranes to concentrate or fractionate dissolved molecules. Molecules much larger than the pores are retained in the feed solution and are concentrated in direct proportion to the volume of liquid that passes through the membrane. Molecules having a size which is close to the pore size of the membrane concentrate to a lesser extent with some of the molecules passing through the membrane in the permeate. The concentration of freely permeable molecules (salts) in the sample remains essentially unchanged. Membranes suitable for ultrafiltration (referred to as ultrafiltration or UF membranes) are defined by the molecular weight cut-off (MWCO) of the membrane used. Ultrafiltration can be applied in cross-flow or dead-end mode.

[0061] The term “diafiltration” refers to a technique that uses ultrafiltration membranes to completely remove, replace or lower the concentration of salts or solvents from solutions containing proteins, peptides, nucleic acids, and other biomolecules. The process selectively utilizes permeable (porous) membrane filters to separate the components of solutions and suspensions based on their molecular size. An ultrafiltration membrane retains molecules that are larger than the pores of the membrane while smaller molecules such as salts, solvents and water, which are 100% permeable, freely pass through the membrane. During diafiltration, buffer is introduced into the recycle tank while filtrate is removed from the unit operation. In processes where the product is in the retentate, diafiltration washes components out of the product pool into the filtrate, thereby exchanging buffers and reducing the concentration of undesirable species. When the product is in the filtrate, diafiltration washes it through the membrane into a collection vessel.

[0062] The term “diavolume” refers to a measure of the extent of washing that has been performed during a diafiltration step. It is based on the volume of diafiltration

buffer introduced into a unit operation compared to the retentate volume. If a constant volume diafiltration is being performed, where the retentate volume is held constant and diafiltration buffer enters at the same rate that filtrate leaves, a diavolume is calculated as follows: $DV = \text{total buffer volume introduced into the operation during diafiltration} / \text{retentate volume}$.

[0063] The term “concentration factor” refers to the amount by which a product has been concentrated in the feed stream.

[0064] The term “concentration” refers to the relative amount of a given substance contained within a solution or in a particular volume of space or the amount of solute per unit volume of solution. As used herein, concentration is measured by the number of biological molecules or materials of interest per solution volume.

[0065] The term “polymer” refers to a large molecule, or macromolecule, composed of many repeated subunits. Polymers range from familiar synthetic plastics such as polystyrene to natural biopolymers such as DNA and proteins that are fundamental to biological structure and function. Polymers, both natural and synthetic, are generally created via polymerization of many small molecules, known as monomers. Polymers suitable for use in the formation of nanofiber compositions used in the embodiments described herein include thermoplastic and thermosetting polymers. Additional exemplary polymers which may be used for making nanofiber compositions as described below.

[0066] The term “nylon” as used herein refers to nylon-6, nylon-6,6, nylon 6,6-6,10, and copolymers, derivative compounds, blends and combinations thereof.

[0067] The term “nanofibers” refers to fibers having diameters varying from a few tens of nanometers up to several hundred nanometers, but generally less than one micrometer.

[0068] The term “nanofiber composition,” as used herein, refers to an assembly of multiple nanofibers in the form of a mat or membrane, such that the thickness of the mat or membrane is at least about 10 times greater than the diameter of a single fiber in the mat or membrane. The nanofibers can be arranged randomly in the mat or membrane, or be aligned along one or multiple axes.

[0069] The term “electrospinning,” as used herein, refers to an electrostatic spinning process of producing nanofibers from a polymer solution or melt by applying an electric potential to such solution. The electrostatic spinning process for making an electrospun nanofiber mat or membrane for a filtration medium, including suitable

apparati for performing the electrostatic spinning process are described in detail in International Publication Nos. WO 2005/024101, WO 2006/131081, and WO 2008/106903, each of which is incorporated by reference herein. In some embodiments, the nanofiber compositions are made from a single nanofiber, wherein the single nanofiber is made by a single pass of a moving collection apparatus positioned between the spinning drum and the collector through the process. A fibrous web of nanofibers can be formed by one or more spinning drums running simultaneously above the same moving collection apparatus.

[0070] In some embodiments, a fibrous mat/membrane is made by depositing nanofiber (s) from a nylon solution. The nanofiber mat/membrane has a basis weight of between about 5 g/m² and about 15 g/m², as measured on a dry basis, i.e., after the residual solvent has been evaporated or removed.

[0071] The phrase “electrospun nanofiber composition” or “electrospun nanofiber membrane composition” refers to a porous nanofiber mat or membrane made from a polymer using the electrospinning process. The electrospun nanofiber composition generally has a porosity ranging from about 80% to about 95%, a thickness ranging from about 1 μm to about 500 μm or from about 50 μm to about 200 μm, and a liquid permeability greater than about 300 LMH/psi. In some embodiments of described herein, electrospun nanofibers are produced having an average diameter of less than 15 nm. In some embodiments, the average diameter of the electrospun nanofibers is between 6 nm and 13 nm.

[0072] In some embodiments, the electrospun nanofiber compositions are incorporated into a suitable TFF device or a module, such as, for example, a cassette such as a Millipore Pellicon® 3 cassette, a spiral wound device or a hollow fiber device. The NF UF membranes may be easier to incorporate into devices, such as spiral wound or flat cassettes, and may exhibit greater product recovery, higher concentration factors, require less equipment and energy to operate, smaller manufacturing footprint, require lower pumping capacity, and provide less air-liquid interface, lower risk of contamination, and better product quality.

[0073] In general, the use of the nanofiber compositions in TFF mode results in greater product recovery (greater than 90% yield or greater than 95% yield), higher concentration factors, less equipment use and energy to operate, lower pumping capacity, smaller manufacturing footprint, less air-liquid interface, as well as potentially lower risk of contamination, and better product quality.

[0074] Screens are often inserted into the feed and/or filtrate channels in spiral wound and flat plate or cassette modules to increase turbulence in the channels and reduce concentration polarization. This is not an option, however, with hollow fiber modules. In a hollow fiber module, the feed stream is pumped into the lumen (inside) of the tube and filtrate passes through the membrane to the shell side, where it is removed. Because of the very open feed flowpath, low shear is generated even with moderate crossflow rates. While this may be useful for highly shear sensitive products, in general it reduces the efficiency of the module by requiring very high pumping capacity to achieve competitive fluxes.

[0075] The terms “flux” and “flow rate” are used interchangeably herein to refer to the rate at which a volume of fluid passes through the electrospun nanofiber compositions described herein.

[0076] The term “filtrate” or “permeate,” as used interchangeably herein, refers to the solution that crosses a filter or membrane, e.g., an electrospun nanofiber composition used herein, as well as the solution that has already crossed a filter or membrane.

[0077] The term “retentate,” as used herein, refers to the component or portion of the solution that is retained and does not cross a filter or membrane, e.g., a electrospun nanofiber composition used herein, as well as that which has not yet crossed a filter or membrane. In case a Stirred Cell is employed, the liquid with solute that remains on the upstream side of the filter or membrane in a Stirred Cell is referred to as the retentate. In case of a TFF cassette or spiral device, the liquid which flows through the feed/retentate channels of a cassette or spiral device and returns from the device back to the feed tank is referred to as the retentate.

[0078] The term “Stirred Cell,” as used herein, refers to an apparatus that simulates or creates tangential flow filtration with stirring to generate cross-flow on the retentate side of a membrane, where gas pressure is applied directly to Stirred Cell. Solutes above the membrane's molecular weight (MW) cut-off are retained in cell, while water and solutes below the cut-off pass into the filtrate and out of cell.

[0079] The term “effective pore size”, as used herein, describes a structural property of a porous material assessed with a functional, rather than visual, method. For the purposes of comparing porous materials with dramatically different structures, such as solution-cast membranes and nanofiber mats/membranes, visual methods like microscopy are usually inadequate in predicting whether these materials would be expected to perform similarly in the same application. However, functional methods,

such as bubble point measurements, liquid-liquid porometry, intrusion porosimetry, sieving of macromolecules and/or particles of given sizes, allow one of skilled in the art to compare the properties of different materials. Thus, comparisons are possible between different materials, which can be described having “smaller,” “larger” or “similar” effective pore sizes depending on how they perform in a functional test.

[0080] The term “dextran” as used herein refers to a complex, branched glucan (polysaccharide made of many glucose molecules) composed of chains of varying lengths (from 3 to 10,000 kilodaltons).

[0081] The term “polysaccharide” or “polysaccharides” are polymeric carbohydrate molecules composed of long chains of monosaccharide units bound together by glycosidic linkages and on hydrolysis give the constituent monosaccharides or oligosaccharides. Polysaccharides range in structure from linear to highly branched. Examples include storage polysaccharides such as starch and glycogen, and structural polysaccharides such as cellulose and chitin.

[0082] Polysaccharides are often quite heterogeneous, containing slight modifications of the repeating unit. Depending on the structure, these macromolecules can have distinct properties from their monosaccharide building blocks. They may be amorphous or even insoluble in water. When all the monosaccharides in a polysaccharide are the same type, the polysaccharide is called a homopolysaccharide or homoglycan, but when more than one type of monosaccharide is present they are called heteropolysaccharides or heteroglycans.

[0083] The term “conjugated polysaccharide vaccine” as used herein refers to a vaccine which is created by covalently attaching an antigen (e.g., a polysaccharide or polysaccharide based organism) to a carrier protein (preferably from the same microorganism), thereby conferring the immunological attributes of the carrier on the attached antigen. An unconjugated polysaccharide antigen cannot be loaded onto the MHC complex, which can only bind peptides, and thus will not be presented to a T cell for activation of the presenting B cell. In the case of a conjugated polysaccharide vaccine, the carrier peptide linked to the polysaccharide target antigen is able to be presented on the MHC molecule. The T cell that recognizes the carrier peptide will activate the B cell, causing it to produce antibodies to the polysaccharide antigen that it had originally bound. This technique for the creation of an effective immunogen is most often applied to bacterial polysaccharides for the prevention of invasive bacterial disease. Examples of conjugated polysaccharide vaccines known in the art include,

but are not limited to, *Haemophilus influenzae* B (Hib; bacterial meningitis and pneumonia) [Merck, Sanofi, GSK], *Neisseria meningitidis* (bacterial meningitis), [Wyeth Pharmaceuticals, Inc., a subsidiary of Pfizer Inc.], and *Streptococcus pneumonia* (bacterial pneumonia) includes the 13-valent pneumococcal conjugate vaccine (PCV13 [Prevnar 13, Wyeth Pharmaceuticals, Inc., a subsidiary of Pfizer Inc.]). Bioconjugate vaccines against *S. aureus* and *P. aeruginosa*, are also under development.

[0084] The term “virus-like particles” refers to biological materials which resemble viruses, but are non-infectious because they do not contain any viral genetic material. The expression of viral structural proteins, such as Envelope or Capsid, can result in the self-assembly of virus like particles (VLPs). VLPs derived from the Hepatitis B virus and composed of the small HBV derived surface antigen (HBsAg) were described over 40 years ago from patient sera. More recently, VLPs have been produced from components of a wide variety of virus families including Parvoviridae (e.g. adeno-associated virus), Retroviridae (e.g. HIV), and Flaviviridae (e.g. Hepatitis C virus). VLPs can be produced in a variety of cell culture systems including mammalian cell lines, insect cell lines, yeast, and plant cells.

[0085] The phrase “biological material of interest,” as used herein, refers to proteins, virus like particles and vaccines, especially conjugated polysaccharide vaccines, which may be purified using the embodiments described herein. Such biological materials of interest typically have a molecular weight of about 500,000 Daltons or greater than 50000 Daltons.

II. Exemplary Nanofiber Polymeric Materials

[0086] Polymers which may be employed for making nanofiber compositions used in the methods described herein include thermoplastic and thermoset polymers.

Nonlimiting examples of suitable polymers include nylon, polyimide, aliphatic polyamide, aromatic polyamide, polysulfone, cellulose, cellulose acetate, polyether sulfone, polyurethane, poly(urea urethane), polybenzimidazole, polyetherimide, polyacrylonitrile, poly(ethylene terephthalate), polyethylene, polypropylene, polyaniline, poly(ethylene oxide), poly(ethylene naphthalate), poly(butylene terephthalate), styrene butadiene rubber, polystyrene, poly(vinyl chloride), poly(vinyl alcohol), poly(vinyl acetate), poly(vinylidene fluoride), poly(vinyl butylene), copolymers, derivative compounds, blends and combinations thereof. Suitable polyamide condensation polymers, include nylon-6; nylon-4,6; nylon-6,6; nylon 6,6-

6,10; copolymers of the same, and other linear generally aliphatic nylon compositions and the like.

III. Exemplary Methods for Forming a Fibrous Mat/Membrane

[0087] In various embodiments, the nanofiber compositions used in the various embodiments described herein are made using electrospinning processes, which are previously known in the art.

[0088] In some embodiments, a fibrous mat/membrane is made by depositing nanofiber(s) from a nylon solution. The nanofiber mat/membrane has a basis weight of between about 0.1 g/m² and about 10 g/m², as measured on a dry basis, (i.e., after the residual solvent has evaporated or otherwise been removed).

[0089] In other embodiments, nylon is dissolved in a mixture of solvents including, but not limited to, formic acid, sulfuric acid, acetic acid, 2,2,2-trifluoroethanol, 2,2,2,3,3,3-hexafluoropropanol, and water.

[0090] In some embodiments, the nylon solution is prepared by dissolving dry nylon polymer in one group of solvents, i.e. first preparing a stock solution, and then adding other solvents to make the solution ready for electrospinning.

[0091] In some embodiments, the nylon polymer (i.e., starting solution) is partially hydrolyzed over the course of solution preparation, such that the average molecular weight of the partially hydrolyzed nylon polymer (i.e., ending solution) is less than the average molecular weight of the starting nylon polymer.

[0092] In an additional embodiment of the invention, conductivity of the nylon solution is adjusted with a suitable ionizable compound in a given solvent. Examples of such suitable ionizable compounds include, but are not limited to, organic and inorganic salts, acids and bases. An example of a preferred compound used to adjust the conductivity of a nylon solution is ammonium formate.

[0093] In another embodiment of the invention, the environment inside the electrospinning chamber is controlled to ensure that ambient humidity is kept at dew point above approximately 12° C.

[0094] In one embodiment of the invention, a variety of porous single or multilayered substrates or supports are arranged on a moving or stationary collection belt to collect and combine with the electrospun nanofiber mat medium, forming a composite filtration device.

IV. Methods of Using the Membranes in TFF Filtration Mode

[0095] In various embodiments described herein, the electrospun nanofiber compositions are used in TFF mode to purify a biological material of interest (e.g., a protein, conjugated polysaccharide vaccine or a virus-like particle) having a molecular weight of about or greater than 500KDa.

[0096] In case of operation in TFF mode, a pump is generally used to generate flow of the feed stream through the channel between two membrane surfaces. During each pass of fluid over the surface of the membrane, the applied pressure forces a portion of the fluid through the membrane and into the filtrate stream. The result is a gradient in the feedstock concentration from the bulk conditions at the center of the channel to the more concentrated wall conditions at the membrane surface. There is also a concentration gradient along the length of the feed channel from the inlet to the outlet (retentate) as progressively more fluid passes to the filtrate side.

[0097] In some embodiments, the electrospun Nylon-6 Nanofiber Ultrafiltration membrane (NF UF) can be incorporated into Tangential flow filtration modules of several format types similar to the PES UF membrane. The most common formats used for tangential flow filtration are flat plate cassettes (e.g., Pellicon® 3) or spiral wound devices. The NF UF can be made into flat sheet tangential flow filtration packets in a layered structure containing the membrane, retentate and permeate screens, and an outer polymeric film having retentate and permeate ports and then over-molded or injection molded into a flat cassette device with retentate and permeate ports. Alternatively, the NF UF can be wound into a spiral with retentate and permeate screens and sealed on the edges to provide a retentate and permeate flow path and then placed in a cylindrical holder with sealed flow paths to separate retentate and permeate ports. Polymer screens are inserted into the retentate and/or permeate channels in spiral wound and flat plate modules to increase turbulence in the channels and reduce concentration polarization. The turbulence promoted channels have higher mass transfer coefficients at lower cross flow rates, meaning that higher fluxes are achieved with lower pumping requirements. Turbulence-promoted retentate channels are, therefore, more efficient than open channels. Using a suspended screen in a flat plate module gives some of the benefits of both open and turbulence-promoted channels.

[0098] Tangential flow filtration using NF UF membrane can concentrate and purify a biological material of interest such as a conjugated polysaccharide vaccine to a higher purity level by permeating out the smaller impurities and reducing the volume

to increase the concentration to 20 mg/mL of the vaccine product. Also the NF UF membrane can retain the biological material and diafilter or perform a buffer exchange of small salts or pH buffers salts for additional purification steps or final formulation. The experiments described in the Examples below can be used to purify, concentrate, or buffer exchange a conjugate polysaccharide vaccine or biological molecule of interest in the same way as the model Dextrans used herein.

[0099] Embodiments are further illustrated by the following examples which should not be construed as limiting. The contents of all references, patents and published patent applications cited throughout this application, as well as the Figures, are incorporated herein by reference.

Examples

Example 1: Preparation of Nanofiber Mats/Membranes

[00100] Electrospun Nylon-6 nanofiber composite parvovirus retentive mats are made as described in the PCT published patent application no. WO2014093345, incorporated herein by reference, and are designated NF UF (i.e., Nanofiber UF membrane). Nylon-6 under the trademark Ultramid B24 (BASF Corp., Florham Park, NJ, USA) is used to electrospin the bilayered composite base and active retentive layer nanofiber mats from solution onto a smooth Hirose nonwoven substrate (Hirose Paper Manufacturing Co., Ltd, Tosa-City, Kochi, Japan, part number # HOP-60HCF). The base layer is electrospun from 10.3% w/w Nylon-6 in Acetic : Formic Acid mixture (2:1) and is approximately 25-30 microns thick with an average fiber diameter of 70 nm. The active retentive layer with an average fiber diameter of 10 nm is electrospun from a solution of 8.0% w/w Nylon-6 in Acetic acid : Formic acid: water: 2,2,2-trifluoroethanol (TFE): Ammonium Formate mixture (20.5:20.5:10.3:40:0.7) and is estimated to be a few microns thick. The electrospun Nanofiber UF membranes are produced on a pilot scale electrospinning apparatus from Elmarco (Liberec, Czech Republic) using three rotating electrodes at 60 Hz, distance of 140 mm, controlled humidity between 10° and 16° dew point, voltage of 60 kV, and line speed of 2 cm/min.

Example 2: Preparation of Polyethersulfone Ultrafiltration membranes

[00101] Polyethersulfone ultrafiltration membranes (PES UF) are custom made using solution immersion casting onto a polyolefin nonwoven substrate using custom membrane casting equipment (EMD Millipore, Jaffrey, NH USA).

[00102] Generally, the solution immersion process involves the conversion of a homogeneous polymer solutions of two or more components into a two-phase system with a solid, polymer-rich phase forming the rigid membrane structure and a liquid, polymer-poor phase forming the membrane pores. (see, e.g., as described in: *Membranes and Membrane Processes*, 1986 Springer US, Drioli, Enrico; Nakagaki, Masayuki. *Preparation of Microporous Membranes by Phase Inversion Processes*, Strathmann, H., p 115-135).

Example 3: Investigation of Membrane Characterizations

[00103] The characteristics of the two membranes, NF UF and PES UF, are investigated using various techniques described below.

1. SEM Images and Fiber Diameter

[00104] Representative scanning electron micrographs (SEM images) of the electrospun Nylon-6 Nanofiber ultrafiltration membrane (NF UF) and the polyethersulfone ultrafiltration membrane (PES UF) are shown in Figures 1 and 2, respectively. In Figure 1, samples are cut from the discs and mounted on an aluminum SEM stub with double-sided conductive carbon tape. They are then coated with 5 nm of iridium using a Cressington 208HR high resolution sputter coater. The samples are imaged in a FEI Quanta 200F field emission scanning electron microscope (FESEM) at 5kV. The image shows that the Nylon-6 nanofibers are a random overlaying non-woven mat of polymeric fibers with a diameter on the order of ~ 10 nanometers relative to the 500 nanometer scale bar. The porosity in the electrospun NylonNF UF results from the spaces between the overlapping fibers.

[00105] Figure 2 depicts that the porosity of a polyethersulfone ultrafiltration membrane (PES UF) made using a solution phase inversion process. Samples are cut from membrane disks and then mounted on an aluminum SEM stub with double-sided conductive carbon tape. They are then coated with 5 nm of iridium using a Cressington 208HR high resolution sputter coater. The sample images are taken in an FEI Quanta 200F field emission scanning electron microscope (FESEM) at 5kV.

[00106] Comparing the PES UF in Figure 2 to Figure 1 of the electrospun Nylon-6 NF UF shows how drastically different they are in terms of 3-dimensional structure or morphology.

[00107] Fiber radius, as shown in Figure 3, is measured utilizing a custom developed Euclidean Distance Map (EDM) routine within Image Pro Plus v6.0. The average fiber diameter of each nanofiber layer sample is calculated and the final

diameter is determined by subtracting the 5 nm of the metal coating applied during sample preparations for SEM. The mean fiber diameter of the Electrospun Nylon-6 Nanofiber Ultrafiltration membrane (NF UF) is two times the mean radius, then subtracting the 5 nanometers of the metal coating of the sample preparation for SEM.

2. Mean Flow Bubble Point and Water Permeability

[00108] This experiment describes the measurement of the mean bubble point and water permeability, as measured for the NF UF and the PES UF membranes. As demonstrated herein and shown in Figure 4, the NF UF membrane samples exhibit higher water permeability at similar or higher mean flow bubble points than the 4 different samples of the PES UF membranes prescreened for benchmarking.

[00109] Mean flow bubble point is measured according to ASTM E1294-89, “Standard Test Method for Pore Size Characteristics of Membrane Filters Using Automated Liquid Porosimeter”. The automated bubble point method according to ASTM F316 using a custom-built capillary flow porosimeter is similar, in principle, to a commercial apparatus from Porous Materials, Inc. (Ithaca, N.Y, USA). Nanofiber UF (NF UF) membrane samples die cut to 25 mm in diameter with a polyolefin nonwoven substrate are wetted with perfluorohexane Fluorinert™ FC-72 (10 dynes/cm), commercially available from (3M, St. Paul, MN USA). Each sample is placed in a holder, a differential pressure of air is applied and the fluid removed from the sample. The differential pressure at which wet flow is equal to one-half the dry flow (flow without wetting solvent) is used to calculate the mean flow pore size using supplied software.

[00110] Mean flow bubble points of the Polyethersulfone UF (PES UF) membranes are measured using 2-propanol. NF UF membrane mean flow bubble points are adjusted to the surface tension of 2-propanol (21.4 dynes/cm) for comparison to PES UF samples, as shown in Figure 4. Figure 4 shows that four samples of the Electrospun Nylon-6 NF UF membranes with Dextran sieving R90 cutoffs of 1000 kDa have greater water permeability and higher Mean Flow Bubble Points than the PES UF membranes with a Dextran sieving R90 cutoff of 1200 kDa.

[00111] Water permeability in LMH/psi is measured using 44.5 mm diameter membrane disks in 50 mL Stirred Cells (Model 8050, EMD Millipore, Billerica, MA) with a filter area of 13.4 cm² area and 0.5 mL hold-up volume at 3 psi. NF UF membranes die cut with a polyolefin nonwoven substrate are placed dry onto a second polyolefin nonwoven substrate and secured into the Stirred Cell. PES UF membranes

are wet with ethanol, exchanged into water, and secured into the Stirred Cell on a second polyolefin nonwoven disk. Samples are water wet and flushed with 2 x 50 mL water at 5 psi to remove all air.

3. Dextran R90 cutoffs

[00112] In this experiment, Dextran rejection measurements are used to determine Dextran R90 cutoffs for the NF UF and PES UF membranes, as shown in Figure 5. NF UF samples included Dextran R90 cutoffs of 1000 and 1500 kDa. Four different PES UF membrane samples have Dextran R90 cutoffs of 800, 1200, 1700 and 4800 kDa. The four PES UF membranes are common in the industry for the ultrafiltration of macromolecules and demonstrate similar Dextran retention curves to those of the NF UF membrane samples, as shown in Figure 5. Figure 5 shows that four samples of the electrospun Nylon-6 NF UF membrane with Dextran sieving R90 cutoffs of 1000 kDa have similar Dextran sieving curves on both the x and y-axis and in terms of slope relative to duplicate samples of the PES UF membrane with a Dextran sieving R90 cutoff of 1200 kDa.

[00113] NF UF membranes are similar in Dextran R90 and mean flow bubble point to the PES UF membranes, as demonstrated in Figure 6 and show higher water permeability at similar Dextran R90, as shown in Figure 7.

[00114] Figure 6 shows that four samples of the electrospun Nylon-6 NF UF membrane samples with Dextran sieving R90 cutoffs of 1000 kDa have lower Dextran sieving R90 cutoffs and higher mean flow bubble points than the PES UF membrane samples with a Dextran sieving R90 cutoff of 1200 kDa. The Electrospun Nylon-6 Nanofiber Ultrafiltration membrane (NF UF) has smaller average pore size that provides higher bubble points and lower Dextran sieving R90 cutoffs.

[00115] Figure 7 shows that four samples of the Electrospun Nylon-6 NF UF membrane samples with Dextran sieving R90 cutoffs of 1000 kDa have greater water permeability and lower Dextran sieving R90 than the PES UF membrane samples with a higher Dextran sieving R90 cutoff of 1200 kDa.

[00116] Dextran molecular weight sieving measurements of the NF UF and PES UF membranes are made using a custom Dextran retention test. All membrane samples are prepared in Stirred Cells and pre-flushed as described in Example 3-2. Analytical size-exclusion chromatography of the feed and permeate samples is used to generate the MW rejection and sieving curves from which the Dextran R90 cutoff is determined for each membrane.

[00117] A mixed Dextran feed of 0.75% w/w Dextrans in pH 7.0 50 mM phosphate buffer is used to challenge the NF UF or PES UF membranes. Dextrans are purchased from Pharmacosmos A/S (Roervangsvej 30, DK-4300, Holbaek, Denmark). The average molecular weights (M_w) of the Dextrans used are as follows: 1,000 Da (Dextran T1, 5510 0001 4000); 3,500 Da (Dextran T3.5, 5510 0003 4007); 10,000 Da (Dextran T10, 5510 0010 4007); 40,000 Da (Dextran T40, 5510 0040 4007); 70,000 Da (Dextran T70, 5510 0070 4007); 500,000 Da (Dextran T500, 5510 0500 4006); and 2,000,000 Da (Dextran T2000, 5510 2000 4007).

[00118] 40 mL of the mixed Dextran feed is poured into the Stirred Cell. A standard magnetic stir bar is placed in the cell and set to stir on a magnetic stir plate at 320 RPM. PVC tubing 1/16" ID (Fisher scientific catalog no. 14-190-118) attached to a peristaltic pump is connected to the permeate side to draw liquid at constant flow rate of 0.22 mL/min. Under constant Flux of 10 LMH, the first 2 to 3 ml is discarded, then re-circulated for about one hour to allow equilibration, and a permeate sample is collected for further analysis using gel permeation chromatography (GPC).

[00119] Analytical size-exclusion chromatography of Dextrans is performed with a Waters 2695 separation module and a Waters 2414 refractive index detector using a Phenomenex Shodex OH pak 13 μ m SB-806 M HQ gel filtration column (part number: SB-806MHQ, column size: 300 $\times$ 8 mm, Phenomenex Inc., Torrance, CA). The isocratic mobile phase is composed of 50 mM potassium phosphate at pH 7.0 with 10 mg/L of sodium azide. The column is run at a flow rate of 1.0 mL/min for 20 min at a temperature of 35°C.

[00120] Molecular weight Dextran standards used to calibrate molecular weight from retention time are purchased from Sigma-Aldrich (St. Louis, MO), Glucose, MW = 180 Da (#158968), Maltoheptaose, MW = 1,153 Da (#284017) and American Polymer Standards (Mentor, OH) Dextrans: M_p = 2,800 Da (DXT3K), M_p = 6,300 Da (DXT7K), M_p = 20,500 Da (DXT25K), M_p = 43,000 Da (DXT47K), M_p = 85,000 Da (DXT97K), M_p = 245,000 Da (DXT325K), M_p = 350,000 Da (DXT550K), M_p = 1,465,000 Da (DXT2100K), M_p = 6,300,000 Da (DXT5900K), and M_p = 9,110,000 Da (DXT 8035K), where M_p is the mean peak molecular weight.

Example 4: TFF (UF/DF) Membrane Application Comparison Using Custom Feeds

[00121] The Nanofiber UF with a R_{90} = 1000 kDa and PES UF membrane with a R_{90} = 1200 kDa are chosen for the membrane comparison in TFF (UF/DF)

modes using custom Dextran feeds summarized in Table 1 below. The aforementioned membranes are designated NF UF and PES UF and have the physical properties which are demonstrated in Figures 4 – 7.

[00122] The electrospun NF UF membrane has an equivalent or improved performance to the solution immersion cast PES UF membrane in Tangential Flow Filtration (TFF) mode. Both ultrafiltration and diafiltration modes for Dextran concentration and low molecular weight clearance showed the Nanofiber membrane behaves like an ultrafiltration membrane with respect to yield, selectivity, and filtration flux, as summarized in Table 1.

Table 1

Example #	Model Feed	Water		Feed A (0.0385% w/w)		Feed B (0.844% w/w)		Feed C (8.44% w/w)	
	Membrane	NF UF	PES UF	NF UF	PES UF	NF UF	PES UF	NF UF	PES UF
5,6,7	<u>Transport & Selectivity</u>	TMP = 3 psi		TMP = 0.25 - 7 psi		TMP = 3 - 20 psi		TMP = 3 - 20 psi	
3-2	Water Permeability	NF UF > PES UF		N/A		N/A		N/A	
5	Flux vs TMP	N/A		NF UF > PES UF		NF UF > PES UF		NF UF > PES UF	
6	Mass Transport vs TMP			NF UF > PES UF		NF UF > PES UF		NF UF > PES UF	
7	Selectivity vs Flux			NF UF $\geq$ PES UF		NF UF $\geq$ PES UF		NF UF $\geq$ PES UF	
8	<u>Diafiltration</u>	N/A		1.) 30 LMH @ 640 RPM 2.) 60 LMH @ 320 RPM		N/A		N/A	
8	Yield	N/A		NF UF $\geq$ PES UF		N/A		N/A	
8	Selectivity	N/A		NF UF $\geq$ PES UF		N/A		N/A	
9	<u>Ultrafiltration</u>	N/A		1.) 0.5 psi @ 600 RPM Concentrate 2, 4, and 8x		1.) 5 psi @ 600 RPM 2.) 7 psi @ 600 RPM Concentrate 2, 4, 8x		1.) 5 psi @ 300 RPM 2.) 7 psi @ 300 RPM Concentrate 2 and 3x	
9	Yield	N/A		NF UF $\geq$ PES UF		NF UF $\geq$ PES UF		NF UF $\geq$ PES UF	
9	Selectivity	N/A		NF UF $\geq$ PES UF		NF UF $\geq$ PES UF		NF UF $\geq$ PES UF	
9	Flux	N/A		NF UF > PES UF		NF UF > PES UF		NF UF > PES UF	

[00123] The membranes are examined side-by-side in duplicate in TFF mode for transport and selectivity, diafiltration and ultrafiltration. Table 1 and the remaining examples summarize the experimental comparison. The transport and selectivity are measured by Flux versus TMP, Mass Transport versus TMP and Selectivity versus Flux by sampling retentates and permeates through the Flux versus TMP experiment.

[00124] Three custom Dextran feeds are prepared for the NF UF and PES UF TFF (UF/DF) membrane evaluations in order to simulate the concentration and separation steps used in the conjugated polysaccharide vaccine industry.

[00125] The Dextrans used are commercially available from Pharmacosmos A/S (Roervangsvej 30, DK-4300, Holbaek, Denmark): 2,000,000 Da Dextran (T2000, 5510 2000 9007) and 110,000 Da Dextran (T110, 5510 0110 9006) with weight average molecular weights (M_w) of 1,950,000 and 112,000 Da. The three feeds A, B, and C covering 3 orders of magnitude are: 0.0385; 0.844; and 8.44% w/w total

Dextran mass percent in pH 7.0 50 mM phosphate buffer, as shown in Table 2. Table 2 details the mass % of each Pharmacosmos stock number, mass ratios, and viscosity at 20°C.

Table 2. Summary of TFF (UF/DF) membrane application comparison

<u>Feed</u>	<u>Total Dextran (% w/w)</u>	<u>μ, 20°C (cP)</u>	<u>Mass Ratio (T2000:T110)</u>	<u>T2000 (% w/w)</u>	<u>T110 (% w/w)</u>
A	0.0385	3.1	10:1	0.0350	0.0035
B	0.844	4.5	18:1	0.800	0.044
C	8.44	27.4	18:1	8.00	0.44

[00126] The three feeds have very polydisperse molecular weight distributions ranging by 3 orders of magnitude from 10,000 to 10,000,000 Da, as can be seen in the gel permeation chromatograms of Feed A, as shown in Figure 8, using 0.0385% w/w Dextran and gel permeation chromatograms of Feeds B and C, as shown in Figure 9, using 0.844% and 8.44% w/w Dextran, where Feed C is 10x Feed B or results in a chromatogram as shown in Figure 9 when diluted 1:10 with buffer.

[00127] The three molecular weights 7,250,000 Da (D7250), 2,000,000 Da (D2000), and 110,000 Da (D110) are selected for the following comparative ultrafiltration and diafiltration Examples.

[00128] The chromatogram in Figure 8 shows that Feed A has a very polydisperse molecular weight distribution covering 3 orders of magnitude from 10,000 to 10,000,000 Daltons. The percentages of the three molecular weights 7,250,000 Da (D7250), 2,000,000 Da (D2000), and 110,000 Da (D110) in Table 3 are from the peak areas of each MW over the total area.

[00129] The chromatogram in Figure 9 shows that Feed B has very polydisperse molecular weight distribution covering 3 orders of magnitude from 10,000 to 10,000,000 Daltons. The percentages of the three molecular weights 7,250,000 Da (D7250), 2,000,000 Da (D2000), and 110,000 Da (D110) in Table 3 are from the peak areas of each MW over the total area. Feed C in Tables 2 and 3 is 10x Feed B or identical to Figure 9 when diluted 1:10 with buffer.

[00130] Table 3 summarizes the actual peak height percentage of Dextran with MW of 7,250,000 Da (D7250), 2,000,000 Da (D2000), and 110,000 Da (D110) in each of the three feeds. Based on the peak height percentage of 7,250,000 Da (D7250), 2,000,000 Da (D2000), and 110,000 Da (D110) in the feeds and the total

Dextran mass percents of 0.0385, 0.844, and 8.44%, the actual percentage of D7250, D2000, and D110 are calculated, as summarized in Table 3.

Table 3. Custom Dextran Feeds

<u>Feed</u>	<u>Total Dextran (% w/w)</u>				<u>Actual (% w/w)</u>		
		<u>D7250 (%)</u>	<u>D2000 (%)</u>	<u>D110 (%)</u>	<u>D7250</u>	<u>D2000</u>	<u>D110</u>
A	0.0385	0.475	0.941	0.854	1.829×10^{-4}	3.623×10^{-4}	3.288×10^{-4}
B	0.844	0.402	0.768	1.046	3.393×10^{-3}	6.482×10^{-3}	8.828×10^{-3}
C	8.44				3.393×10^{-2}	6.482×10^{-2}	8.828×10^{-2}

[00131] In the subsequent experiments, the concentrations, yields, and selectivity are all calculated based on the actual peak heights at each MW versus the feed chromatograms, as demonstrated by Figures 8 and 9 and based on the percentages in Table 3 for the three selected molecular weights under examination of D7250, D2000, and D110.

[00132] Samples are diluted as needed to remain on scale of the GPC refractive index detector and adjusted when needed for dilution. A dilution series of Feeds A and B are used to generate the concentration equations for D7250, D2000, and D110 in order to calculate the concentrations of each MW in the Ultrafiltration concentration experiments, as discussed in detail in Example 9.

Example 5. Measurement of Feed Flux Versus TMP

[00133] Custom Dextran Feeds A, B, and C, demonstrated in Tables 2 and 3, are used to generate average flux versus trans-membrane pressure (TMP) curves. Figures 10, 11, and 12 for feeds A, B, and C, respectively, demonstrate that the NF UF membrane has higher average Dextran Feed flux versus TMP than the PES UF membrane having similar Dextran R90 cutoffs. The average flux for feeds A, B, and C cover three orders of magnitude in LMH, as shown in Figures 10, 11, 12, respectively, and there is mass transport polarization for the high concentration feed C in case of both the NF UF and PES UF membranes, as shown in Figure 12.

[00134] The NF UF membrane had both higher average Dextran feed flux versus TMP, as demonstrated in Figures 10, 11 and 12 as well as higher water flux, as shown in Figure 7.

[00135] Experiments are conducted in Stirred Cells as described in Example 3. Feeds are stirred at 320 RPM and pressurized using house air. Feed and permeate samples are collected at each pressure for GPC analysis.

[00136] Figure 10 shows that the electrospun Nylon-6 NF UF membrane with a Dextran sieving R90 cutoff of 1000 kDa has greater Feed A Flux at the same TMP compared to the PES UF membrane with a higher Dextran sieving R90 cutoff of 1200 kDa.

[00137] Figure 11 shows that the electrospun Nylon-6 NF UF membrane with a Dextran sieving R90 cutoff of 1000 kDa has greater Feed B Flux versus TMP than the PES UF membrane with a higher Dextran sieving R90 cutoff of 1200 kDa.

[00138] Figure 12 shows that the electrospun Nylon-6 NF UF membrane with a Dextran sieving R90 cutoff of 1000 kDa has greater Feed C Flux versus TMP than the PES UF membrane with a higher Dextran sieving R90 cutoff of 1200 kDa.

Example 6. Measurement of Mass Transport Versus TMP

[00139] The Dextran mass/concentration transport is measured by collecting feed and permeate samples from Example 5 at each pressure for GPC analysis. Figures 13 and 14 demonstrate the gel permeation chromatograms of Feed A for one of the two samples of the NF UF and PES UF membrane samples. The transport of D7250, D2000, and D110 are determined by the ratio C_P / C_F where C_P and C_F are the concentrations in the feed and permeate at each pressure.

[00140] Figures 13 and 14 demonstrate how the Feed A concentration slightly increases through the Flux versus TMP experiment.

[00141] In Figure 13, the chromatograms overlay shows how the Feed A concentration in the permeate is initially higher and then decreases slightly before increasing again through the Flux versus TMP experiment, indicating that the membrane initially passes more of the D7250, D2000, and D110 before a surface concentration polarization equilibrium can form.

[00142] In Figure 14, the chromatograms overlay show how the Feed A concentration in the permeate is initially higher and then slightly decreases before increasing again through the Flux versus TMP experiment, indicating the membrane initially passes more of the D7250, D2000, and D110 before a surface concentration polarization equilibrium can form.

[00143] In case of Figure 15, the transport of D7250, D2000, and D110 is the ratio C_P / C_F , where C_P and C_F are the concentrations in the feed and permeate at each

TMP (psi). Figure 15 shows that the average mass/concentration transport for Dextrans in Feed A is greater versus TMP for the electrospun Nylon-6 NF UF relative to the PES UF membranes.

[00144] In case of Figure 16, the transport of D7250, D2000, and D110 is the ratio C_P / C_F , where C_P and C_F are the concentrations in the feed and permeate at each TMP (psi). Figure 16 shows that the average mass/concentration transport for Dextrans in Feed B is greater versus TMP for the electrospun Nylon-6 NF UF membrane than the PES UF membrane.

[00145] To summarize, as observed, the mass transport or concentration passage of Dextrans D7250, D2000, and D110 for the NF UF membrane (as shown in Figure 13) is higher than for the PES UF membrane (as shown in Figure 14). The average C_P / C_F is calculated for Feed A and plotted versus the TMP (as shown in Figure 15). Both the NF UF and PES UF membranes initially pass more of the D7250, D2000, and D110 before a surface concentration polarization equilibrium can form (as shown in Figures 13, 14, and 15). The average mass/concentration transport for Dextrans in Feed B is greater for the NF UF membrane relative to the PES UF membrane (as shown in Figure 16).

Example 7. Measurement of Selectivity Versus Flux

[00146] The mass transport relationship C_P / C_F from Example 6 for D7250, D2000, and D110 is used to generate a selectivity factor versus flux from the flux versus TMP data above. The selectivity factor is determined using the equation $[(C_P / C_F)_{D110} / (C_P / C_F)_{D2000 \text{ or } D7250}]$ in order to determine the average passage selectivity of D110/D2000 and D110/D7250 versus flux.

[00147] Average selectivity factor versus flux for the NF UF and PES UF membranes using Feeds A and B is shown in Figures 17 and 18 respectively. As observed, the PES UF membrane has higher selectivity factors than the NF UF membrane with increase in TMP/Flux, however, the average selectivity approaches 1 at similar flux for both the NF UF and PES UF membranes with Feeds A and B (as shown in Figures 17 and 18, respectively). Both membranes have their best selectivity at low constant flux. The hold-up volume of 0.5 mL in the 50 mL Stirred Cell causes some dilution and shift in the actual data versus TMP and flux.

[00148] Figure 17 shows that the electrospun Nylon-6 NF UF and PES UF membranes have similar selectivities of D110/D2000 and D110/D7250 using Feed A

versus average flux (LMH) and that both are greater than 1 and approach 1 at similar flux.

[00149] Figure 18 shows that the electrospun Nylon-6 NF UF) and PES UF membranes have similar selectivities of D110/D2000 and D110/D7250 using Feed B versus average flux (LMH) and that both are greater than 1 and approach 1 at similar flux.

Example 8. Measurement of Diafiltration at Constant Flux

[00150] Two constant volume Diafiltration experiments in duplicate are conducted to compare the NF UF and PES UF membranes using Feed A. Stirred Cells with membrane samples are prepared, as described above. Peristaltic pumps with matching flow rates equivalent to 30 or 60 LMH (0.68 or 1.36 mL/min) are used to draw from the permeate and feed the retentate with buffer. Retentate and permeate samples are taken at each 40 mL diavolume for analysis by GPC. The 30 LMH experiment is stirred at 640 RPM and the 60 LMH at 320 RPM.

[00151] Figures 19 and 20 show the gel permeation chromatograms of the retentate and permeate samples at each diavolume from 1 to 6 for one of the duplicates for the NF UF and PES UF membrane samples from the 30 LMH and 640 RPM experimental run. Both the NF UF and PES UF membranes behave similarly in selectively retaining the higher MW Dextran (D7250, D2000) and permeating the lower MW Dextran (D110), as shown in Figures 21 and 22.

[00152] The chromatogram overlay in Figure 19 shows how Feed A concentration is initially higher and then with the increasing diavolumes, the retentates MW distribution shifts to the left towards higher MW while the permeates shift to the right towards lower MW.

[00153] The chromatogram overlay in Figure 20 shows how Feed A concentration is initially higher and then with increasing diavolumes, the retentates MW distribution shifts to the left towards higher MW while the permeates shift to the right towards lower MW.

[00154] The average retentate C/C_0 versus diavolumes of Feed A is calculated for the Diafiltration at 30 LMH and 640 RPM (as shown in Figure 21) and 60 LMH and 320 RPM (as shown in Figure 23). Under both diafiltration conditions, the NF UF and PES UF membranes have similar average retention yields versus diavolumes for D7250, D2000, and D110 (as shown in Figures 21 and 23).

[00155] Figure 21 shows that the NF UF and the PES UF membranes have similar average retention yields versus diavolumes for D7250, D2000, and D110.

[00156] Figure 22 shows that the NF UF and the PES UF membranes have similar average retentate selectivity for D7250/D110 and D2000/D110 versus diavolume.

[00157] Figure 23 shows that the NF UF and the PES UF membranes have similar average retention yields versus diavolumes for D7250, D2000, and D110. Both membranes have similar lower retention at higher flux and lower stirring, than observed in Figure 21.

[00158] The average retentate selectivities for the NF UF and PES UF membranes in Figures 21 and 23 are calculated using $D7250/D110 = (C/C_0)_{D7250}/(C/C_0)_{D110}$ and $D2000/D110 = (C/C_0)_{D2000}/(C/C_0)_{D110}$ and plotted versus diavolumes (as shown in Figures 22 and 24).

[00159] Figure 24 shows that the NF UF and the PES UF membranes have similar average retentate selectivity for D7250/D110 and D2000/D110 versus diavolume. Both membranes have similar lower average retentate selectivity at higher flux and lower stirring than observed in Figure 22.

[00160] The average D7250/D110 and D2000/D110 are very similar for both the NF UF and PES UF membranes at both 30 LMH at 640 RPM and 60 LMH at 320 RPM. Both membranes have similar lower retention (as shown in Figure 23) and selectivity (as shown in Figure 24) at higher flux and lower stirring.

Example 9. Ultrafiltration at constant TMP

[00161] Five ultrafiltration concentration experiments are conducted in duplicate to compare the NF UF and PES UF membranes at different conditions of constant TMP and stirring using Feeds A, B, and C (summarized in Table 1). Feed A (as shown in Figures 25, 26, 27) under 1 condition, Feed B (as shown in Figures 28 and 29) under 2 conditions, and Feed C (as shown in Figures 30, 31, 32) under 2 conditions.

[00162] All five UF concentration runs show that the NF UF and PES UF membranes provide similar average yield and selectivity, while the NF UF membrane has consistently higher average flux over the UF concentration factors for all the feeds and conditions.

[00163] Stirred Cells with membrane samples for each condition are prepared in duplicate, as described in Example 3-2. Permeate volume over time is measured in

order to determine flux and track concentration factors. Retentate samples are taken at each concentration factor for GPC analysis to determine Yield and Selectivity of D7250, D2000, and D110, as described above.

[00164] Feeds A and B with 0.0385 and 0.844% w/w total Dextran mass percent (as set forth in Table 2) are concentrated to 2, 4, and 8x from the initial 50 mL volume. Feed A is concentrated at a constant TMP = 0.5 psi and 600 RPM (as shown in Figures 25, 26, 27). Figure 25 shows that NF UF membrane has higher initial average feed flux compared to the PES UF membrane and maintains it throughout the 2, 4 and 8x concentration runs. Figure 26 shows similar average yield and selectivity for D7250, D2000, and D110 as C / C_{theo} versus concentration factor during 2, 4 and 8x ultrafiltration concentration runs. Figure 27 shows average C / C_{theo} versus average Flux during the 2, 4, 8x (Left to Right) ultrafiltration concentration where NF UF and PES UF membranes have similar average yield and selectivity, while the NF UF membrane has a consistently higher average flux during the 2, 4 and 8x concentration runs.

[00165] Feed B is concentrated at 5 psi and 600 RPM (as shown in Figure 28) and 7 psi and 600 RPM (as shown in Figure 29). Better yield and selectivity is observed for both the NF UF and PES NF membranes at the lower pressure (see, Figure 28 versus 29), but a slightly higher average flux as expected at 7 psi (as shown in Figure 29).

[00166] Feed C with 8.44% w/w total Dextran mass percent (as set forth in Table 2) is concentrated to 2 and 3x from an initial volume of 40 mL. Feed C is concentrated at 5 psi and 300 RPM (as shown in Figures 30 and 31) and at 7 psi and 300 RPM (as shown in Figure 32). In case of Feed C, after 2x concentration, the pressure is increased to 12 psi and it is observed in all cases that the flux and yield decrease for the NF UF and PES UF membranes. Figure 30 shows the flux decrease for both the NF UF and PES UF membranes at 5 psi. Yields and selectivities are similar for the NF UF and PES UF membranes, while the NF UF membrane has a consistently higher average flux during the 2 and 3x concentration runs (as shown in Figures 31 and 32).

Example 10: TFF System for the Purification of a Biological Material Using NF UF Membrane

[00167] In a representative example, the NF UF membrane is used in a TFF mode to purify a biological material of interest having a molecular weight greater than

500 KDa. Examples of such biological materials include, but are not limited to, conjugated polysaccharide vaccine, other types of vaccines, virus like particles, and proteins with MW > 500,000 Daltons.

[00168] A schematic of a TFF system used for the purification of a biological material of interest using the NF UF membrane is shown in Figure 33. The biological material of interest is present in a feed hold tank or vessel. The typical equipment used are additional buffer tanks or vessels, feed pump, feed valve, feed pressure gauge, TFF modules containing the NF UF membrane such as flat plate cassettes with holders or spiral wound devices with fittings, retentate pressure gauge, retentate valve to control pressure, and permeate vessels. If the feed is being concentrated by ultrafiltration the retentate is returned to the feed tank, if diafiltration is being performed a separate vessel collects the retentate and a diafiltration buffer vessel is plumbed into the feed pump.

[00169] The specification is most thoroughly understood in light of the teachings of the references cited within the specification which are hereby incorporated by reference. The embodiments within the specification provide an illustration of embodiments and should not be construed as limiting in scope. The skilled artisan (practitioner) readily recognizes that many other embodiments are encompassed by this disclosure. All publications and reference materials are incorporated by reference in their entirety. To the extent that the material incorporated by reference contradicts or is inconsistent with the present specification, the present specification will supercede any such material. The citation of any references herein is not an admission that such references are prior art.

[00170] Unless otherwise indicated, all numbers expressing quantities of ingredients, cell culture, treatment conditions, and so forth used in the specification, including claims, are to be understood as being modified in all instances by the term “about.” Accordingly, unless otherwise indicated to the contrary, the numerical parameters are approximations and may vary depending upon the desired properties sought to be obtained by the embodiments disclosed herein. Unless otherwise indicated, the term “at least” preceding a series of elements is to be understood to refer to every element in the series. Those skilled in the art will recognize, or be able to ascertain using no more than routine experimentation, many equivalents to the specific embodiments described herein. Such equivalents are intended to be encompassed by the following claims.

[00171] Many modifications and variations of the embodiments disclosed herein can be made without departing from its spirit and scope, as will be apparent to those skilled in the art. The specific embodiments described herein are offered by way of example only and are not meant to be limiting in any way. It is intended that the specification and examples be considered as exemplary only, with a true scope and spirit of the disclosure being indicated by the following claims.

Claims

What is claimed is:

1. Method of purifying a biological material of interest in a sample comprising:
 - a. providing a sample containing the biological material of interest having a molecular weight equal to or greater than 500 KDa, wherein the biological material of interest is selected from a therapeutic protein, a conjugated polysaccharide vaccine and a virus-like particle;
 - b. contacting the sample in tangential filtration (TFF) mode with an electrospun nanofiber membrane composition comprising nylon nanofibers having an average fiber diameter less than 15 nm, thereby resulting in a permeate and a retentate; and
 - c. collecting the retentate containing the biological material of interest, thereby purifying the biological material of interest.
2. The method of claim 1, wherein the method results in an increase in the concentration of the biological material of interest.
3. The method of claim 1, wherein the electrospun nanofiber composition exhibits a higher water permeability in TFF mode compared to a solution cast polymeric membrane.
4. The method of claim 1, wherein the electrospun nanofiber membrane composition exhibits a higher flux in TFF mode compared to a solution cast polymeric membrane.
5. The method of claim 1, wherein the collecting step comprises diafiltration.
6. The method of claim 1, wherein the electrospun nanofiber membrane composition is made from Nylon-6.
7. The method of claim 1, wherein the purified biological material of interest has a 90% yield or greater than 90% yield.
8. The method of claim 1, wherein the electrospun nanofiber membrane composition is incorporated into a device suitable for TFF.
9. The method of claim 8, wherein the device is a cassette or a spiral wound device.