## CLAIMS

1. A resin composition, comprising:

(A) an acrylic resin;

(B) a multifunctional nitrogen-containing heterocyclic compound represented by chemical formula (1) or chemical formula (2)




(C) a latent curing agent;

(D) a radical polymerization inhibitor; and

(E) an anionic polymerization retarder.

2. The resin composition according to claim 1, further comprising:

(F) a compound having a glycidyl group, other than the acrylic resin.

3. The resin composition according to claim 2, wherein the (F) component is a vinyl compound having at least one glycidyl group.

4. The resin composition according to claim 2, wherein the (F) component is polybutadiene having at least one glycidyl group.

5. The resin composition according to claim 1, wherein [thiol equivalent of (B) component]/[acryl equivalent of (A) component] is 0.5 to 2.0.

6. The resin composition according to claim 1, wherein the content of the (D) component is 0.0001 to 1.0 part by mass with respect to 100 parts by mass of the resin composition.

7. The resin composition according to claim 1, wherein the content of the (E) component is 0.001 to 1.0 part by mass with respect to 1 part by mass of the (C) component.

8. The resin composition according to claim 1, wherein the (D) component is at least one selected from the group consisting of N-nitroso-N-phenylhydroxylamine aluminum, triphenylphosphine, p-methoxyphenol, and hydroquinone.

9. The resin composition according to claim 1, wherein the (E) component is at least one selected from the group consisting of boric acid ester, aluminum chelate, and organic acid.

10. An adhesive agent comprising the resin composition according to claim 1.

11. A sealing agent comprising the resin composition according to claim 1.

12. The resin composition according to claim 2, wherein [thiol equivalent of (B) component]/[acryl equivalent of (A) component] is 0.5 to 2.0.

13. The resin composition according to claim 2, wherein the content of the (D) component is 0.0001 to 1.0 part by mass with respect to 100 parts by mass of the resin composition.

14. The resin composition according to claim 2, wherein the content of the (E) component is 0.001 to 1.0 part by mass with respect to 1 part by mass of the (C) component.

15. The resin composition according to claim 2, wherein the (D) component is at least one selected from the group consisting of N-nitroso-N-phenylhydroxylamine aluminum, triphenylphosphine, p-methoxyphenol, and hydroquinone.

16. The resin composition according to claim 2, wherein the (E) component is at least one selected from the group consisting of boric acid ester, aluminum chelate, and organic acid.

17. An adhesive agent comprising the resin composition according to claim 2.

18. A sealing agent comprising the resin composition according to claim 2.