

**PANEL OR SLAB FORMED BY STONE AGGLOMERATE CONTAINING AN
ORGANIC BINDER OF A PLANT ORIGIN**

Technical Field of the Invention

5 The present invention relates to panels or slabs formed
by stone agglomerate for the manufacture of which an organic
binder containing an ingredient of a plant origin is used. The
panels or slabs, object of the invention, are formed from
stone materials or the like, granulated and subsequently
10 agglomerated by means of a binder, specifically an organic
resin containing one or more polyols of a plant origin.

 Furthermore, by means of using this binder together with
materials from waste and used and/or recycled products, a
material with good features and with a very high content of
15 recycled material or material of a renewable origin can be
obtained.

 The manufactured panel or slab containing a resin part
of a plant origin of the present invention is particularly
suitable for its use indoors as a kitchen counter, a bathroom
20 counter, or any work surface, as well as for its use as
flooring or sidings.

Background of the Invention

 The process of manufacturing stone blocks, commercially
known as Brentonstone, described in document US 4,698,010, is
25 well known. By means of said process, a mass of inorganic
fillers of a known particle size, pigments or dyes, an organic
binder and additives is formed, in amounts suitable to make
the formation of said material possible by means of the
simultaneous action of vacuum compression and vibration.

30 There are currently several patent documents, such as
for example, US 2006/0162618 A1, ES 2166947 T3, WO 2005/111126
A1, WO 99/23045 A1, which describe processes for obtaining
slabs from stone materials, generally granulated materials
which are agglomerated in most cases by means of a binder that
35 is usually a polyester, epoxy or acrylic type thermoset

organic resin and, in any case, a petrochemical polymer, with an amount of synthetic diluents such as styrene, toluene, xylene, etc., and other additives, as the case may be.

Document ES 2187313 A1, by the authors of the present application, describes a method for manufacturing artificial stone slabs that can be applied to decoration from a mixture of ground materials with different particle sizes of silicas, glasses, granites, ferro-silicon quartz, marble or other similar materials and 7% to 14% by weight of polyester resin, as well as other additives, such as a dye for example, as well as a catalyst, a coupling agent and accelerant which act on the resin. Also by the same authors, document WO 2005/014256 A1 describes a material with appearance of natural stone formed from a mixture of natural stone materials and 6% to 30% by weight of polyester resin, to which an antimicrobial material is added to prevent the proliferation of bacteria or microbes on the surface, the obtained material being suitable for domestic use, specifically in bathroom and kitchen counters. Likewise, in document WO 2006/134179 A2, slabs of artificial stone and polymerizable resin (4% to 15% polyester) having a veined effect are obtained by using the vacuum vibro-compression technique like in the two documents mentioned above.

Document EP 2011632 A2, also by the authors of the present application, describes a process for manufacturing slabs with mixtures similar to those described in the previous documents and 5% to 15% polyester resin, characterized in that the curing process for obtaining the hardening of said resin is carried out by means of microwave irradiation and calcium carbonate or sulfate are added to the resin as catalysts to facilitate said process.

In recent years, the consumption of stone agglomerates for their use as kitchen counters, bathroom counters or as a work surface in general, and also for their use as flooring or wall cladding, has considerably increased, being a very common

product so the production level and, therefore, the consumption of resin, have greatly increased.

As a result, an important part of research in this field has been dedicated to searching for components which come from renewable and/or recycled raw materials that are more environmentally friendly and make the overall process cleaner and more efficient, and at the same time allow manufacturing a material with excellent mechanical and aesthetic features.

Thus, raw materials from stone waste from construction, recycled glass, industrial waste, etc., are described in various patent documents, such as for example document KR 20020051443, which describes the manufacture of construction materials, such as bricks, blocks, tiles, etc, using limestone and waste materials generally from construction. Document ES 2249163 A1 describes a system of using disposable alabaster waste, using said waste in a container where a settling process is carried out by vibrating said waste, and the polyester resin is subsequently poured in, with which the combination is mixed under vacuum. The resin used is preferably polyester resin mixed with alabaster or dolomite powder.

Other documents using waste materials are, for example, WO 00/44686 A1 which uses waste glass for manufacturing artificial stone, and ES 2121529 A1 which uses ground recycled glass for manufacturing cement agglomerates. Document WO 89/11457 A1 also uses a synthetic resin with a mixture of recycled glass and new glass, among other materials, to obtain artificial stone with a natural appearance.

Document US 2006/0051598 A1 describes a slab or block manufactured from an agglomerate material comprising fragments, in the form of powder, grit or the like, and pure silicon tablets previously used in the electronic industry as wafer supporting microchips and silicon tablets of printed circuits, mixing all the components with an agglutinating agent and a dye for obtaining the desired product.

There are also documents in the state of the art which describe the use of resins that are less aggressive with the environment, or in which the reactive solvent which usually contains said resin is removed. As in the case of patent application WO 2007/138529 A2, which describes the manufacture of a stone agglomerate from the use of a polyester resin free of reactive diluents (without styrene) and formed by the reaction between an epoxidized triglyceride and at least one carboxylic anhydride and in which the necessary triglycerides can be obtained starting from vegetable or animal fats. With this method, which is already known in other sectors as shown in documents US 3,296,202 and DE19627165, a resin is obtained which is not a polyester resin *per se*, but rather a partially epoxidized system. Despite the fact that the physico-mechanical properties of these resins are very satisfactory, the main problem with their use is that it would be necessary to have the process infrastructure suitable epoxidizing the fatty acids and, with it, obtaining the resin. Furthermore, the catalytic system needed for polymerizing this resin is completely different from the systems which are used today, which would make it necessary to make substantial mechanical changes in the already implemented processes, with the economic investment this involves, and eliminating the possibility of being able to reuse current systems.

Instead of removing the styrene which is used with the resin, another possibility would be to obtain said resin from elements of a plant origin. Thus, document US 6,222,005 B1 describes a process for preparing a polyester resin by means of two steps: a) reacting a carboxylic acid, containing at least two carboxyl groups, or its corresponding anhydride containing one ethylenic unsaturation with a saturated, monohydric alcohol having a boiling point of less than 150°C, in an amount sufficient to obtain the half ester, and b) reacting the half ester obtained in (a) with a polyol in the presence of an oil containing one unsaturation or the

corresponding fatty acid, which can be present by up to 45%. Said oil is selected from the group of castor, peanut, olive, cottonseed, soybean or rape seed oil. The use of said unsaturated oils allows reducing the use of petroleum byproducts. The resin thus obtained is used in the manufacture of composites for agricultural, marine and transport equipment.

Therefore, there is still a need to develop polyester resins derived from petroleum byproducts, with optimal properties for manufacturing quartz agglomerates in which the glycols of a petrochemical origin are partially substituted with glycols obtained from a plant origin, the catalytic system of which is the one typically used and does not require mechanical changes in the process and obtains a quartz agglomerate with features similar to or better than those traditionally obtained.

Thus, the present invention describes a panel or slab formed from a polyester resin which has been partially replaced with polyols of a plant origin, such as from corn, for example. Furthermore, it has surprisingly been found that said resin containing polyols of a plant origin is perfectly suitable for the process of manufacturing said panel or slab, partially or entirely substituting the conventional inorganic aggregates with others from different industrial processes or other uses, such as ground glass from recycled bottles, flat glass from the glass manufacturing industry, porcelain material from waste processes in processes for manufacturing porcelain, etc,. Thus, a panel or slab with resin of a plant origin, and furthermore with a high raw material content of renewable and/or recycled raw materials, and which is therefore environmentally friendly, is obtained.

Object of the Invention

An object of the present invention relates to a method for manufacturing artificial stone panels or slabs particularly suitable for their use indoors, comprising a

phase of grinding the different materials of varied particle size forming the filler, another phase containing the agglutinating agent with the catalyst and optionally other additives, mixing said phases until homogenizing the materials with the agglutinating agent, a phase of molding and compacting pulp obtained by vacuum vibro-compression, and a phase of hardening by polymerization of the agglutinating agent by means of heating, ending with a phase of cooling and polishing, characterized in that said agglutinating agent is made up of a polyester resin in which 12-30% of the polyol has been substituted with a polyol of a plant origin.

In a particular embodiment, the agglutinating agent used during the method constituting the first object of the invention is present between 5% and 18% of the agglomerate.

Preferably, the agglutinating agent used is a polyester resin with 12-30% of a polyol of a plant origin, the polyol preferably being of a plant origin from corn. In a particular embodiment said polyol is selected from one or more of the group consisting of ethylene glycol, 1,2-propanediol, 1,3-propanediol, 1,4-butanediol, 2,2-dimethyl-1,3-propanediol, diethylene glycol, dipropylene glycol, polyoxyethylene glycol and polyoxypropylene glycol. More preferably, the polyol used is 1,2-propanediol and/or the 1,3-propanediol.

In another particular embodiment, the method for manufacturing artificial stone panels or slabs is characterized in that the materials forming part of the composition can be, among others, marble, dolomite, opaque quartz, crystalline quartz, silica, glass, mirror, cristobalite, granite, feldspar, basalt, ferro-silicon, etc.

In another particular embodiment, the method of the object of the invention is characterized in that the materials forming part of the composition can be of variable particle size and partially or entirely come from recycling or residual waste.

In another particular embodiment, the method of the

object of the invention is characterized in that at least one of the materials forming part of the filler has been substituted by approximately 40%-90% with a similar waste or recycled material. Preferably at least one of the materials forming part of the filler is substituted by 50% with a similar waste or recycled material. More preferably, at least one of the materials forming part of the filler has been substituted by 90% with a similar waste or recycled material.

Thus, the object of invention relates to a panel or slab particularly suitable for its use indoors, manufactured according to the method described above, in which the agglutinating agent is made up of 5% to 18% of polyester resin in which 12-30% of polyol has been substituted with a polyol of a plant origin, which can furthermore contained recycled material.

Description of the Invention

The present invention consists of obtaining stone agglomerates in the form of a panel or slab using a polyester resin, during the manufacture of which the traditionally used polyol of a petrochemical origin has been partially substituted with a polyol obtained from the fermentation of plant matter, such as from corn, for example.

If a general process for manufacturing panels or slabs with a high percentage of polyester resin of a petrochemical origin, for example, 35%, by the present invention is considered, up to 12-30% of said resin can be substituted with polyol of a plant origin.

Any polyol of a plant origin would be suitable, the preferred one being from corn. The preferred polyols in the present invention are ethylene glycol, 1,2-propanediol, 1,3-propanediol, 1,4-butanediol, 2,2-dimethyl-1,3-propanediol, diethylene glycol, dipropylene glycol, polyoxyethylene glycol and polyoxypropylene glycol; and more preferably the polyol of a renewable origin would be 1,2-propanediol and/or 1,3-propanediol.

The main physicochemical parameters of the resin thus obtained are illustrated in the following table:

Viscosity 25°C (cps)	290-600
Density 25°C (g/cm ³)	1.00 - 1.18
Barcol Hardness (of the polymerized resin)	45 - 60

The method followed for manufacturing the quartz agglomerate is the traditional one for this type of material, according to which a mixture of aggregates of a known particle size is mixed with a resin acting as a binder to form the manufacturing mass. Furthermore, additives such as dyes and pigments, antimicrobial additives, coupling agents, ultraviolet filters and accelerants and catalysts for the polymerization can be added to said mass.

Preferred Embodiment of the Invention

In the case of the present invention, the resin used is an unsaturated polyester resin containing between 12% and 30% of a polyol obtained from plant matter. Preferred polyols would be 1,2-propanediol and 1,3-propanediol.

As conventional aggregates and, by way of example, marble, dolomite, opaque quartz, crystalline quartz, silica, glass, mirror, cristobalite, granite, feldspar, basalt, ferro-silicon, etc., can be mentioned.

Furthermore, it has been seen that it is possible to obtain an agglomerate with a high content of recycled material using this resin, if materials such as recycled glass (from glass recycled by the end consumer as well as from waste from industrial processes), ground mirror from post-industrial waste, manufacturing waste from the ceramic industry and/or aluminum silicate from vitrified ash, are introduced. By combining the raw materials traditionally used in the manufacture of a conventional stone agglomerate with them, a material with a high content of environmentally friendly recycled material is obtained, as has already been mentioned.

The preferred percentages for the mixture of the agglomerate of the present invention, as has been experimentally confirmed, are the following (% by weight):

- Recycled glass: 35-90%.
- Ground mirror from waste: 10-90%.
- Waste of the ceramic industry: 10-30%.
- Aluminum silicate from vitrified ash: 6-35%.

And the resin content of the agglomerate will be between 5% and 18%, more preferably between 7% and 13%.

Depending on the particular ingredient and on its percentage in the formulation, it will be convenient to substitute all or only part of the amount of the new material with waste or recycled material, according to the aforementioned percentages. In the event that only a percentage is substituted and one and the same ingredient, new and waste ingredient, is used, both of them, already in the desired form, in pellets, powder, etc., according to the characteristics of the end product to be obtained, are previously mixed, being subsequently mixed with the rest of the ingredients.

According to the present invention, the agglutinating material for obtaining the stone conglomerate is a mixture of synthetic resin, specifically a polyester resin containing polyol of a petrochemical origin together with a polyol of a plant origin, preferably from corn, which are previously mixed, and once mixed the usual additives are added for both the polymerization step and for the end product. Said additives preferably are an accelerant, a catalyst, a coupling agent, and one or more pigments or dyes in solid or liquid state. An antimicrobial agent, such as Triclosan, for example, can also be added as an additive.

The invention is illustrated below by means of non-limiting examples of the invention.

EXAMPLES

Four examples of preparations of agglomerates have been

formulated, using to that end different ingredients and percentages thereof.

Examples 1 and 2:

In Examples 1 and 2, one and the same material with conventionally used aggregates has been formulated, substituting the currently used resin (35% of polyols of a petrochemical origin) with a resin containing 22% of polyols of a plant origin and 11% of polyols of a petrochemical origin which are illustrated in the following table:

Ingredients *	Example 1	Example 2
Micronized quartz (%)	26	26
0.1-0.6 mm mirror (%)	15	15
0.6-1.2 mm mirror (%)	15	15
0.6-1.2 ground silica (%)	34.5	34.5
Resin of a petrochemical origin	9.5	
22% plant polyol resin		9.5

*A catalyst, an accelerant, silane and dye in solution have been added as additives.

The mechanical features of the material, according to the UNE EN-14617-2 standard, for determining the bending strength of stone agglomerates, are the following:

Property	Example 1	Example 2
Bending modulus (MPa)	13720-14396	12991-14241
Bending strength (MPa)	43.5-53.1	51.2-56.4
Maximum load withstood (N)	6206-7644	7404-8104

It is inferred from the results that the suitable adjustment of the plant polyol content can, surprisingly, even improve to a certain extent the results obtained with the traditionally used resin.

Examples 3 and 4:

In the Examples 3 and 4, different proportions of new and recycled materials have been used, in addition to the

resin with a different polyol. The new and recycled material have been previously mixed individually before being added to the mixture.

Ingredients *	Example 3	Example 4
Micronized quartz (%)	25	10
Micronized recycled glass material (%)	--	15
0.1-0.6 mm new glass (%)	15	5
0.1-0.6 mm recycled glass (%)	--	10
0.6-1.2 mm new glass (%)	16.5	5
0.6-1.2 mm recycled glass (%)	--	11.5
0.1-0.4 mm ground silica (%)	7.5	--
0.1-0.4 aluminum silicate from vitrified ash (%)	--	7.5
0.6-1.2 new mirror (%)	10	--
0.6-1.2 recycled mirror (%)	--	10
2.5-4.5 ground quartz (%)	17.5	17.5
Resin of a petrochemical origin	8.5	--
22% plant polyol resin	--	8.5

5

* A catalyst, an accelerant, silane and dye in solution have been added as additives.

The mechanical characteristics of the agglomerate slabs obtained are shown in the following table:

10

Test	Standard	Unit	Reference*	Result**
Determination of the bending strength	UNE EN 14617-2	MPa	29 - 70	35 - 62
Determination of the abrasion	UNE EN 14617-4	Mm	22 - 33	23 - 33

resistance				
Determination of the impact strength	UNE EN 14617-9	Cm	25 - 97	32 - 81
Determination of the compression strength	UNE EN 14617-15	MPa	112 - 248	110 - 200
Determination of the apparent mass and absorption coefficient	UNE EN 14617-1	Kg/cm ³	2.25 - 2.45	2.25 - 2.45
		%	0.04 - 0.14	0.04 - 0.14
Determination of the freeze-thaw resistance	UNE EN 14617-5	KMf25	0.90 - 1.20	0.97 - 1.18

*A mean obtained with different slabs of quartz agglomerate containing the polyester resin of a petrochemical origin as a agglomerating agent has been used as a reference.

5 ** The results of this column are the mean of the measurements taken with slabs of the formulations according to Examples 2 and 4.

CLAIMS

1.- A method for manufacturing artificial stone panels or slabs, comprising a phase of grinding the different materials with varied particle size forming the filler, another phase containing the agglutinating agent with the catalyst and optionally other additives, mixing said phases until homogenizing the materials with the agglutinating agent, a phase of molding and compacting pulp obtained by vacuum vibro-compression, and a phase of hardening by polymerization of the agglutinating agent by means of heating, characterized in that the agglutinating agent is made up of a polyester resin in which 12-30% of the polyol has been substituted with a polyol of a plant origin.

2.- The method for manufacturing artificial stone panels or slabs according to claim 1, characterized in that the agglutinating agent is present between 5% and 18% of the agglomerate.

3.- The method for manufacturing artificial stone panels or slabs according to claims 1-2, characterized in that the agglutinating agent is a polyester resin with 12-30% of a polyol of a plant origin.

4.- The method for manufacturing artificial stone panels or slabs according to claims 1-3, characterized in that the polyol of a plant origin comes from corn.

5.- The method for manufacturing artificial stone panels or slabs according to claims 1-4, characterized in that the polyol of a plant origin is preferably selected from one or more of the group consisting of ethylene glycol, propylene glycol, 1,2-propanediol, 1,3-propanediol, 1,4-butanediol, 2,2-dimethyl-1,3-propanediol, diethylene glycol, dipropylene glycol, polyoxyethylene glycol and polyoxypropylene glycol.

6.- The method for manufacturing artificial stone panels or slabs according to claims 1-5, characterized in that the polyol is preferably 1,2-propanediol and/or 1,3-propanediol.

7.- The method for manufacturing artificial stone panels or slabs according to claims 1-5, characterized in that the materials forming part of the composition can be, among others, marble, dolomite, opaque quartz, crystalline quartz, silica, glass, mirror, cristobalite, granite, feldspar, basalt, ferro-silicon, etc.

8.- The method for manufacturing artificial stone panels or slabs according to claims 1-7, characterized in that the materials forming part of the composition can be of variable particle size and can partially or entirely come from recycling or residual waste.

9.- The method for manufacturing artificial stone panels or slabs according to claims 1-8, characterized in that at least one of the materials forming part of the filler has been substituted with similar waste or recycled material by 40%-100%.

10.- The method for manufacturing artificial stone panels or slabs according to claims 1-9, characterized in that at least one of the materials forming part of the filler has been substituted with similar waste or recycled material by 45-55%.

11.- The method for manufacturing artificial stone panels or slabs according to claims 1-9, characterized in that at least one of the materials forming part of the filler has been substituted with similar waste or recycled material by 85-95%.

12.- The method for manufacturing artificial stone panels or slabs according to any of claims 9 to 11, characterized in that one or more of the materials forming part of the filler are from the following group: recycled glass, ground mirror from waste, waste material from the ceramic industry and aluminum silicate from vitrified ash.

13.- The method for manufacturing artificial stone panels or slabs according to any of claims 9 to 12, characterized in that recycled glass is used.

14.- The method for manufacturing artificial stone panels or slabs according to any of claims 9 to 12, characterized in that ground mirror from waste is used.

5 15.- The method for manufacturing artificial stone panels or slabs according to any of claims 9 to 12, characterized in that waste material from the ceramic industry is used.

10 16.- The method for manufacturing artificial stone panels or slabs according to any of claims 9 to 12, characterized in that aluminum silicate from vitrified ash is used.

15 17.- A panel or slab particularly suitable for its use indoors, manufactured according to the method of claims 1 to 16, characterized in that the agglutinating agent is made up of 5% to 18% polyester resin in which 12-30% of a polyol of a petrochemical origin has been substituted with a polyol of a plant origin.