CLAIMS

1. A soft capsule film composition, comprising: (A) a native gellan gum; (B) one or more hydrophilic polysaccharides excluding deacylated gellan gum; (C) a starch or modified starch; (D) a plasticizer; and (E) water, wherein a gelling agent other than (A) the native gellan gum and (B) the one or more hydrophilic polysaccharides is not an essential component.

2. The soft capsule film composition according to claim 1, wherein (C) the starch or the modified starch is one or more starches selected from a natural starch, an oxidized starch, a hydroxypropylated starch, an acetylated starch, a starch subjected to acetylation, hydroxypropylation, octenylsuccination, phosphorylation, crosslinking, acid treatment, and moist heat treatment in the presence of a salt, and a starch dispersion obtained by ultrasonically treating a starch paste solution.

3. The soft capsule film composition according to claim 1 or 2, wherein (C) the starch or the modified starch is one or more starches selected from sago starch, sweet potato starch, mung bean starch, wheat starch, corn starch, rice starch, waxy corn starch, waxy potato starch, waxy wheat starch, waxy rice starch, and modified starches obtained therefrom.

4. The soft capsule film composition according to any one of claims 1 to 3, wherein (C) the starch or the modified starch is one or more starches selected from waxy potato

starch, an oxidized starch, a starch subjected to moist heat treatment in the presence of a salt, and a starch dispersion formed by subjecting the starch glue solution to ultrasonic treatment.

5. The soft capsule film composition according to any one of claims 1 to 4, wherein a content mass ratio of (A) the native gellan gum to (B) the one or more hydrophilic polysaccharides excluding deacylated gellan gum [(A):(B)] is 1:1 to 1:0.01.

6. The soft capsule film composition according to claim 2 or 4, wherein (C) the starch or the modified starch is a starch dispersion formed by subjecting the starch glue solution to ultrasonic treatment, the starch dispersion being derived from waxy corn starch.

7. The soft capsule film composition according to claim 6, wherein the waxy corn starch used for the starch dispersion formed by subjecting a starch glue solution to ultrasonic treatment is an unmodified natural starch.

8. The soft capsule film composition according to any one of claims 1 to 5, wherein (C) the starch or the modified starch is waxy corn starch subjected to moist heat treatment in the presence of a salt.

9. A soft capsule film, wherein the soft capsule film is obtained using the soft capsule film composition according to any one of claims 1 to 8.

10. A soft capsule, wherein the soft capsule is obtained using the soft capsule film composition according to any one of claims 1 to 8.